

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 February 2002 (07.02.2002)

PCT

(10) International Publication Number
WO 02/10499 A2

(51) International Patent Classification⁷: **D06M**

(21) International Application Number: PCT/EP01/07562

(22) International Filing Date: 3 July 2001 (03.07.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
720/MUM/2000 1 August 2000 (01.08.2000) IN
0022704.1 15 September 2000 (15.09.2000) GB

(71) Applicant (for AE, AG, AU, BB, BZ, CA, CY, GB, GD, GH, GM, IE, IL, KE, LC, LK, LS, MN, MW, NZ, SD, SG, SL, SZ, TT, TZ, UG, ZA, ZW only): **UNILEVER PLC** [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB).

(71) Applicant (for AL, AM, AT, AZ, BA, BE, BF, BG, BJ, BR, BY, CF, CG, CH, CI, CM, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, FR, GA, GE, GN, GR, GW, HR, HU, ID, IS, IT, JP, KG, KP, KR, KZ, LR, LT, LU, LV, MA, MC, MD, MG, MK, ML, MR, MX, MZ, NE, NL, NO, PL, PT, RO, RU, SE, SI, SK, SN, TD, TG, TJ, TM, TR, UA, UZ, VN, YU only): **UNILEVER NV** [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL).

(71) Applicant (for IN only): **HINDUSTAN LEVER LIMITED** [IN/IN]; Hindustan Lever House, 165/166 Backbay Reclamation, Maharashtra, Mumbai 400 020 (IN).

(72) Inventors: **BABU, Gangundi, Prakash**; Hindustan Lever Ltd, Research Centre, Chakala, Andheri (East), Mumbai 400 099 (IN). **DHANUKA, Vinodkumar, Ramniran**;

Hindustan Lever Ltd, Research Centre, Chakala, Andheri (East), Mumbai 400 099 (IN). **DIVECHA, Kaushik, Narotam**; Hindustan Lever Ltd, Research Centre, Chakala, Andheri (East), Mumbai 400 099 (IN). **KESWANI, Manish, Hardas**; K.L. Kulkarni, Plot Number 4, Suprabha Building, Behind Hanuman Temple, Ganesh Colony, Jalgaon Maharashtra (IN). **RAJAN, Raghavachari**; Hindustan Lever Ltd, Research Centre, 64 Main Road, Whitefield P.O., Bangalore 560 066 (IN).

(74) Agents: **FRANELLA, Mary, Evelyn** et al.; Unilever PLC, Patent Department, Colworth House, Sharnbrook, Bedford, Bedfordshire MK44 1LQ (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: TEXTILE TREATMENT PROCESS AND PRODUCT

(57) Abstract: A process for treating a yarn and/or a fabric to form fine inorganic particulate material in the intra-yarn pores and/or on the surface of the fibres constituting the yarn or fabric, which would substantially maintain fabric reflectance after repeated wash/wear cycles without affecting the desired characteristics of air permeability. The inorganic particles are preferably formed by reacting in an aqueous medium a first reagent selected from mineral and organic acids and a second reagent selected from alkali or alkaline earth metal salts with inorganic anions. The invention also relates to a treatment product composition directed to provide instant inorganic deposits in the yarn or fibre surface.



WO 02/10499 A2

- 1 -

TEXTILE TREATMENT PROCESS AND PRODUCT**TECHNICAL FIELD**

5 The present invention relates to a process for treating a yarn and/or a fabric to form a fine inorganic particulate material in the intra-yarn pores and/or on the surfaces of the fibres constituting the yarn or fabric, which would substantially maintain fabric reflectance after repeated
10 wash/wear cycles without affecting the desired characteristics of air permeability. The invention also relates to a treatment product composition directed to provide instant inorganic deposits in the yarn or fibre surface.

15

BACKGROUND AND PRIOR ART

It is well known that yarns used for producing fabrics and the fabrics so obtained have pores. In particular, the
20 yarns per se, have inter-fibre pores while the fabric obtained of such yarn apart from such inter-fibre/intra-yarn pores also have inter-yarn pores. It is found that during use of the fabric, particulate soils and/or oily soils get trapped in the minute intra-yarn pores which get firmly
25 bonded to the yarn or fabric.

In a typical hand washing cleaning operation using a detergent solution, the yarn or fabric has the detergent applied to it or it is soaked in the solution which is then
30 followed by rubbing with a brush to dislodge and remove soil and particles from the soiled fabric. By the action of

- 2 -

rubbing with a hard surface in presence of a conventional detergent product the cleaning is generally satisfactory. Machine wash is another method used for cleaning fabric where the mechanical agitation in presence of a detergent
5 composition is used to dislodge the soil particles to achieve necessary cleaning.

An unsoiled new fabric generally has a reflectance value of about 88 when measured at a wavelength of 460 nm with UV
10 filter. It is found that following soiling and wash regimes, fabric reflectance may drop to below 65 leading to greying of the fabric. It is established that smaller dirt/soil particles pose a serious challenge in terms of their removal since they accumulate in intra-yarn pores and
15 on the fibre surface. Such small soil particles deposited in or on the fabric are the main cause for decline in fabric reflectance.

US 4035148 (Procter & Gamble), US 4566980 (Creative
20 Products) and US 4873000 (Sterling Drug) disclose carpet treatment products which involve particulate material deposits in the carpet fibres. The particles are subsequently vacuumed off together with any dirt or soil to which they are associated. All the available art uses
25 "external deposition" techniques i.e. particulates were taken in bulk solution and deposited onto the fabric and then removed.

- 3 -

WO 9842909 (Koala Konnections) discloses a fabric with UV blocking particles bound to the fabric by binding agents. It discloses the process of deposition followed by heat treatment.

5

In the pending application GB 9929838.2 (Unilever) fine particles of clay are deposited on the fabric which block the inter-fibre regions of the fabric thus preventing the entrapment of environmental soil into the fabric. In order to maintain the reflectance of the fabric it needs to be retreated for deposition of fresh sacrificial layer after each wash and wear cycle. Although this provides satisfactory cleaning, the deposit of the clay on the fabric blocks the inter-fibre and inter-yarn regions which lead to substantial reduction in air flow passage through the fabric adding to the discomfort of the wearer of the fabric.

10

The present inventors have surprisingly found that a fabric or yarn which comprises fine particulate inorganic particles either on the surface or in the pores of the fibres maintains the fabric reflectance after repeated wash/wear cycles without affecting the desired characteristics of air permeability.

20

25 DEFINITION OF THE INVENTION

30

According to a first aspect, the present invention provides a process for the production of a treated textile yarn or fabric which comprises treating the yarn or fabric with at least two reagents capable of reacting together to form a fine inorganic particulate material, whereby the fine

- 4 -

inorganic particulate material is precipitated in the intra-yarn pores and/or on the surfaces of the fibres constituting the yarn or fabric.

- 5 According to a second aspect, the invention provides a treatment product comprising at least two separate ingredients capable of reacting together in an aqueous medium to form a fine inorganic particulate material, preferably having a particle size not exceeding 5 μm .

10

DETAILED DESCRIPTION OF THE INVENTION

The Process For the Production of a Treated Textile Yarn or Fabric

15

- In this first aspect of the invention, the fine inorganic particulate material in the intra-yarn pores and/or on the fibre surface can be provided by reacting in an aqueous medium a first reagent selected from mineral and organic acids and a second reagent selected from alkali or alkaline earth metal salts with inorganic anions.
- 20

- The mineral acid may be selected from hydrochloric acid, sulphuric acid, nitric acid or phosphoric acid. If hydrochloric acid is used it is preferably at a concentration of from 0.1 to 0.8 gmol/l. If phosphoric acid is used it is preferably at a concentration of from 0.02 to 0.2 gmol/l.
- 25

- 5 -

The inorganic anion may be selected from silicate, aluminate, carbonate, hydroxide, phosphate, chloride, sulphate or nitrate and preferably aluminate or silicate.

5 In a first preferred embodiment, the process of producing the treated fabric/yarn comprises:

- (a) treating the yarn or fabric with one of the first and second reagents in aqueous solution,
- 10 (b) subsequently, treating the yarn or fabric with the other of the first and second reagents in aqueous solution

15 to facilitate deposition of the inorganic particulate in the intra-yarn pores and/or fibre surface.

Preferably in the above process, in step (a) the yarn or fabric is treated with the reagent solution having the lower diffusion coefficient. This is to prevent the first reagent
20 from coming out of the intra yarn pores when the second reagent is added to the yarn or fabric. The second reagent with higher diffusion coefficient penetrates into the intra yarn pores and reacts with the first reagent which is already present there.

25

In a second preferred embodiment, the process of producing the treated fabric or yarn comprises treating the fabric or yarn with an aqueous solution of alkali metal silicate and urea whereby silica is precipitated in the intra-yarn pores
30 and/or on the surfaces of the fibres constituting the yarn or fabric.

- 6 -

In a third preferred embodiment such a process comprises treating the yarn or fabric with a dilute alkali metal silicate solution, through which CO₂ is bubbled, whereby silica is precipitated in the intra-yarn pores and/or on the surfaces of the fibres constituting the yarn or fabric.

Alternatively, the process of producing the treated fabric/yarn comprises treating the yarn or fabric with a dilute alkali metal silicate solution followed by drying the yarn or fabric in air, whereby silica is precipitated in the intra-yarn pores and/or on the surfaces of the fibres constituting the yarn or fabric.

Preferably the drying is carried out for a period of at least two hours such that complete conversion of the alkali metal silicate into silica is achieved. The deposition of silica is dependent upon the concentration of the alkali metal silicate solution as well as the drying time and the deposition can be varied depending upon the desired end deposit on the yarn/fabrics.

It is found that yarn or fabric treated by the above process has deposits of fine inorganic particulate material providing for reduced soiling of fabrics, including oily soils, and maintaining higher reflectance in repeated wear/wash cycles.

It is believed that the yarn or fabric treated by the above process has selective deposition of the particulate material only in the small intra-yarn pores and not in the inter-yarn regions which provides firstly, the maintenance of fabric

- 7 -

reflectance even after repeated wash/wearing cycles is achieved and secondly, the desired air permeability through the fabric pores is maintained to provide comfort in use or wearing of the fabric.

5

The Treatment Product

The second aspect of the present invention is a treatment product which comprises at least two separate ingredients capable of reacting together in an aqueous medium to form a fine inorganic particulate material, preferably having a particle size not exceeding 5 μm . It is preferred that the product comprises (a) at least one first ingredient selected from mineral and organic acids and (b) at least one second ingredient selected from alkali or alkaline earth metal salts with inorganic anions wherein (a) and (b) are capable of reaction in an aqueous medium to form a fine inorganic particulate material.

20 The product is preferably accompanied with an instruction manual detailing directions of use of the product for carrying out in-situ deposition of the inorganic particulate material in the intra-yarn pores and/or on the surfaces of the fibres constituting the yarn or fabric.

25

The constituent (a) of the product is preferably a mineral acid, preferably selected from, hydrochloric acid, sulphuric acid, nitric acid and phosphoric acid. Alternatively it is also preferred that (a) is an organic acid, preferably selected from citric acid, acetic acid and lauric acid or a combination thereof.

30

- 8 -

The constituent (b) of the product is selected to have an inorganic anion selected from alkali metal silicate, aluminate, carbonate, hydroxide, phosphate, chloride, sulphate or nitrate and preferably aluminate or alkali metal silicate.

In a first preferred embodiment of the invention, ingredient (a) comprises hydrochloric acid in a concentration of from 0.1 to 0.8 gmol/l and (b) comprises sodium aluminate in a concentration of from 0.1 gmol/l to 0.8 gmol/l.

In a second preferred embodiment of the invention, ingredient (a) comprises phosphoric acid in amount of 0.02 gmol/l to 0.2 gmol/l and (b) comprises sodium aluminate in a concentration of 0.1 gmol/l to 1.0 gmol/l.

In a third preferred embodiment of the invention, ingredient (a) comprises a mineral acid selected from hydrochloric acid in a concentration of from 0.1 to 0.8 gmol/l and phosphoric acid in a concentration of from 0.02 to 0.2 gmol/l and (b) comprises alkaline earth metal salt selected from sodium aluminate and sodium silicate in a concentration of from 0.04 gmol/l to 0.4 gmol/l.

The invention is further illustrated by the following non-limiting Examples.

EXAMPLESExamples 1 to 4 and Comparative Example A

5 In this example, in-situ deposition of aluminium trihydrate was carried out by wicking a yarn/fabric in hydrochloric acid and a solution of sodium aluminate.

10 The wicking was carried out by hanging the swatch vertically by means of threads in such a way that bottom edge of swatch just dips inside the first solution kept below. After wicking was complete the swatch was kept in a horizontal position and the second solution was added to the swatch uniformly and dried for 24 hours. The concentration of the
15 solution was determined using the stoichiometry and based on the percentage weight addition of precipitate on the fabric.

In Example 1 the fabric was first wicked under hydrochloric acid followed by sodium aluminate solution to produce
20 aluminium trihydrate particles. In Example 2 the fabric was first wicked under sodium aluminate solution followed by hydrochloric acid to produce aluminium trihydrate particles. In Example 3 the fabric was only wicked in hydrochloric acid which could be further treated with sodium aluminate
25 solution to provide a treated fabric according to the present invention. In Example 4 the fabric was only wicked in sodium aluminate solution which could be further treated with hydrochloric acid to provide a treated fabric according to the present invention. In Comparative Example A, the
30 fabric was untreated.

- 10 -

All the fabrics were then subjected to a soiling and wash protocol described below.

Soiling and Wash Protocol

5

The fabrics were soiled artificially with particulate soil and sebum to provide a much reduced reflectance value.

10

The fabrics after soiling were soaked in 2.5 g/l commercial detergent solution in water. The composition of the commercial detergent used is described in Table 1. Three swatches were soaked in detergent solution. After soaking, the swatches were mechanically agitated in a water shaker for 30 minutes. After the mechanical agitation, the swatches were rinsed three times using water. Then the swatches were taken out and dried. This protocol was followed for 6 cycles.

15

- 11 -

Table 1

Composition	Concentration (wt%)
Na linear alkylbenzene sulphonate	25
Nonionic surfactant C ₁₂ EO ₇	0.5
Nonionic surfactant C ₁₂ EO ₃	1.5
Soda ash	23
Sodium tripolyphosphate	32
Silica	5.9
Water	To 100

Reflectance Measurement

5

Colour Eye 7000 A (Gretag Macbeth) instrument was used for reflectance measurements. The reflectance of fabric was monitored at the wavelength of 460 nm with UV filter. The reflectance value of the original fabric was about 88. The reflectance value was measured before the first soiling after the treatment. Each soiling and wash forms one cycle.

10

To assess the reflectance maintenance the reflectance values after cycle 1 and cycle 6 were noted and are shown in Table 2.

15

- 12 -

Table 2

Example	Reflectance Value	
	After cycle 1	After cycle 6
1	86.5	84.4
2	87.7	86.9
3	84.9	81.6
4	86.6	83.0
A	85.6	81.2

5 Examples 5 to 7 and Comparative Example B

In Example 5 the fabric was first wicked under phosphoric acid followed by sodium aluminate solution to produce aluminium trihydrate particles. In Example 6 the fabric was
10 first wicked under sodium aluminate solution followed by phosphoric acid to produce aluminium trihydrate particles. In Example 7 the fabric was first wicked in sodium silicate solution followed by sodium aluminate to produce sodium aluminium silicate particles. In Comparative Example B, the
15 fabric was untreated.

The reflectance values noted after cycle 1 and cycle 6 and compared with reflectance values of untreated fabric. The results obtained are shown in Table 3.

Table 3

Example	Reflectance Value	
	After cycle 1	After cycle 6
5	88.4	86.7
6	88.2	88.4
7	88.1	85.4
B	87.8	82.0

Example 8 and Comparative Example C

5

The air permeability of the treated fabric of Example 1 and the untreated fabric of Comparative Example A were measured according to the Anderson protocol. This utilises a known area of material, of known thickness, across which a constant pressure difference is imposed. The air permeability of the fabric is calculated by measuring the resultant velocity of air through the fabric and applying Darcy's law. In one particular form Darcy's law states:

10

$$\frac{V}{A} = \frac{K \Delta P}{\mu x}$$

15

in which, V is the volumetric flow rate (m³/s), A is the area of the fabric (m²), K is the permeability (m²), ΔP is the pressure difference across the fabric (N/m²), μ is the viscosity of air (kg/ms), and x is the thickness of the fabric (m).

20

- 14 -

Thus the permability, K, is measured by the above protocol. The physical constants for these experiments were as follows: $A = 10^{-5} \text{ m}^2$; $\Delta P = 200 \text{ N/m}^2$; $\mu = 1.85 \times 10^{-5} \text{ kg/ms}$; $x = 2 \times 10^{-4} \text{ m}$.

5

The fabric permeability of the treated fabric of Example 1 and the untreated fabric of Comparative Example A after each exposure-wash cycle, was measured after each wash. The air permeability data are given in Table 4.

10

Table 4

No. of wash cycles	Permeability, K (m^2)	
	8	C
None (fresh fabric)	11.4	11.4
1	11.0	11.2
3	10.6	10.2
6	9.2	8.5

As would be evident from the above result after six wash/soil cycles the air permeability of treated fabric is reduced only by 20 % while those of untreated fabric air-permeability reduced by more than 25 %. This is basically due to the in-situ deposition on the treated fabric of the invention substantially in the intra yarn pores and not in the inter yarn regions. The permeability of untreated fabric was lower than the treated ones due to particulate soil accumulation.

15

20

- 15 -

Examples 9 to 11 and Comparative Example D

The following examples further illustrate other possible methods of deposition of inorganic particulate such as silica.

In Example 9 a fabric of weight 12 g was treated with 30 g of a solution of neutral sodium silicate and 20 g of urea in 300 ml of water and was heated to 95°C and maintained at that temperature for 4 hours. In this way silica was deposited by the in-situ precipitation method. The fabric was subsequently rinsed in water and dried.

In Example 10 a fabric was soaked in a 15% neutral sodium silicate solution and CO₂ gas was bubbled into it for 4 hours. In this way silica was deposited by bubbling CO₂ gas through sodium silicate solution. The fabric was rinsed in water and dried.

In Example 11 initially the fabric was soaked in 15% neutral sodium silicate solution and then dried in the air for 24 hours. The reaction between CO₂ (from air) and sodium silicate (on the fabric) resulted in silica deposition. The fabric was rinsed in water and dried

In Comparative Example D the fabric was untreated.

- 16 -

The fabrics were subjected to a soiling and wash protocol and reflectance measurements are as described above and the reflectance measurements were done after one and ten cycles and the results are presented in Table 5.

5

Table 5

Example	Reflectance Value	
	After cycle 1	After cycle 10
9	85	77
10	84	71
11	82.8	72.2
D	82	68

10 It is thus possible by way of the present invention to
provide treated yarn/fabric with selective in-situ
deposition of inorganic material which would both provide
for maintenance of fabric reflectance even after repeated
soiling and wash cycles and will not adversely affect the
15 desired air permeability for the fabric.

- 17 -

CLAIMS

- 1 A process for the production of a treated textile yarn
or fabric which comprises treating a textile yarn or
5 fabric with at least two reagents capable of reacting
together to form a fine inorganic particulate material,
whereby the fine inorganic particulate material is
precipitated in the intra-yarn pores and/or on the
surfaces of the fibres constituting the yarn or fabric.
10
- 2 A process as claimed in claim 1, characterised in that
the fine inorganic particulate material is formed by
reacting in an aqueous medium a first reagent selected
from mineral and organic acids and a second reagent
15 selected from alkali or alkaline earth metal salts with
inorganic anions.
- 3 A process as claimed in claim 2, characterised in that
the first reagent is a mineral acid selected from
20 hydrochloric acid, sulphuric acid, nitric acid or
phosphoric acid.
- 4 A process as claimed in claim 3, characterised in that
the first reagent is hydrochloric acid having a
25 concentration of from 0.1 to 0.8 g/mol/l or phosphoric
acid having a concentration of from 0.02 to 0.2 g/mol/l.

- 18 -

- 5 A process as claimed in any preceding claim,
characterised in that the second reagent is a salt
having an inorganic anion selected from silicate,
aluminate, carbonate, hydroxide, phosphate, chloride,
5 sulphate or nitrate.
- 6 A process as claimed in claim 5, characterised in that
the second reagent is aluminate or silicate.
- 10 7 A process as claimed in any one of claims 2 to 6,
characterised in that it comprises:
- (a) treating the yarn or fabric with one of the first
 and second reagents in aqueous solution,
- 15 (b) subsequently, treating the yarn or fabric with the
 other of the first and second reagents in aqueous
 solution.
- 8 A process as claimed in claim 7, characterised in that
20 in step (a) the yarn or fabric is treated with the
reagent solution having the lower diffusion
coefficient.
- 9 A process as claimed in claim 1, characterised in that
25 it comprises treating the yarn or fabric with an
aqueous solution of alkali metal silicate and urea
whereby silica is precipitated in the intra-yarn pores
and/or on the surfaces of the fibres constituting the
yarn or fabric.

30

- 19 -

- 10 A process as claimed in claim 1, characterised in that
it comprises treating the yarn or fabric with a dilute
alkali metal silicate solution, through which CO₂ is
bubbled, whereby silica is precipitated in the intra-
5 yarn pores and/or on the surfaces of the fibres
constituting the yarn or fabric.
- 11 A process as claimed in claim 1, characterised in that
it comprises treating the yarn or fabric with a dilute
10 alkali metal silicate solution followed by drying the
yarn or fabric in air, whereby silica is precipitated
in the intra-yarn pores and/or on the surfaces of the
fibres constituting the yarn or fabric.
- 15 12 A treatment product characterised in that it comprises
at least two separate ingredients capable of reacting
together in an aqueous medium to form a fine inorganic
particulate material, preferably having a particle size
not exceeding 5 µm.
- 20 13 A treatment product as claimed in claim 12,
characterised in that it comprises
- 25 (a) at least one first ingredient selected from
mineral and organic acids, and
- (b) at least one second ingredient selected from
alkali and alkaline earth metal salts with
inorganic anions

- 20 -

wherein constituents (a) and (b) are capable of reacting in an aqueous medium to form a fine inorganic particulate material.

5 14 A treatment product as claimed in claim 12 or claim 13, characterised in that it further comprises an instruction manual detailing directions of use of the product for carrying out in-situ deposition of the fine inorganic particulate material in the intra-yarn pores
10 and/or on the surfaces of the fibres constituting the yarn or fabric.

15 A treatment product as claimed in any one of claims 12 to 14, characterised in that ingredient (a) is a
15 mineral acid selected from hydrochloric acid, sulphuric acid, nitric acid and phosphoric acid and/or an organic acid selected from citric acid, acetic acid and lauric acid.

20 16 A treatment product as claimed in any one of claims 12 to 15, characterised in that ingredient (b) is a salt having an inorganic anion selected from silicate, aluminate, carbonate, hydroxide, phosphate, chloride, sulphate and nitrate.

25
17 A treatment product as claimed in claim 16, characterised in that ingredient (b) is an aluminate or a silicate.

- 21 -

- 18 A treatment product as claimed in any one of claims 12
to 17, characterised in that ingredient (a) comprises
hydrochloric acid, in a concentration of from 0.1 to
0.8 gmol/l and wherein ingredient (b) comprises sodium
5 aluminate in a concentration of from 0.1 gmol/l to
0.8 gmol/l.
- 19 A treatment product as claimed in any one of claims 12
to 17, characterised in that ingredient (a) comprises
10 phosphoric acid in a concentration of from 0.02 gmol/l
to 0.2 gmol/l and ingredient (b) comprises sodium
aluminate in a concentration of from 0.1 gmol/l to
1.0 gmol/l.
- 15 20 A treatment product as claimed in any one of claims 12
to 17, characterised in that ingredient (a) comprises a
mineral acid selected from hydrochloric acid in a
concentration of from 0.1 to 0.8 gmol/l and phosphoric
acid in a concentration of from 0.02 to 0.2 gmol/l and
20 (b) a salt selected from sodium aluminate and sodium
silicate in concentration of 0.04 gmol/l to 0.4 gmol/l.