




- (51) **International Patent Classification:**
B44C 1/17 (2006.01) *B42D 15/00* (2006.01)
- (21) **International Application Number:**
PCT/US2012/051395
- (22) **International Filing Date:**
17 August 2012 (17.08.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (71) **Applicant (for all designated States except US):** **VISUAL PHYSICS, LLC** [US/US]; 1245 Old Alpharetta Road, Alpharetta, GA 30005 (US).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** **GOSNELL, Jonathan, D.** [US/US]; 7845 Brookwood Way, Cumming, GA 30041 (US). **JORDAN, Gregory, R.** [US/US]; 1520 Dunn Road, Cumming, GA 30040 (US). **KENNEDY, Caroline, B.** [US/US]; 672 Fanning Drive, Winter Springs, FL 32708 (US).
- (74) **Agents:** **BONZAGNI, Mary R.** et al; Holland & Bonzagni, P.C., 171 Dwight Road, Suite 302, Longmeadow, MA 01106-1700 (US).

- (81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report (Art. 21(3))

(54) **Title:** A PROCESS FOR TRANSFERRING MICROSTRUCTURES TO A FINAL SUBSTRATE



(57) **Abstract:** A process and a transfer film for transferring microstructures to a flexible or rigid final substrate that offers advantages in both speed and precision is provided. The inventive process involves subjecting a transfer film in a continuous roll-to-roll process to the following operations: either forming microstructures on, or transferring microstructures to a surface of the transfer film; and then transferring the microstructures from the transfer film onto a surface of the final substrate. The microstructures are single or multi-layer structures that are made up of: voids in a substantially planar surface, the voids optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations thereof.

W^o 2014/028031 A1

A PROCESS FOR TRANSFERRING
MICROSTRUCTURES TO A FINAL SUBSTRATE

TECHNICAL FIELD

5 [0001] The present invention generally relates to a continuous roll-to-roll process for producing and transferring security devices in the form of microstructures from a transfer film to a final substrate.

BACKGROUND AND SUMMARY OF THE INVENTION

10 [0002] Security threads as well as security patches may be mounted on a surface of a security document {e.g., currency or banknote paper) or label either during or post manufacture. Mounting of these devices may be achieved by any number of known techniques including: applying a pressure-sensitive adhesive to the backside of the device and pressing the device to the surface of the document or label; and applying a heat activated adhesive to the backside of
15 the device and applying the device using thermal transfer techniques, to the surface of the document or label.

[0003] The production of these security devices and the application of these devices to security documents or labels take place in separate operations. Combining these operations in a continuous roll-to-roll process for producing and transferring these security devices to a final
20 substrate would realize advantages in both speed and precision.

[0004] The present invention fulfills this need by providing a continuous roll-to-roll process for producing and transferring security devices in the form of microstructured elements or microstructures from a transfer film to a final substrate.

[0005] More specifically, the present invention provides a transfer film for transferring
25 microstructures to a final substrate. The microstructures transferred by the transfer film to a final substrate are single or multi-layer structures that comprise: voids in a substantially planar surface, the voids optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations thereof.

[0006] In a first exemplary embodiment, the transfer film comprises a carrier film and
30 one or more thermal release adhesive layers on a surface of the carrier film, wherein the thermal release adhesive layer(s) is made up of a plurality of expandable microspheres and one or more pressure sensitive adhesives.

[0007] The term "thermal release adhesive", as used herein, means an adhesive that decreases its adhesion to a surface when heated to temperatures higher than about 60 °C, while the term "expandable microspheres", as used herein, means polymer microspheres that start expansion and/or foaming when heated to temperatures higher than about 60 °C.

5 **[0008]** Thermal release adhesives (e.g., thermal release tapes) are known in the art and have been used in semiconductor wafer processing and other electronic component manufacturing processes. Suppliers of thermal release products used for electronic applications include Nitto Denko Corporation, 1-2, Shimohozumi 1-chome Ibaraki-shi, Osaka Japan (Nitto Denko), which sells REVALPHA[®] thermal release adhesive tapes and sheets, and
10 Haeun Chemtec Co., Ltd., Shingil-dong, Danwon-gu, Ansan, Kyungki-do, 425-839, Korea, which sells REXPAN[™] heat release film. However, the thickness and cost of these products are prohibitive for anything other than small scale samples, and are not suitable for volume production as described herein.

[0009] The term "pressure sensitive adhesive", as used herein, means an adhesive that
15 needs only minimal pressure to adhere or stick to a surface.

[0010] In an exemplary embodiment, the one or more thermal release adhesive layers are prepared from a formulation comprising from about 25 to about 99 % by wt. (preferably, from about 75 to about 97 % by wt., more preferably, from about 90 to about 96 % by wt.) of an energy {e.g., ultraviolet (UV) radiation) curable pressure sensitive adhesive (PSA) formulation,
20 and from about 1 to about 75 % by wt. (preferably, from about 3 to about 25 % by wt., more preferably, from about 4 to about 10 % by wt.) of expandable microspheres.

[0011] In this exemplary embodiment, the energy curable PSA formulation generally comprises:

25 from about 5 to about 95 % by wt. (preferably, from about 10 to about 70 % by wt., more preferably, from about 30 to about 60 % by wt.) of one or more elastomeric oligomers;

from about 1 to about 75 % by wt. (preferably, from about 5 to about 60 % by wt., more preferably, from about 10 to about 40 % by wt.) of one or more tackifying resins;

30 from about 0.5 to about 75 % by wt. (preferably, from about 5 to about 60 % by wt., more preferably, from about 20 to about 50 % by wt.) of one or more reactive monomeric diluents; and

from about 0.1 to about 15 % by wt. (preferably, from about 1 to about 8 % by wt., more preferably, from about 3 to about 6 % by wt.) of one or more photoinitiators.

[0012] In a second exemplary embodiment, the transfer film comprises a carrier film and one or more cured binder layers. In this embodiment, the microstructures have one or more cured conformal release coating layers on a surface thereof, and are bonded to the transfer film by way of the one or more cured binder layers. Heat is not required to initiate release during transfer of the microstructures.

[0013] The present invention further provides a method of using the transfer films described above, which method comprises using the transfer films (a) to transfer the above-described microstructures in a continuous roll-to-roll process to a final substrate, or (b) as manufacturing substrates during production of the microstructures and then to transfer the microstructures in a continuous roll-to-roll process to a final substrate.

[0014] Also provided is a process for transferring microstructures to a final substrate. In a first exemplary embodiment, the process comprises subjecting the transfer film first described above in a continuous roll-to-roll process to the following operations: either forming microstructures on, or transferring microstructures to a surface of the thermal release adhesive layer(s) of the transfer film, wherein the microstructures are single or multi-layer structures that comprise: voids in a substantially planar surface, wherein the voids are optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations thereof; and then transferring the microstructures from the transfer film onto a surface of the final substrate.

[0015] In a first preferred embodiment, the process comprises: forming the microstructures on a surface of a disposable manufacturing substrate; bringing the formed microstructures into contact with a surface of the transfer film while applying pressure thereto, thereby activating the pressure sensitive adhesive in the thermal release adhesive layer(s) of the transfer film, adhering the microstructures to its surface; stripping away the disposable manufacturing substrate; applying one or more heat and/or pressure activated adhesives to the microstructures on the transfer film; bringing the adhesive coated microstructures on the transfer film into contact with a surface of the final substrate while applying both heat and pressure to the transfer film, thereby causing the microspheres in the thermal release adhesive layer(s) to expand (or foam) and deactivate the pressure sensitive adhesive, allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the

adhesive on the microstructures, allowing the microstructures to adhere to the surface of the final substrate.

[0016] This embodiment is particularly suited for microstructures having so-called "up/down non-parity" (e.g., refractive optical systems). As will be readily appreciated by those skilled in the art, such structures are intended to be viewed from a top or upper side rather than a bottom or lower side. The inventive process allows the microstructures on the disposable manufacturing substrate to be visually inspected for quality assurance purposes before transferring the microstructures to the transfer film, and further allows the microstructures to be properly positioned in an upright position on a surface of the final substrate.

[0017] In a second preferred embodiment, the process comprises: forming the microstructures on a surface of the thermal release adhesive layer(s) of the transfer film; applying one or more heat and/or pressure activated adhesives to the formed microstructures on the transfer film; bringing the adhesive coated microstructures into contact with a surface of the final substrate while applying both heat and pressure to the transfer film, thereby causing the microspheres in the thermal release adhesive layer(s) to expand (or foam) and deactivate the pressure sensitive adhesive, allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the adhesive on the microstructures, allowing the microstructures to adhere to the surface of the final substrate.

[0018] This embodiment is particularly suited for microstructures that do not require an upper/lower surface inspection (e.g., conductive circuit elements or structures). Such structures could be symmetrical in cross section and are not necessarily intended to be viewed from a top or upper side rather than a bottom or lower side.

[0019] In a second exemplary embodiment, the process is a continuous roll-to-roll process that comprises:

forming the microstructures on a surface of a disposable manufacturing substrate;

applying one or more release coating layers to a surface of the microstructures, the release coating layer(s) conforming to the microstructure surface, and then curing the release coating layer(s);

applying one or more binder layers to a surface of a carrier film and optionally also to the cured release coated surface of the microstructures, and while these surfaces are in contact with each other, curing the binder layer(s);

mechanically removing the disposable manufacturing substrate from the microstructures now bonded to the carrier film; and then

transferring the microstructures from the carrier film onto a surface of the final substrate.

5 **[0020]** In a preferred embodiment, the microstructures are transferred from the carrier film onto a surface of the final substrate by: applying one or more heat and/or pressure activated adhesives to the microstructures on the carrier film; bringing the adhesive coated microstructures on the carrier film into contact with a surface of the final substrate; applying both heat and pressure to the carrier film and then lifting the carrier film from the microstructures
10 causing separation between the microstructures and the release coating layer(s), thereby allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the adhesive on the microstructures, thereby allowing the microstructures to adhere to the surface of the final substrate.

[0021] Other features and advantages of the invention will be apparent to one of ordinary skill from the following detailed description and accompanying drawings.
15

[0022] Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. All publications, patent applications, patents and other references mentioned herein are incorporated by reference in their entirety. In case of conflict, the present specification,
20 including definitions, will control. In addition, the materials, methods/processes, and examples are illustrative only and not intended to be limiting.

BRIEF DESCRIPTION OF THE DRAWINGS

[0023] Particular features of the disclosed invention are illustrated by reference to FIG. 1, which is a schematic flow diagram of the second exemplary embodiment of the inventive process for transferring microstructures to a final substrate. Components in this drawing are not necessarily to scale, emphasis instead being placed upon clearly illustrating the principles of the present disclosure.
25

DETAILED DESCRIPTION OF THE INVENTION

30 **[0024]** The subject invention provides methods or processes for producing microstructures {e.g., precision cast microstructures) on a continuous roll-to-roll substrate or film

in ways that allow these microstructures to be subsequently transferred to a final substrate. Advantages in speed and precision are realized by using roll-to-roll processes to produce microstructures, while providing a means for transferring the microstructures to a final surface that is not necessarily compatible with or suitable for flexible web processing {e.g., rigid final
5 substrates such as glass). In this way, final substrates may have precision microstructures applied to their surface, without being subjected to all of the conditions which are necessary for the production of, for example, precision cast microstructures.

[0025] The present invention is useful in the production of passport security laminates, the application of security patches or seals on value documents, labels on products, thin films or
10 foils to banknotes, conductors or insulating circuit components onto rigid substrates, and other general applications of microstructured elements or microstructures to a surface.

[0026] For avoidance of doubt, nanostructures are also contemplated by the present invention, as are (as alluded to above) end-use applications outside of the security field.

[0027] Exemplary embodiments of the inventive system will now be disclosed. There is
15 no intent, however, to limit the present disclosure to the embodiments disclosed herein. On the contrary, the intent is to cover all alternatives, modifications and equivalents.

[0028] The microstructures used in the present invention are single or multi-layer structures that comprise: voids in a substantially planar surface, the voids optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations
20 thereof. In an exemplary embodiment, the microstructures {e.g., optical or physical structures} are precision cast microstructures that include any and all types of structures whose form may be produced by backfilling a negative void in a cured or hardened matrix on a flexible substrate.

[0029] Examples of such contemplated precision cast microstructures include multilayer optical systems such as refractive, reflective, diffractive, and hybrid micro-optic structures, as
25 well as other single or multilayer structures such as conductive traces, circuit patterns, microlenses, waveguides, negative space air lenses, insulating ceramic structures, icon image elements, microtext, anti-reflective structures, light refracting prisms, micromirror structures, patterned semiconductors, patterned or unpatterned metallization, fluorescent security print, porous filtration structures, chemical or electronic sensor elements, photoresist masking
30 structures, ruled gratings, periodic or aperiodic arrays, structures for increasing surface area, tactility altering structures, structures for facilitating mechanical bonding, etc.

[0030] Generally speaking, the size of these microstructures (*i.e.*, width or depth) is limited only by that which is achievable by casting from an embossing tool onto a flexible substrate. The size may range from tens of nanometers (a few atomic layers thick) in depth in some cases to a few micrometers in most cases, and up to millimeter scale structures.

5 **[0031]** Precision casting of microstructures in a roll-to-roll form on a flexible substrate or film has many advantages, particularly when considered together with a transferrable process, as will be described. The term "precision casting", as used herein, means the replication of a microstructured surface having a predesigned pattern of voids and/or raised areas, or negative and positive features.

10 **[0032]** By using radiation cured polymers on film, or hot embossable films, for example, the surface of the master is copied continuously, and a precise pattern of voids and/or raised areas may be formed in a cured matrix, resulting in precisely formed microstructures or "icon elements." Exemplary processes are described in U.S. Patent No. 7,333,268 to Steenblik *et al.*, U.S. Patent No. 7,468,842 to Steenblik *et al.*, U.S. Patent No. 7,738,175 to Steenblik *et al.*, U.S. Patent Application Serial No. 12/820,320 to Steenblik *et al.*, and U.S. Patent Application Serial
15 No. 13/360,017 to Samuel M. Cape *et al.*, which are all incorporated herein by reference in their entirety. By casting these structures, each negative space results in a voluminous region that can be backfilled with a second material that can be much different than the material used to cast the matrix. For example, slurries, pastes, dispersions, gels, powders, liquids, and flakes
20 may all be used to fill the voids, resulting in a precision element that is contained within the volume of the matrix. This allows for the formation of shapes using materials that would be difficult or impossible to cast without using this matrix backfilling technique. The backfilled material may be further cured, washed, etc. to ensure desired properties such as degree of crosslinking, etc.

25 **[0033]** Once a first layer of such backfilled embossed matrix has been formed, any practical number of additional layers may be added thereafter, such as a second layer of backfilled precision elements, or precision elements that are not backfilled such as a microlens layer, or a polymer spacer layer followed by a microlens layer, a metallization layer, or other functional coatings. Additionally, it is possible and often desirable to apply a coating to the
30 flexible substrate before the first microstructured layer is cast, in order to facilitate replication from the embossing master and for removal of the microstructured elements at a later time. This coating may be tailored to provide adhesion or release properties between the flexible

substrate and the microstructured layer. For example, such a coating may be prepared from polymers having low surface energy, such as UV curable silicone-modified polyacrylates.

[0034] In an example of the first exemplary embodiment of the inventive process for transferring microstructures having "up/down non-parity", the precision cast single or multi-layer microstructures are formed on a flexible disposable manufacturing substrate, and then the microstructures are transferred away from the manufacturing substrate and onto a new carrier film having one or more thermal release adhesive layers. The thermal release adhesive layer(s) is used to provide a strong bond between the new carrier film and the microstructures and to allow for the release of these microstructures at a later time upon the application of heat. To summarize, the inventive process:

- a) Enables the removal of the flexible disposable manufacturing substrate (*i.e.*, base film) from the precision cast microstructures, which lack any significant strength, body or structural integrity when taken by themselves;
- b) Enables the conversion and handling of the microstructured elements using traditional web or sheet based equipment such that further coatings and adhesives may be applied, and so that the otherwise fragile structures may be slit, die-cut, perforated, sheeted, etc.; and
- c) Enables the transfer of the microstructures from the thermal release adhesive coated carrier film (*i.e.*, the TRA transfer film) to a final substrate without suffering from damaging effects of the transfer process such as heat, pressure, and tension, while allowing the carrier film to be rewound and discarded after the transfer process is complete.

[0035] The thermal release adhesive layer(s) of the transfer film provides a strong bond between the precision cast microstructures and the new carrier film yet has a mechanism for decisive, predictable release at a later time when the microstructures are transferred to the final substrate.

[0036] The formulation used to prepare the thermal release adhesive layer(s) of the present invention is made specifically to have strong bonding at room temperatures, and significantly reduced bond strength when elevated temperatures are applied. The adhesive formulation may be said to be 'activated' when it is in the low temperature, high bond strength state, and 'deactivated' when it is in an elevated temperature, diminished bond strength state.

[0037] As noted above, the inventive thermal release adhesive formulation, in a more preferred embodiment, comprises from about 90 to about 96 % by weight of an energy curable PSA formulation, and from about 4 to about 10 % by weight of expandable microspheres.

[0038] The energy curable PSA formulation used in the inventive thermal release adhesive formulation, in a more preferred embodiment, comprises:

from about 30 to about 60 % by wt. of one or more elastomeric oligomers, which provide high elongation and structure to the formulation;

from about 10 to about 40 % by wt. of one or more tackifying resins, which impart elasticity, flexibility and adhesion to the formulation;

from about 20 to about 50 % by wt. of one or more reactive monomeric diluents, which serve to modify the degree of crosslinking and the glass transition temperature of the formulation; and

from about 3 to about 6 % by wt. of one or more photoinitiators.

[0039] Specific examples of suitable PSA formulations include, but are not limited to, the following:

PSA Formulation 1:

- 30 wt. % trimethylolpropane triacrylate, which is sold under the trade designation SR-351 by Sartomer Company of Exton, PA., USA. (Sartomer)
- 33 wt. % aromatic urethane/tackifier oligomer, which is sold under the trade designation CN3000 by Sartomer
- 33 wt. % isobornyl acrylate, which is sold under the trade designation SR-506 NS by Sartomer
- 4 wt. % liquid mixture of two photoinitiators, sold under the trade designation OMNIRAD 1000 by IGM Resins Inc. of St. Charles, IL, USA (IGM)

PSA Formulation 2:

- 19 wt. % urethane acrylate oligomer, which is sold under the trade designation CN973H85 by Sartomer
- 32 wt. % tackifier resin, which is sold under the trade designation S 115 by Sartomer
- 45 wt. % 2(2-ethoxyethoxy) ethyl acrylate (EOEOEA), a reactive monomeric diluent, which is sold

under the trade designation SR256 by Sartomer
 4 wt. % 2-hydroxy-2-methyl-1-phenyl-1-propanone photoinitiator, which is sold under the trade designation OMNIRAD 73 by IGM

5

[0040] Specific examples of suitable expandable microspheres, which start expansion and/or foaming when heated to temperatures higher than about 60 °C, include:

expandable plastic microspheres, sold under the trade designation EXPANCEL®
 10 by Casco Adhesives AB, P.O. Box 11538, Stockholm, Sweden 100 01 (Casco);
 dry thermoplastic microspheres, sold under the trade designation DUALITE® by Henkel Corporation, One Henkel Way, Rocky Hill, CT 06067 (Henkel);
 thermal expandable microsphere, sold under the trade designation ADVANCELL EM by Sekisui Kagaku Kogyo Kabushiki Kaisha (dba Sekisui Chemical Co. Ltd.), 4-4,
 15 Nishitemma 2-chome, Kita-ku Osaka-shi, Osaka, Japan 530-8565 (Sekisui); and
 expandable microspheres available from Matsumoto Yushi-Seiyaku Co., Ltd., 2-1-3 Shibukawa-cho Yao-shi, Osaka, Japan (Matsumoto), Kureha Corporation, 3-3-2, Nihonbashi-Hamacho, Chuo-ku, Tokyo, Japan 103-8552 (Kureha), and Hangzhou Hi-Tech Fine Chemical Co., Ltd., Haihong Technical and Industrial Area, Liangzhu Town,
 20 Yuhang District, Hangzhou, Zhejiang, China (Haihong Group).

[0041] A specific example of a suitable TRA formulation is set forth below:

TRA Formulation:

25 90 wt. % a radiation curable PSA formulation, which is sold under the trade designation AROCURE™ by Ashland Inc., 50 E. RiverCenter Blvd., P.O. Box 391, Covington, KY 41012-0391 (Ashland)
 30 10 wt. % expandable microspheres, which are sold under the trade designation EXPANCEL™ by Akzo Nobel Inc., 525 West Van Buren, Chicago, IL 60607, USA (Akzo Nobel).

[0042] The TRA works through the mechanism of microsphere expansion, allowing for
 35 precise control of release. During the release process, the adhesive bond strength declines dramatically. In one example, the bond strength of the activated TRA was found to be between 5.3 to 9.6 Newtons/inch (N/in), while the heat-deactivated strength was measured to be

approximately 0.9 to 0.1 N/in. Typical microspheres for this use will start expanding at 80-180 °C and continue to expand up to 125-220 °C. Once the adhesive has been heated in this way, the tack and bond strength are permanently reduced.

[0043] Before expansion, the microspheres preferably range from 5 to 50 microns in diameter, and after heating they preferably expand to 15 to 150 microns in diameter. More preferably, the microspheres range from 6 to 20 microns in diameter before expansion.

[0044] Prior to heating, preferable thermal release adhesive layer thicknesses range from 3 to 100 microns and more preferably from 5 to 25 microns. After heating, this layer will typically double in thickness.

[0045] Preparation of the TRA formulation may be accomplished by combining premixed energy curable PSA in its liquid state with the weighed quantity of polymeric microspheres (e.g., polymeric microsphere powder), followed by blending with a high shear mixer. The resulting suspension of powder with energy curable PSA will remain stable in its liquid form for an extended period of time as long as exposure to sources of heat and UV radiation are avoided.

[0046] The TRA formulation is applied to a carrier film. Suitable carrier films may be any flexible material that is capable of receiving a coating and being conveyed through production equipment. For example, polymeric materials such as biaxially oriented polyethylene terephthalate (PET), polypropylene (PP), nylon 6 polyamide (PA), polyethylene naphthalate (PEN), cellulose acetate or other film materials, as well as non-polymeric materials such as paper constitute suitable carrier films.

[0047] Methods suitable for liquid adhesive application may be used to apply the TRA formulation to a carrier film as long as the microsphere activation temperature is not exceeded. For example, a suitable layer thickness of TRA formulation may be achieved by drawing down onto a carrier film with a wire wrapped rod (e.g., a #14 Meyers rod), or by means of a flexographic printing unit or gravure cylinder. The liquid TRA formulation may be heated above room temperature in order to reduce the viscosity for ease of application (i.e., to facilitate pumping or pouring) as long as the microsphere activation temperature is not exceeded. When a thin layer has been applied to the carrier film with the desired thickness (e.g., 15 micron thickness), the TRA may be cured by UV radiation, for example, by passing the coated carrier film beneath a 300 Watts/in Hg lamp at 40 fpm. Alternatively, the TRA may be electron beam cured by passing the uncured resin through an e-beam curing unit. In addition, both methods may be used in combination.

[0048] Once cured, the TRA becomes activated so that it has high tack and peel strength {e.g., peel strength values ranging from about 5 to about 50 N/in (ASTM D903-98)}, and is ready to be brought into contact with the desired bonding surface. For example, a flexible micro-optic security film may be brought into contact with the TRA and carrier film {i.e., the TRA transfer film), forming a laminated structure that remains bonded until it is desirable to release the bond by application of heat.

[0049] The entire laminated structure thus formed may then be rewound and handled as a single flexible film, allowing further processing such as: stripping away the base manufacturing film, applying adhesives on the exposed side of the micro-optic film, die cutting, printing, metalizing, or other film converting operations. The adhesive bond of the TRA may then be deactivated by heating {e.g., 80-220 °C) at a point in time when it is advantageous to transfer the microstructure from the TRA transfer film {e.g., TRA/60 gauge PET carrier film) onto the final substrate. As noted above, such a process may be useful in the production of passport security laminates, the application of security patches or seals on value documents, labels on products, thin films or foils to banknotes, conductors or insulating circuit components onto rigid substrates, and other general applications of microstructured elements or microstructures to a surface.

[0050] Deactivation of the TRA occurs whenever the softening temperature of the polymeric shell of the microspheres has been reached or exceeded, causing volume expansion (or foaming) and a significant decrease in the adhesive bond strength compared to its preheated state. Heating methods suitable for causing deactivation of the TRA include forced hot air, heated roller, infrared heating, oven or hotplate heating, heated foil stamping roller, passport laminator, heated shoe, heated platen, heated bath, and the like.

[0051] In a preferred process for transferring microstructures having "up/down non-parity" to a final substrate, the continuous roll-to-roll process comprises:

- forming microstructures on a disposable flexible manufacturing substrate;
- optionally, backfilling the microstructures with a curable material;
- applying an energy curable TRA in liquid form to a separate carrier film and curing by application of UV light, e-beam radiation, or both, thereby forming a "TRA transfer film";

- nipping together the formed microstructures on the flexible manufacturing substrate to the TRA layer of the TRA transfer film, thereby activating the pressure

sensitive adhesive in the TRA layer and allowing the adhesive to adhere the microstructures to the TRA layer;

stripping away the disposable flexible manufacturing substrate;

converting the microstructure/TRA transfer film using methods known in the art, including, but not limited to, applying other heat and/or pressure activated adhesives {e.g., tack-free, heat-activated adhesives), primers or coatings, to the transfer film, followed by slitting or die cutting the film to desired final dimensions, and sheeting the cut film into stacks or rewinding onto reels or spools, thereby forming a "transfer ready system";

transferring the adhesive-coated microstructures to a final substrate by bringing the microstructures on the transfer ready system into contact with the final substrate for thermal lamination, whereby heat and pressure are applied to the transfer ready system, thereby causing the microspheres in the TRA layer to expand (or foam) and deactivate the pressure sensitive adhesive, thereby allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the adhesive on the microstructures, allowing the microstructures to adhere to the surface of the final substrate; and

rewinding and discarding the transfer film with deactivated TRA, leaving the final substrate with newly affixed microstructures on its surface, ready for further processing or printing as desired.

[0052] In an exemplary embodiment, the microstructure is a multi-layer optical system in the form of a security thread or foil, and the final substrate is banknote paper. In this exemplary embodiment, the heat and pressure of lamination causes the thread/foil to securely bond to the banknote paper, while at the same time exceeding the deactivation temperature of the TRA, thereby causing the TRA and carrier film to separate from the thread/foil. This process provides an advantageous means of delivering a security thread/foil to banknote paper, following by rewinding and discarding the carrier film containing deactivated TRA.

[0053] In another exemplary embodiment, the microstructure is a die-cut, heat-seal label, and the final substrate is product packaging.

[0054] In an exemplary embodiment of the inventive process for transferring microstructures having "up/down parity" {i.e., cross-sectional symmetry), the precision cast single or multi-layer microstructures are formed directly on the TRA transfer film, and then the

microstructures are transferred away from the TRA transfer film onto the final substrate. In this configuration, care must be taken to avoid overheating the TRA during the microstructure casting step. Casting resins with low viscosities (resins that do not need additional heat to flow freely such as neopentyl glycol diacrylate (available from Sartomer under the trade designation SR247)), combined with an internally water cooled casting surface (comparable to a flexographic chill drum) allow microstructures to be UV cured against the TRA without overheating the expandable microspheres or causing premature expansion.

[0055] In a preferred process, the continuous roll-to-roll process comprises:

applying an energy curable TRA in liquid form to a separate carrier film and curing by application of UV light, e-beam radiation, or both, thereby forming a "TRA transfer film";

forming microstructures on the TRA transfer film;

optionally, backfilling the microstructures with a curable material;

converting the microstructure/TRA transfer film by applying other heat and/or pressure activated adhesives {e.g., tack-free, heat-activated adhesives), primers or coatings, to the transfer film, followed by slitting or die cutting the film to desired final dimensions, and sheeting the cut film into stacks or rewinding onto reels or spools, thereby forming a "transfer ready film";

transferring the adhesive-coated microstructures to a final substrate by bringing the microstructures on the transfer ready system into contact with the final substrate for thermal lamination, whereby heat and pressure are applied to the transfer ready system, thereby causing the microspheres in the TRA layer to expand (or foam) and deactivate the pressure sensitive adhesive, thereby allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the adhesive on the microstructures, allowing the microstructures to adhere to the surface of the final substrate; and

rewinding and discarding the transfer film with deactivated TRA, leaving the final substrate with newly affixed microstructures on its surface, ready for further processing or printing as desired.

[0056] In an exemplary embodiment, the microstructure is an embedded lens array structure, and the final substrate is a laser engravable polycarbonate substrate. Here, the embedded lens array structure is made up of a low refractive index (RI) (e.g., $n=1.35-1.45$)

5 concave polymeric matrix backfilled with high RI (e.g., $n=1.5-1.8$) polymer, the applied adhesive is a heat-activated adhesive, and the embedded lens array structure of the transfer ready film is brought into contact with a surface of the laser engravable polycarbonate substrate and heated under pressure to a point in which the embedded lens array structure is thermally laminated to the surface of the polycarbonate substrate. In this embodiment, the heat and pressure of lamination causes the embedded lens structure to securely bond to the intended polycarbonate final substrate, while at the same time exceeding the deactivation temperature of the TRA, causing the TRA transfer film to separate from the embedded lens structure. This process provides an advantageous means of delivering a lens structure to a surface of a laser engravable polycarbonate surface, such that further processing steps may occur, such as laser writing through the lens structure into the polycarbonate, providing an optically variable laser written effect.

10 **[0057]** In another exemplary embodiment, the microstructure is a reflective optical system, and the final substrate is currency or banknote paper. In this embodiment, the reflective optical system is cast against the TRA transfer film. It is suitable to form such a multi-layer microstructure directly onto the TRA transfer film that will be used to transfer the optics to the final substrate (rather than onto a flexible disposable manufacturing substrate followed by transferring onto the TRA transfer film). This is so because a reflective optical system operates with the reflector side against the final substrate and so is compatible and advantageous to use with this method.

20 **[0058]** To produce this reflective optical system, the following method may be used. A thin layer (e.g., 5 microns) of TRA is coated onto a 60 gauge film of PET and cured by application of UV light. Next, icons are formed as voids in a radiation cured liquid polymer (e.g., acrylated urethane) that is cast from an icon mold, then the icon voids are filled with a submicron particle pigmented coloring material by gravure-like doctor blading against the polymeric icon surface, then the fill is solidified by suitable means (e.g., solvent removal, radiation curing, or chemical reaction), then the reflective lens elements are cast against the filled icons by bringing the icon side of the film against a lens mold filled with radiation curable polymer, and the polymer is solidified by application of UV light or other actinic radiation. Next the lens elements are metalized (e.g., with aluminum) using a physical vapor deposition process, which is known in the art of holographic foil manufacture. Following metallization, an optional sealing layer may be applied to further protect the metal coating, followed by the

application and drying of an adhesive, for example, a tack-free, heat-activated polyurethane foiling adhesive. Next, the entire structure (*i.e.*, TRA transfer film with optical microstructure (icon layer/reflective lens elements/metal reflecting layer/sealing layer/adhesive layer)) may be converted into its final form by undergoing slitting and rewinding onto reels that are compatible with holographic foil transfer equipment. In this form, the micro-optic system may be transferred away from the TRA transfer film and onto the final substrate by the application of heat and pressure. For example, the structure may be brought into contact with currency or banknote paper while a foiling die applies pressure at 140 °C. At this temperature, the foiling adhesive bonds the structure (by the side having reflector elements) to the final paper substrate, while the TRA provides the mechanism for release of the micro-optic system from the TRA transfer film. Then the desired final product (paper with surface applied reflective micro-optics) is rewound and the waste TRA transfer film is rewound and discarded or recycled.

[0059] In yet another exemplary embodiment, the microstructures are conductive circuit traces, and the final substrate is a glass substrate, which constitutes a subassembly of a touch screen display. In this embodiment, heat and pressure causes the conductive circuit traces to bond to the glass substrate, while releasing from the TRA transfer film. This process provides a means of producing the microstructure conductive circuit traces in high volume on a roll-to-roll basis, and subsequent delivery to an inflexible final substrate, resulting in an economically produced subassembly of a touch screen display.

[0060] In a further exemplary embodiment, the microstructure is in the form of a regular array of microstructured pre-ceramic polymers, and the final substrate is a quartz substrate, which forms a temperature sensing diffraction grating. In this embodiment, heat and pressure allows the 'green cured' array of pre-ceramic polymers (referring to a ceramic that is yet to be fired) to transfer away from the TRA transfer film and onto the quartz substrate. Next, the quartz and pre-ceramic are fired in a kiln at high temperatures (*e.g.*, 1400-1600 °C), resulting in a sintered ceramic microstructure fused to a quartz substrate.

[0061] This process provides a means of producing a microstructured diffraction grating using ceramic precursors in high volume and at low temperatures on a roll-to-roll basis, and subsequent transfer to an inflexible final substrate. In this way, further processes incompatible with a flexible web can occur such as high temperature firing, resulting in the formation of a microstructured ceramic surface that can survive extremes in temperature exposure, but is produced using economical flexible web processes. In this example, the microstructured

ceramic grating on quartz substrate finds use as a temperature monitor or a strain gauge. By reflecting a laser off of its surface and measuring the distance between the reflected bright zones (areas of constructive interference), highly accurate changes in groove spacing due to temperature or strain can be detected and calculated.

5 **[0062]** An alternative process for transferring microstructures to a final substrate will now be described. This alternative process provides improvements in overall system thickness, transfer speed, stability over time, and elimination of residue on the transferred microstructures.

[0063] The alternative process does not require the use of heat to initiate release of the microstructures from the carrier film (and thus is compatible with cold foiling methods), although
10 it is still compatible and may be used with thermally activated adhesives. This process is also compatible with a cast spacer between focusing elements {e.g., lenses) and icons, and as such is not limited to the "spacer-less" structure shown in FIG. 1. Additionally, where the release layer(s) and binder layer(s) are 'fully cured' and stable, temperatures encountered during, for example, heated foiling, may facilitate removal of the carrier, but do so without leaving a residue
15 on the microstructures.

[0064] As mentioned above, the alternative process for transferring microstructures employs:

- 1) one or more release coatings, which are applied to (and conform to) an upper surface of the microstructures, and are cured; and
- 20 2) one or more binder layers, which are cured in contact with the carrier film and the cured release coating(s) on the upper surface of the microstructures.

Together, these layers serve to bind the microstructures firmly to the carrier film until a later time when it is desirable to transfer the microstructures to a final substrate such as currency paper
25 and to discard the carrier film. Moreover, by employing a fully cured binder, temperature and pressure instability is avoided.

[0065] The one or more binder layers, in a preferred embodiment, are prepared from an energy curable {e.g., UV curable) binder formulation generally comprising:

- (a) from about 0 to about 99.8 % by wt. (preferably, from about 10 to about
30 50 % by wt.) of an energy curable polyacrylate oligomer;
- (b) from about 0 to about 99.8 % by wt. (preferably, from about 20 to about 80 % by wt.) of an energy curable acrylate monomer; and

(c) from about 0.2 to about 35 % by wt. (preferably, from about 1 to about 12 % by wt.) of a free radical photoinitiator.

The binder formulation may be applied between the carrier film and microstructures (when still attached to the manufacturing substrate) during the continuous roll-to-roll process. The formulation is applied at thicknesses ranging from about 0.5 to about 25 microns (preferably, from about 2 to about 10 microns), and the layers bonded using, for example, a traditional wet lamination process where the two layers are brought together with uncured resin between the layers and then cured together. A relatively strong bond to the carrier film is realized such that release never occurs at the interface between the binder layer(s) and the carrier film. In a preferred embodiment, a carrier film having 'print receptive' surface treatment is used, while in another preferred embodiment, the surface energy of the carrier film is modified during production using, for example, corona or plasma pretreatment.

[0066] In a more preferred embodiment, the one or more binder layers are prepared from a formulation comprising:

(a) 40 wt. % of an energy curable polyacrylate oligomer sold under the trade designation CN293 by Sartomer;

(b) 60 wt. % of an energy curable acrylate monomer sold under the trade designation CD420 by Sartomer; and

(c) 4 wt. % of a liquid mixture of two photoinitiators sold under the trade designation OMNIRAD 1000 by IGM.

[0067] In order to prevent a permanent bond between the binder and microstructures (e.g., a microlens-based film structure), the microstructures are first treated with a 'release' formulation that has low bond strength (i.e., peel strength of less than 1 N/in (ASTM D903-98)). In this way, the cured binder bonds strongly to the carrier film and also bonds strongly to the cured release coating layer(s). This combination provides a bond which is strong under one set of conditions (favorable for removal of the manufacturing substrate) as well as a bond that is easily broken under another set of conditions (favorable for transfer of the microstructures to final substrate).

[0068] The one or more conformal release coating layers, in a preferred embodiment, are prepared from an energy curable (e.g., UV curable) formulation generally comprising:

(a) from about 1 to about 98 wt. % (preferably, from about 5 to about 20 wt. %) of isodecyl acrylate;

(b) from about 2 to about 50 wt. % (preferably, from about 10 to about 35 wt. %) of a free radical photoinitiator; and

(c) from about 0 to about 90 wt. % (preferably, from about 10 to about 80 wt. %) of 2-propanol (isopropyl alcohol).

5 The formulation, which has been found to work over a range of dilutions with isopropyl alcohol, is applied by roll coating, or other suitable method for applying a fluid to a flexible substrate {e.g., flexo coating, anilox coating, gravure coating, metering rod (Meyer bar), curtain coating, rotary screen, silk screen, immersion, reverse roll, knife-over-roll, gap coating, or air knife) at thicknesses ranging from about 0.1 to about 10 microns, preferably, from about 0.5 to about 2
10 microns. The viscosity of the formulation ranges from about 2 to about 50 centipoise (cps) (preferably, from about 5 to about 15 cps), allowing the formulation to conform to the surface of the microstructures. The release coating layer(s), both before and after full cure, have a sufficiently low interfacial bond strength. In particular, the interfacial bond strength is low enough that when the microstructures are bonded to the final substrate by an adhesive and the
15 carrier film is peeled away, separation will occur at the interface of the microstructures and the release coating layer(s). The ease of separation is controlled by the component properties of the release coating. For example, a monofunctional component such as isodecyl acrylate with a low glass transition temperature ($T_g = -60\text{ }^\circ\text{C}$) will have a much lower bond strength than a higher functionality component such as trimethylolpropane ethoxy triacrylate (TMPEOTA) ($T_g =$
20 $37\text{ }^\circ\text{C}$), which has a larger number of reactive sites per polymer molecule. During hot or cold foiling operations, the necessary force for breaking this bond is supplied as tension when the carrier film is pulled away from the microstructures and rewound on a waste reel.

[0069] In a more preferred embodiment, the release formulation comprises:

(a) 10 wt. % of isodecyl acrylate;

25 (b) 30 wt. % of a liquid mixture of two photoinitiators sold under the trade designation OMNIRAD 1000 by IGM; and

(c) 60 wt. % of isopropyl alcohol.

[0070] The conditions that provide either a strong bond or weak bond using this construction are determined by the geometry of separation {i.e., by the angle at which the
30 manufacturing substrate is peeled away relative to the carrier film). With a low angle of peel {i.e., obtuse angles greater than 90° to about 180° }, the bond is high between the carrier and the microstructures, due to the distribution of force over a larger area (similar to the difficulty of

separating two flat plates of glass with a layer of water between). With a high angle of peel (*i.e.*, acute angles less than 90 to about 0°), the stress is concentrated to a smaller region, breaking bonds at the interface closest to the source of stress, allowing the manufacturing substrate to be removed without disrupting the bond between the microstructures and the carrier film. Once the manufacturing substrate has been removed and the adhesive applied, the microstructures may be applied to the final substrate such as paper on a commercial foiling unit (*e.g.*, a Leonard Kurz MHS foiling machine), or passport booklet laminating machine. This equipment is designed to lift away carrier films to rewind and discard, and this lifting process easily breaks the bond between the microstructures and the film at the release coating interface.

10 [0071] Referring now to **FIG. 1** in detail, a schematic flow diagram of one embodiment of this alternative process for transferring microstructures to a final substrate is shown generally at 10. The inventive process is a continuous roll-to-roll process that in this exemplary embodiment comprises:

forming the microstructures on a surface of a disposable manufacturing substrate (shown generally in process steps (A) and (B) in FIG. 1);

applying one or more release coating layers to a surface of the microstructures, the release coating layer(s) conforming to the microstructure surface, and then curing the release coating layer(s) (shown generally in process step (C) in FIG. 1);

applying one or more binder layers to a surface of a carrier film and optionally also to the cured release coated surface of the microstructures, and while these surfaces are in contact with each other, curing the binder layer(s) (shown generally in process step (D) in FIG. 1);

mechanically removing the disposable manufacturing substrate from the microstructures now bonded to the carrier film (shown generally in process step (E) in FIG. 1);

converting the bonded or laminated film structure using methods known in the art, including, but not limited to, applying other heat and/or pressure activated adhesives (*e.g.*, tack-free, heat-activated adhesives), primers or coatings, to the film structure (shown generally in process step (F) in FIG. 1), followed by slitting or die cutting the structure to desired final dimensions (shown generally in process step (G) in FIG. 1), and sheeting the cut film into stacks or rewinding onto reels or spools, thereby forming a "transfer ready system";

transferring the adhesive-coated microstructures to a final substrate by bringing the microstructures on the transfer ready system into contact with the final substrate (shown generally in process step (H) in FIG. 1) for thermal lamination, whereby heat and pressure are applied to the transfer ready system and then the carrier film is lifted from the microstructures causing separation between the microstructures and the release coating layer(s), thereby allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the adhesive on the microstructures, thereby allowing the microstructures to adhere to the surface of the final substrate; and
rewinding and discarding the carrier film (shown generally in process step (I) in FIG. 1), leaving the final substrate with newly affixed microstructures on its surface, ready for further processing or printing as desired.

[0072] As noted above, this alternative process provides improvements in overall system thickness and transfer speed. The binder layer(s) is cured between films allowing the binder to be rolled out to a very thin layer between the films, which reduces overall system caliper. This reduction in caliper translates into run speed improvements because the conductance of heat through the system is faster when there is less material acting as a thermal mass to slow down the melting of the adhesive.

[0073] Other features and advantages of the invention will be apparent to one of ordinary skill from the following detailed description and accompanying drawings. Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. All publications, patent applications, patents and other references mentioned herein are incorporated by reference in their entirety. In case of conflict, the present specification, including definitions, will control. In addition, the materials, methods, and examples are illustrative only and not intended to be limiting.

[0074] What is claimed is:

CLAIMS

1. A transfer film for transferring microstructures to a final substrate, the transfer film comprising a carrier film and one or more adhesive or binder layers on a surface of the carrier film, wherein the microstructures are single or multi-layer structures that comprise: voids in a substantially planar surface, the voids optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations thereof.

2. The transfer film of claim 1, which comprises a carrier film and one or more thermal release adhesive layers on a surface of the carrier film, wherein the one or more thermal release adhesive layers is made up of a plurality of expandable microspheres and one or more pressure sensitive adhesives.

3. The transfer film of claim 2, wherein the microstructures are adhered to a surface of the one or more thermal release adhesive layers, wherein adhesion between the microstructures and the one or more thermal release adhesive layers decreases when the one or more thermal release adhesive layers is heated to a temperature higher than about 60 °C.

4. The transfer film of claim 2, wherein the expandable microspheres are polymer microspheres that start expansion and/or foaming when heated to temperatures higher than about 60 °C.

5. The transfer film of claim 2, wherein the one or more thermal release adhesive layers is prepared from a formulation comprising from about 25 to about 99 % by wt. of an energy curable pressure sensitive adhesive formulation, and from about 1 to about 75 % by wt. of expandable microspheres.

6. The transfer film of claim 5, wherein the energy curable pressure sensitive adhesive formulation comprises:

from about 5 to about 95 % by wt. of one or more elastomeric oligomers;

from about 1 to about 75 % by wt. of one or more tackifying resins;

from about 0.5 to about 75 % by wt. of one or more reactive monomeric diluents;

and

from about 0.1 to about 15 % by wt. of one or more photoinitiators.

7. The transfer film of claim 1, which comprises a carrier film and one or more cured binder layers on a surface of the carrier film, wherein the one or more cured binder layers is made up of one or more energy curable polyacrylates and a free radical photoinitiator.

8. A method of using a transfer film made up of a carrier film and one or more adhesive or binder layers on a surface of the carrier film, wherein the microstructures are single or multi-layer structures that comprise: voids in a substantially planar surface, the voids optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations thereof, wherein the method comprises using the transfer film (a) to transfer the microstructures in a continuous roll-to-roll process to a final substrate, or (b) as a manufacturing substrate during production of the microstructures and then to transfer the microstructures in a continuous roll-to-roll process to a final substrate.

9. The method of claim 8, wherein the transfer film is made up of a carrier film and one or more thermal release adhesive layers on a surface of the carrier film, wherein the one or more thermal release adhesive layers is made up of a plurality of expandable microspheres and one or more pressure sensitive adhesives.

10. The method of claim 8, wherein the transfer film is made up of a carrier film and one or more cured binder layers on a surface of the carrier film, wherein the one or more cured binder layers is made up of one or more energy curable polyacrylates and a free radical photoinitiator.

11. The method of using a transfer film of claim 8, wherein the microstructures are in the form of a multi-layer optical structure that has been converted into a security thread or foil, and wherein the final substrate is banknote paper.

12. The method of using a transfer film of claim 8, wherein the microstructures are in the form of a single or multi-layer structure that has been converted into a die-cut, heat-seal label, and wherein the final substrate is product packaging.

13. The method of using a transfer film of claim 8, wherein the microstructures are in the form of an embedded lens array structure, and wherein the final substrate is a laser engravable polycarbonate substrate.

14. The method of using a transfer film of claim 8, wherein the microstructures are in the form of a reflective optical system that has been converted into a security thread or foil, and wherein the final substrate is banknote paper.

15. The method of using a transfer film of claim 8, wherein the microstructures are conductive circuit traces, and wherein the final substrate is a glass substrate that constitutes a subassembly of a touch screen display.

16. The method of using a transfer film of claim 8, wherein the microstructures are in the form of a regular array of microstructured pre-ceramic polymers, and wherein the final substrate is a quartz substrate that forms a temperature sensing diffraction grating.

17. A process for transferring microstructures to a final substrate, the method
5 comprising subjecting a transfer film made up of a carrier film and one or more adhesive or binder layers on a surface of the carrier film in a continuous roll-to-roll process to the following operations: either forming microstructures on, or transferring microstructures to a surface of the one or more adhesive or binder layers of the transfer film, wherein the microstructures are single or multi-layer structures that comprise: voids in a substantially planar surface, wherein the
10 voids are optionally filled or coated with another material; raised areas in a substantially planar surface; or combinations thereof; and then transferring the microstructures from the transfer film onto a surface of the final substrate.

18. The process of claim 17, wherein the transfer film is made up of a carrier film and one or more thermal release adhesive layers on a surface of the carrier film, wherein the one or
15 more thermal release adhesive layers is made up of a plurality of expandable microspheres and one or more pressure sensitive adhesives.

19. The process of claim 18, wherein adhesion between the one or more thermal release adhesive layers and microstructures formed on or transferred to a surface thereof decreases when the one or more thermal release adhesive layers is heated to a temperature
20 higher than about 60 °C.

20. The process of claim 18, wherein the expandable microspheres are polymer microspheres that start expansion and/or foaming when heated to temperatures higher than about 60 °C.

21. The process of claim 18, wherein the one or more thermal release adhesive
25 layers is prepared from a formulation comprising from about 25 to about 99 % by wt. of an energy curable pressure sensitive adhesive formulation, and from about 1 to about 75 % by wt. of expandable microspheres.

22. The process of claim 21, wherein the energy curable pressure sensitive adhesive formulation comprises:

30 from about 5 to about 95 % by wt. of one or more elastomeric oligomers;
from about 1 to about 75 % by wt. of one or more tackifying resins;

from about 0.5 to about 75 % by wt. of one or more reactive monomeric diluents;
and

from about 0.1 to about 15 % by wt. of one or more photoinitiators.

23. The process of claim 18, which comprises: forming the microstructures on a
5 surface of a disposable manufacturing substrate; bringing the formed microstructures into
contact with a surface of the transfer film while applying pressure thereto, thereby activating the
pressure sensitive adhesive in the one or more thermal release adhesive layers of the transfer
film and adhering the microstructures to the surface of the transfer film; stripping away the
disposable manufacturing substrate; applying one or more heat and/or pressure activated
10 adhesives to the microstructures on the transfer film; bringing the adhesive coated
microstructures on the transfer film into contact with a surface of the final substrate while
applying both heat and pressure to the transfer film, thereby causing the microspheres in the
one or more thermal release adhesive layers to expand or foam and deactivate the pressure
sensitive adhesive, allowing transfer of the microstructures onto the surface of the final
15 substrate, while simultaneously activating the adhesive on the microstructures, allowing the
microstructures to adhere to the surface of the final substrate.

24. The process of claim 23, wherein the microstructures are cast in a continuous
process from a microstructured surface having a predesigned pattern of voids and/or raised
areas onto the surface of the disposable manufacturing substrate.

20 25. The process of claim 23, which further comprises applying a coating to the
surface of the disposable manufacturing substrate prior to forming the microstructures on that
surface, wherein the coating is prepared from one or more polymers having low surface energy.

26. The process of claim 25, wherein the one or more polymers having low surface
energy are ultraviolet curable silicone-modified polyacrylates.

25 27. The process of claim 18, which comprises: forming the microstructures on a
surface of the one or more thermal release adhesive layers of the transfer film; applying one or
more heat and/or pressure activated adhesives to the formed microstructures on the transfer
film; bringing the adhesive coated microstructures into contact with a surface of the final
substrate while applying both heat and pressure to the transfer film, thereby causing the
30 microspheres in the one or more thermal release adhesive layers to expand or foam and
deactivate the pressure sensitive adhesive, allowing transfer of the microstructures onto the

surface of the final substrate, while simultaneously activating the adhesive on the microstructures, allowing the microstructures to adhere to the surface of the final substrate.

28. The process of claim 27, wherein the microstructures are cast in a continuous process from a microstructured surface having a predesigned pattern of voids and/or raised areas onto the surface of the one or more thermal release adhesive layers of the transfer film.

29. The process of claim 27, which further comprises applying a coating to the surface of the one or more thermal release adhesive layers of the transfer film prior to forming the microstructures on that surface, wherein the coating is prepared from one or more polymers having low surface energy.

30. The process of claim 29, wherein the one or more polymers having low surface energy are ultraviolet curable silicone-modified polyacrylates.

31. The process of claim 17, wherein the transfer film is made up of a carrier film and one or more cured binder layers on a surface of the carrier film, wherein the one or more cured binder layers is made up of one or more energy curable polyacrylates and a free radical photoinitiator.

32. The process of claim 17, which comprises:

forming the microstructures on a surface of a disposable manufacturing substrate;

applying one or more release coating layers to a surface of the microstructures, the one or more release coating layers conforming to the microstructure surface, and then curing the one or more release coating layers;

applying one or more binder layers to a surface of a carrier film and optionally also to the cured release coated surface of the microstructures, and while these surfaces are in contact with each other, curing the one or more binder layers;

mechanically removing the disposable manufacturing substrate from the microstructures now bonded to the carrier film; and then

transferring the microstructures from the carrier film onto a surface of the final substrate.

33. The process of claim 32, wherein the microstructures are cast in a continuous process from a microstructured surface having a predesigned pattern of voids and/or raised areas onto the surface of the disposable manufacturing substrate.

34. The process of claim 32, wherein the one or more release coating layers is made up of isodecyl acrylate, a free radical photoinitiator, and optionally, isopropyl alcohol.

35. The process of claim 32, which further comprises:

5 applying one or more heat and/or pressure activated adhesives to the microstructures on the carrier film;

bringing the adhesive coated microstructures on the carrier film into contact with a surface of the final substrate;

10 applying both heat and pressure to the carrier film and then lifting the carrier film from the microstructures causing separation between the microstructures and the one or more release coating layers, thereby allowing transfer of the microstructures onto the surface of the final substrate, while simultaneously activating the adhesive on the microstructures, thereby allowing the microstructures to adhere to the surface of the final substrate.

15




FIG. 1

INTERNATIONAL SEARCH REPORT

International application No PCT/US2012/051395

A. CLASSIFICATION OF SUBJECT MATTER INV. B44C1/17 B42D15/0Q ADD.				
According to International Patent Classification (IPC) or to both national classification and IPC				
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) B44C B42D				
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched				
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EPO-Internal , WPI Data				
C. DOCUMENTS CONSIDERED TO BE RELEVANT				
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.		
X	WO 01/53113 A1 (FLEX PRODUCTS INC [US]) 26 July 2001 (2001-07-26)	1,8,17		
Y	abstract figures 1,15,16 page 2, lines 10-19 page 6, line 17 - page 22, line 16 -----	9,18-30		
X	EP 1 354 925 A1 (NITTO DENKO CORP [JP]) 22 October 2003 (2003-10-22)	1-6		
Y	abstract page 1 paragraphs [0026] - [0038], [0085] - [0102] -----	9,18-30		
X	EP 1 002 640 A1 (AGRA VADEKO INC [CA]) 24 May 2000 (2000-05-24)	1,8,11, 14,17, 32,33		
	the whole document ----- - / -			
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none;"><input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C.</td> <td style="width: 50%; border: none;"><input checked="" type="checkbox"/> See patent family annex.</td> </tr> </table>			<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C.	<input checked="" type="checkbox"/> See patent family annex.
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C.	<input checked="" type="checkbox"/> See patent family annex.			
* Special categories of cited documents :				
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention			
"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone			
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art			
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family			
"P" document published prior to the international filing date but later than the priority date claimed				
Date of the actual completion of the international search	Date of mailing of the international search report			
5 April 2013	12/04/2013			
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Guidoin, M			

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2012/051395

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2011/017498 AI (LAUFFER JOHN M [US] ET AL) 27 January 2011 (2011-01-27) the whole document -----	1,7,8, 10, 13, 15, 17, 31-34

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2012/051395

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
wo 0153113	AI	26-07-2001	AU 1194901 A 31-07 -2001
			AU 2001211949 B2 18-08 -2005
			CA 2397806 AI 26- 07-2001
			CN 1423598 A 11-06 -2003
			CN 1666888 A 14-09 -2005
			EP 1252027 AI 30- 10-2002
			EP 1762398 A2 14-03 -2007
			EP 1849620 A2 31- 10-2007
			EP 1849621 A2 31-10 -2007
			JP 2003520986 A 08- 07-2003
			KR 20070007975 A 16-01 -2007
			US 2004101676 AI 27- 05-2004
			US 2005128543 AI 16-06 -2005
			US 2007183047 AI 09- 08-2007
			WO 0153113 AI 26-07 -2001
EP 1354925	AI	22-10-2003	CN 1451707 A 29-10-2003
			DE 60304763 T2 14-09-2006
			EP 1354925 AI 22-10-2003
			JP 3853247 B2 06-12-2006
			JP 2003306653 A 31-10-2003
			SG 107634 AI 29-12-2004
			TW 1255844 B 01-06-2006
EP 1002640	AI	24-05-2000	AT 267696 T 15--06--2004
			AU 5945699 A 25--05--2000
			CA 2290019 AI 20--05--2000
			DE 69917565 DI 01--07--2004
			DE 69917565 T2 09--06--2005
			EP 1002640 AI 24--05--2000
			GB 2343864 A 24--05--2000
			US 6447630 BI 10--09--2002
US 2011017498	AI	27-01-2011	NONE