



(51) International Patent Classification:  
*G09B 23/30* (2006.01)

(21) International Application Number:  
PCT/US2017/029281

(22) International Filing Date:  
25 April 2017 (25.04.2017)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
62/327,925 26 April 2016 (26.04.2016) US

(71) Applicant: **APPLIED MEDICAL RESOURCES CORPORATION** [US/US]; 22872 Avenida Empresa, Rancho Santa Margarita, CA 92688 (US).

(72) Inventor: **HOFSTETTER, Gregory, K.**; 22872 Avenida Empresa, Rancho Santa Margarita, CA 92688 (US).

(74) Agent: **LUKAS, Rimas, T.**; Applied Medical Resources Corporation, 22872 Avenida Empresa, Rancho Santa Margarita, CA 92688 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,

DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: RESIDUAL STRESS FEATURES IN ORGAN MODELS




**FIG. 15**

(57) Abstract: Simulated tissue structures and methods of making them are disclosed. An elastic first material is placed in tension. An elastic second material is adhered to the first material while the first material is in tension. The adhered second material and the first material in tension forms a first shape of the simulated tissue structure. Tension on the first material is released. In releasing the tension of the first material, a force is exerted on the adhered second material bring the combination of the first material and the second material into a second shape. The first shape is maintained by a mold or mandrel and the second shape is the desired shape of the simulated tissue structure.



## RESIDUAL STRESS FEATURES IN ORGAN MODELS

### Cross-Reference to Related Applications

**[0001]** This patent application claims priority to and benefit of U.S. Provisional Patent Application Serial No. 62/327,925 entitled “Residual stress features in organ models” filed on April 26, 2016 incorporated herein by reference in its entirety.

### Field of the Invention

**[0002]** This invention relates to surgical training tools, and in particular, to simulated tissue structures and organ models for teaching and practicing surgical procedures and methods for making them.

### Background of the Invention

**[0003]** A highly-skilled operation technique is required of surgeons, in general, and, in particular, for performing laparoscopic surgical procedures. In laparoscopic surgery, several small incisions are made in the abdomen for the insertion of trocars or small cylindrical tubes approximately 5 to 10 millimeters in diameter through which surgical instruments and a laparoscope are placed into the abdominal cavity. The laparoscope illuminates the surgical field and sends a magnified image from inside the body to a video monitor giving the surgeon a close-up view of organs and tissues. The surgeon performs the operation by manipulating the surgical instruments placed through the trocars while watching the live video feed on a monitor. Because the surgeon does not observe the organs and tissues directly with the naked eye, visual information is obtained by a two-dimensional image on a monitor instead of a three-dimensional observation. The loss of information when presenting a three-dimensional environment via a two-dimensional image is substantial. In particular, depth perception is reduced when viewing a two-dimensional image as a guide for manipulating instruments in three dimensions.

**[0004]** Furthermore, because the trocars are inserted through small incisions and rest against the abdominal wall, the manipulation of instruments is restricted by the abdominal wall which has a fulcrum effect on the instrument. The

fulcrum effect defines a point of angulation that constrains the instrument to limited motion. Also, hand motion in one linear direction causes magnified tip motion in the opposite direction. Not only is the instrument motion viewed on the screen in the opposite direction, but also, the magnified tip motion is dependent on the fraction of the instrument length above the abdominal wall. This lever effect not only magnifies motion but also magnifies tool tip forces that are reflected to the user. Hence, the operation of an instrument with a fulcrum requires intentional learning and practice and is not intuitively obvious.

**[0005]** Also, surgical instruments are placed through ports having seals which induce a stick-slip friction caused by the reversal of tool directions. For example, stick-slip friction may arise from the reversal of tool directions when, for example, quickly changing from pulling to pushing on tissue. During such motion, rubber parts of the seals rub against the tool shaft causing friction or movement of the instrument with the seal before the friction is overcome and the instrument slides relative to the seal. Stick-slip friction, or oil-canning, at the seal and instrument interface creates a non-linear force.

**[0006]** Hand-eye coordination skills are necessary and must be practiced in order to correlate hand motion with tool tip motion especially via observation on a video monitor. Also, in laparoscopic surgery, tactile sensation through the tool is diminished. Because haptics are reduced or distorted, the surgeon must develop a set of core haptic skills that underlie proficient laparoscopic surgery. The acquisition of all of these skills is one of the main challenges in laparoscopic training and the present invention is aimed at improving systems and methods for laparoscopic skills training and technique performance.

**[0007]** Not only do new practitioners have to learn laparoscopic skills, but also, experienced laparoscopic surgeons seek to polish old skills as well as to learn and practice new surgical techniques that are unique to newly introduced surgical procedures. While training can be acquired in the operating room, interest in devising faster and more efficient training methods, preferably outside the operating room has increased. Surgeons that attain a reasonable level of skills outside the operating room are better prepared when they enter the operating room and, thereby, valuable

operating room experience can thus be optimized, lowering the risk to patients and reducing costs. To acquaint surgeons with basic surgical skills outside the operating room, various simulators have been devised and tested. An example of a surgical simulator is the SIMSEI® laparoscopic trainer manufactured by Applied Medical Resources Corporation in California and described in U.S. Patent No. 8,764,452 incorporated by reference herein in its entirety. The SIMSEI® laparoscopic trainer employs three-dimensional live or fake organs inside a simulated abdominal cavity that is obscured from direct observation by the user.

**[0008]** Use of a live human or animal organ in a laparoscopic simulator requires freshness for the internal organ. Also, live organs require sanitary arrangements to be made to protect the trainee from being infected by germs and the like. Additional costs are also required for the sanitary management and sterilization of instruments which are used after the exercise of a surgical operation is performed. Also, the used live organ must be properly disposed. Furthermore, the smell of a live organ can be foul and may distract the trainee from focusing on techniques and skills. Therefore, artificial organs and tissues that simulate live organs and tissues are desirable so that live organs can be replaced in surgical training.

**[0009]** Many artificial organs have been used in place of live human or animal organs in surgical training. Typically, these artificial organ models are made of silicone, urethane elastomer, styrene elastomer or the like. These artificial organs must respond properly when incised, manipulated or sutured, for example, and provide the same feeling and tactile characteristics as in real life surgery. However, many artificial organs lack certain properties and realism that are necessary to bridge the gap between artificial and real organs. Furthermore, the degree of realism must be targeting to provide means for teaching the skills that are peculiar to laparoscopic skills training. As such, certain realisms may be more important in a laparoscopic environment when compared to an open surgical environment. Therefore, there is a need for artificial organs and tissues and, in particular, for artificial organs and tissues that are targeted for laparoscopic skills training that may also be used for non-laparoscopic skills training.

### Summary of the Invention

**[0010]** According to one aspect of the invention, a method of making a simulated tissue structure is provided. The method includes the step of providing a mandrel having a first end, a second end, a longitudinal axis and an outer diameter. The method includes the step of providing at least one elastic ring having a central aperture. The at least one elastic ring has a relaxed diameter that is smaller than the outer diameter of the mandrel. The method includes the step of stretching the at least one elastic ring onto the mandrel in a direction traverse to the longitudinal axis of the mandrel into a position in which the mandrel is located inside the central aperture and the at least one ring is expanded around the outer diameter of the mandrel. The method includes the step of applying a layer of uncured silicone onto the mandrel and the at least one stretched elastic ring. The method includes the step of curing the layer to adhere the layer to the elastic rings while the elastic ring is expanded. The method includes the step of removing the layer and the elastic rings after the step of curing the layer. The method includes the step of allowing the elastic ring to return toward its relaxed diameter.

**[0011]** According to another aspect of the invention, a method of making a simulated tissue structure is provided. The method includes the step of providing at least one elastic strip. The strip has a length and a width. The relaxed length is longer than the width. The method includes the step of stretching the elastic strip to elongate its length. The method includes the step of applying a layer of uncured silicone to the elastic strip while the strip is elongated. The method includes the step of curing the layer to adhere the layer to the stretched elastic strip. The method includes the step of releasing the elastic strip from being stretched and elongated after the step of curing the layer.

**[0012]** According to another aspect of the invention, a method of making a simulated tissue structure is provided. The method includes the step of providing at least one elastic sheet. The sheet has a length along a longitudinal axis, a width along a lateral axis and a thickness defined between an upper surface and a lower surface. The method includes the step of stretching the elastic sheet. The method includes the step of applying a layer of uncured silicone to the elastic sheet while the sheet is

maintained in a stretched position. The method includes the step of curing the layer to adhere the layer to the stretched elastic strip. The method includes the step of relaxing the stretched elastic strip after the step of curing the layer.

**[0013]** According to another aspect of the invention, a method for making a simulated tissue structure is provided. The method includes the step of providing an elastic first material having a relaxed state having an unstretched width and an unstretched length. The method includes the step of stretching the first material. The method includes the step of providing a second material. The method includes the step of adhering the second material to the first material while the first material is stretched and while the first material and second material are held in a first shape. The method includes the step of allowing the first material to return toward the relaxed state to form a simulated tissue structure having a second shape that is different from the first shape.

**[0014]** According to another aspect of the invention, a simulated tissue structure is provided. The simulated tissue structure includes a first layer of elastic material having a length along a longitudinal axis and a width along a lateral axis. The simulated tissue structure includes a second layer of elastic material connected to the first layer such that the first layer exerts a compression force on the second layer along at least one of the longitudinal axis and the lateral axis when in a first shape. The compression force moves the first layer and the second layer into a second shape defined by the compression force being in equilibrium with the second layer; the second shape being an anatomical shape.

#### Brief Description of the Drawings

**[0015]** FIG. 1 is a top perspective view of a mandrel and a plurality of unstretched silicone rings according to the present invention.

**[0016]** FIG. 2 is a top perspective view of a plurality of silicone rings stretched around a mandrel according to the present invention.

**[0017]** FIG. 3 is a top perspective view of a plurality of silicone rings stretched around a mandrel and overlaid with a silicone layer according to the present invention.

**[0018]** FIG. 4 is a top perspective view of a simulated tissue structure according to the present invention.

**[0019]** FIG. 5 is a top perspective view of a mandrel and unstretched silicone ring according to the present invention.

**[0020]** FIG. 6 is a top perspective view of a silicone ring stretched around one end of a mandrel according to the present invention.

**[0021]** FIG. 7 is a top perspective view of a silicone ring stretched around a mandrel and overlaid with a silicone layer according to the present invention.

**[0022]** FIG. 8 is a top perspective view of a simulated tissue structure according to the present invention.

**[0023]** FIG. 9 is a top perspective view of an unstretched silicone strip adjacent to a mold according to the present invention.

**[0024]** FIG. 10 is a top perspective view of a stretched silicone strip clipped to a mold according to the present invention.

**[0025]** FIG. 11 is a top perspective view of a stretched silicone strip clipped to a mold overlaid with a layer of silicone according to the present invention.

**[0026]** FIG. 12 a top perspective view of a simulated tissue structure according to the present invention.

**[0027]** FIG. 13 is a top perspective view of a mandrel, a plurality of unstretched silicone rings, and an unstretched silicone strip according to the present invention.

**[0028]** FIG. 14 is a top perspective view of a plurality of silicone rings stretched around a mandrel and a strip stretched alongside the mandrel overlaid with a layer of silicone according to the present invention.

**[0029]** FIG. 15 is a top perspective view of a simulated tissue structure according to the present invention.

**[0030]** FIG. 16 is a top perspective of view of a mandrel and unstretched, patterned sheet according to the present invention.

**[0031]** FIG. 17 is a top perspective view of a mandrel and a stretched, patterned sheet according to the present invention.

**[0032]** FIG. 18 is a top perspective view of a mandrel partially wrapped by a stretched, patterned sheet according to the present invention.

**[0033]** FIG. 19 is a top perspective view of a mandrel wrapped by a stretched, patterned sheet overlaid with a layer of silicone according to the present invention.

**[0034]** FIG. 20 is a top perspective view of a simulated tissue structure according to the present invention.

**[0035]** FIG. 21 is a top perspective view of a strip of elastic material overlaid with a layer of silicone according to the present invention.

**[0036]** FIG. 22 is a top perspective view of an elongate vessel placed on a strip of elastic material in spiral fashion while stretched in the direction of the arrows according to the present invention.

**[0037]** FIG. 23 is a top perspective view of a simulated tissue structure of FIG. 22 in an equilibrium state according to the present invention.

**[0038]** FIG. 24 is top view of a sheet of elastic material with a hole in a relaxed condition according to the present invention.

**[0039]** FIG. 25 is a top view of a sheet in a stretched condition with a hole covered with a layer of silicone cured to the sheet while the sheet is stretched according to the present invention.

**[0040]** FIG. 26 is a top perspective view of a simulated tissue structure of FIG. 25 in equilibrium, unstretched state according to the present invention.

**[0041]** FIG. 27 is a top view of a sheet in a stretched condition with a layer of silicone cured to the sheet while the sheet is stretched in the direction of the arrows according to the present invention.

**[0042]** FIG. 28 is a top perspective view of a simulated tissue structure of FIG. 25 in an equilibrium, unstretched condition according to the present invention.

**[0043]** FIG. 29 is a top view of a layer of mesh material according to the present invention.

**[0044]** FIG. 30 is a top view of a plurality of strips of mesh material spaced apart, stretched in the direction of the arrows and a layer of silicone cured to the strips while the strips are stretched according to the present invention.

**[0045]** FIG. 31 is a top view of a simulated tissue structure according to the present invention.

#### Detailed Description of the Invention

**[0046]** The following description is provided to enable any person skilled in the art to make and use the surgical tools and perform the methods described herein and sets forth the best modes contemplated by the inventors of carrying out their inventions. Various modifications, however, will remain apparent to those skilled in the art. It is contemplated that these modifications are within the scope of the present disclosure. Different embodiments or aspects of such embodiments may be shown in various figures and described throughout the specification. However, it should be noted that although shown or described separately each embodiment and aspects thereof may be combined with one or more of the other embodiments and aspects thereof unless expressly stated otherwise. It is merely for easing readability of the specification that each combination is not expressly set forth.

**[0047]** There are multiple anatomical examples within the human body where there are valves that are able to contract, where tissue planes come together and taper, or tissue planes which are under tension in their normal state. Additionally, there are anatomical structures within the body that stretch preferentially in a certain direction and not another. All of these examples are difficult to simulate while creating organ models using current manufacturing techniques.

**[0048]** According to the present invention, the process of manufacturing such a simulated tissue structure 10 generally includes providing a pre-made silicone piece or sheet. The piece of silicone is stretched and held in place in the stretched configuration. While the sheet is stretched, uncured silicone liquid is applied over the stretched silicone piece and allowed to cure to create a layer. When the wet silicone is finished curing, the final product is removed from the mold or mandrel. The premade stretched silicone relaxes, tending toward its unstretched configuration which changes the shape of the final silicone object including the layer. In an alternative variation, a piece or sheet of elastic mesh is employed instead of pre-made piece or sheet of silicone and uncured silicone is applied over the stretched piece of elastic mesh and

allowed to cure to create a layer. When mesh is used, the final shape of the simulated tissue structure is less dramatic compared to the stretched silicone as wet silicone fills the interstices of the mesh reducing the degree of retraction. However, the stretch characteristics resulting in the final simulated tissue structure can be advantageously tailored to limit stretch in one direction while allowing full stretch in another direction. In yet another variation, instead of applying uncured silicone to the stretched piece of silicone or stretched piece of mesh, a piece of cured silicone that is at rest and not stretched is glued in place to the stretched piece.

**[0049]** With particular reference to FIGs. 1-4, in one variation of this method, silicone ring-shaped bands 12 are placed on a cylindrical mandrel 14. The pre-made, silicone ring-shaped bands 12 and mandrel 14 are provided as shown in FIG. 1. The mandrel 14 has an outer diameter that is larger than the resting, unstressed diameter of the bands 12. Before the mandrel 14 is placed in the mandrel-turning device, a number of pre-made, cured, silicone bands 12 are stretched over the mandrel 14 and spread out evenly along its length as shown in FIG. 2. Then, a layer of uncured silicone 16 is painted on the mandrel 14 and over the premade stretched silicone rings 12 as shown in FIG. 3 while the mandrel 14 is rotating. The silicone layer 16 is allowed to cure. Afterwards, the simulated tissue structure 10 is removed from the mandrel 14. When multiple bands 12 are stretched over a mandrel 14 and then removed from the mandrel 14 along with the cured silicone layer 16, the bands 12 will tend to return to their normal, reduced resting shape and diameter. The outer layer 16 is cured to the bands 12 interconnecting them into a unitary structure 10 as shown in FIG. 4. The resulting unitary simulated tissue structure 10 has a plurality of locations 18 of reduced diameter in the same locations of the bands 12 as shown in FIG. 4. The simulated tissue structure 10 will be substantially cylindrical, tubular in shape with a central lumen extending along a longitudinal axis between an opening at the proximal end and an opening at the distal end. The simulated tissue structure 10 in the reduced-diameter locations 18 forms an undulating silicone tube when removed from the mandrel 14 that simulates the look and feel of a real colon. In this way, this method can be used for creating simulated valves of Houston, for example, within the colon.

**[0050]** In another variation of this method, simulated tissue structures 10 having simulated natural orifices 20 through which simulated surgery is practiced are created. For example, to make a simulated natural orifice 20, such as a simulated anus, a premade silicone ring-shaped band 12 and mandrel 14 are provided as shown in FIG. 5. The mandrel 14 has an outer diameter that is greater than the unstretched, resting inner diameter of the band 12 in the desired location along the mandrel 14 where the simulated natural orifice 20 is desired to be created. The band 12 is stretched around that desired location of the mandrel, in this case, around one end of a mandrel 14 as shown in FIG. 6, and a layer 16 of wet silicone is painted onto the mandrel 14 and band 12 as shown in FIG. 7. The silicone layer 16 is allowed to cure and then the construct is removed from the mandrel 14. As a result of the layer 16 curing onto the stretched cured silicone band 12, the location of the band 12, the end with the premade silicone band 12 tends to return to its normal unstretched diameter creating an area location 18 of reduced diameter of the simulated tissue structure 10 compared to the surrounding outer layer 16 of cured silicone as shown in FIG. 8. In a variation of this method, the formed shrunken end with a reduced diameter may then be stretched again, this time, over a central peg on a trans-anal adapter mold (not shown). Another layer of silicone is then applied to the stretched end by pouring silicone into the mold and allowed to attach to the band and first layer. Once cured, the pre-stretched construct is removed from the peg and the band again shrinks back to its original size.

**[0051]** In another variation of this method, a strip 22 of cured silicone having a resting length  $x$  is provided as shown in FIG. 9. The strip 22 of silicone is stretched to length  $y$  and held in place at length  $y$  which is greater than length  $x$  as shown in FIG. 10. The strip 22 can be attached to a mold 24, for example, or on a mandrel 14 by some means such as clips 26 as shown in FIG. 10. A layer 16 of wet, uncured silicone is applied over and around the stretched strip 22 as shown in FIG. 11. The uncured silicone layer 16 is allowed to cure. Removing the construct from the mold 24 or mandrel 14 entails releasing the force keeping the strip 22 stretched. As a result, the strip 22 will tend to return toward its normal relaxed length,  $x$ , moving, contracting the cured layer 16 of silicone surrounding it creating wrinkles and bunching around the strip 22 as shown in FIG. 12. When the work-piece is removed from the mold or

mandrel, the stretched strip will relax, causing bunching of the newer, now cured silicone layer 16 as shown in FIG. 12.

**[0052]** Turning now to FIGs. 13-15, a combination of one or more methods may be employed. For example, bands 12 together with a strip 22 may be employed over a mandrel 14. One or more bands 12, a mandrel 14 and at least one strip 22 are provided as shown in FIG. 13. The bands 12 have a resting inner diameter that is smaller than the outer diameter of the mandrel 14. The strip 22 has a resting length,  $x$ , and is stretched to length,  $y$ , and held in place along the mandrel 14 as shown in FIG. 14. The circular, hoop-shaped bands 12 are stretched and placed over the strip 22 and mandrel as shown in FIG. 14. Alternatively, the bands 12 are stretched and placed between the strip 22 and mandrel 14. An outer layer 16 of uncured, wet silicone is applied to the one or more bands 12, one or more strip 22 and onto the mandrel 14 as shown in FIG. 14 and allowed to cure. When the outer layer has finished curing, the construct is removed from the mandrel 14 and the resulting simulated tissue structure 10 is shown in FIG. 15. As can be seen in FIG. 15, when the cured construct is removed, the bands 12 will tend to return to their resting, normal diameter/configuration pulling the cured silicone layer 16 inwardly to create a tubular structure with valleys or tubular structure with reduced radial dimensions in the location of the rings 12. Also, the stretched strip 22 will tend to return to its normal, resting dimension and shorten bringing the cured silicone layer 16 into contraction along the length of the strip 22, thereby, in some cases, as show in FIG. 14, imparting the resulting tissue structure 10 with a natural curvature having a concavity in the outer layer 16 on the side with the strip 22.

**[0053]** Turning now to FIGs 16-20, there is shown another variation of making a simulated tissue structure 10 in which a patterned strip 22 is employed over a mandrel 14. The patterned strip 22 is a piece of cured silicone and/or mesh material that is cut into a desired pattern/shape. The mesh if employed is stretchable mesh. In the variation shown in FIGs. 16-20, the pattern strip 22 has a repeating H-like shape having a longitudinal spine intersected by lateral strips. The pattern strip 22 is stretched longitudinally along the mandrel 14 in the direction of the arrows in FIG. 17. The pattern strip 22 is wrapped around the mandrel 14 while stretched as shown in FIG. 18 and

adhered in position on the mandrel 14 with adhesive or other fastener. Then a layer 16 of uncured silicone is applied over the stretched pattern strip 22 and over the mandrel 14 and allowed to cure. When the layer 16 is cured, the construct is removed from the mandrel 14. The cured layer 16 is bonded to the pattern strip 22 and the stretched pattern strip 22 and/or mesh naturally relaxes and returns to an unstretched, equilibrium configuration resulting in the unique luminal simulated tissue structure 10 shown in FIG. 20 having a directional curvature imparted by the spine of the pattern strip 16 with bulbous portions formed between the lateral strips where openings were formed by the spaces between the lateral strips.

**[0054]** Turning now to FIGs. 21-23, another variation for forming a simulated tissue structure 10 is shown. A thin strip 22 of cured silicone is stretched along its longitudinal axis as shown by the arrows in FIG. 21. While in the stretched position, a thin layer 16 of uncured silicone is applied to the surface of the stretched strip 22. While the layer 16 is still wet, a solid or hollow tubular vessel 28 made of silicone is placed on the stretched strip 22. In one variation, the vessel 28 is placed in spiral fashion around the stretched strip 22 as shown in FIG. 22. The vessel 28 is wrapped around without tension in the vessel 28 and the wet layer 16 of silicone is allowed to cure to adhere the vessel 28. When cured, the final simulated tissue structure 10 is a spiraled, tortuous vessel shown in FIG. 23.

**[0055]** Turning now to FIGs. 24-26, another variation for forming a simulated tissue structure 10 is shown. A pre-made sheet 30 of silicone is provided. A hole 32 is cut out of the sheet 30 as shown in FIG. 24. The sheet 30 with the hole is uniformly stretched as shown by the arrows in FIG. 25. The hole 32 may be any suitable size and shape. A layer 16 of uncured silicone is applied to over the stretched hole 32 and allowed to cure as shown in FIG. 25. Alternatively, a pre-made, cured silicone patch 36 that is slightly larger than the stretched hole 32 and having a complementary shape is glued in place on the stretched hole 32 as shown in FIG. 25. In both cases, when the sheet 30 is released and removed from the staging platform, the sheet 30 returns to an unstretched equilibrium position and now has a dome feature formed by the cured silicone layer 16 in an otherwise flat sheet 30. The domed feature of layer 16 extends upwardly from the relaxed flat sheet 30 as shown in FIG. 26.

**[0056]** Turning now to FIGs. 27-28, in another variation, the flat, cured silicone sheet 30 does not have a hole in it. The sheet 30 without a hole is uniformly stretched in the direction of the arrows in FIG. 27 and an uncured silicone layer 16 is applied on one or more areas of the sheet 30. Areas on the sheet 30 that have wet silicone applied and cured will curl away from the newly added silicone layer 16, that is, in the areas of applied silicone layer 16, the side of the construct having the layer 16 of newly applied silicone will be convex and the side of the sheet 30 that was stretched will be concave. This technique is useful to tailor the shape of otherwise flat sheets that are used to create simulated anatomy particularly in areas where thin membranous layers join to other structures.

**[0057]** With reference to FIGs. 29-31, another variation of forming a simulated tissue structure 10 according to the present invention is shown. As mentioned previously, when mesh is employed and stretched and an uncured layer of silicone is applied to the stretched mesh, the wet silicone enters the interstices of the mesh and the qualities the simulated tissue structure 10 arising from the retraction of the mesh material are less pronounced relative to a non-porous material. However, a mesh-based simulated tissue structure 10 provides advantageous tactile properties. A mesh layer 38 is provided and by stretching the mesh layer 38 to its elastic limit in only one direction, while leaving the mesh layer 38 relaxed in the other direction, simulated anatomical structures that stretch preferentially in one direction over another can be created. This application of a mesh layer 38 in a simulated tissue structure wherein the mesh layer 38 is stretched in one direction before the application of a layer 16 of uncured silicone can be used to make sheets that stretch preferentially or other simulated anatomical structures such as simulated tendons that are flexible enough to bend but do not readily stretch. Another example of this would be incorporating a strip of mesh into the sidewall of a simulated bowel so that when it is insufflated, the simulated bowel will expand circumferentially but not longitudinally. The mesh material is an interwoven or intertwined braid or network of grouped or ungrouped interlocking filaments creating an open texture structure with small substantially uniform windows/interstices. The braid of the mesh such that two intersecting systems of filamentary elements are interlaced so that each filamentary element of one system is

alternatively guided over and under each filamentary element of the other system. Such a pattern of the braid is referred to as a plain weave. The number of intersections within a unit of length of measure defines the density of the weave with more intersections making the weave tighter and the size of the windows becomes smaller. Because of the weave arrangement and density, the mesh material can stretch along the lateral axis as the bands can slide over and relative to each other making the windows larger in size. Widening of the mesh when stretched laterally reduces the length of the mesh. The mesh material can also stretch along the longitudinal axis of the mesh. Lengthening of the mesh when stretched longitudinally reduces the width of the mesh layer. The mesh material may have a dominant direction of stretch depending on the shape and direction of the weave in which the mesh material stretches a greater distance relative to an inferior stretch direction which is generally perpendicular to the dominant stretch direction. FIG. 29 illustrates a sheet 38 of mesh material having a plurality of filaments forming a weave having a primary dominant stretch direction 40 and a secondary inferior stretch direction 42. The mesh sheet 38 may be cut into strips 44. The strips 44 are spaced apart and then stretched in the direction of the secondary stretch direction 42 to a maximum elongation in the secondary stretch direction 42. The mesh strips 44 are maintained at the maximum elongation and a layer 16 of uncured silicone is applied over the mesh strips 44 as shown in FIG. 30. The silicone layer 16 is allowed to cure while the mesh strips 44 remain stretched. After the silicone layer 16 has cured the mesh strips 44 and silicone layer 16 is trimmed as desired. With reference to FIGs. 29-31, when the strips 44 are released, the resulting simulated tissue structure 10 is very stretchy in the primary dominant stretch direction 40 and resists stretching in the secondary inferior stretch direction while having a minor insubstantial effect on the final shape of the structure 10 but has a major effect on the tactile qualities such as stretch.

**[0058]** The above-mentioned methods involve carefully combining uncured silicone with pre-made and stretched silicone or mesh material, which results in a more lifelike feel and appearance of the simulated anatomy. The degree of the effects produced by the resultant simulated tissue structure can be controlled by altering the thickness and durometer of both the pre-made stretched silicone pieces and the wet

silicone being used. The larger the difference in thickness and durometer between the cured and wet silicone being use, the greater and more dramatic the effects will be in the resulting simulated tissue structure.

**[0059]** All of these techniques are ways of intentionally incorporating residual stress into simulated anatomy. There are many examples in the human body with structures that contain residual stress, and these techniques aim to mimic these real tissue structures in terms of look, feel, and manufacturability.

**[0060]** Currently, many organ structures are made in several pieces in order to reduce the complexity of the molding. These pieces are then glued together in order to get a desired curved shape. Advantageously, through the use of pre-stretched pieces in order to create residual stresses according to the present invention, less complex molds can be used. Additionally, in order to create curved simulated intestines, a straight tube is currently “kinked” in order to take the desired path. Advantageously, residual stresses of the present invention can help create more realistic curves without collapsing tubes through kinking and still allow for easy demolding.

**[0061]** It is understood that various modifications may be made to the embodiments disclosed herein. Therefore, the above description should not be construed as limiting, but merely as exemplifications of preferred embodiments. Those skilled in the art will envision other modifications within the scope and spirit of the present disclosure.

## Claims

We claim:

1. A method of making a simulated tissue structure comprising the steps of:  
providing a mandrel having a first end, a second end, a longitudinal axis and an outer diameter;  
providing at least one elastic ring having a central aperture; the at least one elastic ring having a relaxed diameter smaller than the outer diameter of the mandrel;  
stretching the at least one elastic ring onto the mandrel traverse to the longitudinal axis into a position in which the mandrel is located inside the central aperture and the at least one ring is expanded around the outer diameter of the mandrel;  
applying a layer of uncured silicone onto the mandrel and the at least one stretched elastic ring;  
curing the layer to adhere the layer to the elastic rings while the elastic ring is expanded;  
removing the layer and the elastic rings after the step of curing the layer; and  
allowing the elastic ring to return toward its relaxed diameter.
2. The method of any one of the previous claims wherein the elastic rings are made of cured silicone.
3. The method of any one of the previous claims wherein the elastic rings are made of mesh.
4. The method of any one of the previous claims wherein multiple elastic rings are spaced apart along the longitudinal axis.
5. The method of any one of the previous claims wherein the step of applying a layer includes forming a lumen with the layer having at least one opening at one of the first end and the second end.

6. The method of any one of the previous claims further including the step of:  
placing one elastic ring proximal to the opening.
7. The method of any one of the previous claims further including the steps of:  
providing an elastic strip; the strip having a length and a width; the relaxed length of the strip being longer than the width of the strip;  
stretching the elastic strip to increase the length;  
placing the strip in juxtaposition with the mandrel; and  
wherein the step of applying a layer includes applying the layer to the elastic strip while the strip is stretched; and  
wherein the step of removing includes removing the elastic strip; and  
wherein the step of curing includes curing the layer to adhere to the elastic strip while the strip is stretched.
8. The method of any one of the previous claims wherein the step of placing the strip includes placing the strip under the at least one elastic ring such that the strip is between the mandrel and the at least one ring.
9. A method of making a simulated tissue structure comprising the steps of:  
providing at least one elastic strip; the strip having a length and a width; the relaxed length being longer than the width;  
stretching the elastic strip to elongate its length;  
applying a layer of uncured silicone to the elastic strip while the strip is elongated;  
curing the layer to adhere the layer to the stretched elastic strip; and  
releasing the elastic strip from being stretched and elongated after the step of curing the layer.
10. The method of any one of the previous claims further including the steps of:

providing a mandrel having a first end, a second end, a longitudinal axis and an outer diameter;

placing the strip in juxtaposition with the mandrel; and

removing the layer and the elastic strip after the step of curing the layer;

wherein the step of applying a layer includes applying the layer to the mandrel.

11. The method of any one of the previous claims wherein the step of placing the strip includes placing the length of the strip along the longitudinal axis of the mandrel.

12. The method of any one of the previous claims wherein the step of providing a mandrel includes providing a mandrel having a substantially cylindrical shape.

13. The method of any one of the previous claims further including the steps of:  
providing an elongate cylindrical vessel;  
applying the vessel to the layer of uncured silicone before the step of curing the layer; and  
curing the layer to adhere the vessel to the elastic strip.

14. The method of any one of the previous claims wherein the elastic strip is made of silicone and mesh.

15. The method of any one of the previous claims wherein the elastic strip is made of cured silicone.

16. The method of any one of the previous claims wherein the elastic strip is made of mesh.

17. The method of any one of the previous claims wherein the mesh has a dominant stretch direction and an inferior stretch direction; the mesh being stretchable a greater distance in the dominant stretch direction relative to the inferior stretch direction;

wherein the step of stretching the elastic strip includes stretching the elastic strip along the inferior stretch direction.

18. The method of any one of the previous claims further including the step of arranging a plurality of elastic strips such that the elastic strips are parallel and spaced apart from each other.

19. A method of making a simulated tissue structure comprising the steps of:  
providing at least one elastic sheet; the sheet having a length along a longitudinal axis, a width along a lateral axis and a thickness defined between an upper surface and a lower surface;  
stretching the elastic sheet;  
applying a layer of uncured silicone to the elastic sheet while stretched;  
curing the layer to adhere the layer to the stretched elastic strip; and  
relaxing the stretched elastic strip after the step of curing the layer.

20. The method of any one of the previous claims further including the step of forming a hole in the elastic sheet extending between the top surface and the bottom surface prior to the step of stretching the elastic sheet and prior to the step of applying a layer of uncured silicone.

21. The method of any one of the previous claims wherein the step of applying a layer includes applying a layer to cover the hole.

22. The method of any one of the previous claims wherein the elastic sheet is made of silicone.

23. The method of any one of the previous claims wherein the elastic sheet is made of mesh.

24. The method of any one of the previous claims wherein the elastic sheet is made of silicone and mesh.
25. The method of any one of the previous claims wherein the elastic sheet is cut to form a pattern.
26. The method of any one of the previous claims wherein the step of stretching the elastic sheet includes stretching the elastic sheet along the longitudinal axis and the lateral axis.
27. The method of any one of the previous claims further including the steps of:  
providing a mandrel;  
placing the elastic sheet onto the mandrel; and  
removing the layer and elastic sheet after the step of curing the layer  
wherein the step of applying the layer includes applying the layer to the mandrel.
28. The method of any one of the previous claims wherein the mandrel is substantially cylindrical.
29. The method of any one of the previous claims wherein the pattern includes at least one spine along the longitudinal axis and at least one lateral strip along the lateral axis.
30. The method of any one of the previous claims wherein each lateral strip includes two ends and further including the steps of:  
wrapping the lateral ends around the mandrel; and  
adhering the lateral ends together.
31. A simulated tissue structure obtained by the method of claim 1.

32. The simulated tissue structure of claim 31 wherein the simulated tissue structure is a simulated bowel.
33. The simulated tissue structure obtained by the method of claim 9.
34. The simulated tissue structure of claim 33 wherein the simulated tissue structure is a simulated bowel.
35. A method of making a simulated tissue structure comprising the steps of:  
providing an elastic first material having a relaxed state having an unstretched width and an unstretched length;  
stretching the first material;  
providing a second material;  
adhering the second material to the first material while the first material is stretched and while the first material and second material are held in a first shape;  
allowing the first material to return toward the relaxed state to form a simulated tissue structure having a second shape that is different from the first shape.
36. The method of any one of the previous claims wherein the second material is uncured silicone and wherein the step of adhering the second material to the first material includes the step of curing the second material onto the first material.
37. The method any one of the previous claims wherein when in the second shape, the second material is stretched by the first material.
38. The method of any one of the previous claims wherein the first material has a first durometer and the second material has a second durometer that is substantially the same as the first durometer.
39. A simulated tissue structure obtained by the method of claim 35.

40. The method of any one of the previous claims further including the step of embedding the first material inside the second material.

41. The method of any one of the previous claims wherein the second material is larger than the first material.

42. The method of any one of the previous claims further including the step of placing the first material and the second material on a mold or mandrel that defines the first shape.

43. The method of any one of the previous claims further including the step of removing the first material and the second material from the mold or mandrel to define the second shape; the second shape being the shape of the simulated tissue structure.

44. A simulated tissue structure comprising:

a first layer of elastic material having a length along a longitudinal axis and a width along a lateral axis;

a second layer of elastic material connected to the first layer such that the first layer exerts a compression force on the second layer along at least one of the longitudinal axis and the lateral axis when in a first shape; the compression force moving the first layer and the second layer into a second shape defined by the compression force being in equilibrium with the second layer; the second shape being an anatomical shape.

45. The simulated tissue structure of any one of the previous claims wherein the first shape is cylindrical having a longitudinal axis.

46. The simulated tissue structure of any one of the previous claims wherein the first layer exerts a compression force along the longitudinal axis; the longitudinal axis of the first layer being traverse to the longitudinal axis of the cylindrical first shape; the first layer forming a ring around the longitudinal axis of the cylindrical first shape.

47. The simulated tissue structure of any one of the previous claims wherein the second layer is made of silicone.

48. The simulated tissue structure of any one of the previous claims wherein the second layer is cured to adhere to the first layer.

1/7





**FIG. 2**




**FIG. 3**








**FIG. 4**

2/7



3/7




**FIG. 9**




**FIG. 10**




**FIG. 11**




**FIG. 12**

4/7




**FIG. 13**




**FIG. 14**









**FIG. 15**

5/7



6/7



**FIG. 21**




**FIG. 22**




**FIG. 23**




**FIG. 24**




**FIG. 25**




**FIG. 26**

7/7




**FIG. 27**




**FIG. 28**




**FIG. 29**





**FIG. 30**

**FIG. 31**



## INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2017/029281

A. CLASSIFICATION OF SUBJECT MATTER  
INV. G09B23/30  
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
G09B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages                                                                           | Relevant to claim No. |
|-----------|--------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------|
| A         | US 2012/276511 A1 (PARRY DAVID [US] ET AL)<br>1 November 2012 (2012-11-01)<br>paragraph [0075]<br>paragraph [0076]; figures 2,4<br>paragraph [0063]<br>----- | 1-48                  |
| A         | US 2005/016548 A1 (BRASSEL FRIEDHELM [DE])<br>27 January 2005 (2005-01-27)<br>the whole document<br>-----                                                    | 1-48                  |
| A         | WO 99/57699 A1 (ADVANCED RES & TECH INST<br>[US]) 11 November 1999 (1999-11-11)<br>the whole document<br>-----                                               | 1-48                  |
| A         | EP 2 400 475 A1 (TERUMO CORP [JP])<br>28 December 2011 (2011-12-28)<br>the whole document<br>-----                                                           | 1-48                  |



Further documents are listed in the continuation of Box C.



See patent family annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

4 July 2017

Date of mailing of the international search report

12/07/2017

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040,  
Fax: (+31-70) 340-3016

Authorized officer

Kirchler, Dominik

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2017/029281

| Patent document<br>cited in search report | Publication<br>date | Patent family<br>member(s) | Publication<br>date       |
|-------------------------------------------|---------------------|----------------------------|---------------------------|
| US 2012276511                             | A1                  | 01-11-2012                 | NONE                      |
| -----                                     |                     |                            |                           |
| US 2005016548                             | A1                  | 27-01-2005                 | AT 482813 T 15-10-2010    |
|                                           |                     | AU 2002338842              | A1 14-04-2003             |
|                                           |                     | CN 1596185                 | A 16-03-2005              |
|                                           |                     | DE 10148341                | A1 24-04-2003             |
|                                           |                     | EP 1429907                 | A1 23-06-2004             |
|                                           |                     | JP 2005504350              | A 10-02-2005              |
|                                           |                     | US 2005016548              | A1 27-01-2005             |
|                                           |                     | WO 03028978                | A1 10-04-2003             |
| -----                                     |                     |                            |                           |
| WO 9957699                                | A1                  | 11-11-1999                 | AU 3878799 A 23-11-1999   |
|                                           |                     | US 6511325                 | B1 28-01-2003             |
|                                           |                     | WO 9957699                 | A1 11-11-1999             |
| -----                                     |                     |                            |                           |
| EP 2400475                                | A1                  | 28-12-2011                 | CN 102317992 A 11-01-2012 |
|                                           |                     | EP 2400475                 | A1 28-12-2011             |
|                                           |                     | US 2012028231              | A1 02-02-2012             |
|                                           |                     | WO 2010095519              | A1 26-08-2010             |
| -----                                     |                     |                            |                           |