



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁵ : C12N 11/06, G01N 33/549	A1	(11) International Publication Number: WO 93/16176 (43) International Publication Date: 19 August 1993 (19.08.93)
(21) International Application Number: PCT/US93/01248 (22) International Filing Date: 11 February 1993 (11.02.93) (30) Priority data: 07/835,206 13 February 1992 (13.02.92) US (71) Applicant: BIO-METRIC SYSTEMS, INC. [US/US]; 9924 West 74th Street, Eden Prairie, MN 55344 (US). (72) Inventors: SWAN, Dale, Gustaf ; 1856 Parker Road, St. Louis Park, MN 55426 (US). JOSEPHSON, Mark, Willi- am ; 6515 Logan Avenue South, Richfield, MN 55243 (US). SWANSON, Melvin, John ; 5290 Mount Carmel Road, Carver, MN 55315 (US).		(74) Agents: GOLDMAN, Philip, M. et al.; Fredrikson & By- ron, 1100 International Centre, 900 Second Avenue South, Minneapolis, MN 55402 (US). (81) Designated States: AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: IMMOBILIZATION OF CHEMICAL SPECIES IN CROSSLINKED MATRICES		
(57) Abstract <p>A method of immobilizing a chemical specie in a three-dimensional, crosslinked matrix. The method involves bringing together in covalent bonding proximity a desired chemical specie and a polymeric coupling compound having at least two latent reactive groups per molecule, each latent reactive group being capable when activated of covalently bonding to another coupling compound molecule or to the chemical specie. The chemical specie desirably is free of latent reactive groups that are activated upon activation of the latent reactive groups are simultaneously activated to cause formation via covalent bonding of a three-dimensional molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound, and molecules of the coupling compound are covalently bonded to each other. Preferably, the three-dimensional matrix is formed as a coating upon a surface to which covalent bonds are formed upon activation of the latent reactive groups of the coupling compound.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

5

IMMOBILIZATION OF CHEMICAL
SPECIES IN CROSSLINKED MATRICES

10

BACKGROUND OF THE INVENTION

It is often desirable to provide products such as catheters, blood bags, chromatography media, membranes, cell culture ware and the like with surfaces which have particular, predetermined characteristics. For example, it may be desirable to provide guide wires and catheters with external surfaces that permit them to slide easily within the vascular system of a human or other animal. It may be appropriate to provide the surfaces of prostheses that are to be implanted within the body with growth factors or similar chemical species that may contribute to the rapid proliferation of tissue on the prosthesis or, to the contrary, with chemical species for the purpose of preventing ongrowth of tissue. Some devices such as artificial eyes desirably have surfaces that are wettable and lubricous to the touch and that hence are comfortably received within the eye socket. Poorly adherent surfaces, as of certain polymers, may be treated to improve adhesive characteristics. Blood bags and other tubes which may come into contact with blood may be treated with hemocompatible agents such as heparin or a heparin derivative. Bandages or other devices which come into contact with wounds may have surfaces that are provided with antibiotic materials. Various diagnostic tests may involve test protocols in which antibodies or antigens are covalently immobilized upon a surface.

30

U.S. patent 4,716,122 (Sheefers) refers to the use of a heterobifunctional photoactivatable compound, one functional group being an aryl azide and the other

being an N-hydroxysuccinimide ester to bind an antibody or other protein to a solid surface.

A series of papers by Guire, et al describes the use of polyfunctional photoderivatives of glucose oxidase and catalase in association with concanavalin A and glucose oxidase, respectively: Guire et al, Stepwise-Crosslinking Reagents for Photocoupling of Enzymes and Lectins to Mammalian Cells, Glycoconjugate Research II, pp. 1051-1054, (1979); Guire et al, Stepwise Thermophotochemical Crosslinking for Enzyme Stabilization and Immobilization; Enzyme Engineering 3, pp. 63-70 (1978); and Guire et al, Photochemical Coupling of Enzymes to Mammalian Cells, Pharmacological Research Communications, 9, No. 2, pp 131-141 (1977).

U.S. patent 4,979,959 (Guire) refers to a biocompatible device in which various molecules such as cell attachment factors are covalently bonded to a solid surface through a chemical linking moiety.

International Application No. PCT/US88/04487 published February 8, 1990 (Guire et al) refers to the bonding of various polymeric species to a solid surface through the use of latent reactive groups.

U.S. patent 3,959,078 (Guire) refers to the bonding of enzymes to a surface using a chemical linker employing an aryl azide photochemical group.

U.S. patent 4,007,089 (Smith III) teaches bonding a biologically active compound to a surface through a bifunctional linking compound by first attaching that compound to a surface via a phenyl azide group and then attaching the linking compound to the biologically active compound through an s-triazine group.

U.S. patent 5,024,742 (Nesburn et al) teaches a method of crosslinking collagen molecules to themselves or to other surfaces using a heterobifunctional reagent.

To covalently bond a specific chemical specie to a surface through photoactivation, a photoreactive group or other latent reactive group usually is first
5 attached to the chemical specie and thereafter is activated to cause covalent bonding to the solid surface. Although procedures of this type have been quite successful, it has been necessary to manufacture latent reactive group-containing derivatives of each of the chemical species that one wishes to covalently bond to a
10 surface. For example, heparin may be photoderivatized as taught in International Application No. PCT/US88/04487 published February 8, 1990 and may be applied to various devices that come into contact with blood such as blood bags, tubes, and the like. However, the synthesis of latent reactive group-containing derivatives of various chemical species can be very expensive, both from the
15 standpoint of developing the protocol for the synthesis of the derivative and also with respect to the manufacture of commercial quantities of the derivative.

It is also possible to attach desired chemicals to a surface by first providing the surface with latent reactive groups, then bringing the desired molecules into bonding association with the latent reactive groups, and activating the latent
20 reactive groups to cause the formation of covalent bonds. Reference is made particularly to U.S. Patent 4,722,906 (Guire). The method of this patent is dependent upon the ability of the target molecules to diffuse into bonding association with the latent reactive groups carried by the solid surface, however, and is highly selective of the target molecules that are to be attached.

BRIEF DESCRIPTION OF THE INVENTION

It has now been found that a wide variety of chemical species such as heparin, growth factors, natural and synthetic polymers and the like may be covalently immobilized in an insoluble, three dimensional, crosslinked matrix, preferably in solid or semi-solid form and most preferably in film form, utilizing a polymeric coupling compound having latent reactive groups. The invention avoids the necessity of synthesizing latent reactive group derivatives of the various chemical species, and provides a three dimensional matrix which exhibits properties of the chemical specie, the coupling compound or both. Speaking broadly, the method of the invention involves bringing together in covalent bonding proximity a desired chemical specie and a polymeric coupling compound having at least two latent reactive groups per molecule, each latent reactive group being capable of covalently bonding to another coupling compound molecule or to the chemical specie. The method involves simultaneously activating the latent reactive groups to cause formation via covalent bonding of a three-dimensional molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound, and molecules of the coupling compound are covalently bonded to each other.

Preferably, a film comprising the coupling compound and the chemical specie is formed upon a surface, as by coating the surface with a solution containing the coupling compound and the chemical specie. In the most preferred embodiment, latent reactive groups carried by the polymeric coupling compound form covalent bonds to the surface, thereby co-immobilizing the coupling compound and the chemical specie to the surface. If desired, the surface may be a

liquid surface or a surface to which the latent reactive groups do not readily form covalent bonds, and the completed film with its three dimensional, crosslinked structure may be removed from the surface for use elsewhere as, for example, a protective wound dressing.

5 Thus, in the preferred embodiment, the method of the invention involves forming on a surface a coating of the chemical specie that is desired together with and in covalent bonding proximity to a polymeric coupling compound having at least two latent reactive groups per molecule, each latent reactive group being capable of covalently bonding to a coupling compound molecule (either the same
10 or different), to the chemical specie, or to the surface. The method involves simultaneously activating the latent reactive groups to cause formation via covalent bonding of a three-dimensional molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound, and molecules of the coupling compound are covalently bonded to each other and to
15 the surface.

The covalent bonds between the chemical specie and the coupling compound, between the coupling compound and the surface, and between different molecules of the coupling compound, form simultaneously, that is, during the same step. Thus, the chemical specie and the coupling compound are co-
20 immobilized upon the surface. By judicious choice of the type and quantity of the coupling compound relative to the chemical specie, one may obtain three dimensional crosslinked networks of varying complexity and permeability.

The resulting three dimensional networks may be slightly or highly swellable in a solvent, but the networks remain insoluble. Free molecules of the

chemical specie or another compound (that is, molecules that are not covalently bound to the coupling compound) may be incorporated into the three-dimensional network as desired.

The polymeric coupling compound contains an average of at least two latent reactive groups per molecule. Preferably, the average number of such groups per 100 Angstroms extended chain length ranges from 0.05 to 12 and preferably from 0.2 to 2. The coupling compound desirably is formed or derived from a synthetic polymer, although coupling compounds derived from natural polymers also may be employed.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The coupling compounds employed in the present invention are polymeric in nature; that is, they have repeating units and a molecular weight distribution. Most preferably, the coupling compounds are derived from or formed as synthetic polymers. The polymers of the invention include oligomers, homopolymers and copolymers resulting from addition or condensation polymerization, and natural polymers including nucleic acids, oligosaccharides, linear polysaccharides such as amylose, dextran, chitosan, heparin and hyaluronic acid, and branched polysaccharides such as amylopectin, glycogen and hemi-celluloses. The polymers may include several distinct polymer types, as may be prepared by terminal or side chain grafting. The polymers of the invention may include cellulose-based products such as hydroxyethyl cellulose, hydroxypropyl cellulose, carboxymethyl cellulose, nitrocellulose, cellulose acetate and cellulose butyrate, acrylics such as those polymerized from hydroxyethyl acrylate, hydroxyethyl methacrylate, glyceryl acrylate, glyceryl methacrylate, acrylic acid, methacrylic acid, acrylamide

and methacrylamide, vinyls such as polyvinyl pyrrolidone and polyvinyl alcohol, nylons such as polycaprolactam, polylauryl lactam, polyhexamethylene adipamide and polyhexamethylene dodecanediamide, polyurethanes and polylactic acids. Of particular importance are the vinyl polymers such as polyvinyl pyrrolidone and
5 polyacrylamide and the polyethers such as polyethylene glycol. For brevity, the invention is described below primarily with respect to the use of single coupling compounds that are homopolyfunctional (that is, that bear two or more identical latent reactive groups (and such is preferred)). However, one may employ a mixture of polymeric coupling compounds, if desired, and the coupling compounds
10 themselves may be heteropolyfunctional (that is, they may contain two or more different latent reactive groups) and they may have different properties which they confer upon the matrix.

The polymeric coupling compounds employed in the invention desirably are soluble or at least dispersible in a solvent (to form, for example, a colloidal
15 suspension), and preferably are soluble in water to at least the extent of 1 gram/1 at 23°C. Moreover, the polymers of the invention desirably have extended chain lengths of at least about 45 Angstroms, and preferably at least about 1000 Angstroms.

"Extended Chain Length", as used herein, refers to theoretical straight line
20 lengths measured along the backbone of a polymeric coupling compound, assuming that the polymer chain is stretched out to its maximum length consistent with observing proper bond angles between adjacent atoms. For example, polyethylene, $-(CH_2-CH_2)-$, exhibits an "extended" chain length between alternate carbon atoms of about 2.5 Å (observing a bond angle of 109.5°), although the

sum of the (carbon-carbon) bond distances along the molecule between alternate carbon atoms is about 3.06 Å.

Latent reactive groups, broadly defined, are groups which respond to specific applied external stimuli to undergo active specie generation with resultant covalent bonding to an adjacent chemical structure, e.g., an adjacent same or different molecule. Latent reactive groups are those groups of atoms in a molecule which retain their covalent bonds unchanged under conditions of storage but which, upon activation by an external energy source, form covalent bonds with other molecules. The latent reactive groups generate active species such as free radicals and particularly nitrenes, carbenes, and excited states of ketones upon absorption of external electric, electromagnetic or kinetic (thermal) energy. Latent reactive groups may be chosen to be responsive to various portions of the electromagnetic spectrum, and latent reactive groups that are responsive to e.g., ultraviolet and visible portions of the spectrum are preferred and are referred to herein occasionally as "photochemical" groups. Latent reactive groups as described are generally well known.

The azides constitute a preferred class of latent reactive groups and include arylazides (N_3) such as phenyl azide and particularly 4-fluoro-3-nitrophenyl azide, acyl azides ($-\text{C}-\text{N}_3$) such as benzoyl azide and p-methylbenzoyl azide, azido formates ($-\text{O}-\text{C}-\text{N}_3$) such as ethyl azidoformate, phenyl azidoformate, sulfonyl azides ($-\text{S}-\text{N}_3$) such as benzenesulfonyl azide, and phosphoryl azides $(\text{RO})_2\text{P}-\text{N}_3$ such as diphenyl phosphoryl azide and diethyl phosphoryl azide. Diazo compounds constitute another class of latent reactive groups and include diazoalkanes ($-\text{CHN}_2$) such as

diazomethane and diphenyldiazomethane, diazoketones (-C-CHN₂) such as diazoacetophenone and 1-trifluoromethyl-1-diazo-2-pentanone, diazoacetates (-O-C-CHN₂) such as t-butyl diazoacetate and phenyl diazoacetate, and beta-keto-alpha-diazoacetates (-C-C-C-O-) such as t-butyl alpha diazoacetoacetate. Other latent

5 reactive groups include the aliphatic azo compounds such as azobiscyanovaleric acid, the diazirines (C) such as 3-trifluoromethyl-3-phenyldiazirine, and the ketenes (-CH=C=O) such as ketene and diphenylketene. Photoactivatable aryl ketones such as benzophenone and acetophenone are of particular importance inasmuch as these groups are subject to multiple reactivation in water and hence

10 provide increased coupling efficiency. Peroxy compounds are contemplated as another class of latent reactive groups and include dialkyl peroxides such as di-t-butyl peroxide and dicyclohexyl peroxide and diacyl peroxides such as dibenzoyl peroxide and diacetyl peroxide and peroxyesters such as ethyl peroxybenzoate.

Upon activation of the latent reactive groups, the coupling compounds are

15 covalently bound to coupling compound molecules and to chemical species (and, in the preferred embodiment, to the surfaces to which the chemical species are to be co-immobilized), by covalent bonds through residues of the latent reactive groups. Exemplary latent reactive groups, and their residues upon activation, are as follows:

20	<u>Latent Reactive Group</u>	<u>Residue Functionality</u>	
	aryl asides	amine	R-NH-R'
	acyl asides	amide	R-C-NH-R'
	azidoformates	carbamate	R-O-C-NH-R'
	sulfonyl asides	sulfonamide	R-S-NH-R'
25	phosphoryl asides	phosphoramidate	(RO) ₂ P-NH-R'
	dialkyl peroxides	new C-C bond	
	diazoketones	new C-C bond & ketone	
	diazoacetates	new C-C bond & ester	

	beta-keto-alpha-diazoacetates	new CC bond & B-ketoester
	aliphatic azo	new C-C bond
	diazirines	new C-C bond
	ketenes	new C-C bond
5	photoactivated ketones	new C-C bond & alcohol
	dialkyl peroxides	ethers
	diacyl peroxides	esters & new CC bonds
	peroxyesters	ethers, esters, and new C-C bonds

10 The coupling compounds of the invention desirably have an average of at least two and preferably three or more latent reactive groups per molecule. Three-dimensional molecular networks may be formed through the use of polymeric coupling compound molecules each having two or more latent reactive groups, and in general the density of covalent bonds resulting from activation of the reactive

15 groups and hence the "tightness" of the three-dimensional molecular network that is formed will be increased by decreasing the distance between latent reactive groups that are employed in the coupler compound.

Depending upon the method of fabrication of the polymeric coupling compound, that compound may contain varying numbers of latent reactive groups.

20 A bifunctional polymeric coupling compound may have one latent reactive group at each of its two ends. For example, 4-bromomethylbenzophenone (derived from the free radical bromination of 4-methylbenzophenone) may be reacted with polyethylene glycol to form a bifunctional coupling compound having $-(\text{CH}_2-\text{CH}_2-\text{O})-$ repeating units and terminating in benzophenone latent reactive groups.

25 Polymeric coupling compounds used in the invention may have latent reactive groups incorporated at random positions along the polymer backbone. It may in some instances be desirable to provide polymers with more predictable sites for attachment of latent reactive groups, as described further below.

Polymeric coupling compounds desirably, but not necessarily, have latent reactive

groups at their ends or at random locations along their backbones (spaced from their ends) or both. By "backbone" as used herein in connection with polymer molecules, reference is made to the chain of atoms that is characteristic of the polymer and that results from the polymerization reaction. For example, 5 polyethylene glycol polymers are characterized by a "backbone" of repeating $-(\text{CH}_2-\text{CH}_2-\text{O})-$ groups, whereas polyacrylamide and polyvinyl pyrrolidone have backbones characterized by carbon-carbon bonds, alternating carbon atoms in the backbone having pendent amide or pyrrolidone groups, respectively.

A polymer that includes at least one latent reactive group along its 10 backbone spaced from its ends can be prepared by copolymerizing the basic monomer or monomers for the polymer with a monomer to which can be readily attached a latent reactive group such as a photoreactive group. For example, a photoreactive polyacrylamide polymer can be obtained by copolymerizing 15 acrylamide with a small quantity of N-(3-aminopropyl)methacrylamide to provide random amine-functional groups along the polymer backbone, and then reacting the polymer with an amine-reactive photoreactive reagent such as benzoylbenzoylchloride. Coupling compounds may be derived from naturally occurring polymers such as hyaluronic acid by known methods such as those 20 taught in U.S. Patent 5,002,582, the teachings of which are incorporated herein by reference. The polymeric coupling compounds employed in the present invention desirably carry a sufficient number of latent reactive groups so that the average number of latent reactive groups per 100 Angstrom extended chain length ranges from 0.05 to 12 and preferably from 0.2 to 2.

The chemical species which can be co-immobilized together with the coupling compound in a three dimensional network according to the invention may be chosen from a wide variety of suitable substances. The chemical species used herein preferably are free of latent reactive groups of the type carried by the coupling compounds, that is, latent reactive groups that are activated upon activation of the latent reactive groups of the coupling compounds during the activation step. If desired, two or more chemical species may be employed, each lending to the matrix its particular properties. For example, it may be desired to immobilize at the same time an anticoagulant such as heparin, a thrombolytic agent such as streptokinase and, if desired, a protease inhibitor.

Some chemical species and the desired properties that these species exhibit when co-immobilized upon a surface are exemplified in the following non-limiting list:

	CHEMICAL SPECIES	FUNCTIONAL ACTIVITY
15	<u>Synthetic Polymers</u>	
	Sulfonic acid-substituted polyacrylamide	Lubricity, negatively charged surface
	Polyacrylamide	Lubricity, protein repulsion
	Polyethylene glycol	Lubricity, cell and protein repulsion
20	Polyethyleneimine	Positively charged surface
	Polylactic acid	Negatively charged surface
	Polyvinyl alcohol	Lubricity
	Polyvinyl pyrrolidone	Lubricity
	Quaternary amine-substituted polyacrylamide	Lubricity, positively charged surface
25	Silicones	Lubricity
	Conductive polymers (e.g., polyvinylpyridine, polyacetylene, polypyrrole)	Electric conductivity
30	<u>Carbohydrates</u>	
	Alginic acid	Lubricity, hydrophilicity
	Cellulose	Lubricity, hydrophilicity, biodegradable source
	glucose	

	Chitosan	Positively charged surface,
	hydrophilicity	
	Clycogen	Hydrophilicity, biodegradable glucose
	source	
5	Heparin	Antithrombogenicity, hydrophilicity,
	cell	attachment
	Hyaluronic acid	Lubricity, negatively charged surface
	Pectin	Lubricity, hydrophilicity
	Mono-, di- saccharides	Hydrophilicity
10	Dextran sulfate	Chromatography media
	<u>Proteins</u>	
	Antibodies	Antigen binding
	Antithrombotic agents, e.g.,	Antithrombogenic surface
15	Antithrombin III	
	Albumin	Nonthrombogenic surface
	Attachment proteins/peptides	Cell attachment
	Enzymes	Catalytic surfaces
	Extracellular matrix proteins/peptides	Cell attachment and growth
20	Growth factors, proteins/peptides	Cell growth
	Hirudin	Antithrombogenic surface
	Thrombolytic proteins (e.g.,	Thrombolytic activity
	streptokinase, plasmin)	
	<u>Lipids</u>	
25	Fatty acids	Hydrophobicity, biocompatibility
	Mono-,di- and triglycerides	Hydrophobicity, lubricity,
	biodegradable fatty	acid source
30	Phospholipids	Hydrophobicity, lubricity,
	biodegradable fatty	acid source
	Prostaglandins/leukotrienes	Nonthrombogenic surface/immobilized
	messengers	
35	<u>Nucleic Acids</u>	
	DNA	Substrate for nucleases/affinity binding
	RNA	Substrate for nucleases/affinity binding
	Nucleosides, nucleotides	Source of purines, pyrimidines, enzyme
40	cofactors	
	<u>Drugs/vitamins/cofactors</u>	
	Enzyme cofactors	Immobilized enzymes
	Heme compounds	Globin binding/surface oxygenation
45	Drugs Drug activity	
	<u>Non-polymeric Materials</u>	
	Dyes (e.g., azo dyestuffs)	Coloring agents

Fluorescent compounds
(e.g., fluorescein)

Fluorescence

5 The product that is formed via activation of the latent reactive groups
carried by the coupling compound is an insoluble, three dimensional crosslinked
matrix that is
desirably in solid or at least semi-solid (e.g., gel) form and that exhibits the
properties of the chemical specie(s) incorporated in it, or properties of the
10 coupling compound(s), or both. The coupling compound may be a polymer that
itself provides the matrix with valuable properties; for example, use of a photo-
derivatized polyvinylpyrrolidone may confer slipperiness and water wettability to
the matrix. Both the coupling compound and the chemical specie may provide the
matrix with desired properties. For example, a matrix formed from
15 photopolyacrylamide as the polymeric coupling compound and heparin as the
chemical specie may exhibit a reduction in protein absorption characteristic of the
polyacrylamide and the antithrombogenic activity characteristic of heparin.

 The matrices may be in the form of fibers, beads or other particles (for
use, for example, in chromatographic columns), or in the form of free-flowing or
20 non-flowing gels. However, the matrices preferably are in the form of films
which may be continuous or discontinuous and which may have thicknesses
ranging from a few nanometers up to a millimeter or more. A film may be self
supporting, as when in sheet or tubing form; it may be in the form of a coating
formed on and supported by a surface and in its most preferred form covalently
25 bonded to the surface.

The crosslink density of the three-dimensional polymeric network that is formed can be varied as desired by judicious choice of the type and the amount of the coupling compound. For example, the use of polymeric coupling compounds that contain relatively few latent reactive groups will result in fewer covalent bonds being formed per unit length measured along the extended backbone of the polymer or per unit of molecular weight of the polymer, and the resulting three-dimensional network will be more open; that is, it will have a larger effective pore size. The use of polymeric coupling compounds having a greater number of latent reactive groups, or, for that matter, having latent reactive groups concentrated along a certain portion of the molecule, will provide a more tightly crosslinked, dense three-dimensional matrix.

The tightness of the three-dimensional network that is formed will depend upon the density of covalent bonds formed from the latent reactive groups carried by the coupling compound and this, in turn, depends upon the number of latent reactive groups per molecule of the coupling compound and the relative amounts of coupling compound and chemical specie that are employed. Of course, the ability of the polymeric coupling compound to become extended in solution (in contrast to assuming a tightly coiled configuration) also contributes to the loftiness or openness of the three dimensional network, and polymeric coupling compounds that are soluble to the extent of at least about 1 g/l in water are preferred.

The three-dimensional network that is formed in accordance with the method of the invention not only has utility in providing the resulting film with characteristics of the co-immobilized chemical specie, but also has utility in that it can be used to capture free chemical species (chemical species not covalently

bound to a coupling compound molecule) so that the matrix, when in contact with a suitable liquid medium such as an aqueous solution, may gradually release the free chemical specie into the medium. The quantity of chemical specie that is thus released by the three-dimensional polymer network and the rate of release may
5 depend upon a number of factors, including the loftiness or openness of the three-dimensional network, the amount of the free chemical specie that is employed, and the degree of affinity or repulsion between the three-dimensional network and the chemical specie.

In a preferred embodiment, the polymeric coupling compound and the
10 chemical specie exhibit an affinity permitting them in solution to assume a preferred orientation with respect to each other prior to activation of the latent reactive groups, thereby facilitating covalent bonding therebetween when the latent reactive groups are activated. The affinity of the coupling compound and the chemical specie may involve the hydrophobic or hydrophilic characteristics of
15 these compounds, e.g., in which hydrophobic portions of these compounds preferentially orient next to each other. The affinity between the coupling compound and the chemical specie may involve ionic attraction between portions of the molecules. For example, the polymeric coupling compound may be polyionic and the chemical specie also may be ionic, the coupling compound
20 having a net charge opposite the net charge of the chemical specie. The coupling compound may be a vinyl copolymer containing aminopropyl pendent groups resulting from the use of an aminopropylmethacrylate monomer, the coupling compound thus having a net positive charge. The chemical specie may be a dextran sulfate having a net negative charge. In this embodiment, prior to the step

of activating the latent reactive groups, the coupling compound and the chemical specie are brought into association permitting ionic attraction between them to pre-orient the chemical specie and the polymeric coupling compound with respect to each other before they are covalently bonded. Desirably, the polyionic coupling
5 compound and the ionic chemical specie are provided in solution together to facilitate ionic attraction between them.

Free chemical species may be positioned or entrapped within the three-dimensional network that is formed by being present during formation of the network or by being added after the network has been formed. By employing a
10 large amount of the chemical specie in comparison to the coupling compound, one may ensure that at least some of the chemical specie will not become covalently bound to the coupler, and the resulting free chemical specie may thus become physically entrapped within the network, and some may be slowly released.

If substantially all of the chemical specie becomes involved via covalent
15 bonding within the three-dimensional network, additional chemical specie may be incorporated in the network by replacing the solvent that is present in the network with a solvent solution containing the chemical species. For example, solvent may be removed from a film that is initially formed, and the dried film may then be contacted with a solution of an additional quantity of the same or a different
20 chemical species, causing molecules of the chemical species to enter the network and to become trapped therein upon removal of the solvent in a subsequent drying procedure. The resulting films, when placed in contact with a liquid medium such as blood or an open wound containing serous fluid, will release molecules of the free chemical species into the blood or serous fluid, the amount and rapidity of the

release of the chemical agent depending upon how readily the chemical species can migrate from the coating into the blood or serous fluid, and, of course, upon the concentration gradients of the chemical species that are established. The remaining film, however, will yet retain molecules of the chemical species

5 covalently bonded to it such that it will continue to itself exhibit characteristics of the chemical species. For example, heparin may be co-immobilized with a photoderivatized polyacrylamide coupling compound upon a surface, the process making use of a large amount of heparin so that some of the heparin is not covalently bonded to the polyacrylamide. The resulting film, when brought into

10 contact with blood, releases heparin into the blood at a decreasing rate over a period of time. Once all of the available free heparin has escaped from the surface of the film into the blood, the heparin molecules that are covalently bound to the surface will continue to provide the surface with the antithrombogenic characteristics of heparin.

15 If desired, the three-dimensional network that is formed may be chosen to be subject to destruction in use. For example, the network may include ester linkages that are cleavable by the esterases in blood issuing from a wound. For example, a protective coating may be made from a vinyl polymer coupling compound containing aminoethylmethacrylate mere units to which latent reactive

20 groups are coupled and a biologically active chemical species such as heparin. The coating may slowly degrade when in contact with blood due to hydrolysis of the ester bonds by esterases in the blood. In this manner, chemical species containing heparin and having the antithrombogenic properties of heparin may be slowly released.

If desired, free molecules of other chemical species (that is, molecules not covalently bound to the coupling compound) can be incorporated in the three-dimensional matrix. For example, as taught in greater detail below, photopolyacrylamide and heparin may be co-immobilized on a surface, and an antibiotic such as cephalosporin or vancomycin may be incorporated in the matrix. Upon contact with blood, the antibiotic is released gradually by being leached from the surface, leaving behind a heparinized surface. Different free molecules of various chemical species may be incorporated in a single matrix in this manner. For example, several antibiotics may be employed which exhibit activity against different microorganisms, or which provide more effective control over a single microorganism. If it is desired to form the film upon a surface to which the film is covalently bonded as it is formed, then the latent reactive groups that are employed are preferably attracted to the surface to be coated so that the latent reactive groups will readily come into covalent bonding proximity with the surface. Photochemical groups such as the aryl azides and the aromatic ketones commonly are relatively hydrophobic, as are many of the solid surfaces (e.g., polystyrene, polysulfone and polyolefin) that may be coated in accordance with the invention. "Hydrophilic" and "hydrophobic" are used herein to describe compositions broadly, as water loving and water hating, respectively, in line with the following observations: Hydrophilic compounds are usually relatively polar and often are ionizable. Such compounds usually bind water molecules strongly. Hydrophobic compounds are usually relatively non-polar and non-ionizing. Hydrophobic surfaces will generally cause water molecules to structure in an ice-like conformation at or near the surface. "Hydrophobic" and "hydrophilic" are

relative terms, of course, and are used herein in the sense that various compositions, liquids and surfaces may be hydrophobic or hydrophilic relative to one another. A discourse on the subject is found in Hoffman, Letter to the Editor: A general classification scheme for "hydrophilic" and "hydrophobic" biomaterial surfaces, J. Biol. Mat. Res. 20, pp. ix-xi (1986).

Crosslinked, three-dimensional matrix films of co-immobilized coupling compound and chemical species can be produced by combining the polymeric coupling compound and chemical species precursors in solution and then physically forming the solution into a sheet or film configuration before activating the latent reactive groups. For example, an aqueous solution of the precursors may be floated upon the surface of a non-miscible liquid such as a perfluorocarbon liquid. After activating the latent reactive groups of the polymeric coupling compound, the film, which may at this point be self-supporting, may be removed from the liquid surface. It is contemplated that this process may be performed on a continuous basis if desired, the precursor solution being sheeted onto a bath of the non-miscible liquid at one end of the bath, and the continuous self-supporting film being removed from the other end of the bath. The surface upon which the film is physically formed may be a solid surface such as polytetrafluoroethylene to which the latent reactive groups, when activated, do not readily bond and from which the film may be removed.

The method of the invention finds particular utility, however, in the formation of a film upon a surface, desirably a solid surface, to which the film becomes covalently bonded by latent reactive groups of the coupling compound. In this embodiment, the surface itself becomes chemically involved in the

formation of the three-dimensional matrix. Such surfaces preferably have abstractable hydrogen atoms and participate readily in the formation of covalent bonds upon activation of the latent reactive groups.

5 In the preferred process of the invention, the coupling compound and the selected chemical specie (several coupling compounds or chemical species or both may be used) are applied to a surface, and the latent reactive groups of the coupling compounds are simultaneously reacted to form covalent bonds between the chemical specie and the coupling compound, between the coupling compound and the surface, and between different molecules of the coupling compound, to
10 form a three dimensional molecular network. If desired, the coupling compound and the chemical specie may be combined and partially pre-reacted before they are applied to the surface.

To facilitate the co-immobilization process, the polymeric coupling compound and the chemical specie are applied to a surface from a solvent
15 medium, preferably from solution and most preferably from aqueous solution. Preferably, the coupling compound and the chemical specie are combined in solution and applied as a wet film to the surface, following which the latent reactive groups are activated, by light, in the case of photoreactive groups. Solvent may be partially or totally removed from the wet film before activation of
20 the latent reactive groups. Alternatively, the latent reactive groups may be reacted in the presence of the solvent. The coupling compound and the chemical specie may be applied to the surface as separate, wet films which blend or interdiffuse together to bring the coupling compound and the chemical specie into covalent

bonding proximity, and it is contemplated that the first wet film may be at least partially dried before application of the second film.

Defined broadly, the "surface" upon which may be formed a film according to the invention is defined by the interface between distinct phases of compositions, the solid surface of a tangible object such as a sheet of material being perhaps the most commonly thought of surface and being defined by a gas-solid interface. Surfaces may be defined by the interface between liquid and solid compositions as exemplified by the solid surface of solid particles in suspension, by the interface between immiscible liquids as exemplified by emulsions, and by gas-liquid interfaces as exemplified by the surface of a liquid bath.

A solid surface as referred to herein is a tangible surface defined by the interface between solid phase materials (including soft gels) and gas or liquid phases. Specific examples include the surfaces of medical devices such as blood bags, catheters, bone and tissue prostheses, and living bone and tissue surfaces. Other solid surfaces are exemplified as the surfaces of membranes, fibers such as hollow fibers employed in chemical reactors and fibers employed in structural composites, and chromatographic media particles and the like.

The invention may be more easily understood by reference to the following illustrative, non-limiting examples:

EXAMPLE 1: Preparation of Bis(benzoylbenzyl)

Polyethyleneglycol Ether (BBE-PEG(3350)-BBE)

To 100 g of polyethylene glycol 3350 (PEG(3350)) in a 1 liter round bottom flask was added 400 ml of toluene. The toluene was evaporated off to

remove moisture. The PEG was then dissolved in tetrahydrofuran (250 ml) by stirring at reflux temperatures under an argon atmosphere, and the solution was allowed to cool. To the solution was added NaH (2.3 g) and the solution was stirred for an hour, after which 20.5 g of bromomethylbenzophenone was added.

5 The cloudy mixture was stirred overnight. Ammonium chloride (10.2 g) and water (4 ml) were added and the mixture was stirred for 30 minutes. The solvent was evaporated off, and 150 ml of toluene was added and the cloudy solution was filtered to obtain a clear filtrate. The clear solution was then slowly added to 300 ml of ice cold diethyl ether to precipitate the polymer which was then collected by
10 filtration, washed with ethyl ether and dried.

EXAMPLE 2: Preparation of Photoderivatized Polyacrylamide (Photo PAA)

Acrylamide (10.24 g) was dissolved in 200 ml of deionized water. To the solution was added 0.279 mg of N-(3-aminopropyl)methacrylamide, 0.33 g of ammonium persulfate and 0.155 g of N,N,N',N'-tetramethylethylenediamine. The
15 solution was evacuated in a filter flask with a water aspirator for 10 minutes. The tubing was clamped and the solution left under vacuum for one hour. The resulting polymer solution was dialyzed against deionized water. To 150 ml of polymer solution in a PTFE bottle containing 3.0 g of polymer was added 0.504 ml of triethylamine. To this solution was added 30 ml of 28.4 mg/ml 4-
20 benzoylbenzoylchloride in CHCl₃. The bottle was capped tightly and shaken for one hour. The bottle was then centrifuged for 10 minutes to separate the phases after which the aqueous layer was removed, dialyzed and lyophilized.

EXAMPLE 3: Co-immobilization of Polyvinylpyrrolidone

1.0 gm of polyvinylpyrrolidone (PVP) having a number average molecular weight of about 360,000 was dissolved in 25ml of water. 350 mg of BBE-PEG(3350)-BBE prepared as in Example 1 were dissolved in 25 ml of water. The solutions were mixed and lyophilized. 100 mg samples were illuminated with ultraviolet light for 10 seconds and for 10 minutes, respectively, to achieve limited pre-reaction of the photoreactive groups carried by the photopolyethylene glycol. The dry mixtures were redissolved in water and diluted to give a solution that was 4.5 mg/ml in 30% isopropanol. 65 ul of these solutions were sprayed onto one side of a 1" x 1" piece of polymethylmethacrylate (PMMA), and the coating was irradiated with ultraviolet light for 3 minutes. Both samples were readily wettable with water. After washing, the wet films were slippery when rubbed with the fingers (a characteristic of PVP but not of PMMA or photo PEG), indicating that the PVP had been bound to the surface.

EXAMPLE 4: Heparin Co-immobilized onto Regenerated Cellulose and Polysulfone Hollow Fiber Dialysis Membranes.

Heparin was dissolved at 3 mg/ml in an aqueous solution of photo PAA prepared as in Example 2 at 3 mg/ml for subsequent co-immobilization on membrane surfaces. Another aqueous solution was prepared by dissolving heparin at 6 mg/ml in photo PAA at 3 mg/ml. A photoreactive derivative of heparin (photoheparin) was prepared by reacting heparin with benzoyl-benzoyl-epsilon-aminocaproyl-N-oxysuccinimide in dimethylsulfoxide/carbonate buffer, pH 9.0. The solvent was evaporated and the photoheparin was dialyzed vs. water, and lyophilized, and then dissolved in water at 3 mg/ml. Heparin was also dissolved in water at 3 mg/ml for subsequent absorption onto membrane surfaces. Each

solution was applied to specimens of regenerated cellulose membranes by soaking overnight at 37°C. The membranes were then dried and UV illuminated in a N₂ atmosphere for 2 minutes. The membranes were then washed four times for three minutes each in an ultrasonic bath of 0.5% Tween 20 in phosphate buffered saline (PBS) followed by the same washing procedure in deionized water. The membranes were further washed for 24 hours in 0.5% Tween 20 followed by a 24-hour wash in 1% bovine serum albumin (BSA). Heparin activity was then measured by a Factor Xa inhibition assay. The results are given below.

Regenerated Cellulose Immobilization Condition	Heparin Activity (mU/cm ²)
Adsorbed heparin	2.4
Photo-heparin	5.8
Co-immobilized heparin (3 mg/ml)	5.2
Coimmobilized heparin (6 mg/ml)	7.9

In a similar experiment, heparin at several concentrations was coimmobilized with photo-PAA as described above onto polysulfone hollow fiber membranes. After washing, the heparin activity was measured, yielding the following results:

Heparin Concentration, mg/ml	Heparin Activity (mU/cm ²)
6.0	8.4 ± 2.5
2.5	8.4 ± 1.9
1.0	7.2 ± 1.3
0.6	4.6 ± 1.4

EXAMPLE 5: Collagen Co-immobilized onto PTFE Membranes for Cell Culture.

Photo PAA was prepared as follows:

To 2 grams of N-(3-aminopropyl)methacrylamide (APMA) in 80 ml of dry dimethylsulfoxide was added 4.96 gm of 4-benzoylbenzoyl-epsilon-aminocaproyl-N-oxysuccinimide and 2.26 ml of N,N,N',N'-tetramethylethylenediamine. The solution was stirred for four hours, after which
5 20 gm of acrylamide in 286 ml of DMSO and 300 mg of azobis(isobutyronitrile) in 100 ml of DMSO were added. The solution was bubbled with helium for 5 minutes, after which the space above the solution was filled with argon. Polymerization was allowed to occur at 55°C for 24 hours. The polymer was then precipitated in ethanol, redissolved in 250 ml of deionized water, and dialyzed vs.
10 water. Insoluble material was removed by filtration, and the clear solution was lyophilized.

Polytetrafluoroethylene (PTFE) membranes were first prewetted with methanol and then were soaked for 4 hours in an aqueous solution (5 mg/ml) of the photo PAA prepared above. The coatings then were illuminated with UV light
15 for 3 minutes and washed in PBS. Native bovine skin collagen (containing types I and III) at 1.25 mg/ml was dialyzed vs. 3 mM HCl, and the photo PAA prepared as above was dissolved in the collagen solution at 5 mg/ml. Porous PTFE membranes that previously had been coated with photo PAA and irradiated were then soaked in the solution for 4 hours at 4°C. The membranes were illuminated
20 with UV light for 3 minutes, after which they were washed extensively with PBS and air dried.

The collagen-coated membranes thus produced were tested in cell culture studies using both PA-I (human, ovarian) and NRK (rat, kidney) cell lines and demonstrated good cell attachment and growth.

EXAMPLE 6: Co-immobilization of Streptokinase

Polyethylene tubing was filled with a solution containing 2.5 mg/ml photo PAA prepared as in Example 5 and 2.5 mg/ml streptokinase, after which the tubing was UV illuminated for 8 minutes. After rinsing the tubing by circulating 5 buffer through it for 24 hours, streptokinase activity was detected in the tubing by adding plasminogen (0.5 units/ml) and D-val-leu-lys-p-nitroanilide and measuring at 405 nm the color generated by release of p-nitroaniline.

EXAMPLE 7: Co-immobilization of Photopolyacrylamide and Heparin to Polyvinylchloride Tubing

10 Photopolyacrylamide prepared as in Example 3 was dissolved in water at 25 mg/ml. Sodium heparin was dissolved in water at 50 mg/ml. 20 ml of the photo PAA solution prepared as in Example 2 and 5 ml of the heparin solution were mixed to give 25 ml of co-immobilization solution containing 30 mg/ml of total solids. External surfaces of polyvinylchloride tubing were precleaned with an 15 alcohol wipe followed by argon plasma treatment and then were dipped in the co-immobilization solution. Excess solution was drained away, the coating was air dried, and a second, identical coating application was performed. The tubing was exposed to UV light to cure the hydrogel-heparin matrix. Surface treatment of the polyvinylchloride by this two-coat process resulted in heparin activity levels of 20 3500 mU/cm² as measured by a thrombin inhibition assay. Long term exposure of these coated materials to albumin-containing phosphate-buffered saline (intended to simulate blood contact) gave significant release of soluble heparin and also resulted in immobilized heparin activities of approximately 10 mU/cm².

EXAMPLE 8: Co-immobilization of Photo PAA and Heparin to a Surface with Subsequent Loading and Release of Antimicrobial Agents.

Photo PAA, as prepared in Example 2, and heparin are co-immobilized upon a surface as described in Example 7. After rinsing away the unbound heparin with water and subsequently drying the coating, the immobilized polyacrylamide-heparin matrix is placed overnight in an aqueous solution containing 100 mg/ml of vancomycin. The tubing is removed and air-dried. Upon subsequent blood contact with the tubing, the antibiotic is released from the photo PAA-heparin hydrogel at a gradually decreasing rate. Complete release of the matrix-adsorbed drug leaves a biocompatible heparinized, hydrogel surface.

EXAMPLE 9: Preparation of Co-immobilized Photo PAA/Hyaluronic Acid Film

To 10 ml of a 10 mg/ml solution of hyaluronic acid in water was added 200 mg of the photo PAA prepared in Example 5. The viscous solution was spread onto a polytetrafluoroethylene (PTFE) textured surface, was allowed to dry, and was illuminated with ultraviolet light. The resulting film was removed from the PTFE surface as an intact film, the pattern of the textured PTFE being evident on the lower surface of the film. When wet with water, the film swelled but did not dissolve. A solution of hyaluronic acid alone was also spread on an identical film, dried and illuminated. The resulting film readily redissolved in water.

EXAMPLE 10: Polyethylene Glycol Co-immobilization onto Polycarbonate Membranes.

The mono benzoylbensyl ether of polyethylene glycol (BBE-PEG-OH) was synthesized using polyethylene glycol (HO-PEG-OH) by the following procedure: To polyethylene glycol (20 g, mol. wt. 8000) dissolved in 100 ml of dry tetrahydrofuran (THF) was added 60 mg of NaH followed by stirring under a positive N₂ pressure for 2 hours. 4-Bromomethylbenzophenone (344 mg) was added and the solution was stirred overnight under a positive N₂ pressure. The reaction was quenched by adding 267 mg of NH₄Cl in 2 ml of water. The THF was evaporated off, then the polymer was dissolved in 100 ml of saturated NaCl solution. The solution was extracted twice with 100 ml of CHCl₃. The chloroform solution was dried over Na₂SO₄. The solvent was evaporated and the resulting BBE-PEG-OH polymer was dissolved in and precipitated from toluene/ethyl ether.

A mixture of equal weights of BBE-PEG-OH, HO-PEG-OH and the BBE-PEG-BBE of Example 1 was dissolved at 0.5 mg/ml in a 50% isopropanol solution in water. Commercially available porous polycarbonate membranes were soaked in the resulting solution for 10 minutes and were dried in a cold air stream for 3 minutes. The membranes were exposed to UV radiation for 10 seconds, and then were washed in water for 15 minutes and air dried. The wettability of the membranes, as measured by the ease with which an aqueous solution passes through them, was tested by measuring the time required to pass 500 ml of water through 47 mm diameter discs under a pressure drop across the discs of 625 mm Hg. 14 Minutes were required for the discs prepared above, whereas 17 minutes were required for identical polycarbonate discs that were treated instead

by soaking in a polyvinyl pyrrolidone solution. For comparison, water under this pressure differential will not pass through an uncoated polycarbonate disc.

EXAMPLE 11: Synthesis of Polyionic Polymeric Coupling Compound

To 85 mg of N-(3-aminopropyl)methacrylamide in 5 ml of dry
5 dimethylsulfoxide was added 102 mg of benzoylbenzoyl-epsilon-aminocaproyl-N-oxysuccinimide and 40 ul of N,N,N¹N¹-tetramethylethylenediamine. The solution was stirred overnight, after which 1.0 gm of N-
acryloyltris(hydroxymethyl)aminomethane in 5 ml of DMSO and 50 mg of
azobis(isobutyronitrile) in 5 ml of DMSO were added. The solution was bubbled
10 with nitrogen for 5 minutes, sealed and stored at 55°C overnight. The resulting polymer was precipitated in ethanol, redissolved in 10 ml of deionized water, dialyzed vs. water and lyophilized.

EXAMPLE 12: Coimmobilization of Dextran Sulfate onto Polystyrene Beads
for Purifying Clotting Factors from Blood.

15 The ionic polymer prepared in Example 11 and the photo PAA prepared as in Example 5 were each dissolved in deionized water at 5 mg/ml. To each solution dextran sulfate (average molecular weight of 500,000) was added at 10 mg/ml. These solutions were incubated with polystyrene beads (297-1000 um diameter) for 24 hours at room temperature with mixing. The beads were then
20 filtered to remove coating solutions and air dried. The beads were then spread into thin layers on aluminum foil, illuminated with UV light for 1.5 minutes, shaken, and illuminated for an additional 1.5 minutes. The beads were then washed with deionized water and tested for ability to bind Azure A (which turns from blue to purple upon binding to a sulfated surface). By visual observation,

both preparations of coated beads were significantly colored but the beads coated with dextran sulfate coimmobilized with the polyionic polymeric coupling compound were significantly more purple than the beads coated with dextran sulfate coimmobilized with the photo PAA, which is indicative of a higher concentration of dextran sulfate coimmobilized with the ionic coupling compound.

5 While a preferred embodiment of the present invention has been described, it should be understood that various changes, adaptations and modifications may be made therein without departing from the spirit of the invention and the scope of the appended claims.

WHAT IS CLAIMED IS:

1. Method for immobilizing a chemical specie in a matrix that includes the chemical specie and a separate coupling compound to provide the matrix with properties of the chemical specie, the coupling Compound or both, comprising
 - a. bringing together in covalent bonding proximity a desired chemical specie and a polymeric coupling compound having at least two latent reactive groups per molecule, each latent reactive group being capable of covalently bonding to another coupling compound molecule or to the chemical specie; and
 - b. simultaneously activating the latent reactive groups to cause formation via covalent bonding of a three-dimensional molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound, and molecules of the coupling compound are covalently bonded to each other.
2. The method of claim 1 wherein the chemical specie is free of latent reactive groups that are activated during activation of the latent reactive groups of the coupling compound.
3. The method of claim 2 including the step of providing a mixture of the chemical specie and the polymeric coupling compound in a solvent solution, and forming a film from the solution before activation of the latent reactive groups.
4. The method of claim 3 including the step of spreading the solution upon a surface to form said film on the surface.

5. The method of claim 4 wherein said surface is the surface of a liquid.
6. The method of claim 4 wherein said surface is a solid surface.
7. The method of claim 6 wherein, upon activation of said latent
5 reactive groups, covalent bonds are simultaneously formed between the coupling compound and the surface.
8. The method of claim 2 wherein the coupling compound is a bifunctional polymeric coupling compound having a latent reactive group at each end.
10. 9. The method of claim 2 wherein the coupling compound has at least
one latent reactive group along its length spaced from its ends.
10. The method of claim 2 wherein said coupling compound is a photoderivatized vinyl polymer.
11. The method of claim 10 wherein said coupling compound is a
15 photoderivatized polyacrylamide or a photoderivatized polyvinylpyrrolidone.
12. The method of claim 2 wherein said coupling compound is a photoderivatized polyether.
13. The method of claim 12 wherein said coupling compound is a photoderivatized polyethylene glycol.
20. 14. The method of claim 2 wherein said polymeric coupling compound and chemical specie exhibit affinity permitting them in solution to assume a preferred orientation with respect to each other prior to activation of the latent reactive groups to facilitate covalent bonding therebetween when the latent reactive groups are activated, the method comprising the step of bringing the coupling

compound and the chemical specie into association permitting then to assume said preferred orientation prior to activation of the latent reactive groups of the coupling compound.

5 15. The method of claim 14 wherein the coupling compound is polyionic and the chemical specie is ionic, the coupling compound having a net charge opposite the net charge of the chemical specie, the method including the step of bringing the coupling compound and the chemical specie into association permitting ionic attraction therebetween prior to activation of the latent reactive groups of the coupling compound.

10 16. Method for forming a matrix having a first chemical specie immobilized therein and including free molecules of a second chemical specie whereby the second chemical specie molecules may be gradually released from the matrix, comprising

- 15 a. bringing together in covalent bonding proximity a first chemical specie and a polymeric coupling compound having at least two latent reactive groups per molecule, each latent reactive group being capable of covalently bonding to another coupling compound molecule or to the chemical specie;
- 20 b. simultaneously activating the latent reactive groups to cause formation via covalent bonding of a three-dimensional molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound, and molecules of the coupling compound are covalently bonded to each other, and

- c. contacting the three dimensional network with a second, different chemical species under conditions favoring incorporation of the second chemical species in said three dimensional network.
17. The method of claim 16 wherein said first chemical specie is an antithrombic agent and said second chemical species is an antibiotic.
18. Method for covalently immobilizing to a surface a chemical specie comprising
- a. forming on the surface a coating of the chemical specie together with and in covalent bonding proximity to a polymeric coupling compound having at least two latent reactive groups per molecule, each latent reactive group being capable of covalently bonding to another coupling compound molecule, to the chemical specie or to the surface; and
- b. simultaneously activating said latent reactive groups to cause formation via covalent bonds of a three dimensional molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound and molecules of the coupling compound are covalently bonded to each other and to the surface.
19. The method of claim 18 wherein the chemical specie is free of latent reactive groups that are activated during activation of the latent reactive groups of the coupling compound.

20. The method of claim 19 including the step of providing a mixture of the chemical specie and the polymeric coupling compound in a solvent solution, and forming a coating of the solution on the surface.

21. The method of claim 20 including the step of evaporating solvent from the solution prior to activating said latent reactive groups.

22. The method of claim 20 including the step of activating the latent reactive groups in the presence of the solvent.

23. The method of claim 19 including the steps of providing separate but contiguous and interdiffusing coating layers on the surface, one layer comprising a solution of the chemical specie and the other layer comprising a solution of the coupler.

24. The method of claim 23 wherein the layer comprising the solution of the coupler is positioned nearer the surface than the solution of the chemical specie.

25. The method of claim 19 wherein sufficient excess of the chemical specie is employed in the solution to provide free molecules of the specie which are not covalently coupled to the coupling compound upon reaction of the reactive groups, and wherein at least a portion of said free molecules are carried by and within the three dimensional network.

26. The method of claim 25 including the step of activating the latent reactive groups in the presence of the solvent.

27. The method of claim 20 wherein the coupling compound is polyionic and the chemical specie is ionic, the coupling compound having a net charge opposite the net charge of the chemical specie, the method including the

step of bringing the coupling compound and the chemical specie into association permitting ionic attraction therebetween prior to activation of the latent reactive groups of the coupling compound.

28. Method of providing a surface with a coating containing both
5 immobilized and free molecules of a desired chemical specie whereby free molecules of the specie may be gradually released from the surface and the immobilized molecules of the specie remain on the surface, comprising forming on the surface a coating of the chemical specie together with and in covalent bonding proximity to a polymeric coupling compound having at least two latent reactive
10 groups each capable of reaction upon activation to form covalent bonds to itself, to the chemical specie or to the surface, said specie being free of latent reactive groups that are activated upon activation of the latent reactive groups of the coupling compound; and simultaneously activating the latent reactive groups of the coupling compound to cause formation via covalent bonds of a three dimensional
15 molecular network in which molecules of the chemical specie are covalently bonded to molecules of the coupling compound and molecules of the coupling compound are covalently bonded to each other and to the surface, the method including the step of employing sufficient excess of the chemical specie to provide free molecules of the specie which are not covalently coupled to the coupling
20 compound upon reaction of the reactive groups, at least a portion of said free molecules being carried by and within the three dimensional network.

29. Method of providing a surface with a coating containing immobilized molecules of a first chemical specie and free molecules of a second, different chemical specie, whereby the second chemical specie molecules may be

gradually released from the surface, comprising forming on the surface a coating of the first chemical specie together with and in covalent bonding proximity to a polymeric coupling compound having at least two latent reactive groups each capable of reaction upon activation to form covalent bonds to itself, to the first
5 chemical specie or to the surface, said first chemical specie being free of latent reactive groups that are activated upon activation of the latent reactive groups of the coupling compound; and simultaneously activating the latent reactive groups of the coupling compound to cause formation via covalent bonds of a three dimensional molecular network in which molecules of the first chemical specie are
10 covalently bonded to molecules of the coupling compound and molecules of the coupling compound are covalently bonded to each other and to the surface, the method including the step of contacting the three dimensional network thus formed with said second chemical species under conditions favoring incorporation of the second chemical species in said three dimensional network.

15 30. The method of claim 29 wherein said first chemical specie is an antithrombic agent and said second chemical species is an antibiotic.

31. Method for covalently immobilizing to a surface a chemical specie comprising

20 a. forming on the surface a coating of the chemical specie together with and in covalent bonding proximity to a polymeric coupling compound having an average of at least two latent reactive groups per molecule and wherein the number of latent reactive groups per 100 Angstroms of the extended chain length of the polymer ranges from 0.05 to 12, each latent reactive group being capable upon

- activation by actinic radiation of covalent bonding to another polymer molecule, to the chemical specie or to the surface, the chemical specie being free of latent reactive groups that are activated upon activation of the latent reactive groups of the coupling compound; and
- 5
- b. simultaneously activating the latent reactive groups of the coupling compound to cause formation via covalent bonds of a three dimensional molecular network of said polymer molecules in which molecules of the chemical specie are covalently bonded to molecules of the polymer and molecules of the polymer are covalently bonded to each other and to the surface.
- 10

32. The method of claim 1 wherein the latent reactive groups of the coupling compound are groups which respond to specific applied external electromagnetic radiation to generate active species selected from the group consisting of carbenes, nitrenes and excited states of ketones.

15

33. The method of claim 32 wherein the latent reactive groups are photochemically reactive groups.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US93/01248

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :C12N 11/06; G01N 33/549

US CL :435/181; 436/532; 530/816

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 435/179, 180, 181; 436/530, 531, 532; 530/814, 815, 816

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO, A, 90/00887 (Guire et al) 08 February 1990, entire document.	1-33
Y	WO, A, 91/16425 (Sigrist et al) 31 October 1991, entire document.	1-33
Y	US, A, 3,975,350 (Hudgin et al) 17 August 1976, entire document.	16, 17, 25, 26, 28-30
Y	US, A, 3,959,078 (Guire) 25 May 1976, entire document.	1-33
Y	US, A, 4,722,906 (Guire) 02 February 1988, entire document.	1-33

 Further documents are listed in the continuation of Box C.
 See patent family annex.

* Special categories of cited documents:	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&"	document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means		
"P" document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

06 MAY 1993

Date of mailing of the international search report

17 MAY 1993

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Authorized officer

DAVID M. NAFF

Facsimile No. NOT APPLICABLE

Telephone No. (703) 308-0196

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US93/01248

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,979,959 (Guire) 25 December 1990, entire document.	1-33