

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 May 2004 (06.05.2004)

PCT

(10) International Publication Number
WO 2004/037215 A1

- (51) International Patent Classification⁷: **A61K 6/06**, C04B 28/06
- (21) International Application Number: PCT/SE2002/001480
- (22) International Filing Date: 21 August 2002 (21.08.2002)
- (25) Filing Language: Swedish
- (26) Publication Language: English
- (30) Priority Data: 0103189-7 26 September 2001 (26.09.2001) SE
- (71) Applicant (for all designated States except US): **DOXA AKTIEBOLAG** [SE/SE]; Axel Johanssons Gata 4-6, Kristallen, S-754 51 UPPSALA (SE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **HERMANSSON, Leif** [SE/SE]; Stenbrohultsvägen 20, 3 tr, S-757 58 UPPSALA (SE). **ENGQVIST, Håkan** [SE/SE]; Margaretavägen 12, S-741 44 KNIVSTA (SE).
- (74) Agents: **KYLIN, Peter** et al.; Hynell Patenttjänst AB, Patron Carls väg 2, S-683 40 HAGFORS/UDDEHOLM (SE).
- (81) Designated States (*national*): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK (utility model), SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: METHOD FOR THE MANUFACTURING OF A POWDERED MATERIAL, THE POWDERED MATERIAL AND A CERAMIC MATERIAL MANUFACTURED THERE FROM.

(57) Abstract: Powdered material, the binder phase of which mainly consists of a cement-based system, which powdered material has the capacity following saturation with a liquid reacting with the binder phase to hydrate to radiopaque and chemically bonded ceramic material. According to the invention, said binder phase mainly consists of CaOAl_2O_3 (ss) and/or $3\text{CaOAl}_2\text{O}_3$ (ss). The material also contains one or more heavy atom types with a density over 5g/cm^3 . The invention also relates to a method for manufacturing the powdered material and the chemically bonded ceramic material formed from the powdered material, in which said binder phase has a mol ratio $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$ (ss) to $3\text{CaOAl}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ (ss) of a maximum of 2:1.



WO 2004/037215 A1

METHOD FOR THE MANUFACTURING OF A POWDERED MATERIAL, THE POWDERED MATERIAL AND A CERAMIC MATERIAL MANUFACTURED THERE FROM.

TECHNICAL FIELD

- 5 The present invention relates to a radiopaque and chemically bonded ceramic material, the binder phase of which consists mainly of a cement-based system. The invention also relates to a powdered material that has the capacity to form said ceramic material when it is saturated with a liquid reacting with the binder phase, and a method of manufacturing this powdered material. The invention has been developed primarily with a view to dental and
10 orthopaedic purposes, but can also be applied in other application areas.

PRIOR ART AND PROBLEMS

- The present invention relates to binding agent systems of the cement system type, in particular the system $\text{CaO-Al}_2\text{O}_3\text{-(SiO}_2\text{)-H}_2\text{O}$. Studies carried out according to the
15 invention and earlier works (SE 463 493, SE 502 987 and SE 514 686) have produced results that indicate great potential for the system for strong and acid-resistant materials such as dental filling material. No other dental filling material existing today meets all the requirements in respect of biocompatibility, aesthetics and function that can be posed by patients and dental service staff.

20

- A description is given below of the practical demands that should generally be made on a dental filling material. Good handling ability with simple applicability in a cavity, moulding that permits good modellability, hardening/solidification that is sufficiently rapid for filling work and provides serviceability directly following a visit to the dentist.
- 25 Furthermore, high strength and corrosion resistance exceeding that of earlier filling materials, good biocompatibility, radiopacity for X-ray purposes, good aesthetics and safe handling for staff without any allergy-provoking or toxic additives in the material are required. Good long-term attributes as regards dimensional stability are also demanded.
- 30 In SE 463 493 it was described how a chemically bonded ceramic material, e.g. for dental purposes, can be caused to exhibit increased strength characteristics in that a powder body consisting of one or more hydraulic binding agents and possible ballast material is compacted at such a high external pressure and at so low a temperature that a well held-together raw compact is obtained without sintering reactions on compacting. The filling

density in this raw compact has increased to at least 1.3 times the initial filling density, which is defined as the filling density attained through shaking, vibration and/or light packing of the loose powder into a container. The user of the material prepares the same by saturating the raw compact with a hydration liquid prior to application of the material or in situ in a cavity, e.g. a tooth cavity.

More recently it has been shown in SE 502 987 that for cement systems complete hydration (which was regarded as reducing the risk of dimensional changes) can take place if complete soaking and subsequent compaction of the cement system takes place with the aid of a specially designed stopper.

More recently still it has been shown in SE 514 686 that a cement system of the type referred to in SE 463 493 or SE 502 987 can be caused to exhibit dimensionally stable long-term attributes if the material includes one or more expansion-compensating additives.

Materials that are produced according to SE 463 493, SE 502 987 or SE 514 686 have certainly proved to satisfy most of the demands that can be made according to the above on dental filling material. However, it has proved to be the case that the aesthetics of the material suffer, in spite of a colour similar to natural tooth colour, due to the fact that the material is opaque, which means that the material does not have adequate optical attributes to appear natural. Natural tooth transmits light, especially enamel. The manner in which the light is diffused through the tooth is described as translucent, which is to be differentiated from transparent. A definition of a translucent material reads: "A material that reflects, transmits and absorbs light. Objects cannot be seen clearly through the material when the material is placed between the object and the observer." (Lemire, Burk, Color in dentistry, J.M. Ney Company (1975)). One method of measuring translucence is to determine the ratio between the quantity of reflected light with a white background and with a black background (ISO 9917). A material is described as translucent if it has opacity of between 35 and 90%, as opaque above 90% and transparent below 35%. Natural dentine has an opacity of approx. 70%, while natural enamel has an opacity of around 35%. The ability of a filling material to imitate the appearance of the natural tooth depends to a large extent on the material being translucent.

In the abstract to JP 57209871 it is stated that translucence can be attained in a material of Portland cement and water glass.

In JP 51111828, a method is described for the production of $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$. In the
5 method, the raw materials for the binder phase are mixed with a surplus of water for 1-20
hours, with gradual heating from room temperature to 100°C . It is stated that hydrated
calcium aluminate in the form of $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$ is formed thereby. This hydrated
calcium aluminate is heated to between room temperature and 100°C and compressed at the
10 same time at 50-800 MPa for 10-60 minutes, possibly following the addition of further
water, to form a ceramic that is then dried at $60\text{-}250^\circ\text{C}$ without the water of crystallization
being evaporated. In the method described in JP 51111828, the mechanical compression of
already hydrated material is thus executed.

A related problem is that of achieving radiopacity at the same time as translucence, the
15 former being required in a filling material in order for it to be able to be distinguished
clearly from natural tooth and the onset of decay respectively in X-raying. The problem is
due to the fact that the X-ray contrast aids that are common nowadays, e.g. ZrO_2 and SnO_2 ,
interfere with the translucence. Even in an orthopaedic context or other non-biological
context it is often desirable to have radiopacity, even if the need for translucence does not
20 exist in this case.

Yet another problem is that of achieving the highest possible mechanical strength and
hardness in the ceramic material formed. It is also desirable here, especially in connection
with dental purposes, primarily fillings, for hardness to develop rapidly. Increased chemical
25 stability is also an aspect, in which the share of Al^{3+} in the material influences stability. It
is desirable for the quantity Al^{3+} to be minimized.

ACCOUNT OF THE INVENTION

One object of the present invention is to provide a ceramic material of the type stated in the
30 introduction, which material exhibits radiopacity, high mechanical strength and rapid
hardness development. The material shall preferably exhibit translucence at the same time,
at least if the material is intended for dental purposes. The invention also aims to provide a
powdered material that has the capacity following saturation with a liquid reacting with the
binder phase to hydrate to a chemically bonded ceramic material of the type intended

according to the invention. The invention also aims to offer a method for the manufacture of such a powdered material. The invention also aims to offer a ceramic filler material.

5 The desired objects and others are achieved according to the invention in that the binder phase of the powdered material mainly consists of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and in that the powdered material and thus the ceramic material contain an atom type with a density above 5 g/cm^3 , expressed as the density of the element that corresponds to the atom type.

10 In product terms, this means that the binder phase of the ceramic material formed has a mol ratio $\text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O}$ (ss) to $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$ (ss) of a maximum of 2:1, preferably of less than 1:5 and even more preferably less than 1:10.

15 The designation (ss) here means "solid solution". As will be described in greater detail later, this means that the binder phase can, but does not have to, contain other atom types that are present in solid solution in the binder phase, these replacing Ca and/or Al in full or in part. In the quantity ratios that are indicated, these other atom types are counted as Ca or Al.

20 The term binder phase is taken here to mean a cement content in the material, regardless of whether the powdered material or the hydrated ceramic product is in question.

In method terms, the object of the invention is achieved in that the method for the manufacture of the powdered material comprises the stages of:

- 25 a) Mixing raw materials for the binder phase containing Ca and Al in a ratio Ca:Al greater than or equal to 1:2.4, preferably greater than or equal to 1:2.2 and most preferably greater than or equal to 1:2, but no greater than 3:2.
- b) Physically reducing diffusion paths between atoms in the various raw materials,
- 30 c) Sintering the material at an increased temperature to form said binder phase, which consists mainly of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss), the material in stage a) and/or following stage c being brought to contain one or more heavy atom types with a density of over 5 g/cm^3 , expressed as the density for the element of the atom type.

On hydration, two final phases, $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ and $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$ will always be formed from conventional cement mixtures containing calcium aluminates of the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$. The invention is based on the knowledge that $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$ is not desirable as it can have a detrimental effect on the mechanical properties of the ceramic product. To have more than one phase also affects the refraction of light by the ceramic material, since $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$ and $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ have different refractive indices. It is therefore desirable to be able to manufacture a material that has only one phase, namely $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$, in the hydrated state, or at least to be able to manufacture a material that has a minimized content of $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$. By using only $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ as the binder phase, the hydrated material can be controlled to contain only $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$. $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ has a higher mechanical strength than $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$ and the refraction is also reduced, resulting in lower opacity, i.e. increased translucence. It is also the case that the hydration time is shortened, as fewer phases are formed, and that several stages in the hydration process are shorter. By instead using only $\text{CaO}\cdot\text{Al}_2\text{O}_3$ as the binder phase, the hydrated material can be controlled to contain $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ to $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$ in the ratio 1:2, which signifies a considerably greater proportion of $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ than if conventional powder mixtures containing calcium aluminates of the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ are used. Naturally mixtures of $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ can also be used for a reduced formation of $\text{Al}_2\text{O}_3\cdot 3\text{H}_2\text{O}$. However, the binder phase's content of $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ should be minimized and preferably omitted completely.

Yet another advantage of the ceramic material according to the invention is that it contains a lower proportion of Al ions than conventional calcium aluminate compositions, which ought to be an advantage in biological systems, especially in orthopaedic applications.

With a view to achieving radiopacity, the powdered material, and thus also the ceramic product, contains at least one heavy atom type with a density of over 5 g/cm^3 , preferably Zr, La, Ta, Zn, Ba and/or Sr. It is preferred that this/these atom type(s) form part of one or more compounds that also contain fluoride.

According to one aspect of the invention, the powdered material and thus also the ceramic product contains in addition to the binder phase one or more additives that contain the heavy atom type or atom types and that have a refractive index in visible light that deviates by a maximum of 15%, preferably a maximum of 10% and even more preferably a

maximum of 5% from the refractive index of the binder phase when the binder phase is hydrated. It is preferred that the additive is a glass, i.e. amorphous phase, most preferred a silicate glass.

- 5 Examples of additive materials that satisfy one or more of the stated requirements are: silicate glass, barium aluminium borosilicate glass, barium aluminium fluorosilicate glass, barium sulphate, barium fluoride, zirconium-zinc-strontium-borosilicate glass, apatite, fluorapatite and similar materials. In these materials barium can be exchanged for strontium and the materials can also contain fluoride. The additive materials can also have any
- 10 morphology or form, including: spheres, regular or irregular forms, whiskers, plates or the like. Particles of the additive material should be smaller than 50 μm , preferably smaller than 20 μm and even more preferred smaller than 10 μm . The size of the particles is measured by laser diffraction and calculated as the volume mean value $D[4,3]$. Additive materials of this type can be present in total quantities of at least 3% by volume, preferably
- 15 at least 5% by volume and even more preferred at least 10% by volume, but at most 55% by volume, preferably at most 50% by volume and even more preferred at most 45% by volume in the powdered material.

- According to the above, according to an alternative embodiment of the invention, the heavy
- 20 atom type or atom types can instead be included in the actual binder phase in such a way that they replace Ca and go into the solid solution (ss) in the binder phase, or alternatively form a compound that is close chemically and/or structurally. Apart from Ca positions (where Ba, Sr etc. can replace Ca), solid solution (ss) in e.g. $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$ is possible in H_2O positions (where oxides of Si, Ti, Zr etc. or fluorides can replace H_2O) and in Al
- 25 positions (where Fe, V, Sn, Bi and P etc. can replace Al), it being possible to influence properties apart from radiopacity, such as dimensional stability, chemical resistance etc. positively. To manufacture the binder phase, raw materials are preferably used in this case that contain a heavy atom type in the same group as Ca in the periodic system, suitably Ba and/or Sr, and in addition possibly fluoride. The advantage of this is that the actual binder
- 30 phase is radiopaque, and that the atoms that provide radiopacity do not interfere with translucence.

The two variants can naturally also be combined, additives with a heavy atom type being mixed into the powdered material together with the binder phase, which binder phase also contains heavy atom type(s).

- 5 In the same way as Ba and/or Sr can be used to replace Ca in the binder phase, with a view to achieving radiopacity and translucence at the same time, silicon in the form of fine crystalline silica (microsilica) and/or Portland cement (OPC) can be caused to go into solid solution (ss) in the binder phase, with a view to achieving dimensional stability of the ceramic product.

10

Solid solution (ss) in e.g. $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ can be produced in such a way that the solid solutions – with increased radiopacity – are non-hydrating. In these cases, these can be used advantageously as an inert phase to analogue solid solutions that are hydrating. This considerably increases the degree of freedom as regards the choice of raw materials and manufacturing criteria.

15

- The powdered material shall further satisfy the requirements indicated above for mouldability and durability, and be easy to handle in connection with its wetting and application in a cavity, e.g. a tooth cavity. The ceramic material formed should also, for dental applications, meet the demands made on such a material according to the above. It is especially preferred that the material exists in the form of a raw compact that has a degree of compaction of 40-80% by volume solid phase, preferably 50-70% by volume solid phase and even more preferred 55-65% by volume solid phase prior to hydration, in a manner such as described in SE 463 493. However, the invention is also fully applicable in connection with a wet-moulded material that exists in powder form prior to hydration, such as the material described in SE 502 987. The material can also contain one or more expansion-compensating additives suitable for giving the ceramic material dimensionally stable long-term attributes, such as described in SE 514 686. It is generally the case that said binder phase consists at least chiefly of calcium aluminate cement. However, the addition of one or more other cement binder phases to a total amount of less than 30% by volume can be used, preferably 1-20% by volume and even more preferred 1-10% by volume. Admixtures of ordinary Portland cement (OPC cement) or fine crystalline silica, which according to the above can possibly be included in solid solution in the binder phase, are used advantageously. Furthermore, it is desirable for the material to have a hardness of

20
25
30

at least 50 HV in the hydrated state, preferably at least 100 HV and even more preferably at least 140 HV.

DETAILED DESCRIPTION OF THE INVENTION

- 5 According to one aspect of the invention, the binder phase of the powdered material consists up to at least 70% by weight, preferably at least 80% by weight and even more preferably at least 90% by weight, of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss).

- 10 According to another aspect of the invention, the binder phase of the powdered material consists mainly of $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss), preferably up to at least 70% by weight, more preferably at least 80% by weight and most preferably at least 90% by weight. Alternatively, the binder phase of the powdered material consists mainly of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss), preferably up to at least 70% by weight, more preferably at least 80% by weight and most preferably at least 90% by weight. All mixtures between these alternatives are also
15 conceivable.

A first embodiment of the method for manufacturing the powdered material comprises the stages of:

- a) Mixing raw materials for the binder phase containing Ca and Al in a ratio Ca:Al
20 greater than or equal to 1:2.4, preferably greater than or equal to 1:2.2 and most preferably greater than or equal to 1:2, but no greater than 3:2.
- b) Mechanically reducing the diffusion paths between atoms in the various raw materials by pressurizing the raw materials, e.g. through cold isostatic pressing, at a pressure of 10-350 MPa, preferably 50-300 MPa and even more preferably 150-250 MPa, to form
25 a pressed powder body,
following which the powder body is finely divided into granules, preferably of less than 1 mm, even more preferably of less than 0.5 mm and most preferably of less than 0.3 mm in size,
- c) Sintering the material at a temperature of at least 1200°C to form said binder phase,
30 which consists mainly of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss),
- d) Grinding the material to a particle size of less than 80 μm , preferably less than 30 μm and even more preferably less than 20 μm ,
- e) Mixing the material with any additives,

- f) Pressing the material to form a raw compact with a degree of compaction of 40-80% by volume solid phase, preferably 50-70% by volume solid phase and even more preferredly 55-65% by volume solid phase.
- 5 According to one aspect of the method, said sintering is carried out at a minimum of 1250°C, preferably a minimum of 1275°C and even more preferredly at least 1300°C but at most 1600°C, preferably at most 1550°C and even more preferredly at most 1360°C, for at least 2 hours, preferably at least 4 hours and even more preferredly at least 6 hours, said sintering preferably being preceded by drying at an increased temperature that is below the
- 10 sintering temperature, e.g. at a temperature of around 1000°C.

A second embodiment of the method for manufacturing the powdered material comprises the stages of:

- a) Mixing raw materials for the binder phase containing Ca and Al in a ratio Ca:Al
- 15 greater than or equal to 1:2.4, preferably greater than or equal to 1:2.2 and most preferredly greater than or equal to 1:2, but no greater than 3:2.
- b) Chemically reducing the diffusion paths between atoms in the various raw materials by mixing the raw materials with 2-10 times more water than powder raw material, which mixture is heated to 30-100°C while stirring for 1-20 hours, preferably 2-5 hours, to
- 20 form $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$ in grain shape, following which any dissolved water is evaporated at a temperature lower than 250°C, preferably lower than 150°C, even more preferredly lower than 100°C but at least 50°C,
- c) Sintering the material through heat treatment at a temperature of over 250°C, preferably over 500°C and even more preferredly over 1000°C for at least 15 minutes,
- 25 preferably at least 1 hour, the water of crystallization evaporating and said binder phase being formed, which consists mainly of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss),
- d) Grinding the material to a particle size of less than 80 μm , preferably less than 30 μm and even more preferredly less than 20 μm ,
- e) Mixing the material with any additives,
- 30 f) Pressing the material to form a raw compact with a degree of compaction of 40-80% by volume solid phase, preferably 50-70% by volume solid phase and even more preferredly 55-65% by volume solid phase.

According to one aspect of the method, regardless of the embodiment, said raw materials containing Ca and Al consist of at least one of the raw materials in the group that consists of powdered CaO, CaCl₂, Ca(OH)₂ and CaCO₃ and at least one of the raw materials in the group that consists of powdered Al₂O₃, AlCl₃, Al₂O₃·H₂O and Al(OH)₃. In the event that it is desired to manufacture a binder phase that contains a heavy atom type in solid solution, the whole or parts of the raw materials containing Ca can be exchanged for Ba and/or Sr compound(s), e.g. BaO, BaCl₂, BaO₂, Ba(OH)₂·8H₂O, BaF₂, BaH₂, SrO, SrCl₂, Sr(OH)₂·8H₂O, SrF₂, SrH₂. 0 to 100%, preferably 20-50%, of the raw material containing Ca can thereby be exchanged for raw material containing Ba and/or Sr.

10

In the event that it is desired to manufacture a binder phase containing silicon and/or fluoride in solid solution, the raw materials can also contain fine crystalline silica (microsilica) and/or Portland cement (OPC) and/or fluorides of Na, Ca, Ba, Sr etc.

15 In the event that it is desired to manufacture a binder phase that contains metals such as iron, vanadium, titanium, zirconium, tin, bismuth in solid solution, the raw materials can also contain oxides, hydroxides or salts of these elements.

20 In the event that it is desired to manufacture a binder phase that contains phosphorus in solid solution, the raw materials can also contain Ca, Ba, Sr-phosphates and apatites including fluorapatite.

25 According to an aspect of the invention, it is preferred that the material, regardless of the embodiment, is ground in stage d and possibly screened so that the material has particle sizes of over 3 µm, preferably over 2 µm and even more preferably over 1 µm and/or particle sizes under 300 nm, preferably under 200 nm. The particle size is measured by laser diffraction and the volume-weighted mean value is indicated (also called D[4,3]).

30 It is preferred from the translucence viewpoint that the raw materials for the binder phase have a high whiteness, the whiteness value preferably exceeding 70, preferably exceeding 74 according to ASTM E313. The content of transition metals in the powder mixture should for the same reason be under 0.5% by weight, preferably under 0.4% by weight.

The translucence can be improved further by a low level of porosity of the finished ceramic material, preferably a porosity level of less than 20%, even more preferred of less than 10% and still more preferred of less than 5%.

- 5 Thanks to the invention, the ceramic material formed can be caused to have a translucence corresponding to 35-90%, preferably 40-85% and even more preferred 50-80% opacity. At the same time, a hardness of at least 50 HV, preferably at least 100 HV and even more preferred 140 HV can be achieved.
- 10 To manufacture a filler material, the method for manufacture according to the second embodiment can be interrupted after stage b. A filler material of this kind is a ceramic product in itself according to the invention, which can be used as an additive in stage e. The stirring in stage b can possibly be controlled in this case so that the selected desired form can be achieved for the filler particles, or also the grains can be post-treated to the desired
- 15 shape.

EXAMPLE 1

- A series of experiments was carried out to study the effect of different process parameters in the manufacture of calcium aluminate, $3\text{CaO}\cdot\text{Al}_2\text{O}_3$, and its influence on the material's
- 20 translucence and mechanical properties, without regard to radiopacity.

Description of raw materials

- Calcium aluminate of the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ forming part of e.g. calcium aluminate cement (Alcoa or alternatively Lafarge) CaO , $\text{Ca}(\text{OH})_2$, $\text{Al}(\text{OH})_3$, Al_2O_3 (Merck).
- 25

Examples a) – d) below describe

- a) Manufacture of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ at high temperature from CaO and Al_2O_3
- b) Manufacture of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ at low temperature from CaO and Al_2O_3
- 30 c) Manufacture of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ at high temperature from $\text{Ca}(\text{OH})_2$ and $\text{Al}(\text{OH})_3$
- d) Manufacture of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ at low temperature from $\text{Ca}(\text{OH})_2$ and $\text{Al}(\text{OH})_3$

The raw materials were mixed in such proportions that the mol ratio Ca:Al was 3:2.

Following mixing, the powder was subjected to cold isostatic pressing in examples a) – d) at 250 MPa for a green body. Following pressing, the green bodies were ground into small granules. The powder mixtures in examples a) – d) were then sintered according to the following cycles:

- 5
- a) 1000°C for 1 hour followed by 1480°C for 8 hours then cooling to room temperature for 1 hour.
 - b) 1000°C for 1 hour followed by 1350°C for 12 hours then cooling to room temperature for 1 hour.
 - 10 c) 1000°C for 1 hour followed by 1480°C for 4 hours then cooling to room temperature for 1 hour.
 - d) 1000°C for 1 hour followed by 1350°C for 6 hours then cooling to room temperature for 1 hour.

- 15 Verification (X-ray diffraction) of the resulting phase composition in examples a-d) following sintering showed that all the original powder has been converted to $3\text{CaO}\cdot\text{Al}_2\text{O}_3$

The powders in examples a-d) were ground in a ball mill with inert grinding balls of silicon nitride with a filling level of 35%. Isopropanol was used as the grinding liquid. Following grinding, all the powder had a grain size of less than 20 μm . Following evaporation of the solvent, cylindrical raw compacts were made with a diameter of 10 mm and a height of 1 mm, which were wetted with water. The material was then kept moist at 37°C for a week prior to measurements of translucence. The measurements of translucence were carried out according to ISO 9917 (100 means opaque and 35 to 90 means translucence). The hardness (Vickers method) of the material was measured after one week. The material was compared with a calcium aluminate cement containing the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ (LaFarge). The phase composition following hydration was also verified (X-ray diffraction (XRD)). The results are shown in Table 1.

Table 1

Sample designation	Hardness HV _{0.1}	Opacity (%) (C _{0.70})	Phase composition (XRD)
Reference	130	73	Al ₂ O ₃ ·3H ₂ O and 3CaO·Al ₂ O ₃ ·6H ₂ O
A	275	39	3CaO·Al ₂ O ₃ ·6H ₂ O
B	290	43	3CaO·Al ₂ O ₃ ·6H ₂ O
C	282	40	3CaO·Al ₂ O ₃ ·6H ₂ O
D	295	44	3CaO·Al ₂ O ₃ ·6H ₂ O

The results show that a material with increased hardness and improved translucence can be obtained by manufacturing the raw material for the material in a controlled manner with controlled phase composition.

EXAMPLE 2

A series of experiments was carried out to study the effect of different process parameters in the manufacture of calcium aluminate, CaO·Al₂O₃, and its influence on the material's translucence and mechanical properties, without regard to radiopacity.

Description of raw materials

Calcium aluminate of the phases CaO·Al₂O₃ and CaO·2Al₂O₃ forming part of e.g. calcium aluminate cement (Alcoa or alternatively Lafarge) CaO, Ca(OH)₂, Al(OH)₃, Al₂O₃ (Merck).

Examples a) – d) below describe

- a) Manufacture of CaO·Al₂O₃ at high temperature from CaO and Al₂O₃
- b) Manufacture of CaO·Al₂O₃ at low temperature from CaO and Al₂O₃
- c) Manufacture of CaO·Al₂O₃ at high temperature from Ca(OH)₂ and Al(OH)₃
- d) Manufacture of CaO·Al₂O₃ at low temperature from Ca(OH)₂ and Al(OH)₃

The raw materials were mixed in such proportions that the mol ratio Ca:Al is 1:2.

Following mixing, the powders were subjected to cold isostatic pressing in examples a) – d) at 250 MPa to a green body. Following pressing, the green

bodies were ground into small granules. The powder mixtures in examples a) – d) were then sintered according to the following cycles:

- e) 1000°C for 1 hour followed by 1480°C for 8 hours then cooling to room temperature for 1 hour.
- 5 f) 1000°C for 1 hour followed by 1350°C for 12 hours then cooling to room temperature for 1 hour.
- g) 1000°C for 1 hour followed by 1480°C for 4 hours then cooling to room temperature for 1 hour.
- 10 h) 1000°C for 1 hour followed by 1350°C for 6 hours then cooling to room temperature for 1 hour.

Verification (X-ray diffraction) of the resulting phase composition in examples a-d) following sintering showed that all the original powder has been converted to $\text{CaO} \cdot \text{Al}_2\text{O}_3$.

- 15 The powders in examples a-d) were ground in a ball mill with inert grinding balls of silicon nitride with a filling level of 35%. Isopropanol was used as the grinding liquid. Following grinding, all the powder had a grain size of less than 20 μm . Following evaporation of the solvent, cylindrical sample bodies were made with a diameter of 10 mm and a height of 1 mm, which were wetted with water. The material was then kept moist at 37°C for a week
- 20 prior to measurements of translucence. The measurements of translucence were carried out according to ISO 9917 (100 means opaque and 35 to 90 means translucence). The hardness (Vickers method) of the material was measured after one week. The materials were compared with a calcium aluminate cement containing the phases $\text{CaO} \cdot \text{Al}_2\text{O}_3$ and $\text{CaO} \cdot 2\text{Al}_2\text{O}_3$ (LaFarge) with the mol ratio 1:1. The phase composition following hydration
- 25 was also verified (X-ray diffraction (XRD)). The results are shown in Table 2.

Table 2

Sample designation	Hardness $\text{HV}_{0.1}$	Opacity (%) ($C_{0.70}$)	Phase composition (XRD), $\text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O} : 3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$
Reference	130	73	7:2
A	175	50	2:1
B	192	49	2:1
C	174	54	2:1
D	180	53	2:1

The results show that a material with increased hardness and improved translucence can be obtained by manufacturing the raw material for the material in a controlled manner with controlled composition of the binder phase.

5 EXAMPLE 3

A series of experiments was carried out to manufacture calcium aluminate with a solid solution of Ba and Sr ($3\text{CaO}\cdot\text{Al}_2\text{O}_3$ (ss)) and its influence on the material's radiopacity.

Description of raw materials

- 10 Calcium aluminate of the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ forming part of e.g. calcium aluminate cement (Alcoa or alternatively Lafarge) CaO , BaO , SrO , Al_2O_3 (Merck).

Examples a) – b) below describe

- a) Manufacture of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ (ss) from CaO , BaO and Al_2O_3
15 b) Manufacture of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ (ss) from CaO , SrO and Al_2O_3

The raw materials were mixed in such proportions that the mol ratio (Ca, Ba):Al in a) was 3:2 with the mol ratio Ca:Ba 2:1 and (Ca, Sr):Al in b) was 3:2 with the mol ratio Ca:Sr 1:1.

- 20 The powder mixtures were mixed with 1 part powder and 5 parts water with stirring and heating to 75°C . The water and the powder were mixed for 6 hours. Phase analysis of the powder formed showed that it consisted completely of $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 6\text{H}_2\text{O}$ (ss). This powder was heated up in an oven to 1000°C for 2 hours. Verification (X-ray diffraction) of the resulting phase composition in examples a-b) following heating showed that all the original
25 powder has been converted to $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ (ss).

- The powders in examples a-b) were ground in a ball mill with inert grinding balls of silicon nitride with a filling level of 35%. Isopropanol was used as the grinding liquid. Following grinding, all the powder had a grain size of less than $20\text{ }\mu\text{m}$. Following evaporation of the
30 solvent, cylindrical raw compacts were made with a diameter of 10 mm and a height of 1 mm, which were wetted with water. The material was then kept moist at 37°C for a week prior to measurements of radiopacity. The measurements of radiopacity were carried out according to ANSI/ADA Specification No. 27 (1 mm sample body as opaque as 2 mm Al).

The material was compared with a calcium aluminate cement containing the phases $\text{CaO} \cdot \text{Al}_2\text{O}_3$ and $\text{CaO} \cdot 2\text{Al}_2\text{O}_3$ (LaFarge). The results are shown in Table 3.

Table 3

Sample designation	Radiopacity
Reference	No
A	Yes
B	Yes

5

The results show that a radiopaque material consisting of only the binder phase can be obtained using the method according to the invention.

10 EXAMPLE 4

A series of experiments was carried out to manufacture calcium aluminate with a solid solution ($3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss)) and its influence on the material's radiopacity.

Description of raw materials

15 Calcium aluminate of the phases $\text{CaO} \cdot \text{Al}_2\text{O}_3$ and $\text{CaO} \cdot 2\text{Al}_2\text{O}_3$ forming part of e.g. calcium aluminate cement (Alcoa or alternatively Lafarge) CaO , CaF_2 , BaO , SrO , Fe_2O_3 , Al_2O_3 (Merck).

Examples a) – c) below describe

20

- e) Manufacture of $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) from CaO , BaO and Al_2O_3
- f) Manufacture of $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) from CaO , SrO and Al_2O_3
- g) Manufacture of $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) from CaO , SrO , Fe_2O_3 and Al_2O_3

25 The raw materials in the examples were mixed according to the mol ratios:

- a) $(\text{Ca}, \text{Ba}) : \text{Al}$ as 3:2 with the mol ratio $\text{Ca} : \text{Ba}$ 2:1
- b) $(\text{Ca}, \text{Sr}) : \text{Al}$ as 3:2 with the mol ratio $\text{Ca} : \text{Sr}$ 1:1
- c) $(\text{Ca}, \text{Sr}) : (\text{Al} : \text{Fe})$ as 3:2 with the mol ratios $\text{Ca} : \text{Sr}$ 1:1 and $\text{Al} : \text{Fe}$ 5:1

Following mixing, the powder was subjected to cold isostatic pressing in examples a) – c) at 250 MPa for a green body. Following pressing, the green bodies were ground into small granules. The powder mixtures in examples a) – c) were then sintered according to the following cycle: 1000°C for 1 hour followed by 1480°C for 8 hours then cooling to room temperature for 1 hour.

Verification (X-ray diffraction) of the resulting phase composition in examples a-c) following sintering showed that all the original powder has been converted to $3\text{CaO}\cdot\text{Al}_2\text{O}_3$ (ss).

The powders in examples a-c) were ground in a ball mill with inert grinding balls of silicon nitride with a filling level of 35%. Isopropanol was used as the grinding liquid. Following grinding, all the powder had a grain size of less than 20 μm . Following evaporation of the solvent, cylindrical raw compacts were made with a diameter of 10 mm and a height of 1 mm, which were wetted with water. The material was then kept moist at 37°C for a week prior to measurements of radiopacity. The measurements of radiopacity were carried out according to ANSI/ADA Specification No. 27 (1 mm sample body as opaque as 2 mm Al). The material was compared with a calcium aluminate cement containing the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ (LaFarge). The results are shown in Table 4.

Table 4

Sample designation	Radiopacity
Reference	No
A	Yes
B	Yes
C	Yes

The results show that a radiopaque material consisting of only the binder phase can be obtained using the method according to the invention.

EXAMPLE 5

Experiments were carried out to study the effect of the phase composition of the binder phase on the development of hardness with time for the material, without regard to radiopacity.

Description of raw materials

Calcium aluminate of the phases $\text{CaO} \cdot \text{Al}_2\text{O}_3$ and $\text{CaO} \cdot 2\text{Al}_2\text{O}_3$ forming part of e.g. calcium aluminate cement (Alcoa or alternatively Lafarge). Calcium aluminate cement of the phase $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ manufactured according to Example 1 and calcium aluminate of the phase $\text{CaO} \cdot \text{Al}_2\text{O}_3$ manufactured according to Example 2.

Examples a) – c) below describe

- a) The hardness as a function of time for calcium aluminate consisting of the phases $\text{CaO} \cdot \text{Al}_2\text{O}_3$ and $\text{CaO} \cdot 2\text{Al}_2\text{O}_3$ (reference)
 - 10 b) The hardness as a function of time for calcium aluminate consisting of the phase $\text{CaO} \cdot \text{Al}_2\text{O}_3$
 - c) The hardness as a function of time for calcium aluminate consisting of the phase $3\text{CaO} \cdot \text{Al}_2\text{O}_3$.
- 15 The powders in examples a-c) were ground in a ball mill with inert grinding balls of silicon nitride with a filling level of 35%. Isopropanol was used as the grinding liquid. Following grinding, all the powder had a grain size of less than 20 μm . Following evaporation of the solvent, cylindrical sample bodies were made with a diameter of 10 mm and a height of 1 mm, which were wetted with water. The material was then kept moist at 37°C for a week
- 20 between measurements of hardness (Vickers method load 100g). Measurements were carried out after 1, 2, 4, 8 and 16 days. The results are shown in Table 5.

Table 5

Material	Hardness 1 day	Hardness 2 days	Hardness 4 days	Hardness 8 days	Hardness 16 days
A	83	98	117	127	141
B	110	132	150	175	180
C	160	200	230	281	285

- 25 The results show that the hardness is developed more rapidly with time due to the fact that the raw material for the material was manufactured in a controlled manner with controlled composition of the binder phase.

EXAMPLE 6

A series of experiments was carried out to manufacture inert filler particles with solid solution ($3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 3\text{SiO}_2$ (ss)) and to study their influence on the material's radiopacity.

5 *Description of raw materials*

Calcium aluminate of the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ forming part of e.g. calcium aluminate cement (Alcoa or alternatively Lafarge) CaO , CaF_2 , SiO_2 , SrO , Fe_2O_3 , Al_2O_3 (Merck).

- 10 The raw materials were mixed according to the mol ratios (Ca, Sr):(Al, Fe):(Si) 3:2:3 with the mol ratio Ca:Sr 1:1, Al:Fe 5:1 and $\text{CaO}:\text{CaF}_2$ 10:1.

- Following mixing, the powder was subjected to cold isostatic pressing at 250 MPa for a green body. Following pressing, the green bodies were ground into small granules. The
15 powder mixture was then sintered according to the following cycle: 1000°C for 1 hour followed by 1480°C for 8 hours then cooling to room temperature for 1 hour.

- Verification (X-ray diffraction) of the resulting phase composition in examples a-c) following sintering showed that all the original powder has been converted to
20 $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot\text{SiO}_2$ (ss).

- The powder was ground together with 70% by volume binder phase consisting of $3\text{CaO}\cdot\text{Al}_2\text{O}_3$, manufactured according to EXAMPLE 1, in a ball mill with inert grinding balls of silicon nitride with a filling level of 35%. Isopropanol was used as the grinding
25 liquid. Following grinding, all the powder had a grain size of less than $20\text{ }\mu\text{m}$. Following evaporation of the solvent, cylindrical raw compacts were made with a diameter of 10 mm and a height of 1 mm, which were wetted with water. The material was then kept moist at 37°C for a week prior to measurements of radiopacity. The measurements of radiopacity were carried out according to ANSI/ADA Specification No. 27 (1 mm sample body as
30 opaque as 2 mm Al). The material was compared with a calcium aluminate cement containing the phases $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ (LaFarge). The results are shown in Table 6.

Table 6

Sample designation	Radiopacity
Reference	No
Material	Yes

The results show that a radiopaque material can be obtained by causing the powdered material according to the invention to contain inert particles.

5

The invention is not restricted to the embodiments described, but can be varied within the scope of the claims.

CLAIMS

1. Powdered material, the binder phase of which mainly consists of a cement-based system, which powdered material has the capacity following saturation with a liquid
5 reacting with the binder phase to hydrate to a radiopaque and chemically bonded ceramic material, characterized in that said binder phase mainly consists of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and that the powdered material contains one or more heavy atom types with a density over 5 g/cm^3 , expressed as the density for the element of the atom type.
- 10 2. Powdered material according to claim 1, characterized in that said binder phase consists up to at least 70% by weight, preferably at least 80% by weight and even more preferred at least 90% by weight of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss).
- 15 3. Powdered material according to claim 1 or 2, characterized in that said binder phase mainly consists of $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss), preferably up to at least 70% by weight, even more preferred at least 80% by weight and most preferred at least 90% by weight.
- 20 4. Powdered material according to claim 1 or 2, characterized in that said binder phase mainly consists of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss), preferably up to at least 70% by weight, even more preferred at least 80% by weight and most preferred at least 90% by weight.
- 25 5. Powdered material according to any of the above claims, characterized in that said heavy atom type consists of one or more atom types in the group that consists of V, Fe, Zr, La, Bi, Sn, Ta, Zn, Ba and/or Sr.
- 30 6. Powdered material according to any of the above claims, characterized in that it contains one or more additives that contain the heavy atom type or atom types and that have a refractive index in visible light that deviates by at most 15%, preferably at most 10% and even more preferred at most 5% from the refractive index of the binder phase when the binder phase is hydrated, said additives preferably consisting of a glass, most preferred a silicate glass.

7. Powdered material according to any of the above claims, characterized in that the heavy atom type or atom types are present in solid solution (ss) in the binder phase, the heavy atom type or atom types preferably consisting of one or more heavy atom types in group 2 in the periodic system and even more preferred consisting of Ba and/or Sr,
5 which fully or partly replaces Ca in the binder phase.
8. Powdered material according to any of the above claims, characterized in that silicon and/or fluoride are present in solid solution (ss) in the binder phase, preferably in raw material in the form of fine crystalline silica and/or Portland cement and/or fluorides of
10 Na, Mg, Mn, Ca, Sr or Ba.
9. Powdered material according to any of the above claims, characterized in that iron and/or phosphorus are present in solid solution (ss) in the binder phase, preferably in raw material in the form of iron oxides, iron hydroxides or salt of iron and/or
15 phosphorus in the form of phosphates of Ca, Ba, Sr or as apatites, preferably fluorapatite.
10. Powdered material according to any of the above claims, characterized in that it contains non-hydrated inert material, preferably of the type $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot \text{X}$ (ss), in
20 which X consists of an oxide or fluoride.
11. Powdered material according to any of the above claims, characterized in that it is present in the form of a raw compact that has a degree of compaction of 40-80% by volume solid phase, preferably 50-70% by volume solid phase and even more
25 preferred 55-65% by volume solid phase.
12. Powdered material according to any of the above claims, characterized in that it is present in loose powder form or in the form of granules.
- 30 13. Method for the manufacture of a powdered material, the binder phase of which mainly consists of a cement-based system, which powdered material has the capacity following saturation with a liquid reacting with the binder phase to hydrate to a radiopaque and chemically bonded ceramic material, characterized by the stages of:

- a) Mixing raw materials for the binder phase containing Ca and Al in a ratio Ca:Al greater than or equal to 1:2.4, preferably greater than or equal to 1:2.2 and most preferred greater than or equal to 1:2, but no greater than 3:2.
- b) Physically reducing diffusion paths between atoms in the various raw materials,
- 5 c) Sintering the material at an increased temperature to form said binder phase, which consists mainly of $\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss) and/or $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ (ss); the material in stage a and/or following stage c being brought to contain one or more heavy atom types with a density over 5 g/cm^3 , expressed as the density of the element of the atom type.
- 10 14. Method according to claim 13, characterized in that said diffusion paths are reduced mechanically or chemically.
- 15 15. Method according to claim 13, characterized in that the diffusion paths are reduced mechanically in stage b, stage b including pressurizing of the raw material, preferably through cold isostatic pressing, at a pressure of 10-350 MPa, preferably 50-300 MPa and even more preferred 150-250 MPa, to forming of a pressed powder body, following which the powder body is preferably finely divided into granules, preferably of less than 1 mm, even more preferred less than 0.5 mm and most preferred less
- 20 than 0.3 mm in size.
- 25 16. Method according to claim 15, characterized in that said sintering in stage c is executed at at least 1200°C , preferably at least 1250°C and even more preferred at least 1275°C and most preferred at least 1300°C , but at most 1600°C , preferably at most 1550°C and even more preferred at most 1360°C for at least 2 hours, preferably at least 4 hours and even more preferred at least 6 hours, said sintering preferably being preceded by drying at an increased temperature below the sintering temperature.
- 30 17. Method according to claim 13, characterized in that the diffusion paths are reduced chemically in stage b, stage b including mixing of the raw materials with preferably 2-10 times more water than powdered raw material, which mixture is heated to preferably $30-100^\circ\text{C}$ with stirring for preferably 1-20 hours, even more preferred 2-5 hours, to form $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$ (ss), following which any dissolved water is

preferably evaporated at a temperature lower than 250°C, preferably lower than 150°C, even more preferred lower than 100°C, but at least 50°C.

- 5 18. Method according to claim 17, characterized in that said sintering in stage c is executed at a temperature above 250°C, preferably above 500°C and even more preferred over 1000°C for at least 15 minutes, preferably at least 1 hour, water of crystallization evaporating.
- 10 19. Method according to any of claims 13-18, characterized in that said raw materials containing Ca and Al in stage a consist of at least one of the raw materials in the group that consists of powdered CaO, CaCl₂, Ca(OH)₂ and CaCO₃ and at least one of the raw materials in the group that consists of powdered Al₂O₃, Al₂O₃·H₂O, AlCl₃ and Al(OH)₃.
- 15 20. Method according to any of claims 13-19, characterized in that said heavy atom type consists of one or more atom types in the group that consists of Zr, La, Ta, Zn, Ba and/or Sr.
- 20 21. Method according to any of claims 13-20, characterized in that up to 100%, preferably 20-50%, of the raw material containing Ca in stage a is exchanged for a raw material or raw materials containing one or more heavy atom types in group 2 in the periodic system, preferably a raw material or raw materials containing Ba and/or Sr.
- 25 22. Method according to any of claims 13-21, characterized in that the raw materials in stage a also contain fine crystalline silica (microsilica) and/or Portland cement (OPC).
- 30 23. Method according to any of claims 13-22, characterized by, following stage c, a stage:
d) the material is ground to a particle size of less than 80 µm, preferably less than 30 µm and even more preferred less than 20 µm.
24. Method according to one of claims 13 or 23, characterized by, following stage c or d, a stage:
e) the material is mixed with additives, preferably containing one or more additives that contain the heavy atom type or atom types and that preferably have a refractive

index in visible light that deviates by at most 15%, preferably at most by 10% and even more preferred by at most by 5% from the refractive index of the binder phase when the binder phase is hydrated, said additives preferably consisting of a glass, most preferred a silicate glass.

- 5
25. Method according to one of claims 23 or 24, characterized by, following stage d or e, a stage:
- f) the material is pressed to a raw compact with a degree of compaction of 40-80% by volume solid phase, preferably 50-70% by volume solid phase and even more
- 10 preferred 55-65% by volume solid phase.
26. Radiopaque and chemically bonded ceramic material, the binder phase of which mainly consists of a cement-based system, preferably for dental purposes, characterized in that said binder phase has a mol ratio $\text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O}$ (ss) to
- 15 $3\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{H}_2\text{O}$ (ss) of a maximum of 2:1, preferably less than 1:5 and even more preferred less than 1:10, and that the material also contains one or more heavy atom types with a density over 5 g/cm^3 , expressed as the density of the element of the atom type.
- 20 27. Ceramic material according to claim 26, characterized in that it has translucence corresponding to 35-90%, preferably 40-85% and even more preferred 50-80% opacity.
28. Ceramic material according to any of claims 26-27, characterized in that it has a
- 25 hardness of at least 50 MV, preferably at least 100 MV and even more preferred at least 140 MV.
29. Ceramic material according to claim 26, characterized in that it is a filler material in particle form.
- 30
30. Ceramic material according to any of claims 26-29, characterized in that it consists of a hydrated powdered material according to any of claims 1-12.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 02/01480

A. CLASSIFICATION OF SUBJECT MATTER

IPC7: A61K 6/06, C04B 28/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: A61K, C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 0071082 A1 (ALBERT-LUDWIGS-UNIVERSITÄT FREIBURG), 30 November 2000 (30.11.00) --	1-30
A	DATABASE WPI Week 198306 Derwent Publications Ltd., London, GB; Class L02, AN 1983-13228K & JP 57209871 A (YOIDA S), 23 December 1982 (1982-12-23) abstract --	6-12, 24-25
A	WO 0176534 A1 (DOXA CERTEX AKTIEBOLAG), 18 October 2001 (18.10.01) --	1-30

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"B" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

4 December 2002

Date of mailing of the international search report

05-12-2002

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Marie Karlsson/EÖ
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 02/01480

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 0021489 A1 (DOXA CERTEX AKTIEBOLAG), 20 April 2000 (20.04.00) --	1-30
A	DATABASE WPI Week 197646 Derwent Publications Ltd., London, GB; Class L02, AN 1976-86141X & JP 51 111828 A (MATSUSHITA ELECTRIC WORKS LTD), 2 October 1976(1976-10-02) abstract -- -----	1-30

INTERNATIONAL SEARCH REPORT

Information on patent family members

28/10/02

International application No.

PCT/SE 02/01480

Patent document cited in search report			Publication date	Patent family member(s)		Publication date
WO	0071082	A1	30/11/00	AU	5068700 A	12/12/00
				DE	19923956 A	30/11/00
WO	0176534	A1	18/10/01	AU	4701901 A	23/10/01
				AU	6035400 A	09/01/01
				EP	1204891 A	15/05/02
				SE	516264 C	10/12/01
				SE	0001321 A	12/10/01
				US	2002088796 A	11/07/02
WO	0021489	A1	20/04/00	AU	1305300 A	01/05/00
				BR	9914430 A	26/06/01
				CA	2342584 A	20/04/00
				CN	1323188 T	21/11/01
				EP	1121087 A	08/08/01
				HU	0103371 A	28/12/01
				NO	20011848 A	12/06/01
				SE	514686 C	02/04/01
				SE	9803502 A	13/04/00