

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 January 2009 (08.01.2009)

PCT

(10) International Publication Number
WO 2009/005208 A1

(51) International Patent Classification:
G03G 9/08 (2006.01)

(74) Agent: **PARK, Yong Soon**; 2nd Floor, Sangwon Bldg.,
636-15, Yeoksam-dong, Gangnam-gu, Seoul 135-908,
(KR).

(21) International Application Number:
PCT/KR2008/001482

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date: 17 March 2008 (17.03.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10-2007-0067759 5 July 2007 (05.07.2007) KR

(71) Applicant (*for all designated States except US*): **LG CHEM. LTD.** [KR/KR]; 20, Yoido-dong Young-dungpo-gu, Seoul 150-721 (KR).

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **JANG, Wook** [KR/KR]; 101-905, Samsung-Pureun Apt., Jeonmin-dong, Yuseong-gu, Daejeon 305-390 (KR). **LEE, Chang Soon** [KR/KR]; 212-402, Daewoo-Prugio Gwanpyeong-dong, Yuseong-gu, Daejeon 305-509 (KR).

Published:

— with international search report

(54) Title: METHOD OF PRODUCING POLYMERIZED TONER

(57) Abstract: A method for producing a toner is provided. The method comprises the steps of (1) dispersing a water-soluble polyvinyl alcohol having a degree of polymerization of 1,500 to 2,500 and a degree of saponification of 75 to 98% in an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol, (2) preparing a mixture of monomers, (3) mixing the aqueous dispersion with the monomer mixture, and (4) polymerizing the monomers.

WO 2009/005208 A1

Description

METHOD OF PRODUCING POLYMERIZED TONER

Technical Field

- [1] The present invention relates to a method for producing a polymerized toner, and more specifically to a method for producing a polymerized toner, characterized in that a water-soluble polyvinyl alcohol is dispersed in an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol.

[2]

Background Art

- [3] Toners are used for the development of electrophotographic images and in a variety of electrostatic printing and copying apparatuses. Toners refer to coating substances that can be transferred and fixed to objects to form desired patterns thereon. As computer-aided documentation has been generalized in recent years, there has been a rapidly increasing demand for imaging apparatuses, such as printers. In response to this demand, the use of toners is also on the rise.
- [4] Methods for the production of toners are largely classified into two types of methods based on pulverization and polymerization. The first type of methods based on pulverization is most widely known. According to a typical method based on pulverization, a resin and a pigment is melt-mixed or extruded, pulverized and sorted on the basis of size to obtain toner particles. However, the toner particles have a broad particle diameter distribution and are very irregular in shape (e.g., sharp edges), which are disadvantageous in terms of charge properties and flowability.
- [5] To overcome the above disadvantages of the first type of methods, the second type of methods based on polymerization for the production of spherical toner particles has been proposed. It is known that the second type of methods can be carried out by emulsion polymerization/aggregation and suspension polymerization. According to emulsion polymerization, however, the size distribution of particles is difficult to control and the reproducibility of toner quality remains problematic. For these reasons, suspension polymerization is predominantly employed in preference to emulsion polymerization.
- [6] However, toner particles produced by suspension polymerization also have a broad size distribution, which necessitates an additional separation step. Further, a toner having undergone size separation is consumed in a large amount during printing and is unsatisfactory in terms of transferability.
- [7]

Disclosure of Invention

Technical Problem

- [8] The present invention has been made in view of the above problems, and it is an object of the present invention to provide a method for producing a polymerized toner that has a preferable volume average particle diameter, has a narrow particle size distribution, is consumed in a small amount during printing and is transferred at a high rate.

[9]

Technical Solution

- [10] In order to accomplish the object of the present invention, there is provided a method for producing a toner whose volume average particle diameter (d_v) is between 5 and 10 μm and the ratio d_v/d_p , *i.e.* volume average particle diameter (d_v)/number average particle diameter (d_p), is not larger than 1.5, the method being characterized by the addition of a water-soluble polyvinyl alcohol having a degree of polymerization and a degree of saponification in particular ranges to an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol.

- [11] Specifically, the method of the present invention comprises the following steps:

- [12] (1) dispersing a water-soluble polyvinyl alcohol having a degree of polymerization of 1,500 to 2,500 and a degree of saponification of 75 to 98% in an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol;
- [13] (2) preparing a mixture of monomers;
- [14] (3) mixing the aqueous dispersion with the monomer mixture; and
- [15] (4) polymerizing the monomers.

[16]

Advantageous Effects

- [17] According to the method of the present invention, a water-soluble polyvinyl alcohol having a degree of polymerization and a degree of saponification in particular ranges is added to an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol, and particular monomers are subjected to suspension polymerization to produce a polymerized toner whose volume average particle diameter (d_v) is between 5 and 10 μm and the ratio d_v/d_p is not greater than 1.5.

[18]

Best Mode for Carrying Out the Invention

- [19] The present invention will now be described in detail.

- [20] The present invention provides a method for producing a toner, comprising the steps of dispersing a water-soluble polyvinyl alcohol having a degree of polymerization of 1,500 to 2,500 and a degree of saponification of 75 to 98% in an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol, preparing a mixture of

monomers, mixing the aqueous dispersion with the monomer mixture, and polymerizing the monomers.

[21] In an embodiment, the polymerization is carried out by suspension polymerization as follows.

[22] **(1) Preparation of Polymerized Toner**

[23] A water-soluble polyvinyl alcohol (PVA) is added to an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol. At this time, the polyvinyl alcohol is added in an amount of 1 to 10 parts by weight, based on 100 parts by weight of the aqueous dispersion.

[24] Examples of monomers suitable for use in the present invention include aromatic vinyl monomers, acrylate monomers, methacrylate monomers, diene monomers, and mixtures thereof. Optionally, an acidic or basic olefin monomer may be added to the monomer mixture.

[25] Specifically, the monomer mixture includes 30 to 95 parts by weight of an aromatic vinyl monomer, 5 to 70 parts by weight of at least one monomer selected from the group consisting of acrylate, methacrylate and diene monomers, optionally 0.1 to 30 parts by weight of an acidic or basic olefin monomer, 1 to 20 parts by weight of a pigment, 0.1 to 30 parts by weight of a wax, 0.001 to 10 parts by weight of a crosslinking agent, 0.1 to 20 parts by weight of a charge control agent, and 0.001 to 8 parts by weight of a molecular weight modifier, based on the total weight of all monomers used.

[26] 1 to 60 parts by weight of the monomer mixture is mixed with 100 parts by weight of the aqueous dispersion to obtain a mixed solution.

[27] Polymerization is carried out while applying a shear force to the mixed solution using a homogenizer to prepare toner cores.

[28] If required, 0.01 to 10 parts by weight of at least one polar polymer selected from polyesters and styrene-acrylate polymers may be added to the monomer mixture.

[29] As the aromatic vinyl monomer, there may be used, for example, styrene, monochlorostyrene, methylstyrene or dimethylstyrene. The aromatic vinyl monomer is preferably used in an amount of 30 to 95 parts by weight, based on the total weight of all monomers used.

[30] As the acrylate monomer, there may be used, for example, methyl acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate, dodecyl acrylate or 2-ethylhexyl acrylate. As the methacrylate monomer, there may be used, for example, methyl methacrylate, ethyl methacrylate, n-butyl methacrylate, isobutyl methacrylate, dodecyl methacrylate or 2-ethylhexyl methacrylate. As the diene monomer, there may be used, for example, butadiene or isoprene.

[31] At least one monomer selected from the acrylate, methacrylate and diene monomers

is preferably used in an amount of 5 to 70 parts by weight, based on the total weight of all monomers used.

- [32] As the acidic olefin monomer, for example, an α,β -ethylenically unsaturated compound having at least one carboxyl group may be used. As the basic olefin monomer, there may be used, for example, a methacrylic acid ester, a methacrylamide, a vinylamine or a diallylamine of an aliphatic alcohol having at least one group selected from amine and quaternary ammonium groups, or an ammonium salt thereof. It is preferable to use at least one olefin monomer selected from the acidic and basic olefin monomers in an amount of 0.1 to 30 parts by weight, based on the total weight of all monomers used.
- [33] The wax may be selected from: petroleum waxes, such as paraffin wax, micro-crystalline wax and ceresin wax; natural waxes, such as carnauba wax; synthetic waxes, such as ester wax, polyethylene wax and polypropylene wax; and mixtures thereof. It is preferable to use the wax in an amount of 0.1 to 30 parts by weight, based on the total weight of all monomers used.
- [34] The molecular weight modifier may be selected from mercaptan compounds, such as t-dodecyl mercaptan and n-dodecyl mercaptan, and mixtures thereof. It is preferable to use the molecular weight modifier in an amount of 0.001 to 8.000 parts by weight, based on the total weight of all monomers used.
- [35] As the pigment, there may be used: an inorganic pigment selected from metal powder, metal oxide, carbon, sulfide, chromate and ferrocyanide pigments; an organic pigment selected from azo dye, acidic dye, basic dye, mordant dye, phthalocyanine, quinacridone and dioxane pigments; or a mixture thereof. It is preferable to use the pigment in an amount of 1 to 20 parts by weight, based on the total weight of all monomers used.
- [36] As the charge control agent, there may be used: a cationic charge control agent, such as a nigrosine type acidic dye, a higher aliphatic metal salt, an alkoxyamine, a chelate, a quaternary ammonium salt, an alkylamide, a fluorine-treated activator or a naphthenic acid metal salt; an anionic charge control agent, such as an acidic organic complex, chlorinated paraffin, a chlorinated polyester, a sulfonylamine of copper phthalocyanine or a styrene-acrylate polymer having sulfonic acid groups; or a mixture thereof. It is preferable to use the charge control agent in an amount of 0.1 to 20 parts by weight, based on the total weight of all monomers used.
- [37] As the crosslinking agent, there may be used, for example, divinylbenzene, ethylene dimethacrylate, ethylene glycol dimethacrylate, diethylene glycol diacrylate, 1,6-hexamethylene diacrylate, allyl methacrylate, 1,1,1-trimethylolpropane triacrylate, triallylamine or tetraallyloxyethane. It is preferable to use the crosslinking agent in an amount of 0.001 to 10 parts by weight, based on the total weight of all monomers used.

- [38] The monomer mixture may further include 0.01 to 5 parts by weight of a reaction initiator, based on the total weight of all monomers used. An oil-soluble or water-soluble initiator can be used as the reaction initiator. Specific examples of suitable reaction initiators include azo initiators, such as azobisisobutyronitrile and azobisvaleronitrile; organic peroxides, such as benzoyl peroxide and lauroyl peroxide; and generally used water-soluble initiators, such as potassium persulfate and ammonium persulfate. The reaction initiator is preferably used in an amount of 0.01 to 5.00 parts by weight and more preferably 0.1 to 2.0 parts by weight, based on the total weight of all monomers used.
- [39] The water-soluble polyvinyl alcohol (PVA) has a degree of polymerization of 1,500 to 2,500 and preferably 1,700 to 2,100. The water-soluble polyvinyl alcohol (PVA) has a degree of saponification of 75 to 98% and preferably 85 to 95%. If the degree of polymerization of the polyvinyl alcohol is lower than 1,500, it is difficult to sufficiently disperse the monomer mixture in the aqueous dispersion. Meanwhile, if the degree of polymerization of the polyvinyl alcohol is greater than 2,500, the solubility of the polyvinyl alcohol in the aqueous medium is lowered, making it difficult to render the aqueous dispersion homogeneous. If the degree of saponification of the polyvinyl alcohol is less than 75%, the polyvinyl alcohol is less soluble with increasing temperatures (60°C and 90°C) to precipitate in the aqueous medium, making it impossible to properly disperse the monomer mixture in the aqueous dispersion. Meanwhile, if the degree of saponification of the polyvinyl alcohol exceeds 98%, the hydrophilicity of the polyvinyl alcohol increases, resulting in a deterioration in the performance of the polyvinyl alcohol as a dispersant.
- [40]
- [41] **(2) Removal of Polyvinyl Alcohol (PVA)**
- [42] The polyvinyl alcohol (PVA) is separated from the solution containing the polymerized toner by a suitable method. First, the aqueous dispersion containing the polyvinyl alcohol (PVA) and the polymerized toner is diluted with distilled water. At this time, the amount of the distilled water used is two times larger than that of the aqueous dispersion. A homogenizer is used to apply a shear force to the dilute aqueous solution, followed by separation and cleaning using suitable equipment, such as a filter, a filter press, a general centrifuge or a continuous decanter type high-speed centrifuge, to separate the polyvinyl alcohol from the toner.

[43]

Mode for the Invention

- [44] Hereinafter, the present invention will be explained in more detail with reference to the following examples. However, these examples are provided to assist in a further

understanding of the invention and for illustrative purposes, and are not intended to limit the scope of the present invention.

[45]

[46] EXAMPLES

[47] [Example 1]

[48] (Production of Polymerized Toner)

[49] To 400 parts by weight of ion-exchange water was added 5 parts by weight of a water-soluble polyvinyl alcohol (degree of polymerization: 1,700, degree of saponification: 90%) as a dispersant. The mixture was stirred at room temperature for 10 minutes, heated to a reaction temperature of 70°C, and further stirred for 20 minutes to prepare an aqueous dispersion.

[50] 4 parts by weight of allyl methacrylate as a crosslinking agent and 0.02g of n-dodecyl mercaptan as a molecular weight modifier were added to a mixture of 160 parts by weight of styrene, 36 parts by weight of n-butyl acrylate and 4 parts by weight of acrylic acid as monomers. One part by weight of a styrene-acrylic polymer having sulfonic acid groups as a charge control agent was sufficiently dissolved in the monomer mixture, and 10 parts by weight of carbon black was added thereto. After the resulting mixture was stirred in a bead mill at 2,000 rpm for 2 hours, beads were removed to prepare 215 parts by weight of a mixture of the monomers and the pigment.

[51] The monomer mixture was mixed with the aqueous dispersion to obtain a mixed solution. The mixed solution was heated to 70°C in a water bath, and 5 parts by weight of paraffin wax was added thereto. The resulting mixture was allowed to react with stirring for 20 minutes. The reaction was continued while stirring using a paddle stirrer at 600 rpm for 15 hours to obtain a polymerized toner.

[52]

[53] (Centrifugal Cleaning)

[54] The aqueous dispersion containing the polyvinyl alcohol (PVA) and the polymerized toner was diluted with a two-fold amount of distilled water. A homogenizer was used to apply a shear force to the dilute aqueous solution, followed by centrifugation in a centrifuge (Beckman J2-21M, Rotor JA-14) at 3,000 rpm for 15 minutes to obtain a concentrate containing the polymerized toner. The concentrate was diluted with a two-fold amount of distilled water. A homogenizer was used to apply a shear force to the dilute aqueous solution, followed by centrifugation in a centrifuge (Beckman J2-21M, Rotor JA-14) at 3,000 rpm for 15 minutes. The above procedure was further repeated twice to remove the polyvinyl alcohol (PVA) from the toner surface. Filtration was conducted to remove moisture, leaving a toner cake. The toner cake was dried in a vacuum oven at room temperature for 48 hours to produce a toner.

[55]

[56] (Size and Shape of Toner Particles)

[57] A Multisizer Coulter Counter and a scanning electron microscope (SEM) were used to observe and measure the size and shape of the toner particles.

[58]

[59] (Surface Treatment of Toner Particles)

[60] Two parts by weight of silica having a size of 15 nm was added to 100 parts by weight of the toner particles and stirred using a Henschel coater at a high rate of 5,000 rpm for 7 minutes to embed the silica on the surface of the toner particles.

[61]

[62] (Consumed Amount and Transfer Rate of Toner)

[63] The surface-treated toner was filled in a toner feeder of a printer cartridge (HP4600 Printer, Hewlett-Packard). The toner feeder filled with the toner was weighed before printing. Rectangles of 19 cm (w) x 1.5 cm (h) were printed on 1,000 sheets of paper (A4 size). The toner feeder was weighed after printing. The amount of the toner consumed was calculated by the following equation:

[64] **Amount of toner consumed (g) = Weight of toner feeder before printing - Weight of toner feeder after printing on 1,000 sheets of paper**

[65] The weight of a drum separable from the toner feeder was measured before and after printing. The amount of the toner wasted without being transferred to the paper was calculated by the following equation:

[66]

[67] **Amount of toner wasted (g) = Weight of drum after printing on 1,000 sheets of paper - Weight of drum before printing**

[68] From the amount of the toner consumed and the amount of the toner wasted, the transfer rate of the toner was calculated by the following equation:

[69]

$$\text{Transfer rate of toner (\%)} = \frac{\text{Amount of toner consumed} - \text{Amount of toner wasted}}{\text{Amount of toner consumed}} \times 100$$

[70] The results are shown in Table 1.

[71]

[72] [Example 2]

[73] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 1,900 and a degree of saponification of 90% was added to the aqueous dispersion medium. The results are shown in Table 1.

[74]

[75] [Example 3]

- [76] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 2,100 and a degree of saponification of 90% was added to the aqueous dispersion medium. The results are shown in Table 1.
- [77]
- [78] [Example 4]
- [79] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 1,700 and a degree of saponification of 85% was added to the aqueous dispersion medium. The results are shown in Table 1.
- [80]
- [81] [Example 5]
- [82] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 2,100 and a degree of saponification of 85% was added to the aqueous dispersion medium. The results are shown in Table 1.
- [83]
- [84] [Comparative Example 1]
- [85] A polymerized toner was produced in the same manner as in Example 1 except that no polyvinyl alcohol was added to the aqueous dispersion medium. The results are shown in Table 1.
- [86]
- [87] [Comparative Example 2]
- [88] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 2,000 and a degree of saponification of 99% was added to the aqueous dispersion medium. The results are shown in Table 1.
- [89]
- [90] [Comparative Example 3]
- [91] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 1,200 and a degree of saponification of 90% was added to the aqueous dispersion medium. The results are shown in Table 1.
- [92]
- [93] [Comparative Example 4]
- [94] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 3,000 and a degree of saponification of 90% was added to the aqueous dispersion medium. The results are shown in

Table 1.

[95]

[96] [Comparative Example 5]

[97] A polymerized toner was produced in the same manner as in Example 1 except that a polyvinyl alcohol having a degree of polymerization of 1,7000 and a degree of saponification of 70% was added to the aqueous dispersion medium. The results are shown in Table 1.

[98]

TABLE 1

	Degree of polymerization of PVA	Degree of saponification (%) of PVA	dv ¹⁾	dv/dp ²⁾	Amount of toner consumed (g)	Transfer rate of toner (%)
Example 1	1,700	90	7.5	1.4	17	97
Example 2	1,900	90	7.8	1.3	19	98
Example 3	2,100	90	8.1	1.2	20	98
Example 4	1,700	85	7.1	1.4	18	97
Example 5	2,100	85	7.3	1.3	17	96
Comparative Example 1	-	-	6.7	1.8	25	90
Comparative Example 2	2,000	99	-	-	-	-
Comparative Example 3	1,200	90	6.5	1.7	26	88
Comparative Example 4	3,000	90	7.9	1.4	23	93
Comparative Example 5	1,700	70	4.8	1.7	20	85

Note.

dv¹⁾: Volume average particle diameterdv/dp²⁾: Volume average particle diameter (dv)/Number average particle diameter (dp)

Claims

- [1] A method for producing a toner, the method comprising the steps of:
- (1) dispersing a water-soluble polyvinyl alcohol having a degree of polymerization of 1,500 to 2,500 and a degree of saponification of 75 to 98% in an aqueous medium to prepare an aqueous dispersion of the polyvinyl alcohol;
 - (2) preparing a mixture of monomers;
 - (3) mixing the aqueous dispersion with the monomer mixture; and
 - (4) polymerizing the monomers.
- [2] The method according to claim 1, wherein the polyvinyl alcohol is used in an amount of 0.1 to 20 parts by weight, based on the total weight of all monomers used.
- [3] The method according to claim 1, wherein 1 to 60 parts by weight of the monomer mixture is mixed with 100 parts by weight of the aqueous dispersion; and the monomer mixture includes 30 to 95 parts by weight of an aromatic vinyl monomer, 5 to 70 parts by weight of at least one monomer selected from the group consisting of acrylate, methacrylate and diene monomers, 1 to 20 parts by weight of a pigment, 0.1 to 30 parts by weight of a wax, 0.001 to 10 parts by weight of a crosslinking agent, 0.1 to 20 parts by weight of a charge control agent, and 0.001 to 8 parts by weight of a molecular weight modifier, based on 100 parts by weight of all monomers used.
- [4] The method according to claim 3, wherein the monomer mixture further includes 0.01 to 10 parts by weight of at least one polar polymer selected from polyesters and styrene-acrylate polymers, based on 100 parts by weight of the monomer mixture without the polar polymer.
- [5] The method according to claim 3, wherein the monomer mixture further includes 0.1 to 30 parts by weight of an acidic or basic olefin monomer, based on 100 parts by weight of all monomers used.
- [6] The method according to claim 3, wherein the aromatic vinyl monomer is selected from the group consisting of styrene, monochlorostyrene, methylstyrene and dimethylstyrene.
- [7] The method according to claim 3, wherein the acrylate monomer is selected from the group consisting of methyl acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate, dodecyl acrylate and 2-ethylhexyl acrylate; the methacrylate monomer is selected from the group consisting of methyl methacrylate, ethyl methacrylate, n-butyl methacrylate, isobutyl methacrylate, dodecyl methacrylate and 2-ethylhexyl methacrylate; and the diene monomer is selected from the group consisting of butadiene and isoprene.

- [8] The method according to claim 3, wherein the wax is selected from: petroleum waxes, including paraffin wax, microcrystalline wax and ceresin wax; natural waxes, including carnauba wax; synthetic waxes, ester wax, polyethylene wax and polypropylene wax; and mixtures thereof.
- [9] The method according to claim 3, wherein the molecular weight modifier is selected from mercaptan compounds, including t-dodecyl mercaptan and n-dodecyl mercaptan, and mixtures thereof.
- [10] The method according to claim 3, wherein the pigment is selected from: inorganic pigments, including metal powder, metal oxide, carbon, sulfide, chromate and ferrocyanide pigments; organic pigments, including azo dye, acidic dye, basic dye, mordant dye, phthalocyanine, quinacridone and dioxane pigments; and mixtures thereof.
- [11] The method according to claim 3, wherein the charge control agent is: a cationic charge control agent selected from the group consisting of nigrosine type acidic dyes, higher aliphatic metal salts, alkoxyamines, chelates, quaternary ammonium salts, alkylamides, fluorine-treated activators and naphthenic acid metal salts; an anionic charge control agent selected from the group consisting of acidic organic complexes, chlorinated paraffin, chlorinated polyesters, sulfonylamines of copper phthalocyanine and styrene-acrylate polymers having sulfonic acid groups; or a mixture thereof.
- [12] The method according to claim 3, wherein the crosslinking agent is selected from the group consisting of divinylbenzene, ethylene dimethacrylate, ethylene glycol dimethacrylate, diethylene glycol diacrylate, 1,6-hexamethylene diacrylate, allyl methacrylate, 1,1,1-trimethylolpropane triacrylate, triallylamine, and tetraallyloxyethane.
- [13] The method according to claim 1, wherein the monomers are polymerized by applying a shear force to the mixed solution of the aqueous dispersion and the monomer mixture using a homogenizer.
- [14] The method according to claim 1, wherein the toner has a volume average particle diameter (d_v) between 5 and 10 μm and the ratio d_v/d_p (volume average particle diameter/number average particle diameter (d_p)) not larger than 1.5.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR2008/001482**A. CLASSIFICATION OF SUBJECT MATTER****G03G 9/08(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 8 : G03G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS(KIPO internal) , DELPHION, Espacenet, JPO, USPTO

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	JP 3530904 B2 (MINOLTA CO., LTD.) 24 MAY 2004 See claims; paragraphs [0006], [0007], [0009], [0020] and [0031]; table 1; examples.	1, 3-14 2
Y A	JP 3049328 B2 (KONICA CORP.) 5 JUNE 2000 See claim 1; paragraphs [0007] and [0012] - [0024]; examples.	2 1, 3-14
A	JP 2748419 B2 (MITSUBISHI KASEI CORP.) 6 MAY 1998 See claim 2; page 2, line 17 - page 3, line 21; examples.	1-14
A	KR 10-0657414 B1 (LG CHEM. LTD.) 13 DECEMBER 2006 See claims; page 3, lines 1 - 36 and page 4, lines 3 - 38; examples.	1-14

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

23 JUNE 2008 (23.06.2008)

Date of mailing of the international search report

23 JUNE 2008 (23.06.2008)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
Government Complex-Daejeon, 139 Seonsa-ro, Seo-
gu, Daejeon 302-701, Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

SEO Sang Yong

Telephone No. 82-42-481-5576



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2008/001482

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 3530904 B2	24.05.2004	JP 11-133658 A	21.05.1999
JP 3049328 B2	05.06.2000	JP 4-281466 A	07.10.1992
JP 2748419 B2	06.05.1998	JP 2-51164 A	21.02.1990
KR 10-0657414 B1	13.12.2006	KR 2005-98662 A	12.10.2005