



(86) Date de dépôt PCT/PCT Filing Date: 2016/04/20
(87) Date publication PCT/PCT Publication Date: 2016/10/27
(45) Date de délivrance/Issue Date: 2020/01/28
(85) Entrée phase nationale/National Entry: 2017/10/17
(86) N° demande PCT/PCT Application No.: DE 2016/000164
(87) N° publication PCT/PCT Publication No.: 2016/169543
(30) Priorité/Priority: 2015/04/20 (DE10 2015 105 987.8)

(51) Cl.Int./Int.Cl. *C09D 4/02* (2006.01)
(72) Inventeurs/Inventors:
WEHNER, JOCHEN, DE;
COSTA, ANDREA, DE
(73) Propriétaire/Owner:
MANKIEWICZ GEBR. & CO. GMBH & CO. KG, DE
(74) Agent: BORDEN LADNER GERVAIS LLP

(54) Titre : SYSTEME DE REVETEMENT AMELIORE, UTILISATION DUDIT SYSTEME POUR REVETIR DES COMPOSANTES ET COMPOSANTES AINSI REVETUES DESTINEES A DES VEHICULES SUR RAIL ET UN AERONEF
(54) Title: IMPROVED COATING SYSTEM, USE THEREOF FOR COATING COMPONENTS AND THUS COATED COMPONENTS FOR RAIL VEHICLES AND AIRCRAFT

(57) Abrégé/Abstract:

The invention relates to improved coating materials based on RMA systems, which cross-link with the aid of the classic Michael addition. The coating materials comprise at least 15 - 70 wt.-% of one or more CH acidic compounds A, 4 - 40 wt.-% of one or more vinylogous carbonyl compounds B, 0.1 - 15 wt.-% of one or more latent-alkaline catalysts C, up to 10 wt.-% of one or more light stabilizers, up to 20 wt.-% of one or more open-time extenders, and up to 20 wt.-% of one or more pot life extenders, in each case relative to the total amount of the coating material. The invention also relates to the coatings and coating systems produced therefrom, in particular base-coat varnish systems, and to coated components, particularly components for rail vehicles and aircrafts such as railway cars or airplanes.

ABSTRACT

The invention relates to improved coating materials based on RMA systems, which cross-link with the aid of the classic Michael addition. The coating materials comprise at least 15 - 70 wt.-% of one or more CH acidic compounds A, 4 - 40 wt.-% of one or more vinylogous carbonyl compounds B, 0.1 - 15 wt.-% of one or more latent-alkaline catalysts C, up to 10 wt.-% of one or more light stabilizers, up to 20 wt.-% of one or more open-time extenders, and up to 20 wt.-% of one or more pot life extenders, in each case relative to the total amount of the coating material. The invention also relates to the coatings and coating systems produced therefrom, in particular base-coat varnish systems, and to coated components, particularly components for rail vehicles and aircrafts such as railway cars or airplanes.

**IMPROVED COATING SYSTEM, USE THEREOF FOR COATING COMPONENTS AND
THUS COATED COMPONENTS FOR RAIL VEHICLES AND AIRCRAFT**

The present invention relates to improved coating materials based on RMA systems, which cross-link with the aid of a classic Michael addition. The invention also relates to coatings produced therefrom and coated components, in particular components for rail vehicles and aircraft, e.g., railway cars or air planes.

Coating materials, which cross-link in a Michael addition reaction, are known. The coatings produced therefrom have high weathering stability and chemical resistances. The rapid curing of these coating materials is achieved by the use of high catalyst content, whereby, however, the processing time or the pot life of the coating material is strongly reduced.

Rapid curing is particularly advantageous primarily in the case of coating or painting large components, for example, airplanes or railway cars. However, merely due to the size of the surfaces, a relatively long time is required for coating the entire component, so that the coating materials used must have long pot lives and long open times. In the following, pot life is designated as the time interval between mixing all components of a coating material and the time at which the cross-linking reaction in the coating material has progressed to the extent that the coating material may no longer be processed. In the following, open time is designated as the time interval in which a coating material film applied to a surface may be corrected without impairing the gradient properties.

During application of the coating material, the already coated areas must additionally be able to absorb the overspray that occurs during painting of the adjacent areas, without surface defects forming, for example, due to a poor progression. In the following, overspray is designated as material loss of the coating material caused during spray painting. The material loss may be caused by spraying past caused by an unfavourable orientation of the spray gun toward the workpiece or by strongly interrupted workpieces, like grids. Overspray may also occur due to coating material drops flowing off laterally in front of the workpiece surfaces. Overspray absorption is thereby the property of an applied coating material to absorb material from an overspray such that the desired smooth surface of the film or coating is retained.


After application of the coating material as a film or layer on a substrate surface, a very fast drying or curing is desired for the coating. Forced drying at increased temperature is generally not possible for large components, as correspondingly large ovens would be required for this. Therefore, fast drying at room temperature is particularly desirable primarily for coating or painting very large components.

Binder systems cross-linking in a Michael addition, designated in the following as RMA systems, are known from EP 2374836 A1 and have a favourable ratio of pot life to drying time. The described binder systems show short drying times with long pot lives even at room temperature. Reference is thus specifically made to EP 2374836 A1 as a part of the description. The disadvantage of the known RMA systems is that the coating

materials and coatings produced therefrom do not show the necessary and conventional properties.


It is therefore desirable to provide improved coating materials, coatings, and coating systems based on RMA systems which are particularly suitable for coating components of aircraft and rail vehicles.

In one aspect, the present invention provides a coating material for producing a coating having at least 15 to 70 wt.% of one or more CH acidic compounds A, 4 to 40 wt.% of one or more vinylogous carbonyl compounds B, 0.1 to 15 wt.% of one or more latent-basic catalysts C, 0.00001 to 10 wt.% of one or more light stabilizers, 0.00001 to 20 wt.% of one or more open time extenders, and 0.00001 to 20 wt.% of one or more pot life extenders, wherein each wt.% is based on the total amount of the coating material, wherein the CH acidic compounds A are compounds of the formula



wherein R is hydrogen, an alkyl- or aryl radical, Y is an alkyl-, aralkyl-, aryl-, alkoxy radical or an amino group, and Y' is an alkyl-, aralkyl-, aryl-, alkoxy radical or an amino group, wherein the vinylogous compounds B are acrylates and/or maleates, and wherein the latent-basic catalysts C are substituted carboxylic acid salts of the formula

3a



wherein R is hydrogen, an alkyl- or aralkyl-, or a polymer radical, X⁺ is an alkali or an alkaline earth metal cation, a quaternary ammonium- or phosphonium salt of the formula (R')₄Z⁺, wherein Z is nitrogen or phosphorus, and R' is the same or different, is hydrogen, an alkyl-, aral-, or aralkyl radical, or a polymer.

In another aspect, the present invention provides a use of the coating material as defined herein for producing at least one coating in a coating system.

In a further aspect, the present invention provides a method for coating a component comprising (a) applying the coating material as defined herein to a substrate, and (b) curing the applied coating material for 1 to 12 hours at temperatures between 5 and 45°C.

In a further aspect, the present invention provides a component coated with at least one coating produced from the coating material as defined herein.

The coating materials according to the invention comprise at least one RMA system which has one or more CH acidic compounds A, one or more vinylogous carbonyl compounds B, and one or more latent-basic catalysts C, and also one or more light stabilizers, one or more pot life extenders, and one or more open time extenders.

In the following, the expression light stabilizer is understood to refer to additives and adjuvants that protect coatings from the influence of UV light, in particular prevent or at least significantly delay polymer degradation caused by UV radiation. The expression pot life extenders is understood to refer to additives and adjuvants which, as components of the ready to be used mixed coating material, delay the curing of the coating material prior to application. They evaporate during application so that the curing of the applied coating material is not affected, in particular, is not extended. The expression open time extenders is understood to refer to additives and adjuvants

which also remain in the coating material after application and delay curing for the coating.

The coating materials according to the invention contain at least

- 15 through 70, preferably 20 through 60, particularly preferably 25 through 55 wt.% CH acidic compounds A,
- 4 through 40, preferably 8 through 35, particularly preferably 10 through 30 wt.% vinylogous carbonyl compounds B,
- 0.1 through 15, preferably 0.2 through 10, particularly preferably 0.3 through 5 wt.% latent-basic catalysts C,
- 0.00001 through 10, preferably 0.5 through 5, particularly preferably 1 through 3 wt.% light stabilizers,
- 0.00001 through 20, preferably 0.01 through 10, particularly preferably 0.1 through 5 wt.% open time extenders, and
- 0.0001 through 20, preferably 0.01 through 15, particularly preferably 0.1 through 10 wt.% pot life extenders,
- 0 through 70, preferably 0.00001 through 65, particularly preferably 0.00001 through 40 wt.% pigments,
- 0 through 25, preferably 0.00001 through 8, particularly preferably 0.00001 through 5 wt.% dispersing additives,
- 0 through 60, preferably 0.00001 through 40, particularly preferably 0.00001 through 30 wt.% functional fillers, and
- 0 through 50, preferably 0.00001 through 40, particularly preferably 0.00001 through 30 wt.% aprotic solvents,


wherein the indicated amounts respectively relate to the total amount of the coating material.

According to the invention, the compounds A and B are used in a molar ratio A:B of 0.5:1 through 2:1, preferably of 0.75:1 through 1.6:1, particularly preferably of 0.9:1 through 1.3:1,

especially preferably of 0.95:1 through 1.1:1, wherein the molar amounts refer to the acidic protons of the compounds A and to the vinylogous carbonyl groups of the compounds B.

According to the invention, the catalysts C and compounds A are used in a molar ratio C:A of 0.8:1 through 2.5:1, particularly 1.1:1 through 1.9:1, particularly preferably 1.3:1 through 1.7:1, wherein the molar amounts refer to the cation X^+ of catalyst C and the acidic protons of the compounds A.

Suitable CH acidic compounds A are compounds with the general Formula I



I

where

R is hydrogen, an alkyl- or aryl radical, and
Y, Y' are alkyl-, aralkyl-, aryl-, alkoxy radicals or amino groups, preferably primary amino groups, and Y and Y' may be the same or different.

Furthermore, the $-\text{C}(=\text{O})-\text{Y}$ and/or $-\text{C}(=\text{O})-\text{Y}'$ groups from Formula I may be replaced by CN- or aryl groups.


According to the invention, malonic acid esters, acetoacetic acid esters, or mixtures thereof are preferably used. Malonic acid esters are particularly preferred with oligomer and polymer substituents, for example, based on polyesters, polyurethanes, polyacrylates, epoxy resins, polyamides, or polycarbonates. Malonic acid esters are particularly preferred with oligomer and

polymer substituents based on polyesters, polyurethanes, and/or polycarbonates. The acetoacetic acid esters used preferably contain oligomer and polymer substituents, for example, based on polyalcohols, polyvinyl alcohols, epoxy resins, hydroxy-functional polyethers, polyesters, or polyacrylates. Acetoacetic acid esters are particularly preferred with oligomer and polymer substituents based on polyesters and/or polyacrylates. Compounds are more particularly preferred that are selected from the group containing malonic acid esters with oligomer and polymer substituents based on polyesters, which are obtained from the reaction of at least malonic acid, malonic acid dimethyl ester, and/or malonic acid diethyl ester with hexahydrophthalic acid and/or its anhydride and neopentyl glycol, and acetoacetic acid esters with oligomer and polymer substituents based on polyesters, which are obtained from the reaction of at least acetoacetic acid, acetoacetic acid methyl ester, and/or acetoacetic acid ethyl ester with hexahydrophthalic acid and/or its anhydride and neopentyl glycol.

Suitable vinylogous carbonyl compounds B are, for example, acrylates and/or maleates, in particular unsaturated acryloyl-functional compounds. According to the invention, acrylesters are preferred that are made from compounds containing 1 through 20 carbon atoms and at least 2, preferably 2 through 6 hydroxyl groups. According to the invention, polyesters are additionally preferred that are obtained from reacting maleic acid, fumaric acid, and/or itaconic acid, or anhydrides thereof with di- or polyvalent hydroxyl compounds which may contain a monovalent hydroxyl- or carboxyl compound. Resins are additionally preferred, like polyesters, polyurethanes, polyethers, and/or alkyd resins which correspondingly contain activated unsaturated

groups, for example, urethane acrylates, polyether acrylates, polyfunctional polyacrylates, polyalkylmaleates, and polyacrylates that are obtained from the reaction of acrylic acid with epoxy resins. According to the invention, butanediol diacrylate, hexanediol diacrylate, trimethylolpropane triacrylate, entaerythritol tetraacrylate, di(trimethylolpropane)tetraacrylate, dipentaerythritol hexaacrylate, dipropylene glycol diacrylate, and tripropylene glycol diacrylate are particularly preferred.

Suitable latent-basic compounds for the catalysts C are, for example, substituted carboxylic acid salts of Formula II:



where

R is hydrogen, an alkyl or aralkyl (Ar-R), or a polymer,

X⁺ is an alkali or alkaline earth metal cation, in particular lithium, sodium, or potassium, or a quaternary ammonium or phosphonium salt of the formula (R')₄Z⁺,

where

Z is nitrogen or phosphorus,

R' is the same or different, is hydrogen, an alkyl-, aral-, or aralkyl radical, or a polymer,

and where

R and R' may form a ring structure

or

R and R' may be a polymer.

According to the invention, R is preferably an alkyl group or an aralkyl group, particularly preferably an alkyl group with 1 through 4 carbon atoms. The carbonate group and the cation X^+ may also additionally be present on a molecule with the corresponding structure. Furthermore, R' is preferably an alkyl group, particularly preferably an alkyl group with 1 through 4 carbon atoms, particularly preferably with 3 through 4 carbon atoms. According to the invention, ammonium- and/or phosphonium carbonate are preferably used. Suitable ammonium carbonates are, for example, tetrahexylammonium methyl carbonate, tetrahexylammonium hydrogen carbonate, tetradecanyl trihexylammonium methyl carbonate, tetradecylammonium methyl carbonate, tetrabutylammonium methyl carbonate, tetrabutylammonium ethyl carbonate, tetrabutylammonium hydrogen carbonate, tetrapropylammonium methyl carbonate, tetrapropylammonium ethyl carbonate, tetrapropylammonium hydrogen carbonate, benzyltrimethylammonium methyl carbonate, trihexylmethylammonium methyl carbonate, or trioctylmethylammonium methyl carbonate. Tetrabutylammonium methyl carbonate, tetrabutylammonium ethyl carbonate, tetrabutylammonium hydrogen carbonate, tetrapropylammonium methyl carbonate, tetrapropylammonium ethyl carbonate, tetrapropylammonium hydrogen carbonate, and mixtures thereof are particularly preferably used.

Suitable light stabilizers are radical scavengers like sterically inhibited aliphatic amines, e.g., based on substituted 2,2,6,6-tetramethylpiperidines, UV absorbers like 2-hydroxyphenyl benzotriazoles, 2-hydroxybenzophenones, 2-hydroxyphenyltriazines, or oxalanilides, and quenchers like

organic nickel compounds and peroxide decomposers like thioethers or phosphites. Radical scavengers, for example, sterically inhibited aliphatic amines based on substituted 2,2,6,6-tetramethylpiperidines, and/or UV absorbers, for example, 2-hydroxyphenyl benzotriazoles, 2-hydroxybenzophenones, 2-hydroxyphenyltriazines, and oxalanilides are preferably used. Substituted 2,2,6,6-tetramethylpiperidines, 2-hydroxyphenyltriazines, 2-hydroxybenzophenones, and mixtures thereof are particularly preferably used.

Suitable pot life extenders are short-chain alcohols which have an evaporation number below 35, preferably below 20. Alcohols with up to 6 carbon atoms, preferably up to 4, particularly up to 3 are particularly suitable. Thus, for example, methanol, ethanol, n-propanol, i-propanol, n-butanol, i-butanol, and mixtures thereof may be used according to the invention.

Suitable open time extenders are basic NH-functional compounds with a pK_a value between 4 and 14. Succinimides, 1,2,4,-triazoles, 1,2,3,-benzotriazoles, 5,5-diphenylhydantoins, hydantoins, (RS)-3-ethyl-3-methylpyrrolidine-2,5-dione, and mixtures thereof are preferred. Succinimides, 1,2,4,-triazoles, 1,2,3,-benzotriazoles, and mixtures thereof are particularly preferred.

In another embodiment of the present invention, inorganic and/or organic pigments may be added to the coating materials to produce a colour-producing coating. Additional additives, like dispersing additives and functional fillers, may also be added, in order to improve the required properties of the coating material and/or of the coating.

Inorganic and/or organic pigments may be added to the coating materials according to the invention in amounts up to 70, preferably 0.00001 through 65, particularly preferably 0.00001 through 40 wt.%, wherein the indicated amounts respectively relate to the total amount of the coating material. Suitable inorganic pigments are, for example, titanium dioxide, iron oxides, chromium oxides, chromium titanates, bismuth vanadate, cobalt blue, and carbon blacks. Titanium dioxide, iron oxides, and carbon blacks are preferred inorganic pigments. Suitable organic pigments are, for example, pigment yellow 151, pigment yellow 213, pigment yellow 83, pigment orange 67, pigment orange 62, pigment orange 36, pigment red 170, pigment violet 19, pigment violet 23, pigment blue 15:3, pigment blue 15:6, pigment green 7. Preferred pigments are pigment yellow 151, pigment orange 67, pigment red 170, pigment violet 19, pigment blue 15:3, pigment green 7.

In another embodiment, the coating materials may additionally contain up to 25, preferably 0.00001 through 8, particularly preferably 0.00001 through 5 wt.% dispersing agents, wherein the indicated amounts respectively relate to the total amount of the coating material. Suitable dispersing agents are, for example, high molecular weight block copolymers with pigment affinic groups, highly branched polyesters, and acrylate polyester copolymers with pigment affinic groups. Preferably used dispersing additives are high molecular weight block copolymers with pigment affinic groups.

In another embodiment, the coating materials may additionally contain up to 60, preferably 0.00001 through 50, particularly

preferably 0.00001 through 40 wt.% functional fillers, wherein the indicated amounts respectively relate to the total amount of the coating material. Suitable fillers are, for example, carbonates like chalk, limestone, calcite, precipitated calcium carbonate, dolomite, barium carbonate, sulphates like barite, blanc fixe, calcium sulphate, silicates like talc, pyrophyllite, chlorite, hornblende, mica, china clay, wollastonite, powdered slate, precipitated calcium silicates, precipitated aluminium silicates, precipitated calcium aluminium silicates, precipitated sodium aluminium silicates, feldspars, mullite, silicas like quartz, fused silica, cristobalite, diatomaceous earth, siliceous earth, precipitated silica, pumice powder, perlite, calcium metasilicate, fibres from melts of glass or basalts, glass powder, glass beads, and slags. The preferred fillers used are barium sulphate and/or talc.

In another embodiment according to the invention, the coating materials contain up to 50, preferably 0.00001 through 40, particularly preferably 0.00001 through 30 wt.% aprotic solvents, wherein the indicated amounts respectively relate to the total amount of the coating material. The expression aprotic solvents is understood in the following to refer to solvents that contain no ionisable protons in the molecule. Suitable aprotic solvents are, for example, aliphatic hydrocarbons, cycloaliphatic hydrocarbons, aromatic hydrocarbons, ketones, esters, ethers, ether esters, in particular, ethylacetate, butyl acetate, acetone, n-butanone, methyl isobutyl ketone, methoxypropyl acetate, and dimethyl sulfoxide. Preferably used solvents are ethylacetate, butyl acetate, acetone, n-butanone, methyl isobutyl ketone, methoxypropyl acetate, and mixtures thereof.

The compounds used as catalysts C according to the invention are latent bases, as the carbonate salt according to Formula II is in equilibrium with its disassociation products, carbon dioxide and the corresponding hydroxide- or alkoxy base. As long as carbon monoxide may not escape from the system, the equilibrium lies more strongly in favour of the carbonate salt. Only when a carbon dioxide is removed, and thus a sufficient amount of base is present, does the cross-linking begin with the aid of the Michael addition. With regard to storage of the coating materials according to the invention in closed containers, from which carbon dioxide may not escape, the coating material may be basically formulated as a single component system. The shelf life may, however, be increased if the individual components of the coating material according to the invention are formulated in multicomponent systems. Thus, for example, a catalyst component, which contains the catalysts C, is only mixed shortly before processing with the binder components, which contain the CH acidic compounds A and the vinylogous carbonyl compounds B.

According to the invention, the CH acidic compounds A and the vinylogous carbonyl compounds B may be contained in a binder component together with the light stabilizers, open time extenders, and pot life extenders used. This binder component may additionally contain pigments, additionally other additives, and solvents. The catalysts C and, if necessary, additional solvents and pot life extenders, may be contained in a catalyst component. In one preferred embodiment, the CH acidic compounds A may be present in a first binder component, the vinylogous carbonyl compounds B in a second binder component, and the catalysts C in a catalyst component. In one such three-component

system, the CH acidic compounds A are contained in the first binder component together with the open time extenders and light stabilizers. If necessary, this first binder component may additionally contain pigments and fillers, and additional additives. The vinylogous carbonyl compounds B are preferably contained in the second binder component. Furthermore, the second binder component may also contain pigments, fillers, and additional additives. The catalysts C are contained in the catalyst component. Furthermore, the catalyst component may contain solvents and pot life extenders.

It is known that the addition of additional components, which are customary for producing a coating, reduces the shelf life of RMA systems. The coating materials according to the invention with their particular selection of light stabilizers, open time extenders, pot life extenders, pigments, dispersing agents, functional fillers, and aprotic solvents have an unexpectedly high shelf life in comparison to previously known coating materials based on RMA systems.

Furthermore, the properties of coatings, which are produced from coating materials based on RMA systems, are negatively influenced by the presence of other components of the coating material, in contrast to coatings which are produced from coating materials based on conventional binders, for example, epoxy resins or polyurethanes. It has been surprisingly demonstrated that the coating materials according to the invention result in coatings which have properties necessary for use for components of railway vehicles and aircraft, in particular gloss retention, mechanical stabilities, and light stability.

In one particularly preferred embodiment, the coating materials according to the invention comprise at least:

- 15 through 70, preferably 20 through 60, particularly preferably 25 through 55 wt.% of CH acidic compounds A, for example, malonic acid esters with oligomer and polymer substituents based on polyesters, which are obtained from the reaction of at least malonic acid, malonic acid dimethyl ester, and/or malonic acid diethyl ester with hexahydrophthalic acid and/or its anhydride and neopentyl glycol, and acetoacetic acid esters with oligomer and polymer substituents based on polyesters, which are obtained from the reaction of at least acetoacetic acid, acetoacetic acid methyl ester, and/or acetoacetic acid ethyl ester with hexahydrophthalic acid and/or its anhydride and neopentyl glycol,
- 4 through 40, preferably 8 through 35, particularly preferably 10 through 30 wt.% vinylogous carbonyl compounds B, for example, butanediol diacrylate, hexanediol diacrylate, trimethylolpropane triacrylate, pentaerythritol tetraacrylate, di(trimethylolpropane)tetraacrylate, and/or dipentaerythritol-hexaacrylate,
- 0.1 through 15, preferably 0.2 through 10, particularly preferably 0.3 through 5 wt.% catalysts C, for example, tetrabutylammonium methyl carbonate, tetrabutylammonium ethyl carbonate, tetrabutylammonium hydrogen carbonate, tetrapropylammonium methyl carbonate, tetrapropylammonium ethyl carbonate, tetrapropylammonium hydrogen carbonate, and mixtures thereof,
- 0.00001 through 10, preferably 0.5 through 5, particularly preferably 1 through 3 wt.% light stabilizers, for example, substituted 2,2,6,6-tetramethylpiperidines, 2-

hydroxyphenyltriazines, 2-hydroxybenzophenones, and mixtures thereof,

- 0.00001 through 20, preferably 0.01 through 10, particularly preferably 0.1 through 5 wt.% open time extenders, for example, succinimides, 1,2,4,-triazoles, 1,2,3,-benzotriazoles, and mixtures thereof,
- 0.00001 through 20, preferably 0.01 through 15, particularly preferably 0.1 through 10 wt.% pot life extenders, for example, methanol, ethanol, n-propanol, i-propanol, n-butanol, i-butanol, and mixtures thereof,
- 0 through 50, preferably 0.00001 through 40, particularly preferably 0.00001 through 30 wt.% aprotic solvents, for example, ethylacetate, butyl acetate, acetone, n-butanone, methyl isobutyl ketone, methoxypropyl acetate, and mixtures thereof, and

wherein the indicated amounts respectively relate to the total amount of the coating material.

In one particularly preferred embodiment, the coating materials according to the invention have at least:

- 15 through 70, preferably 20 through 60, particularly preferably 20 through 55 wt.% of CH acidic compounds A, for example, malonic acid esters with oligomer and polymer substituents based on polyesters, which are obtained from the reaction of at least malonic acid, malonic acid dimethyl ester, and/or malonic acid diethyl ester with hexahydrophthalic acid and/or its anhydride and neopentyl glycol, and acetoacetic acid esters with oligomer and polymer substituents based on polyesters, which are obtained from the reaction of at least acetoacetic acid, acetoacetic acid methyl ester, and/or

- acetoacetic acid ethyl ester with hexahydrophthalic acid and/or its anhydride and neopentyl glycol,
- 4 through 40, preferably 8 through 35, particularly preferably 10 through 30 wt.% vinylogous carbonyl compounds B, for example, butanediol diacrylate, hexanediol diacrylate, trimethylolpropane triacrylate, pentaerythritol tetraacrylate, di(trimethylolpropane)tetraacrylate, and/or dipentaerythritol-hexaacrylate,
 - 0.1 through 15, preferably 0.2 through 10, particularly preferably 0.3 through 5 wt.% catalysts C, for example, tetrabutylammonium methyl carbonate, tetrabutylammonium ethyl carbonate, tetrabutylammonium hydrogen carbonate, tetrapropylammonium methyl carbonate, tetrapropylammonium ethyl carbonate, tetrapropylammonium hydrogen carbonate, and mixtures thereof,
 - 0.00001 through 10, preferably 0.5 through 5, particularly preferably 1 through 3 wt.% light stabilizers, for example, substituted 2,2,6,6-tetramethylpiperidines, 2-hydroxyphenyltriazines, 2-hydroxybenzophenones, and mixtures thereof,
 - 0.00001 through 20, preferably 0.01 through 10, particularly preferably 0.1 through 5 wt.% open time extenders, for example, succinimides, 1,2,4,-triazoles, 1,2,3,-benzotriazoles, and mixtures thereof,
 - 0.00001 through 20, preferably 0.01 through 15, particularly preferably 0.1 through 10 wt.% pot life extenders, for example, methanol, ethanol, n-propanol, i-propanol, n-butanol, i-butanol, and mixtures thereof,
 - 0 through 70, preferably 0.00001 through 65, particularly preferably 0.00001 through 40 wt.% inorganic and/or organic pigments, for example, titanium dioxide, iron oxides, carbon

blacks, pigment yellow 151, pigment orange 67, pigment red 170, pigment violet 19, pigment blue 15:3, pigment green 7, and mixtures thereof,

- 0 through 25, preferably 0.00001 through 8, particularly preferably 0.00001 through 5 wt.% dispersing additives, for example, high molecular weight block copolymers with pigment affinic groups,
- 0 through 60, preferably 0.00001 through 40, particularly preferably 0.00001 through 30 wt.% functional fillers, for example, barium sulphate and/or talc, and
- 0 through 50, preferably 0.00001 through 40, particularly preferably 0.00001 through 30 wt.% aprotic solvents, for example, ethylacetate, butyl acetate, acetone, n-butanone, methyl isobutyl ketone, methoxypropyl acetate, and mixtures thereof,

wherein the indicated amounts respectively relate to the total amount of the coating material.

The coating materials according to the invention may be used to produce coating systems which have a structure made from two or more coatings. The coating materials according to the invention may thereby be used to produce at least one layer or coating. In one preferred embodiment, the coating materials are used for producing a two-layer structure; they are particularly preferably used to construct a base coat-clear coat system. In the following, coating materials and coatings, which contain no colouring agents, are designated as clear coats. In the following, coating materials and coatings, which contain colouring agents, for example, dyes or pigments, are designated as base coats. Base coat-clear coat systems are also often used

for aircraft and rail vehicles, as they are very weather resistant, primarily with respect to gloss retention.

The coating materials according to the invention have a surprisingly higher shelf life in comparison to previously known RMA coating materials and coatings. They also show improved drying behaviour. Coatings obtained from the coating materials according to the invention additionally have an improved light stability, in particular less yellowing and higher gloss retention.

The coating materials according to the invention have pot lives greater than or equal to 1 hour, preferably greater than or equal to 2 hours, particularly preferably between 2 and 4 hours. The pot life is generally determined via the flow time from a flow cup. The end of the pot life is determined as the point at which the flow time shows double the value of the starting flow time. The testing method is described below in detail in the Examples. Furthermore, the coating materials according to the invention demonstrate open times of greater than or equal to 15 minutes, preferably greater than or equal to 20 minutes, particularly preferably greater than or equal to 25 minutes. In addition to the long pot lives and open times, the coating materials according to the invention surprisingly demonstrate an unusually broad climate window in which they may be processed without deterioration. They are processable, for example, at temperatures up to 45°C and at relative air humidity of up to 99%. In addition, they demonstrate a long overspray absorption, for example, over a time interval of more than 25 minutes.

In contrast to conventionally used coating materials based on polyurethane, the coating materials according to the invention have significantly reduced drying times. In addition, the coatings according to the invention may be masked more quickly, i.e., they are already cured at room temperature 1 through 4 hours after application to the extent that, e.g., pattern stencils may be applied which are removed again after painting the pattern without damaging the coating. Glued on stencils are conventionally used to apply colour decorations and patterns to a coating.

Due to their properties, the coating materials according to the invention are suitable primarily for a use for coating large components. They are suitable in particular for coating large surface area components, as they are used, for example, in rail car construction and aircraft construction.

The present invention also relates to a method for coating components. The method according to the invention thereby comprises the steps: (a) applying the coating material according to the invention to a surface of a substrate, and (b) curing the applied coating material for 1 through 12, preferably 1 through 6, particularly preferably 1 through 4 hours at temperatures between 5 and 45, preferably 15 and 40, particularly preferably 20 and 35°C.

The coating materials according to the invention have an above-average high solids content and correspondingly contain low proportions of volatile organic substances, for example, solvents. The solids content is defined as the proportion by mass of a coating material that remains as residue after 30

minutes during evaporation at 105°C. Essentially, the solids generally comprise binders, non-volatile additives, pigments, and fillers. The solids content of the coating materials according to the invention lie between 65 and 95, preferably 70 and 90, particularly preferably between 75 and 85 wt.%, relative to the total weight of the coating materials.

Coating materials with high solids contents are usually poorly processable using conventional spraying methods. In contrast, the coating materials according to the invention are easily applied with the aid of hydraulic very high pressure spraying (airless), airless spraying with air support (airmix), and with the aid of pneumatic spraying or compressed air spraying. High quality surfaces are surprisingly obtained even using these application methods. Electrostatically supported airspray or airmix methods are particularly suitable according to the invention.

Suitable substrates are metals, for example, aluminium, aluminium alloys, steels, and iron alloys, plastic materials, and glass- and carbon fibre reinforced fibre composite materials. The component surfaces to be coated may be provided with a primer, for example, the conventional primers known to the person skilled in the art based on epoxy resins or polyurethanes.

In the case of coating materials according to the invention, which have multiple components, all components are mixed prior to the application. The mixing may thereby be carried out manually or by machine. In another embodiment, a coating system may be produced with at least one additional coating, in that

additional coating materials are applied and cured on the first coating.

In one preferred embodiment of the method according to the invention, a coating system is produced in a two-layer structure. First, a base coat is applied and cured; then, a clear coat is applied on this coating and cured. The base coat or the clear coat or both the base and clear coats may be produced from coating materials according to the invention.

The coatings according to the invention have a dry coating thickness of 20 through 150 μm . Low coating thicknesses that still have high opacity are suitable, in particular, for coating components for aerospace, as weight may thus be saved.

As the coating materials according to the invention may be cured at room temperature, they are primarily suitable for coating large components, as they are used, for example, to build aircraft and railway cars. They are suitable in particular for the coating of fuselages, wings, radomes, vertical fins, elevators, engine claddings, winglets, and landing flaps, and also for driving units, rail car parts, roofs, doors, and chassis linings. They are also suitable for coating interior components of rail vehicles and aircraft, for example, ceiling panels, wall claddings, floor panels, luggage compartment covers, and doors.

Examples

The production of the coating materials is carried out according to coating technology standards, which are known and familiar to the person skilled in the art. The catalyst solution used in Example Recipes 1 and 2 is produced in that 42.8 g diethyl carbonate and 26.1 g *i*-propanol are added to a solution of 17.1 g tetrabutyl ammonium hydroxide in 14 g water.

Example Recipe 1: Clear coat

Substance	Amount [wt.%]
Filler component	
Malonate functional polyester with a concentration of acidic protons of 5.66 mol/kg relative to the solvent-free polyester, 85% in butyl acetate.	52
Di(trimethylolpropane)tetraacrylate	23
Hexanediol diacrylate	5.5
Bis(1,2,2,6,6-pentamethyl-4-piperidiny)-sebacate	3
Succinimide	1.5
Methyl ethyl ketone	6
Catalyst component	
Catalyst solution	6
Isopropanol	3

Example Recipe 2: Base coat

Substance	Amount [wt.%]
Filler component 1	
Malonate functional polyester with a concentration of acidic protons of 5.66 mol/kg relative to the solvent-free polyester, 85% in butyl acetate.	31
Titanium dioxide	35
High molecular weight block copolymer with pigment affinic groups	1
Bis(1,2,2,6,6-pentamethyl-4-piperidiny)-sebacate	1
Succinimide	1
Butyl acetate	4.5
Filler component 2	
Di(trimethylolpropane)tetraacrylate	14
Hexanediol diacrylate	3
Catalyst component	
Catalyst solution	3.5
Isopropanol	2
Methyl ethyl ketone	4

To evaluate the shelf life of the coating materials according to the invention, the pot life and the drying time of Example Recipe 2 were determined. Samples were thereby tested or used to produce a coating after 1 day of storage at 23°C, after 28 days of storage at 40°C, and after 1 year of storage at 20 through 23°C respectively.

Determination of pot life: The pot life is determined using a flow cup. In this method, a liquid is filled into a cup with a defined volume, which has a defined nozzle in its bottom. The coating material runs out through the nozzle, wherein the time

from the discharge of the liquid jet up until the liquid jet breaks off is measured as the flow time. All preparations and measurements are carried out at a temperature of 23°C. Initially, all components of the coating material are mixed and the flow time of the mixture is immediately measured (initial flow time). The measurement is repeated at regular intervals. The end of the pot life is reached when the flow time is double the initial flow time.

Determination of drying time: To determine the drying time, a drying time recorder, a drying time measurement device from BYK Gardner, is used. For this purpose, the coating material to be examined is uniformly applied on glass strips with the aid of a film drawer. The glass strips are subsequently laid in a linear recorder. Needles are then applied to the coating and drawn across the drying film at a defined, constant speed. A characteristic drying image of the coating is thereby created, in which the individual time segments show the different curing states: flow or open time, initial trace, film tearing, and surface track. The curing of the coating material thereby begins at the end of the open time, i.e., at the point at which the track etched by the needle remains visible in the applied film. It ends with the surface track, i.e., at the time at which the needle no longer leaves a visible track in the applied film.

The properties of the coatings which are produced from the differently stored coating materials from Example Recipe 2 were also examined to determine the shelf life of the coating material. For this purpose, gloss and elongation at break were determined. Samples were used to produce a coating after 1 day of storage at 23°C, after 28 days of storage at 40°C, and after

1 year of storage at 20 through 23°C respectively. To produce the sample bodies, Example Recipe 2 was applied to primed aluminium plates using cup guns and cured at room temperature.

Determination of surface gloss: The gloss of the coating surface is determined as a reflectometer value. The reflectometer value of a sample is defined as the ratio of the light beams reflected by the sample surface and a glass surface with a refractive index of 1,567 in the mirror direction. The measurement values are determined with the aid of a conventional refractometer at an angle of 60°.

Determination of elongation at break: The elongation at break is determined using the cylindrical mandrel bend test. The sample bodies are bent around a mandrel for this purpose. The smaller the radius of the mandrel, around which the plate may be bent without damaging or breaking the coating, the greater the elongation at break of the coating. The diameter of the mandrel is indicated as the measured value.


Table: Shelf life of Example Recipe 2

Storage	1 day, 24°C	28 days, 40°C	1 year, 20 - 23°C
Pot life	2.5 h	2.5 h	2.5 h
Open time	59 min	60 min	56 min
Surface track ends	136 min	132 min	128 min
Elongation at rupture	12 mm	12 mm	12 mm
Gloss	87	88	87

As the table shows, the coating materials according to the invention have a high shelf life. After longer storage at increased temperatures, the coating materials themselves do not demonstrate a deterioration in their processability. The coatings produced therefrom also show no impairment to their properties.

CLAIMS:

1. A coating material for producing a coating having at least 15 to 70 wt.% of one or more CH acidic compounds A, 4 to 40 wt.% of one or more vinylogous carbonyl compounds B,
- 0.1 to 15 wt.% of one or more latent-basic catalysts C, 0.00001 to 10 wt.% of one or more light stabilizers, 0.00001 to 20 wt.% of one or more open time extenders, and 0.00001 to 20 wt.% of one or more pot life extenders, wherein each wt.% is based on the total amount of the coating material,
- wherein the CH acidic compounds A are compounds of the formula



wherein

R is hydrogen, an alkyl- or aryl radical,

Y is an alkyl-, aralkyl-, aryl-, alkoxy radical or an amino group, and

Y' is an alkyl-, aralkyl-, aryl-, alkoxy radical or an amino group,

wherein the vinylogous compounds B are acrylates and/or maleates, and

wherein the latent-basic catalysts C are substituted carboxylic acid salts of the formula



wherein

R is hydrogen, an alkyl- or aralkyl-, or a polymer radical,

X⁺ is an alkali or an alkaline earth metal cation, a quaternary ammonium- or phosphonium salt of the formula (R')₄Z⁺,

wherein

Z is nitrogen or phosphorus, and

R' is the same or different, is hydrogen, an alkyl-, aral-, or aralkyl radical, or a polymer.

2. The coating materials according to claim 1, which further comprises up to 70 wt.% of one or more inorganic and/or organic pigments.

3. The coating material according to claim 2, wherein the pigments are selected from the group consisting of titanium dioxide, iron oxides, chromium oxides, chromium titanates, bismuth vanadate, cobalt blue, carbon blacks, pigment yellow 151, pigment yellow 213, pigment yellow 83, pigment orange 67, pigment orange 62, pigment orange 36, pigment red 170, pigment violet 19, pigment violet 23, pigment blue 15:3, pigment blue 15:6, and pigment green 7.

4. The coating material according to any one of claims 1 to 3, wherein the light stabilizers are selected from the group

consisting of radical scavengers, UV absorbers, quenchers, and peroxide decomposers.

5. The coating material according to any one of claims 1 to 4, wherein the pot life extenders are selected from the group consisting of alcohols which have up to 6 carbon atoms and an evaporation number below 35.

6. The coating material according to any one of claims 1 to 5, wherein the open time extenders are selected from the group consisting of basic NH-functional compounds with a pK_a value between 4 and 14.

7. The coating material according to any one of claims 1 to 6, which further comprises up to 25 wt.% of one or more dispersing additives.

8. The coating material according to claim 7, wherein the one or more dispersing additives are selected from the group consisting of block copolymers with pigment affinic groups, branched polyesters, and acrylate polyester copolymers with pigment affinic groups.

9. The coating material according to any one of claims 1 to 8, which further comprises up to 60 wt.% of one or more functional fillers.

10. The coating material according to claim 9, wherein the one or more functional fillers are selected from the group consisting of carbonates, sulphates, silicates, and silicas.

11. The coating material according to any one of claims 1 to 10, which further comprises up to 50 wt.% of one or more aprotic solvents.

12. The coating material according to claim 11, wherein the one or more aprotic solvents are selected from the group consisting of aliphatic hydrocarbons, cycloaliphatic hydrocarbons, aromatic hydrocarbons, ketones, esters, ethers, and ether esters.

13. The coating material according to claim 12, wherein the one or more aprotic solvents are selected from the group consisting of ethyl acetate, butyl acetate, acetone, n-butanone, methyl isobutyl ketone, methoxypropyl acetate, and dimethyl sulfoxide.

14. A use of the coating material according to any one of claims 1 to 13 for producing at least one coating in a coating system.

15. The use according to claim 14, wherein the at least one coating is at least one base coat.

16. The use according to claim 14, wherein the at least one coating is at least one clear coat.

17. A method for coating a component comprising (a) applying the coating material as defined in any one of claims 1 to 13 to a substrate, and (b) curing the applied coating material for 1 to 12 hours at temperatures between 5 and 45°C.

18. The method according to claim 17, wherein the coating material is applied in step (a) by means of spraying methods.

19. The method according to claim 17 or 18, wherein all components of the coating material are mixed prior to step (a).

20. A component coated with at least one coating produced from the coating material as defined in any one of claims 1 to 13.

21. The component according to claim 20, wherein the component is a rail vehicle component or an aircraft component.