

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau



(10) International Publication Number

WO 2018/122134 A1

(43) International Publication Date

05 July 2018 (05.07.2018)

WIPO | PCT

(51) International Patent Classification:

C07F 17/00 (2006.01) *C08L 23/10* (2006.01)
B01J 31/38 (2006.01) *C08L 53/00* (2006.01)
C08F 4/64 (2006.01)

SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(21) International Application Number:

PCT/EP2017/084273

(22) International Filing Date:

21 December 2017 (21.12.2017)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

16207302.7 29 December 2016 (29.12.2016) EP

Published:

— with international search report (Art. 21(3))


(71) Applicant: BOREALIS AG [AT/AT]; IZD Tower, Wagramerstrasse 17-19, A-1220 Vienna (AT).

(72) Inventors: TOELTSCH, Wilfried; Eferdingerstrasse 5, 4614 Marchtrenk (AT). SCHWARZENBERGER, Simon; Ramsauerstraße 83, 4020 Linz (AT). LEHTINIEMI, Ismo; Tähkäpää 2, 04500 Kellokoski (FI).

(74) Agent: CAMPBELL, Neil; Dehns, St Bride's House, 10 Salisbury Square, London EC4Y 8JD (GB).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,

(54) Title: CATALYSTS



(57) Abstract: Claimed are metallocene-complexes of formula (I) [formula (I')] wherein M is Hf or Zr, L is a bridge comprising 1-2 C- or Si-atoms, The other variables are as defined in the claims.

- 1 -

Catalysts

This invention relates to new bisindenyl ligands, complexes thereof and catalysts comprising those complexes. The invention also relates to the use of the new bisindenyl

5 metallocene catalysts for the production of polypropylene homopolymers or propylene copolymers, especially with ethylene, with high activity levels, high molecular weight, and hence low MFR, and with ideal melting points. The catalysts are especially useful in the manufacture of propylene ethylene copolymers as they exhibit remarkable catalyst activity in such polymerisations.

10 Metallocene catalysts have been used to manufacture polyolefins for many years. Countless academic and patent publications describe the use of these catalysts in olefin polymerisation. Metallocenes are now used industrially and polyethylenes and polypropylenes in particular are often produced using cyclopentadienyl based catalyst systems with different substitution patterns.

15 The present inventors sought new metallocenes, which provide high activity, especially in the case of the homopolymerization of propylene or in the case of copolymerization between propylene and ethylene. The desired catalysts should also have improved performance in the production of high melting temperature and high molecular weight polypropylene homopolymers. The desired catalysts should also have improved 20 performance in the production of propylene-ethylene copolymers, for instance having high activity for high Mw copolymer products. The desired catalysts should also provide propylene-ethylene copolymers having desirable melting points. Various prior art references aim for one or more of these features.

C₂-symmetric metallocenes are disclosed for example in WO2007/116034. This 25 document reports the synthesis and characterisation of, *inter alia*, the metallocene rac-Me₂Si(2-Me-4-Ph-5-OMe-6-tBuInd)₂ZrCl₂ and the use of it as a polymerisation catalyst after activation with MAO for the homopolymerisation of propylene and copolymerisation of propylene with ethylene and higher alpha-olefins in solution polymerisation.

WO02/02576 describes, *inter alia*, rac-Me₂Si[2-Me-4-(3,5-tBu₂Ph)Ind]₂ZrCl₂ and 30 rac-Me₂Si[2-Me-4-(3,5-tBu₂Ph)Ind]₂ZrCl₂ (see also WO2014/096171) and its use in the manufacture of high Mw and high melting point polypropylene.

- 2 -

WO06/097497 describes, *inter alia*, *rac*-Me₂Si(2-Me-4-Ph-1,5,6,7-tetrahydro-s-indacen-1-yl)₂ZrCl₂ supported on silica and its use in the homo- and copolymerisation of propylene with ethylene.

WO2011/076780 describes the use of *rac*-Me₂Si(2-Me-4-Ph-1,5,6,7-tetrahydro-s-

5 indacen-1-yl)₂ZrCl₂ activated with methylalumoxane in solid particulated form without an external carrier, for propylene homopolymerisation

US 6,057,408 describes the influence of the 4-aryl substituent on the molecular weight of ethylene-propylene copolymers produced in liquid slurry.

Asymmetrical metallocenes able to produce isotactic polypropylene have been 10 described in the literature. WO2013/007650, describes certain asymmetrical catalysts comprising alkoxy groups at the 5-position of one of the rings such as dimethylsilylene (η^5 -6-*tert*-butyl-5-methoxy-2-methyl-4-phenyl-1*H*-inden-1-yl)-(η^5 -6-*tert*-butyl-2-methyl-4-phenyl-1*H*-inden-1-yl)zirconium dichloride. Despite its good performance, catalysts based on this reference are limited in terms of polypropylene homopolymer melting temperature, 15 productivity at low MFR. In addition, the overall productivity of the catalyst still needs to be improved.

WO2015/158790 discloses, *inter alia*, the complex “2-Zr” [dimethylsilanediyl [η^5 -6-*tert*-butyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-2-methylinden-1-yl]-[η^5 -4-(3,5-di-*tert*-butylphenyl)-2-methyl-5,6,7-trihydro-s-indacen-1-yl] zirconium dichloride] and describes the 20 use of this complex in the formation of ethylene/1-octene copolymers in a solution process. A direct comparison is made between a catalyst system of this metallocene, MAO and Trityl tetrakis(pentafluorophenyl)borate, against equivalent systems in which the metallocene is also *C*₁ and has two indenyl ligands “1-Zr” [anti-dimethylsilylene(2-methyl-4-phenyl-5-methoxy-6-*tert*-butyl-indenyl)(2-methyl-4-(4-*tert*-butyl-phenyl)indenyl)zirconium dichloride] 25 or is *C*₂ and has two indacenyl ligands “3-Zr” [dimethylsilylenebis-(2-i-butyl-4-(4'-*tert*-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl)zirconium dichloride]. The catalyst system containing 2-Zr is found to be inferior in terms of 1-octene incorporation to those containing 1-Zr and 3-Zr.

The catalysts of the invention should ideally be suited for use in solution or in 30 conventional solid supported form, e.g. using silica or alumina supports, or can be used in solid form, however, being free of external support or carrier.

- 3 -

The present applicant has previously developed an alternative to conventional inorganic supports. In WO03/051934, the inventors proposed an alternative form of catalyst which is provided in solid form but does not require a conventional external carrier material such as silica. The invention is based on the finding that a homogeneous catalyst system





5 containing an organometallic compound of a transition metal can be converted, in a controlled way, to solid, uniform catalyst particles by first forming a liquid/liquid emulsion system, which comprises as the dispersed phase, said solution of the homogeneous catalyst system, and as the continuous phase a solvent immiscible therewith, and then solidifying said dispersed droplets to form solid particles comprising the said catalyst.

10 The invention described in WO03/051934 enabled the formation of solid spherical catalyst particles of said organo transition metal catalyst without using e.g. external porous carrier particles, such as silica, normally required in the art. Thus, problems relating to catalyst silica residues can be solved by this type of catalyst. Further, it could be seen that catalyst particles having improved morphology, will give, due to the replica effect, polymer 15 particles having improved morphology as well. Catalysts of this invention should be able to utilise this method.

20 The inventors have developed new metallocene catalysts having improved polymerisation behaviour, higher catalyst productivity, improved performance in the production of high molecular weight polypropylene homopolymers, and reduced chain transfer to ethylene, enabling the production of propylene-ethylene copolymers. During copolymer manufacture, the reduced chain transfer to ethylene, enables the production of propylene-ethylene copolymers having higher molecular weights than are currently 25 achievable using alternative C_1 metallocenes.

A number of known metallocenes are set out in the table below:

25

			
CE3	CE2	CE1	CE4

- 4 -

<i>rac</i> -dimethylsilanediylbis[2-methyl-4-(4- <i>tert</i> -butylphenyl)indenyl]zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl(2-methyl-4-(4- <i>tert</i> -butylphenyl)inden-1-yl)(2-methyl-4-phenyl-5-methoxy-6- <i>tert</i> -butyl inden-1-yl) zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl(2-methyl-4-(4- <i>tert</i> -butylphenyl)inden-1-yl)(2-methyl-4-(4- <i>tert</i> -butylphenyl)-5-methoxy-6- <i>tert</i> -butyl inden-1-yl) zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl[2-methyl-4-(3',5'-di- <i>tert</i> -butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3',5'-di- <i>tert</i> -butylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl]zirconium dichloride
WO98/040331	WO2013/007650	WO2013/007650	WO2015/158790

The metallocene structures above exhibit moderate activity, and provide high melting polypropylene, or high molecular weight C2/C3 copolymers. However, it would be desirable to provide catalysts which have even higher activity, and which provide higher molecular

5 weight polypropylene and high molecular weight C2/C3 polymers. The present invention solves this problem.

The inventors have now found that further modification of the C_1 -symmetric metallocene ligand structure provides improved performance in both C3 homopolymerisation and C3/C2 random copolymerisation.

10 In particular, the catalysts of the invention enable

- very high activity in propylene homopolymerisation and propylene ethylene copolymerisation;
- improved performance in production of high molecular weight propylene homopolymers;
- improved comonomer incorporation in propylene copolymers;
- high activity for high Mw polymer products;
- desirable melting points.

Moreover, most metallocenes whose structure has been optimized to produce high molecular weight isotactic PP, show molecular weight limitations when used to produce 20 ethylene-propylene copolymers in the gas phase. It is known that tensile and impact properties of a heterophasic PP/EPR, for a given rubber comonomer composition, can be improved by increasing the molecular weight of the rubber phase (as described for example

- 5 -

in J. Appl. Polym. Sci. 2002, vol. 85, pp. 2412-2418 and in J. Appl. Polym. Sci. 2003, vol. 87, pp. 1702-1712). In addition, conventional metallocene catalysts produce a homopolymer matrix (hPP) with narrow Mw/Mn (usually below 3.0). It is known that a broad molecular weight distribution (Mw/Mn as measured by GPC) of the hPP matrix is beneficial for 5 processability and stiffness (as described for example in J. Appl. Polym. Sci. 1996, vol. 61, pp. 649-657).

We have additionally found that the metallocene complexes of the invention, thanks to the combination of indenyl ligands having different substitution patterns, can produce ethylene propylene rubber in the gas phase having higher molecular weight compared to 10 metallocenes of the prior art. They can also increase the Mw/Mn of the hPP component within a heterophasic PP/EPR blend. Especially, when producing a reactor blend in three steps (three reactors), the Mw/Mn of the homopolymer matrix can be made relatively broad.


Heterophasic PP/EPR blends can be made with rubber contents above 50 wt%, having good bulk densities and which are free-flowing also at the highest rubber contents.

15

Summary of Invention

Viewed from one aspect the invention provides a complex of formula (I):

20



- 6 -

M is Hf or Zr;

each X is a sigma ligand;

L is a bridge of formula $-(ER^8_2)_y-$;

y is 1 or 2;

5 E is C or Si;

each R⁸ is independently a C₁-C₂₀-hydrocarbyl, tri(C₁-C₂₀-alkyl)silyl, C₆-C₂₀-aryl, C₇-C₂₀-arylalkyl or C₇-C₂₀-alkylaryl or L is an alkylene group such as methylene or ethylene;

Ar and Ar' are each independently an aryl or heteroaryl group optionally substituted by 1 to 3 groups R¹ or R^{1'} respectively;

10 R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group, C₇₋₂₀ arylalkyl, C₇₋₂₀ alkylaryl group or C₆₋₂₀ aryl group with the proviso that if there are four or more R¹ and R^{1'} groups present in total, one or more of R¹ and R^{1'} is other than tert butyl;

R² and R^{2'} are the same or are different and are a CH₂-R⁹ group, with R⁹ being H or

15 linear or branched C₁₋₆-alkyl group, C₃₋₈ cycloalkyl group, C₆₋₁₀ aryl group;

each R³ is a -CH₂-, -CHRx- or C(Rx)₂- group wherein Rx is C₁₋₄ alkyl and where m is 2-6;


R⁵ is a linear or branched C₁-C₆-alkyl group, C₇₋₂₀ arylalkyl, C₇₋₂₀ alkylaryl group or C₆-C₂₀-aryl group;

20 R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C₁-C₆ alkyl group; and

R⁷ and R^{7'} are the same or are different and are H or a linear or branched C₁-C₆-alkyl group.

Viewed from another aspect the invention provides a complex of formula (Ia)

- 7 -



M is Hf or Zr;

each X is a sigma ligand;

L is a bridge of formula $-(ER^8_2)_y-$;

5 y is 1 or 2;

E is C or Si;

each R^8 is independently a C_1-C_{20} -hydrocarbyl, tri(C_1-C_{20} -alkyl)silyl, C_6-C_{20} -aryl, C_7-C_{20} -arylalkyl or C_7-C_{20} -alkylaryl or L is an alkylene group such as methylene or ethylene;

each n is independently 0, 1, 2 or 3;

10 R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1-C_6 -alkyl group, C_{7-20} arylalkyl, C_{7-20} alkylaryl group or C_{6-20} aryl group with the proviso that if there are four or more R^1 and $R^{1'}$ groups present in total, one or more of R^1 and $R^{1'}$ is other than tert butyl;

R^2 and $R^{2'}$ are the same or are different and are a CH_2-R^9 group, with R^9 being H or

15 linear or branched C_{1-6} -alkyl group, C_{3-8} cycloalkyl group, C_{6-10} aryl group;

each R^3 is a $-CH_2-$, $-CHRx-$ or $C(Rx)_2-$ wherein Rx is C_{1-4} alkyl and where m is 2-6;

R^5 is a linear or branched C_1-C_6 -alkyl group, C_{7-20} arylalkyl, C_{7-20} alkylaryl group or C_6-C_{20} -aryl group;


R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_1-C_6 alkyl group; and

- 8 -

R^7 and $R^{7'}$ are the same or are different and are H or a linear or branched C_1 - C_6 -alkyl group.

In a preferred embodiment of formula (Ia), L is of formula $-SiR_2^8-$, wherein each R^8 is independently a C₁-C₂₀-hydrocarbyl, tri(C₁-C₂₀-alkyl)silyl, C₆-C₂₀-aryl, C₇-C₂₀-arylalkyl or 5 C₇-C₂₀-alkylaryl.

Viewed from another aspect the invention provides a complex of formula (Ib):



wherein

M is Hf or Zr;

10 each X is a sigma ligand;

L is an alkylene bridge (e.g. methylene or ethylene) or a bridge of the formula $-\text{SiR}^8_2-$, wherein each R^8 is independently a $\text{C}_1\text{-C}_{20}$ -hydrocarbyl, tri($\text{C}_1\text{-C}_{20}$ -alkyl)silyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl or $\text{C}_7\text{-C}_{20}$ -alkylaryl;

each n is independently 0, 1, 2 or 3;

15 R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1 - C_6 -alkyl group, C_{7-20} arylalkyl, C_{7-20} alkylaryl group or C_{6-20} aryl group with the

- 9 -

proviso that if there are four or more R¹ and R^{1'} groups present in total, one or more of R¹ and R^{1'} is other than tert butyl;

R² and R^{2'} are the same or are different and are a CH₂-R⁹ group, with R⁹ being H or linear or branched C₁₋₆-alkyl group, C₃₋₈ cycloalkyl group, C₆₋₁₀ aryl group;

5 R⁵ is a linear or branched C₁-C₆-alkyl group, C₇₋₂₀ arylalkyl, C₇₋₂₀ alkylaryl group or C₆-C₂₀-aryl group;

R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C₁-C₆ alkyl group; and

10 R⁷ and R^{7'} are the same or are different and are H or a linear or branched C₁-C₆-alkyl group.

Viewed from another aspect the invention provides a catalyst comprising

(i) a complex of formula (I) as hereinbefore defined and

(ii) a cocatalyst comprising a compound of a group 13 metal,

15 The catalyst of the invention can be used in non-supported form or in solid form. The catalyst of the invention may be used as a homogeneous catalyst or heterogeneous catalyst.

The catalyst of the invention in solid form, preferably in solid particulate form, can be either supported on an external carrier material, like silica or alumina, or, in a particularly preferred embodiment, is free from an external carrier, however still being in solid form. For example, the solid catalyst is obtainable by a process in which

20 (a) a liquid/liquid emulsion system is formed, said liquid/liquid emulsion system comprising a solution of the catalyst components (i) and (ii) dispersed in a solvent so as to form dispersed droplets; and

(b) solid particles are formed by solidifying said dispersed droplets.

Viewed from another aspect the invention provides a process for the manufacture of a 25 catalyst as hereinbefore defined comprising obtaining a complex of formula (I) and a cocatalyst as hereinbefore described;

forming a liquid/liquid emulsion system, which comprises a solution of catalyst components (i) and (ii) dispersed in a solvent, and solidifying said dispersed droplets to form solid particles.

30 Viewed from another aspect the invention provides the use in propylene polymerisation of a catalyst as hereinbefore defined, especially for the formation of a

- 10 -

polypropylene homopolymer or propylene copolymer, e.g. with ethylene or a C4-10 alpha olefin such as 1-hexene.

Viewed from another aspect the invention provides a process for the polymerisation propylene comprising reacting propylene and optional comonomers with a catalyst as hereinbefore described, especially for the formation polypropylene homopolymer or propylene copolymer, e.g. with ethylene.

Definitions

Throughout the description the following definitions are employed.

By "free from an external carrier" is meant that the catalyst does not contain an external support, such as an inorganic support, for example, silica or alumina, or an organic polymeric support material.

The term "C₁₋₂₀ hydrocarbyl group" includes C₁₋₂₀ alkyl, C₂₋₂₀ alkenyl, C₂₋₂₀ alkynyl, C₃₋₂₀ cycloalkyl, C₃₋₂₀ cycloalkenyl, C₆₋₂₀ aryl groups, C₇₋₂₀ alkylaryl groups or C₇₋₂₀ arylalkyl groups or of course mixtures of these groups such as cycloalkyl substituted by alkyl. Linear and branched hydrocarbyl groups cannot contain cyclic units. Aliphatic hydrocarbyl groups cannot contain aryl rings.

Unless otherwise stated, preferred C₁₋₂₀ hydrocarbyl groups are C₁₋₂₀ alkyl, C₄₋₂₀ cycloalkyl, C₅₋₂₀ cycloalkyl-alkyl groups, C₇₋₂₀ alkylaryl groups, C₇₋₂₀ arylalkyl groups or C₆₋₂₀ aryl groups, especially C₁₋₁₀ alkyl groups, C₆₋₁₀ aryl groups, or C₇₋₁₂ arylalkyl groups, e.g. C₁₋₈ alkyl groups. Most especially preferred hydrocarbyl groups are methyl, ethyl, propyl, isopropyl, tert-butyl, isobutyl, C₅₋₆-cycloalkyl, cyclohexylmethyl, phenyl or benzyl.

The term "halo" includes fluoro, chloro, bromo and iodo groups, especially chloro or fluoro groups, when relating to the complex definition.

The oxidation state of the metal ion is governed primarily by the nature of the metal ion in question and the stability of the individual oxidation states of each metal ion.

It will be appreciated that in the complexes of the invention, the metal ion M is coordinated by ligands X so as to satisfy the valency of the metal ion and to fill its available coordination sites. The nature of these σ -ligands can vary greatly.

- 11 -

The terms “C4 phenyl ring” and “C4’ phenyl ring” relate to the substituted phenyl rings attached to the 4 and 4’ positions of the indenyl and indacenyl rings, respectively. The numbering of these rings will be evident from the structures indicated herein.

Catalyst activity is defined in this application to be the amount of polymer produced/g

5 catalyst/h. Catalyst metal activity is defined here to be the amount of polymer produced/g Metal/h. The term productivity is also sometimes used to indicate the catalyst activity although herein it designates the amount of polymer produced per unit weight of catalyst.

The term “molecular weight” is used herein to refer to weight average molecular weight Mw unless otherwise stated.

10 There can be up to 6 R¹ and R^{1'} groups combined in the complex of formula (I). It is required that if there are four or more R¹ and R^{1'} groups, at least one is not tert butyl. There may be 0, 1, 2 or 3 tert butyl groups on the complex but no more.

Detailed Description of invention


15

This invention relates to a series of new ligands, complexes and hence catalysts that are ideal for the polymerisation of propylene. The complexes of the invention are asymmetrical. Asymmetrical means simply that the two ligands forming the metallocene are different, that is, each ligand bears a set of substituents that are chemically different.

20 The complexes of the invention are preferably chiral, racemic bridged bisindenyl C₁-symmetric metallocenes. Although the complexes of the invention are formally C₁-symmetric, the complexes ideally retain a pseudo-C₂-symmetry since they maintain C₂-symmetry in close proximity of the metal center although not at the ligand periphery. By nature of their chemistry both anti and syn enantiomer pairs (in case of C₁-symmetric complexes) are formed during the synthesis of the complexes. For the purpose of this invention, racemic-anti means that the two indenyl ligands are oriented in opposite directions with respect to the cyclopentadienyl-metal-cyclopentadienyl plane, while racemic-syn means that the two indenyl ligands are oriented in the same direction with respect to the cyclopentadienyl-metal-cyclopentadienyl plane, as shown in the scheme below.

25 30

- 12 -




Formula (I), and any sub formulae, are intended to cover both syn- and anti-

5 configurations. Preferred complexes are in the anti configuration.

It is preferred if the metallocenes of the invention are employed as the racemic or racemic-anti isomers. Ideally therefore at least 95%mol, such as at least 98%mol, especially at least 99%mol of the metallocene is in the racemic or racemic-anti isomeric form.

In the catalysts of the invention the following preferences apply. Catalysts according to the invention are of formula (I):



In a complex of formula (I) it is preferred if M is Zr or Hf, preferably Zr;

15 Each X is a sigma ligand. Most preferably each X is independently a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group or an R group, where R is a C₁₋₆ alkyl, phenyl or benzyl group. Most preferably X is chlorine, benzyl or a methyl group. Preferably both X groups

- 13 -

are the same. The most preferred options are two chlorides, two methyl or two benzyl groups, especially two chlorides.

L is $-(ER^8_2)_y-$. It is preferred if E is Si. It is preferred if y is 1. $-(ER^8_2)_y-$ is preferably a methylene or ethylene linker or L is a bridge of the formula $-SiR^8_2-$, wherein each R⁸ is independently a C₁-C₂₀-hydrocarbyl, tri(C₁-C₂₀-alkyl)silyl, C₆-C₂₀-aryl, C₇-C₂₀-arylalkyl or C₇-C₂₀-alkylaryl. The term C₁₋₂₀ hydrocarbyl group therefore includes C₁₋₂₀ alkyl, C₂₋₂₀ alkenyl, C₂₋₂₀ alkynyl, C₃₋₂₀ cycloalkyl, C₃₋₂₀ cycloalkenyl, C₆₋₂₀ aryl groups, C₇₋₂₀ alkylaryl groups or C₇₋₂₀ arylalkyl groups or of course mixtures of these groups such as cycloalkyl substituted by alkyl. Unless otherwise stated, preferred C₁₋₂₀ hydrocarbyl groups are C₁₋₂₀ alkyl, C₄₋₂₀ cycloalkyl, C₅₋₂₀ cycloalkyl-alkyl groups, C₇₋₂₀ alkylaryl groups, C₇₋₂₀ arylalkyl groups or C₆₋₂₀ aryl groups. If L is an alkylene linker group, ethylene and methylene are preferred.

Preferably both R⁸ groups are the same. It is preferred if R⁸ is a C₁-C₁₀-hydrocarbyl or C₆-C₁₀-aryl group, such as methyl, ethyl, propyl, isopropyl, tertbutyl, isobutyl, C₅₋₆-cycloalkyl, cyclohexylmethyl, phenyl or benzyl, more preferably both R⁸ are a C₁-C₆-alkyl, C₃₋₈ cycloalkyl or C₆-aryl group, such as a C₁-C₄-alkyl, C₅₋₆ cycloalkyl or C₆-aryl group and most preferably both R⁸ are methyl or one is methyl and another cyclohexyl. Alkylene linkers are preferably methylene or ethylene. L is most preferably $-Si(CH_3)_2-$.

Ar and Ar' are preferably phenyl rings.

Each substituent R¹ and R^{1'} are independently the same or different, and are preferably a linear or branched C₁-C₆-alkyl group or C₆₋₂₀ aryl groups, more preferably a linear or branched C₁-C₄ alkyl group. Preferably each R¹ and each R^{1'} are independently methyl, ethyl, isopropyl or -CMe₃, especially methyl or -CMe₃. Preferably each R¹ is the same and each R^{1'} is the same.

Each n is independently 0, 1, 2 or 3, preferably 1 or 2. The total of the two "n" values is ideally 2, 3 or 4. When n is 1 the ring is preferably substituted with the group R¹ or R^{1'} at the *para* position (4 or 4' position). When n is 2 the ring is preferably substituted with the groups R¹ or R^{1'} at the *ortho* positions (3 and 5, or 3' and 5' positions).

In all embodiments of the invention the substitution of the C(4) and C(4') phenyl groups are subject to the proviso that the complex is substituted in total with 0, 1, 2 or 3 CMe₃ groups across the C(4) and C(4') phenyl rings combined, preferably 0, 1 or 2 CMe₃

- 14 -

groups across the C(4) and C(4') phenyl rings combined. Alternatively stated, if the two n values sum to 4 or more, at least one R¹ or R^{1'} group present cannot represent tert butyl.

Ideally, no C(4) or C(4') ring will comprise two branched substituents. If a C(4) or C(4') ring contains two substituents (i.e. n is 2) then it is preferred if R¹ or R^{1'} is C1-4 linear alkyl, e.g. methyl.

If a C(4) or C(4') ring contains one substituent (i.e. n is 1) then it is preferred that R¹ or R^{1'} is a branched C4-6 alkyl, e.g. tert butyl.

In a particular embodiment, Ar and Ar' in formula I (or any formula below) are independently selected from phenyl rings substituted in the 3,5- or 4-positions with a linear or branched C₁-C₄ alkyl group; i.e. corresponding to 3,5 or 4-position substitutions with R¹ and R_{1'} being a C₁-C₄ alkyl group and n being 1 or 2. In a particular embodiment, Ar and Ar' in formula I are independently selected from 3,5-dimethyl phenyl, 3,5-ditertbutyl and 4-(tert-butyl)-phenyl. Therefore, in a particular embodiment, in the complex of formula I, both Ar and Ar' are 3,5-dimethyl phenyl, both Ar and Ar' are 4-(tert-butyl)-phenyl, or one of Ar and Ar' is 3,5-dimethyl phenyl and the other is 4-(tert-butyl)-phenyl. Other preferred options include one of Ar or Ar' being 3,5-ditertbutylphenyl with the other being 3,5-dimethylphenyl or 4-tertbutylphenyl. These particular embodiments may be applied to all of the structures II-VIII described herein, where technically viable. In other words, in a particular embodiment, R¹, R^{1'} and each independent value of n are selected such that the C(4) or C(4') phenyl rings are 3,5-dimethyl phenyl, 3,5-ditertbutylphenyl and/or 4-(tert-butyl)-phenyl.

In an embodiment at least one of the C(4) or C(4') phenyl rings is 3,5-dimethyl phenyl.

In an embodiment at least one of the C(4) or C(4') phenyl rings is 4-(tert-butyl)-phenyl.

R² and R^{2'} are each the same or different, and are a CH₂-R⁹ group, with R⁹ being H or linear or branched C₁-C₆-alkyl group, like methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec.-butyl and tert.-butyl or C₃₋₈ cycloalkyl (e.g. cyclohexyl) or C₆₋₁₀ aryl (pref phenyl). Preferably R² and R^{2'} are the same and are a CH₂-R⁹ group, with R⁹ being H or linear or branched C₁-C₄-alkyl group, more preferably R² and R^{2'} are the same and are a CH₂-R⁹ group, with R⁹ being H or linear or branched C₁-C₃-alkyl group. Most preferably R² and R^{2'} are both methyl.

- 15 -

R^3 is preferably $-CH_2-$. The subscript m is preferably 2 to 4, such as 3 (thus forming a 5 membered ring).

R^5 is a preferably linear or branched C_1 - C_6 -alkyl group or C_{6-20} aryl group, such as methyl, ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec.-butyl and tert.-butyl, preferably a

5 linear C_1 - C_4 -alkyl group, more preferably a C_1 - C_2 -alkyl group and most preferably methyl.

R^6 is a $C(R^{10})_3$ group, with each R^{10} being the same or different and being a linear or branched C_1 - C_6 -alkyl group. Preferably each R^{10} are the same or different with R^{10} being a linear or branched C_1 - C_4 -alkyl group, more preferably with R^{10} being the same and being a C_1 - C_2 -alkyl group. Most preferably R^6 is a tert.-butyl group and hence all R^{10} groups are


10 methyl.

R^7 and $R^{7'}$ are each the same or different, and are H or a linear or branched C_1 - C_6 -alkyl group, preferably H or a linear or branched C_1 - C_4 -alkyl group, and more preferably H or a C_1 - C_2 -alkyl group. In some embodiments one of R^7 or $R^{7'}$ is H and the other is a linear or branched C_1 - C_6 -alkyl group, preferably a linear or branched C_1 - C_4 -alkyl group and more

15 preferably a C_1 - C_2 -alkyl group. It is especially preferred that R^7 and $R^{7'}$ are the same. It is most preferred that both R^7 and $R^{7'}$ are H.

In a preferred embodiment, the invention provides a complex of formula (II)

- 16 -



wherein

M is Hf or Zr;

X is a sigma ligand, preferably each X is independently a hydrogen atom, a halogen

5 atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or benzyl group;

L is an alkylene bridge or a bridge of the formula $-\text{SiR}^8_2-$, wherein each R⁸ is independently C₁-C₆-alkyl, C₃₋₈ cycloalkyl or C₆-aryl group;

each n is independently 1 or 2;

10 R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group with the proviso that if there are four R¹ and R^{1'} groups present, all 4 cannot simultaneously be tert butyl;


R² and R^{2'} are the same or are different and are a CH₂-R⁹ group, with R⁹ being H or linear or branched C₁₋₆-alkyl group;

R⁵ is a linear or branched C₁-C₆-alkyl group; and

15 R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C₁-C₆ alkyl group.

In a further preferred embodiment, the invention provides a complex of formula (III)

- 17 -



wherein

M is Hf or Zr;

each X is a sigma ligand, preferably each X is independently a hydrogen atom, a

5 halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or benzyl group;

L is -SiR⁸₂₋, wherein each R⁸ is C₁₋₆ alkyl or C₃₋₈ cycloalkyl;

each n is independently 1 or 2;

10 R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C_{1-C₆}-alkyl group, group with the proviso that if there are four R¹ and R^{1'} groups


present, all 4 cannot simultaneously be tert butyl;

R⁵ is a linear or branched C_{1-C₆}-alkyl group; and

R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C_{1-C₆} alkyl group.

In a further preferred embodiment, the invention provides a complex of formula (IV)

- 18 -



wherein

M is Hf or Zr;

each X is a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or

5 benzyl group;

L is -SiR⁸₂₋, wherein each R⁸ is C₁₋₄ alkyl or C₅₋₆ cycloalkyl;

each n is independently 1 or 2;


10 R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group with the proviso that if there are four R¹ and R^{1'} groups present, all 4 cannot simultaneously be tert butyl,

R⁵ is a linear or branched C₁-C₆-alkyl group; and

R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C₁-C₆ alkyl group.

In a further preferred embodiment, the invention provides a complex of formula (V)

- 19 -



wherein

M is Hf or Zr;

X is a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or benzyl

5 group;

L is -SiMe₂;

each n is independently 1 or 2;

R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group, group with the proviso that if there are four R¹ and R^{1'} groups


10 present, all 4 cannot simultaneously be tert butyl,

R⁵ is a linear or branched C₁-C₄-alkyl group; and

R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C₁-C₄ alkyl group.

In a further preferred embodiment, the invention provides a complex of formula (VI)

- 20 -



wherein

M is Hf or Zr;

X is a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or benzyl

5 group;

L is -SiMe₂;

each n is independently 1 or 2;


10 R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group, group with the proviso that if there are four R¹ and R^{1'} groups present, all 4 cannot simultaneously be tert butyl;

R⁵ is a linear C₁-C₄-alkyl group such as methyl; and

R⁶ is tert butyl.

In a further preferred embodiment, the invention provides a complex of formula (VII)

- 21 -



wherein

M is Hf or Zr;

X is a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or benzyl

5 group, especially chlorine;

L is -SiMe₂;

each n is independently 1 or 2;

10 R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₄-alkyl group with the proviso that if there are four R¹ and R^{1'} groups present,


all 4 cannot simultaneously be tert butyl;

R⁵ is methyl; and

R⁶ is tert butyl.

In a preferred embodiment, the invention provides a complex of formula (VIII)

- 22 -



wherein

M is Hf or Zr;

X is Cl;

5 L is $-\text{SiMe}_2$;

each n is independently 1 or 2;

R¹ and R^{1'} are each independently methyl or tert butyl with the proviso that if there are four R¹ and R^{1'} groups present, all 4 cannot simultaneously be tert butyl,

R⁵ is methyl; and

10 R⁶ is tert butyl.

In any of formula (I) to (VIII) it is preferred if the 4-position substituent on either indenyl or indacenyl ring is a 3,5-dimethylphenyl- or 4-tBu-phenyl group.

In any of formula (I) to (VIII) it is preferred if the 4-position substituent on one of the indenyl or indacenyl ring is a 3,5-ditertbutyl and the other indenyl or indacenyl ring carries a 15 4-position 3,5-dimethylphenyl- or 4-tBu-phenyl group. In such a structure it is preferred if the ditertbutylphenyl is present on the indenyl ring.

- 23 -

In any of formula (I) to (VIII) it is preferred that if n=2 then both R¹ groups are the same.

In any of formula (I) to (VIII) it is preferred that if n=2 then both R^{1'} groups are the same.

5 In any of formula (I) to (VIII) it is preferred that if n=2 then R¹ groups are on the 3,5-position.

In any of formula (I) to (VIII) it is preferred that if n=2 then R^{1'} groups are on the 3,5-position.

In any of formula (I) to (VIII) it is preferred that if n=1 then R¹ is on the 4-position.

10 In any of formula (I) to (VIII) it is preferred that if n=1 then R^{1'} is on the 4-position.

Particular complexes of the invention include:

15 *Racemic-anti-dimethylsilanediyl[2-methyl-4-(4-tert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

Racemic-anti-dimethylsilanediyl[2-iso-butyl-4-(4-tert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

20 *Racemic-anti-dimethylsilanediyl[2-neo-pentyl-4-(4-tert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

Racemic-anti-dimethylsilanediyl[2-benzyl-4-(4-tert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

25 *Racemic-anti-dimethylsilanediyl[2-cyclohexylmethyl-4-(4-tert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

Racemic-anti-dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

30

- 24 -

Racemic-anti-dimethylsilanediyl[2-iso-butyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

5 *Racemic-anti-dimethylsilanediyl[2-neo-pentyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

Racemic-anti-dimethylsilanediyl[2-benzyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

10 *Racemic-anti-dimethylsilanediyl[2-cyclohexylmethyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

15 *Racemic-anti-dimethylsilanediyl[2-cyclohexylmethyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*







Racemic-anti-dimethylsilanediyl[2-methyl-4-(4-tert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-ditert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

20 *Racemic-anti-dimethylsilanediyl[2-methyl-4-(3,5-ditert-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tert-butylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

25 *Racemic-anti-dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(4-tertbutylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,*

Racemic-anti-dimethylsilanediyl[2-methyl-4-(4-tertbutylphenyl)-5,6,7-trihydro-s-indacen-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyldienyl zirconium dichloride or dimethyl,

- 25 -

		
MC-IE1	MC-IE2	MC-IE3
<i>rac-anti</i> -dimethylsilanediyl [2-methyl-4-(4'- <i>tert</i> -butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(4'- <i>tert</i> -butylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl] zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl [2-methyl-4-(3',5'-dimethylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3',5'-dimethylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl] zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl [2-methyl-4-(4'- <i>tert</i> -butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3',5'-dimethylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl] zirconium dichloride
		
MC-IE4	MC-IE5	MC-IE6
<i>rac-anti</i> -dimethylsilanediyl[2-methyl-4-(4'- <i>tert</i> -butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3',5'-di- <i>tert</i> -butylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl]zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl[2-methyl-4-(3',5'-dimethylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3',5'-di- <i>tert</i> -butylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl]zirconium dichloride	<i>rac-anti</i> -dimethylsilanediyl[2-methyl-4-(3',5'-di- <i>tert</i> -butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(4'- <i>tert</i> -butylphenyl)-5-methoxy-6- <i>tert</i> -butylinden-1-yl]zirconium dichloride

For the avoidance of doubt, any narrower definition of a substituent offered above can be combined with any other broad or narrowed definition of any other substituent.

- 26 -

Throughout the disclosure above, where a narrower definition of a substituent is presented, that narrower definition is deemed disclosed in conjunction with all broader and narrower definitions of other substituents in the application.


5 **Synthesis**

The ligands required to form the catalysts of the invention can be synthesised by any process and the skilled organic chemist would be able to devise various synthetic protocols for the manufacture of the necessary ligand materials. WO2007/116034 discloses the 10 necessary chemistry and is herein incorporated by reference. Synthetic protocols can also generally be found in WO2002/02576, WO2011/135004, WO2012/084961, WO2012/001052, WO2011/076780 and WO2015/158790. The examples section also provides the skilled person with sufficient direction.


15 **Intermediates**

Whilst the invention primarily relates to complexes and catalysts thereof, the ligands used to form those complexes are also new. The invention further relates therefore to ligands of formula (Ib') from which the MX_2 coordination has been removed and the proton returned 20 to the indenyl. Ligands of interest are therefore of formula (I')

- 27 -



preferably (Ib')



5

wherein the substituents are as hereinbefore defined and the dotted lines represent a double bond present in between carbons 1 and 2 or 2 and 3 of the indenyl ring, and between carbons 1' and 2' or 2' and 3' of the indacenyl ring. It will be appreciated therefore that this

- 28 -

molecule contains double bond isomers. By double bond isomers is meant the compounds where the double bond is positioned between the 2 and 3 atoms rather than 1 and 2 atoms of the bicyclic ring. It may be that more than one double bond isomer is present in a sample.

Preferred ligands are analogues of the complexes (II) to (VIII) described above from which

5 MX₂ coordination has been removed and the proton returned to the indenyl.

Cocatalyst


To form an active catalytic species it is normally necessary to employ a cocatalyst as 10 is well known in the art. Cocatalysts comprising one or more compounds of Group 13 metals, like organoaluminium compounds or borates used to activate metallocene catalysts are suitable for use in this invention.

The olefin polymerisation catalyst system of the invention comprises (i) a complex as defined herein; and normally (ii) an aluminium alkyl compound (or other appropriate 15 cocatalyst), or the reaction product thereof. Thus the cocatalyst is preferably an alumoxane, like MAO or an alumoxane other than MAO.

Borate cocatalysts can also be employed. It will be appreciated by the skilled man that where boron based cocatalysts are employed, it is normal to preactivate the complex by reaction thereof with an aluminium alkyl compound, such as TIBA. This procedure is well 20 known and any suitable aluminium alkyl, e.g. Al(C₁₋₆-alkyl)₃, can be used.

It is also possible to use a mixture of Al based and B based cocatalysts.

The aluminoxane cocatalyst can be one of formula (X):



25

where n is usually from 6 to 20 and R has the meaning below.

Aluminoxanes are formed on partial hydrolysis of organoaluminium compounds, for example those of the formula AlR₃, AlR₂Y and Al₂R₃Y₃ where R can be, for example, C1-C10 alkyl, preferably C1-C5 alkyl, or C3-10-cycloalkyl, C7-C12 -arylalkyl or alkylaryl 30 and/or phenyl or naphthyl, and where Y can be hydrogen, halogen, preferably chlorine or

- 29 -

bromine, or C1-C10 alkoxy, preferably methoxy or ethoxy. The resulting oxygen-containing aluminoxanes are not in general pure compounds but mixtures of oligomers of the formula (X).

The preferred aluminoxane is methylaluminoxane (MAO). Since the aluminoxanes

5 used according to the invention as cocatalysts are not, owing to their mode of preparation, pure compounds, the molarity of aluminoxane solutions hereinafter is based on their aluminium content.

It has been surprisingly found however, that in the context of heterogeneous catalysis, where catalysts are not supported on any external carrier or supported as described above,

10 that in specific cases higher activities can be achieved if a boron based cocatalyst is also employed as a cocatalyst. It will be appreciated by the skilled man that where boron based cocatalysts are employed, it is normal to preactivate the complex by reaction thereof with an aluminium alkyl compound, such as TIBA. This procedure is well known and any suitable aluminium alkyl, preferably an aluminium alkyl compounds of the formula (X) AlR_3 with R

15 being a linear or branched C₂-C₈-alkyl group, can be used.

Preferred aluminium alkyl compounds are triethylaluminium, tri-isobutylaluminium, tri-isohexylaluminium, tri-n-octylaluminium and tri-isoctylaluminium.

Boron based cocatalysts of interest include boron compounds containing a borate 3⁺ ion, i.e. borate compounds. These compounds generally contain an anion of formula:


20



where Z is an optionally substituted phenyl derivative, said substituent being a halo-C₁₋₆-alkyl or halo group. Preferred options are fluoro or trifluoromethyl. Most preferably, 25 the phenyl group is perfluorinated. Such ionic cocatalysts preferably contain a non-coordinating anion such as tetrakis(pentafluorophenyl)borate.

Suitable counterions are protonated amine or aniline derivatives or phosphonium ions. These may have the general formula (XII) or (XIII):


30



- 30 -

where Q is independently H, C₁₋₆-alkyl, C₃₋₈ cycloakyl, phenylC₁₋₆-alkylene- or optionally substituted Ph. Optional substituents may be C₁₋₆-alkyl, halo or nitro. There may be one or more than one such substituent. Preferred substituted Ph groups include therefore para-substituted phenyl, preferably tolyl or dimethylphenyl.

5 It is preferred if at least one Q group is H, thus preferred compounds are those of formula:



10 Preferred phenyl-C₁₋₆-alkyl- groups include benzyl.

Suitable counterions therefore include: methylammonium, anilinium, dimethylammonium, diethylammonium, N-methylanilinium, diphenylammonium, N,N-dimethylanilinium, trimethylammonium, triethylammonium, tri-n-butylammonium, methyldiphenylammonium, p-bromo-N,N-dimethylanilinium or p-nitro-N,N-

15 dimethylanilinium, especially dimethylammonium or N,N-dimethylanilinium. The use of pyridinium as an ion is a further option.

Phosphonium ions of interest include triphenylphosphonium, triethylphosphonium, diphenylphosphonium, tri(methylphenyl)phosphonium and tri(dimethylphenyl)phosphonium. A more preferred counterion is trityl (CPh₃⁺) or analogues thereof in which the Ph group is 20 functionalised to carry one or more alkyl groups. Highly preferred borates of use in the invention therefore comprise the tetrakis(pentafluorophenyl)borate ion.

Preferred ionic compounds which can be used according to the present invention include:

tributylammoniumtetra(pentafluorophenyl)borate,

25 tributylammoniumtetra(trifluoromethylphenyl)borate,

tributylammoniumtetra-(4-fluorophenyl)borate,

N,N-dimethylcyclohexylammoniumtetrakis-(pentafluorophenyl)borate,

N,N-dimethylbenzylammoniumtetrakis(pentafluorophenyl)borate,

N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate,

30 N,N-di(propyl)ammoniumtetrakis(pentafluorophenyl)borate,

di(cyclohexyl)ammoniumtetrakis(pentafluorophenyl)borate,

triphenylcarbeniumtetrakis(pentafluorophenyl)borate,

- 31 -

or ferroceniumtetrakis(pentafluorophenyl)borate.

Preference is given to triphenylcarbeniumtetrakis(pentafluorophenyl) borate,

N,N- dimethylcyclohexylammoniumtetrakis(pentafluorophenyl)borate,

5 N,N- dimethylbenzylammoniumtetrakis(pentafluorophenyl)borate or
N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate.

It has been surprisingly found that certain boron cocatalysts are especially preferred.

Preferred borates of use in the invention therefore comprise the trityl ion. Thus the use of

N,N-dimethylammonium-tetrakis(pentafluorophenyl)borate and $\text{Ph}_3\text{CB}(\text{PhF}_5)_4$ and analogues

10 therefore are especially favoured.

In one embodiment, preferably both cocatalysts, an aluminoxane and a boron based cocatalyst, are used in the catalyst system of the present invention.

Suitable amounts of cocatalyst will be well known to the skilled man.

The molar ratio of boron to the metal ion of the metallocene may be in the range 0.5:1

15 to 10:1 mol/mol, preferably 1:1 to 10:1, especially 1:1 to 5:1 mol/mol.

The molar ratio of Al in the aluminoxane to the metal ion of the metallocene may be in the range 1:1 to 2000:1 mol/mol, preferably 10:1 to 1000:1, and more preferably 50:1 to 500:1 mol/mol.

20 Catalyst Manufacture

The metallocene complex of the present invention can be used in combination with a suitable cocatalyst as a catalyst for the polymerization of propylene, e.g. in a solvent such as toluene or an aliphatic hydrocarbon, (i.e. for polymerization in solution), as it is well known 25 in the art. Preferably, polymerization of propylene takes place in the condensed phase or in gas phase.

The catalyst of the invention can be used in supported or unsupported form. The particulate support material used is preferably an organic or inorganic material, such as silica, alumina or zirconia or a mixed oxide such as silica-alumina, in particular silica, alumina or 30 silica-alumina. The use of a silica support is preferred. The skilled man is aware of the procedures required to support a metallocene catalyst.

- 32 -

Especially preferably the support is a porous material so that the complex may be loaded into the pores of the support, e.g. using a process analogous to those described in WO94/14856 (Mobil), WO95/12622 (Borealis) and WO2006/097497. The particle size is not critical but is preferably in the range 5 to 200 μm , more preferably 20 to 80 μm . The use 5 of these supports is routine in the art.

In an alternative embodiment, no support is used at all. Such a catalyst can be prepared in solution, for example in an aromatic solvent like toluene, by contacting the metallocene (as a solid or as a solution) with the cocatalyst, for example methylalumininoxane or a borane or a borate salt previously dissolved in an aromatic solvent, or can be prepared by 10 sequentially adding the dissolved catalyst components to the polymerization medium. In a preferred embodiment, the metallocene (when X differs from alkyl or hydrogen) is prereacted with an aluminum alkyl, in a ratio metal/aluminum of from 1:1 up to 1:500, preferably from 1:1 up to 1:250, and then combined with a solution of the borane or borate cocatalyst dissolved in an aromatic solvent, either in a separate vessel or directly into the polymerization 15 reactor. Preferred metal/boron ratios are between 1:1 and 1:100, more preferably 1:1 to 1:10.

In one particularly preferred embodiment, no external carrier is used but the catalyst is still presented in solid particulate form. Thus, no external support material, such as inert organic or inorganic carrier, for example silica as described above is employed.

In order to provide the catalyst of the invention in solid form but without using an 20 external carrier, it is preferred if a liquid/liquid emulsion system is used. The process involves forming dispersing catalyst components (i) and (ii) in a solvent, and solidifying said dispersed droplets to form solid particles.

In particular, the method involves preparing a solution of one or more catalyst 25 components; dispersing said solution in an solvent to form an emulsion in which said one or more catalyst components are present in the droplets of the dispersed phase; immobilising the catalyst components in the dispersed droplets, in the absence of an external particulate porous support, to form solid particles comprising the said catalyst, and optionally recovering said particles.

This process enables the manufacture of active catalyst particles with improved 30 morphology, e.g. with a predetermined spherical shape, surface properties and particle size and without using any added external porous support material, such as an inorganic oxide, e.g. silica. By the term "preparing a solution of one or more catalyst components" is meant

that the catalyst forming compounds may be combined in one solution which is dispersed to the immiscible solvent, or, alternatively, at least two separate catalyst solutions for each part of the catalyst forming compounds may be prepared, which are then dispersed successively to the solvent.

5 In a preferred method for forming the catalyst at least two separate solutions for each or part of said catalyst may be prepared, which are then dispersed successively to the immiscible solvent.

More preferably, a solution of the complex comprising the transition metal compound and the cocatalyst is combined with the solvent to form an emulsion wherein that inert 10 solvent forms the continuous liquid phase and the solution comprising the catalyst components forms the dispersed phase (discontinuous phase) in the form of dispersed droplets. The droplets are then solidified to form solid catalyst particles, and the solid particles are separated from the liquid and optionally washed and/or dried. The solvent forming the continuous phase may be immiscible to the catalyst solution at least at the 15 conditions (e. g. temperatures) used during the dispersing step.

The term "immiscible with the catalyst solution" means that the solvent (continuous phase) is fully immiscible or partly immiscible i.e. not fully miscible with the dispersed phase solution.

Preferably said solvent is inert in relation to the compounds of the catalyst system to 20 be produced. Full disclosure of the necessary process can be found in WO03/051934 which is herein incorporated by reference.

The inert solvent must be chemically inert at least at the conditions (e.g. temperature) used during the dispersing step. Preferably, the solvent of said continuous phase does not contain dissolved therein any significant amounts of catalyst forming compounds. Thus, the 25 solid particles of the catalyst are formed in the droplets from the compounds which originate from the dispersed phase (i.e. are provided to the emulsion in a solution dispersed into the continuous phase).

The terms "immobilisation" and "solidification" are used herein interchangeably for 30 the same purpose, i.e. for forming free flowing solid catalyst particles in the absence of an external porous particulate carrier, such as silica. The solidification happens thus within the droplets. Said step can be effected in various ways as disclosed in said WO03/051934. Preferably solidification is caused by an external stimulus to the emulsion system such as a

- 34 -

temperature change to cause the solidification. Thus in said step the catalyst component (s) remain "fixed" within the formed solid particles. It is also possible that one or more of the catalyst components may take part in the solidification/immobilisation reaction.

Accordingly, solid, compositionally uniform particles having a predetermined particle 5 size range can be obtained.

Furthermore, the particle size of the catalyst particles of the invention can be controlled by the size of the droplets in the solution, and spherical particles with a uniform particle size distribution can be obtained.

The invention is also industrially advantageous, since it enables the preparation of the 10 solid particles to be carried out as a one-pot procedure. Continuous or semicontinuous processes are also possible for producing the catalyst.

Dispersed Phase

15 The principles for preparing two phase emulsion systems are known in the chemical field. Thus, in order to form the two phase liquid system, the solution of the catalyst component (s) and the solvent used as the continuous liquid phase have to be essentially immiscible at least during the dispersing step. This can be achieved in a known manner e.g. by choosing said two liquids and/or the temperature of the dispersing step/solidifying step 20 accordingly.

A solvent may be employed to form the solution of the catalyst component (s). Said solvent is chosen so that it dissolves said catalyst component (s). The solvent can be preferably an organic solvent such as used in the field, comprising an optionally substituted hydrocarbon such as linear or branched aliphatic, alicyclic or aromatic hydrocarbon, such as a 25 linear or cyclic alkane, an aromatic hydrocarbon and/or a halogen containing hydrocarbon.

Examples of aromatic hydrocarbons are toluene, benzene, ethylbenzene, propylbenzene, butylbenzene and xylene. Toluene is a preferred solvent. The solution may comprise one or more solvents. Such a solvent can thus be used to facilitate the emulsion formation, and usually does not form part of the solidified particles, but e.g. is removed after 30 the solidification step together with the continuous phase.

Alternatively, a solvent may take part in the solidification, e.g. an inert hydrocarbon having a high melting point (waxes), such as above 40°C, suitably above 70°C, e. g. above

- 35 -

80°C or 90°C, may be used as solvents of the dispersed phase to immobilise the catalyst compounds within the formed droplets.

In another embodiment, the solvent consists partly or completely of a liquid monomer, e.g. liquid olefin monomer designed to be polymerised in a "prepolymerisation" 5 immobilisation step.

Continuous Phase

The solvent used to form the continuous liquid phase is a single solvent or a mixture 10 of different solvents and may be immiscible with the solution of the catalyst components at least at the conditions (e.g. temperatures) used during the dispersing step. Preferably said solvent is inert in relation to said compounds.

The term "inert in relation to said compounds" means herein that the solvent of the continuous phase is chemically inert, i.e. undergoes no chemical reaction with any catalyst 15 forming component. Thus, the solid particles of the catalyst are formed in the droplets from the compounds which originate from the dispersed phase, i.e. are provided to the emulsion in a solution dispersed into the continuous phase.

It is preferred that the catalyst components used for forming the solid catalyst will not be soluble in the solvent of the continuous liquid phase. Preferably, said catalyst components 20 are essentially insoluble in said continuous phase forming solvent.

Solidification takes place essentially after the droplets are formed, i.e. the solidification is effected within the droplets e.g. by causing a solidifying reaction among the compounds present in the droplets. Furthermore, even if some solidifying agent is added to the system separately, it reacts within the droplet phase and no catalyst forming components 25 go into the continuous phase.

The term "emulsion" used herein covers both bi-and multiphasic systems.

In a preferred embodiment said solvent forming the continuous phase is an inert solvent including a halogenated organic solvent or mixtures thereof, preferably fluorinated organic solvents and particularly semi, highly or perfluorinated organic solvents and 30 functionalised derivatives thereof. Examples of the above-mentioned solvents are semi, highly or perfluorinated hydrocarbons, such as alkanes, alkenes and cycloalkanes, ethers, e.g. perfluorinated ethers and amines, particularly tertiary amines, and functionalised derivatives

- 36 -

thereof. Preferred are semi, highly or perfluorinated, particularly perfluorinated hydrocarbons, e.g. perfluorohydrocarbons of e.g. C3-C30, such as C4-C10. Specific examples of suitable perfluoroalkanes and perfluorocycloalkanes include perfluoro-hexane, -heptane, -octane and -(methylcyclohexane). Semi fluorinated hydrocarbons relates

5 particularly to semifluorinated n-alkanes, such as perfluoroalkyl-alkane.

"Semi fluorinated" hydrocarbons also include such hydrocarbons wherein blocks of -C-F and -C-H alternate. "Highly fluorinated" means that the majority of the -C-H units are replaced with -C-F units. "Perfluorinated" means that all -C-H units are replaced with -C-F units. See the articles of A. Enders and G. Maas in "Chemie in unserer Zeit", 34. Jahrg. 2000,

10 Nr.6, and of Pierandrea Lo Nostro in "Advances in Colloid and Interface Science", 56 (1995) 245-287, Elsevier Science.

Dispersing step

15 The emulsion can be formed by any means known in the art: by mixing, such as by stirring said solution vigorously to said solvent forming the continuous phase or by means of mixing mills, or by means of ultra sonic wave, or by using a so called phase change method for preparing the emulsion by first forming a homogeneous system which is then transferred by changing the temperature of the system to a biphasic system so that droplets will be
20 formed.

The two phase state is maintained during the emulsion formation step and the solidification step, as, for example, by appropriate stirring.

Additionally, emulsifying agents/emulsion stabilisers can be used, preferably in a manner known in the art, for facilitating the formation and/or stability of the emulsion. For
25 the said purposes e.g. surfactants, e.g. a class based on hydrocarbons (including polymeric hydrocarbons with a molecular weight e.g. up to 10 000 and optionally interrupted with a heteroatom(s)), preferably halogenated hydrocarbons, such as semi- or highly fluorinated hydrocarbons optionally having a functional group selected e.g. from -OH, -SH, NH₂, NR², -COOH, -COONH₂, oxides of alkenes, -CR²=CH₂, where R² is hydrogen, or C1-C20 alkyl,
30 C2-20-alkenyl or C2-20-alkynyl group, oxo-groups, cyclic ethers and/or any reactive derivative of these groups, like alkoxy, or carboxylic acid alkyl ester groups, or, preferably semi-, highly- or perfluorinated hydrocarbons having a functionalised terminal, can be used.

- 37 -

The surfactants can be added to the catalyst solution, which forms the dispersed phase of the emulsion, to facilitate the forming of the emulsion and to stabilize the emulsion.

Alternatively, an emulsifying and/or emulsion stabilising aid can also be formed by reacting a surfactant precursor bearing at least one functional group with a compound

5 reactive with said functional group and present in the catalyst solution or in the solvent forming the continuous phase. The obtained reaction product acts as the actual emulsifying aid and or stabiliser in the formed emulsion system.

Examples of the surfactant precursors usable for forming said reaction product include e.g. known surfactants which bear at least one functional group selected e.g. from -

10 OH, -SH, NH₂, NR"₂, -COOH, -COONH₂, oxides of alkenes, -CR"=CH₂, where R" is hydrogen, or C1-C20 alkyl, C2-20-alkenyl or C2-20-alkynyl group, oxo-groups, cyclic ethers with 3 to 5 ring atoms, and/or any reactive derivative of these groups, like alkoxy or carboxylic acid alkyl ester groups; e.g. semi-, highly or perfluorinated hydrocarbons bearing one or more of said functional groups. Preferably, the surfactant precursor has a terminal

15 functionality as defined above.

The compound reacting with such surfactant precursor is preferably contained in the catalyst solution and may be a further additive or one or more of the catalyst forming compounds. Such compound is e.g. a compound of group 13 (e.g. MAO and/or an aluminium alkyl compound and/or a transition metal compound).

20 If a surfactant precursor is used, it is preferably first reacted with a compound of the catalyst solution before the addition of the transition metal compound. In one embodiment e.g. a highly fluorinated C1-n (suitably C4-30-or C5-15) alcohol (e.g. highly fluorinated heptanol, octanol or nonanol), oxide (e.g. propenoxide) or acrylate ester is reacted with a cocatalyst to form the "actual" surfactant. Then, an additional amount of cocatalyst and the

25 transition metal compound is added to said solution and the obtained solution is dispersed to the solvent forming the continuous phase. The "actual" surfactant solution may be prepared before the dispersing step or in the dispersed system. If said solution is made before the dispersing step, then the prepared "actual" surfactant solution and the transition metal solution may be dispersed successively (e. g. the surfactant solution first) to the immiscible solvent, or be combined together before the dispersing step.

Solidification

The solidification of the catalyst component(s) in the dispersed droplets can be effected in various ways, e.g. by causing or accelerating the formation of said solid catalyst forming reaction products of the compounds present in the droplets. This can be effected, 5 depending on the used compounds and/or the desired solidification rate, with or without an external stimulus, such as a temperature change of the system.

In a particularly preferred embodiment, the solidification is effected after the emulsion system is formed by subjecting the system to an external stimulus, such as a temperature change. Temperature differences of e.g. 5 to 100°C, such as 10 to 100°C, or 20 10 to 90°C, such as 50 to 90°C.

The emulsion system may be subjected to a rapid temperature change to cause a fast solidification in the dispersed system. The dispersed phase may e. g. be subjected to an immediate (within milliseconds to few seconds) temperature change in order to achieve an instant solidification of the component (s) within the droplets. The appropriate temperature 15 change, i. e. an increase or a decrease in the temperature of an emulsion system, required for the desired solidification rate of the components cannot be limited to any specific range, but naturally depends on the emulsion system, i. a. on the used compounds and the concentrations/ratios thereof, as well as on the used solvents, and is chosen accordingly. It is also evident that any techniques may be used to provide sufficient heating or cooling effect to 20 the dispersed system to cause the desired solidification.

In one embodiment the heating or cooling effect is obtained by bringing the emulsion system with a certain temperature to an inert receiving medium with significantly different temperature, e. g. as stated above, whereby said temperature change of the emulsion system is sufficient to cause the rapid solidification of the droplets. The receiving medium can be 25 gaseous, e. g. air, or a liquid, preferably a solvent, or a mixture of two or more solvents, wherein the catalyst component (s) is (are) immiscible and which is inert in relation to the catalyst component (s). For instance, the receiving medium comprises the same immiscible solvent used as the continuous phase in the first emulsion formation step.

Said solvents can be used alone or as a mixture with other solvents, such as aliphatic 30 or aromatic hydrocarbons, such as alkanes. Preferably a fluorinated solvent as the receiving medium is used, which may be the same as the continuous phase in the emulsion formation, e. g. perfluorinated hydrocarbon.

- 39 -

Alternatively, the temperature difference may be effected by gradual heating of the emulsion system, e. g. up to 10°C per minute, preferably 0.5 to 6°C per minute and more preferably in 1 to 5°C per minute.

In case a melt of e. g. a hydrocarbon solvent is used for forming the dispersed phase, 5 the solidification of the droplets may be effected by cooling the system using the temperature difference stated above.

Preferably, the "one phase" change as usable for forming an emulsion can also be utilised for solidifying the catalytically active contents within the droplets of an emulsion system by, again, effecting a temperature change in the dispersed system, whereby the 10 solvent used in the droplets becomes miscible with the continuous phase, preferably a fluorous continuous phase as defined above, so that the droplets become impoverished of the solvent and the solidifying components remaining in the "droplets" start to solidify. Thus the immisciblity can be adjusted with respect to the solvents and conditions (temperature) to control the solidification step.

15 The miscibility of e.g. organic solvents with fluorous solvents can be found from the literature and be chosen accordingly by a skilled person. Also the critical temperatures needed for the phase change are available from the literature or can be determined using methods known in the art, e. g. the Hildebrand-Scatchard-Theorie. Reference is also made to the articles of A. Enders and G. and of Pierandrea Lo Nostro cited above.

20 Thus according to the invention, the entire or only part of the droplet may be converted to a solid form. The size of the "solidified"droplet may be smaller or greater than that of the original droplet, e. g. if the amount of the monomer used for the prepolymerisation is relatively large.

25 The solid catalyst particles recovered can be used, after an optional washing step, in a polymerisation process of propylene. Alternatively, the separated and optionally washed solid particles can be dried to remove any solvent present in the particles before use in the polymerisation step. The separation and optional washing steps can be effected in a known manner, e. g. by filtration and subsequent washing of the solids with a suitable solvent.

30 The droplet shape of the particles may be substantially maintained. The formed particles may have an average size range of 1 to 500 µm, e.g. 5 to 500 µm, advantageously 5 to 200 µm or 10 to 150 µm. Even an average size range

- 40 -

of 5 to 60 μm is possible. The size may be chosen depending on the polymerisation the catalyst is used for. Advantageously, the particles are essentially spherical in shape, they have a low porosity and a low surface area.

The formation of solution can be effected at a temperature of 0-100°C, e.g. at 20-

5 80°C. The dispersion step may be effected at -20 °C-100°C, e.g. at about -10-70°C, such as at -5 to 30°C, e.g. around 0 °C.

To the obtained dispersion an emulsifying agent as defined above, may be added to improve/stabilise the droplet formation. The solidification of the catalyst component in the droplets is preferably effected by raising the temperature of the mixture, e.g. from 0 °C 10 temperature up to 100°C, e.g. up to 60-90°C, gradually. E.g. in 1 to 180 minutes, e.g. 1-90 or 5-30 minutes, or as a rapid heat change. Heating time is dependent on the size of the reactor.

During the solidification step, which is preferably carried out at about 60 to 100 °C, preferably at about 75 to 95 °C, (below the boiling point of the solvents) the solvents may preferably be removed and optionally the solids are washed with a wash solution, which can 15 be any solvent or mixture of solvents such as those defined above and/or used in the art, preferably a hydrocarbon, such as pentane, hexane or heptane, suitably heptane. The washed catalyst can be dried or it can be slurried into an oil and used as a catalyst-oil slurry in polymerisation process.

All or part of the preparation steps can be done in a continuous manner. Reference is 20 made to WO2006/069733 describing principles of such a continuous or semicontinuous preparation methods of the solid catalyst types, prepared via emulsion/solidification method.

Catalyst off- line prepolymerisation

25 The use of the heterogeneous catalysts, where no external support material is used (also called “self-supported” catalysts) might have, as a drawback, a tendency to dissolve to some extent in the polymerisation media, i.e. some active catalyst components might leach out of the catalyst particles during slurry polymerisation, whereby the original good morphology of the catalyst might be lost. These leached catalyst components are very active 30 possibly causing problems during polymerisation. Therefore, the amount of leached components should be minimized, i.e. all catalyst components should be kept in heterogeneous form.

- 41 -

Furthermore, the self-supported catalysts generate, due to the high amount of catalytically active species in the catalyst system, high temperatures at the beginning of the polymerisation which may cause melting of the product material. Both effects, i.e. the partial dissolving of the catalyst system and the heat generation, might cause fouling, sheeting and 5 deterioration of the polymer material morphology.

In order to minimise the possible problems associated with high activity or leaching, it is possible to "off line prepolymerise" the catalyst before using it in polymerisation process.

It has to be noted that off line prepolymerisation in this regard is part of the catalyst preparation process, being a step carried out after a solid catalyst is formed. The catalyst off 10 line prepolymerisation step is not part of the actual polymerisation process configuration comprising a prepolymerisation step. After the catalyst off line prepolymerisation step, the solid catalyst can be used in polymerisation.

Catalyst "off line prepolymerisation" takes place following the solidification step of the liquid-liquid emulsion process. Pre-polymerisation may take place by known methods 15 described in the art, such as that described in WO 2010/052263, WO 2010/052260 or WO 2010/052264. Preferable embodiments of this aspect of the invention are described herein.

As monomers in the catalyst off-line prepolymerisation step preferably alpha-olefins are used. Preferable C₂-C₁₀ olefins, such as ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-heptene, 1-octene, 1-nonene 1-decene, styrene and 20 vinylcyclohexene are used. Most preferred alpha-olefins are ethylene and propylene, especially propylene.

The catalyst off-line prepolymerisation may be carried out in gas phase or in an inert diluent, typically oil or fluorinated hydrocarbon, preferably in fluorinated hydrocarbons or mixture of fluorinated hydrocarbons. Preferably perfluorinated hydrocarbons are used. The 25 melting point of such (per)fluorinated hydrocarbons is typically in the range of 0 to 140 °C, preferably 30 to 120 °C, like 50 to 110 °C.

Where the catalyst off line prepolymerisation is done in fluorinated hydrocarbons, the temperature for the pre-polymerisation step is below 70°C, e.g. in the range of -30 to 70°C, preferably 0-65°C and more preferably in the range 20 to 55°C. Pressure within the 30 reaction vessel is preferably higher than atmospheric pressure to minimize the eventual leaching of air and/or moisture into the catalyst vessel. Preferably the pressure is in the range

- 42 -

of at least 1 to 15 bar, preferably 2 to 10 bar. The reaction vessel is preferably kept in an inert atmosphere, such as under nitrogen or argon or similar atmosphere.

Off line prepolymerisation is continued until the desired pre-polymerisation degree, defined as weight of polymer matrix/weight of solid catalyst before pre-polymerisation step, 5 is reached. The degree is below 25, preferably 0,5 to 10.0, more preferably 1.0 to 8.0, most preferably 2,0 to 6,0.

Use of the off-line catalyst prepolymerisation step offers the advantage of minimising leaching of catalyst components and thus local overheating.

After off line prepolymerisation, the catalyst can be isolated and stored.

10

Polymerisation

The catalysts according to the invention are especially suited to the formation of propylene homopolymers or propylene-ethylene copolymers. The ethylene content in such a propylene-ethylene polymer may vary depending on the desired properties of the polymer.

15 Typically ethylene content will range from 0.1 to 10 mol%. Especially, the catalysts of the present invention are used to manufacture propylene homopolymers or propylene random copolymers with ethylene as comonomer.

Polymerization in the method of the invention may be effected in one or more, e.g. 1, 20 2 or 3, polymerization reactors, using conventional polymerization techniques, e.g. gas phase, solution phase, slurry or bulk polymerization or combinations thereof, like a combination of a slurry and at least one gas phase reactor.

In case of propylene polymerisation for slurry reactors, the reaction temperature will generally be in the range 60 to 110°C (e.g. 60-90°C), the reactor pressure will generally be in the range 5 to 80 bar (e.g. 20-60 bar), and the residence time will generally be in the range 25 0.1 to 5 hours (e.g. 0.3 to 2 hours). The monomer is usually used as reaction medium.

For gas phase reactors, the reaction temperature used will generally be in the range 60 to 115°C (e.g. 70 to 110°C), the reactor pressure will generally be in the range 10 to 25 bar, and the residence time will generally be 0,5 to 8 hours (e.g. 0,5 to 4 hours). The gas used will be the monomer optionally as mixture with a non-reactive gas such as nitrogen or propane. In 30 addition to actual polymerisation steps and reactors, the process can contain any additional polymerisation steps, like prepolymerisation step, and any further after reactor handling steps as known in the art.

- 43 -

For solution polymerization, an aliphatic or aromatic solvent can be used to dissolve the monomer and the polymer, and the polymerization temperature will generally be in the range 80 to 200°C (e.g. 90 to 150°C)

Generally the quantity of catalyst used will depend upon the nature of the catalyst, the 5 reactor types and conditions and the properties desired for the polymer product. As is well known in the art hydrogen can be used for controlling the molecular weight of the polymer.

The metallocene catalysts of the invention possess excellent catalyst activity and good comonomer response. The catalysts are also able to provide polymers of high weight average molecular weight Mw.

10 Moreover, the random copolymerisation behaviour of metallocene catalysts of the invention shows a reduced tendency of chain transfer to ethylene. Polymers obtained with the metallocenes of the invention have normal particle morphologies.

It is especially preferred if the catalysts of the invention are used in the manufacture of heterophasic PP/EPR blends. These reactor blends may be produced in two-steps 15 (homopolypropylene in bulk + ethylene-propylene rubber in gas phase) or three steps (hPP in bulk + hPP in gas phase + EPR in gas phase). Such polymers may typically be characterized by one or more of the following features: EPR is fully soluble in xylene at room temperature. The iV(EPR) is above 2,0 dL/g when measured in decaline. The Mw/Mn of the hPP, as measured by GPC, is greater than 3.5.

20 Viewed from another aspect the invention provides a process for the preparation of a heterophasic polypropylene copolymer comprising:

(I) polymerising propylene in bulk in the presence of a catalyst as herein defined to form a polypropylene homopolymer matrix;
25 (II) in the presence of said matrix and said catalyst and in the gas phase, polymerising propylene and ethylene to form a heterophasic polypropylene copolymer comprising a homopolymer matrix and an ethylene propylene rubber.

Viewed from another aspect the invention provides a process for the preparation of a heterophasic polypropylene copolymer comprising:

(I) polymerising propylene in bulk in the presence of a catalyst as herein defined to form 30 a polypropylene homopolymer;
(II) in the presence of said homopolymer and said catalyst and in the gas phase, polymerising propylene to form a polypropylene homopolymer matrix;

- 44 -

(III) in the presence said matrix and said catalyst and in the gas phase, polymerising propylene and ethylene to form a heterophasic polypropylene copolymer comprising a homopolymer matrix and an ethylene propylene rubber (EPR).

In such a process, it is preferred if the EPR component is fully soluble in xylene at 5 room temperature. The EPR component may have a C2 content of 15 to 60 wt%. It is preferred if the iV of the EPR is above 2,0 dL/g when measured in decaline. It is also preferred if the Mw/Mn of the hPP matrix component, as measured by GPC, is broader than 3.5, such as 4.0 to 8.0. The xylene soluble content may range from 15 to 60 wt%.

It will be appreciated that the catalyst may be subject to prepolymerisation as known 10 in the art. The split between the steps may vary. For a two step procedure, a suitable split is 40 to 70 wt% of EPR vs 30 to 60 wt% homopolymer component, such as 50 to 70 EPR vs 50 to 30 wt% homopolymer.

For a three step process, splits are preferably 30 to 50 wt% in step (I), 30:50 wt% in step (II) and 10 to 30 wt% in step (III).

15

Polymers

It is a feature of the invention that the claimed catalysts enable the formation of polymers with high molecular weight. These features can be achieved at commercially interesting polymerisation temperatures, e.g. 60°C or more. It is a preferred feature of the 20 invention that the catalysts of the invention are used to polymerise propylene at a temperature of at least 60°C, preferably at least 65°C, such as at least 70°C. In a particular embodiment, the propylene polymers obtained using the catalysts of the invention have a polydispersity index (Mw/Mn) of 2.0 or greater, such as 2.2-6.5. In particular, propylene polymers obtained in three-stage polymerisation processes can have broad polydispersities of 4.5-6.2. Therefore, 25 in a particular embodiment, the propylene polymers of the invention may have a polydispersity index of 2.0-7.0, such as 3.0-7.0, or 4.0-6.5.

Polypropylene homopolymers

Polypropylene homopolymers made by the metallocenes of the invention can be made 30 with Mw (weight average molecular weight) values in the range of 40 to 2 000 kg/mol, preferably in the range of 50 to 1 500 kg/mol depending on the use and amount of hydrogen used as Mw regulating agent. The catalysts of the invention enable the formation of

- 45 -

polypropylene homopolymers with high melting points. In a preferred embodiment the propylene homopolymer formed by the process of the invention has a melting point of more than 149.0 °C, preferably more than 149.5 °C, especially more than 150.0 °C. Propylene homopolymers having melting points up to 158.0 °C are possible.

5

Propylene-ethylene copolymers

Propylene-ethylene copolymers made by the metallocenes of the invention can be made with Mw values in the range of 40 to 2,000 kg/mol, preferably in the range of 50 to 1,500 kg/mol depending on the amount of comonomer content and/or use and amount of 10 hydrogen used as Mw regulating agent. The polymers made by the catalysts of the invention are useful in all kinds of end articles such as pipes, films (cast, blown or BOPP films, such as for example BOPP for capacitor film), fibers, moulded articles (e.g. injection moulded, blow moulded, rotomoulded articles), extrusion coatings and so on.

It has been found that certain heterophasic propylene-ethylene copolymers obtained 15 using the catalysts of the invention have high intrinsic viscosity (iV). In particular, values of 2.0 dl/g or more are preferred such as 2.0 to 5.0 dl/g for the EPR component. The catalysts therefore enable the formation of high Mw EPR components.

The invention will now be illustrated by reference to the following non-limiting examples and figures.

20

Brief description of the Figures

Figure 1 illustrates metal activities of the inventive examples and closest references (comparative examples) in bulk propylene homopolymerisation experiments. Both MC-E1 25 and MC-E2 demonstrate improved performance over the references, while MC-E3 has performance comparable to the C_1 -symmetric reference MC-CE1.

Figure 2 illustrates polypropylene homopolymer melting temperatures for samples produced with the inventive examples and closest references (comparative examples). Inventive 30 examples provide at least roughly 2 degrees higher melting temperature when compared to polymers produced using the known C_1 -symmetric metallocenes. . The C_2 -symmetric

- 46 -

references provide comparable or higher melting temperature, however, with clearly lower activity.

Figure 3 illustrates metal activities of the inventive examples and closest references

5 (comparative examples) in ethylene-propylene random copolymerisation. All inventive examples provide clearly improved performance when compared to the references.

Figure 4 illustrates Mw results for the propylene homopolymer samples produced with inventive examples and closest references (comparative examples) in bulk propylene

10 homopolymerisation experiments. The Mw values are comparable to the results obtained with the C1-symmetric references and improved over the result with the C2-symmetric references.

Figure 5 illustrates that catalysts of the invention provide high Mw in ethylene-propylene random copolymerisation. Moreover, comparison of the results in Figure 5 and Figure 4

15 shows that ethylene has a strong positive effect on Mw with the catalysts of the invention, while with MC-CE1, MC-CE2 and MC-CE4 Mw results are comparable. With MC-CE3, ethylene has a strong negative effect on Mw.

Figure 6 illustrates productivity-MFR correlation for silica catalysts (2-step experiments).

20 Productivities are based on metallocene amounts.

Figure 7 illustrates composition – molecular weight correlation of the rubber phase (xylene insoluble fraction) of heterophasic copolymers produced with silica catalysts (3-step experiments).

25

Analytical tests

Measurement methods:

Al and Zr determination (ICP-method)

30

The elementary analysis of a catalyst was performed by taking a solid sample of mass, M, cooling over dry ice. Samples were diluted up to a known volume, V, by dissolving in nitric acid (HNO₃, 65 %, 5 % of V) and freshly deionised (DI) water (5 % of V). The solution

- 47 -

was then added to hydrofluoric acid (HF, 40 %, 3 % of V), diluted with DI water up to the final volume, V, and left to stabilise for two hours.

The analysis was run at room temperature using a Thermo Elemental iCAP 6300 Inductively Coupled Plasma – Optical Emission Spectrometer (ICP-OES) which was 5 calibrated using a blank (a solution of 5 % HNO₃, 3 % HF in DI water), and 6 standards of 0.5 ppm, 1 ppm, 10 ppm, 50 ppm, 100 ppm and 300 ppm of Al, with 0.5 ppm, 1 ppm, 5 ppm, 20 ppm, 50 ppm and 100 ppm of Hf and Zr in solutions of 5 % HNO₃, 3 % HF in DI water.

Immediately before analysis the calibration is ‘resloped’ using the blank and 100 ppm Al, 50 ppm Hf, Zr standard, a quality control sample (20 ppm Al, 5 ppm Hf, Zr in a solution 10 of 5 % HNO₃, 3 % HF in DI water) is run to confirm the reslope. The QC sample is also run after every 5th sample and at the end of a scheduled analysis set.

The content of hafnium was monitored using the 282.022 nm and 339.980 nm lines and the content for zirconium using 339.198 nm line. The content of aluminium was monitored via the 167.079 nm line, when Al concentration in ICP sample was between 0-10 15 ppm (calibrated only to 100 ppm) and via the 396.152 nm line for Al concentrations above 10 ppm.

The reported values are an average of three successive aliquots taken from the same sample and are related back to the original catalyst by inputting the original mass of sample and the dilution volume into the software.

20 In the case of analysing the elemental composition of off-line prepolymerised catalysts, the polymeric portion is digested by ashing in such a way that the elements can be freely dissolved by the acids. The total content is calculated to correspond to the weight-% for the prepolymerised catalyst.

25 **DSC analysis**

Melting temperature T_m was measured on approx. 5 mg samples with a Mettler-Toledo 822e differential scanning calorimeter (DSC), according to ISO11357-3 in a heat/cool/heat cycle with a scan rate of 10 °C/min in the temperature range of +23 to +225 °C under a nitrogen 30 flow rate of 50 ml min⁻¹. Melting temperature was taken as the endotherm peak, respectively in the second heating step. Calibration of the instrument was performed with H₂O, Lead, Tin, Indium, according to ISO 11357-1.

- 48 -

Melt Flow Rate

The melt flow rate (MFR) is determined according to ISO 1133 and is indicated in g/10 min.

The MFR is an indication of the flowability, and hence the processability, of the polymer.

The higher the melt flow rate, the lower the viscosity of the polymer. The MFR is determined

5 at 230°C and may be determined at different loadings such as 2.16 kg (MFR₂) or 21.6 kg (MFR₂₁).

Intrinsic viscosity

Intrinsic viscosity (IV) has been measured according to DIN ISO 1628/1, October 1999 (in

10 Decalin at 135 °C).

GPC: Molecular weight averages, molecular weight distribution, and polydispersity index (M_n, M_w, M_w/M_n)

Molecular weight averages (M_w, M_n), Molecular weight distribution (MWD) and its

15 broadness, described by polydispersity index, PDI= M_w/M_n (wherein M_n is the number average molecular weight and M_w is the weight average molecular weight) were determined by Gel Permeation Chromatography (GPC) according to ISO 16014-4:2003 and ASTM D 6474-99.

A PolymerChar GPC instrument, equipped with infrared (IR) detector was used with 3 x

20 Olexis and 1x Olexis Guard columns from Polymer Laboratories and 1,2,4-trichlorobenzene (TCB, stabilized with 250 mg/L 2,6-Di tert butyl-4-methyl-phenol) as solvent at 160 °C and at a constant flow rate of 1 mL/min. 200 µL of sample solution were injected per analysis.

The column set was calibrated using universal calibration (according to ISO 16014-2:2003)

with at least 15 narrow MWD polystyrene (PS) standards in the range of 0,5 kg/mol to 11 500

25 kg/mol. Mark Houwink constants for PS, PE and PP used are as described per ASTM D 6474-99. All samples were prepared by dissolving 5.0 – 9.0 mg of polymer in 8 mL (at 160 °C) of stabilized TCB (same as mobile phase) for 2.5 hours for PP or 3 hours for PE at max. 160°C under continuous gentle shaking in the autosampler of the GPC instrument

30 **Quantification of polypropylene homopolymer microstructure by NMR spectroscopy**

Quantitative nuclear-magnetic resonance (NMR) spectroscopy was used to quantify the isotacticity and content of regio-defects of the polypropylene homopolymers. Quantitative

- 49 -

$^{13}\text{C}\{\text{H}\}$ NMR spectra recorded in the solution-state using a Bruker Advance III 400 NMR spectrometer operating at 400.15 and 100.62 MHz for ^1H and ^{13}C respectively. All spectra were recorded using a ^{13}C optimised 10 mm selective excitation probehead at 125°C using nitrogen gas for all pneumatics. Approximately 200 mg of material was dissolved in 1,2-

5 tetrachloroethane- d_2 (TCE- d_2). This setup was chosen primarily for the high resolution needed for tacticity distribution quantification (Busico, V., Cipullo, R., Prog. Polym. Sci. 26 (2001) 443; Busico, V.; Cipullo, R., Monaco, G., Vacatello, M., Segre, A.L., Macromolecules 30 (1997) 6251). Standard single-pulse excitation was employed utilising the NOE and bi-level WALTZ16 decoupling scheme (Zhou, Z., Kuemmerle, R., Qiu, X.,

10 Redwine, D., Cong, R., Taha, A., Baugh, D. Winniford, B., J. Mag. Reson. 187 (2007) 225; Busico, V., Carbonniere, P., Cipullo, R., Pellecchia, R., Severn, J., Talarico, G., Macromol. Rapid Commun. 2007, 28, 11289). A total of 6144 (6k) transients were acquired per spectra using a 3 s recycle delay. Quantitative $^{13}\text{C}\{\text{H}\}$ NMR spectra were processed, integrated and relevant quantitative properties determined from the integrals using proprietary computer

15 programs. All chemical shifts are internally referenced to the methyl signal of the isotactic pentad mmmm at 21.85 ppm.

The tacticity distribution was quantified through integration of the methyl region between 23.6 and 19.7 ppm correcting for any sites not related to the stereo sequences of interest

20 (Busico, V., Cipullo, R., Prog. Polym. Sci. 26 (2001) 443; Busico, V., Cipullo, R., Monaco, G., Vacatello, M., Segre, A.L., Macromolecules 30 (1997) 6251). The pentad isotacticity was determined through direct integration of the methyl region and reported as either the mole fraction or percentage of isotactic pentad mmmm with respect to all steric pentads i.e. [mmmm] = mmmm / sum of all steric pentads. When appropriate integrals were corrected for

25 the presence of sites not directly associated with steric pentads.

Characteristic signals corresponding to regio irregular propene insertion were observed (Resconi, L., Cavallo, L., Fait, A., Piemontesi, F., Chem. Rev. 2000, 100, 1253). The presence of secondary inserted propene in the form of 2,1 erythro regio defects was indicated

30 by the presence of the two methyl signals at 17.7 and 17.2 ppm and confirmed by the presence of other characteristic signals. The amount of 2,1 erythro regio defects was quantified using the average integral (e) of the e6 and e8 sites observed at 17.7 and 17.2 ppm

- 50 -

respectively, i.e. $e = 0.5 * (e6 + e8)$. Characteristic signals corresponding to other types of regio irregularity were not observed (Resconi, L., Cavallo, L., Fait, A., Piemontesi, F., Chem. Rev. 2000, 100, 1253). The amount of primary inserted propene (p) was quantified based on the integral of all signals in the methyl region (CH3) from 23.6 to 19.7 ppm paying attention

5 to correct for other species included in the integral not related to primary insertion and for primary insertion signals excluded from this region such that $p = CH3 + 2*e$. The relative content of a specific type of regio defect was reported as the mole fraction or percentage of said regio defect with respect all observed forms of propene insertion i.e. sum of all primary (1,2), secondary (2,1) and tertiary (3,1) inserted propene units, e.g. $[21e] = e / (p + e + t + i)$.

10 The total amount of secondary inserted propene in the form of 2,1-erythro or 2,1-threo regio defects was quantified as sum of all said regio irregular units, i.e. $[21] = [21e] + [21t]$.

Quantification of copolymer microstructure by NMR spectroscopy

Quantitative nuclear-magnetic resonance (NMR) spectroscopy was used to quantify the

15 comonomer content and comonomer distribution of the copolymers, specifically propene-co-ethylene copolymers. Quantitative $^{13}\text{C}\{^1\text{H}\}$ NMR spectra recorded in the solution-state using a Bruker Advance III 400 NMR spectrometer operating at 400.15 and 100.62 MHz for ^1H and ^{13}C respectively. All spectra were recorded using a ^{13}C optimised 10 mm selective excitation probehead at 125°C using nitrogen gas for all pneumatics. Approximately 200 mg

20 of material was dissolved in 1,2-tetrachloroethane- d_2 (TCE- d_2) with chromium-(III)-acetylacetone ($\text{Cr}(\text{acac})_3$) resulting in a 65 mM solution of relaxation agent in solvent (Singh, G., Kothari, A., Gupta, V., Polymer Testing 28 5 (2009), 475). This setup was chosen primarily for the high resolution and quantitative spectra needed for accurate ethylene content determination. Standard single-pulse excitation was employed without NOE, using an

25 optimised tip angle, 1 s recycle delay and bi-level WALTZ16 decoupling scheme (Zhou, Z., Kuemmerle, R., Qiu, X., Redwine, D., Cong, R., Taha, A., Baugh, D. Winniford, B., J. Mag. Reson. 187 (2007) 225; Busico, V., Carbonniere, P., Cipullo, R., Pellecchia, R., Severn, J., Talarico, G., Macromol. Rapid Commun. 2007, 28, 11289). A total of 6144 (6k) transients were acquired per spectra. Quantitative $^{13}\text{C}\{^1\text{H}\}$ NMR spectra were processed, integrated and

30 relevant quantitative properties determined from the integrals using proprietary computer programs. All chemical shifts were indirectly referenced to the central methylene group of the ethylene block (EEE) at 30.00 ppm using the chemical shift of the solvent. This approach allowed comparable referencing even when this structural unit was not present.

- 51 -

Characteristic signals corresponding to regio irregular propene insertion were observed (Resconi, L., Cavallo, L., Fait, A., Piemontesi, F., Chem. Rev. 2000, 100, 1253).].

Characteristic signals corresponding to the incorporation of ethylene were observed (Cheng, H. N., Macromolecules 17, 1984, 1950). The comonomer content was calculated as 5 the mole fraction or percent of incorporated ethylene with respect to all monomer in the copolymer using the method of Wang et. al. (Wang, W-J., Zhu, S., Macromolecules 33, 2000, 1157) through integration of multiple signals spanning the whole spectral ^{13}C spectra. This analyse method was chosen for its robust nature and ability to account for the presence of regio irregular propene insertion when needed. Integral regions were slightly adjusted to 10 increase applicability across the whole range of encountered comonomer contents.

For systems where only isolated ethylene incorporation (PPEPP) was observed the method of Wang et. al. was modified to reduce the influence of non-zero integrals used to quantify higher order comonomer sequences. In such cases the term for the absolute ethylene content was determined based upon only $E = 0.5(S\beta\beta + S\beta\gamma + S\beta\delta + 0.5(S\alpha\beta + S\alpha\gamma\square))$ or 15 $E = 0.5(I_H + I_G + 0.5(I_C + I_D))$ using the same notation as Wang et. al. (Wang, W-J., Zhu, S., Macromolecules 33, 2000, 1157). The term used for absolute propylene content (P) was not modified and the mole fraction of ethylene calculated as $[E] = E / (E + P)$. The comonomer content in weight percent was calculated from the mole fraction in the usual way i.e. $[E \text{ wt\%}] = 100 * ([E] * 28.06) / (([E] * 28.06) + ((1-[E]) * 42.08))$.

20

Examples

Metallocene synthesis

Reagents

2,6-Dimethylaniline (Acros), 1-bromo-3,5-dimethylbenzene (Acros), 1-bromo-3,5-di-25 tert-butylbenzene (Acros), bis(2,6-diisopropylphenyl)imidazolium chloride (Aldrich), triphenylphosphine (Acros), NiCl_2 (DME) (Aldrich), dichlorodimethylsilane (Merck), ZrCl_4 (Merck), trimethylborate (Acros), $\text{Pd}(\text{OAc})_2$ (Aldrich), NaBH_4 (Acros), 2.5 M nBuLi in hexanes (Chemetall), CuCN (Merck), magnesium turnings (Acros), silica gel 60, 40-63 μm 30 (Merck), bromine (Merck), 96% sulfuric acid (Reachim), sodium nitrite (Merck), copper powder (Alfa), potassium hydroxide (Merck), K_2CO_3 (Merck), 12 M HCl (Reachim), TsOH (Aldrich), MgSO_4 (Merck), Na_2CO_3 (Merck), Na_2SO_4 (Akzo Nobel), methanol (Merck), diethyl ether (Merck), 1,2-dimethoxyethane (DME, Aldrich), 95% ethanol (Merck),


- 52 -

dichloromethane (Merck), hexane (Merck), THF (Merck), and toluene (Merck) were used as received. Hexane, toluene and dichloromethane for organometallic synthesis were dried over molecular sieves 4A (Merck). Diethyl ether, THF, and 1,2-dimethoxyethane for organometallic synthesis were distilled over sodium benzophenoneketyl. CDCl_3 (Deutero

5) and CD_2Cl_2 (Deutero GmbH) were dried over molecular sieves 4A. 4-Bromo-6-*tert*-butyl-5-methoxy-2-methylindan-1-one was obtained as described in WO2013/007650.

Synthesis of MC IE1

4-(4-*tert*-Butylphenyl)-1-methoxy-2-methyl-1,2,3,5,6,7-hexahydro-*s*-indacene



10 The precursor 4-bromo-1-methoxy-2-methyl-1,2,3,5,6,7-hexahydro-*s*-indacene was made according to the procedure described in WO2015/158790 A2 (pp 26-29).

To a mixture of 1.5 g (1.92 mmol, 0.6 mol.%) of $\text{NiCl}_2(\text{PPh}_3)\text{IPr}$ and 89.5 g (318.3 mmol) of 4-bromo-1-methoxy-2-methyl-1,2,3,5,6,7-hexahydro-*s*-indacene, 500 ml (500 mmol, 1.57 equiv) of 1.0 M 4-*tert*-butylphenylmagnesium bromide in THF was added. The 15 resulting solution was refluxed for 3 h, then cooled to room temperature, and 1000 ml of 0.5 M HCl was added. Further on, this mixture was extracted with 1000 ml of dichloromethane, the organic layer was separated, and the aqueous layer was extracted with 250 ml of dichloromethane. The combined organic extract was evaporated to dryness to give a greenish oil. The title product was isolated by flash-chromatography on silica gel 60 (40-63 μm ; 20 eluent: hexanes-dichloromethane = 3:1, vol., then 1:3, vol.). This procedure gave 107 g (ca. 100%) of 1-methoxy-2-methyl-4-(4-*tert*-butylphenyl)-1,2,3,5,6,7-hexahydro-*s*-indacene as a white solid mass.

Anal. calc. for $\text{C}_{24}\text{H}_{30}\text{O}$: C, 86.18; H, 9.04. Found: C, 85.99; H, 9.18.


^1H NMR (CDCl_3), *syn*-isomer: δ 7.42-7.37 (m, 2H), 7.25-7.20 (m, 3H), 4.48 (d, J = 5.5 Hz, 1H), 3.44 (s, 3H), 2.99-2.47 (m, 7H), 2.09-1.94 (m, 2H), 1.35 (s, 9H), 1.07 (d, J = 6.9

- 53 -

Hz, 3H); Anti-isomer: δ 7.42-7.37 (m, 2H), 7.25-7.19 (m, 3H), 4.39 (d, J = 3.9 Hz, 1H), 3.49 (s, 3H), 3.09 (dd, J = 15.9 Hz, J = 7.5 Hz, 1H), 2.94 (t, J = 7.3 Hz, 2H), 2.78 (tm, J = 7.3 Hz, 2H), 2.51-2.39 (m, 1H), 2.29 (dd, J = 15.9 Hz, J = 5.0 Hz, 1H), 2.01 (quin, J = 7.3 Hz, 2H), 1.36 (s, 9H), 1.11 (d, J = 7.1 Hz, 3H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl₃), *syn*-isomer: δ 149.31, 142.71,

5 142.58, 141.46, 140.03, 136.71, 135.07, 128.55, 124.77, 120.02, 86.23, 56.74, 39.41, 37.65, 34.49, 33.06, 32.45, 31.38, 25.95, 13.68; *Anti*-isomer: δ 149.34, 143.21, 142.90, 140.86, 139.31, 136.69, 135.11, 128.49, 124.82, 119.98, 91.53, 56.50, 40.12, 37.76, 34.50, 33.04, 32.40, 31.38, 25.97, 19.35.

4-(4-*tert*-Butylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene



10


To a solution of 107 g 1-methoxy-2-methyl-4-(4-*tert*-butylphenyl)-1,2,3,5,6,7-hexahydro-*s*-indacene (prepared above) in 700 ml of toluene, 600 mg of TsOH was added, and the resulting solution was refluxed using Dean-Stark head for 10 min. After cooling to room temperature the reaction mixture was washed with 200 ml of 10% NaHCO₃. The 15 organic layer was separated, and the aqueous layer was additionally extracted with 2x100 ml of dichloromethane. The combined organic extract was evaporated to dryness to give a red oil. The product was purified by flash-chromatography on silica gel 60 (40-63 μm ; eluent: hexanes, then hexanes-dichloromethane = 5:1, vol.) followed by vacuum distillation, b.p. 210-216°C/5-6 mm Hg. This procedure gave 77.1 g (80%) of 4-(4-*tert*-butylphenyl)-6-20 methyl-1,2,3,5-tetrahydro-*s*-indacene as a yellowish glassy material.

Anal. calc. for C₂₃H₂₆: C, 91.34; H, 8.66. Found: C, 91.47; H, 8.50.

^1H NMR (CDCl₃): δ 7.44-7.37 (m, 2H), 7.33-7.26 (m, 2H), 7.10 (s, 1H), 6.45 (br.s, 1H), 3.17 (s, 2H), 2.95 (t, J = 7.3 Hz, 2H), 2.78 (t, J = 7.3 Hz, 2H), 2.07 (s, 3H), 2.02 (quin, J = 7.3 Hz, 2H), 1.37 (s, 9H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl₃): δ 149.37, 145.54, 144.79, 142.91, 139.92, 138.05, 137.15, 134.06, 128.36, 127.02, 124.96, 114.84, 42.11, 34.53, 33.25, 32.16, 25 31.41, 25.96, 16.77.

- 54 -


2-methyl-[4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl](chlorodimethylsilyl)dimethylsilane



To a solution of 22.3 g (73.73 mmol) of 4-(4-*tert*-butylphenyl)-6-methyl-1,2,3,5-tetrahydro-s-indacene in 300 ml of ether, cooled to -50°C , 30.4 ml (73.87 mmol) of 2.43 M $^n\text{BuLi}$ in hexanes was added in one portion. The resulting mixture was stirred overnight at room temperature, then the resulting suspension with a large amount of precipitate was cooled to -78°C (wherein the precipitate was substantially dissolved to form an orange solution), and 47.6 g (369 mmol, 5 equiv.) of dichlorodimethylsilane was added in one portion. The obtained solution was stirred overnight at room temperature and then filtered through a glass frit (G4). The filtrate was evaporated to dryness to give 28.49 g (98%) of 2-methyl- [4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl](chlorodimethylsilyl)dimethylsilane as a colorless glass which was used without further purification.

^1H NMR (CDCl_3): δ 7.50-7.45 (m, 2H), 7.36 (s, 1H), 7.35-7.32 (m, 2H), 6.60 (s, 1H), 3.60 (s, 1H), 3.10-2.82 (m, 4H), 2.24 (s, 3H), 2.08 (quin, $J = 7.3$ Hz, 2H), 1.42 (s, 9H), 0.48 (s, 3H), 0.22 (s, 3H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ 149.27, 144.41, 142.15, 141.41, 139.94, 139.83, 136.85, 130.19, 129.07, 126.88, 124.86, 118.67, 49.76, 34.55, 33.27, 32.32, 31.44, 26.00, 17.6

2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-indan-1-one



- 55 -

A mixture of 31.1 g (100 mmol) of 2-methyl-4-bromo-5-methoxy-6-*tert*-butyl-indan-1-one, 25.0 g (140 mmol) of 4-*tert*-butylphenylboronic acid, 29.4 g (280 mmol) of Na₂CO₃, 1.35 g (6.00 mmol, 6 mol.%) of Pd(OAc)₂, and 3.15 g (12.0 mmol, 12 mol.%) of PPh₃ in 130 ml of water and 380 ml of DME was refluxed for 6 h in argon atmosphere. The formed


5 mixture was evaporated to dryness. To the residue 500 ml of dichloromethane and 500 ml of water were added. The organic layer was separated, the aqueous layer was additionally extracted with 100 ml of dichloromethane. The combined organic extract was dried over Na₂SO₄, evaporated to dryness, and the crude product was isolated using flash chromatography on silica gel 60 (40-63 µm; eluent: hexanes-dichloromethane = 2:1, vol.).

10 This crude product was recrystallized from n-hexane to give 29.1 g (81%) of a white solid.

Anal. calc. for C₂₅H₃₂O₂: C, 82.37; H, 8.85. Found: C, 82.26; H, 8.81.

¹H NMR (CDCl₃): δ 7.74 (s, 1H, 7-H in indenyl), 7.48 (d, J = 8.0 Hz, 2H, 2,6-H in C₆H₄^tBu), 7.33 (d, J = 8.0 Hz, 2H, 3,5-H in C₆H₄^tBu), 3.27 (s, 3H, OMe), 3.15 (dd, J = 17.3 Hz, J = 7.7 Hz, 1H, 3-H in indan-1-on), 2.67-2.59 (m, 1H, 2-H in indan-1-on), 2.48 (dd, J = 17.3 Hz, J = 3.7 Hz, 3'-H in indan-1-on), 1.42 (s, 9H, ^tBu in C₆H₄^tBu), 1.38 (s, 9H, 6-^tBu in indan-1-on), 1.25 (d, J = 7.3 Hz, 3H, 2-Me in indan-1-one).

2-methyl-5-*tert*-butyl-6-methoxy-7-(4-*tert*-butylphenyl)-1*H*-indene



20 To a solution of 28.9 g (79.2 mmol) of 2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-indan-1-one in 400 ml of THF cooled to 5°C 5.00 g (132 mmol) of NaBH₄ was added. Further on, 100 ml of methanol was added dropwise to this mixture by vigorous stirring for ca. 7 h at 5°C. The resulting mixture was evaporated to dryness, and the residue was partitioned between 500 ml of dichloromethane and 1000 ml of 0.5 M HCl. The organic layer was separated, the aqueous layer was additionally extracted with 100 ml of dichloromethane. The combined organic extract was evaporated to dryness to give a colorless oil. To a solution of this oil in 500 ml of toluene 1.0 g of TsOH was added. The formed

- 56 -

mixture was refluxed with Dean-Stark head for 15 min and then cooled to room temperature using water bath. The resulting reddish solution was washed by 10% aqueous Na_2CO_3 , the organic layer was separated, the aqueous layer was extracted with 2x100 ml of dichloromethane. The combined organic extract was dried over K_2CO_3 and then passed


5 through short pad of silica gel 60 (40-63 μm). The silica gel pad was additionally washed with 50 ml of dichloromethane. The combined organic elute was evaporated to dryness to give a yellowish crystalline mass. The product was isolated by re-crystallization of this mass from 150 ml of hot n-hexane. Crystals precipitated at 5°C were collected dried in vacuum. This procedure gave 23.8 g of white macrocrystalline 2-methyl-5-*tert*-butyl-6-methoxy-7-(4-10 *tert*-butylphenyl)-1*H*-indene. The mother liquor was evaporated to dryness and the residue was recrystallized from 20 ml of hot n-hexane in the same way. This procedure gave additional 2.28 g of the product. Thus, the total yield of the title product was 26.1 g (95%).

Anal. calc. for $\text{C}_{25}\text{H}_{32}\text{O}$: C, 86.15; H, 9.25. Found: C, 86.24; H, 9.40.

^1H NMR (CDCl_3): δ 7.44 (d, J = 8.5 Hz, 2H, 2,6-H in $\text{C}_6\text{H}_4\text{'Bu}$), 7.40 (d, J = 8.5 Hz, 2H, 3,5-15 H in $\text{C}_6\text{H}_4\text{'Bu}$), 7.21 (s, 1H, 4-H in indenyl), 6.43 (m, 1H, 3-H in indenyl), 3.20 (s, 3H, OMe), 3.15 (s, 2H, 1-H in indenyl), 2.05 (s, 3H, 2-Me in indenyl), 1.43 (s, 9H, 5- 'Bu in indenyl), 1.37 (s, 9H, 'Bu in $\text{C}_6\text{H}_4\text{'Bu}$).

[2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilane

- 57 -



To a solution of 8.38 g (24.04 mmol) of 2-methyl-5-*tert*-butyl-7-(4-*tert*-butylphenyl)-6-methoxy-1*H*-indene in 150 ml of ether 9.9 ml (24.06 mmol) of 2.43 M *n*BuLi in hexanes was added in one portion at -50°C. This mixture was stirred overnight at room temperature,


5 then the resulting yellow solution with yellow precipitate was cooled to -50°C, and 150 mg of CuCN was added. The obtained mixture was stirred for 0.5 h at -25°C, then a solution of 9.5 g (24.05 mmol) of 2-methyl-[4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl](chloro)dimethylsilane in 150 ml of ether was added in one portion. This mixture was stirred overnight at room temperature, then filtered through a pad of silica gel 60 (40-63 µm),
10 which was additionally washed by 2x50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure, and the residue was dried in vacuum at elevated temperature. This procedure gave 17.2 g (ca. 100%) of [2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilane (ca. 95% purity by NMR spectroscopy, approx. 1:1 mixture of
15 stereoisomers) as yellowish glassy solid which was used in the next step without additional purification.

¹H NMR (CDCl₃): δ 7.50 (s, 0.5H), 7.48-7.41 (m, 6H), 7.37-7.33 (m, 2.5H), 7.26 (s, 0.5H), 7.22 (s, 0.5H), 6.57 and 6.50 (2s, sum 2H), 3.71, 3.69, 3.67 and 3.65 (4s, sum 2H), 3.23 and 3.22 (2s, sum 3H), 3.03-2.80 (m, 4H), 2.20, 2.16 and 2.14 (3s, sum 6H), 2.08-1.99 (m, 2H), 1.43 and 1.41 (2s, sum 9H), 1.39 (s, 18H), -0.19, -0.20, -0.21 and -0.23 (4s, sum

- 58 -

6H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ 155.49, 155.46, 149.41, 149.14, 149.11, 147.48, 147.44, 146.01, 145.77, 143.95, 143.91, 143.76, 143.71, 142.14, 142.10, 139.52, 139.42, 139.34, 139.29, 139.20, 139.16, 137.10, 137.05, 137.03, 135.20, 130.05, 130.03, 129.73, 129.11, 127.25, 127.22, 126.20, 126.13, 125.98, 125.94, 125.05, 124.82, 120.59, 120.52, 118.51, 118.26, 60.51, 60.48, 47.31, 46.89, 46.72, 35.14, 34.55, 33.34, 33.28, 32.30, 31.47, 31.45, 31.24, 31.19, 26.02, 25.99, 17.95, 17.86.

Anti-dimethylsilanediyl[2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]zirconium dichloride



10

To a solution of 17.2 g (ca. 24.04 mol) of [2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (prepared above) in 250 ml of ether, cooled to -50°C , 19.8 ml (48.11 mmol) of 2.43 M $^n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred for 4 h at room temperature, then the resulting cherry-red solution was cooled to -60°C , and 5.7 g (24.46 mmol) of ZrCl_4 was added. The reaction mixture was stirred for 24 h at room temperature to give red solution with orange precipitate. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered through glass frit (G4). The filtrate was evaporated to 90 ml. Yellow powder precipitated from this solution overnight at room temperature was collected, washed with 10

- 59 -

ml of cold toluene, and dried in vacuum. This procedure gave 4.6 g (22%) of a ca. 4 to 1 mixture of *anti*- and *syn*-zirconocenes. The mother liquor was evaporated to ca. 40 ml, and 20 ml of n-hexane was added. Orange powder precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 6.2 g (30%) of a ca. 1 to 5 1 mixture of *anti*- and *syn*-zirconocenes. Thus, the total yield of *anti*- and *syn*-zirconocenes isolated in this synthesis was 10.8 g (52%). Pure *anti*-zirconocene was obtained after crystallization of the above-described 4.6 g sample of a ca. 4 to 1 mixture of *anti*- and *syn*-zirconocenes from 20 ml of toluene. This procedure gave 1.2 g of pure *anti*-zirconocene.


10 *Anti*-dimethylsilanediyl[2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]zirconium dichloride:

Anal. calc. for C₅₀H₆₀Cl₂OSiZr: C, 69.25; H, 6.97. Found: C, 69.43; H, 7.15.

15 ¹H NMR (CDCl₃): δ 7.59-7.38 (group of m, 10H), 6.74 (s, 1H), 6.61 (s, 1H), 3.37 (s, 3H), 3.08-2.90 (m, 3H), 2.86-2.78 (m, 1H), 2.20 (s, 3H), 2.19 (s, 3H), 2.10-1.92 (m, 2H), 1.38 (s, 9H), 1.33 (s, 18H), 1.30 (s, 3H), 1.29 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 159.94, 150.05, 149.86, 144.79, 144.01, 143.20, 135.50, 135.41, 133.87, 133.73, 133.62, 132.82, 132.29, 129.23, 128.74, 126.95, 126.87, 125.36, 125.12, 122.93, 121.68, 121.32, 120.84, 117.90, 81.65, 81.11, 62.57, 35.74, 34.58, 33.23, 32.17, 31.37, 31.36, 30.32, 26.60, 18.39, 18.30, 2.65, 2.57¹.

20 Synthesis of MC-IE2

4-Bromo-2,6-dimethylaniline



159.8 g (1.0 mol) of bromine was slowly (over 2 h) added to a stirred solution of 121.2 g (1.0 mol) of 2,6-dimethylaniline in 500 ml of methanol. The resulting dark-red 25 solution was stirred overnight at room temperature, then poured into a cold solution of 140 g (2.5 mol) of potassium hydroxide in 1100 ml of water. The organic layer was separated, and


¹ Resonance originated from one carbon atom was not found because of overlapping with some other signal.

- 60 -

the aqueous one was extracted with 500 ml of diethyl ether. The combined organic extract was washed with 1000 ml of water, dried over K_2CO_3 , and evaporated in vacuum to give 202.1 g of 4-bromo-2,6-dimethylaniline (purity ca. 90%) as dark-red oil which crystallized upon standing at room temperature. This material was further used without additional 5 purification.

1H NMR ($CDCl_3$): δ 7.04 (s, 2H), 3.53 (br.s, 2H), 2.13 (s, 6H).

1-Bromo-3,5-dimethylbenzene




97 ml (1.82 mol) of 96% sulfuric acid was added dropwise to a solution of 134.7 g 10 (ca. 673 mmol) of 4-bromo-2,6-dimethylaniline (prepared above, purity ca. 90%) in 1400 ml of 95% ethanol cooled to $-10^{\circ}C$, at a such a rate to maintain the reaction temperature below 7°C. After the addition was complete, the solution was stirred at room temperature for 1 h. Then, the reaction mixture was cooled in an ice-bath, and a solution of 72.5 g (1.05 mol) of sodium nitrite in 150 ml of water was added dropwise over ca. 1 h. The formed solution was 15 stirred at the same temperature for 30 min. Then the cooling bath was removed, and 18 g of copper powder was added. Upon completion of the rapid evolution of nitrogen additional portions (ca. 5 g each, ca. 50 g in total) of copper powder were added with 10 min intervals until gas evolution ceased completely. The reaction mixture was stirred at room temperature overnight, then filtered through a glass frit (G3), diluted with two-fold volume of water, and 20 the crude product was extracted with 4x150 ml of dichloromethane. The combined extract was dried over K_2CO_3 , evaporated to dryness, and then distilled in vacuum (b.p. 60-63°C/5 mm Hg) to give a yellowish liquid. This product was additionally purified by flash-chromatography on silica gel 60 (40-63 μ m; eluent: hexane) and distilled once again (b.p. 51-52°C/3 mm Hg) to give 63.5 g (51%) of 1-bromo-3,5-dimethylbenzene as a colorless liquid.

25 1H NMR ($CDCl_3$): δ 7.12 (s, 2H), 6.89 (s, 1H), 2.27 (s, 6H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 139.81, 129.03, 128.61, 122.04, 20.99.

(3,5-Dimethylphenyl)boronic acid

- 61 -



A solution of 3,5-dimethylphenylmagnesium bromide obtained from a solution of 190.3 g (1.03 mol) of 1-bromo-3,5-dimethylbenzene in 1000 ml of THF and 32 g (1.32 mol, 28% excess) of magnesium turnings was cooled to -78°C, and 104 g (1.0 mol,


5 trimethylborate was added in one portion. The resulting heterogeneous mixture was stirred overnight at room temperature. The boronic ester was hydrolyzed by careful addition of 1200 ml of 2 M HCl. 500 ml of diethyl ether was added, the organic layer was separated, and the aqueous layer was additionally extracted with 2x500 ml of diethyl ether. The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness to give white mass.

10 The latter was triturated with 200 ml of n-hexane, filtered through glass frit (G3), and the precipitate was dried in vacuo. This procedure gave 114.6 g (74%) of (3,5-dimethylphenyl)boronic acid.

Anal. calc. for C₈H₁₁BO₂: C, 64.06; H, 7.39. Found: C, 64.38; H, 7.72.

¹H NMR (DMSO-d₆): δ 7.38 (s, 2H), 7.00 (s, 1H), 3.44(very br.s, 2H), 2.24 (s, 6H).

15 **2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-tert-butyl-indan-1-one**



A mixture of 49.14 g (157.9 mmol) of 2-methyl-4-bromo-5-methoxy-6-tert-butylindan-1-one, 29.6 g (197.4 mmol, 1.25 eq.) of (3,5-dimethylphenyl)boronic acid, 45.2 g (427 mmol) of Na₂CO₃, 1.87 g (8.3 mmol, 5 mol.%) of Pd(OAc)₂, 4.36 g (16.6 mmol, 10 mol.%) of PPh₃, 200 ml of water, and 500 ml of 1,2-dimethoxyethane was refluxed for 6.5 h. DME was evaporated on a rotary evaporator, 600 ml of water and 700 ml of dichloromethane were added to the residue. The organic layer was separated, and the aqueous one was additionally extracted with 200 ml of dichloromethane. The combined extract was dried over


- 62 -

K_2CO_3 and then evaporated to dryness to give a black oil. The crude product was purified by flash chromatography on silica gel 60 (40-63 μm , hexane-dichloromethane = 1:1, vol., then, 1:3, vol.) to give 48.43 g (91%) of 2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylindan-1-one as a brownish oil.

5 Anal. calc. for $\text{C}_{23}\text{H}_{28}\text{O}_2$: C, 82.10; H, 8.39. Found: C, 82.39; H, 8.52.

10 ^1H NMR (CDCl_3): δ 7.73 (s, 1H), 7.02 (s, 3H), 7.01 (s, 3H), 3.32 (s, 3H), 3.13 (dd, J = 17.5 Hz, J = 7.8 Hz, 1H), 2.68-2.57 (m, 1H), 2.44 (dd, J = 17.5 Hz, J = 3.9 Hz), 2.36 (s, 6H), 1.42 (s, 9H), 1.25 (d, J = 7.5 Hz, 3H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ 208.90, 163.50, 152.90, 143.32, 138.08, 136.26, 132.68, 130.84, 129.08, 127.18, 121.30, 60.52, 42.17, 35.37, 34.34, 30.52, 21.38, 16.40.

2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1H-indene



8.2 g (217 mmol) of NaBH_4 was added to a solution of 48.43 g (143.9 mmol) of 2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylindan-1-one in 300 ml of THF cooled 15 to 5°C. Then, 150 ml of methanol was added dropwise to this mixture by vigorous stirring for ca. 7 h at 5°C. The resulting mixture was evaporated to dryness, and the residue was partitioned between 500 ml of dichloromethane and 500 ml of 2 M HCl. The organic layer was separated, the aqueous layer was additionally extracted with 100 ml of dichloromethane. The combined organic extract was evaporated to dryness to give a slightly yellowish oil. To a 20 solution of this oil in 600 ml of toluene 400 mg of TsOH was added, this mixture was refluxed with Dean-Stark head for 10 min and then cooled to room temperature using a water bath. The formed solution was washed by 10% Na_2CO_3 , the organic layer was separated, the aqueous layer was extracted with 150 ml of dichloromethane. The combined organic extract was dried over K_2CO_3 and then passed through a short layer of silica gel 60 (40-63 μm). The 25 silica gel layer was additionally washed by 100 ml of dichloromethane. The combined organic elute was evaporated to dryness, and the resulting oil was dried in vacuum at elevated


- 63 -

temperature. This procedure gave 45.34 g (98%) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1*H*-indene which was used without additional purification.

Anal. calc. for C₂₃H₂₈O: C, 86.20; H, 8.81. Found: C, 86.29; H, 9.07.

¹H NMR (CDCl₃): δ 7.20 (s, 1H), 7.08 (br.s, 1H), 6.98 (br.s, 1H), 6.42 (m, 1H), 3.25 (s, 3H), 5 3.11 (s, 2H), 2.36 (s, 6H), 2.06 (s, 3H), 1.43 (s, 9H). ¹³C{¹H} NMR (CDCl₃): δ 154.20, 145.22, 141.78, 140.82, 140.64, 138.30, 137.64, 131.80, 128.44, 127.18, 126.85, 116.98, 60.65, 42.80, 35.12, 31.01, 21.41, 16.65.

[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-Butyl-1*H*-inden-1-yl](chloro)dimethylsilane




To a solution of 9.0 g (28.08 mmol) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1*H*-indene in 150 ml of ether, cooled to -50°C, 11.6 ml (28.19 mmol) of 2.43 M ⁿBuLi in hexanes was added in one portion. The resulting mixture was stirred for 6 h at room temperature, then the obtained yellow suspension was cooled to -60°C, and 18.1 g (140.3 mmol, 5 equiv.) of dichlorodimethylsilane was added in one portion. The obtained solution was stirred overnight at room temperature and then filtered through a glass frit (G3). The filtrate was evaporated to dryness to give [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-Butyl-1*H*-inden-1-yl](chloro)dimethylsilane as a slightly yellowish oil which was further used without an additional purification.

20 ¹H NMR (CDCl₃): δ 7.38 (s, 1H), 7.08 (s, 2H), 6.98 (s, 1H), 6.43 (s, 1H), 3.53 (s, 1H), 3.25 (s, 3H), 2.37 (s, 6H), 2.19 (s, 3H), 1.43 (s, 9H), 0.43 (s, 3H), 0.17 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 155.78, 145.88, 143.73, 137.98, 137.56, 137.49, 136.74, 128.32, 127.86, 127.55, 126.64, 120.86, 60.46, 49.99, 35.15, 31.16, 21.41, 17.55, 1.11, -0.58.

1-methoxy-2-methyl-4-(3,5-Dimethylphenyl)-1,2,3,5,6,7-hexahydro-s-indacene

- 64 -



To a mixture of 2.0 g (2.56 mmol, 1.8 mol.%) of $\text{NiCl}_2(\text{PPh}_3)\text{IPr}$ and 40.0 g (142.3 mmol) of 4-bromo-1-methoxy-2-methyl-1,2,3,5,6,7-hexahydro-*s*-indacene, 200 ml (200 mmol, 1.4 eq) of 3,5-dimethylphenylmagnesium bromide 1.0 M in THF was added. The


5 resulting solution was refluxed for 3 h, then cooled to room temperature, and 400 ml of water followed by 500 ml of 1.0 M HCl solution were added. Further on, this mixture was extracted with 600 ml of dichloromethane, the organic layer was separated, and the aqueous layer was extracted with 2x100 ml of dichloromethane. The combined organic extract was evaporated to dryness to give a slightly greenish oil. The product was isolated by flash-chromatography
10 on silica gel 60 (40-63 μm ; eluent: hexanes-dichloromethane = 2:1, vol., then 1:2, vol.). This procedure gave 43.02 g (99%) of 1-methoxy-2-methyl-4-(3,5-dimethylphenyl)-1,2,3,5,6,7-hexahydro-*s*-indacene as a colorless thick oil as a mixture of two diastereoisomers.

Anal. calc. for $\text{C}_{22}\text{H}_{26}\text{O}$: C, 86.23; H, 8.55. Found: C, 86.07; H, 8.82.

^1H NMR (CDCl_3), Syn-isomer: δ 7.21 (s, 1H), 6.94 (br.s, 1H), 6.90 (br.s, 2H), 4.48 (d, J = 5.5 Hz, 1H), 3.43 (s, 3H), 2.94 (t, J = 7.5 Hz, 2H), 2.87-2.65 (m, 3H), 2.63-2.48 (m, 2H), 2.33 (s, 6H), 2.02 (quin, J = 7.5 Hz, 2H), 1.07 (d, J = 6.7 Hz, 3H); Anti-isomer: δ 7.22 (s, 1H), 6.94 (br.s, 1H), 6.89 (br.s, 2H), 4.38 (d, J = 4.0 Hz, 1H), 3.48 (s, 3H), 3.06 (dd, J = 16.0 Hz, J = 7.5 Hz, 1H), 2.93 (t, J = 7.3 Hz, 2H), 2.75 (td, J = 7.3 Hz, J = 3.2 Hz, 2H), 2.51-2.40 (m, 1H), 2.34 (s, 6H), 2.25 (dd, J = 16.0 Hz, J = 5.0 Hz, 1H), 2.01 (quin, J = 7.3 Hz, 2H),
20 1.11 (d, J = 7.1 Hz, 3H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3), Syn-isomer: δ 142.69, 142.49, 141.43, 139.97, 139.80, 137.40, 135.46, 128.34, 126.73, 120.09, 86.29, 56.76, 39.43, 37.59, 33.11, 32.37, 25.92, 21.41, 13.73; Anti-isomer: δ 143.11, 142.72, 140.76, 139.72, 139.16, 137.37, 135.43, 128.29, 126.60, 119.98, 91.53, 56.45, 40.06, 37.65, 33.03, 32.24, 25.88, 21.36, 19.36.

4-(3,5-Dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene

- 65 -




To the solution of 43.02 g (140.4 mmol) 1-methoxy-2-methyl-4-(3,5-dimethylphenyl)-1,2,3,5,6,7-hexahydro-s-indacene in 600 ml of toluene, 200 mg of TsOH was added, and the resulting solution was refluxed using Dean-Stark head for 15 min. After 5 cooling to room temperature the reaction mixture was washed with 200 ml of 10% NaHCO₃. The organic layer was separated, and the aqueous layer was additionally extracted with 300 ml of dichloromethane. The combined organic extract was evaporated to dryness to give light orange oil. The product was isolated by flash-chromatography on silica gel 60 (40-63 µm; eluent: hexanes, then hexanes-dichloromethane = 10:1, vol.). This procedure gave 35.66 g 10 (93%) of 4-(3,5-dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-s-indacene as a slightly yellowish oil which spontaneously solidified to form a white mass.

Anal. calc. for C₂₁H₂₂: C, 91.92; H, 8.08. Found: C, 91.78; H, 8.25.

¹H NMR (CDCl₃): δ 7.09 (s, 1H), 6.98 (br.s, 2H), 6.96 (br.s, 1H), 6.44 (m, 1H), 3.14 (s, 2H), 2.95 (t, *J* = 7.3 Hz, 2H), 2.76 (t, *J* = 7.3 Hz, 2H), 2.35 (s, 6H), 2.07 (s, 3H), 2.02 (quin, *J* = 7.3 Hz, 2H). ¹³C{¹H} NMR (CDCl₃): δ 145.46, 144.71, 142.81, 140.17, 139.80, 137.81, 137.50, 134.33, 128.35, 127.03, 126.48, 114.83, 42.00, 33.23, 32.00, 25.87, 21.38, 16.74.

[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-Butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilane

- 66 -



To a solution of 7.71 g (28.1 mmol) of 4-(3,5-dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene in a mixture of 150 ml of ether and 20 ml of THF 11.6 ml (28.19 mmol) of 2.43 M $^n\text{BuLi}$ in hexanes was added in one portion at -50°C . This mixture was 5 stirred for 6 h at room temperature, then the resulting orange solution was cooled to -50°C , and 150 mg of CuCN was added. The obtained mixture was stirred for 0.5 h at -25°C , then a solution of [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl](chlorodimethylsilane (prepared above, ca. 28.08 mmol) in 150 ml of ether was added in one portion. This mixture was stirred overnight at room temperature, then filtered through a 10 pad of silica gel 60 (40-63 μm), which was additionally washed by 2x50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure to give a yellow oil. The product was isolated by flash-chromatography on silica gel 60 (40-63 μm ; eluent: hexanes-dichloromethane = 10:1, vol., then 5:1, vol.). This procedure gave 11.95 g (65%) of [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-Butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (as ca. 1:1 15 mixture of stereoisomers) as a yellowish glassy solid.


Anal. calc. for $\text{C}_{46}\text{H}_{54}\text{OSi}$: C, 84.87; H, 8.36. Found: C, 85.12; H, 8.59.

^1H NMR (CDCl_3): δ 7.48 and 7.33 (2s, sum 1H), 7.26-7.18 (m, 1H), 7.16-7.07 (m, 2H), 7.04-6.95 (m, 4H), 6.51 and 6.45 (2s, sum 2H), 3.69 and 3.65 (2s, sum 2H), 3.28 and 20 3.26 (2s, sum 3H), 3.01-2.74 (m, 4H), 2.38 ad 2.37 (2s, sum 12H), 2.20 and 2.15 (2s, sum 6H), 2.09-1.97 (m, 2H), 1.43 and 1.42 (2s, sum 9H), -0.17, -0.18, -0.19 and -0.24 (4s, sum

- 67 -

6H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ 155.29, 147.45, 147.39, 145.99, 145.75, 143.93, 143.90, 143.72, 143.69, 142.06, 142.01, 140.08, 140.06, 139.46, 139.37, 139.26, 139.03, 139.00, 138.24, 137.50, 137.34, 137.07, 136.99, 130.39, 128.23, 128.14, 127.92, 127.50, 127.46, 127.26, 126.12, 126.05, 125.99, 125.94, 120.55, 120.51, 118.46, 118.27, 60.49, 47.33, 46.86, 46.76, 35.14, 33.33, 33.28, 32.18, 31.26, 31.21, 25.95, 25.91, 21.44, 17.96, 17.88, -5.27, -5.39, -5.50, -5.82.

Anti-dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]zirconium dichloride



10

To a solution of 11.95 g (18.36 mol) of [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilane (prepared above) in 200 ml of ether, cooled to -50°C, 15.1 ml (35.7 mmol) of 2.43 M $^n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred for 3 h at room temperature, then the resulting red solution was cooled to -78°C, and 4.28 g (18.37 mmol) of ZrCl_4 was added. The reaction mixture was stirred for 24 h at room temperature to give light red solution with orange precipitate. This mixture was evaporated to dryness. The residue was treated with 250 ml of hot toluene, and the formed suspension was filtered through glass frit (G4). The filtrate was evaporated to 40 ml. Red powder precipitated from this solution overnight at room temperature was collected, washed with 10 ml of cold toluene, and dried in vacuum. This procedure gave 0.6 g of *syn*-zirconocene. The mother liquor was evaporated to ca. 35 ml, and 15 ml of n-hexane was added to the warm solution. The red

15

20

- 68 -

powder precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 3.49 g *syn*-zirconocene. The mother liquor was evaporated to ca. 20 ml, and 30 ml of n-hexane was added to the warm solution. The yellow powder precipitated from this solution overnight at room temperature was collected and dried in 5 vacuum. This procedure gave 4.76 g *anti*-zirconocene as a solvate with toluene (x 0.6 toluene) contaminated with ca. 2% of *syn*-isomer. Thus, the total yield of *syn*- and *anti*-zirconocenes isolated in this synthesis was 8.85 g (59%).

10 *Anti*-dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]zirconium dichloride:

Anal. calc. for $C_{46}H_{52}Cl_2OSiZr \times 0.6C_7H_8$: C, 69.59; H, 6.61. Found: C, 69.74; H, 6.68.

15 1H NMR ($CDCl_3$): δ 7.47 (s, 1H), 7.40 (s, 1H), 7.37-7.03 (m, 4H), 6.95 (s, 2H), 6.71 (s, 1H), 6.55 (s, 1H), 3.43 (s, 3H), 3.03-2.96 (m, 2H), 2.96-2.87 (m, 1H), 2.87-2.76 (m, 1H), 2.34 and 2.33 (2s, sum 12H), 2.19 and 2.18 (2s, sum 6H), 2.06-1.94 (m, 2H), 1.38 (s, 9H), 1.28 (s, 3H), 1.27 (s, 3H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 159.73, 144.59, 143.99, 143.00, 138.26, 137.84, 137.59, 136.80, 135.35, 133.85, 133.63, 132.95, 132.52, 128.90, 128.80, 127.40, 126.95, 126.87, 126.65, 122.89, 121.61, 121.53, 120.82, 117.98, 81.77, 81.31, 62.62, 35.73, 33.20, 32.12, 30.37, 26.49, 21.47, 21.38, 18.40, 18.26, 2.64, 2.54.

20 *Syn*- dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]zirconium dichloride.


Anal. calc. for $C_{46}H_{52}Cl_2OSiZr$: C, 68.11; H, 6.46. Found: C, 68.37; H, 6.65.

25 1H NMR ($CDCl_3$): δ 7.51 (s, 1H), 7.39 (s, 1H), 7.36-6.99 (m, 4H), 6.95 (s, 2H), 6.60 (s, 1H), 6.44 (s, 1H), 3.27 (s, 3H), 2.91-2.75 (m, 4H), 2.38 and 2.34 (2s, sum 18H), 1.99-1.87 (m, 1H), 1.87-1.74 (m, 1H), 1.42 (s, 3H), 1.36 (s, 9H), 1.19 (s, 3H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 158.74, 143.41, 142.84, 142.31, 138.30, 137.77, 137.55, 136.85, 135.87, 135.73, 134.99, 134.75, 131.64, 128.83, 128.76, 127.97, 127.32, 126.82, 126.22, 123.91, 121.35, 121.02, 120.85, 118.56, 83.47, 83.08, 62.32, 35.53, 33.33, 31.96, 30.33, 26.53, 21.45 (two 30 resonances), 18.56, 18.43, 2.93, 2.65.

Alternative Synthesis of MC-IE2

2-methyl-4-bromo-5-methoxy-6-*tert*-butyl-indan-1-one is obtained as described above.

5 One-pot synthesis of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1*H*-indene from 2-methyl-4-bromo-5-methoxy-6-*tert*-butyl-indan-1-one



Step 1: 2 mol.% Pd(P'Bu₃)₂, 2-MeTHF, 7 h at reflux

10 A mixture of 2-methyl-4-bromo-5-methoxy-6-*tert*-butyl-indan-1-one (15.75 g, 50.61 mmol), (3,5-dimethylphenyl)boronic acid (9.5 g, 63.34 mmol, 1.25 equiv.), Na₂CO₃ (14.5 g, 137 mmol), Pd(P'Bu₃)₂ (0.51 g, 1 mmol), 66 ml of water and 165 ml of 2-methyltetrahydrofuran was refluxed for 7 h. After cooling to room temperature, the organic layer was separated, dried over K₂CO₃, and the resulting solution was used in the following step without

15 additional purification.

¹H NMR (CDCl₃): δ 7.73 (s, 1H), 7.02 (s, 3H), 7.01 (s, 3H), 3.32 (s, 3H), 3.13 (dd, *J* = 17.5 Hz, *J* = 7.8 Hz, 1H), 2.68-2.57 (m, 1H), 2.44 (dd, *J* = 17.5 Hz, *J* = 3.9 Hz), 2.36 (s, 6H), 1.42 (s, 9H), 1.25 (d, *J* = 7.5 Hz, 3H). ¹³C{¹H} NMR (CDCl₃): δ 208.90, 163.50, 152.90, 143.32, 138.08, 136.26, 132.68, 130.84, 129.08, 127.18, 121.30, 60.52, 42.17, 35.37, 34.34, 30.52,

20 21.38, 16.40

Step 2: a) NaBH₄/2-MeTHF/MeOH; b) TsOH/toluene at reflux


NaBH₄ (5.2 g, 138 mmol) was added to the above solution of 2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-indan-1-one in 165 ml of 2-methyltetrahydrofuran cooled to 5°C. Further on, 80 ml of methanol was added dropwise to this mixture for ca. 7 h at 5°C. The resulting mixture was evaporated to dryness, 300 ml of dichloromethane and 300 ml water were added to the residue, and thus obtained mixture was acidified with 2 M HCl to pH~6.5. The organic layer was separated; the aqueous layer was additionally extracted with

- 70 -

100 ml of dichloromethane. The combined organic extract was passed through a pad (~200 ml) of silica gel 60 (40-63 μ m; eluent: dichloromethane). The obtained elute was evaporated to dryness to give a slightly brownish oil. 200 mg of TsOH was added to a solution of this oil in 200 ml of toluene. This mixture was refluxed with Dean-Stark head for 10 min and then 5 cooled to room temperature using a water bath. The formed solution was washed with 10% Na_2CO_3 , the organic layer was separated, and the aqueous layer was extracted with 50 ml of dichloromethane. The combined organic extract was dried over K_2CO_3 and then evaporated to dryness. The residue was dissolved in 100 ml of n-hexane, and the obtained solution was passed through a short pad (~20 ml) of silica gel 60 (40-63 μ m; eluent: n-hexane). The silica 10 gel layer was additionally washed by 40 ml of n-hexane. The combined organic elute was evaporated to dryness, and the resulting oil was dried in vacuum at elevated temperature to give 15.35 g (95%) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1*H*-indene which was used in the following step without additional purification.

¹H NMR (CDCl₃): δ 7.20 (s, 1H), 7.08 (br.s, 1H), 6.98 (br.s, 1H), 6.42 (m, 1H), 3.25 (s, 3H), 3.11 (s, 2H), 2.36 (s, 6H), 2.06 (s, 3H), 1.43 (s, 9H). ¹³C{¹H} NMR (CDCl₃): δ 154.20, 145.22, 141.78, 140.82, 140.64, 138.30, 137.64, 131.80, 128.44, 127.18, 126.85, 116.98, 60.65, 42.80, 35.12, 31.01, 21.41, 16.65.

Synthesis of 4-(3,5-dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene



20

Step 3 to 6 according to patent literature (e.g. WO2015158790).

Step 7:

200 ml (200 mmol, 1.4 eq) of 3,5-dimethylphenylmagnesium bromide 1.0 M in THF was
 25 added to a mixture of 2.0 g (2.56 mmol, 1.8 mol.%) of $\text{NiCl}_2(\text{PPh}_3)\text{IPr}$ and 40.0 g (142.3 mmol) of 1-methoxy-2-methyl-4-bromo-1,2,3,5,6,7-hexahydro-*s*-indacene. The resulting

- 71 -

solution was refluxed for 3 h and then cooled to room temperature, and 400 ml of water followed by 500 ml of 1.0 M HCl solution were added. Then this mixture was extracted with 600 ml of dichloromethane, the organic layer was separated, and the aqueous layer was extracted with 2×100 ml of dichloromethane. The combined organic extract was evaporated

5 to dryness to give a slightly greenish oil. The product was isolated by flash-chromatography on silica gel 60 (40-63 μ m; eluent: hexanes-dichloromethane = 2:1, vol., then 1:2, vol.). This procedure gave 43.02 g (99%) of 1-methoxy-2-methyl-4-(3,5-dimethylphenyl)-1,2,3,5,6,7-hexahydro-s-indacene as a colorless thick oil as a mixture of two diastereoisomers.

¹H NMR (CDCl₃), Syn-isomer: δ 7.21 (s, 1H), 6.94 (br.s, 1H), 6.90 (br.s, 2H), 4.48 (d, J = 5.5 Hz, 1H), 3.43 (s, 3H), 2.94 (t, J = 7.5 Hz, 2H), 2.87-2.65 (m, 3H), 2.63-2.48 (m, 2H), 2.33 (s, 6H), 2.02 (quin, J = 7.5 Hz, 2H), 1.07 (d, J = 6.7 Hz, 3H); Anti-isomer: δ 7.22 (s, 1H), 6.94 (br.s, 1H), 6.89 (br.s, 2H), 4.38 (d, J = 4.0 Hz, 1H), 3.48 (s, 3H), 3.06 (dd, J = 16.0 Hz, J = 7.5 Hz, 1H), 2.93 (t, J = 7.3 Hz, 2H), 2.75 (td, J = 7.3 Hz, J = 3.2 Hz, 2H), 2.51-2.40 (m, 1H), 2.34 (s, 6H), 2.25 (dd, J = 16.0 Hz, J = 5.0 Hz, 1H), 2.01 (quin, J = 7.3 Hz, 2H), 1.11 (d, J = 7.1 Hz, 3H). ¹³C{¹H} NMR (CDCl₃), Syn-isomer: δ 142.69, 142.49, 141.43, 139.97, 139.80, 137.40, 135.46, 128.34, 126.73, 120.09, 86.29, 56.76, 39.43, 37.59, 33.11, 32.37, 25.92, 21.41, 13.73; Anti-isomer: δ 143.11, 142.72, 140.76, 139.72, 139.16, 137.37, 135.43, 128.29, 126.60, 119.98, 91.53, 56.45, 40.06, 37.65, 33.03, 32.24, 25.88, 21.36, 19.36.

Step 8:


20 TsOH (200 mg) was added to the solution of 43.02 g (140.4 mmol) of 1-methoxy-2-methyl-4-(3,5-dimethylphenyl)-1,2,3,5,6,7-hexahydro-s-indacene in 600 ml of toluene and the resulting solution was refluxed using Dean-Stark head for 15 min. After cooling to room temperature the reaction mixture was washed with 200 ml of 10% NaHCO₃. The organic layer was separated, and the aqueous layer was additionally extracted with 300 ml of dichloromethane. The combined organic extract was evaporated to dryness to give light orange oil. The product was isolated by flash-chromatography on silica gel 60 (40-63 μ m; eluent: hexanes, then hexanes-dichloromethane = 10:1, vol.). This procedure gave 35.66 g (93%) of 4-(3,5-dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-s-indacene as a slightly yellowish oil which spontaneously solidified to form a white mass.

25 30 ¹H NMR (CDCl₃): δ 7.09 (s, 1H), 6.98 (br.s, 2H), 6.96 (br.s, 1H), 6.44 (m, 1H), 3.14 (s, 2H), 2.95 (t, J = 7.3 Hz, 2H), 2.76 (t, J = 7.3 Hz, 2H), 2.35 (s, 6H), 2.07 (s, 3H), 2.02 (quin, J = 7.3

- 72 -

Hz, 2H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ 145.46, 144.71, 142.81, 140.17, 139.80, 137.81, 137.50, 134.33, 128.35, 127.03, 126.48, 114.83, 42.00, 33.23, 32.00, 25.87, 21.38, 16.74

Synthesis of MC-IE2



Step 9: a) $^n\text{BuLi}$ in $^n\text{Bu}_2\text{O}$, -5°C ; b) 5 equiv Me_2SiCl_2 , THF, -30°C .

$^n\text{BuLi}$ in hexanes (2.43 M, 20.2 ml, 49.09 mmol) was added in one portion to a solution of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1*H*-indene (15.69 g, 48.96 mmol) in 250 ml of di-*n*-butyl ether cooled to -5°C . The resulting mixture was stirred overnight at

10 room temperature, then the formed white suspension with a large amount of precipitate (which makes effective stirring difficult) was cooled to -30°C , and THF (8 ml, 7.11 g, i.e. ca. 2.01 ratio of THF to the starting indene was used) was added to give a clear orange solution. This solution was cooled to -30°C , and then dichlorodimethylsilane (31.6 g, 244.9 mmol, 5 equiv.) was added in one portion. The obtained mixture was stirred overnight at room

15 temperature and then filtered through a glass frit (G3). The filtrate was evaporated to dryness to give [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl]chlorodimethylsilane as a slightly yellowish oil (containing some hard-to-remove impurity of di-*n*-butyl ether) which was used in the following step without additional purification

Step 10: $^n\text{BuLi}$ in hexanes (2.43 M, 20.1 ml, 48.84 mmol) was added in one portion to a 20 solution of 4-(3,5-dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene (13.43 g, 48.94 mmol) in a mixture of di-*n*-butyl ether (200 mL) and THF (8 ml, 7.11 g, i.e. ca. 2.02 ratio of THF to the starting indene) at -10°C . This mixture was stirred overnight at room temperature, giving an orange suspension. To this suspension, a solution of [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl]chlorodimethylsilane (as prepared

- 73 -

above, ca. 48.96 mmol) in 120 ml of di-*n*-butyl ether was added in one portion. This mixture was stirred overnight at room temperature.

Step 11:

⁷BuLi in hexanes (2.43 M, 11.6 ml, 28.19 mmol) was added in one portion to a solution of


5 9.16 g (14.07 mol) of [6-*tert*-butyl-4-(3,5-dimethylphenyl)-5-methoxy-2-methyl-1*H*-inden-1-yl][4-(3,5-dimethylphenyl)-2-methyl-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane in 190 ml of di-*n*-butyl ether cooled to -30°C. This mixture was stirred for 4 h at room temperature, then the resulting ruby solution was cooled to -30°C (some yellow precipitate formed), and then ZrCl₄ (3.28 g, 14.08 mmol) was added. The reaction mixture was stirred for 24 h at 10 room temperature to give light red solution with orange precipitate. This precipitate was filtered off (G4) and then dried in vacuum to give 4.7 g of a mixture of *syn*-complex and LiCl (thus, the adjusted net weight of *syn*-complex was 3.51 g). The filtrate was evaporated until a viscous oil was obtained, which was then triturated with 40 ml of n-hexane. The obtained suspension was filtered through glass frit (G3), and the so obtained precipitate was dried 15 under vacuum. This procedure gave 3.5 g of pure *anti*-zirconocene dichloride (D69) as a yellow powder. Yellow powder precipitated from the solution overnight at -25°C was collected and dried under vacuum. This procedure gave 1.85 g of *anti*-zirconocene contaminated with 5% of its *syn*-isomer. Thus, the total yield of *syn*- and *anti*-zirconocenes isolated in this synthesis was 8.86 g (78%).

20

Synthesis of MC-IE3

[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane

- 74 -



To a solution of 7.87 g (24.56 mmol) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-dimethylphenyl)-1*H*-indene in 150 ml of ether, 10.1 ml (24.54 mmol) of 2.43 M *n*BuLi in hexanes was added in one portion at -50°C. This mixture was stirred overnight at room

5 temperature, then the resulting yellow solution with a large amount of yellow precipitate was cooled to -50°C (wherein the precipitate disappeared completely), and 150 mg of CuCN was added. The obtained mixture was stirred for 0.5 h at -25°C, then a solution of 9.70 g (24.55 mmol) of 2-methyl-[4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl](chloro)dimethylsilane in 150 ml of ether was added in one portion. This mixture was

10 stirred overnight at room temperature, then filtered through a pad of silica gel 60 (40-63 µm), which was additionally washed with 2x50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure, and the residue was dried in vacuum at elevated temperature. This procedure gave 16.2 g (97%) of [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (>95% purity by NMR, approx. 1:1 mixture of the

15 stereoisomers) as a yellowish glassy solid which was further used without an additional purification.

¹H NMR (CDCl₃): δ 7.49 (s, 0.5H), 7.47-7.42 (m, 2H), 7.37-7.32 (m, 2.5H), 7.25 (s, 0.5H), 7.22 (s, 0.5H), 7.15-7.09 (m, 2H), 7.01-6.97 (m, 1H), 6.57, 6.56 and 6.45 (3s, sum 2H), 3.70, 3.69, 3.67 and 3.65 (4s, sum 2H), 3.28 and 3.27 (2s, sum 3H), 3.01-2.79 (m, 4H),

- 75 -

2.38 (s, 6H), 2.19, 2.16 and 2.13 (3s, sum 6H), 2.07-2.00 (m, 2H), 1.43 and 1.41 (2s, sum

9H), 1.38 (s, 9H), -0.18, -0.19, -0.20 and -0.23 (4s, sum 6H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ


155.30, 155.27, 149.14, 149.10, 147.45, 147.38, 146.01, 145.77, 143.98, 143.92, 143.73,

143.68, 142.13, 142.09, 139.51, 139.41, 139.26, 139.23, 139.19, 139.15, 138.22, 137.51,

5 137.08, 137.05, 136.98, 130.05, 130.01, 129.11, 128.22, 127.90, 127.48, 127.44, 126.18, 126.13, 125.97, 125.92, 124.82, 120.55, 120.49, 118.50, 118.27, 60.54, 60.50, 47.34, 47.33, 46.87, 46.72, 35.14, 34.54, 33.34, 33.28, 32.30, 31.44, 31.25, 31.20, 26.02, 26.01, 21.45, 17.95, 17.87.

Anti-dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]zirconium

10 **dichloride**



To a solution of 16.2 g (23.86 mmol) of [2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-

15 indacen-1-yl]dimethylsilane (prepared above) in 250 ml of ether, cooled to -50°C, 19.7 ml (47.87 mmol) of 2.43 M $^n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred for 4 h at room temperature, then the resulting red solution was cooled to -50°C, and 5.57 g (23.9 mmol) of ZrCl_4 was added. The reaction mixture was stirred for 24 h at room temperature to give red solution with orange precipitate. This mixture was evaporated to dryness. The residue was treated with 150 ml of hot toluene, and the formed suspension was filtered through glass frit (G4). The filtrate was evaporated to 50 ml, and then 20 ml of n-

- 76 -

hexane was added. The orange crystals precipitated from this solution overnight at room temperature were collected, washed with 10 ml of cold toluene, and dried in vacuum. This procedure gave 5.02 g (25%) of *anti*-zirconocene as a solvate with toluene (x 0.75 toluene).

The mother liquor was evaporated to ca. 30 ml, and 30 ml of n-hexane was added. The 5 orange powder precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 6.89 g (34%) of a ca. 3 to 7 mixture of *anti*- and *syn*-zirconocenes. Thus, the total yield of *rac*-zirconocene isolated in this synthesis was 11.91 g (60%).


Anti-dimethylsilanediyl[2-methyl-4-(3,5-dimethylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]zirconium dichloride.

Anal. calc. for C₄₈H₅₆Cl₂OsiZr x 0.75C₇H₈: C, 70.42; H, 6.88. Found: C, 70.51; H, 6.99.

¹H NMR (CDCl₃): δ 7.63-7.03 (very br.s, 2H), 7.59-7.51 (br.m, 2H), 7.51-7.42 (m, 15 4H), 6.98 (s, 1H), 6.78 (s, 1H), 6.60 (s, 1H), 3.46 (s, 3H), 3.11-3.04 (m, 1H), 3.04-2.93 (m, 2H), 2.88-2.81 (m, 1H), 2.36 (s, 6H), 2.22 (s, 3H), 2.21 (s, 3H), 2.12-1.94 (m, 2H), 1.41 (s, 9H), 1.36 (s, 9H), 1.32 (s, 3H), 1.31 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 159.78, 149.90, 144.67, 144.07, 143.07, 136.75, 135.44, 135.40, 133.97, 133.51, 132.90, 132.23, 128.84, 128.76, 127.34, 127.01, 126.73, 125.28, 125.17, 122.89, 121.68, 121.59, 120.84, 117.94, 20 81.60, 81.26, 62.61, 35.73, 34.60, 33.20, 32.17, 31.36, 30.34, 26.56, 21.40, 18.41, 18.26, 2.65, 2.54.

Synthesis of MC-IE4

Chloro[2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilane




- 77 -

⁷BuLi in hexanes (2.43 M, 16.9 ml, 41.07 mmol) was added in one portion to a solution of 12.43 g (41.1 mmol) of 4-(4-*tert*-butylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene in 200 ml of ether cooled to -50°C. The resulting mixture was stirred overnight at room temperature; the resulting yellow slurry (light orange solution with a large amount of yellow 5 precipitate) was then cooled to -50°C, during the cooling the precipitate completely dissolved to form an orange solution, and 26.5 g (205 mmol, 5 equiv.) of dichlorodimethylsilane was added in one portion. The obtained solution was stirred overnight at room temperature and then filtered through a glass frit (G3), the flask and the filter cake were rinsed with 50 ml of toluene. The filtrate was evaporated to dryness to give 16 g (99%) 10 of chloro[2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane as slightly yellowish oil which was used without further purification.

¹H NMR (CDCl₃): δ 7.47-7.41 (m, 2H), 7.34-7.27 (m, 3H), 6.56 (s, 1H), 3.56 (s, 1H), 3.05-2.78 (m, 4H), 2.20 (s, 3H), 2.04 (quin, *J* = 7.4 Hz, 2H), 1.38 (s, 9H), 0.44 (s, 3H), 0.18 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 149.27, 144.42, 142.14, 141.40, 139.94, 139.83, 136.84, 15 130.18, 129.07, 126.87, 124.86, 118.67, 49.76, 34.55, 33.26, 32.31, 31.43, 26.00, 17.60, 1.17, -0.60

[2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane



20

⁷BuLi in hexanes (2.43 M, 13.8 ml, 33.53 mmol) was added in one portion to a solution of 13.55 g (33.49 mmol) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-di-*tert*-butylphenyl)-1*H*-indene in 200 ml of ether at -50°C. This mixture was stirred for 5 h at room temperature; the

- 78 -


resulting orange slurry with a large amount of yellow precipitate was then cooled to -50°C, and 150 mg of CuCN was added. The obtained mixture was stirred for 0.5 h at -25°C, then a solution of 13.23 g (33.49 mmol) of chloro[2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane in 150 ml of ether was added in one portion. This

5 mixture was stirred overnight at room temperature, then filtered through a pad of silica gel 60 (40-63 µm), which was additionally washed with 2×50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure, and the product was isolated by flash-chromatography on silica gel 60 (40-63 µm; eluent: hexanes-dichloromethane = 10:1, then 3:1 vol). This procedure gave 18.4 g (72%) of [2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-
10 methoxy-6-*tert*-butyl-1*H*-inden-1-yl][4-(4-*tert*-butylphenyl)-2-methyl-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (>95% purity by NMR, approx. 1:1 mixture of stereoisomers) as yellowish glass which was used without further purification.

¹H NMR (CDCl₃): δ 7.52-7.40 (m, 3H), 7.40-7.30 (m, 4H), 7.27 (s, 1H), 7.22 (s, 1H), 6.57, 6.52 and 6.51 (3s, sum 2H), 3.71, 3.69 and 3.66 (3s, sum 2H), 3.20 and 3.19 (2s, sum 3H),
15 3.02-2.77 (m, 4H), 2.20, 2.18 and 2.16 (3s, sum 6H), 2.09-1.97 (m, 2H), 1.43 and 1.42 (2s, sum 9H), 1.38 and 1.37 (2s, sum 27H), -0.18, -0.19 and -0.23 (3s, sum 6H). ¹³C{¹H} NMR (CDCl₃): δ 155.49, 150.23, 149.15, 149.11, 147.36, 147.29, 146.04, 145.83, 143.99, 143.70, 142.15, 142.10, 139.53, 139.42, 139.24, 139.18, 139.13, 137.21, 137.17, 137.10, 130.07, 130.02, 129.13, 128.06, 126.18, 124.82, 124.72, 120.46, 120.40, 119.84, 118.54, 118.31,
20 60.08, 47.29, 46.92, 46.80, 35.17, 34.86, 34.54, 33.31, 32.31, 31.57, 31.46, 31.23, 31.19, 26.01, 18.08, 18.04, 17.99, 17.88, -5.30, -5.57, -5.62, -5.84.

Anti-dimethylsilanediyl[2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-5,6,7-trihydro-*s*-indacen-1-yl]zirconium
25 dichloride MC-IE4

- 79 -



⁷BuLi in hexanes (2.43 M, 19.9 ml, 48.36 mmol) was added in one portion to a solution of 18.4 g (24.11 mmol) of [2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (as prepared above) in 200 ml of ether cooled to -60°C. This mixture was stirred overnight at room temperature; the resulting orange slurry was then cooled to -60°C and 5.62 g (24.12 mmol) of ZrCl₄ was added. The reaction mixture was stirred for 24 h at room temperature to give a red solution with a small amount of precipitate. This mixture was evaporated to dryness. The residue was heated with 150 ml of toluene, and the formed suspension was filtered through glass frit (G4). The filtrate was evaporated to 80 ml, and then 20 ml of n-pentane was added. Orange powder precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 6.02 g (27%) of *syn*-zirconocene as a solvate with toluene (x 1 PhMe) contaminated with ca. 2% of *anti*-isomer. The mother liquor was evaporated to ca. 30 ml, and 30 ml of n-hexane was added.

10 Orange powder precipitated from this solution overnight at room temperature was collected and dried under vacuum. This procedure gave 1.38 g (6%) of *syn*-zirconocene as a solvate with toluene (x 1 PhMe) contaminated with ca. 8% of *anti*-isomer. The mother liquor was evaporated to the oily state, and this oil was dissolved in 50 ml of n-hexane. Yellow powder precipitated from this solution over 2 days at -30°C was collected and dried in vacuum. This procedure gave 7.3 g (33%) of *anti*-zirconocene contaminated with ca. 3% of *syn*-isomer.

15 Thus, the total yield of *anti*- and *syn*-zirconocenes isolated in this synthesis was 14.7 g (66%).

7.3 g (33%) of *anti*-zirconocene contaminated with ca. 3% of *syn*-isomer was additionally recrystallized from a hot mixture of 15 ml of toluene and 30 ml of n-hexane.

- 80 -

Light-orange crystals precipitated overnight at room temperature were collected and dried under vacuum. This procedure gave 4.6 g of pure *anti*-zirconocene as a solvate with toluene (x 0.8 PhMe).

5 *Anti*-dimethylsilanediyl[2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(4-*tert*-butylphenyl)-5,6,7-trihydro-*s*-indacen-1-yl]zirconium dichloride

Anal. calc. for C₅₄H₆₈Cl₂OSiZr x 0.8C₇H₈: C, 71.80; H, 7.52. Found: C, 72.04; H, 7.75.

10 ¹H NMR (CDCl₃): δ 7.60-7.30 (set of signals, sum 9H), 6.73 (s, 1H), 6.60 (s, 1H), 3.33 (s, 3H), 3.16-3.02 (m, 1H), 3.02-2.88 (m, 2H), 2.88-2.77 (m, 1H), 2.20 (s, 3H), 2.19 (s, 3H), 2.11-1.91 (m, 2H), 1.38 (s, 9H), 1.34 (s, 9H), 1.33 (s, 18H), 1.29 (s, 3H), 1.28 (s, 3H).
¹³C{¹H} NMR (CDCl₃): δ 160.02, 149.90, 144.69, 143.96, 143.05, 135.95, 135.51, 135.40, 133.99, 133.72, 132.85, 132.16, 128.80, 127.54, 126.97, 125.16, 124.25, 122.74, 121.76, 121.12, 120.68, 120.45, 117.96, 81.85, 81.23, 62.26, 35.77, 34.96, 34.61, 33.18, 32.14, 31.56, 31.38, 30.32, 26.53, 18.39 (two resonances), 2.66, 2.61.

15

Synthesis of MC-IE5

Chloro[2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane



20

⁷BuLi in hexanes (2.43 M, 12.6 ml, 30.62 mmol) was added in one portion to a solution of 8.4 g (30.61 mmol) of 4-(3,5-dimethylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene in a mixture of 150 ml of ether and 10 ml of THF cooled to -50°C. The resulting mixture was stirred overnight at room temperature; the obtained red solution was then cooled to -50°C, and 19.8 g (153.4 mmol, 5.01 equiv.) of dichlorodimethylsilane was added in one portion. This mixture was stirred overnight at room temperature and then filtered through a glass frit (G3), the flask and the filter cake were rinsed with 50 ml of toluene. The filtrate was evaporated to dryness to give 11.3 g (ca. 100%) of chloro[2-methyl-4-(3,5-dimethylphenyl)-


- 81 -

1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane as reddish oil which was used without further purification.

¹H NMR (CDCl₃): δ 7.29 (s, 1H), 6.97 (s, 3H), 6.50 (m, 1H), 3.55 (s, 1H), 3.06-2.72 (m, 4H), 2.37 (s, 6H), 2.20 (s, 3H), 2.04 (quin, J = 7.4 Hz, 2H), 0.43 (s, 3H), 0.19 (s, 3H). ¹³C{¹H}

5 ¹³C NMR (CDCl₃): δ 144.39, 142.06, 141.36, 139.81, 139.78, 137.40, 130.49, 128.24, 127.20, 126.80, 118.65, 49.74, 33.25, 32.20, 25.93, 21.43, 17.63, 1.16, -0.53

[2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane




10

⁷BuLi in hexanes (2.43 M, 12.6 ml, 30.62 mmol) was added in one portion to a solution of 12.39 g (30.62 mmol) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(3,5-di-*tert*-butylphenyl)-1*H*-indene in 200 ml of ether at -50°C. This mixture was stirred overnight at room temperature; the resulting yellow slurry was then cooled to -50°C, and 150 mg of CuCN was added. The 15 obtained mixture was stirred for 0.5 h at -25°C, then a solution of 11.3 g (30.61 mmol) of chloro[2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (as prepared above) in 150 ml of ether was added in one portion. This mixture was stirred for 20 h at room temperature, then filtered through a pad of silica gel 60 (40-63 µm) which was additionally washed by 2×50 ml of dichloromethane. The combined filtrate was evaporated 20 under reduced pressure to give 22.34 g (99%) of [2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane as orange glass which was used without further purification.

- 82 -

Anti-dimethylsilanediyl[2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-*s*-indacen-1-yl]zirconium dichloride MC-IE5



5 ⁿBuLi in hexanes (2.43 M, 25 ml, 60.75 mmol) was added in one portion to a solution of 22.34 g (30.39 mmol) of [2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (as prepared above) in 250 ml of ether cooled to -50°C. This mixture was stirred overnight at room temperature, then the resulting dark-red solution was cooled to 10 -60°C, and 7.09 g (30.43 mmol) of ZrCl₄ was added. The reaction mixture was stirred for 24 h at room temperature to give orange slurry (red solution with yellow precipitate). This mixture was evaporated to dryness. The residue was heated with 150 ml of toluene, and the formed suspension was filtered through glass frit (G4). The filtrate was evaporated to 60 ml, and the obtained suspension was heated to get a clear solution. Yellow powder precipitated 15 from this solution over 30 min at room temperature was collected and dried under vacuum. This procedure gave 3.7 g of pure *anti*-zirconocene. Yellow powder precipitated from the mother liquor overnight at room temperature was collected and dried under vacuum. This procedure gave 10.1 g of a ca. 40 to 60 mixture of *anti*- and *syn*-zirconocenes. The mother liquor was evaporated to dryness and triturated with 10 ml of n-hexane. This procedure gave 20 3.38 g of a ca. 40 to 60 mixture of *anti*- and *syn*-zirconocenes. Thus, the total yield of *anti*- and *syn*-zirconocenes isolated in this synthesis was 17.18 g (63%).

Anti-dimethylsilanediyl[2-methyl-4-(3,5-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-dimethylphenyl)-5,6,7-trihydro-*s*-indacen-1-yl]zirconium dichloride

- 83 -


Anal. calc. for $C_{52}H_{64}Cl_2OSiZr$: C, 69.76; H, 7.21. Found: C, 69.93; H, 7.49.

1H NMR ($CDCl_3$): δ 7.75-7.01 (4 very br.s, sum 4H), 7.49 (s, 1H), 7.40 (s, 1H), 7.34 (t, J = 1.8 Hz, 1H), 6.95 (m, 1H), 6.66 (s, 1H), 6.57 (s, 1H), 3.30 (s, 3H), 3.09-3.01 (m, 1H), 2.98-2.90 (m, 2H), 2.86-2.79 (m, 1H), 2.32 (s, 6H), 2.18 (s, 3H), 2.17 (s, 3H), 2.08-1.94 (m, 2H), 1.38 (s, 9H), 1.32 (s, 18H), 1.29 (s, 3H), 1.28 (s, 3H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 159.85, 150.41 (broad s), 144.69, 143.92, 142.96, 138.30, 137.59 (broad s), 135.87, 135.35, 134.02, 133.57, 132.73, 132.42, 128.79, 127.55, 127.10, 126.97 (broad s), 124.41 (broad s), 122.83, 122.14, 121.24, 120.65, 120.38, 117.94, 81.87, 81.03, 62.25, 35.77, 34.98, 33.18, 31.99, 31.49, 30.37, 26.43, 21.31, 18.44, 18.37, 2.66, 2.63.

10

Synthesis of MC-IE6

Chloro[2-methyl-4-(3,5-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane




15 $nBuLi$ in hexanes (2.43 M, 15.0 ml, 36.45 mmol) was added in one portion to a solution of 13.07 g (36.45 mmol) of 4-(3,5-di-*tert*-butylphenyl)-6-methyl-1,2,3,5-tetrahydro-*s*-indacene in 200 ml of ether cooled to $-50^{\circ}C$. The resulting mixture was stirred overnight at room temperature; the so obtained light-orange solution containing a large amount of white precipitate was then cooled to $-60^{\circ}C$ and 23.5 g (182.1 mmol, 5 equiv.) of dichlorodimethylsilane was added in one portion. This mixture was stirred overnight at room temperature and then filtered through a glass frit (G3), the flask and the filter cake were rinsed with 50 ml of toluene. The filtrate was evaporated to dryness to give 16.6 g (ca. 100%) of chloro[2-methyl-4-(3,5-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane as yellowish oil which was used without further purification.

20 25 1H NMR ($CDCl_3$): δ 7.36 (s, 1H), 7.30 (s, 1H), 7.23 (s, 2H), 6.58 (s, 1H), 3.57 (s, 1H), 3.05-2.93 (m, 2H), 2.93-2.83 (m, 2H), 2.21 (s, 3H), 2.10-2.01 (m, 2H), 1.36 (s, 18H), 0.45 (s, 3H), 0.20 (s, 3H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 150.02, 144.42, 142.12, 141.53, 139.93, 139.91,

- 84 -

138.77, 131.40, 127.00, 123.93, 120.15, 118.63, 49.77, 34.88, 33.31, 32.50, 31.56, 26.03, 17.71, 1.25, -0.53.

5 **[2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane**



⁷BuLi in hexanes (2.43 M, 15.0 ml, 36.45 mmol) was added in one portion to a solution of 12.7 g (36.44 mmol) of 2-methyl-5-*tert*-butyl-6-methoxy-7-(4-*tert*-butylphenyl)-1*H*-indene in 200 ml of ether at -50°C. This mixture was stirred overnight at room temperature, then the 10 resulting yellowish slurry with a large amount of precipitate was cooled to -40°C and 100 mg of CuCN was added. The obtained mixture was stirred for 0.5 h at -25°C, then a solution of 16.6 g (ca. 36.45 mmol) of chloro[2-methyl-4-(3,5-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane in 150 ml of ether was added in one portion. This mixture was stirred overnight at room temperature, then filtered through a pad of silica gel 60 (40-63 µm) 15 which was additionally washed with 2×50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure, and the residue was dried in vacuum at elevated temperature. This procedure gave 27.78 g (ca. 100%) of [2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-*s*-indacen-1-yl]dimethylsilane (ca. 95% purity by NMR, approx. 1:1 mixture of 20 stereoisomers) as yellowish glass which was used without further purification.

¹H NMR (CDCl₃): δ 7.54-7.20 (set of signals, sum 9H), 6.59 (s, 1H), 6.51 (s, 1H), 3.74, 3.69, 3.68 and 3.67 (4s, sum 2H), 3.23 and 3.22 (2s, sum 3H), 3.05-2.83 (m, 4H), 2.22 and 2.16


- 85 -

(2s, sum 6H), 2.11-1.99 (m, 2H), 1.44 and 1.41 (2s, sum 9H), 1.39 and 1.37 (2s, sum 27H), -0.18, -0.19 and -0.22 (3s, sum 6H). $^{13}\text{C}\{\text{H}\}$ NMR (CDCl_3): δ 155.52, 149.97, 149.95,

149.43, 147.47, 146.01, 145.79, 144.10, 144.06, 143.79, 143.75, 142.15, 142.11, 139.65, 139.53, 139.40, 139.32, 139.18, 139.15, 139.04, 139.00, 137.14, 137.09, 135.26, 131.29,

5 129.77, 127.29, 127.27, 126.34, 126.27, 126.00, 125.05, 124.01, 120.62, 120.55, 120.04, 120.01, 118.49, 118.25, 60.52, 60.48, 47.42, 47.35, 46.92, 46.72, 35.17, 34.89, 34.57, 33.40, 33.35, 32.49, 31.58, 31.50, 31.28, 31.23, 26.04, 26.02, 18.09, 17.97.

Anti-dimethylsilanediyl[2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-di-*tert*-butylphenyl)-5,6,7-trihydro-s-indacen-1-yl]zirconium dichloride MC-IE-6



$^n\text{BuLi}$ in hexanes (2.43 M, 30 ml, 72.9 mmol) was added in one portion to a solution of 27.78 g (36.4 mmol) of [2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl-1*H*-inden-1-yl][2-methyl-4-(3,5-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilane (as prepared above) in 300 ml of ether cooled to -50°C . This mixture was stirred overnight at room temperature; the resulting red solution was then cooled to -50°C and 8.49 g (36.43 mmol) of ZrCl_4 was added. The reaction mixture was stirred for 24 h at room temperature to give an orange slurry (red solution with orange precipitate). This mixture was evaporated to dryness. The residue was heated with 150 ml of toluene, and the formed suspension was filtered through glass frit (G4). The filtrate was evaporated to 80 ml and heated to get a clear solution. Light-red crystals precipitated from this solution overnight at room temperature were collected and dried under vacuum. This procedure gave 8.3 g of

- 86 -

syn-zirconocene as a solvate with toluene (x 1 PhMe) contaminated with ca. 2% of *anti*-isomer. The mother liquor was evaporated to ca. 60 ml, 15 ml of n-hexane was added, and the resulting mixture was heated to get a clear solution. Yellow crystals precipitated from this solution overnight at room temperature were collected and dried in vacuum. This procedure

5 gave 6.1 g of *anti*-zirconocene contaminated with ca. 2% of *syn*-isomer. The mother liquor was evaporated to ca. 30 ml, the resulting suspension was heated to ca. 100°C and was filtered while hot via glass frit (G3). The obtained solid was dried under vacuum to give 2.4 g of *anti*-zirconocene contaminated with less than 1% of *syn*-isomer. The mother liquor was evaporated to dryness, and the obtained residue was recrystallized from a mixture of 20 ml of


10 toluene and 5 ml of n-hexane to give 8.4 g of a ca. 28 to 72 mixture of *anti*- and *syn*-zirconocenes. Thus, the total yield of *anti*- and *syn*-zirconocenes isolated in this synthesis was 25.2 g (75%).

Anti-dimethylsilanediyl[2-methyl-4-(4-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl][2-methyl-4-(3,5-di-*tert*-butylphenyl)-5,6,7-trihydro-*s*-indacen-1-yl]zirconium dichloride:

Anal. calc. for C₅₄H₆₈Cl₂OSiZr: C, 70.24; H, 7.42. Found: C, 70.52; H, 7.70.

¹H NMR (CDCl₃): δ 7.61-7.30 (set of signals, sum 9H), 6.71 (s, 1H), 6.56 (s, 1H), 3.38 (s, 3H), 3.12-3.01 (m, 1H), 3.01-2.88 (m, 2H), 2.88-2.76 (m, 1H), 2.19 (s, 3H), 2.17 (s, 3H), 2.12-1.88 (m, 2H), 1.38 (s, 9H), 1.34 (s, 27H), 1.29 (s, 3H), 1.28 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 159.92, 150.25, 150.00, 144.60, 143.92, 143.11, 137.55, 135.17, 134.00, 133.83, 133.76, 133.39, 133.21, 129.29, 126.92, 126.77, 125.31, 123.68, 123.09, 121.36, 121.21, 120.82, 117.84, 81.87, 81.42, 62.71, 35.74, 35.00, 34.62, 33.27, 32.45, 31.58, 31.42, 30.42, 26.64, 18.46, 18.29, 2.73, 2.60.


25 **Synthesis of comparative metallocene MC-CE1**



- 87 -

MC-CE1 (*rac*-*anti*-dimethylsilanediyl(2-methyl-4-(4-*tert*-butylphenyl) inden-1-yl)(2-methyl-4-(4'-*tert*-butylphenyl)-5-methoxy-6-*tert*-butyl inden-1-yl) zirconium dichloride) was synthetized according to the procedure as decribed in WO WO2013007650, E7.


Synthesis of comparative metallocene MC-CE2



5

MC-CE2 (*rac*-*anti*-dimethylsilanediyl(2-methyl-4-(4'-*tert*-butylphenyl) inden-1-yl)(2-methyl-4-phenyl-5-methoxy-6-*tert*-butyl inden-1-yl) zirconium dichloride) was synthetized according to the procedure as decribed in WO WO2013007650, E2.

Synthesis of comparative metallocene MC-CE3



10


MC-CE3 (*rac*-dimethylsilanediylbis[2-methyl-4-(4-*tert*-butylphenyl)indenyl] zirconium dichloride) was synthetized according to the procedure as described in WO98040331, example 65.

15

20

- 88 -


Synthesis of comparative metallocene MC-CE4



MC-CE4 (*rac-anti*-dimethylsilanediyl[2-methyl-4-(3',5'-di-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3',5'-di-*tert*-butylphenyl)-5-methoxy-6-*tert*-butylinden-1-yl]zirconium dichloride) was synthetized according to the procedure as described in WO2015158790, example C2-Zr.

5

Synthesis of comparative metallocene MC-CE5



10 MC-CE5 (*rac*- μ -{bis-[η^5 -2-methyl-4-(4-*tert*-butylphenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl]dimethylsilanediyl}dichlorozirconium) was prepared as described in WO2006/097497A1. The 1 H NMR spectrum of it corresponds to that reported in the mentioned patent application.














15 Comparative metallocene MC-CE6 and comparative metallocene MC-CE7 are made analogously.

15

20

- 89 -

Summary of Examples

MC-CE1	MC-CE2	MC-CE3	MC-CE4
			
MC-CE5	MC-CE6	MC-CE7	
			
MC-IE1	MC-IE2	MC-IE3	MC-IE4
			
MC-IE5	MC-IE6		
			

- 90 -

Non supported Catalyst preparation examples

Materials

5 Inventive metallocenes MC-IE1, MC-IE2, MC-IE3, MC-IE4, MC-IE5 and MC-IE6 and
comparative metallocenes MC-CE1, MC-CE2, MC-CE3, MC-CE4, MC-CE5, MC-CE6 and
MC-CE7 as described above were used in preparing catalysts. MAO was used as a 30 wt-%
solution in toluene. Trityl tetrakis(pentafluorophenyl)borate (Boulder Chemicals) was used
as purchased. As surfactants were used perfluoroalkylethyl acrylate esters (CAS number
10 65605-70-1) purchased from the Cytonix corporation, dried over activated molecular sieves
(2 times) and degassed by argon bubbling prior to use (S1) or 1H,1H-Perfluoro(2-methyl-3-
oxahexan-1-ol) (CAS 26537-88-2) purchased from Unimatec, dried over activated molecular
sieves (2 times) and degassed by argon bubbling prior to use (S2). Hexadecafluoro-1,3-
15 dimethylyclohexane (PFC) (CAS number 335-27-3) was obtained from commercial sources
and dried over activated molecular sieves (2 times) and degassed by argon bubbling prior to
use. Propylene is provided by Borealis and adequately purified before use. Triethylaluminum
was purchased from Crompton and used in pure form. Hydrogen is provided by AGA and
purified before use.

All the chemicals and chemical reactions were handled under an inert gas atmosphere using
20 Schlenk and glovebox techniques, with oven-dried glassware, syringes, needles or cannulas.

Catalyst Example IE1

Inside the glovebox, 85.9 mg of dry and degassed surfactant S2 was mixed with 2 mL of
MAO in a septum bottle and left to react overnight. The following day, 43.9 mg MC-IE1
25 (0,076 mmol, 1 equivalent) was dissolved with 4 mL of the MAO solution in another septum
bottle and left to stir inside the glovebox.

After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant
solution were successively added into a 50 mL emulsification glass reactor containing 40 mL
of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total
30 amount of MAO is 5 mL (450 equivalents). A red emulsion formed immediately and stirred
during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube
to 100 mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the
speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the

- 91 -

stirrer turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.62 g of a red free flowing powder was obtained.

5 Catalyst Example IE-2:

Inside the glovebox, 86.2 mg of dry and degassed surfactant S2 was mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 41.1 mg MC-IE2 (0,076 mmol, 1 equivalent) was dissolved with 4 mL of the MAO solution in another septum bottle and left to stir inside the glovebox.

10 After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant solution were successively added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total amount of MAO is 5 mL (450 equivalents). A red emulsion formed immediately and stirred during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube
15 to 100 mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.54 g of a red free flowing powder was obtained.

20

Catalyst Example IE-3: Inside the glovebox, 85.3 mg of dry and degassed surfactant S2 was mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 42.4 mg MC-IE-3 (0,076 mmol, 1 equivalent) were dissolved with 4 mL of the MAO
25 solution in another septum bottle and left to stir inside the glovebox.

After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant solution were successively added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total amount of MAO is 5 mL (450 equivalents). A red emulsion formed immediately and stirred
30 during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100 mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the

- 92 -

stirrer turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.52 g of a red free flowing powder was obtained.

5 Catalyst Example IE- 3.1b

Inside the glovebox, 234.3 mg of S2 surfactant solution (14 wt% in toluene) was added dropwise to 5 mL of 30 wt.-% MAO. The solutions were left under stirring for 30 min. Then, around 95.6 mg of metallocene MC-IE3 (0.114 mmol, 1 equivalent) was added to MAO/surfactant solution and the solution was stirred for 60 minutes. Then 104.9 mg of trityl 10 tetrakis(pentafluorophenyl)borate was added. The mixture was left to react at room temperature inside the glovebox for 60 minutes.

Then, 5 mL of catalyst solution were added into a 50 mL emulsification glass reactor containing 40mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). A red emulsion formed immediately and stirred during 15 minutes at -10 °C / 15 600rpm. Then the emulsion was transferred via a 2/4 Teflon tube to 100 mL of hot PFC at 90 °C and stirred at 600rpm until the transfer is completed. Then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 35 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.70 g 20 of a red free flowing powder was obtained.

Catalyst Example IE4

Inside the glovebox, S2 surfactant solution (27.6 mg of dry and degassed S2 dilute in 0.2 mL 25 toluene) was added dropwise to 5 mL of 30 wt.-% MAO. The solution was left under stirring for 10 min. Then, around 46.7 mg of metallocene MC-IE4 was added to 5 ml MAO/surfactant solution and the solution was stirred for 60 minutes. Then, the MAO/MC-IE-4/S2 solution (5.2 mL) was added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). A red 30 emulsion formed immediately and stirred during 15 minutes at -10 °C / 600rpm. Then the emulsion was transferred via a 2/4 Teflon tube to 100 mL of hot PFC at 90 °C and stirred at 600rpm until the transfer is completed. Then the speed was reduced to 300 rpm. After 15

- 93 -

minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle on top of the PFC and after 35 minutes, the solvent was siphoned off. The remaining nice red catalyst was dried during 2 hours at 50 °C over an argon flow.

5

Comparative Catalyst example CE-1 Inside the glovebox, 80 μ l of dry and degassed surfactant S1 was mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 66.3 mg MC-CE1(0,076 mmol, 1 equivalent) was dissolved with 4 mL of the MAO solution in another septum bottle and left to stir inside the glovebox.

10 After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant solution were successively added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total amount of MAO is 5 mL (300 equivalents). A red emulsion formed immediately and stirred during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100 mL
15 of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.31 g of a red free flowing powder was obtained.

20

Comparative Catalyst example CE-1b (same metallocene as comparative example CE-1)

Inside the glovebox, 85.6 mg of dry and degassed S2 were mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 44.2 mg of MC-CE1 (0,051 mmol, 1 equivalent) were dissolved with 4 mL of the MAO solution in another septum bottle
25 and left to stir inside the glovebox.

After 60 minutes, 1 mL of the surfactant solution and the 4 mL of the MAO-metallocene solution were successively added into a 50mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). *Total amount of MAO is 5 mL (300 equivalents)*. A red emulsion formed immediately and stirred during 15 minutes at -10 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, and then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed

- 94 -

and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 35 minutes the solvent was siphoned off. The remaining catalyst was dried during 2 hours at 50 °C over an argon flow. 0.75 g of a red free flowing powder was obtained.

5 Comparative Catalyst example CE-2

Inside the glovebox, 80 µl of dry and degassed surfactant S1 was mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 58.7 mg MC-CE2 (0,076 mmol, 1 equivalent) were dissolved with 4 mL of the MAO solution in another septum bottle and left to stir inside the glovebox.

10 After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant solution were successively added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total amount of MAO is 5 mL (300 equivalents). A red emulsion formed immediately and stirred during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100 mL
15 of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.52 g of a red free flowing powder was obtained.

20

Comparative Catalyst example CE-3

Inside the glovebox, 80 µl of dry and degassed surfactant S1 was mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 56.2 mg MC-CE3 (0,076 mmol, 1 equivalent) was dissolved with 4 mL of the MAO solution in another septum bottle
25 and left to stir inside the glovebox.

After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant solution were successively added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total amount of MAO is 5 mL (300 equivalents). A red emulsion formed immediately and stirred during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100 mL
30 of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer

- 95 -

turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C over an argon flow. 0.56 g of a red free flowing powder was obtained.

5 Comparative Catalyst example CE-4

Inside the glovebox, 80 μ l of dry and degassed surfactant S1 was mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 73.0 mg MC-CE4 (0,076 mmol, 1 equivalent) were dissolved with 4 mL of the MAO solution in another septum bottle and left to stir inside the glovebox.

10 After 60 minutes, 4 mL of the MAO-metallocene solution and 1 mL of the surfactant solution were successively added into a 50 mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). Total amount of MAO is 5 mL (300 equivalents). A red emulsion formed immediately and stirred during 15 minutes at 0 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100 mL
15 of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 45 minutes the solvent was siphoned off. The remaining red catalyst was dried during 2 hours at 50 °C under an argon flow. 0.50 g of a red free flowing powder was obtained.

20 Comparative Catalyst example CE-5

Inside the glovebox, 85.7 mg of dry and degassed S2 were mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 38.0 mg of MC-CE5 (0,051 mmol, 1 equivalent) were dissolved with 4 mL of MAO in another septum bottle and left to stir inside the glovebox.

25 After 60 minutes, 1 mL of the surfactant solution and the 4 mL of the MAO-metallocene solution were successively added into a 50mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). *Total amount of MAO is 5 mL (300 equivalents)*. A red emulsion formed immediately and stirred during 15 minutes at -10 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, and then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 35

- 96 -

minutes the solvent was siphoned off. The remaining catalyst was dried during 2 hours at 50 °C over an argon flow. 0.66 g of a red free flowing powder was obtained.

Comparative Catalyst example CE-6

5 Inside the glovebox, 85.7 mg of dry and degassed S2 were mixed with 2 mL of MAO in a septum bottle and left to react overnight. The following day, 58.1 mg of MC-CE6 (0,051 mmol, 1 equivalent) were dissolved with 4 mL of MAO in another septum bottle and left to stir inside the glovebox.

10 After 60 minutes, 1 mL of the surfactant solution and the 4 mL of the MAO-metallocene solution were successively added into a 50mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). *Total amount of MAO is 5 mL (300 equivalents)*. A red emulsion formed immediately and stirred during 15 minutes at -10 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon tube to 100mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, and 15 then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 35 minutes the solvent was siphoned off. The remaining catalyst was dried during 2 hours at 50 °C over an argon flow. 0.60 g of a red free flowing powder was obtained.

20 Comparative Catalyst Example CE-7

Inside the glovebox, 72.0 mg of dry and degassed S2 were mixed with 2 mL MAO in a septum bottle and left to react overnight. The following day, 39.8 mg of MC-CE7 (0,051 mmol, 1 equivalent) were dissolved with 4 mL of MAO in another septum bottle and left to stir inside the glovebox.

25 After 60 minutes, 1 mL of the surfactant solution and the 4 mL of the MAO-metallocene solution were successively added into a 50mL emulsification glass reactor containing 40 mL of PFC at -10 °C and equipped with an overhead stirrer (stirring speed = 600 rpm). *Total amount of MAO is 5 mL (300 equivalents)*. A red emulsion formed immediately and stirred during 15 minutes at -10 °C / 600 rpm. Then the emulsion was transferred via a 2/4 teflon 30 tube to 100mL of hot PFC at 90 °C, and stirred at 600 rpm until the transfer is completed, and then the speed was reduced to 300 rpm. After 15 minutes stirring, the oil bath was removed and the stirrer turned off. The catalyst was left to settle up on top of the PFC and after 35

- 97 -

minutes the solvent was siphoned off. The remaining catalyst was dried during 2 hours at 50 °C over an argon flow. 0.72 g of a red free flowing powder was obtained.

5 Table 1. Catalyst synthesis summary and elemental analysis

Metallocene	Cat Ex	ICP Zr (wt.-%)	Al/Zr (mol/mol)
MC-IE1	IE1	0.27	453
MC-IE2	IE2	0.26	479
MC-IE3	IE3	0.26	481
MC-IE3	IE3b	0.50	215
MC-IE4	IE4	0.26	479
MC-CE1	CE1	0.35	291
MC-CE1	CE1b	0.31	421
MC-CE2	CE2*	0.41	283
MC-CE3	CE3	0.40	294
MC-CE4	CE4	0.33	335
MC-CE5	CE5	0.28	474
MC-CE6	CE6	0.37	346
MC-CE7	CE7	0.28	423

*CE2 Zr content (ICP) was re-measured over WO2013/007650 (E2).

Silica Supported Catalyst Examples:

10 The silica-MAO catalysts have been prepared on 30μ SUNSPERA DM-L-303 silica produced by AGC Si-Tech Co, previously calcined at 600°C for 2 hours in an Electric Muffle Furnace under a flow of dry air.

Preparation of silica supported metallocene catalyst (Silica-IE1)

Step-1

15 Toluene was dried over molecular sieves and degassed by bubbling with argon for at least 30 minutes.

Inside the glovebox, 6.3 g of the calcined silica was charged into a round-bottom flask equipped with an overhead stirrer and a sealed septum, and then ~30 mL of dry and degassed toluene was added into it. The resulting suspension was cooled down to 0 °C under mild stirring (200 – 300 rpm) and 16 mL of MAO solution added dropwise.

20 After around 20 minutes, the cooling bath was removed and stirring was continued for 2 hours. The silica-MAO slurry was allowed to settle and then the supernatant toluene solution

- 98 -

was siphoned off via a 2/4 teflon tube. Then, around 20 mL of dried and degassed toluene was added and the slurry was stirred for 15 minutes at room temperature.

The flask was placed into the oil bath and warmed up to 80 °C and the slurry solution was stirred for additional 30 min. Then the silica-MAO slurry was again allowed to settle for 10 5 min. The hot toluene solution was siphoned off.

This washing procedure was repeated one more time, and then an additional washing has been performed using toluene (20 ml pentane, stirring 15 min). The toluene layer was siphoned off, then the solid was dried under argon flow at room temperature for about 3 h. The white flowing MAO-silica powder was collected and used for supported catalyst 10 preparation Silica-IE1.

Step-2

Inside the glove box, 0.25 mL of MAO solution was added to MC-IE1 solution (30 mg of MC-IE1 in 1 ml of toluene) in a septum bottle.

1 g of dry silica-MAO powder was placed into a 20 mL glass vial, and then ~5 mL of dry and 15 degassed toluene was added into it. Then the complex solution was added and the slurry solution was stirred for 60 minutes at room temperature and the resulting slurry was allowed to stand overnight in the glove box. Then 5 mL of dried and degassed toluene was added; the bath temperature was set to 40°C and stirred for 60 minutes. The solid catalyst was allowed to settle, and then the toluene layer was removed. Then another 5 mL of dried and degassed 20 toluene was added; the bath temperature was set to 60°C and stirred for 2 hours minutes. The solid catalyst was allowed to settle, and then the toluene layer was removed. Then three additional washing step has been performed at room temperature using 5 ml of dry toluene and the toluene layer was siphoned off and then the solid was dried under argon flow at room temperature for 3 h. 0.967 g of a red silica supported flowing powder was collected.

25 **Preparation of silica supported metallocene catalyst (Silica-IE2)**

Step 1

Toluene was dried over molecular sieves and degassed by bubbling with argon for at least 30 minutes. Inside the glovebox, 10 g of the calcined silica was charged into a round-bottom flask equipped with an overhead stirrer and a sealed septum, then ~50 mL of dry and 30 degassed toluene was added into it. The resulting suspension was cooled down to 0 °C under

- 99 -

mild stirring (200 – 300 rpm) by means of a cooling bath. 25 mL of a 30 wt-% MAO solution in toluene was slowly added with a dry and degassed syringe or by siphonation onto the silica suspension (dropwise, adding time~ 1h). Then the cooling bath was removed and stirring was continued for 2 hours. The silica-MAO slurry was allowed to settle and then the supernatant

5 toluene solution was siphoned off with an oven-dried cannula.

~30 mL of dried and degassed toluene was added, the slurry was stirred for 15 minutes at room temperature, then the flask was placed into the oil bath and warmed up to 80 °C.

Stirring was continued for additional 15 min, then the slurry was again allowed to settle for 10 min. The hot toluene solution was siphoned off from the top of the settled silica-MAO

10 layer. This washing procedure was repeated one more time, and then an additional washing has been performed using pentane (30ml pentane, stirring 15 min, settling 10min). The pentane layer was siphoned off, then the solid was dried under argon flow at room temperature (20-25°C) for about 3 h and finally the flask was placed in a water bath (+50°C) and the last residues of solvent were removed under argon flow through silica-MAO solid

15 layer. During the final drying steps the silica-MAO solid turned into an easily flowing powder.

This MAO-silica activated carrier was used to prepare catalyst Silica-IE2 (and to prepare Silica-CE1, and Silica-CE2).

Step 2

20 Preparation of complex solution. Inside a glove box, 0.25 mL of the toluene-MAO solution was added to a solution of 23 mg of rac-anti-dimethylsilanediyl[2-methyl-4-(3'5'-dimethyl phenyl)-1,5,6,7-tetrahydro-s-indacen-1-yl][2-methyl-4-(3'5'-dimethylphenyl)-5-methoxy-6-tertbutylinden-1-yl]zirconiumdichloride metallocene (MC-IE2) in 1 ml of toluene in a septum bottle.

25 1 g of the previously prepared silica-MAO dry powder was placed into a 20 mL glass vial, and the complex solution was added. The resulting slurry was allowed to stand overnight in the glove box. 5 mL of dried and degassed toluene was added; the bath temperature was set to 60°C and stirred for 30 minutes. The solid catalyst was allowed to settle, and then the toluene layer was removed by syringe. The washing step was repeated twice more (2x5 mL toluene).

30 The solid was allowed to cool down to room temperature and one final washing step was carried out by adding 5 ml of dry pentane, stirring the slurry gently for 30 min, allowing the

- 100 -

catalyst to settle, and finally removing pentane by syringe and drying the solid under argon flow for 3 h.

Preparation of silica supported metallocene catalyst (Silica-CE2)

Preparation was carried out as for catalyst Silica-IE2 but using 32 mg of metallocene MC-

5 CE2

Preparation of silica supported metallocene catalyst (Silica-CE1)

Preparation was carried out as for catalyst Silica-IE2 but using 30 mg of metallocene MC-CE1

The available composition data of the catalysts from ICP are listed in Table 1.

10

Table 1. Composition data of the catalysts used in this investigation

Catalyst	MC	Zr (wt%)	Al (wt%)	Al/Zr (molar)	MC (wt%)
Silica-CE2	MC-CE2	0,20	14,8	250	1,69
Silica-CE1	MC-CE1	0,18	14,8	280	1,63
Silica-IE1	MC-IE1	0,27	17,7	220	2,57
Silica-IE2	MC-IE2	0,19	15,3	270	1,69

Polymerisation examples

15

Homopolymerisation of propylene with unsupported metallocenes

The polymerisations were performed in a 5 L reactor. 200 μ l of triethylaluminum was fed as a scavenger in 5 mL of dry and degassed pentane. The desired amount of hydrogen was then loaded (measured in mmol) and 1100 g of liquid propylene was fed into the reactor. The

20 temperature was set to 20 °C. The desired amount of catalyst (5 to 15 mg) in 5mL of PFC is flushed into the reactor with a nitrogen overpressure. After 5 minutes prepolymerisation, the temperature is raised to 70 °C over a period of 15 minutes. The polymerisation is stopped after 60 minutes by venting the reactor and flushing with nitrogen before the polymer is collected. Polymerisation conditions and results are disclosed in Table 2.

25

C_3/C_2 random copolymerisation with unsupported metallocenes

The polymerisations were performed in a 5 L reactor. 200 μ l of triethylaluminum was fed as a scavenger in 5 mL of dry and degassed pentane. The desired amount of hydrogen (6 mmol)

- 101 -

was then loaded and 1100 g of liquid propylene was fed into the reactor. Desired amount of ethylene was fed in to the reactor. The temperature was set to 30 °C. The desired amount of catalyst (5 to 20 mg) in 5mL of PFC is flushed into the reactor with a nitrogen overpressure.

The temperature is then raised to 70 °C over a period of 15 minutes. The polymerisation is

5 stopped after 30 minutes by venting the reactor and flushing with nitrogen before the polymer is collected.

The catalyst activities were calculated on the basis of the 60 minute (homopolymerisation of propylene) or 30 minute (C₃/C₂ random copolymerisation) period according to the following formula:

10

$$\text{Catalyst Activity (kg-PP/g-Cat/h)} = \frac{\text{amount of polymer produced (kg)}}{\text{catalyst loading (g)} \times \text{polymerisation time (h)}}$$

Polymerisation results of C₃/C₂ random copolymerisations are collected in Table 3.

Performance of the inventive examples with comparison to the closest references is

15 summarised in Figures 1- 5. The best overall performance is obtained with the new metallocenes of the invention: high activity in homopolymerisation and in C₃/C₂ random copolymerisation, good homopolymer melting temperature and good molecular weight capability. Most importantly, ethylene has a strong positive effect on Mw with the catalysts of the invention

Polymer analysis

Table 2 Propylene homopolymerisation in liquid propylene. Polymerisation time 60 minutes. $T_p = 70^\circ\text{C}$.

Run #	Catalyst Amt (mg)	H2 (mmol)	Yield (g)	Activity (kg-PP/g-Cat/h)	Metal activity (kg-PP/g-Zr/h)	Mw (kg/mol)	Mw/Mn	T_m (°C)	2,1ε (%)	mmmm (%)
IE 1.1	9.1	6	372	40.8	15128	516	2.5	150.9	0.96	99.59
IE 2.1	8.1	6	322	39.7	15266	514	2.6	150.4	0.93	99.70
IE 3.1	7.7	6	250	32.5	12493	510	2.7	150.8	0.91	99.61
IE 3.1b	6.7	6	463	69.1	13926	521	2.5	156.4	-	-
CE 1.1	9.8	6	479	48.8	13956	472	2.2	149.4	1.09	99.77
CE 2.1	10.0	6	298	29.8	7268	486	2.3	146.9	n.d.	n.d.
CE 3.1	10.0	6	269	26.9	6720	418	2.3	151.0	0.92	99.38
CE 4.1	8.7	6	213	24.4	7409	233	2.8	156.2	0.54	99.44

Table 3. Ethylene-propylene random copolymerisations (with hydrogen, 6 mmol). Polymerisation time 30 minutes. $T_p = 70^\circ\text{C}$.

Run #	Catalyst Amt (mg)	C2 (g)	Yield (g)	Activity (kg-PP/g-Cat/h)	Metal activity (kg-PP/g-Zr/h)	Mw (kg/mol)	Mw/Mn	T_m (°C)	NMR C2 (wt.-%)
IE 1.2	7.5	50.0	247.7	66.1	24464	702	2.6	119.4	4.22
IE 3.2	8.1	50.0	433.3	107.0	41149	720	2.7	121.4	4.06
CE 1.2	7.6	49.9	199	52.4	14962	517	2.4	120.3	4.15
CE 2.2	15.0	49.9	236	31.4	7665	504	2.6	119.3	3.58
CE 3.2	8.7	50.0	85	19.6	4908	297	2.4	124.3	3.55
CE 4.2	9.1	50.5	176	38.6	11688	246	2.3	113.4	5.17

Polymerisation examples with offline prepolymerised catalyst.

Off-line prepolymerization (“prepping”) procedure

5 The **CE5** catalyst was pre-polymerised according to the following procedure: Off-line pre-polymerisation experiment was done in a 125 mL pressure reactor equipped with gas-feeding lines and an overhead stirrer. Dry and degassed perfluoro-1,3-dimethylcyclohexane (15 cm³) and the desired amount of the catalyst (**CE5**, 398.7 mg) to be pre-polymerised were loaded into the reactor inside a glove box and the reactor was sealed. The reactor was then taken out from the glove box and placed inside a water cooled bath kept at 25 °C. The overhead stirrer and the feeding lines were connected and stirring speed set to 450 rpm. The experiment was started by opening the propylene feed into the reactor. The total pressure in the reactor was raised to about 5 barg and held constant by propylene feed via mass flow controller 10 until the target degree of polymerisation was reached. The reaction was stopped by flashing the volatile components. Inside glove box, the reactor was opened and the content poured into a glass vessel. The perfluoro-1,3-dimethylcyclohexane was evaporated until a constant weight was obtained to yield 1.8057 g of the pre-polymerised catalyst.

15

15 The catalysts listed in the table 4 below were prepolymerised as described in the above procedure.

Table 4: prepolymerisation of catalysts (pp = offline prepolymerised)

Catalyst - name	Catalyst weighed amount (mg)	Yield (g)	Prep-degree (g Pol/g-Cat)
ppCE5	398.7	1.8057	3.5
ppCE6	393.3	1.6514	3.2
ppCE1b	400.3	1.8622	3.7
ppCE7	399.5	1.7488	3.4
ppIE1	399.5	1.8154	3.5
ppIE3	408.6	1.8096	3.4
ppIE2	402.0	1.6670	3.2

The polymers have been produced in a 20-L reactor following three different procedures, as described in Table 5.

5 Table 5. Polymerisation procedures

procedure	step s	bulk			Time min	GP1				GP2			
		T °C	H2 NL	P barg		T °C	Time min	H2 NL	P barg	T °C	Time min	C2/C3 wt/wt	
1	2	80	1.5	~40					20	70	~70	0.25	
2	3	80	1.5	40	24	80	60	1.2	20	70	90	0.25	
3	3	80	1.5	40	24	80	60	1.2	20	70	90- 120	1.00	

The details of the polymerisation procedures are described in the following:

Procedure 1: 2-step polymerisation

10 *Step 1: Prepolymerisation and bulk homopolymerisation*

A 21.2 L stainless-steel reactor containing 0.4 barg propylene was filled with 3950 g propylene. Triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was injected into the reactor by additional 240 g propylene. The solution was stirred at 20 °C and 250 rpm for at least 20 min. The catalyst was injected as described in the following. The desired amount of solid, prepolymerised catalyst was loaded into a 5 ml stainless steel vial and a second 5 ml vial containing 4 ml n-heptane was added on top inside a glovebox. Then the vial on top was pressurized with 10 bars of nitrogen and attached to the autoclave. The valve between the two vials was opened and the solid catalyst was contacted with n-heptane under nitrogen pressure for 2 s, and then flushed into the reactor with 240 g propylene. The prepolymerisation was run for 10 min. At the end of the prepolymerisation step the temperature was raised to 80 °C. When the internal reactor temperature has reached 71°C, 1.5 NL of H2 was added via mass flow controller in one minute. The reactor temperature was held constant at 80°C throughout the polymerisation. The polymerisation time was

measured starting when the internal reactor temperature reached 2 °C below the set polymerisation temperature.

Jacket T constraints: during the transition between prepolymerisation and target reactor temperature, the jacket temperature is controlled with a cooling device (HB-Therm).

5 The set temperature limits to prevent overheating of the reactor were:

dTSW: Defines the maximum temperature of the jacket liquid

Set = max10°C >target temperature

dTIW: Defines the maximum temperature difference between jacket and reactor

10 during heating .

Set= max35°C > actual temperature

Step 2: gas phase C3C2 r-PP.polymerisation

After the bulk step was completed, the stirrer speed was reduced to 50 rpm and the pressure was reduced down to 0.3 bar-g by venting the monomers. Then

15 triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was injected into the reactor by additional 250 g propylene through a steel vial. The pressure was then again reduced down to 0.3 bar-g by venting the monomers. The stirrer speed was set to 180 rpm and the reactor temperature was set to 70 °C. Then the reactor pressure was increased to 20 bar-g by feeding a C3/C2 gas mixture (C2/C3=0.74 wt/wt).

20 Pressure and temperature were held constant by feeding via mass flow controller a C3/C2 gas mixture (of composition corresponding to the target polymer composition) and by thermostat, until the set time for this step had expired.

Then the reactor was cooled down (to about 30°C) and the volatile components flashed out. After flushing the reactor 3 times with N2 and one vacuum/N2 cycle,

25 the product was taken out and dried overnight in a fume hood. 100g of the polymer is additivated with 0.5 wt% Irganox B225 (solution in acetone) and dried overnight in a hood followed by 2 hours in a vacuum drying oven at 60°C.

Jacket T constraints. During the transition between bulk and gas phase temperature, the jacket temperature is controlled with a cooling device (HB-Therm). The set

30 temperature limits to prevent overheating of the reactor were:

- 106 -

dTSW: Defines the maximum temperature of the jacket liquid
Set = max10°C >target temperature
dTIW: Defines the maximum temperature difference between jacket and reactor
during heating .

5 Set= max35°C > actual temperature.

Procedure 2: 3-step polymerisation

Step 1: Prepolymerisation and bulk homopolymerisation

Step 1 was performed as described in procedure 1 above.

10 *Step 2: gas phase homopolymerisation*

After the bulk step was completed, the stirrer speed was reduced to 50 rpm and the pressure was reduced to 23 bar-g by venting the monomer. Afterwards the stirrer speed was set to 180 rpm, the reactor temperature to 80 °C and the pressure to 24 bar-g. Hydrogen (1.2 NL) was added via flow controller in one minute. During the 15 gas phase homopolymerisation, both pressure and temperature have been held constant via mass flow controller (feeding propylene) and thermostat for 60 minutes.

Step 3: gas phase ethylene-propylene copolymerisation

Step 3 was performed as step 2 of procedure 1 described above. Differences:

Feeding a C2/C3 gas mixture of C2/C3=0,56(wt/wt) in the transition. Polymerisation

20 in this step was run for 90 min.

Procedure 3: 3-step polymerisation

Step 1: Prepolymerisation and bulk homopolymerisation

The autoclave containing 0.4 barg propylene was filled with 3970 g propylene.

25 Triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was injected into the reactor by additional 240 g propylene. The solution was stirred at 20 °C and 250 rpm for at least 20 min. The catalyst was injected as described in the following. The desired amount of solid, prepolymerised catalyst was loaded into a 5 ml stainless steel vial and a second 5 ml vial containing 4 ml n-heptane was added on top inside 30 a glovebox. Then the vial on top was pressurized with 10 bars of nitrogen and attached to the autoclave. The valve between the two vials was opened and the solid

catalyst was contacted with n-heptane under nitrogen pressure for 2 s, and then flushed into the reactor with 240 g propylene. The prepolymerisation was run for 10 min. At the end of the prepolymerisation step the temperature was raised to 80 °C. When the internal reactor temperature has reached 71°C, 1.5 NL of H2 was added

5 via mass flow controller in three minutes. The reactor temperature was held constant at 80°C throughout the polymerisation. The polymerisation time was measured starting when the internal reactor temperature reached 2 °C below the set polymerisation temperature.

Jacket T constraints. During the transition between prepolymerisation and target

10 reactor temperature, the jacket temperature is controlled with a cooling device (HB-Therm). The set temperature limits to prevent overheating of the reactor were:

dTSW: Defines the maximum temperature of the jacket liquid

Set = max10°C >target temperature

dTIW: Defines the maximum temperature difference between jacket and reactor

15 during heating .

Set= max35°C > actual temperature

Step 2: gas phase homopolymerisation

After the bulkstep was completed, the stirrer speed was reduced to 50 rpm and the

20 pressure was reduced to the desired gas phase pressure.(=target pressure-0,5) by venting the monomer. Afterwards the stirrer speed was set to 180 rpm, the reactor temperature to 80 °C and the pressure to 24barg. The desired amount of hydrogen was added via flow controller. During the gas phase homopolymerisation, both target pressure and temperature have been held constant via mass flow controller

25 (feeding propylene) and thermostat until the runtime for this step was expired.

Step 3: gas phase C3C2 r-PP.polymerisation

After the first gasphase step was completed, the stirrer speed was reduced to 50 rpm and the pressure was reduced down to 0.3 barg by venting the monomers. Then triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was injected into the

30 reactor by additional 250 g propylene through a steel vial. The pressure was then again reduced down to 0.3 barg by venting the monomers. The stirrer speed was set

- 108 -

to 180 rpm and the reactor temperature was set to 70 °C. Then the reactor pressure was increased to 20 bar-g by feeding a C3/C2 gas mixture (C2/C3=2.22 wt/wt). Pressure and temperature were held constant by feeding via mass flow controller a C3/C2 gas mixture (of composition corresponding to the target polymer composition) and by thermostat, until the set time for this step had expired.

Then the reactor was cooled down (to about 30°C) and the volatile components flashed out. After purging the reactor 3 times with N2 and one vacuum/N2 cycle, the product was taken out and dried overnight in a fume hood. 100g of the polymer is additivated with 0.5 wt% Irganox B225 (solution in acetone) and dried overnight in a hood followed by one hour in a vacuum drying oven at 60°C.

Jacket T constraints. During the transition between bulk and first gas phase and first and second gasphase, the jacket temperature is controlled with a cooling device (HB-Therm). The set temperature limits to prevent overheating of the reactor were:

dTSW: Defines the maximum temperature of the jacket liquid

15 Set = max10°C >target temperature

dTIW: Defines the maximum temperature difference between jacket and reactor during heating .

Set= max35°C > actual temperature.

20 Results are set out in tables 6 to 8.

Table 6. Two-step polymerisations (procedure 1), result summary

Metallocene	MC-CE1	MC-CE5	MC-CE6	MC-IE1	MC-IE2
Catalyst	ppCE1b	ppCE5	ppCE6	ppIE1	ppIE2
MFR whole material	9.4	5	16	4	2.5
XS_{gravim}	57	64	52	63	54
C2(XS)	24.8	27.3	27.1	27.7	24.4
iV_{EPR}	1.6	1.9	1.6	2.3	2.3

- 109 -

Table 7. Three-step polymerisations (procedure 2), result summary

Metallocene	MC-CE1	MC-CE7	MC-IE3	MC-IE2
Catalyst	ppCE1b	ppCE7	ppIE3	ppIE2
MFR whole material	9	14	9	6
Split bulk-GP1-GP2 (calc with MFC)	50-35-15	43-32-25	39-32-29	38-36-26
XS_{gravim} (XS_{Crystex})	19 (17)	31 (28)	31 (30)	27 (26)
C2(XS)	21.4	20.9	21.6	20.8
iV_{EPR}	1.6	1.9	2.3	2.4

Table 8. Three-step polymerisations (procedure 3), result summary

Metallocene	MC-CE1	MC-IE1	MC-IE3	MC-IE2
Catalyst	ppCE1b	ppIE1	ppIE3	ppIE2
MFR whole material	9.6	18.6	21.4	9.4
Split bulk-GP1-GP2 (calc with MFC)	45-37-18	40-40-20	39-43-18	44-37-19
XS_{gravim} (XS_{Crystex})	20 (20)	20 (20)	17 (18)	20 (20)
C2(XS)	47.9	47.0	47.6	47.3
iV_{EPR}	1.7	2.1	2.0	2.2

5

The results clearly indicate that the catalysts ppIE1, ppIE2, and ppIE3 produce heterophasic copolymers having a rubber phase with a higher molecular weight than the heterophasic copolymers produced under similar conditions with the comparison catalysts.

10

The Mw/Mn of the matrix produced in the three-step experiments ranges from 4.5 to 6.2.

- 110 -

The need for a cyclopentyl ring condensed on one of the indenes is shown by comparing the iV(EPR) of the heterophasic copolymer obtained with CE1 or CE7 to those obtained with the three inventive metallocenes (Tables 6-8).

5 **Polymerisation procedure for 1-step homopolymerisation hPP in bulk (5 litre reactor) using unsupported metallocene catalyst IE4**

Polymerisation procedure

The polymerisations were performed in a 5 L reactor. 200 μ l of triethylaluminum 10 was fed as a scavenger in 5 mL of dry and degassed pentane. The desired amount of hydrogen was then loaded (mmol, see Table 9) and 1100 g of liquid propylene was fed into the reactor. The temperature was set to 20 °C. The desired amount of catalyst (5 to 15 mg) in 5mL of PFC is flushed into the reactor with a nitrogen overpressure. After 5 minutes prepolymerisation, the temperature is raised to 70 °C 15 over a period of 15 minutes. The polymerisation is stopped after 60 minutes by venting the reactor and flushing with nitrogen before the polymer is collected.

The catalyst activity was calculated based on the 60 minute period at 70 °C according to the following formula:

$$\text{Catalyst Activity (kg-PP/g-Cat/h)} = \frac{\text{amount of polymer produced (kg)}}{\text{catalyst loading (g)} \times \text{polymerisation time (h)}}$$

20 Polymerisation results are collected in Table 9.

Table 9. Results for homopolymerisation in liquid propylene experiments and for the polymer characterisation.

Polymerisation time 60 minutes. Tp = 70 °C.

Catalyst	Catalyst (mg)	H2 (mmol)	Yield (g)	Activity (kg-PP/g-Cat/h)	MFR21 (g/10min)	Tm (°C)
IE4	13.7	1	244.4	17.8	4.64	155.4
IE4	9.0	6	329.5	36.6	72.1	156.7

Polymerisation procedure for 2-step hPP in bulk + gas phase experiments using Silica supported metallocenes

Step 1: Prepolymerisation and bulk homopolymerisation

5 A 20.9 L stainless-steel reactor containing 0.4 bar-g propylene was filled with 3950 g propylene. Triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was placed into a stainless steel vial and injected into the reactor by means of a flow of 240 g propylene. 2.0 NL of H₂ was added via mass flow controller in one minute. The solution was stirred at 20 °C and 250 rpm for at least 20 min. The catalyst was 10 injected as described in the following. The desired amount of solid, prepolymerised catalyst was loaded into a 5 ml stainless steel vial inside a glovebox and a second 5 ml vial containing 4 ml n-heptane pressurized with 10 bars of nitrogen was added on top of the first vial. This catalyst feeder system was mounted on a port on the lid of the reactor, the valve between the two vials was opened and the solid catalyst was 15 contacted with heptane under nitrogen pressure for 2 s, and then flushed into the reactor with 240 g propylene. The prepolymerisation was run for 10 min. At the end of the prepolymerisation step the temperature was raised to 80 °C. The reactor temperature was held constant at 80°C throughout the polymerisation. The liquid propylene polymerisation was run for 40 minutes. The polymerisation time was 20 measured starting when the internal reactor temperature reached 2 °C below the set polymerisation temperature.

Step 2: gas phase homopolymerisation

After the bulk step was completed, the stirrer speed was reduced to 50 rpm and the pressure was reduced to 23.5 bar-g by venting the monomer. Afterwards the stirrer 25 speed was set to 180 rpm, the reactor pressure was set at 24 bar-g while keeping the reactor temperature at 80 °C, and 2.0 NL hydrogen were added via flow controller in 4 minutes. The gas phase homopolymerisation was run for 60 minutes, while keeping the pressure constant by feeding propylene via mass flow controller and the temperature constant at 80 °C by thermostat.

30 The 2-step hPP in bulk + gas phase polymerisation results with the SiO₂ supported catalysts and metallocenes CE1, CE2, IE2 are listed in Table 10 and Table 11. Figure 6 shows the results graphically.

Table 10. 2-step homopolymerisation experiments: settings and results.
Prepoly 10 min, all H2 fed before prepoly; Bulk step at 80°C, 40 min; Gas phase step at 80°C, 24 bar-g.

Catalyst	Catalyst amount	MC amount in catalyst	Time from 20°C to 80°C	Time from bulk to GP	C3 fed in GP (MFC)	total yield	Overall productivity	overall productivity	Bulk split	GP1 split	MFR2	Powder bulk density
	mg	mg	min	min	g	g	kg/g _{cat}	kg/g _{MC}	wt%	wt%	g/10min	g/cm ³
Silica CE2	113	1.91	18	11	495	2158	19	1130	77	23	1.9	0.49
Silica CE1	79	1.29	18	15	364	1585	20	1231	77	23	2.6	0.47
Silica IE2	55	0.93	22	5	302	1571	29	1690	81	19	2.8	0.46

Table 11. 2-step homopolymers: analytics

catalyst	XS	T _m	M _n	M _w	M _w /M _n
	w%	°C	g/mol	g/mol	
Silica CE2	0.4	150	96200	33500	3.5
Silica CE1	0.2	151	89250	31150	3.5
Silica IE2	0.3	154	71000	30400	4.3

Polymerisation procedure for 3-step heterophasic PP/EPR (bulk + gas phase + gas phase) experiments with silica supported metallocenes

Step 1: Prepolymerisation and bulk homopolymerisation

A 20.9 L stainless-steel reactor containing 0.4 bar-g propylene was filled with 3950 g propylene. Triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was placed into a stainless steel vial and injected into the reactor by means of a flow of 240 g propylene. 2.0 NL of H₂ was added via mass flow controller in one minute. The solution was stirred at 20 °C and 250 rpm for at least 20 min. The catalyst was injected as described in the following. The desired amount of solid, prepolymerised catalyst was loaded into a 5 ml stainless steel vial inside a glovebox and a second 5 ml vial containing 4 ml n-heptane pressurized with 10 bars of nitrogen was added on top of the first vial. This catalyst feeder system was mounted on a port on the lid of the reactor, the valve between the two vials was opened and the solid catalyst was contacted with heptane under nitrogen pressure for 2 s, and then flushed into the reactor with 240 g propylene. The prepolymerisation was run for 10 min. At the end of the prepolymerisation step the temperature was raised to 80 °C. The reactor temperature was held constant at 80°C throughout the polymerisation. The liquid propylene polymerisation was run for 30 minutes. The polymerisation time was measured starting when the internal reactor temperature reached 2 °C below the set polymerisation temperature.

Step 2: gas phase homopolymerisation

After the bulk step was completed, the stirrer speed was reduced to 50 rpm and the pressure was reduced to 23.5 bar-g by venting the monomer. Afterwards the stirrer speed was set to 180 rpm, the reactor pressure was set at 24 bar-g while keeping the reactor temperature at 80 °C, and 2.0 NL hydrogen were added via flow controller in 4 minutes. The gas phase homopolymerisation was run for 40 minutes, while keeping the pressure constant by feeding propylene via mass flow controller and the temperature constant at 80 °C by thermostat.¹

Step 3: gas phase ethylene-propylene copolymerisation

30 After the gas phase homopolymerisation step was completed, the stirrer speed was reduced to 50 rpm and the pressure was reduced down to 0.3 bar-g by venting the

monomers. Then triethylaluminum (0.80 ml of a 0.62 mol/l solution in heptane) was injected into the reactor by additional 250 g propylene through a steel vial. The pressure was then again reduced down to 0.3 bar-g by venting the monomers. The stirrer speed was set to 180 rpm and the reactor temperature was set to 70 °C. Then 5 the reactor pressure was increased to 20 bar-g by feeding a C2/C3 gas mixture (C2/C3=0.56 wt/wt). The temperature was held constant by thermostat and the mposition C2/C3=0.25 wt/wt for a set time (values in table 6).

Then the reactor was cooled down to about 30°C while the volatile components were flashed out. After purging the reactor 3 times with N2 and one 10 vacuum/N2 cycle, the product was taken out and dried overnight in a fume hood. 100 g of the polymer was additivated with 0.5 wt% Irganox B225 (solution in acetone) and dried overnight in a hood followed by 2 hours in a pressure was held constant by feeding via mass flow controller a C3/C2 gas mixture of covacuum drying oven at 60°C.

15 The 3-step heterophasic copolymers have been produced in three polymerisation steps: hPP in bulk at 80°C, hPP in gas phase at 80°C, 24 bar-g, then a C2/C3 copolymerisation in gas phase at 70°C, 20 bar-g, without adding H2. The polymerisation results with the SiO2/MAO catalysts based on Asahi Sunspera DM-L-33-C1 silica and metallocenes MC-CE2, MC-CE2, MC-IE1 and MC-IE2 are 20 listed in table 12 and Table 13.

FI1636 - 3.39.131089-01

- 115 -

Table 12. 3-step heterophasic copolymerisation experiments: settings and results. Prepoly 10 min, all H₂ fed before prepoly; Bulk step at 80°C, 30 min; Gas phase 1 step at 80°C, 40 min, 24 bar-g; Gas phase 2 step at 70°C, 20 bar-g, no added H₂.

Table 13. 3-step heterophasic copolymers: analytics

Catalyst	MFR2, powder	Powder bulk density	split bulk	split gas phase 1	split gas phase 2	Soluble fraction	T _m ²	iV(XS)	C2 (FT-IR)(XS)
		g/ml	%	%	%	wt%	°C	dl/g	wt%
Silica-CE2	2,31	0,45	56,6	15,0	28	27,5	150	2,1	19,9
Silica-CE1	0,89	0,45	64,2	15,7	20	16,7	151	2,4	18,5
Silica IE2	4,3	0,44	71,8	12,9	15	11,8	152	3,2	19,2
Silica IE1	5,64	0,44	69,7	16,2	14,1	13,3	153	3,4	20,1


5

Figure 7 shows the correlation between ethylene content of the rubber phase (C2 wt% in xylene soluble fraction) and its molecular weight (intrinsic viscosity). It is apparent that the inventive examples give much higher molecular weight compared to the comparative examples at the same ethylene content in the rubber.

10

Claims

1. A complex of formula (I):



5 M is Hf or Zr;
 each X is a sigma ligand;
 L is a bridge of formula $-(ER^8_2)_y-$;
 y is 1 or 2;
 E is C or Si;
 10 each R^8 is independently a C_1-C_{20} -hydrocarbyl, tri(C_1-C_{20} -alkyl)silyl, C_6-C_{20} -aryl, C_7-C_{20} -arylalkyl or C_7-C_{20} -alkylaryl or L is an alkylene group such as methylene or ethylene;
 Ar and Ar' are each independently an aryl or heteroaryl group optionally substituted by 1 to 3 groups R^1 or $R^{1'}$ respectively;
 15 R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1-C_6 -alkyl group, C_{7-20} arylalkyl, C_{7-20} alkylaryl group or C_{6-20} aryl group with the proviso that if there are four or more R^1 and $R^{1'}$ groups present in total, one or more of R^1 and $R^{1'}$ is other than tert butyl;
 R^2 and $R^{2'}$ are the same or are different and are a CH_2-R^9 group, with R^9 20 being H or linear or branched C_1-6 -alkyl group, C_{3-8} cycloalkyl group, C_{6-10} aryl group;

- 118 -


each R^3 is a $-CH_2-$, $-CHRx-$ or $C(Rx)_2-$ group wherein Rx is C₁₋₄ alkyl and where m is 2-6;

R^5 is a linear or branched C_{1-C₆}-alkyl group, C₇₋₂₀ arylalkyl, C₇₋₂₀ alkylaryl group or C_{6-C₂₀}-aryl group;

5 R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_{1-C₆} alkyl group; and

R^7 and $R^{7'}$ are the same or are different and are H or a linear or branched C_{1-C₆}-alkyl group.

10 2. A complex as claimed in claim 1 of formula (Ia)



M is Hf or Zr;

each X is a sigma ligand;

15 L is a bridge of formula $-(ER^8_2)_y-$;

y is 1 or 2;

E is C or Si;

- 119 -

each R^8 is independently a C_1 - C_{20} -hydrocarbyl, tri(C_1 - C_{20} -alkyl)silyl, C_6 - C_{20} -aryl, C_7 - C_{20} -arylalkyl or C_7 - C_{20} -alkylaryl or L is an alkylene group;

each n is independently 0, 1, 2 or 3;

R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1 - C_6 -alkyl group, C_{7-20} arylalkyl, C_{7-20} alkylaryl group or C_{6-20} aryl group with the proviso that if there are four or more R^1 and $R^{1'}$ groups present in total, one or more of R^1 and $R^{1'}$ is other than tert butyl;

R^2 and $R^{2'}$ are the same or are different and are a CH_2 - R^9 group, with R^9 being H or linear or branched C_{1-6} -alkyl group, C_{3-8} cycloalkyl group, C_{6-10} aryl group;

each R^3 is a $-CH_2-$, $-CHRx-$ or $C(Rx)_2-$ wherein Rx is C_{1-4} alkyl and where m is 2-6;


R^5 is a linear or branched C_1 - C_6 -alkyl group, C_{7-20} arylalkyl, C_{7-20} alkylaryl group or C_6 - C_{20} -aryl group;

R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_1 - C_6 alkyl group; and

R^7 and $R^{7'}$ are the same or are different and are H or a linear or branched C_1 - C_6 -alkyl group.

3. A complex as claimed in claim 2 wherein L is of formula $-SiR^8_2-$, wherein each R^8 is independently a C_1 - C_{20} -hydrocarbyl, tri(C_1 - C_{20} -alkyl)silyl, C_6 - C_{20} -aryl, C_7 - C_{20} -arylalkyl or C_7 - C_{20} -alkylaryl.

4. A complex as claimed in claim 1 of formula (Ib):



wherein

M is Hf or Zr;

each X is a sigma ligand;

5 L is an alkylene bridge or a bridge of the formula $-\text{SiR}^8_2-$, wherein each R^8 is independently a $\text{C}_1\text{-C}_{20}$ -hydrocarbyl, tri($\text{C}_1\text{-C}_{20}$ -alkyl)silyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl or $\text{C}_7\text{-C}_{20}$ -alkylaryl;

each n is independently 0, 1, 2 or 3;

R^1 and $R^{1'}$ are each independently the same or can be different and are a

10 linear or branched C₁-C₆-alkyl group, C₇₋₂₀ arylalkyl, C₇₋₂₀ alkylaryl group or C₆₋₂₀ aryl group with the proviso that if there are four or more R¹ and R^{1'} groups present in total, one or more of R¹ and R^{1'} is other than tert butyl;

R^2 and $R^{2'}$ are the same or are different and are a CH_2-R^9 group, with R^9

being H or linear or branched C₁₋₆-alkyl group, C₃₋₈ cycloalkyl group, C₆₋₁₀ aryl group;

15 group:

R^5 is a linear or branched C₁-C₆-alkyl group, C₇₋₂₀ arylalkyl, C₇₋₂₀ alkylaryl group or C₆-C₂₀-aryl group;

- 121 -


R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_1-C_6 alkyl group; and

R^7 and $R^{7'}$ are the same or are different and are H or a linear or branched C_1-C_6 -alkyl group.

5

5. A complex according to claim 4 in which each n is 1 or 2.

6. A complex according to any preceding claim of formula (II)



10

wherein

M is Hf or Zr;

X is a sigma ligand, preferably each X is independently a hydrogen atom, a halogen atom, C_{1-6} alkoxy group, C_{1-6} alkyl, phenyl or benzyl group;

15 L is an alkylene bridge or a bridge of the formula $-SiR^8_2-$, wherein each R^8 is independently C_1-C_6 -alkyl, C_{3-8} cycloalkyl or C_6 -aryl group;
each n is independently 1 or 2;

- 122 -


R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1 - C_6 -alkyl group with the proviso that if there are four R^1 and $R^{1'}$ groups present, all 4 cannot simultaneously be tert butyl;

R^2 and $R^{2'}$ are the same or are different and are a CH_2 - R^9 group, with R^9 being H or linear or branched C_1 - C_6 -alkyl group;

R^5 is a linear or branched C_1 - C_6 -alkyl group; and

R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_1 - C_6 -alkyl group.

10 7. A complex according to any preceding claim of formula (III)



wherein

M is Hf or Zr;

15 each X is a sigma ligand, preferably each X is independently a hydrogen atom, a halogen atom, C_{1-6} alkoxy group, C_{1-6} alkyl, phenyl or benzyl group;

L is $-SiR^8_2-$, wherein each R^8 is C_{1-6} alkyl or C_{3-8} cycloalkyl;

- 123 -

each n is independently 1 or 2;


R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group, group with the proviso that if there are four R¹ and R^{1'} groups present, all 4 cannot simultaneously be tert butyl;

5 R⁵ is a linear or branched C₁-C₆-alkyl group; and

R⁶ is a C(R¹⁰)₃ group, with R¹⁰ being a linear or branched C₁-C₆ alkyl group.

8. A complex according to any preceding claim of formula (IV)

10



wherein

M is Hf or Zr;

each X is a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl,

15 phenyl or benzyl group;

L is -SiR⁸₂-, wherein each R⁸ is C₁₋₄ alkyl or C₅₋₆ cycloalkyl;

each n is independently 1 or 2;


- 124 -

R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1 - C_6 -alkyl group with the proviso that if there are four R^1 and $R^{1'}$ groups present, all 4 cannot simultaneously be tert butyl,

R^5 is a linear or branched C_1 - C_6 -alkyl group; and

5 R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_1 - C_6 alkyl group.

9. A complex according to any preceding claim of formula (V)



10

wherein

M is Hf or Zr;

X is a hydrogen atom, a halogen atom, C_{1-6} alkoxy group, C_{1-6} alkyl, phenyl or benzyl group;


15 L is $-SiMe_2$;

each n is independently 1 or 2;

- 125 -

R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1 - C_6 -alkyl group, group with the proviso that if there are four R^1 and $R^{1'}$ groups present, all 4 cannot simultaneously be tert butyl,
 5 R^5 is a linear or branched C_1 - C_4 -alkyl group; and
 R^6 is a $C(R^{10})_3$ group, with R^{10} being a linear or branched C_1 - C_4 alkyl group.

10. A complex according to any preceding claim of formula (VI)



10

wherein

M is Hf or Zr;

X is a hydrogen atom, a halogen atom, C_{1-6} alkoxy group, C_{1-6} alkyl, phenyl or benzyl group;

15 L is $-SiMe_2$;

- 126 -


each n is independently 1 or 2;

R¹ and R^{1'} are each independently the same or can be different and are a linear or branched C₁-C₆-alkyl group, group with the proviso that if there are four R¹ and R^{1'} groups present, all 4 cannot simultaneously be tert butyl;

5 R⁵ is a linear C₁-C₄-alkyl group such as methyl; and

R⁶ is tert butyl.

11. A complex according to any preceding claim of formula (VII)



10

wherein

M is Hf or Zr;

X is a hydrogen atom, a halogen atom, C₁₋₆ alkoxy group, C₁₋₆ alkyl, phenyl or benzyl group, especially chlorine;

15 L is -SiMe₂;

each n is independently 1 or 2;


- 127 -

R^1 and $R^{1'}$ are each independently the same or can be different and are a linear or branched C_1 - C_4 -alkyl group with the proviso that if there are four R^1 and $R^{1'}$ groups present, all 4 cannot simultaneously be tert butyl;

R^5 is methyl; and

5 R^6 is tert butyl.

12. A complex according to any preceding claim of formula (VIII)



10 wherein

M is Hf or Zr;

X is Cl;

L is $-SiMe_2$;

each n is independently 1 or 2;

15 R^1 and $R^{1'}$ are each independently methyl or tert butyl with the proviso that if there are four R^1 and $R^{1'}$ groups present, all 4 cannot simultaneously be tert butyl,

R^5 is methyl; and

R^6 is tert butyl.

13. A complex according to any preceding claim wherein at least one of the C(4) or C(4') phenyl rings is 3,5-dimethyl phenyl.

5

14. A complex according to any preceding claim wherein at least one of the C(4) or C(4') phenyl rings is 4-(tert-butyl)-phenyl.

10

15. A complex according to any preceding claim wherein R^1 , $R^{1'}$ and each value of n are selected such that the C(4) or C(4') phenyl rings are 3,5-dimethyl phenyl, 3,5-ditertbutylphenyl and/or 4-(tert-butyl)-phenyl.

16. A catalyst system comprising:

15 (i) a complex according to any of claims 1 to 15;

(ii) a cocatalyst such as an aluminoxane catalyst.

17. A catalyst system according to claim 16 comprising a boron containing cocatalyst, an Al cocatalyst or both Al and B cocatalysts.

20

18. A catalyst system as claimed in claims 16 or 17 in solid form, e.g. supported on an external carrier or in solid particulate form free from an external carrier.

19. A catalyst system as claimed in claim 18 supported on silica.

25

20. A process for the manufacture of a catalyst system as claimed in any of claims 16 to 18, said catalyst system comprising obtaining a complex (i) as claimed in any of claims 1 to 15 and a cocatalyst (ii);

30

30 said process comprising forming a liquid/liquid emulsion system, which comprises a solution of catalyst components (i) and (ii) dispersed in a solvent in the form of dispersed droplets, and solidifying said dispersed droplets to form solid particles of said catalyst system.

21. A process as claimed in claim 20 further comprising off line prepolymerisation of the catalyst.

22. A process for the preparation of a polypropylene homopolymer, a propylene-
5 ethylene copolymer, or a propylene C4-10 alpha olefin copolymer comprising polymerising propylene, propylene and ethylene or proplene and a C4-10 alpha olefin, in the presence of a catalyst system according to any of claims 16 to 19.

23. A process for the preparation of a heterophasic polypropylene copolymer
10 comprising:
(I) polymerising propylene in bulk in the presence of a catalyst as claimed in claim 16 to 19 to form a polypropylene homopolymer matrix;
(II) in the presence of said matrix and said catalyst and in the gas phase, polymerising propylene and ethylene to form a heterophasic polypropylene
15 copolymer comprising a homopolymer matrix and an ethylene propylene rubber.

24. A process for the preparation of a heterophasic polypropylene copolymer comprising:
(I) polymerising propylene in bulk in the presence of a catalyst as claimed in
20 claim 16 to 19 to form a polypropylene homopolymer;
(II) in the presence of said homopolymer and said catalyst and in the gas phase, polymerising propylene to form a polypropylene homopolymer matrix;
(III) in the presence said matrix and said catalyst and in the gas phase, polymerising propylene and ethylene to form a heterophasic polypropylene
25 copolymer comprising a homopolymer matrix and an ethylene propylene rubber (EPR).

26. A process as claimed in claim 23 or 24 in which the EPR component is fully soluble in xylene at room temperature.

30


26. A process as claimed in claim 23 to 25 where the iV of the EPR is above 2.0 dL/g when measured in decaline.

- 130 -


27. A process as claimed in claim 23 to 26 wherein the Mw/Mn of the polypropylene homopolymer matrix component, as measured by GPC, is broader than 3.5, such as 4.0 to 8.0.

5

1/4


**Figure 1.**

5


**Figure 2.**

10

2/4

**Figure 3.**

5

**Figure 4.**

10

3/4





Figure 5.



5

Figure 6.




Figure 7.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2017/084273

A. CLASSIFICATION OF SUBJECT MATTER

INV.	C07F17/00	B01J31/38	C08F4/64	C08L23/10	C08L53/00
ADD.					

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C07F B01J C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>WO 2015/158790 A2 (BOREALIS AG [AT]) 22 October 2015 (2015-10-22)</p> <p>[rel-[(1,2,3,3a,7a-.eta.)-(1R)-4-[3,5-bis(1,1-dimethylethyl)phenyl]-6-(1,1-dimethylethyl)-5-methoxy-2-methyl-1H-inden-1-ylidene](dimethylsilylene)[(1,2,3,3a,8a-.eta.)-(1S)-4-[3,5-bis(1,1-dimethylethyl)phenyl]-2-methyl-s-indacen-1-ylidene]]dichloro-zirconium: compound page 33</p> <p>Use of metallocene in catalyst system together with co-catalyst to polymerize olefins, the co-catalyst preferably being MAO: claims 1-16</p> <p>-----</p> <p>-/-</p>	1-27

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
27 March 2018	10/04/2018
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Lange, Tim

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2017/084273

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>WO 2015/158791 A2 (BOREALIS AG [AT]) 22 October 2015 (2015-10-22) 4-[3,5-bis(t-butyl-phenyl]-6-(t-butyl)-5-methoxy-2-methyl-1H-inden-1-ylidene](dimethylsilylene)-4-[3,5-bis(1,1-dimethylethyl)phenyl]-6,7-dihydro-2-methyl-s-indacen-1(5H)-hafnium dichloride -or hafnium dimethyl: compounds on page 8, lines 20-22 and claim 6</p> <p>Use of metallocene in catalyst system for polymerization of olefins, the catalyst system comprising a co-catalyst, which preferably is MAO: claims 1-18</p> <p>-----</p>	1-27
A	<p>WO 2011/135004 A2 (BOREALIS AG [AT]; RESCONI LUIGI [FI]; CASTRO PASCAL [FI]; HUHTANEN LAU) 3 November 2011 (2011-11-03) compound on page 2</p> <p>-----</p>	1-27
A	<p>WO 2011/076780 A1 (BOREALIS AG [AT]; RESCONI LUIGI [IT]; CASTRO PASCAL [FI]; HUHTANEN LAU) 30 June 2011 (2011-06-30) compound on page 26, corresponding to comparative example "MC-CE5" of application</p> <p>-----</p>	1-27

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/EP2017/084273

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
WO 2015158790	A2	22-10-2015	CN	106459278 A	22-02-2017
			EP	3131934 A2	22-02-2017
			JP	2017511418 A	20-04-2017
			KR	20160147835 A	23-12-2016
			TW	201605913 A	16-02-2016
			US	2017037165 A1	09-02-2017
			WO	2015158790 A2	22-10-2015
<hr style="border-top: 1px dashed black;"/>					
WO 2015158791	A2	22-10-2015	EP	2933277 A1	21-10-2015
			EP	3131935 A2	22-02-2017
			TW	201609841 A	16-03-2016
			US	2017037164 A1	09-02-2017
			WO	2015158791 A2	22-10-2015
<hr style="border-top: 1px dashed black;"/>					
WO 2011135004	A2	03-11-2011	CN	102947354 A	27-02-2013
			EP	2383299 A1	02-11-2011
			JP	5785609 B2	30-09-2015
			JP	2013525557 A	20-06-2013
			KR	20130040893 A	24-04-2013
			US	2013116394 A1	09-05-2013
			WO	2011135004 A2	03-11-2011
<hr style="border-top: 1px dashed black;"/>					
WO 2011076780	A1	30-06-2011	CN	102666605 A	12-09-2012
			EP	2516486 A1	31-10-2012
			US	2013018156 A1	17-01-2013
			WO	2011076780 A1	30-06-2011