

WO 2011/017343 A2

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
10 February 2011 (10.02.2011)(10) International Publication Number
WO 2011/017343 A2

(51) International Patent Classification:

C03C 3/087 (2006.01)

(21) International Application Number:

PCT/US2010/044275

(22) International Filing Date:

3 August 2010 (03.08.2010)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

12/534,490 3 August 2009 (03.08.2009) US

(71) Applicant (for all designated States except US): PPG INDUSTRIES OHIO, INC. [US/US]; 3800 West 143rd Street, Cleveland, Ohio 44111 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): LI, Hong [US/US]; 1621 Norman Drive, Sewickley, Pennsylvania 15143 (US). WATSON, James, C. [US/US]; 444 Terrapin Lane, Lake Wylie, South Carolina 29710 (US).

(74) Agents: CALKINS, Charles, W. et al.; Kilpatrick Stockton, LLP, 1001 West Fourth Street, Winston-Salem, North Carolina 27101 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) Title: GLASS COMPOSITIONS AND FIBERS MADE THEREFROM




FIGURE 1

(57) Abstract: Embodiments of the present invention provides fiberizable glass compositions formed from batch compositions comprising significant amounts of one or more glassy minerals, including perlite and/or pumice.

GLASS COMPOSITIONS AND FIBERS MADE THEREFROM

CROSS REFERENCE TO RELATED APPLICATION

This application claims priority to utility application 12/534,490, filed on August 3, 5 2009, the entire disclosure of which is incorporated by reference.

FIELD OF THE INVENTION

The present invention relates to glass compositions and, in particular, to glass compositions for forming fibers.

BACKGROUND OF THE INVENTION

10 Large scale commercial production of continuous glass fibers (E-glass and C-glass types) comprises melting batch materials consisting primarily of minerals that are crystalline or substantially crystalline in nature. Conversion of these crystalline raw materials to a glassy state requires significant energy to be applied during the melting process. In view of the significant energy investment accompanying crystalline materials, glassy or amorphous 15 minerals have sometimes been used in the production of glass compositions. A glassy or amorphous structure can reduce the amount of energy consumed in the melting process. Glassy minerals such as basalt and obsidian, for example, have been used as significant portions of feedstock for the production of mineral wool.

20 An associated disadvantage with some glassy minerals, however, is the high iron content of such minerals. Basalt and obsidian both comprise relatively large amounts of iron, thereby making their resulting melts highly energy absorbing. As a result, use of conventional gas fired furnaces is typically impractical for melt processing of these minerals. Electrical melting can be used to process glassy minerals of high iron content, but this is often a constraint in high volume glass fiber production as compared with conventional gas 25 fired furnace technology. Raw materials used in the production of E-glass and C-glass fibers are generally low in iron, thereby permitting the use of large scale gas fired furnaces.

Perlite (and its expanded form pumice) is a mineral that naturally occurs in the glassy form. Perlite has not been extensively used as a raw material in glass production, partially 30 because of its compositional parameters. The major constituents of perlite are SiO_2 , Al_2O_3 and alkali oxide (R_2O). SiO_2 is typically present in perlite in an amount between about 70 and about 75 weight percent. Al_2O_3 is typically present in perlite in an amount between about 12 and about 15 weight percent. Alkali oxides are typically present in perlite in an amount between about 3 and about 9 weight percent. These parameters conflict with the

compositional requirements of several widely used glass compositions, including, for example, those of E-glass and C-glass.

E-glass compositions, for example, are well-suited for forming glass fibers. As a result, the majority of glass fibers used in reinforcement applications, such as polymeric reinforcement applications, are formed from E-glass compositions. E-glass compositions generally limit the amount alkali oxides to no more than 2 percent. The high alkali oxide content of perlite is inconsistent with this limitation and renders perlite largely unsuitable for use in batch compositions for the production of E-glass compositions.

Moreover, C-glass compositions have also been used to form fibers resistant to corrosion in acidic environments. In order to resist acidic corrosion, C-glass compositions comprise a high SiO_2 content and a low Al_2O_3 content (< 8 wt. %). The high Al_2O_3 content of perlite generally precludes use of perlite in batch compositions for the production of C-glass compositions.

SUMMARY

In one aspect, the present invention provides glass compositions formed from batch compositions comprising significant amounts of one or more glassy minerals, including perlite and/or pumice. In another aspect, the present invention provides glass fibers formed from glass compositions described herein.

In one embodiment, the present invention provides a glass composition formed from a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, wherein the glassy mineral comprises a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent. In some embodiments, the batch composition comprises at least 65 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent. In some embodiments, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 is perlite, pumice or mixtures thereof.

Moreover, in some embodiments, the batch comprises at least 10 weight percent of a sodium source. A sodium source, in some embodiments, comprises sodium carbonate (soda).

In another embodiment, the present invention provides a glass composition comprising 53-64 weight percent SiO_2 , 8-12 weight percent Al_2O_3 , 8.5-18 weight percent alkali oxide (R_2O) component and a metal oxide (RO) component, wherein the metal oxide component is present in an amount to provide a mass ratio of $\text{R}_2\text{O}/\text{RO}$ ranging from about 0.15 to about 1.5.

5 In some embodiments, a R₂O component comprises Na₂O, K₂O or Li₂O or mixtures thereof. In some embodiments, a glass composition of the present invention comprises Na₂O in an amount ranging from 6.5 weight percent to about 16 weight percent. A glass composition, in some embodiment, comprises K₂O in an amount ranging from 2 weight percent to 4 weight percent. In some embodiments, a glass composition comprises Li₂O in an amount up to 2 weight percent.

10 In some embodiments, a RO component comprises MgO, CaO, SrO, BaO, or ZnO or mixtures thereof. A RO component, in some embodiments, is present in a glass composition of the present invention in an amount ranging from 7 weight percent to 31 weight percent. In one embodiment, a glass composition comprises MgO in an amount up to about 5 weight percent. A glass composition, in some embodiments, comprises CaO in an amount ranging from 7 weight percent to 26 weight percent. In some embodiments, a glass composition comprises ZnO in an amount up to 3 weight percent.

15 Glass compositions of the present invention, in some embodiments, comprise metal oxides in addition to RO including, but not limited to, ZrO₂, TiO₂, MnO₂ or La₂O₃ or mixtures thereof.

20 In another embodiment, the present invention provides a glass composition comprising 56-63 weight percent SiO₂, 9-12 weight percent Al₂O₃, 12-17 weight percent RO (CaO + MgO), 12-14 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

25 In another embodiment, the present invention provides a glass composition comprising 60-64 weight percent SiO₂, 9-12 weight percent Al₂O₃, 7-15 weight percent RO (CaO + MgO), 13-15.5 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

30 In another embodiment, the present invention provides a glass composition comprising 55-63 weight percent SiO₂, 9-14 weight percent Al₂O₃, 11-16.5 weight percent RO (CaO + MgO), 14-17 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

In some embodiments, glass compositions of the present invention have an Fe₂O₃ content of less than 1 weight percent. Glass compositions, in other embodiments, can comprise less than 0.7 weight percent Fe₂O₃.

Glass compositions, according to some embodiments of the present invention are fiberizable. In some embodiments, glass compositions of the present invention have a forming temperature (T_F) ranging from 1120°C to about 1300°C. As used herein, the term “forming temperature” means the temperature at which the glass composition has a viscosity of 1000 poise (or “log 3 temperature”). In some embodiments, glass compositions of the present invention are fiberizable at the forming temperature. Moreover, in some embodiments, glass compositions of the present invention have a liquidus temperature (T_L) ranging from about 1020°C to about 1240°C. In some embodiments, the difference between the forming temperature and the liquidus temperature of a glass composition of the present invention ranges from about 45°C to about 165°C. In some embodiments, the difference between the forming temperature and the liquidus temperature of a glass composition of the present invention is at least 65°C.

In some embodiments, glass compositions of the present invention have a molten density at the forming temperature ranging from 2.35 g/cm² to 2.40 g/cm². In some embodiments, glass composition of the present invention have molten density ranging from 2.36 g/cm² to 2.38 g/cm².

Glass compositions of the present invention, in some embodiments, have a molten surface tension at the forming temperature ranging from about 390 E⁻³ N/m to 400 E⁻³ N/m.

As provided herein, glass fibers can be formed from some embodiments of the glass compositions of the present invention. In some embodiments, fibers formed from glass compositions of the present invention have a modulus (E) ranging from about 53 GPa to about 65 GPa. Moreover, in some embodiments, fibers formed from glass compositions of the present invention have a specific strength ranging from 1.30-1.35 E⁵ m.

Fibers formed from glass compositions of the present invention, in some embodiments, also demonstrate acidic and alkaline corrosion resistance. In one embodiment, for example, a fiber formed from a glass composition of the present invention has a weight loss (wt.%) ranging from about 0.55 to about 0.60 when exposed to 1N H₂SO₄ (pH 0) at 100°C for one hour. In another embodiment, a fiber formed from a glass composition of the present invention has a weight loss (wt.%) ranging from about 0.25 to 0.30 when exposed to 0.1N NaOH (pH 12) at 100°C for one hour.

Glass fibers formed from glass compositions of the present invention can be used in various reinforcement applications. In some embodiments, glass fibers of the present invention are used in the reinforcement of polymers including thermoplastics and thermosets. In some embodiments, glass fibers formed from glass compositions of the present invention

are used in the reinforcement of building materials including, but not limited to, cement and roofing systems such as shingles.

In another aspect, the present invention provides methods of making glass compositions from batch compositions comprising significant amounts of one or more glassy minerals, including perlite and/or pumice.

In one embodiment, a method of making a glass composition of the present invention comprises providing a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent and heating the batch composition to a temperature sufficient to form the glass composition. In some embodiments, the batch composition is heated to a temperature of about 1400°C to about 1450°C.

These and other embodiments are presented in greater detail in the detailed description which follows.

15 BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 provides the results of a high temperature differential thermal analysis (DTA) comparing conversion from solid to liquid of fine particulate perlite and a coarse particulate perlite according to one embodiment of the present invention.

Figure 2 illustrates an apparatus used in the determination of melt viscosities of glass compositions according to embodiments of the present invention.

Figure 3 illustrates the position of the thermocouple and the number of turns of the heating coil of a furnace used in the determination of liquidus temperatures (T_L) of glass compositions according to embodiments of the present invention.

Figure 4 provides temperature-viscosity curves for a glass composition according to one embodiment of the present invention, two commercially available E-glass compositions and a C-glass composition.

Figure 5 provides molten glass surface tensions as a function of temperature for a glass composition according to one embodiment of the present invention and two commercially available E-glass compositions.

Figure 6 is a plot of the melt or molten glass density as a function of temperature for a glass composition according to one embodiment of the present invention and two commercially available E-glass compositions.

Figure 7 is a plot electrical of conductivity as a function of temperature for a glass composition according to one embodiment of the present invention as well as E-glass and C-glass compositions.

Figure 8 provides energy requirements for conversion of several batch compositions to glass melt compositions according to one embodiment of the present invention.

Figure 9 summarizes Weibull statistical analysis of fiber strengths of various glass compositions according to some embodiments of the present invention.

DETAILED DESCRIPTION

Unless indicated to the contrary, the numerical parameters set forth in the following specification are approximations that can vary depending upon the desired properties sought to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques.

Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements. Moreover, all ranges disclosed herein are to be understood to encompass any and all subranges subsumed therein. For example, a stated range of "1 to 10" should be considered to include any and all subranges between (and inclusive of) the minimum value of 1 and the maximum value of 10; that is, all subranges beginning with a minimum value of 1 or more, e.g. 1 to 6.1, and ending with a maximum value of 10 or less, e.g., 5.5 to 10. Additionally, any reference referred to as being "incorporated herein" is to be understood as being incorporated in its entirety.

It is further noted that, as used in this specification, the singular forms "a," "an," and "the" include plural referents unless expressly and unequivocally limited to one referent.

Certain embodiments of the present invention can employ the various thermodynamic and processing advantages offered by glassy minerals to provide glass compositions having desirable properties. In one aspect, the present invention provides glass compositions formed from batch compositions comprising significant amounts of one or more glassy minerals, including perlite and/or pumice. The glass compositions, in some embodiments, can be fiberizable glass compositions. In some embodiments, glass fibers formed from glass compositions of the present invention can demonstrate advantageous properties including, but

not limited to, mechanical and corrosion resistant properties equaling or exceeding glass fibers formed from previous compositions, such as E-glass and C-glass compositions.

Various embodiments of the present invention provide glass compositions, including, without limitation, fiberizable glass compositions. In one embodiment, the present invention provides a glass composition formed from a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, wherein the glassy mineral comprises a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent. In some embodiments, the batch composition comprises at least 65 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent. In another embodiment, the batch composition comprises at least 68 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent.

In some embodiments, a glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent is perlite, pumice or mixtures thereof.

Moreover, in some embodiments, the batch composition comprises at least 10 weight percent of a sodium source. In another embodiment, the batch composition comprises at least 12 weight percent of a sodium source. A suitable sodium source for use in batch compositions of the present invention, in some embodiments, comprises sodium carbonate (soda).

In another embodiment, the present invention provides a glass composition comprising 53-64 weight percent SiO_2 , 8-12 weight percent Al_2O_3 , 8.5-18 weight percent alkali oxide (R_2O) component and a metal oxide (RO) component, wherein the metal oxide component is present in an amount to provide a mass ratio of $\text{R}_2\text{O}/\text{RO}$ ranging from about 0.15 to about 1.5.

In some embodiments, a R_2O component is not limited to a single compound but can comprise several compounds. In some embodiments, a R_2O component comprises Na_2O , K_2O or Li_2O or mixtures thereof. Moreover, in some embodiments and without limitation, a R_2O component can mean Na_2O only, K_2O only, Li_2O only, a combination of Na_2O and K_2O , a combination of K_2O and Li_2O , a combination of Na_2O and Li_2O , or a combination of Na_2O , K_2O and Li_2O .

In some embodiments, a glass composition of the present invention comprises Na_2O in an amount ranging from 6.5 weight percent to about 16 weight percent. In another embodiment, a glass composition comprises Na_2O in an amount ranging from 9 weight

percent to 13 weight percent. In some embodiments, a glass composition comprises Na₂O in an amount ranging from 10 weight percent to 12.5 weight percent.

A glass composition of the present invention, in some embodiments, comprises K₂O in an amount ranging from 2 weight percent to 4 weight percent. In some embodiments, a glass composition comprises K₂O in an amount ranging from 2.5 weight percent to 3.5 weight percent.

In some embodiments, a glass composition of the present invention comprises Li₂O in an amount up to 2 weight percent. A glass composition, in another embodiment, comprises Li₂O in an amount ranging from 0.5 weight percent to 1.5 weight percent.

In some embodiments, a RO component comprises MgO, CaO, SrO, BaO or ZnO or mixtures thereof. In some embodiments, a RO component can comprise MgO only, CaO only, SrO only, BaO only or ZnO only. In some embodiments, a RO component can comprise any combination of two or more metal oxides of MgO, CaO, SrO, BaO and ZnO. A RO component, in some embodiments, is present in a glass composition of the present invention in an amount ranging from 7 weight percent to 31 weight percent.

In one embodiment, a glass composition of the present invention comprises MgO in an amount up to 5 weight percent. A glass composition, in another embodiment, comprises MgO in an amount ranging from 1 weight percent to 4 weight percent. In some embodiments, a glass composition comprises MgO in an amount ranging from 2 weight percent to 3 weight percent.

In some embodiments, a glass composition of the present invention comprises CaO in an amount ranging from 7 weight percent to 26 weight percent. A glass composition, in another embodiment, comprises CaO in an amount ranging from 8 weight percent to 20 weight percent. In some embodiments, a glass composition comprises CaO in an amount ranging from 10 weight percent to 14 weight percent.

In some embodiments, a glass composition comprises ZnO in an amount up to 3 weight percent.

Glass compositions of the present invention, in some embodiments, comprise metal oxides in addition to RO including, but not limited to ZrO₂, TiO₂, MnO₂ or La₂O₃ or mixtures thereof. In some embodiments, a glass composition can comprise ZrO₂ in an amount up to 3 weight percent, TiO₂ in an amount up to 3 weight percent, MnO₂ in an amount up to 3 weight percent and/or La₂O₃ in an amount up to 3 weight percent.

In another embodiment, the present invention provides a glass composition comprising 56-63 weight percent SiO₂, 9-12 weight percent Al₂O₃, 12-17 weight percent RO (CaO + MgO), 12-14 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

5 In another embodiment, the present invention provides a glass composition comprising 60-64 weight percent SiO₂, 9-12 weight percent Al₂O₃, 7-15 weight percent RO (CaO + MgO), 13-15.5 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

10 In another embodiment, the present invention provides a glass composition comprising 55-63 weight percent SiO₂, 9-14 weight percent Al₂O₃, 11-16.5 weight percent RO (CaO + MgO), 14-17 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

15 In some embodiments, glass compositions of the present invention have an Fe₂O₃ content of less than 1 weight percent. Glass compositions, in other embodiments, can comprise less than 0.7 weight percent Fe₂O₃.

20 Glass compositions of the present invention, in some embodiments, have a forming temperature (T_F) ranging from about 1120°C to about 1300°C. In another embodiment, glass compositions of the present invention have a forming temperature ranging from about 1150°C to about 1250°C. In some embodiments, glass compositions have a forming temperature ranging from about 1200°C to about 1225°C.

25 Glass compositions of the present invention, in some embodiments, have a liquidus temperature ranging from about 1020°C to about 1240°C. In another embodiment, glass compositions of the present invention have a liquidus temperature ranging from about 1070°C to about 1200°C. In some embodiments, glass compositions of the present invention have a liquidus temperature ranging from about 1110°C to about 1140°C.

30 In some embodiments, the difference between the forming temperature and the liquidus temperature of a glass composition of the present invention ranges from about 45°C to about 165°C. In some embodiments, the difference between the forming temperature and the liquidus temperature of a glass composition of the present invention is at least 65°C.

In some embodiments, glass compositions of the present invention have a molten density at the forming temperature ranging from 2.35 g/cm² to 2.40 g/cm². In some

embodiments, glass compositions of the present invention have molten density ranging from 2.36 g/cm² to 2.38 g/cm². As discussed further herein, in some embodiments, molten densities of some glass compositions of the present invention are 5% to 7% lower than the molten densities of some E-glass compositions. As a result, glass fibers formed from some 5 glass compositions of the present invention are lighter per unit volume in comparison to some E-glass fibers. Lighter glass fibers can be advantageous in many applications, particularly material reinforcement application, such as polymeric reinforcement applications, where weight savings are often highly desirable. Moreover, as a result of lower densities, glass fibers formed from some glass compositions of the present invention can have larger 10 diameters in comparison to some E-glass fibers of the same weight, thereby providing enhanced mechanical properties.

Additionally, glass compositions of the present invention, in some embodiments, have a molten surface tension at the forming temperature ranging from about 390 E⁻³ N/m to 400 E⁻³ N/m.

15 As provided herein, glass compositions of the present invention can be produced from batch compositions comprising a significant amount of one or more glassy minerals, including perlite and/or pumice. In being produced from batch compositions comprising a significant amount of glassy minerals, glass compositions of the present invention can realize sizable energy savings in some embodiments. As discussed further herein, in some 20 embodiments, production of a melt of a glass composition of the present invention requires up to 33% less energy in comparison to that required to produce a melt of some E-glass compositions.

25 Glass compositions of the present invention can be produced by several methods. In one embodiment, a method of producing a glass composition comprises providing a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, the glassy mineral comprising a combination of SiO₂ and Al₂O₃ in an amount of at least 80 weight percent and heating the batch composition to a temperature sufficient to form a melt of the glass composition. In some embodiments, the batch composition is heated to a temperature of about 1400°C to about 1450°C.

30 In some embodiments, the batch composition comprises at least 65 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO₂ and Al₂O₃ in an amount of at least 80 weight percent. In another embodiment, the batch composition comprises at least 68 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO₂ and Al₂O₃ in an amount of at least 80 weight percent.

In some embodiments, a glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent is perlite, pumice or mixtures thereof. Perlite and/or pumice used in the production of glass compositions of the present invention, in some embodiments, is provided in particulate or powder form. In some embodiments, additional 5 energy savings can be realized by using perlite and/or pumice compositions having fine particle size as opposed to coarser particle sizes. Figure 1 illustrates the results of a high temperature differential thermal analysis (DTA) comparing the conversion from solid to liquid of a fine particulate perlite (about 200 mesh) and a coarse particulate perlite (about 45 mesh). As illustrated in Figure 1, the fine particulate perlite requires less energy during 10 conversion from solid to liquid in comparison to the coarse particulate perlite, although both the fine and the coarse particulate perlite are glassy or amorphous at room temperature. Moreover, the fine particulate perlite begins liquid formation at a lower temperature than the coarse particulate perlite.

Moreover, in some embodiments, batch compositions of the present invention 15 comprise at least 10 weight percent of a sodium source. In some embodiments, batch compositions comprise at least 12 weight percent of a sodium source. A suitable sodium source for use in batch compositions of the present invention, in some embodiments, comprises sodium carbonate (soda).

In some embodiments, batch compositions used to produce glass compositions of the 20 present invention further comprise other minerals including, but not limited to, limestone, dolomite or mixtures thereof. In one embodiment, for example, a batch composition further comprises up to 17 weight percent limestone. In another embodiment, a batch composition further comprises up to 13 weight percent dolomite.

As provided herein, glass fibers can be formed from any of the glass compositions of 25 the present invention. Glass fibers according to the various embodiments of the present invention can be formed using any process known in the art for forming glass fibers, and more desirably, any process known in the art for forming essentially continuous glass fibers. For example, although not limiting herein, the glass fibers according to non-limiting 30 embodiments of the present invention can be formed using direct-melt or indirect-melt fiber forming methods. These methods are well known in the art and further discussion thereof is not believed to be necessary in view of the present disclosure. *See, e.g., K. L. Loewenstein, The Manufacturing Technology of Continuous Glass Fibers, 3rd Ed., Elsevier, N.Y., 1993 at pages 47-48 and 117-234.*

In one embodiment, the present invention provides a glass fiber comprising a glass composition formed from a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, wherein the glassy mineral comprises a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent. In some embodiments, the batch composition comprises at least 65 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent. In another embodiment, the batch composition comprises at least 68 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent.

In another embodiment, the present invention provides a glass fiber comprising 53-64 weight percent SiO_2 , 8-12 weight percent Al_2O_3 , 8.5-18 weight percent alkali oxide (R_2O) component and a metal oxide (RO) component, wherein the metal oxide component is present in an amount to provide a mass ratio of $\text{R}_2\text{O}/\text{RO}$ ranging from about 0.15 to about 1.5.

In another embodiment, the present invention provides a glass fiber comprising 56-63 weight percent SiO_2 , 9-12 weight percent Al_2O_3 , 12-17 weight percent RO ($\text{CaO} + \text{MgO}$), 12-14 weight percent R_2O ($\text{Na}_2\text{O} + \text{K}_2\text{O}$), 0-2 weight percent Li_2O , 0-3 weight percent ZnO , 0-3 weight percent ZrO_2 , 0-3 weight percent MnO_2 and 0-3 weight percent La_2O_3 .

In another embodiment, the present invention provides a glass fiber comprising 60-64 weight percent SiO_2 , 9-12 weight percent Al_2O_3 , 7-15 weight percent RO ($\text{CaO} + \text{MgO}$), 13-15.5 weight percent R_2O ($\text{Na}_2\text{O} + \text{K}_2\text{O}$), 0-2 weight percent Li_2O , 0-3 weight percent ZnO , 0-3 weight percent ZrO_2 , 0-3 weight percent MnO_2 and 0-3 weight percent La_2O_3 .

In another embodiment, the present invention provides a glass fiber comprising 55-63 weight percent SiO_2 , 9-14 weight percent Al_2O_3 , 11-16.5 weight percent RO ($\text{CaO} + \text{MgO}$), 14-17 weight percent R_2O ($\text{Na}_2\text{O} + \text{K}_2\text{O}$), 0-2 weight percent Li_2O , 0-3 weight percent ZnO , 0-3 weight percent ZrO_2 , 0-3 weight percent MnO_2 and 0-3 weight percent La_2O_3 .

In some embodiments, fibers formed from glass compositions of the present invention have a modulus (E) ranging from about 53.0 GPa to about 65.0 GPa. In another embodiment, fibers formed from glass compositions of the present invention have a modulus (E) ranging from about 56 GPa to about 62 GPa. Moreover, in some embodiments, fibers formed from glass compositions of the present invention have a specific strength ranging from 1.30-1.35 $\text{E}^5 \text{ m}$.

Fibers formed from glass compositions of the present invention, in some embodiments, also demonstrate acidic and alkaline corrosion resistance. In one embodiment, for example, a glass fiber formed from a glass composition of the present invention has a weight loss (wt.%) ranging from 0.55 to 0.60 when exposed to 1N H₂SO₄ (pH 0) at 100°C for one hour. In another embodiment, a glass fiber formed from a glass composition of the present invention has a weight loss (wt.%) ranging from 0.60 to 1.70 when exposed to 1N H₂SO₄ (pH 0) at 100°C for one hour.

In another embodiment, a fiber formed from a glass composition of the present invention has a weight loss (wt.%) ranging from about 0.25 to about 0.30 when exposed to 0.1N NaOH (pH 12) at 100°C for one hour. A fiber formed from a glass composition of the present invention, in some embodiments, has a weight loss (wt.%) ranging from 0.35 to 0.85 when exposed to 0.1N NaOH (pH 12) at 100°C for one hour.

Although not limiting herein, glass fibers according to some embodiments of the present invention can be useful in structural reinforcement applications. In some embodiments, glass fibers of the present invention are used in the reinforcement of polymers including thermoplastics and thermosets. In some embodiments, glass fibers formed from glass compositions of the present invention are used in the reinforcement of building materials including, but not limited to, cement and roofing systems such as shingles.

In one embodiment, the present invention provides a polymeric composite comprising a polymeric material and at least one glass fiber in the polymeric material, the at least one glass fiber comprising a glass composition formed from a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, wherein the glassy mineral comprises a combination of SiO₂ and Al₂O₃ in an amount of at least 80 weight percent. In some embodiments, the batch composition comprises at least 65 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO₂ and Al₂O₃ in an amount of at least 80 weight percent. In another embodiment, the batch composition comprises at least 68 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO₂ and Al₂O₃ in an amount of at least 80 weight percent.

In another embodiment, the present invention provides a polymeric composite comprising a polymeric material and at least one glass fiber in the polymeric material, the at least one glass fiber comprising 53-64 weight percent SiO₂, 8-12 weight percent Al₂O₃, 8.5-18 weight percent alkali oxide (R₂O) component and a metal oxide (RO) component, wherein the metal oxide component is present in an amount to provide a mass ratio of R₂O/RO ranging from about 0.15 to about 1.5.

5 In another embodiment, the present invention provides a polymeric composite comprising a polymeric material and at least one glass fiber in the polymeric material, the at least one glass fiber comprising 56-63 weight percent SiO₂, 9-12 weight percent Al₂O₃, 12-17 weight percent RO (CaO + MgO), 12-14 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

10 In another embodiment, the present invention provides a polymeric composite comprising a polymeric material and at least one glass fiber in the polymeric material, the at least one glass fiber comprising 60-64 weight percent SiO₂, 9-12 weight percent Al₂O₃, 7-15 weight percent RO (CaO + MgO), 13-15.5 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

15 In another embodiment, the present invention provides a polymeric composite comprising a polymeric material and at least one glass fiber in the polymeric material, the at least one glass fiber comprising 55-63 weight percent SiO₂, 9-14 weight percent Al₂O₃, 11-16.5 weight percent RO (CaO + MgO), 14-17 weight percent R₂O (Na₂O + K₂O), 0-2 weight percent Li₂O, 0-3 weight percent ZnO, 0-3 weight percent ZrO₂, 0-3 weight percent MnO₂ and 0-3 weight percent La₂O₃.

20 Polymeric composites according to the various embodiments of the present invention can be made by any method known in the art for making polymeric composites. For example, in one embodiment, polymeric composites according to the present invention can be made by impregnating woven fabrics or non-woven fabrics or mats of glass fibers with a polymeric material and then curing the polymeric material. In another embodiment, continuous glass fibers and/or chopped glass fibers comprising glass compositions of the present invention can be disposed in the polymeric material. Depending on the identity of the polymeric material, the polymeric material can be cured subsequent to receiving the continuous or chopped glass fibers.

25 Various non-limiting embodiments of the present invention will now be illustrated in the following, non-limiting examples.

30 Examples 1 through 6 of glass compositions of the present invention provided in Table I were prepared by providing mixtures of ingredients covering 65-72 weight percent perlite, 0-22 weight percent dolomite, 6-35 weight percent limestone and 0-8 weight percent soda. The specific amounts of perlite, dolomite, limestone and/or soda used to produce Examples 1 through 6 were determined by reference to the compositional parameters of each

mineral in relation to the desired compositional parameters of each glass composition. Mixtures of the minerals were subsequently heated to a temperature of about 1400°C to obtain molten glass compositions. The molten glass compositions were cooled to provide glass compositions of Examples 1 through 6.

5

Table I – Glass Compositions

Ex.	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	R ₂ O	Fe ₂ O ₃	TiO ₂	SO ₃	F	M _x O _y
1	59.29	10.84	20.37	3.00	2.82	3.06	5.88	0.48	0.14	0.00	0.00	0.00
2	59.29	10.84	19.37	4.00	2.82	3.06	5.88	0.48	0.14	0.00	0.00	0.00
3	59.29	10.84	18.87	4.50	2.82	3.06	5.88	0.48	0.14	0.00	0.00	0.00
4	59.29	10.84	18.37	5.00	2.82	3.06	5.88	0.48	0.14	0.00	0.00	0.00
5	54.41	9.95	25.68	4.00	2.76	2.59	5.38	0.47	0.14	0.00	0.00	0.00
6	59.29	10.84	23.37	0.00	2.82	3.06	5.88	0.48	0.14	0.00	0.00	0.00

Examples 7 through 13 of glass compositions of the present invention provided in Table II were prepared by providing mixtures of ingredients covering 69-71 weight percent perlite, 6-20 weight percent limestone and 7-10 weight percent soda. The specific amounts of perlite, limestone and soda used to produce Examples 7 through 13 were determined by reference to the compositional parameters of each mineral in relation to the desired compositional parameters of each glass composition. Mixtures of the minerals were subsequently heated to a temperature of about 1400°C to obtain molten glass compositions. The molten glass compositions were cooled to provide glass compositions of Examples 7 through 13.

Table II – Glass Compositions

Ex.	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	R ₂ O	Fe ₂ O ₃	TiO ₂	SO ₃	F	M _x O _y
7	62.66	11.46	9.28	2.98	9.20	3.23	12.43	0.51	0.14	0.25	0.30	0.00
8	61.11	11.17	14.03	0.00	9.29	3.15	12.42	0.49	0.14	0.32	0.30	0.00
9	62.61	11.45	11.26	0.00	10.19	3.23	13.42	0.51	0.14	0.32	0.30	0.00
10	61.13	11.17	13.04	0.00	10.19	3.23	13.42	0.49	0.14	0.32	0.30	0.00
11	58.93	10.76	12.57	0.00	10.34	2.60	13.22	0.47	3.00	0.09	0.28	0.95*
12	58.93	10.76	12.57	0.00	10.34	2.60	13.22	0.47	1.08	0.09	0.28	2.87*
13	57.47	10.78	9.12	0.00	10.44	3.05	13.49	0.62	0.15	0.09	0.28	8.00*

* ZrO₂ and TiO₂ were added to the batch composition used to produce the glass composition.

20

Examples 14 through 19 of glass compositions of the present invention provided in Table III were prepared by providing mixtures of ingredients covering 69-72 weight percent perlite, 0-13 weight percent dolomite, 3-17 weight percent limestone and 7-10 weight percent soda. The specific amounts of perlite, limestone, soda and/or dolomite used to produce

Examples 14 through 19 were determined by reference to the compositional parameters of each mineral in relation to the desired compositional parameters of each glass composition. Mixtures of the minerals were subsequently heated to a temperature of about 1400°C to obtain molten glass compositions. The molten glass compositions were cooled to provide

5 glass compositions of Examples 14 through 19.

Table III – Glass Compositions

Ex.	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	R ₂ O	Fe ₂ O ₃	TiO ₂	SO ₃	F	M _x O _y
14	62.62	11.45	10.77	0.00	10.69	3.23	13.92	0.51	0.14	0.30	0.30	0.00
15	61.91	11.38	7.99	3.00	11.21	3.27	14.48 [#]	0.60	0.14	0.20	0.00	1.0 [#] /0.30*
16	63.65	11.93	4.39	2.56	13.04	3.37	16.41	0.70	0.17	0.20	0.00	0.00
17	61.14	11.17	12.05	0.00	11.26	3.15	14.41	0.49	0.14	0.30	0.30	0.00
18	61.65	11.29	10.94	0.00	11.73	3.18	14.92	0.52	0.14	0.25	0.30	0.00
19	61.65	11.29	7.96	2.98	11.73	3.18	14.92	0.52	0.14	0.30	0.25	0.00

[#] 1 wt% Li₂O replaced 1 wt% Na₂O; Sb₂O₃ used in refining removed

* Sb₂O₃ used for refining

10

Examples 20 through 37 of glass compositions of the present invention provided in Table IV were prepared by providing mixtures of ingredients covering 68-73 weight percent perlite, 0-13 weight percent dolomite, 4-16 weight percent limestone and 12-17 weight percent soda. The specific amounts of perlite, limestone, soda and/or dolomite used to produce Examples 20 through 37 were determined by reference to the compositional parameters of each mineral in relation to the desired compositional parameters of each glass composition. Mixtures of the minerals were subsequently heated to a temperature of about 1400°C to obtain molten glass compositions. The molten glass compositions were cooled to provide glass compositions of Examples 20 through 37.

15

20

Table IV – Glass Compositions

Ex	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	R ₂ O	Fe ₂ O ₃	TiO ₂	SO ₃	F	M _x O _y
20	61.14	11.17	11.05	0.00	12.26	3.15	15.41	0.49	0.14	0.30	0.30	0.00
21	60.78	11.10	11.65	0.00	12.31	3.13	15.44	0.50	0.14	0.20	0.20	0.00
22	60.74	11.09	8.65	2.99	12.31	3.13	15.44	0.50	0.14	0.20	0.25	0.00
23	61.01	10.77	8.25	2.97	12.30	3.91	16.20	0.58	0.07	0.02	0.12	0.00
24	60.64	10.71	8.80	2.96	12.22	3.88	16.10	0.58	0.07	0.02	0.12	0.00
25	60.94	10.76	8.79	2.54	12.28	3.90	16.18	0.58	0.07	0.02	0.12	0.00
26	60.22	10.63	9.15	2.52	10.54	3.86	14.40	2.88	0.07	0.02	0.11	0.00
27	60.92	10.76	8.24	2.97	12.28	3.90	16.18	0.58	0.07	0.18	0.12	0.00
28	60.55	10.69	8.78	2.96	12.20	3.88	16.08	0.58	0.07	0.18	0.12	0.00
29	60.84	10.74	8.77	2.54	12.26	3.90	16.15	0.58	0.07	0.18	0.12	0.00
30	60.12	10.62	9.13	2.51	10.53	3.85	14.38	2.88	0.07	0.17	0.11	0.00
31	55.33	9.77	12.86	5.38	4.59	3.54	8.13	0.54	0.06	0.07	0.11	7.75*

32	58.03	10.25	13.49	5.64	4.81	3.71	8.53	0.56	0.07	0.07	0.11	3.25*
33	55.59	9.82	6.17	3.06	10.03	3.56	13.59	0.53	0.06	0.07	0.11	11.01*
34	62.34	14.32	11.20	0.38	9.04	2.17	11.21	0.34	0.04	0.11	0.06	0.00
35	62.87	11.50	7.98	0.00	13.25	3.24	16.50	0.51	0.14	0.30	0.20	0.00
36	61.14	11.17	10.06	0.00	13.25	3.15	16.40	0.49	0.14	0.30	0.30	0.00
37	60.25	11.01	9.00	1.98	12.70	3.54	16.24	0.81	0.03	0.12	0.00	0.00

* B₂O₃ used as additives

** ZnO used to replace 1 wt% Na₂O and 1 wt% CaO plus Sb₂O₃ removal

The glass composition of Example 38 provided in Table V was prepared in
5 accordance with the glass composition of Example 12 above, except 1 wt% Li₂O was used to
replace 1 wt% Na₂O and any Sb₂O₃ used during refining was removed. The glass
composition of Example 39 in Table V was prepared in accordance with the glass
composition of Example 12 above, except ZnO was used to replace 1 wt% Na₂O and 1 wt%
CaO and any Sb₂O₃ used during refining was removed.

10

Table V – Glass Compositions

Ex.	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	R ₂ O	Fe ₂ O ₃	TiO ₂	SO ₃	F	M _x O _y
38	61.93	11.34	7.99	3.00	10.29	3.20	13.49	0.52	0.14	0.30	0.30	1.00
39	61.93	11.34	6.99	3.00	10.29	3.20	13.49	0.52	0.14	0.30	0.30	2.00

Examples 40 through 71 of glass compositions of the present invention provided in
Table VI were prepared in accordance with the glass composition of Example 12 above,
15 except the glass compositions were designed to include various combinations of Li₂O, La₂O₃,
MnO₂, TiO₂, ZnO and ZrO₂. Various amounts of Li₂CO₃, La₂O₃, MnO₂, TiO₂, ZnO and ZrO₂
were incorporated into the batch composition of Example 12 to produce Examples 39-70.
Moreover, each of the glass compositions of Examples 39-70 also included 0.09 wt% SO₃,
0.27-0.28 wt% F and 0.53-0.55 wt% Fe₂O₃.

20

Table VI – Glass Compositions

Ex.	SiO ₂	Al ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	R ₂ O	Li ₂ O	ZnO	ZrO ₂	TiO ₂	La ₂ O ₃	MnO ₂
40	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	0.91	0.91	2.74	0.91	2.74
41	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	2.74	0.91	2.74	0.91	0.91
42	57.22	10.52	7.38	2.77	10.33	3.01	13.34	1.38	0.92	2.77	0.92	0.92	0.92
43	54.70	10.06	7.06	2.65	9.87	2.87	12.75	0.44	2.65	0.88	2.65	2.65	2.65
44	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	2.67	0.89	0.89	2.67	2.67
45	53.29	9.80	6.88	2.58	9.62	2.80	12.42	1.29	2.58	2.58	2.58	2.58	2.58
46	54.70	10.06	7.06	2.65	9.87	2.87	12.75	0.44	2.65	2.65	2.65	0.88	2.65
47	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	0.89	2.67	2.67	0.89	2.67
48	58.85	10.82	7.59	2.85	10.62	3.09	13.72	0.47	0.95	0.95	0.95	0.95	0.95

49	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	0.91	2.74	0.91	2.74	0.91
50	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	2.74	0.91	0.91	2.74	0.91
51	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	2.67	0.89	2.67	2.67	0.89
52	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	2.67	2.67	0.89	2.67	0.89
53	54.70	10.06	7.06	2.65	9.87	2.87	12.75	0.44	2.65	2.65	0.88	2.65	2.65
54	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	0.91	0.91	2.74	2.74	0.91
55	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	0.89	0.89	2.67	2.67	2.67
56	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	0.89	2.67	2.67	2.67	0.89
57	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	0.91	2.74	0.91	0.91	2.74
58	57.22	10.52	7.38	2.77	10.33	3.01	13.34	1.38	2.77	0.92	0.92	0.92	0.92
59	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	2.67	0.89	2.67	0.89	2.67
60	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	0.91	0.91	0.91	2.74	2.74
61	57.22	10.52	7.38	2.77	10.33	3.01	13.34	1.38	0.92	0.92	2.77	0.92	0.92
62	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	2.67	2.67	2.67	0.89	0.89
63	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	2.74	2.74	0.91	0.91	0.91
64	54.70	10.06	7.06	2.65	9.87	2.87	12.75	0.44	0.88	2.65	2.65	2.65	2.65
65	57.22	10.52	7.38	2.77	10.33	3.01	13.34	1.38	0.92	0.92	0.92	0.92	2.77
66	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	0.89	2.67	0.89	2.67	2.67
67	54.70	10.06	7.06	2.65	9.87	2.87	12.75	0.44	2.65	2.65	2.65	2.65	0.88
68	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	2.74	0.91	0.91	0.91	2.74
69	55.18	10.15	7.12	2.67	9.96	2.90	12.86	1.34	2.67	2.67	0.89	0.89	2.67
70	57.22	10.52	7.38	2.77	10.33	3.01	13.34	1.38	0.92	0.92	0.92	2.77	0.92
71	56.70	10.43	7.32	2.74	10.23	2.98	13.21	0.46	0.91	2.74	2.74	0.91	0.91

I. Melt Properties

The melt properties of several glass compositions of Examples 1 through 71 were investigated. Investigation of the melt properties of glass compositions of the present invention assisted in the determination of how various compositional parameters affect processing considerations including forming temperatures (T_F) and liquidus (T_L) temperatures of the glass compositions.

The measurement of melt viscosity for determining forming temperatures of various glass compositions of the present invention was done by the counter-balance method over the viscosity range of $10^2 - 10^5$ Poise. The apparatus used to execute the method was calibrated using NIST standard glass. Figure 2 shows schematics of the apparatus.

The apparatus (1) for measuring melt viscosity comprised a platinum ball (2) with a diameter of 16 mm. The platinum ball (2) was hung on a thin platinum wire (6) with the help of a special bracket/holder (11) attached to the right scale of the analytical balance. Initially, the first the end of the platinum wire (6) was attached to the bracket/holder at point A. After warming the furnace (9), the platinum ball was placed in the sample melt inside the crucible (3) and the first end of the wire was attached to the bracket/holder at point B to locate the platinum ball (2) in the center of the melt. The distance between the platinum ball (2) and the

walls of the crucible (3) was 13-15 mm. If the distance were smaller, it would affect the precision of the measurement.

The movement of the platinum ball (3) in the melt was performed by changing the weight of the rider. The speed of the movement of the ball in the melt was defined in relative numbers of the balance indicator shift that was observed on the balance scale. When the balance indicator moved 100 points to both sides from zero position, the ball in the melt shifted 1.7 mm from the central position up and down. The sensitivity of the balance was 10 mg per 100 points. A Pt/PtRh thermocouple was placed in the furnace next to the crucible (3) and provided automatic temperature control of the furnace. The hot end of another thermocouple (5) was inside the crucible (10) filled with Al_2O_3 powder. This thermocouple was connected with the potentiometer to control the furnace temperature at the set point. The temperature control had a precision $\pm 1.5^\circ\text{C}$.

During the testing, the platinum ball (2) moved from a marked upper position in the melt to a lower marked position under its gravity, the time of which was recorded using a stopwatch with the precision within 0.1 second. The time of the balance scale shift to 20 – 60 scale divisions was measured depending on the viscosity of the melt. The speed of the platinum ball (2) movement (per scale division/seconds) was taken as an average value of six measurements.

Using the velocity (V) – weight (G) data, a plot of V – G was constructed for each glass composition under investigation, all of which showed straight lines passing through the point of origin of the V – G coordinates. The slope k of each line was correlated with melt viscosity in a form of:

$$\log \eta = a * \log (tgk) + b$$

where a (1.09) and b (0.87) were constants determined from cell calibration using a NIST standard glass (710A). The relative error in defining viscosity was within 3% over the viscosity range, $2.5 < \log \eta < 3.5$, and within 4 – 6% over the range, $\log \eta < 2.5$ and $\log \eta > 3.5$.

The measurement of glass composition liquidus temperature (T_L) was conducted in a tube type gradient furnace with maximum temperature 1250°C . The furnace chamber had a dimension of 480 mm in length and 50 mm in diameter. The geometry and dimension of the furnace were close to those recommended by the ASTM C829 – 81. Figure 3 illustrates the

position of the thermocouple and the number of turns of the heating coil. The coil was made of NiCr resistance alloy wires with diameter of 2 mm.

Table VII summarizes measured liquidus temperature (T_L) and reference temperature of forming (T_F) defined by melt viscosity of 1000 Poise for glass compositions of Examples 1-22. Glass compositions of Examples 1-6 demonstrated liquidus temperatures greater than 1240°C, the upper limit of the gradient temperature furnace setting. As a result, no viscosity measurements were made for these compositions for a determination of forming temperature. Moreover, several glass compositions displayed desirable melt properties by having lower liquidus and forming temperatures while maintaining a difference in liquidus temperature and forming temperature of at least 65°C. Examples 18, 20 and 21 each provided a forming temperature under 1222°C while maintaining a difference in liquidus and forming temperature of at least 75°C.

Table VII – Melt Properties of Glass Compositions

Example	T_L (°C)	T_F (°C)	Delta T ($T_F - T_L$) (°C)
1	1235	1226	-9
2	>1240		
3	>1240		
4	>1240		
5	>1240		
6	>1240		
7		1296	
8	1190	1265	75
9		1290	
10	1185	1246	61
11	1190	1236	46
12	1130	1265	135
13	1185	1224	39
14	1155	1248	93
15	1085	1250	165
16	1170	1225	55
17	1180	1204	24
18	1135	1222	87
19	1090	1252	162
20	1140	1220	80
21	1130	1205	75
22	1120	1262	142

Table VIII summarizes measured liquidus temperature (T_L) and the forming (T_F) temperature for glass compositions of Examples 40 through 71 as a function of weight percent of Li_2O in the glass compositions. As provided in Table VIII, Li_2O plays a significant role in lowering the liquidus and forming temperatures of glass compositions of the present invention with minimum reductions in forming and liquidus temperatures being 30°C and 43°C respectively.

Table VIII – Melt Properties of Glass Compositions

EX.	High Li_2O (1.5 wt %)			EX.	Low Li_2O (0.5 wt %)		
	T_F °C	T_L °C	Delta T °C		T_F °C	T_L °C	Delta T °C
42	1148	1060	88	40	1187	1100	87
44	1156	1054	102	41	1176	1073	103
45	1157	1065	92	43	1165	1083	82
47	1145	1058	87	46	1179	1081	98
51	1142	1067	82	48	1210	1096	114
52	1158	1054	104	49	1210	1098	112
55	1154	1031	123	50	1206	1086	120
56	1160	1024	136	53	1193	1084	109
58	1164	1062	102	54	1205	1090	115
59	1124	1054	70	57	1222	1074	148
61	1160	1054	106	60	1204	1087	117
62	1148	1043	105	63	1215	1068	147
65	1163	1065	98	64	1192	1073	119
66	1162	1057	105	67	1190	1073	117
69	1154	1060	94	68	1190	1087	103
70	1158	1060	98	71	1208	1073	135

Figure 4 provides temperature-viscosity curves for the glass composition of Example 18, two E-glass compositions and a C-glass composition. From Figure 4, it is noted that the temperature-viscosity characteristics of the glass composition of Example 18 are similar to those of the C-glass composition. Moreover, the viscosity change for the glass composition of Example 18 is not as steep as that provided for the E-glass compositions. As a result, the glass composition of claim 18 can be characterized as a “long” glass whereas the E-glass compositions are “short” glasses. Longer glasses, such as Example 18, in principle, favor fine filament production forming due to less forming tension as a result of slower reduction in melt viscosity over the forming temperature range right after fiber exit from the forming tip.

Figure 5 further illustrates the reduction in forming tension by providing molten glass surface tensions as a function of temperature for the glass composition of Example 22 in comparison two E-glass compositions . As provided in Figure 5, the glass composition of

Example 22 at the forming temperature has 9% and 14% lower surface tension than the E-glass compositions.

Figure 6 is a plot of the melt or molten glass density as a function of temperature for the glass composition of Example 22 in comparison with two E-glass compositions. As provided in Figure 6, the glass composition of Example 22 demonstrated a temperature dependency (slope) similar to the E-glass compositions but had a molten density 5% and 7% lower than the E-glass compositions respectively. As a result, glass fibers formed from some glass compositions of the present invention are lighter per unit volume in comparison to some E-glass fibers. Lighter glass fibers can be advantageous in many applications, particularly material reinforcement application, such as polymeric reinforcement applications, where weight savings are highly desirable. Moreover, as a result of lower densities, glass fibers formed from some glass compositions of the present invention can have larger diameters in comparison to some E-glass fibers of the same weight, thereby providing enhanced mechanical properties.

Figure 7 is a plot of electrical conductivity as a function of temperature for the glass composition of Example 25 in comparison with E-glass and C-glass compositions. As provided in Figure 7, the glass composition of Example 25 and the C-glass composition display much higher electrical conductivities than the E-glass due to their significantly higher alkali metal content. The melt conductivity of an inorganic glass composition is generally dominated by the mobile ions of sodium and potassium. As a result of low sodium and potassium ion content in E-glass compositions, electrical melting technology is only used as a secondary boost system for E-glass processing. However, electrical melting technology has been used as a primary energy for the processing of C-glass compositions. Given that glass compositions of the present invention, in some embodiments, demonstrate higher melt conductivities than some C-glass compositions, electrical melting technology may find application to processing glass compositions of the present invention.

Additionally, glass compositions of the present invention formed from batch compositions comprising perlite and/or pumice, in some embodiments, require less energy for converting the batch composition to a glass melt composition. Figure 8 provides the energy required to convert the batch composition comprising perlite to the glass melt composition of Example 12. Figure 8 also provides the energy required to convert an E-glass batch composition to the associated glass melt. As shown in Figure 8, the energy required to convert the batch composition of Example 12 into a glass melt composition was 20% less than the energy required to convert the E-glass batch composition to glass melt composition.

The energy required to convert a second E-glass batch composition to a glass melt composition was also compared with the energy required to convert the batch composition of Example 12 into a glass melt composition. The energy required to convert the batch composition of Example 12 was about 33% percent lower than the energy to convert the second E-glass batch composition to a glass melt composition.

5 II. Acid and Alkaline Corrosion Resistance

Fibers formed from glass compositions of the present invention were made in a laboratory using a single tip bushing set up. To compare with commercial glass fiber 10 corrosion resistance under the same testing conditions, AR-, C-, ECR- and E-glass fibers were also made using the same method using cullet.

Glass fiber resistance to corrosion was evaluated in terms of the relative sample 15 percent weight loss after leaching test. Testing was administered by boiling a fiber strand at 100°C for one hour in sulfuric acid or sodium hydroxide solutions under various pH conditions. All of the tests were performed by keeping ratio of solution volume to the sample mass or volume (5,000 m²) constant. 50 ml of the solution and of 1.375 gram (filament diameter - 22 µm) were used for each test. Triplicate samples were tested to determine average sample weight losses. The results of the acid and alkaline corrosion resistance testing are provided in Table IX.

Table IX – Acid and Alkaline Corrosion Resistance Results (% Weight Loss)

pH	0 1N H ₂ SO ₄	2 0.1N H ₂ SO ₄	12 0.1N NaOH	14 1N NaOH	Note
E-glass (1)	1.02	0.19	0.29	1.24	0 B ₂ O ₃
E-glass (2)	1.04	0.00	0.51	0.92	1.3 B ₂ O ₃
E-glass (3)	17.79		0.87	1.62	6.0 B ₂ O ₃
ECR	0.66	0.00	0.13	1.11	0 B ₂ O ₃ + 4 ZnO
C-Glass ²	0.09	0.13	0.36	7.83	0 B ₂ O ₃
AR-Glass I ³	0.10	0.00	0.00	0.10	17 ZrO ₂
Ex 10	1.12	0.21	0.84	6.42	Baseline
Ex 11	3.58	0.15	0.38	5.60	1%ZrO ₂ + 3% TiO ₂
Ex 12	4.38	0.21	0.62	2.23	2.9 ZrO ₂ + 1.1% TiO ₂
Ex 13	4.79	0.64	0.40	1.01	8% ZrO ₂
Ex 12	0.59	0.22	0.26	8.13	baseline
Ex 38	1.50	0.09	0.68	11.02	
Ex 18	3.10				
Ex 19	0.69	0.66	0.31	8.47	
Ex 57	2.20			2.29	
Ex 58	2.75			3.81	
Ex 59	5.35			5.54	
Ex 63	1.64			2.89	
Ex 67	1.35			3.57	
Ex 71	1.19			3.30	

¹ The average determined from three individual tests and standard deviation is not greater than 0.1 %.

² C-glass (wt%): 66 SiO₂, 5.5 Al₂O₃, 10.4 CaO, 3.6 MgO, 0.3 Fe₂O₃, 0.2 K₂O, 12.5 Na₂O, 0.5F and 0.2 SO₃.

³ AR-glass (wt%): 57 SiO₂, 3.2 Al₂O₃, 15 ZrO₂, 4.2 CaO, 0.1 MgO, 0.1 Fe₂O₃, 0.1 K₂O, 12 Na₂O, 0.5 F and 0.23 SO₃.

5

III. Mechanical Testing

Tensile strengths of fibers formed from the glass composition of Example 37 of the present invention were measured by drawing 10-um diameter fibers from single tip bushing in laboratory. The fibers were subsequently tested by applying tensile force to the fibers from both ends within the same day of fiber forming. Figure 9 summarizes Weibull statistical analysis of the fiber strength with an average of about 3050 MPa and standard error of 22.4 MPa for sample size of 57. Except for the tail, the strength fit the single Weibull distribution well suggesting a single failure mode dominates the fiber failure.

Fiber sonic tensile modulus was measured by drawing 30-um diameter fibers comprising the glass composition of Example 37 of the present invention from a single tip bushing in laboratory. The fibers were subsequently tested by applying dead weight from both ends to measure velocity of sound traveling inside the fiber. Fiber density was also measured. The elastic modulus was calculated using $E = \rho C^2$ where E, ρ , and C are modulus, density, and sound velocity, respectively. Fibers of two sets were formed at two different temperatures, the first set at 1000 Poise melt viscosity (Low T Forming) and the second set at 50°C higher than the first set. (High T Forming) Table X summarizes the statistical analysis of the fiber modulus with an average of about 56.8 GPa and 61.5 GPa for low and high forming temperature cases, respectively.

25

Table X – Tensile Modulus

Statistics	Low T Forming	High T Forming
Mean (GPa)	56.79	61.47
Std Dev (GPa)	4.41	6.73
Std Err Mean (GPa)	0.99	1.37
upper 95% Mean	58.86	64.31
lower 95% Mean	54.73	58.62
Sample Size N	20	24
Fiber Diameter (μm)	29.96 ± 0.36	30.17 ± 0.42
Fiber Density (g/cm ³)	2.356 ± 0.006	2.251 ± 0.028

Desirable characteristics, which can be exhibited by embodiments of the present invention, can include, but are not limited to, the provision of new glass compositions that utilize glassy minerals; the provision of new glass compositions that utilize perlite; the provision of batch compositions requiring less energy to form melts of glass compositions; 5 the provision of new glass compositions demonstrating significant differences in liquidus and forming temperatures; the provision of glass fibers having reduced weights without a concomitant reduction in mechanical properties; and the provision of glass fibers demonstrating desirable acid and alkaline corrosion resistance properties.

It is to be understood that the present description illustrates aspects of the invention 10 relevant to a clear understanding of the invention. Certain aspects of the invention that would be apparent to those of ordinary skill in the art and that, therefore, would not facilitate a better understanding of the invention have not been presented in order to simplify the present description. Although the present invention has been described in connection with certain embodiments, the present invention is not limited to the particular embodiments disclosed, 15 but is intended to cover modifications that are within the spirit and scope of the invention, as defined by the appended claims.

That which is claimed:

1. A glass composition comprising:
 - 53-64 weight percent SiO₂;
 - 8-12 weight percent Al₂O₃;
 - 8.5-18 weight percent alkali oxide component (R₂O); and
 - 5 a metal oxide (RO) component,
wherein the metal oxide component is present in an amount to provide a ratio R₂O / RO ranging from about 0.15 to about 1.5.
2. The glass composition of claim 1, wherein the RO component is present in an amount ranging from 7 weight percent to 31 weight percent.
- 10 3. The glass composition of claim 1, wherein the RO component comprises a mixture of metal oxides.
4. The glass composition of claim 3, wherein the RO component comprises a mixture of CaO and MgO.
- 15 5. The glass composition of claim 1, wherein the RO component comprises CaO in an amount ranging from 7 to 26 weight percent.
6. The glass composition of claim 1, wherein the RO component comprises MgO in an amount up to 5 weight percent.
7. The glass composition of claim 1, wherein the R₂O comprises Na₂O, K₂O or Li₂O or mixtures thereof.
- 20 8. The glass composition of claim of claim 1, wherein R₂O comprises Na₂O in an amount ranging from 6.5 to 16 weight percent
9. The glass composition of claim of claim 1, wherein R₂O comprises K₂O in an amount ranging from 2 to 4 weight percent.
10. The glass composition of claim of claim 1, wherein R₂O comprises Li₂O in an amount 25 up to 2 weight percent.
11. The glass composition of claim 1 further comprising ZrO₂ in an amount up to 8 weight percent.
12. The glass composition of claim 1, wherein the RO component comprises ZnO in an amount up to 3 weight percent.
- 30 13. The glass composition of claim 1 further comprising MnO₂ in an amount up to 3 weight percent.
14. The glass composition of claim 1 further comprising TiO₂ in an amount up to 3 weight percent.

15. The glass composition of claim 1 further comprising La_2O_3 in an amount up to 3 weight percent.

16. The glass composition of claim 1 having a fiber forming temperature ranging from about 1120°C to about 1300°C .

5 17. The glass composition of claim 1, wherein the difference between forming temperature and liquidus temperature of the glass composition is at least about 65°C .

18. The glass composition of claim 1, wherein the difference between forming temperature and liquidus temperature of the glass composition ranges from about 45°C to about 165°C .

10 19. A glass composition formed from a batch composition comprising:
at least 50 weight percent of a glassy mineral, the glassy mineral comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent; and
at least 5 weight percent of a sodium source.

15 20. The glass composition of claim 19, wherein the batch comprises at least 60 weight percent of the glassy mineral.

21. The glass composition of claim 19, wherein the batch comprises at least 65 weight percent of the glassy mineral.

22. The glass composition of claim 19, wherein the batch comprises at least 10 weight percent of the sodium source.

20 23. The glass composition of claim 19, wherein the glassy mineral comprises perlite, pumice or mixtures thereof.

24. A method of producing a glass composition comprising:
providing a batch composition comprising at least 50 weight percent of a glassy mineral and at least 5 weight percent of a sodium source, the glassy comprising a combination of SiO_2 and Al_2O_3 in an amount of at least 80 weight percent; and
heating the batch to form a melt of the glass composition.

25 25. The method of claim 24, wherein the batch composition is heated to a fiber forming temperature ranging from about 1120°C to about 1300°C .

26. The method of claim 25 further comprising fiberizing the glass composition.

30 27. A glass composition comprising:
56-63 weight percent SiO_2 ;
9-12 weight percent Al_2O_3 ;
12-17 weight percent RO ($\text{CaO} + \text{MgO}$);
12-14 weight percent R₂O ($\text{Na}_2\text{O} + \text{K}_2\text{O}$);

0-2 weight percent Li_2O ;
0-3 weight percent ZnO ;
0-3 weight percent ZrO_2 ;
0-3 weight percent MnO_2 ; and
5 0-3 weight percent La_2O_3 .

28. A glass composition comprising:
60-64 weight percent SiO_2 ;
9-12 weight percent Al_2O_3 ;
7-15 weight percent RO ($\text{CaO} + \text{MgO}$); and
10 13-15.5 weight percent R_2O ($\text{Na}_2\text{O} + \text{K}_2\text{O}$);
0-2 weight percent Li_2O ;
0-3 weight percent ZnO ;
0-3 weight percent ZrO_2 ;
0-3 weight percent MnO_2 ; and
15 0-3 weight percent La_2O_3 .

29. A glass composition comprising:
54-63 weight percent SiO_2 ;
9-14 weight percent Al_2O_3 ;
11-16.5 weight percent RO ($\text{CaO} + \text{MgO}$); and
20 14-17 weight percent R_2O ($\text{Na}_2\text{O} + \text{K}_2\text{O}$);
0-2 weight percent Li_2O ;
0-3 weight percent ZnO ;
0-3 weight percent ZrO_2 ;
0-3 weight percent MnO_2 ; and
25 0-3 weight percent La_2O_3 .

30. The glass compositions of any of claims 27 to 29, wherein the glass composition comprises less than 0.7 weight percent Fe_2O_3 .

31. A glass fiber comprising:
53-64 weight percent SiO_2 ;
30 8-12 weight percent Al_2O_3 ;
8.5-18 weight percent alkali oxide (R_2O) component; and
a metal oxide (RO) component, wherein the metal oxide component is present in an amount to provide a mass ratio of $\text{R}_2\text{O}/\text{RO}$ ranging from about 0.15 to about 1.5.

32. A polymeric composite comprising:
a polymeric material; and
at least one glass fiber in the polymeric material, the at least one glass fiber comprising:

5 53-64 weight percent SiO₂;
8-12 weight percent Al₂O₃;
8.5-18 weight percent alkali oxide (R₂O) component; and
a metal oxide (RO) component, wherein the metal oxide component is present in an amount to provide a mass ratio of R₂O/RO ranging from about 0.15 to about 1.5.




FIGURE 1




FIGURE 2

SUBSTITUTE SHEET (RULE 26)

Dimension in Millimeters




FIGURE 3




FIGURE 4




FIGURE 5




FIGURE 6




FIGURE 7





FIGURE 8

**Weibull Parameter Estimates**same as Extreme-Value with $a = \exp(\beta)$, $\beta = 1/d$

Parameter	Estimate	Lower 95%	Upper 95%	Number failed
a	3125.9396	3087.6973	3163.0663	57
β	23.10284	18.517975	28.270664	57

Summary

Group	Number failed	Number censored	Mean	Std Error
Combined	57	0	3050.74	22.3631

FIGURE 9