

[54] FUEL COMPOSITIONS AND ADDITIVE
MIXTURES FOR REDUCING THE
PLUGGING OF EXHAUST GAS CATALYSTS

3,585,012 6/1971 Licke 44/72
3,700,598 10/1972 Plonsker et al. 44/72

[75] Inventor: Larry Plonsker, Baton Rouge, La.

Primary Examiner—Daniel E. Wyman

[73] Assignee: Ethyl Corporation, Richmond, Va.

Assistant Examiner—Y. Harris Smith

[22] Filed: June 27, 1974

Attorney, Agent, or Firm—Donald L. Johnson; Robert
A. Linn

[21] Appl. No.: 483,642

[52] U.S. Cl. 44/68; 44/72

[51] Int. Cl.² C10L 1/22

[58] Field of Search 44/68, 72

[56] References Cited

UNITED STATES PATENTS

3,328,440 6/1967 Shapiro et al. 44/68
3,558,291 1/1971 Abowd, Jr. 44/72

[57]

ABSTRACT

Gasoline compositions and additive mixtures of esters of nitrilotriacetic acid, in amount sufficient to alleviate the plugging of certain catalysts being used in an engine exhaust system to lower the amount of undesirable constituents in exhaust gas from an engine being operated on gasoline containing a cyclopentadienyl manganese antiknock.

40 Claims, No Drawings

FUEL COMPOSITIONS AND ADDITIVE MIXTURES FOR REDUCING THE PLUGGING OF EXHAUST GAS CATALYSTS

BACKGROUND OF THE INVENTION

Cyclopentadienyl manganese compounds are excellent antiknocks in gasoline used to operate internal combustion engines. These manganese compounds have proved to be especially beneficial in solving some of the problems present when low-lead or lead-free gasolines are used with internal combustion engines. Use of such compounds as antiknocks is described in U.S. Pat. Nos. 2,818,417, 2,839,552, and 3,127,351, incorporated herein by reference. Not only are these compounds effective antiknock compounds, but it has also been found that they do not adversely affect the activity of oxidation metal catalysts used to decrease the amount of undesirable constituents in engine exhaust gas. Under some operating conditions it has been found that, although the manganese antiknocks do not lessen the activity of the exhaust gas catalyst, they can interact in some manner at the surface of the catalyst bed leading to a reduction in the size of the openings into the bed thereby causing an increase in exhaust backpressure and a decrease in the effective life of said catalysts. The present invention provides a simple effective means of alleviating this problem.

It has been previously suggested that the addition of triethyl citrate to gasoline mixes containing organomanganese antiknocks tends to reduce catalyst plugging. The use of triethyl citrate, however, has proved to be of rather limited success in reducing the plugging problem, especially at higher temperatures.

SUMMARY

According to the present invention, the useful life of an exhaust gas catalyst in an exhaust system of an engine operating on gasoline containing a cyclopentadienyl manganese antiknock is greatly increased by providing new additive fluids and gasoline compositions which contain an amount of nitrilotriacetic acid or gasoline soluble derivative thereof sufficient to alleviate plugging of the exhaust gas catalyst.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The essence of the present invention resides in reducing the plugging of oxidation metal catalytic apparatus for purifying exhaust gases of internal combustion engines which burn a gasoline containing an organomanganese compound. This reduction in plugging is effected by the addition of esters of nitrilotriacetic acid, its gasoline soluble salts, or other gasoline soluble derivatives to the gasoline. Accordingly, a preferred embodiment is a gasoline suitable for use in an internal combustion engine and containing an amount of organomanganese compound, preferably a cyclopentadienyl manganese tricarbonyl, sufficient to increase its antiknock effectiveness, and also containing an amount sufficient to prevent plugging of the catalyst of esters of nitrilotriacetic acid, its gasoline soluble salts, or other gasoline soluble derivatives.

A further embodiment of the present invention is a gasoline additive fluid composition comprising an organomanganese compound, preferably a cyclopentadienyl manganese tricarbonyl, and most preferably methylcyclopentadienyl manganese tricarbonyl, in an

amount sufficient to improve the antiknock characteristics of the gasoline and esters of nitrilotriacetic acid, its gasoline soluble salts and other gasoline soluble derivatives, preferably the mono-, di-, and triesters of nitrilotriacetic acid, and most preferably the triesters of nitrilotriacetic acid, in an amount sufficient to reduce catalyst plugging.

Since the invention also embodies the operation of an internal combustion engine in a manner which results in reduced plugging of the catalyst, a still further embodiment is a method of operating an internal combustion engine using a gasoline containing an organomanganese, preferably a cyclopentadienyl manganese tricarbonyl, and most preferably methylcyclopentadienyl manganese tricarbonyl antiknock in a manner which results in substantial reduction in the plugging of the catalyst, said method comprising (a) supplying to the fuel induction system of said engine a gasoline containing an organomanganese antiknock and a gasoline soluble solution of the esters of nitrilotriacetic acid, its salts, or other gasoline soluble derivatives, (b) mixing said gasoline with air, (c) inducting the mixture into the combustion chambers of said engine, (d) compressing said mixture, (e) igniting said compressed mixture, and (f) exhausting the resultant combustion products which have a reduced plugging effect on the catalyst through said catalyst.

Liquid hydrocarbon fuels of the gasoline boiling range are mixtures of hydrocarbons having a boiling range of from about 80°F. to about 430°F. Of course, these mixtures can contain individual constituents boiling above or below these figures. These hydrocarbon mixtures contain aromatic hydrocarbons, saturated hydrocarbons and olefinic hydrocarbons. The bulk of the hydrocarbon mixture is obtained by refining crude petroleum by either straight distillation or through the use of one of the many known refining processes, such as thermal cracking, catalytic cracking, catalytic hydroforming, catalytic reforming, and the like. Generally, the final gasoline is a blend of stocks obtained from several refinery processes. The final blend may also contain hydrocarbons made by other procedures such as alkylate made by the reaction of C_4 olefins and butanes using an acid catalyst such as sulfuric acid or hydrofluoric acid.

Preferred gasolines are those having a Research Octane Number of at least 85. A more preferred Research Octane Number is 90 or greater. It is also preferred to blend the gasoline such that it has a content of aromatic hydrocarbons ranging from 10 to about 60 volume percent, an olefinic hydrocarbon content ranging from 0 to about 30 volume percent, and a saturate hydrocarbon content ranging from about 40 to 80 volume percent, based on the whole gasoline.

In order to obtain fuels having properties required by modern automotive engines, a blending procedure is generally followed by selecting appropriate blending stocks and blending them in suitable proportions. The required octane level is most readily accomplished by employing aromatics (e.g., BTX, catalytic reformat or the like), alkylate (e.g., C_{6-9} saturates made by reacting C_4 olefins with isobutane using a HF or H_2SO_4 catalyst), or blends of different types.

The balance of the whole fuel may be made up of other components such as other saturates, olefins, or the like. The olefins are generally formed by using such procedures as thermal cracking, catalytic cracking and polymerization. Dehydrogenation of paraffins to ole-

3 fins can supplement the gaseous olefins occurring in the refinery to produce feed material for either polymerization or alkylation processes. The saturated gasoline components comprise paraffins and naphthenes. These saturates are obtained from (1) virgin gasoline by distillation (straight run gasoline), (2) alkylation processes (alkylates) and (3) isomerization procedures (conversion of normal paraffins to branched chain paraffins of greater octane quality). Saturated gasoline components also occur in so-called natural gasolines. In addition to the foregoing, thermally cracked stocks, catalytically cracked stocks and catalytic reformates contain saturated components.

The classification of gasoline components into aromatics, olefins and saturates is well recognized in the art. Procedures for analyzing gasolines and gasoline components for hydrocarbon composition have long been known and used. Commonly used today is the FIA analytical method involving fluorescent indicator adsorption techniques. These are based on selective adsorption of gasoline components on an activated silica gel column, the components being concentrated by hydrocarbon type in different parts of the column. Special fluorescent dyes are added to the test sample and are also selectively separated with the sample fractions to make the boundaries of the aromatics, olefins and saturates clearly visible under ultraviolet light. Further details concerning this method can be found in "1969 Book of ASTM Standards," January 1969 Edition, under ASTM Test Designation D 1319-66T.

The motor gasolines used in formulating the improved fuels of this invention generally have initial boiling points ranging from about 80° to about 105°F. and final boiling points ranging from about 380° to about 430°F. as measured by the standard ASTM distillation procedure (ASTM D-86). Intermediate gasoline fractions boil away at temperatures within these extremes.

From the standpoint of minimizing atmospheric pollution to the greatest extent possible, it is best to keep the olefin content of the fuel as low as can be economically achieved as olefins reportedly give rise to smog-forming emissions, especially from improperly adjusted vehicular engines. Accordingly, in the preferred base stocks of this invention the olefin content will not exceed about 10 volume percent and the most particularly preferred fuels will not contain more than about 5 percent olefins. Table I illustrates the hydrocarbon type makeup of a number of particularly preferred fuels for use in this invention.

TABLE I

Hydrocarbon Blends of Particularly Preferred Base Fuels			
Fuel	Volume Percentage		
	Aromatics	Olefins	Saturates
A	35.0	2.0	63.0
B	40.0	1.5	58.5
C	20.0	2.5	77.5
D	33.5	1.0	65.5
E	36.5	2.5	61.0
F	43.5	1.5	55.0
G	49.5	2.5	48.0

It is also desirable to utilize base fuels having a low sulfur content as the oxides of sulfur tend to contribute an irritating and choking character to smog and other forms of atmospheric pollution. Therefore, to the extent it is economically feasible, the fuel will contain not more than about 0.1 weight percent of sulfur in the

form of conventional sulfur-containing impurities. Fuels in which the sulfur content is no more than about 0.02 weight percent are especially preferred for use in this invention.

Normally the gasoline to which this invention is applied is lead-free or substantially lead-free, although small amounts of organolead additives usually employed to give fuels of improved performance quality such as tetraalkyllead antiknocks including tetramethyllead, tetraethyllead, physical or redistributed mixtures of tetramethyllead and tetraethyllead, and the like may be present therein. The gasoline may also contain antiknock quantities of other agents such as cyclopentadienyl nickel nitrosyl, N-methyl aniline, and the like. Antiknock promoters such as tert-butyl acetate may be included. The gasoline may further contain blending agents or supplements such as methanol, isopropanol, t-butanol and the like. Antioxidants such as 2,6-di-tert-butylphenol, 2,6-di-tert-butyl-p-cresol, phenylenediamines such as N,N'-di-sec-butyl-p-phenylenediamine, N-isopropylphenylenediamine, and the like, may be present. Likewise, the gasoline can contain dyes, metal deactivators, or other types of additives recognized to serve some useful purpose in improving the gasoline quality.

Cyclopentadienyl manganese tricarbonyls are known antiknocks and their preparation and use are described in U.S. Pat. Nos. 2,818,417, 2,839,552, and 3,127,351. An important antiknock of this type is methylcyclopentadienyl manganese tricarbonyl. The amount of the cyclopentadienyl manganese tricarbonyl added to the gasoline should be an amount adequate to increase its antiknock effectiveness. This has generally been found to be in the range of from about 0.005 to 10 grams per gallon of manganese as a cyclopentadienyl manganese tricarbonyl. A preferred range is from about 0.05 to 6 gm (grams) of manganese per gallon as a cyclopentadienyl manganese tricarbonyl. A more preferred range is from about 0.05 to about 0.25 grams of manganese per gallon, and a most preferred range is from about 0.05 to about 0.125 grams of manganese per gallon as methylcyclopentadienyl manganese tricarbonyl.

The exhaust gas purification apparatus are well known and generally employ an oxidation catalytic metal such as platinum, rhodium, palladium, or iridium or combinations thereof. Some examples of catalytic converter units are described in U.S. Pat. Nos. 3,441,381 and 3,692,497. The essential elements of such units consist of a catalytic reactor formed by an enlarged cylindrical-frustoconical housing having an inlet port and an outlet port. Located within the housing is a catalyst bed which is a honeycomb alumina-magnesia-silica monolithic ceramic-supported platinum catalyst.

In order to obtain rapid warmup required for catalyst activation, the catalytic reactor is preferably located proximate to the engine exhaust outlet. By proximate is meant that it is close enough that the catalyst bed is rapidly heated to "light off" or activation temperature. The exhaust gas temperature required to accomplish this is dependent upon the nature of the catalyst. Noble metal catalysts containing at least some noble metal such as platinum, palladium or mixtures thereof, activate at lower exhaust temperatures, e.g., 350°-500°F. However, in order to ensure activation, the catalytic reactor is preferably located such that the inlet exhaust temperature is above about 1,000°F. and more preferably above about 1,400°F. during normal engine cruise


conditions. It is also at temperatures above about 1,400°F. and at concentrations of manganese of and above 0.25 gms per gallon that the cyclopentadienyl manganese antiknocks are most likely to plug the catalyst and, hence, it is under these conditions that the present invention is most useful. With concentrations of manganese of less than 0.25 gms per gallon and at temperatures under 1,400° F. plugging of the catalyst does not occur.

In tests run with the aforementioned catalytic converters containing monolithic ceramic supports it has been found that plugging occurs by "spikes" forming on the entrance surface of the cordierite ceramic. These form a network which essentially traps large manganese particles and caps the entrance to the monolithic core.

As stated above, the exhaust gas catalyst unit uses a honeycomb, monolithic ceramic, supported platinum catalyst. These are made by coating a corrugated ceramic structure with an activated alumina and a palladium compound. The preferred ceramics are made using alumina-silica, magnesia-alumina-silica (e.g., cordierite) or mixtures thereof. Palladium can be used in place of platinum, and since these elements generally occur in nature together, it is sometimes preferred to use mixtures of platinum and palladium.

The utility of the invention in alleviating plugging with noble metal catalysts suggests its use with other catalysts if an undesirable amount of plugging is noted. Many non-noble metals have been suggested for exhaust gas catalysts. Examples of other catalytic metals include V, Cr, Mn, Fe, Co, Ni, Cu, Zn, Zr, Na, Mo, Ru, Rh, Ag, W, Re, Os, Ir, Pb, Ba, and the like. These are generally used in an oxide form. They may be used individually or in various groupings such as Cu-Cr, Cu-Cr-V, Cu-Pd, Mn-Pd, Ni-Cr and the like. They may be supported on the above monolithic ceramic support or on any other of numerous well-known catalyst supports such as granular, pelletized, or extruded alumina, silica, silica-alumina, zirconia, magnesia, alumina-magnesia and the like.

The antiplugging agents of the present invention have the general formula



wherein R is independently selected from hydrogen, metals, hydrocarbyl radicals of preferably up to 20 carbon atoms, and substituted hydrocarbyl radicals. For purposes of this invention a hydrocarbyl radical can be defined as an organic group solely composed of hydrogen and carbon atoms. Some non-limiting representative examples of hydrocarbyl radicals are alkyl, cycloalkyl, alkenyl, aralkyl, alkaryl, and aryl.

Examples of alkyl groups represented by the R group in the above general formula are methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, n-amyl, and the various positional isomers thereof, and likewise the corresponding straight and branched chain isomers of hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, and the like.

When said R groups are cycloalkyl groups, they may be cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclononyl, cyclodecyl, cy-

cloundecyl, cyclododecyl, and the like. They may also be such cycloaliphatic groups as α -cyclopropyl-ethyl, α -cyclobutyl-propyl, β -cyclobutyl-propyl, and similar alkyl derivatives of the higher cycloalkyls.

The R groups in the above general formula may also be alkenyl groups such as ethenyl, 1-propenyl, 2-propenyl, isopropenyl, 1-butenyl, 2-butenyl, 3-butenyl, and the corresponding branched-chain isomers thereof as for example, 1-isobutenyl, 2-isobutenyl, 2-sec-butenyl, including 1-methylene-2-propenyl, and the various isomers of pentenyl, hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl, and dodecenyl, including 3,3-dimethyl-1-butenyl, 2,3-dimethyl-1-butenyl, 2,3-dimethyl-2-butenyl, 2,3-dimethyl-3-butenyl, 1-methyl-1-ethyl-2-propenyl, and the like.

When said R groups are alkaryl groups, they may be tolyl, 2,3-xylyl, 2,4-xylyl, 2,5-xylyl, 2,6-xylyl, 3,4-xylyl, 3,5-xylyl; o, m, and p-cumenyl, mesityl, o, m, and p-ethylphenyl, 2-methyl-1-naphthyl, 3-methyl-1-naphthyl, 4-methyl-1-naphthyl, 5-methyl-2-naphthyl, 6-methyl-3-naphthyl, 7-methyl-1-naphthyl, 8-methyl-4-naphthyl, 1-ethyl-2-naphthyl, and its various positional isomers and the like.

Examples of aryl groups which may be present in the above general formula are phenyl, naphthyl, and the like.

When said R groups are aralkyl groups, they may be benzyl, phenylethyl, 1-phenylpropyl, 2-phenylpropyl, 3-phenylpropyl, 1- and 2-isomers of phenylisopropyl, 1-, 2-, and 3-isomers of phenylbutyl, and the like.

The substituted hydrocarbyl radicals are hydrocarbyl radicals which contain substituents such as halogen, hydroxyl, carboxyl, alkoxycarbonyl, amino, or amide radicals. Thus, the three R groups may contain the same or different substituents or any one R group may contain one or more of said radicals substituted thereon.

As mentioned above, the R groups may be halogen substituted. Thus, chlorine, bromine, iodine, and fluorine may be substituted on the alkyl, cycloalkyl, alkenyl, alkaryl, aryl, and aralkyl groups which are present. Non-limiting examples of such substituted groups are chloromethyl, chloroethyl, bromoethyl, 2-fluoro-1,2-dibromoethyl, 1-iodopropyl, 2-fluoropropyl, 1-chlorobutyl, 2-bromobutyl, 2-iodo-2-methylpropyl, 1-chloropentyl, 3-fluoro-2-methylbutyl, 3-iodo-2-methylbutyl, 1-chloro-2,2-dimethylpropyl, 2-chloroheptyl, 3-fluorononyl, 1-chlorododecyl, and the like. Examples of halogenated cycloalkyl groups are chlorocyclopropyl, chlorocyclohexyl, 1,2-dichlorohexyl, bromocyclobutyl, iodocyclohexyl, and the like.

Examples of halogen-substituted alkenyl groups are bromoethenyl, chloroethenyl, iodoethenyl, 1-bromododecenyl, and the like.

Examples of halogenated alkaryl groups are chloro-o-tolyl, chloro-p-tolyl, chloro-m-tolyl, 2-bromo-3,4-xylyl, 4-bromo-2,3-xylyl, 5-bromo-2,4-xylyl, 2-bromo-4,5-xylyl, o, m, and p-tolyl, 3-bromomesityl, chloro(-methyl)-1-naphthyl, iodo(ethyl)-1-naphthyl, all positional isomers of the above, and the like.

Examples of halogen substituted aryl groups are bromophenyl, 2-bromo-1-naphthyl, 3-bromo-1-naphthyl and all positional isomers thereof, 2,4-dibromophenyl, 2,3-dibromophenyl, 2,5-dibromophenyl, 2,3,4,5-tetrabromophenyl, 2,3,5,6-tetrabromophenyl, pentabromophenyl, all isomers of chlorophenyl, and all isomers of multichlorophenyl: 2-chloro-1-naphthyl and

the remaining isomers thereof: 2,3-dichloro-1-naphthyl, 2,4-dichloro-1-naphthyl and the remaining positional isomers of dichloronaphthyl, 2,3,4,5-tetrachloro-1-naphthyl.

Amine groups may also be substituted on the R groups. Some non-limiting illustrative examples of R groups containing amine substituents are aminomethyl, 2-aminoethyl, 2,2-diaminoethyl, 2-aminoisopropyl, 5-aminopentyl, 1,2-aminododecyl, 1,2-diaminoethyl, 1,5-diaminopentyl, aminocyclobutyl, aminocyclohexyl, 3-amino-1-propen-1-yl, 5-amino-2-penten-1-yl, aminophenyl, (methylamino)phenyl, 2-amino-o-tolyl, 4-amino-m-tolyl, 3-amino-p-tolyl, and other positional isomers, various isomers of diaminophenyl, amino-2,5-xylyl, and various positional isomers thereof, 2-amino-1-naphthyl, 3-amino-1-naphthyl, 2-amino-3-methyl-1-naphthyl, 2,3-diamino-5-ethyl-1-naphthyl, and the like.


The R groups may contain amide groups which may be illustrated by such non-limiting examples as: carbamoylmethyl, 2-carbamoylethyl, 4-carbamoylbutyl, 8-carbamoyl-2-ethyloctyl, 1,4-dicarbamoylbutyl, carbamoylcyclopentyl, carbamoylcyclohexyl, 2-carbamoyl-o-tolyl, 2-carbamoyl-m-tolyl, 3-carbamoyl-p-tolyl, (carbamoylmethyl)phenyl, (2-carbamoylethyl)benzyl; o, m, and p-(carbamoylethyl)phenyl, and the like.

The preferred hydrocarbyls are the alkyls, especially the lower alkyls having from 1 to about 10 carbon atoms, with the more preferred alkyls being ethyl and methyl. The most preferred alkyl is ethyl.


Some examples of metals represented by the R groups are the monovalent and polyvalent metals, particularly the alkali metals, and especially sodium, potassium, and lithium. Useful metal salts are trisodiumnitrilotriacetate, tripotassiumnitrilotriacetate, and trilithiumnitrilotriacetate. Additional useful metal salts are disodiumnitrilotriacetate, monosodiumnitrilotriacetate, dipotassiumnitrilotriacetate, monopotassiumnitrilotriacetate, dilithiumnitrilotriacetate, monolithiumnitrilotriacetate, monosodiumdipotassiumnitrilotriacetate, disodiummonopotassiumnitrilotriacetate, and the like.

Corresponding esters wherein from 1 to 3 of the metal atoms are replaced with organic groups are also useful antiplugging agents. It is understood that in the case of mono esters the remaining two R groups can both be metal cations, one of the R groups can be a metal cation and one of the R groups can be hydrogen, or both of the R groups can be hydrogen. In the case of diesters the remaining R can be either a metal cation or hydrogen. Typical organic groups are the aforementioned hydrocarbyl and substituted hydrocarbyl groups. The preferred esters are the mono-, di-, and trialkyl esters. The more preferred esters are the trialkyl esters of nitrilotriacetic acid such as the trimethyl, triethyl, tripropyl, tributyl, trioctyl, tridecyl and tridodecyl esters or mixtures of two or more such esters with the most preferred esters being triethylnitrilotriacetate. In order to be most advantageously employed as antiplugging agents, the above compounds should be readily soluble, either directly or indirectly, in the gasoline.

The salts and esters of nitrilotriacetic acid are known compounds whose preparation is known in the art. The trisodium salt of nitrilotriacetic acid, or trisodiumnitrilotriacetate, is formed by the following reaction:



The trisodium salt is converted to nitrilotriacetic acid by treatment with an acid, such as sulfuric acid, as follows:



Examples 1 and 2 show the preparation of triethylnitrilotriacetate from nitrilotriacetic acid.

EXAMPLE 1

To a 100 ml round bottom flask fitted with a Vigoro column and a Dean-Stark trap are placed 19 grams of nitrilotriacetic acid and 126 grams of triethylorthoformate. The mixture is gently heated to reflux until all of the solid nitrilotriacetic acid is dissolved in the triethylorthoformate, resulting in a yellowish liquid. This yellowish liquid is diluted with benzene and washed with distilled water. The excess benzene is then stripped from the washed liquid on a rotary evaporator. The stripped liquid is distilled at 143°C. and a pressure of 1.6 mm Hg. The yield of product (triethylnitrilotriacetate) is 17.2 grams.

EXAMPLE 2

In a 2000 ml round bottom flask fitted with a reflux column and a Dean-Stark trap are placed 100 grams of nitrilotriacetic acid, 300 mls of ethanol, 300 mls of benzene, and 1 gram of paratoluene sulfonic acid. HCl gas is pumped into the flask until the flask is saturated with the gas. The mixture is refluxed until no more H₂O-ethanol collects in the Dean-Stark trap. The ester-benzene-ethanol solution remaining in the flask is neutralized with ammonia gas. The ammonium chloride formed during the neutralization step is filtered from the solution. Excess ethanol and benzene are stripped from the solution on a rotary evaporator. The crude product is vacuum distilled at 149° to 153°C. at a pressure of 3.5 mm Hg. The weight of the final product thus obtained is 67.4 grams of triethylnitrilotriacetate.

Tests were run to illustrate the unusual and beneficial effects of the products of this invention on reducing exhaust catalyst plugging with manganese. In such tests a single cylinder engine was used. The A/F mixture was held at approximately 16.0:1 maintaining 1.8% oxygen in the exhaust stream. The engine speed was run generally with a wide open throttle with the spark firing at an appropriate crank angle, depending on engine characteristics and exhaust gas temperature required.

Generally an exhaust gas temperature range of from 1,500°F. to 1,700°F. in the catalyst entrance cone was maintained.

The exhaust catalysts used were PTX units manufactured and sold by Engelhard Industries. The particular PTX unit used was the PTX-3 which is composed of a cordierite ceramic core which has a random stacked, 16 cell/inch configuration. The ceramic has 0.2 wt. percent platinum with 0.5 g Pt on the entire ceramic core of the PTX-3 unit. This ceramic is 2.625 inches in diameter, 3.8 inches long and is encased in a Monel mesh to take care of thermal expansion differences between the ceramic and steel housing. This is encased in a stainless steel housing 3 inches in outer diameter and 4 inches long. The ceramic is held firmly in place by two retaining rings on the face of the ceramic welded to the steel casing; in addition 1/8 inch square strips are welded to the casing to prevent rotation of the core. The inlet and outlet cover of the unit are 1.5 inches long and the sides form a 45° angle. The casings are joined to a pipe which is connected to the exhaust

system. A standard unleaded gasoline of the type described above was used with from 0.25 to 1.0 g Mn/gal. The concentration of triethyl ester added to the gasoline ranged from 0.2 g/gal to 1.0 g/gal. To determine when the PTX-3 unit was plugged the back pressure in the exhaust stream in front of the PTX-3 unit was measured at predetermined intervals, usually every 1 or 2 hours, as the test progressed. The initial back pressure readings generally varied from 0.2 to 0.6 psi. When the back pressure reached a value of 2.0 psi the system was considered plugged and the test was terminated.

The following results were obtained in the above tests when triethylnitrilotriacetate and methylcyclopentadienyl manganese tricarbonyl were used in the test fuel.

TABLE II


Temp.	Mn conc.	Triethyl-nitrilotriacetate conc.	Hours to plug
1500°F.	1g/gal	0	45
	1g/gal	0.2g/gal	186
	1g/gal	0.1g/gal	113
1600°F.	1g/gal	1.0g/gal	43
	1g/gal	0.2g/gal	38

As demonstrated by the data in Table II when trialkyl esters of nitrilotriacetic acid of the type described above are blended with gasoline containing cyclopentadienyl manganese antiknocks unexpected results are obtained in the alleviation of catalyst plugging.


The amount of antiplugging compound, as for example, triethylnitrilotriacetate, sufficient to reduce the plugging of the catalyst is at least to some extent dependent upon the amount of manganese present in the gasoline and on the inlet exhaust temperature. Generally, the greater the concentration of manganese and the higher the temperature the greater the amount of antiplugging compound needed to reduce plugging of the catalyst. Thus, for example, 0.2 gram of triethylnitrilotriacetate per gallon of gasoline is sufficient to extend the life of the catalyst from about 45 hours to about 186 hours at a temperature of 1,500°F. with unleaded gasoline containing 1 gram of manganese per gallon of gasoline. However, with the same concentration of manganese, but at a temperature of 1,600°F., 1 g/gal of triethylnitrilotriacetate is needed to effectively reduce plugging of the catalyst.

The lower limit at which the antiplugging compounds of the present invention, such as the triethyl esters of nitrilotriacetic acid, are effective to reduce plugging is about 0.01 g/gal. Preferably, the amount of the compound is greater than 0.03 g/gal, and more preferably greater than 0.125 g/gal. There is no real upper limit on the concentration of the antiplugging compound, and, accordingly, the upper limit is restricted by such secondary considerations as economics, etc. However, 1.0 g/gal of the antiplugging compounds, such as the triethyl ester of nitrilotriacetic acid, is sufficient to reduce plugging of the catalyst when using a gasoline containing 0.2 g/gal of manganese at a temperature of 1,500°F. Thus, since the amount of the antiplugging compound, such as the aforementioned triethyl ester, is quite dependent upon the concentration of the manganese, for practical purposes the upper limit is about 10 g/gal.


In addition to being hydrogen, metals, hydrocarbyl radicals, and substituted hydrocarbyl radicals the R groups in the general formula




may also be ammonium and substituted ammonium cations such as morpholinium, alkyl ammonium and mono-, di-, and trialkanol ammonium. Typical of such materials are triammonium, nitrilotriacetate, the normal monoethanolamine salt of nitrilotriacetic acid, the normal diethanolamine salt of nitrilotriacetic acid, the normal triethanolamine salt of nitrilotriacetic acid, the normal tetramethylammonium salt of nitrilotriacetic acid, tri(ethylammonium)nitrilotriacetate, the normal monoisopropanolamine salt of nitrilotriacetic acid, the normal diisopropanolamine salt of nitrilotriacetic acid, the normal morpholine salt of nitrilotriacetic acid and the like. A non-limiting example of a long-chain ammonium salt of nitrilotriacetic acid is



Corresponding esters wherein from 1 to 2 of the ammonium and/or substituted ammonium cations are replaced with organic groups can also be used. Typical organic groups include the aforementioned hydrocarbyl and substituted hydrocarbyl radicals. Thus two of the R groups can be ammonium or ammonium cations while one of the R groups can be said aforementioned organic group; one of the R groups can be an ammonium or substituted ammonium cation, one R group can be hydrogen, and one R group can be said organic group; one R group can be a metal cation, one R group can be an ammonium or substituted ammonium cation, and one R group can be an organic group; or two R groups can be organic groups and the other R group can be an ammonium or substituted ammonium cations. A non-limiting example of a diester monoammonium salt of nitrilotriacetic acid is



It is convenient to utilize additive fluid mixtures which consist of cyclopentadienyl manganese tricarbonyl antiknock agents and antiplugging agents having the general formula




wherein R is independently selected from hydrogen, metals, ammonium and substituted ammonium cation, hydrocarbyl radicals, and substituted hydrocarbyl radicals. These additive fluid mixtures are added to low-lead or unleaded gasoline. In other words, part of the present invention are antiknock-antiplug fluids which

comprise cyclopentadienyl manganese tricarbonyl antiknock agents and the antiplugging agents of the type described hereinabove.


Use of such antiknock-antiplug fluids in addition to resulting in great convenience in storage, handling, transportation, blending with fuels, and so forth, also are potent concentrates which serve the multipurpose functions of being useful as antiknocks and catalyst plugging reducers.

In these fluid compositions the weight ratio of manganese-to-antiplugging agent can vary from about 0.03 gram of antiplugging agent such as triethylnitrilotriacetate to 1 gram of manganese or even 0.01 gram of the antiplugging agent such as triethylnitrilotriacetate to 1 gram of manganese on the one hand to about 10 grams of the antiplugging agent such as triethylnitrilotriacetate to about 1 gram of manganese on the other hand. Some examples of preferred fluids are 0.03 grams of triethylnitrilotriacetate to 0.125 grams of manganese, 0.06 grams of triethylnitrilotriacetate to 0.125 grams of manganese, 0.2 gram of nitrilotriacetate to 1 gram of manganese, 0.1 gram of triethylnitrilotriacetate to 0.25 gram of manganese, 0.5 gram of triethylnitrilotriacetate to 1 gram of manganese, 1 gram of triethylnitrilotriacetate to 1 gram of manganese, 1 gram of trimethylnitrilotriacetate to 1 gram of manganese, and 2 grams of triethylnitrilotriacetate to 1 gram of manganese. The fluids may optionally contain other additives such as antioxidants, antirust agents, detergents, etc., as well as solvents, e.g., a hydrocarbon, to facilitate handling.

Although the preferred antiplugging compounds have the general formula



wherein R has been previously described, it is believed that compounds having the skeletal structure



will have useful properties in reducing the plugging of exhaust catalysts.


Thus for example, one, some, or all of the carbon hydrogens can be replaced by other groups such as alkyls, cycloalkyls, aryls, aralkyls, and alkaryl. Furthermore, said carbon hydrogens may be substituted by halogen, hydroxyl, carboxyl, and amino radicals. A limiting factor regarding the numbers and types of group that can replace the carbon hydrogens is that these groups do not make the compound insoluble in gasoline to such a degree that an effective amount of compound cannot be added.

Although the compounds of the present invention have the most utility when added to gasoline, they can also be used in conjunction with other liquid petroleum distillate fuels such as kerosene, diesel fuel, jet engine fuel, and the like.

Claims to the invention follow.

I claim:

1. As a composition of matter, a gasoline for an internal combustion engine comprising
 - i. about 0.005-10 gms of manganese per gallon as a cyclopentadienyl manganese tricarbonyl wherein said cyclopentadienyl group is a hydrocarbon group containing 5-17 carbon atoms, and
 - ii. amount sufficient to reduce the plugging of an exhaust gas catalyst of a compound having the general formula:



wherein R is independently selected from hydrogen and hydrocarbyl radicals.


2. The composition of claim 1 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

3. The composition of claim 1 wherein each R is methyl.

4. The composition of claim 1 wherein each R is ethyl.

5. The composition of claim 1 wherein said cyclopentadienyl manganese tricarbonyl is methylcyclopentadienyl manganese tricarbonyl.

6. Gasoline comprising
 - i. a cyclopentadienyl manganese tricarbonyl wherein said cyclopentadienyl group is a hydrocarbon group containing 5-17 carbon atoms antiknock compound in an amount sufficient to improve the antiknock characteristics of said gasoline, and
 - ii. a compound in an amount sufficient to reduce the plugging of a noble metal exhaust gas catalyst, said compound having the general formula:



wherein R is independently selected from hydrogen and a hydrocarbyl radical.

7. The gasoline of claim 6 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.


8. The gasoline of claim 7 wherein each R is methyl.

9. The gasoline of claim 7 wherein each R is ethyl.

10. The gasoline of claim 6 wherein R is an aryl group.

11. The gasoline of claim 10 wherein said aryl group is a phenyl group of up to 10 carbon atoms.

12. A substantially lead-free gasoline for use with a noble metal exhaust gas purification catalyst, said gasoline comprising
 - i. a cyclopentadienyl manganese tricarbonyl wherein said cyclopentadienyl group is a hydrocarbon group containing 5-17 carbon atoms antiknock in an amount sufficient to improve the antiknock characteristics of said gasoline, and
 - ii. a compound in an amount sufficient to reduce plugging of said noble metal exhaust gas purification catalyst, said compound having the general formula:



wherein R is independently selected from hydrogen and hydrocarbyl radicals.

13. The gasoline of claim 12 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

14. The gasoline of claim 12 wherein each R is methyl.

15. The gasoline of claim 12 wherein each R is ethyl.


16. The gasoline of claim 12 wherein R is an aryl group.

17. The gasoline of claim 16 wherein said aryl group is a phenyl group of up to about 10 carbon atoms.


18. A gasoline for use with a noble metal exhaust gas purification catalyst, said gasoline comprising

i. a cyclopentadienyl manganese tricarbonyl wherein said cyclopentadienyl group is a hydrocarbon group containing 5-17 carbon atoms antiknock in an amount sufficient to improve the antiknock characteristics of said gasoline, and

ii. a compound in an amount sufficient to reduce the plugging of said noble metal exhaust gas catalyst, said compound having the formula:



19. As a composition of matter an additive fluid for low lead or essentially lead-free gasoline comprising a cyclopentadienyl manganese tricarbonyl wherein said cyclopentadienyl group is a hydrocarbon group containing 5-17 carbon atoms antiknock, and a compound having the general formula:



wherein R is independently selected from hydrogen and hydrocarbyl radicals.

14

20. The composition of claim 19 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

21. The composition of claim 19 wherein each R is methyl.

22. The composition of claim 19 wherein each R is ethyl.

23. The composition of claim 19 wherein R is an aryl group.

24. The composition of claim 23 wherein said aryl group is a phenyl group of up to about 10 carbon atoms.

25. The composition of claim 19 wherein said cyclopentadienyl manganese tricarbonyl is methylcyclopentadienyl manganese tricarbonyl.

26. The composition of claim 25 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

27. The composition of claim 26 wherein said lower alkyl group is ethyl.

28. The composition of claim 26 wherein said lower alkyl group is methyl.

29. The gasoline of claim 18 wherein said cyclopentadienyl manganese tricarbonyl is methylcyclopentadienyl manganese tricarbonyl.

30. The gasoline of claim 12 wherein said cyclopentadienyl manganese tricarbonyl is methylcyclopentadienyl manganese tricarbonyl.

31. The gasoline of claim 30 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

32. The gasoline of claim 31 wherein said lower alkyl group is methyl.

33. The gasoline of claim 37 wherein said lower alkyl group is ethyl.

34. The gasoline of claim 6 wherein said cyclopentadienyl manganese tricarbonyl is methylcyclopentadienyl manganese tricarbonyl.

35. The gasoline of claim 34 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

36. The gasoline of claim 35 wherein said lower alkyl group is methyl.

37. The gasoline of claim 35 wherein said lower alkyl group is ethyl.

38. The composition of claim 5 wherein R is a lower alkyl group having from 1 to about 10 carbon atoms.

39. The composition of claim 38 wherein said lower alkyl group is ethyl.

40. The composition of claim 39 wherein said lower alkyl group is methyl.

* * * * *

50

55

60

65

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 3,926,581
DATED : December 16, 1975
INVENTOR(S) : Larry Plonsker

It is certified that error appears in the above-identified patent and that said Letters Patent are hereby corrected as shown below:

Claim 1 (Column 12, line 9) - after "ii" insert -- an --

Claim 6 (Column 12, line 13) - after "tricarbonyl" insert
-- antiknock compound --

(Column 12, lines 33-34) - after "atoms" delete
-- antiknock compound --

Claim 12 (Column 12, line 58) - after "tricarbonyl" insert
-- antiknock --

(Column 12, line 60) - after "atoms" delete
-- antiknock --

Claim 18 (Column 13, line 20) - after "tricarbonyl" insert
-- antiknock --

(Column 12, line 22) - after "atoms" delete
-- antiknock --

Claim 19 (Column 13, line 37) - after "tricarbonyl" insert
-- antiknock --

(Column 13, line 39) - after "atoms" delete
-- antiknock --

Claim 33 (Column 14, line 31) - "37" should be -- 31 --

Signed and Sealed this
Sixth Day of July 1976

[SEAL]

Attest:

RUTH C. MASON
Attesting Officer

C. MARSHALL DANN
Commissioner of Patents and Trademarks