

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
21 December 2006 (21.12.2006)

PCT

(10) International Publication Number
WO 2006/134403 A2

- (51) International Patent Classification: Not classified
- (21) International Application Number:
PCT/GB2006/050157
- (22) International Filing Date: 15 June 2006 (15.06.2006)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/690,960 16 June 2005 (16.06.2005) US
- (71) Applicant (for all designated States except US): **JOHNSON MATTHEY PLC** [GB/GB]; 40-42 Hatton Garden, London London EC1N 8EE (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **LACEY, Bruce MacDonald** [US/US]; 1114 Buxton Drive, Knoxville, Tennessee TN 37922 (US). **MCMAHON, Steven Lynn** [US/US]; 848 Amy Lea, Sevierville, Tennessee TN 37862 (US). **WANG, Ding Jun** [US/US]; 14 Charles Lane, Sewell, New Jersey NJ 08080 (US).
- (74) Agent: **GIBSON, Sara**; Johnson Matthey Catalysts, P.O. BOX 1, Belasis Avenue, Billingham Cleveland TS23 1LB (GB).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CATALYST AND PROCESS FOR ITS MANUFACTURE

(57) **Abstract:** The inventive catalyst composition is a sponge metal catalyst comprising at least one skeletal porous sponge metal selected from the group consisting of nickel, cobalt, iron and copper, together with a first promoter metal selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and a second promoter metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese, silver, cadmium, praseodymium and neodymium. Processes for the manufacture of the catalyst include impregnation or precipitation of the promoter metals onto the sponge metal catalyst.



WO 2006/134403 A2

Catalyst and process for its manufacture

The present invention concerns an improved sponge metal catalyst and a process for its manufacture.

5

Sponge metal catalysts are well known for use in hydrogenation, for example for hydrogenation of aromatic nitro compounds or of nitriles to organic amines. Sponge metal catalysts are typically made by forming an alloy of the catalytic metal, for example nickel or cobalt, with a leachable metal such as aluminium and then removing the aluminium, usually by reaction and dissolution of the aluminium in a sodium hydroxide solution. The resulting catalytic metal is then in the form of a sponge structure having a high surface area and good activity and selectivity for many commercial hydrogenation processes.

15

It is known to modify the activity and selectivity of sponge metal catalysts by the incorporation of a second or subsequent metal as a promoter. For example, US-A-3997478 describes sponge - nickel catalysts containing as promoter at least two metals selected from the group consisting of chromium, cobalt, molybdenum and manganese. FR-A-2722710 describes a catalyst for the hydrogenation of nitriles to amines of a Raney-nickel-type doped with at least one additional metallic element selected from groups IVB, VB and VIB. The Raney nickel is placed in suspension in a solution of the additive element. US-A-5840989 describes a method of doping a Raney™ nickel catalyst doped with metals by the incorporation of the doping metals in the form of a complex into the alkaline attack medium. The doping metals are preferably chosen from titanium, chromium, zirconium, vanadium, molybdenum, manganese or zinc. Also disclosed is a process for the hydrogenation of nitriles to amines using the catalyst. US-B-6,309,758 describes a precious metal doped porous metal catalyst is disclosed in which the precious metal is present in from 0.01 to 1.5 weight percent and distributed throughout the particles of porous metal to provide a surface to bulk ratio distribution of not greater than 60. EP-A-0880996 describes a formed metal solid-bed catalyst, consisting entirely of catalyst alloy (and up to 15 wt% chromium, iron, cobalt, tantalum, molybdenum and/or titanium as promoters) with a total pore vol. of 0.1-0.6 ml/g and with a surface shell 0.1-2.0 mm thick which is activated by complete or partial leaching of an extractable alloy component.

30

We have now found an improved sponge metal catalyst and preparation method therefor.

35

According to the invention we provide a catalyst composition comprising at least one skeletal porous sponge metal selected from the group consisting of nickel, cobalt, iron and copper, a first promoter metal selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and a second promoter metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese,

silver, cadmium, praseodymium and neodymium. We have found that the use of a combination of the first and second promoter metals is surprisingly more effective than the use of similar promoters alone.

- 5 We further provide a method for the manufacture of a catalyst composition comprising the steps of:-
- a) forming a sponge metal catalyst in which the active skeletal metal is selected from at least one of nickel, cobalt, iron and copper
 - b) depositing upon the surface of said sponge metal catalyst at least one compound of a metal
 - 10 selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and
 - c) depositing upon the surface of said sponge metal catalyst at least one compound of a metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese, silver, cadmium, praseodymium and
 - 15 neodymium.

By active skeletal metal we mean the catalytically active metal which is alloyed with a leachable metal and which is left behind when the leachable metal is dissolved and removed from the alloyed material. The active skeletal metal is in the form of a highly porous sponge structure having a high

20 surface area. The active skeletal metal is selected from nickel, copper, cobalt and iron and may comprise more than one of these metals.

Preferred first promoter metals comprise Pt, Pd and Rh.

Preferred second promoter metals comprise V, Fe, Ce and Zn.

25

The catalyst of the invention is based on a sponge-metal catalyst which is of the type well-known in the art and which is formed using known methods. To form the sponge metal catalyst, first, an alloy is formed having from about 30 to 60 (preferably from about 42 to 56) weight percent of the active skeletal metal, i.e. nickel cobalt, iron and/or copper and from about 70 to 40 (preferably from

30 about 58 to 44) weight percent of a leachable metal. The leachable metal is preferably selected from aluminium or silicon but is most preferably aluminium. Other metals such as titanium, chromium, zirconium, vanadium, molybdenum, manganese or zinc may, optionally, be present in an amount up to about 20%, more preferably from 5 – 15% of the skeletal metal weight. The alloy is crushed and ground into particles having an average particle size of less than 500 μm diameter,

35 preferably less than 75 μm diameter, more preferably less than 50 μm diameter. The resulting catalyst precursor is activated by leaching the aluminium from the alloy with an alkali solution, such as an aqueous solution of sodium hydroxide (preferred) or potassium hydroxide. The alkali is used at a concentration from 15 to 35 and most preferably from 20 to 35 weight percent, commonly about 30%. The aluminium dissolves in the alkali to form an alkali metal aluminate, which is

soluble in water. The leaching can be carried out at ambient temperature but preferably is conducted at elevated temperatures, e.g. from about 40°C to 110°C, particularly about 90 °C to promote a high rate of leaching and removal of the aluminium metal from the alloy to leave the skeletal metal in a highly active form. The leaching is normally carried out over a period of several
5 hours, e.g. from about 2 to about 8 hours. The time taken is, however dependent upon the conditions selected. This process is already well known to the skilled person.

When the present catalyst is contemplated for use in fixed bed reactors, the porous, particulate base metal product may have an average particle size diameter (or largest dimension) of from
10 about 0.1 to 0.8 cm. The alloy is leached with an alkali solution described above having an alkali concentration of from about 5 to 35 weight percent, preferably from about 5 to 20 weight percent. The leaching is normally carried out at elevated temperatures of from about 30°C to about 90 °C, preferably from about 30 to 50°C.

15 The resulting sponge metal catalyst particles therefore comprises from 80 – 95% of the active skeletal metal and may additionally contain some of the leachable metal, e.g. aluminium. Preferably the sponge metal catalyst contains from 1 to 30% of the leachable metal, more preferably from 1 – 15%. When the skeletal metal comprises a major proportion of nickel then it is usual for the leachable metal content in the finished catalyst to be up to about 15% by weight.

20 When other skeletal metals are used, the amount of leachable metal in the finished catalyst is normally less, and may be <5% when the skeletal metal is copper or cobalt, for example. An additional skeletal metal may be present up to about 20% by weight of the skeletal metal as described above.

25 The sponge metal catalyst particles are washed with water to remove the alkali metal aluminate. Washing is normally continued until a pH of between about 9 and about 12.5 is achieved. It is preferred that the washing is conducted under an inert (e.g. N₂ or Ar) atmosphere or one having a dilute concentration (2-8%, preferably 3-5%) of hydrogen. The catalyst is then normally stored under water in order to avoid contact with air. This is because sponge metal catalysts have a high
30 metal surface area and are therefore pyrophoric in air. The sponge metal catalyst product normally has a pore volume (Nitrogen-BET) of from about 0.05 to about 0.3 cc/g; an average pore diameter ranging from about 10 to 500 Angstroms; a surface area (BET) of at least 10 m² /g and preferably ranging from about 20 to about 150 m² /g.

35 Preferably the catalyst comprises from 0.01 to 5%, more preferably from 0.05 to 2% and especially from 0.1 to 1% by weight of the first promoter metal. Preferably the catalyst comprises from 0.01 to 5%, more preferably from 0.05 to 2% and especially 0.1 to 1% by weight of the second promoter metal.

The sponge metal catalyst is preferably in the form of particles which are of a size from 1 to 150 microns. The first and second promoter metals may be uniformly distributed throughout the catalyst mass but preferably the promoter metals are concentrated at the surface of the catalyst mass.

5

US-B-6,309,758 describes a precious metal doped porous metal catalyst is disclosed in which the precious metal is present in from 0.01 to 1.5 weight percent and distributed throughout the particles of porous metal to provide a surface to bulk ratio of not greater than 60. Surface to bulk ratio (S/B) refers to the ratio of surface dopant concentration to bulk dopant concentration, where surface
10 dopant concentration is the atomic ratio of first promoter metal to skeletal metal within the surface volume of a catalyst particle and bulk dopant concentration refers to the atomic ratio of first promoter metal to skeletal metal for the entire catalyst particle. Surface volume refers to the outer volume or shell of a catalyst particle of the present invention which is roughly the outer 50Å of the particle's radius (i.e., extending from the outer surface of the particle inward toward the centre of
15 the particle by about 50 Å).

In a preferred embodiment of the present invention, the S/B ratio is greater than 60, more preferably greater than 100, e.g. from 100 to 500, most preferably greater than 200, e.g. from 200 to 500.

20

The deposition of the first and second metal compounds on the surface of the sponge metal catalyst is preferably out by a process of impregnation of the sponge metal with a solution of the promoter metal compound, but may alternatively be carried out by a process of precipitation of the promoter metal compound from a solution of a metal compound. The deposition of each of the first
25 and second metal compounds may be carried out by similar or different methods. In a preferred method of the invention, the promoter metals may be added to the catalyst by means of post-impregnation, i.e. by impregnating a formed sponge metal catalyst with a solution of a salt or complex of each of the promoter metals together or separately. Alternatively, the promoter metals, or a promoter metal compound may be precipitated onto the skeletal metal from a solution
30 of a salt or complex of each of the promoter metals together or separately. Precipitation methods are well known in the art and include pH-controlled precipitation by formation of an insoluble compound from a solution of a soluble compound by mixing with a (typically alkaline) precipitant. Alternatively the promoter metals may be incorporated with the skeletal metal in the alloy with the leachable metal. As a further alternative, the promoter metal may be added to the caustic leaching
35 solution used in the preparation of the sponge metal. All of these methods are known in the art. The catalyst of the invention contains both a first and a second promoter metal. The first and second promoter metals may be added to the catalyst by different methods at different stages of the process for preparing the catalyst, or they may be added using similar methods and at or about

the same stage of preparation. Solutions of metal salts and complexes are preferably aqueous but organic solvents may be used.

In the preferred process of the invention, the first and second promoter metals are impregnated into the sponge metal catalyst. The second promoter metal may be impregnated into the sponge-metal catalyst before, after or simultaneously with the first promoter metal. The promoter metals are impregnated from a solution of a promoter metal salt. When the salt solutions are not compatible the impregnation of each promoter metal must be carried out as a separate step. When the solutions are compatible and may be mixed then the impregnation may be carried out in the same step using a mixed solution, or in separate steps using separate solutions. Normally aqueous solutions are used. Suitable salts include inorganic salts such as chlorides, nitrates, sulphates etc and organic salts, particularly the metal acetates. Examples of suitable salts used to form a solution of the first promoter metal include $\text{Pd}(\text{NO}_3)_2$ and Na_2PdCl_4 . Examples of suitable salts used to form a solution of the second promoter metal include NaVO_3 , ZnCl_2 , $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, $\text{Ce}(\text{C}_2\text{H}_3\text{O}_2)_3$, AgNO_3 and Na_2VO_4 . The sponge metal catalyst is contacted with the impregnating solution preferably for at least 5 minutes, normally for between 15 and 60 minutes with constant agitation. The pH of the slurry is preferably maintained above 8, more preferably above 9, during impregnation. The impregnation is normally done at room temperature although heating or cooling may be carried out if required. Following impregnation the catalyst is decanted from the impregnation solution and may be washed to remove free impregnation salts. The catalysts are stored in a non-oxidising atmosphere, e.g. in an inert gas such as N_2 or under water.

The catalysts of the present invention are useful in a variety of hydrogenation reactions. In particular the catalysts are useful for the hydrogenation of nitrobenzene to aniline, dinitrotoluene to toluenediamine and for the hydrogenation of organic nitriles to amines such as aliphatic fatty nitriles to primary amines or aliphatic dinitriles to diamines.

The invention will be further described in the following examples which illustrate particular embodiments of the invention but which are not intended to limit the scope of the invention.

30

Analysis

The bulk compositions of the sponge metal catalysts were determined by Inductive Coupled Plasma-Atomic Emission Spectroscopy (ICP-AES). The samples were dissolved with aqua regia solution. The Ni content was determined by difference, assuming the total contents of the elements are 100%.

35

The particle size of the catalysts was measured by laser scattering technique. The near-surface compositions of the catalysts were measured by X-ray Photoelectron Spectroscopy (XPS). Since sponge metal catalysts are highly activated, and thus pyrophoric, they self-ignite on exposure to air

when dry so that the surface compositions may then be altered. To avoid oxidation of the catalyst during the sample transfer and measurement, all samples were placed in the copper sample holder in a fluid in the pre-treatment chamber. The water was then allowed to evaporate under dry N₂ stream over a two hour period to a vacuum of 3×10^{-7} Torr. The sample was then transferred into the analysis chamber without exposure to air. Al K radiation in a 500 μ m spot at 150 W power was used to acquire the spectra. The binding energy was referenced to 284.8 eV of carbon 1s. The compositions were determined by using the sensitivity factors supplied by the manufacturer.

The S/B ratio was calculated in the same way as explained in US 6309758 using the XPS measurement to determine surface composition and ICP-AES to determine the bulk composition. The S/B ratio = surface Pd/Ni divided by bulk Pd/Ni. The results are shown in Table 1.

Example 1 Preparation of a sponge nickel catalyst

Aluminium and nickel metals were heated, melted, and poured together to complete formation of an Al-Ni alloy containing about 50% Ni and 50% Al. The formed alloy was then cooled, crushed, ground and classified. The mean particle size of the powders was about 20 – 25 μ m. The powders were then added in small portions into a reactor containing about 30% NaOH solution. The slurry was agitated at about 90°C for 4 hours. The slurry was then decanted to remove the supernatant and washed with water until the pH was < 11.5. The activated catalyst was stored in the water medium. The assay result of the catalyst is shown in Table 1.

Example 2 Catalyst doped with palladium and vanadium

The sponge Ni catalyst prepared in Example 1 was used to make a promoted catalyst according to the invention. 0.2774 g of Na₂PdCl₄ salt (35.75 wt.% Pd) and 0.2375 g of NaVO₃ were dissolved in 500cm³ of deionised water. 49.48 g of the base sponge Ni catalyst was charged into a 2-liter stainless steel beaker. The water surrounding the catalyst was decanted off and replaced with 500cm³ of deionised water and the mixture was stirred at room temperature for 5 min to form a slurry having a pH of 10.3. While vigorously stirring, the metal salt solution was added into the sponge Ni catalyst slurry. The pH of the sponge Ni slurry was maintained above 9.3. The resulting catalyst was continuously stirred for about 30 min. The supernatant was decanted and analysed by inductively coupled plasma spectroscopy (ICP) to determine the Pd content. Pd was not detectable in the supernatant by ICP. The catalyst was washed with deionised water until no chloride was detected by testing with AgNO₃ solution. The pH of the final catalyst was adjusted to approximately 9.5. The catalyst was then stored under water.

Examples 3 - 5

Catalyst samples were made in the same way as described in Example 2 except that zinc chloride, iron (III) chloride, and cerium acetate respectively were co-impregnated with Pd. The catalyst

contained about 0.2%Pd and 0.2% of the second metal promoter. Table 1 shows the assay data (by ICP) of the catalysts.

Example 6

- 5 A catalyst sample was made by the general procedure of Example 2 using a mixed solution of AgNO_3 and $\text{Pd}(\text{NO}_3)_2$. The final catalyst contained nominal 0.2%Pd and 0.2% Ag.

Example 7 – 10 (comparison)

- As comparison, the same sponge Ni catalyst made in Example 1 was doped with palladium or the
10 second metal only. The nominal Pd or the second metal promoter was about 0.2 wt%. The catalysts were prepared in the same way as in the Example 2, except that only one metal salt was used. In Example 8, the Pd salt was introduced at pH 6 by addition of acetic acid into the sponge Ni slurry. The compositions are shown in Table 1.

Example 11-12

- Using the sponge nickel catalyst prepared in Example 1, the solutions of Na_2PdCl_4 salt (35.75 wt.% Pd) and 0.2375 g of NaVO_3 were separately dissolved in 50cm^3 of deionised water and then added to the sponge nickel slurry in sequence. In Example 11, the palladium solution was added into the sponge Ni catalyst first, followed by addition of the vanadium solution. In Example 12, the
20 vanadium solution was added into the sponge Ni slurry first, followed by addition of palladium salt solution. The resulting slurry was then decanted and washed, as the same way as in Example 2. The assay results are shown in Table 1.

Example 13

- 25 Hydrogenation of nitrobenzene to aniline was carried out at room temperature and 50 psi H_2 using the catalysts of Examples 1 – 10. The activity of each catalyst is shown in Table 1 expressed as $\text{ml H}_2 / \text{min} / \text{g catalyst}$. It is clear that enhanced activity in this reaction was achieved when both Pd and a second metal salt was doped, i.e. using the catalysts of the invention, compared with catalysts containing either no promoter or only a single promoter metal.

30

Examples 14 - 23

- A sponge metal catalyst made by the method described in Example 1 was co-impregnated with palladium and a second metal promoter by the method used in Examples 2 – 5, with the exception that the pH of the catalyst was varied as shown in Table 2. The catalysts were tested for activity in
35 the hydrogenation of nitrobenzene using the method described in Example 13 and the activity is shown in Table 2. All analysis, S/B ratio and activity is measured and calculated as described above.

Table 1

Example	1 st metal promoter salt	2 nd metal promoter salt (2M)	Bulk Compositions by ICP(%)					Surface Pd/Ni (XPS)	S/B Ratio	Activity
			Pd	2M*	Ni	Al	Pd/Ni (Atom)			
1	-	-			92.5	6.5	0	0	NA	127.2
2	Na ₂ PdCl ₄	NaVO ₃	0.20	0.20	92.1	6.5	0.00119	0.350	294	234.7
3	Na ₂ PdCl ₄	ZnCl ₂	0.21	0.20				0.467	392	251.9
4	Na ₂ PdCl ₄	FeCl ₃ ·6H ₂ O	0.22	0.20				0.346	285	208.3
5	Na ₂ PdCl ₄	Ce(C ₂ H ₃ O ₂) ₃	0.20	0.30				NA	NA	208.0
7**	Na ₂ PdCl ₄		0.22					0.435	365	60.3
8**	Na ₂ PdCl ₄		0.17					0.038	31.9	60.7
9**		ZnCl ₂		0.20				NA	NA	60.3
10**		NaVO ₃		0.20				NA	NA	75.5
11	Na ₂ PdCl ₄	NaVO ₃	0.21	0.20				NA	NA	210.9
12	Na ₂ PdCl ₄	NaVO ₃	0.21	0.20				NA	NA	234.5

*2M% is nominal concentration.

** Comparative experiment

Table 2

Example	pH	Pd load (wt%)	2nd promoter metal	2nd metal (wt%)	S/B Ratio	Activity
14	8.07	0.20	Ce	0.20	83	117
15	8.55	0.20	Ce	0.20	177	57
16	8.01	0.20	Cu	0.20	53	106
17	8.54	0.20	Cu	0.20	100	26
18	8.09	0.20	V	0.20	56	198
19	8.53	0.20	V	0.20	25	202
20	10.17	0.20	V	0.20	142	236
21	7.98	0.20	Zn	0.20	196	142
22	8.53	0.20	Zn	0.20	258	127
23	9.55	0.20	Zn	0.20	214	252

5

Example 24

The catalysts of Examples 1 and 2 were tested in the hydrogenation of dinitrotoluene (DNT) to toluenediamine (TDA). The reactions were carried out in a continuous stirred tank reactor at a temperature of 143 °C, a hydrogen pressure of 220 psig using a catalyst charge of 41 mg and a feed solution of DNT in methanol containing 53 mg DNT/ml. Test results shown in Table 3 show deactivation of the reference non-promoted catalyst of Example 1 at a productivity level of 677g DNT per g of catalyst of Example 1. The 0.2/0.2 Pd/V co-promoted catalyst of Example 2, by contrast, shows a productivity in excess of 3060 g DNT per gram catalyst. This represents an improvement in lifetime of 4.5 times.

15

Table 3

Catalyst	Flow Rate, (ml/min)	Batch Reaction Rate (mmol H ₂ /min)	LHSV (g/g cat/hr)	Selectivity (%)	Productivity (g DNT/g cat)
Example 1	0.7	0.68	52.5	97.4	677
Example 2	0.7	0.78	52.5	99.4	3060+

Claims

1. A catalyst composition comprising
 - (i) at least one skeletal porous sponge metal selected from the group consisting of nickel, cobalt, iron and copper,
 - (ii) a first promoter metal selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and
 - (iii) a second promoter metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese, silver, cadmium, praseodymium and neodymium.
2. A catalyst according to claim 1, wherein the first promoter metal is selected from the group consisting of Pt, Pd and Rh.
3. A catalyst according to claim 1 or claim 2, wherein the second promoter metal is selected from the group consisting of V, Fe, Ce and Zn.
4. A catalyst according to any one of the preceding claims, wherein the skeletal metal further comprises a metal selected from the group consisting of titanium, chromium, zirconium, vanadium, molybdenum, manganese and zinc in an amount of 0 – 20 % by weight of the total skeletal metal.
5. A catalyst according to any one of the preceding claims, wherein the catalyst comprises from 0.01 to 5% by weight of the first promoter metal.
6. A catalyst according to any one of the preceding claims, wherein the catalyst comprises from 0.01 to 5% by weight of the second promoter metal.
7. A catalyst according to any one of the preceding claims, wherein the catalyst is in the form of particles which have an average diameter in the range from 1 to 150 microns.
8. A catalyst according to any one of the preceding claims, wherein the distribution of promoter metals through the catalyst particles provides an S/B ratio in the range from 100 to 500,
where S/B ratio means the ratio of surface dopant concentration to bulk dopant concentration,
where surface dopant concentration is the atomic ratio of first promoter metal to skeletal metal within the surface volume of a catalyst particle,
bulk dopant concentration refers to the atomic ratio of first promoter metal to skeletal metal for the entire catalyst particle, and

surface volume refers to the outer volume of a catalyst particle which extends from the outer surface of the particle inward toward the centre of the particle by 50 Å.

9. A method for the manufacture of a catalyst composition comprising the steps of:-
- a) forming a sponge metal catalyst in which the active skeletal metal is selected from at least one of nickel, cobalt, iron and copper and from 0 – 20% by weight of a metal selected from the group consisting of titanium, chromium, zirconium, vanadium, molybdenum, manganese and zinc;
 - b) depositing upon the surface of said sponge metal catalyst at least one compound of a metal selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and
 - c) depositing upon the surface of said sponge metal catalyst at least one compound of a metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese, silver, cadmium, praseodymium and neodymium.
10. A method for the manufacture of a catalyst according to claim 9, wherein step (b) is carried out before step (c).
11. A method for the manufacture of a catalyst according to claim 9, wherein step (c) is carried out before step (b).
12. A method for the manufacture of a catalyst according to claim 9, wherein step (b) and step (c) are carried out in the same process step.
13. A method according to any one of claims 9 - 12, wherein steps (b) and (c) comprise impregnation of said sponge metal catalyst with a solution of a compound of said metal.
14. A method according to any one of claims 9 - 12, wherein steps (b) and (c) comprise precipitation of said metal compound from a solution of a compound of said metal.
15. A method for the manufacture of a catalyst composition comprising the steps of:-
- a) forming an alloy comprising from 70 – 40% wt of a leachable metal, from 30 – 60%wt of at least one active skeletal metal selected from the group consisting of at least one of nickel, cobalt, iron and copper, and at least one of
 - (i) a first promoter metal selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and
 - (ii) a second promoter metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese, silver, cadmium, praseodymium and neodymium.

- b) grinding said alloy into particles having an average size of from 1 to 500 μ ,
- c) contacting said particles with a solution of an alkali metal hydroxide for sufficient time and under conditions suitable to effect leaching of at least 80% of said leachable metal from the alloy to form a sponge metal catalyst and optionally
- d) depositing on the surface of said sponge metal catalyst a compound of at least one of
 - (i) a first promoter metal selected from the group consisting of palladium, platinum, ruthenium, rhodium, osmium and iridium and/or
 - (ii) a second promoter metal selected from the group consisting of iron, nickel, cobalt, zinc, vanadium, cerium, copper, tungsten, molybdenum, titanium, niobium, manganese, silver, cadmium, praseodymium and neodymium.

16. A method for the manufacture of a catalyst according to claim 15, wherein at least one of steps d(i) and d(ii) comprise impregnation of said sponge metal catalyst with a solution of a compound of said metal.

17. A method for the manufacture of a catalyst according to claim 15, wherein at least one of steps d(i) and d(ii) comprise precipitation of said metal compound from a solution of a compound of said metal.

18. A process for the hydrogenation of an organic nitro compound or nitrile to the corresponding amine characterised in that the process is carried out in the presence of a catalyst as claimed in any one of claims 1 – 8 or made by a method as claimed in any one of claims 9 – 17.

19. A process as claimed in claim 18, comprising the hydrogenation of nitrobenzene to aniline, a nitrotoluene to the corresponding aminotoluene, dinitrotoluene to toluenediamine, an aliphatic nitrile to an aliphatic primary amine or of an aliphatic dinitrile to an aliphatic diamine.