



US007144765B2

(12) **United States Patent**
Anda et al.

(10) **Patent No.:** **US 7,144,765 B2**
(45) **Date of Patent:** **Dec. 5, 2006**

(54) **SEMICONDUCTOR DEVICE WITH SCHOTTKY ELECTRODE INCLUDING LANTHANUM AND BORON, AND MANUFACTURING METHOD THEREOF**

See application file for complete search history.

(75) Inventors: **Yoshiharu Anda**, Okayama (JP);
Akiyoshi Tamura, Suita (JP)

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,490,193 A *	12/1984	Ishaq et al.	438/558
5,550,065 A	8/1996	Hashemi et al.	
5,693,969 A	12/1997	Weitzel et al.	
2003/0121468 A1 *	7/2003	Boone et al.	117/78

(73) Assignee: **Matsushita Electric Industrial Co., Ltd.**, Osaka (JP)

FOREIGN PATENT DOCUMENTS

JP	61-91966	5/1986
JP	63-169064	7/1988
JP	63-299164	12/1988
JP	06224441 A	8/1994
JP	9-45894	2/1997

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 25 days.

* cited by examiner

(21) Appl. No.: **11/032,164**

Primary Examiner—George R. Fourson

Assistant Examiner—Thanh V. Pham

(22) Filed: **Jan. 11, 2005**

(74) *Attorney, Agent, or Firm*—Wenderoth, Lind & Ponack, L.L.P.

(65) **Prior Publication Data**

US 2005/0121695 A1 Jun. 9, 2005

Related U.S. Application Data

(62) Division of application No. 10/617,793, filed on Jul. 14, 2003, now Pat. No. 6,967,360.

(57) **ABSTRACT**

A semiconductor device and its manufacturing method. The semiconductor device has a semi-insulating GaAs substrate **310**, a GaAs buffer layer **321** that is formed on the semi-insulating GaAs substrate **310**, AlGaAs buffer layer **322**, a channel layer **323**, a spacer layer **324**, a carrier supply layer **325**, a spacer layer **326**, a Schottky layer **327** composed of an undoped $\text{In}_{0.48}\text{Ga}_{0.52}\text{P}$ material, and an n^+ -type GaAs cap layer **328**. A gate electrode **330** is formed on the Schottky layer **327**, and is composed of LaB_6 and has a Schottky contact with the Schottky layer **327**, and ohmic electrodes **340** are formed on the n^+ -type GaAs cap layer **328**.

(30) **Foreign Application Priority Data**

Feb. 7, 2003 (JP) 2003-031214



10 Claims, 6 Drawing Sheets

(51) **Int. Cl.**

H01L 21/338 (2006.01)


(52) **U.S. Cl.** **438/167; 438/172; 438/FOR. 179; 257/194; 257/E21.403; 257/E21.407**

(58) **Field of Classification Search** **438/167, 438/172, FOR. 179; 257/194**



PRIOR ART

Fig. 1



PRIOR ART

Fig. 2




Fig. 3




Fig 4A




Fig 4B




Fig 4C




Fig 4D




Fig. 5




Fig. 6




Fig. 7





Fig. 8



**SEMICONDUCTOR DEVICE WITH
SCHOTTKY ELECTRODE INCLUDING
LANTHANUM AND BORON, AND
MANUFACTURING METHOD THEREOF**

This is a divisional application of U.S. patent application Ser. No. 10/617,793, filed Jul. 14, 2003, now U.S. Pat. No. 6,967,360.

BACKGROUND OF THE INVENTION

(1) Field of the Invention

The present invention relates to a semiconductor device with a Schottky junction electrode made of a compound semiconductor and its manufacturing method.

(2) Description of the Related Art

In recent years, a Field Effect Transistor (hereinafter, referred to simply as FET), made of a compound semiconductor, for example, III-V family materials such as GaAs or InP, has been widely employed for wireless communication and especially as a power amplifier, a switch and the like of a cell phone terminal. Among FETs made of GaAs out of FETs made of a compound semiconductor, a Pseudomorphic High Electron Mobility Transistor (hereinafter, referred to simply as PHEMT) is generally utilized. Here, PHEMT is a FET with good high-frequency wave characteristics including a strain channel layer generated by bonding two types of semiconductors whose lattice constants are a little different. The FETs made of GaAs, for example, include the strain channel layer generated by bonding InGaAs and AlGaAs.

In the GaAs PHEMT like this, however, an AlGaAs layer that is composed of AlGaAs has a Schottky contact with a gate electrode; parts of both sides in the portion of the AlGaAs layer that do not touch the gate electrode are exposed by recess etching. As a result, a natural oxide film is formed on the surface of the AlGaAs layer, and its surface level density increases even if the AlGaAs layer is protected by a protective insulation film. Especially when the PHEMT is a power FET, the power FET does not work well because of frequency dispersion of current characteristic.

A prior art to solve the problem is "Manufacturing Method of Field Effect Transistor" (Japanese Laid-Open Patent application No. 09-045894 (pp. 3-4, FIG. 1)). The prior art resolves the problem by using an InGaP layer that is composed of InGaP that can better restrain the formation of the natural oxide film on the surface of a semiconductor layer than AlGaAs as the semiconductor layer that has the Schottky contact with the gate electrode.

FIG. 1 is a cross-sectional diagram of a conventional GaAs PHEMT.

In the GaAs PHEMT shown in FIG. 1, an epitaxial layer **120** is formed on a semi-insulating GaAs substrate **110** that is composed of semi-insulating GaAs. Here, the epitaxial layer **120** is made up of a GaAs buffer layer **121** that is composed of a 1- μ m-thick undoped GaAs material and lessens a lattice mismatch between the epitaxial layer **120** and a semi-insulating GaAs substrate **110**; an AlGaAs buffer layer **122** that is composed of an undoped AlGaAs material; a channel layer **123** that is composed of a 20-nm-thick undoped $\text{In}_{0.2}\text{Ga}_{0.8}\text{As}$ material and in which carriers run; a spacer layer **124** that is composed of a 5-nm-thick undoped InGaP material; a carrier supply layer **125** that is a planer-doped only one atom layer with Si, n-type impurity ions; a Schottky layer **126** that is composed of a 30-nm-thick undoped InGaP material; and an n⁺-type GaAs cap layer **127** that is composed of a 100-nm-thick n⁺-type GaAs.

Additionally, on the Schottky layer **126**, a gate electrode **130** that has a Schottky contact with the Schottky layer **126** is formed; and at two parts on the n⁺-type GaAs cap layer **127**, two ohmic electrodes **140** are formed. Further, in the vicinity of the ohmic electrodes **140**, two element separation regions **150** are formed; in the vicinity of the gate electrode **130**, an insulation film **160** that is composed of SiN or SiO is formed.

As is described above, the conventional GaAs PHEMT can restrain an increase in the surface level density because in the conventional GaAs PHEMT, a semiconductor layer that is composed of InGaP including In and P as constituents is used as the Schottky layer **126**. Therefore, the formation of a natural oxide film on the surface of the Schottky layer is restrained.

However, the conventional GaAs PHEMT has a problem explained below.

In the process of manufacturing the conventional GaAs PHEMT, since heat of about 300° C. is added to the Schottky layer and the gate electrode, diffusion at the Schottky interface between the gate electrode and the Schottky layer occurs. As a result, a problem arises in that the Schottky characteristic deteriorates. At this time, leak current of the Schottky junction between a Gate and a Source is larger than that of the conventional PHEMT having the Schottky layer that is composed of AlGaAs, and deterioration such as strain of a device is seen also in RF characteristics.

FIG. 2 is a diagram showing forward current-voltage characteristics between a Gate and a Source of the PHEMT that has a Schottky layer that is composed of InGaP and the gate electrode that is composed of Ti. In FIG. 2, the broken line shows the forward current voltage characteristic between the Gate and the Source of PHEMT before heat processing at 400° C., while the solid line shows the forward current voltage characteristic between the Gate and Source of PHEMT after the heat processing at 400° C.

It is apparent from FIG. 2 that the leak current at a time of low bias increases due to the 400° C. heat processing and that the Schottky junction is greatly deteriorated.

SUMMARY OF THE INVENTION

In view of the foregoing, it is the object of the present invention to provide a semiconductor device and its manufacturing method. The semiconductor can restrain an increase in the surface level density and has superior thermal stability. To achieve the above-mentioned object, the semiconductor of the present invention is a semiconductor device comprising: a Schottky layer; and a Schottky electrode that is formed on the Schottky layer and has a Schottky contact with the Schottky layer. The Schottky layer is composed of a compound semiconductor including In and P, and the portion of the Schottky electrode that touches the Schottky layer is composed of material whose main constituents are La and B. Here, it is acceptable that the Schottky layer is composed of one of InGaP, InP and InAlGaP, and that the portion of the Schottky electrode that touches the Schottky layer is composed of LaB_6 . Additionally, it is agreeable that the semiconductor device is a transistor or a diode.

As noted above, the semiconductor device is made up of the Schottky layer that is composed of a compound semiconductor including In and P, and a Schottky electrode that is formed on the Schottky layer, and a portion of the Schottky electrode that touches the Schottky layer is composed of a material whose main constituents are La and B. Therefore, the semiconductor device can restrain an increase

in the surface level density of the Schottky layer, and has superior thermal stability and good Schottky characteristics.

Additionally, the present invention provides a method of manufacturing a semiconductor device that has (i) an epitaxial layer that comprises a semiconductor layer and a Schottky layer and (ii) a Schottky electrode that is formed on the Schottky layer and has a Schottky contact with the Schottky layer. The manufacturing method includes an epitaxial process of forming an epitaxial layer by forming in sequence a semiconductor layer and a Schottky layer that is composed of a compound semiconductor including In and P on a semi-insulating substrate by epitaxial growth using one of Metal Organic Chemical Vapor Deposition method and Molecular-Beam Epitaxial method; and an electrode forming process of forming a Schottky electrode by evaporating material whose main constituents are La and B onto the Schottky layer. In this process, the portion of the Schottky electrode that touches the Schottky layer is composed of the evaporated material. Here, it is possible that the Schottky layer is composed of one of InGaP, InP and InAlGaP, and that the Schottky layer is formed in the epitaxial process, the Schottky layer being composed of one of InGaP, InP and InAlGaP. Moreover, it is acceptable that the portion of the Schottky electrode that touches the Schottky layer is composed of LaB₆, and LaB₆ is evaporated onto the Schottky layer in the electrode forming process. Furthermore, it is agreeable that the vapor deposition of the material is performed with an electron-beam vapor deposition method.

Hereby, the Schottky electrode can be formed by vapor deposition, and it has the effect of allowing manufacture of the semiconductor device with simple process.

As further information about technical background to this application, Japanese patent application No. 2003-031214 filed on Feb. 7, 2003 is incorporated herein by reference.

BRIEF DESCRIPTION OF THE DRAWINGS

These and other subjects, advantages and features of the invention will become apparent from the following description thereof taken in conjunction with the accompanying drawings that illustrate a specific embodiment of the invention.

FIG. 1 is a cross-sectional diagram showing the structure of a conventional PHEMT.

FIG. 2 is a diagram showing forward current-voltage characteristics between a Gate and a Source of the conventional PHEMT.

FIG. 3 is a cross-sectional diagram showing the structure of a GaAs PHEMT according to the first embodiment of the present invention.

FIG. 4A~FIG. 4D are cross-sectional diagrams showing the structures of the GaAs PHEMTs indicating a manufacturing method for the GaAs PHEMT according to the first embodiment of the present invention.

FIG. 5 is a flowchart showing the method of manufacturing the GaAs PHEMT according to the first embodiment of the present invention.

FIG. 6 is a diagram showing forward current-voltage characteristics between a Gate and a Source of the GaAs PHEMT according to the first embodiment of the present invention.

FIG. 7 is a diagram showing forward current-voltage characteristics between the Gate and the Source of the GaAs PHEMT according to the first embodiment of the present invention and the conventional PHEMT.

FIG. 8 is a cross-sectional diagram showing the structure of an InP PHEMT according to the second embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The semiconductor device according to the present embodiments of the present invention will be explained below with reference to the figures.

The First Embodiment

FIG. 3 is a cross-sectional diagram showing the structure of a GaAs PHEMT according to the first embodiment.

In the PHEMT according to the first embodiment, an epitaxial layer **320** is formed on a semi-insulating GaAs substrate **310** that is composed of the semi-insulating GaAs material. Here, the epitaxial layer **320** is made up of a GaAs buffer layer **321** that is composed of a 1- μ m-thick undoped GaAs material and lessens a lattice mismatch between the epitaxial layer **320** and the semi-insulating GaAs substrate **310**; an AlGaAs buffer layer **322** that is composed of a 100-nm-thick undoped AlGaAs material; a channel layer **323** that is composed of a 20-nm-thick undoped In_{0.2}Ga_{0.8}As material and in which carriers run; a spacer layer **324** that is composed of a 5-nm-thick undoped Al_{0.25}Ga_{0.75}As material; a carrier supply layer **325** that is planer-doped only one atom layer with Si, n-type impurity ions so that the dose of Si is 5×10^{12} cm⁻²; a spacer layer **326** that is composed of a 20-nm-thick undoped Al_{0.25}Ga_{0.75}As material; a Schottky layer **327** that is composed of a 10-nm-thick undoped In_{0.48}Ga_{0.52}P material; and an n⁺-type GaAs cap layer **328** that is composed of a 100-nm-thick n⁺-type GaAs material. By the way, the Schottky layer **327** is described as being composed of In_{0.48}Ga_{0.52}P material, but it may be composed of a compound semiconductor including In and P, for example, InGaP or InAlGaP.

Moreover, on the Schottky layer **327**, a gate electrode **330** that has a Schottky contact with the Schottky layer **327** is formed. At two parts on the n⁺-type GaAs cap layer **328**, two ohmic electrodes **340** are formed. Further, in the vicinity of the ohmic electrodes **340**, two element separation regions **350** are formed. In the vicinity of the gate electrode **330**, an insulation film **360** that is composed of SiN or SiO is formed. Here, the gate electrode **330** is composed of material whose main constituents are La and B, for example, LaB₆.

Next, a manufacturing method of the GaAs PHEMT with the structure described above is explained following the cross-sectional diagram shown in FIG. 4 and the flowchart shown in FIG. 5. It should be noted that the same elements in FIG. 3 are given the same characters and their detailed explanations are omitted here.

For a start, as shown in FIG. 4A, on the semi-insulative GaAs substrate **310**, using an MOCVD (metal organic chemical vapor deposition) method or MBE (molecular-beam epitaxial) method, epitaxial growth is performed in sequence to form the GaAs buffer layer **321**, the AlGaAs buffer layer **322**, the channel layer **323**, the spacer layer **324**, the carrier supply layer **325**, the spacer layer **326**, the Schottky layer **327** and the n⁺-type GaAs cap layer **328** to form the epitaxial layer **320** (Step S510). Then, the element separation regions **350** are formed by shaping a pattern to form the element separation regions **350** with a photo resist **410** and doping the ions into the region where the element separation regions **350** are formed (Step S520). By the way,

the element separation regions **350** may be formed by performing mesa etching to the regions where the element separation regions **350** in the epitaxial layer **320** are formed.

Next, as shown in FIG. **4B**, an aperture is formed in the region where the ohmic electrodes **340** are formed by shaping a pattern to form the ohmic electrodes **340** with the photo resist and performing etching, and the ohmic electrodes **340** are formed by evaporating an ohmic metal that is made of a Ni/Au/Ge alloy and lifting-off the photo resist (Step **S530**).

Now, as shown in FIG. **4C**, an aperture is formed in the region where the gate electrode **330** is formed by shaping a pattern to form the gate electrode **330** with the photo resist **420** and performing etching. By performing recess etching, the aperture is formed in the region where the gate electrode **330** between the ohmic electrodes **340** on the n⁺-type GaAs cap layer **328** is formed, and an aperture **430** is acquired (Step **S540**). At this time, since the etching selectivity between the n⁺-type GaAs cap layer **328** and the Schottky layer **327** is large, a part of the n⁺-type GaAs cap layer **328** can be selectively removed by the recess etching to form the aperture **430**, using a liquid mixture of phosphoric acid, hydrogen peroxide solution and water, and therefore, it is possible to perform stable recess etching.

Next, as shown in FIG. **4D**, the gate electrode **330** is formed by evaporating the gate metal that is composed of material whose main constituents are La and B, for example, LaB₆, using an electron-beam vapor deposition method and the like and lifting off the photo resist (Step **S550**).

Now, evaluation results of the GaAs PHEMT according to the first embodiment are shown.

FIG. **6** and FIG. **7** are diagrams showing the forward current voltage characteristic between the Gate and the Source of the GaAs PHEMT according to the first embodiment. In FIG. **6**, the dotted line shows the forward current voltage characteristic between the Gate and the Source of the PHEMT having the gate electrode that is composed of LaB₆ before heat processing at 400° C.; the solid line shows the forward current voltage characteristic between the Gate and the Source of the PHEMT having the gate electrode that is composed of LaB₆ after heat processing at 400° C. Additionally, in FIG. **7**, the solid line shows the forward current-voltage characteristic between the Gate and the Source of the PHEMT having the gate electrode that is composed of LaB₆ after heat processing at 400° C.; the broken line shows the forward current voltage characteristic between the Gate and the Source of the PHEMT having the gate electrode that is composed of Ti after heat processing at 400° C.; and the dotted line shows the forward current voltage characteristic between the Gate and the Source of the PHEMT having the gate electrode that is composed of Mo after heat processing at 400° C.

In view of FIG. **6**, it is apparent that the PHEMT having the gate electrode that is composed of LaB₆ according to the first embodiment is different from the conventional PHEMT having the gate electrode that is composed of Ti because its leak current does not increase after the heat processing at 400° C., and therefore, it has a thermally stable Schottky characteristic.

Moreover, seeing FIG. **7**, it is apparent that the PHEMT having a gate electrode that is composed of LaB₆ has a higher Schottky barrier than the conventional PHEMT having a gate electrode that is composed of Ti, and the PHEMT having a gate electrode that is composed of LaB₆ has a higher Schottky barrier than the PHEMT having a gate

electrode that is composed of Mo (another high-melting point metal) by about 0.1V. Therefore, the PHEMT has good Schottky characteristics.

As is described above, according to the first embodiment, the Schottky layer **327** is composed of In_{0.48}Ga_{0.52}P material and the gate electrode **330** is composed of LaB₆ material, a high-melting point metal (melting point: 2806° C.). Consequently, interdiffusion by heat processing between the Schottky layer **327** and the gate electrode **330** can be restrained, and it is possible to obtain a PHEMT with superior thermal stability.

Furthermore, according to the first embodiment, the Schottky layer **327** is composed of In_{0.48}Ga_{0.52}P material. Therefore, the PHEMT according to the first embodiment can restrain an increase of the surface level density of the Schottky layer.

Additionally, according to the first embodiment, the Schottky layer **327** is composed of In_{0.48}Ga_{0.52}P material and the gate electrode **330** is composed of LaB₆. Consequently, the PHEMT according to the first embodiment can realize the PHEMT with good Schottky characteristics.

Moreover, according to the first embodiment, the gate electrode **330** is formed by vapor deposition. Therefore, the PHEMT can be manufactured with a simple process.

By the way, according to the first embodiment, the PHEMT is exemplified as a semiconductor device having (1) the gate electrode **330** that has a Schottky contact with the Schottky layer **327** and (2) the Schottky layer **327**. But it is acceptable that the semiconductor device is another semiconductor device having (1) the gate electrode **330** that has a Schottky contact with the Schottky layer **327** and (2) the Schottky layer **327**, for example, a Schottky diode.

Furthermore, according to the first embodiment, the gate electrode **330** is described to be composed of the material whose main constituents are La and B, but it is acceptable that the gate electrode is a lamination layer in which a layer that is composed of another material is formed on the layer that is composed of the material whose main constituents are La and B. At this time, in the process of forming the gate electrode **330**, the lamination layer is formed by evaporating the gate metal that is composed of another material onto the gate electrode **330** after evaporating the gate metal that is composed of the material whose main constituents are La and B onto the gate electrode **330**.

The Second Embodiment

FIG. **8** is a cross-sectional diagram showing the structure of an InP PHEMT according to the second embodiment of the present invention.

In the PHEMT according to the second embodiment, an epitaxial layer **820** is formed on a semi-insulating InP substrate **810** that is composed of the semi-insulating InP. Here, the epitaxial layer **820** is made up of an InAlAs buffer layer **821** that is composed of a 1- μ m-thick undoped InAlAs material and lessens a lattice mismatch between the epitaxial layer **820** and the semi-insulating InP substrate **810**; a channel layer **822** that is composed of a 20-nm-thick undoped In_{0.53}Ga_{0.47}As material and in which carriers run; a spacer layer **823** that is composed of a 5-nm-thick undoped InAlGaAs material; a carrier supply layer **824** that is planer-doped only one atom layer with Si, n-type impurity ions so that the dose is 5×10^{12} cm⁻²; an InAlAs layer **825** that is composed of a 20-nm-thick undoped InAlAs material; a Schottky layer **826** that is composed of a 10-nm-thick undoped InP material; and an n⁺-type InGaAs cap layer **827** that is composed of a 100-nm-thick n⁺-type InGaAs mate-

rial. By the way, the Schottky layer **826** is described to be composed of InP but it may be composed of a compound semiconductor including In and P, for example, InAlGaP.

Additionally, on the Schottky layer **826**, a gate electrode **830** that has a Schottky contact with the Schottky layer **826** is formed; and at two parts on the n⁺-type InGaAs cap layer **827**, two ohmic electrodes **840** are formed. Further, in the vicinity of the ohmic electrodes **840**, two element separation regions **850** are formed. In the vicinity of the gate electrode **830**, an insulation film **860** composed of SiN or SiO is formed. Here, the gate electrode **830** is composed of material whose main constituents are La and B, for example, LaB₆.

Next, a manufacturing method of the InP PHEMT with the structure described above is explained. It should be noted that the figures are omitted because the InP PHEMT according to the second embodiment is manufactured by a method similar to the manufacturing method of the GaAs PHEMT according to the first embodiment.

For a start, on the semi-insulative InP substrate **810**, using an MOCVD method or an MBE method, epitaxial growth is laminated in sequence to form the InAlAs buffer **821**, the channel layer **822**, the spacer layer **823**, the carrier supply layer **824**, the InAlAs layer **825**, the Schottky layer **826**, the n⁺-type InGaAs cap layer **827** which form the epitaxial layer **820**. Then, the element separation regions **850** are formed by shaping a pattern to form the element separation regions **850** with a photo resist and doping the ions into the region where the element separation regions **850** are formed.

Next, an aperture is formed in the region where the ohmic electrodes **840** are formed by shaping a pattern to form the ohmic electrodes **840** with the photo resist and performing etching. The ohmic electrodes **840** are formed by evaporating an ohmic metal that is made of a Ni/PV/Au alloy and lifting-off the photo resist.

Now, an aperture is formed in the region where the gate electrode **830** is formed by shaping a pattern to form the gate electrode **830** with the photo resist and performing etching. By performing recess etching, the aperture is formed in the region where the gate electrode **830** between the ohmic electrodes **840** on the n⁺-type InGaAs cap layer **827** is formed, and an aperture is acquired. At this time, since the etching selectivity between the n⁺-type InGaAs cap layer **827** and the Schottky layer **826** is large, a part of the n⁺-type InGaAs cap layer **827** can be selectively removed by the recess etching to form the aperture, using a liquid mixture of phosphoric acid, hydrogen peroxide solution and water. Therefore, it is possible to perform stable recess etching.

Next, the gate electrode **830** is formed by evaporating the gate metal that is composed of material whose main constituents are La and B, for example, LaB₆, using the electron-beam vapor deposition method or the like and lifting off the photo resist.

As is described above, according to the second embodiment, the Schottky layer **826** is composed of InP and the gate electrode **830** is composed of LaB₆, a high-melting point metal. Consequently, interdiffusion by heat processing between the Schottky layer **826** and the gate electrode **830** can be restrained, and it is possible to realize the PHEMT with superior thermal stability.

Additionally, according to the second embodiment, the Schottky layer **826** is composed of InP and the gate electrode **830** is composed of LaB₆. Therefore, the PHEMT according to the second embodiment can realize the PHEMT with good Schottky characteristics.

Moreover, according to the second embodiment, the Schottky layer **826** is composed of InP. Consequently, the

PHEMT according to the second embodiment can realize the PHEMT that can restrain an increase of the surface level density of the Schottky layer.

Furthermore, according to the second embodiment, the gate electrode **830** is formed by vapor deposition. Therefore, the PHEMT can be manufactured with a simple process.

By the way, according to the second embodiment, the PHEMT is exemplified as the semiconductor device having (1) the gate electrode **830** that has a Schottky contact with the Schottky layer **826**, and (2) the Schottky layer **826**. But it is acceptable that the semiconductor device is another semiconductor device having (1) the gate electrode **830** that has a Schottky contact with the Schottky layer **826**, and (2) the Schottky layer **826**, for example, a Schottky diode.

Additionally, according to the second embodiment, the gate electrode **830** is described to be composed of a material whose main constituents are La and B, but it is acceptable that the gate electrode is a lamination layer in which a layer that is composed of another material is formed on the layer that is composed of the material whose main constituents are La and B. At this time, in the process of forming the gate electrode **830**, the lamination layer is formed by evaporating the gate metal that is composed of another material onto the gate electrode **830** after evaporating the gate metal that is composed of the material whose main constituents are La and B onto the gate electrode **830**.

As is apparent from the above explanation, since the semiconductor device according to the present invention is made up of the Schottky layer that is composed of the compound semiconductor including In and P, and the Schottky electrode having a Schottky contact with the Schottky layer composed of the material whose main constituents are La and B, it has the effect of realizing a semiconductor device that is thermally stable and has good Schottky characteristics. Moreover, because the semiconductor device according to the present invention has the Schottky layer that is composed of the compound semiconductor including In and P, it has the effect of realizing a semiconductor device that can restrain an increase of the surface level density of the Schottky layer. Furthermore, since the Schottky electrode in the semiconductor device according to the present invention is formed by vapor deposition, it enables manufacture the PHEMT with simple process.

Consequently, since the present invention can restrain the increase of the surface level density in the Schottky layer and can provide a semiconductor device with superior thermal stability and good Schottky characteristics, its practical value is extremely high.

What is claimed is:

1. A method of manufacturing a semiconductor device which is a pseudomorphic high electron mobility transistor, said method comprising:

stacking layers sequentially on a semi-insulating GaAs substrate by epitaxial growth, the layers including, sequentially, a GaAs buffer layer, an AlGaAs buffer layer, an undoped InGaAs channel layer, a first undoped AlGaAs spacer layer, a carrier supply layer, a second undoped AlGaAs spacer layer, an undoped InGaP Schottky layer, and a doped GaAs cap layer;

forming a drain electrode and a source electrode on the doped GaAs cap layer so that the drain electrode and the source electrode are in ohmic contact with the doped GaAs cap layer; and

forming a gate electrode on the undoped InGaP Schottky layer so that the gate electrode extends through the

doped GaAs cap layer, the gate electrode being composed of a material having La and B as main constituents.

2. The method of claim 1, further comprising: selectively etching the doped GaAs cap layer using a liquid mixture of phosphoric acid, hydrogen peroxide solution and water so as to expose a surface of the undoped InGaP Schottky layer; wherein said forming of the gate electrode includes forming the gate electrode on the surface of the undoped InGaP Schottky layer exposed during said selectively etching.

3. The method of claim 2, wherein the gate electrode is composed of LaB₆, and said forming of the gate electrode includes evaporating LaB₆ on the undoped InGaP Schottky layer.

4. The method of claim 3, wherein said evaporating is performed using an electron-beam vapor deposition method.

5. The method of claim 1, wherein the gate electrode is composed of LaB₆, and said forming of the gate electrode includes evaporating LaB₆ on the undoped InGaP Schottky layer.

6. A method of manufacturing a semiconductor device which is a pseudomorphic high electron mobility transistor, said method comprising:

stacking layers sequentially on a semi-insulating InP substrate by epitaxial growth, the layers including, sequentially, an InAlAs buffer layer, an undoped InGaAs channel layer, an undoped InAlGaAs spacer layer, a carrier supply layer, an undoped InAlAs layer, an undoped InP Schottky layer, and a doped InGaAs cap layer;

forming a drain electrode and a source electrode on the doped InGaAs cap layer so that the drain electrode and the source electrode are in ohmic contact with the doped InGaAs cap layer; and

forming a gate electrode on the undoped InP Schottky layer so that the gate electrode extends through the doped InGaAs cap layer, the gate electrode being composed of a material having La and B as main constituents.

7. The method of claim 6, further comprising: selectively etching the doped InGaAs cap layer using a liquid mixture of phosphoric acid, hydrogen peroxide solution and water so as to expose a surface of the undoped InP Schottky layer;

wherein said forming of the gate electrode includes forming the gate electrode on the surface of the undoped InP Schottky layer exposed during said selectively etching.

8. The method of claim 7, wherein the gate electrode is composed of LaB₆, and said forming of the gate electrode includes evaporating LaB₆ on the undoped InP Schottky layer.

9. The method of claim 8, wherein said evaporating is performed using an electron-beam vapor deposition method.

10. The method of claim 6, wherein the gate electrode is composed of LaB₆, and said forming of the gate electrode includes evaporating LaB₆ on the undoped InP Schottky layer.

* * * * *