

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
29 June 2006 (29.06.2006)

PCT

(10) International Publication Number
WO 2006/068735 A1

(51) International Patent Classification:
C08F 214/18 (2006.01) *C08K 5/00* (2006.01)

(21) International Application Number:
PCT/US2005/041490

(22) International Filing Date:
16 November 2005 (16.11.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0427913.9 21 December 2004 (21.12.2004) GB

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US];
3m Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors: **HINTZER, Klaus**,; Werk Gendorf, 84504 Burgkirchen (DE). **JURGENS, Michael**,; Werk Gendorf, 84504 Burgkirchen (DE). **KASPAR, Harald**,; Werk Gendorf, 84504 Burgkirchen (DE). **LOCHHAAS, Kai Helmut**,; Werk Gendorf, 84504 Burgkirchen (DE). **SCHWERTFEGER, Werner**,; Werk Gendorf, 84504 Burgkirchen (DE).

(74) Agents: **SZYMANSKI, Brian E.**, et al.; 3m Center, Office Of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FLUOROPOLYMER FOR MAKING A FLUOROELASTOMER

(57) Abstract: The present invention provides a fluoropolymer comprising repeating units derived from one or more gaseous fluorinated olefins and having one or more cure sites comprising (a) a halogen capable of participating in a peroxide cure reaction or (b) a nitrile group, said fluoropolymer further comprising repeating units derived from one or more fluorinated allyl ethers of the formula: $\text{CF}_2=\text{CF}-\text{CF}(\text{Z})-\text{O}-\text{R}_f$ (I) wherein Z represents F or CF_3 and R_f represents a fluorinated alkyl group that may contain one or more catenary oxygen atoms. The fluoropolymer can be cured to a fluoroelastomer. The invention thus also provides a curable fluoroelastomer composition comprising the fluoropolymer and a curing agent.



WO 2006/068735 A1

FLUOROPOLYMER FOR MAKING A FLUOROELASTOMER

1. Field of the invention

The present invention relates to fluoropolymer suitable for making a fluoroelastomer. In particular, the present invention relates to an amorphous fluoropolymer that comprises one or more cure sites and that comprises one or more repeating units deriving from a fluorinated allylether.

2. Background of the invention.

Fluoroelastomers and in particular perfluoroelastomers such as those described in "Modern Fluoropolymers", edited by John Scheirs, Wiley Science 1997, offer excellent protection against high service temperatures and are resistant to a wide variety of chemical reagents. Fluoroelastomers are generally divided in two main classes, namely those that are based on vinylidene fluoride (VF2) and those that do not contain VF2 and are based on perfluoro vinyl ethers, and tetrafluoroethylene (TFE) and/or chlorotrifluoroethylene (CTFE). Fluoroelastomers based on VF2 are disclosed in for example U.S. Pat. No. 5,696,216, U.S. Pat. No. 5,639,838, U.S. Pat. No. 4,418,186 and U.S. Pat. No. 4,619,983.

US 6,294,627 discloses fluoropolymers of VF2 and a perfluorovinyl ether for producing fluoroelastomers having a low Tg. The fluoroelastomers having a particularly low Tg are generally obtained with highly levels of VF2, e.g. of 50 to 80 mole%. Unfortunately, the use of VF2 in fluoroelastomers generally reduces the chemical and heat resistance of the fluoropolymer and in particular, such fluoroelastomers may be prone to swelling when brought in contact with organic solvents as is for example the case in fuel system application. Thus, although a very low Tg can be achieved, this advantage is accompanied with a decrease of other physical properties.

US 5,891,965 discloses fluoropolymers of VF2 and certain perfluorinated allyl ethers. The fluoropolymers are cured using a bisphenol cure composition and low Tg elastomers are obtained. Typically, the amount of VF2 use in the copolymers is 50 mole % or more. Thus, the low Tg fluoroelastomers suffer from the same disadvantages as disclosed above.

US 4,349,650 and JP 2004/244504 also disclose fluoropolymers comprising fluorinated allyl ether repeating units. It is taught in US 4,349,650 that nitrile functionalized fluorinated allyl ethers can be used to make fluoropolymers that can be cured to
5 fluoroelestomers through a cure reaction involving the nitrile groups. No properties of such fluoroelestomers are disclosed however.

Barney et al (J. Poly. Sci. A-1, 8, 1091-1098 (1970)) described the addition of Krytox TM perfluoroalkyl polyether oils to lower T_g. However, these plasticizers can be extracted by
10 solvents over time.

U.S. Pat. No. 4,513,128 describes perfluoro-terpolymers consisting of tetrafluoroethylene, perfluoromethyl vinyl ether and at least 3 mol % of certain long chain vinyl ethers. The long-chain vinyl ether lowers the T_g significantly, however the incorporation is rather
15 difficult. Therefore, one has to run the polymerization in perhalogenated solvents (e.g. R 113) or in aqueous emulsion polymerization in the presence of fluorinated alcohols. The disadvantages of these systems are: the use of perhalogenated solvents (e.g. R 113) is often critical due to environmental concerns and the removal of the fluorinated alcohols is often very difficult because they act as swelling agents.

U.S. Pat. No. 4,766,190 discloses the aqueous emulsion polymerization of tetrafluoroethylene, hexafluoropropylene and perfluorovinyl ethers of the formula
 $\text{CF}_2=\text{CFO}-(\text{CF}_2\text{CFXO})_m-\text{R}_f$ wherein X is F or CF₃, m is 1 to 50 and R_f is a perfluoroalkyl group. Although the disclosed fluoroelestomers have a low T_g, their method of making
25 involves polymerization times of up to 28 hours (see Example 1), making their manufacturing expensive. Similarly, U.S. Pat. No. 5,891,974 describes the aqueous emulsion polymerization of tetrafluoroethylene and certain perfluorovinyl ethers. However, the polymerization process disclosed to make these fluoroelestomers, is again in the order of 30 hours.

It would now be desirable to find further fluoropolymers for making fluoroelastomers. In particular, it would be desirable to find fluoropolymers that can be manufactured in a cost effective way. Desirably the fluoropolymers are easy and conveniently processable in the making of fluoroelastomer articles therefrom. It would further be desired that


5 fluoroelastomers made from such fluoropolymers have good or excellent mechanical and physical properties, including for example excellent chemical and heat resistance and low or no swelling with organic solvents. Desirably, the fluoropolymers would allow producing fluoroelastomers having a low Tg for example as may be required for fuel system applications in for example engines of airplanes.

10

2. Summary of the invention.

In accordance with one aspect of the present invention, there is provided a fluoropolymer comprising repeating units derived from one or more gaseous fluorinated olefins and having one or more cure sites comprising (a) a halogen capable of participating in a

15 peroxide cure reaction or (b) a nitrile group, said fluoropolymer further comprising repeating units derived from one or more fluorinated allyl ethers of the formula:



wherein Z represents F or CF₃ and R_f represents a fluorinated alkyl group that may contain one or more catenary oxygen atoms.

20 In accordance with a further aspect, a curable fluoroelastomer composition comprising (i) a fluoropolymer as defined above and (ii) a curing agent, is provided. The invention also relates to fluoroelastomer articles obtained upon curing the curable fluoroelastomer composition.


25 In a still further aspect, the invention provides a method of making a fluoropolymer as defined above. The method comprises a copolymerization of one or more gaseous fluorinated olefins and one or more fluorinated allyl ethers according to formula (I).

30 It has been found that the fluoropolymers can be readily and cost effectively be produced even with fairly high levels of fluorinated allyl ether repeating units. In particular, the

fluoropolymers can be produced at high temperature without compromising the properties of fluoroelastomers produced therefrom. Furthermore, it has been found that low T_g fluoroelastomers, e.g. of -25°C or lower can be readily be produced, making such fluoroelastomers suitable for a variety of applications where low temperature properties are required such for example in sealings of turbine of airplanes. Further, the low T_g elastomers can be produced without the need for high levels of VF₂ or even without the need for VF₂, with the result that fluoroelastomers may be obtained that have combined beneficial properties of low T_g and good resistance to swelling when placed in contact with organic solvents, including fuels. Furthermore, fluoroelastomers may be produced that have good or excellent base resistance.


4. Detailed description of the invention

The fluoropolymer according to the present invention is typically an amorphous fluoropolymer. That is, the fluoropolymer typically does not have crystallinity or has only a marginal amount of crystallinity. Thus, an amorphous fluoropolymer generally does not display a melting point or has only a marginal or hardly visible melting point. The fluoropolymer may have a fully fluorinated backbone but may in particular embodiments also have a partially fluorinated backbone. Typically, the fluoropolymer will have at least 40% by weight of fluorine in the backbone, for example at least 50 or 65% by weight. The fluoropolymer according to the invention comprises repeating units deriving from a fluorinated allyl ether of the general formula:



wherein Z represents F or CF₃ and R_f represents a fluorinated alkyl group that may contain one or more catenary oxygen atoms (i.e. in-chain oxygen atoms).

In one embodiment, Z in formula (I) represents a fluorine atom. Also, in a particular embodiment, the group R_f is a fluorinated (poly)ether group such as for example a fluorinated group of the formula:









wherein n is an integer of 1 to 5, m is 0 or an integer of 1 to 10 and R^a is a perfluoroalkyl group of 1 to 7 carbon atoms or an alkyl group of 1 to 7 carbon atoms. Examples of R^a

groups include perfluoroalkyl groups that may be linear or branched including for example perfluoromethyl, perfluoroethyl and perfluoropropyl groups. R^a may further represent an alkyl group such as methyl or ethyl. In the above formula, n is typically 1, 2 or 3 and m is for example 0, 1, 2, 3 or 4.

5

Specific examples of fluorinated allyl ethers for use in accordance with this invention include:



wherein t is 0, 1, 2, 3, 4, or 5.

The fluoropolymer may comprise a mixture of repeating units deriving from a mixture of
 20 fluorinated allyl ethers. The amount of repeating units deriving from the fluorinated allyl ethers in the fluoropolymer is not particularly limited and may be varied according to the desired properties in the fluoroelastomer such as for example the T_g of the fluoroelastomer. Generally and depending on the type of fluorinated allyl ether used, an amount of repeating units derived from fluorinated allyl ethers as low as 2 mole % may
 25 already have a substantial impact on the T_g of the fluoroelastomer. Typically, the amount of repeating units deriving from fluorinated allyl ethers according to formula (I) is between 2 and 30 mole%. According to a particular embodiment, the amount may be between 3 and 25 mole% and according to a still further embodiment, the amount may be between 5 and 20 mole%. Amounts between 4 and 15 mole% usually give satisfactory results in a
 30 variety of applications. Depending on the amount of the allyl ether used and on the nature of comonomers used, fluoropolymers can be obtained that having a glass transition

temperature of not more than -10°C , for example not more than -20°C . In particular embodiments, fluoropolymers with a T_g of -25°C or less or -35°C or less can be obtained.

The fluoropolymer of the present invention further comprises one or more gaseous fluorinated monomers which may be perfluorinated or not. Examples of gaseous fluorinated monomers include chlorotrifluoroethylene (CTFE), tetrafluoroethylene (TFE), chlorotrifluoroethylene, vinyl fluoride, vinylidene fluoride (VF₂) and perfluoroalkyl vinyl monomers such as hexafluoropropylene (HFP). The fluoropolymer may further comprise repeating units deriving from non-fluorinated comonomers such as for example olefins such as ethylene and propylene.

The fluoropolymer further has one or more cure-sites. Suitable cure-sites include halogens capable of participating in a peroxide cure reaction such for example a bromine or iodine atom. Further cure-sites include nitrile groups. The cure-sites may be contained in the end-groups of the polymer and/or may be distributed along the chain of the polymer. Generally, the amount of cure-sites in the fluoropolymer is between 0.1 and 5 mole %, for example between 0.2 and 3 mole %.

Particular examples of fluoropolymers according to the invention are copolymers of tetrafluoroethylene and vinylidene fluoride, copolymers of tetrafluoroethylene and ethylene or propylene, copolymers of tetrafluoroethylene and hexafluoropropylene, copolymers of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene and copolymers of tetrafluoroethylene, hexafluoropropylene and ethylene or propylene. It is being understood that the fluoropolymers enumerated in this paragraph further contain one or more fluorinated allyl ethers of formula (I) and further comprise one or more cure-sites.

In a particular embodiment of the invention, a fluoropolymer is used that contains 45 mole % or less of VF₂, for example not more than 30 mole% or not more than 20 mole%. In a still further embodiment, the fluoropolymer contains no VF₂ or less than 5 mole% of VF₂. Fluoropolymers with a low amount of VF₂ can be used to produce fluoroelastomers that


have a good base resistance and have little or no swelling against organic solvents and fuels.

The fluoropolymers can be obtained with any of the known polymerization techniques including solution polymerization and suspension polymerization. The fluoropolymers are generally made through an aqueous emulsion polymerization process, which can be conducted in a known manner. In a particular embodiment, the fluorinated allyl ether is provided to the polymerization as a preemulsion. That is, the fluorinated allylether is prior to the polymerization emulsified in water using a fluorinated surfactant e.g. as described below. The so obtained emulsion of the allyl ether is then used for feeding the fluorinated allyl ether to the polymerization reaction. Alternatively the allylether can be preemulsified and charged as a whole as for example described in EP 1,160,258. The reactor vessel for use in the aqueous emulsion polymerization process is typically a pressurizable vessel capable of withstanding the internal pressures during the polymerization reaction.

Typically, the reaction vessel will include a mechanical agitator, which will produce thorough mixing of the reactor contents and heat exchange system. Any quantity of the fluoromonomer(s) may be charged to the reactor vessel. The monomers may be charged batchwise or in a continuous or semicontinuous manner. By semi-continuous is meant that a plurality of batches of the monomer are charged to the vessel during the course of the polymerization. The independent rate at which the monomers are added to the kettle will depend on the consumption rate of the particular monomer with time. Preferably, the rate of addition of monomer will equal the rate of consumption of monomer, i.e. conversion of monomer into polymer.

The reaction kettle is charged with water, the amounts of which are not critical. To the aqueous phase there is generally also added the fluorinated surfactant, typically a non-telogenic fluorinated surfactant. The polymerization may also be carried out without addition of a fluorinated surfactant. The fluorinated surfactant when used, is typically used in amount of 0.01% by weight to 1% by weight. Suitable fluorinated surfactants include any fluorinated surfactant commonly employed in aqueous emulsion polymerization.

Particularly preferred fluorinated surfactants are those that correspond to the general formula:



wherein Y represents hydrogen, Cl or F; R_f represents a linear or branched perfluorinated alkylene having 4 to 10 carbon atoms; Z represents COO^- or SO_3^- and M represents an alkali metal ion or an ammonium ion. Most preferred fluorinated surfactants for use in this invention are the ammonium salts of perfluorooctanoic acid and perfluorooctane sulphonic acid. Mixtures of fluorinated surfactants can be used.

A chain transfer agent can be used in the polymerization to control the molecular weight of the fluoropolymer. The chain transfer agent is typically charged to the reaction kettle prior to the initiation of the polymerization. Useful chain transfer agents include C_2 - C_6 hydrocarbons such as ethane, alcohols, ethers, esters including aliphatic carboxylic acid esters and malonic esters, ketones and halocarbons. Particularly useful chain transfer agents are dialkylethers such as dimethyl ether and methyl tertiary butyl ether. Further additions of chain transfer agent in a continuous or semi-continuous way during the polymerization may also be carried out. For example, a fluoropolymer having a bimodal molecular weight distribution is conveniently prepared by first polymerizing fluorinated monomer in the presence of an initial amount of chain transfer agent and then adding at a later point in the polymerization further chain transfer agent together with additional monomer.

The polymerization is usually initiated after an initial charge of monomer by adding an initiator or initiator system to the aqueous phase. For example peroxides can be used as free radical initiators. Specific examples of peroxide initiators include, hydrogen peroxide, diacylperoxides such as diacetylperoxide, dipropionylperoxide, dibutylperoxide, dibenzoylperoxide, benzoylacetylperoxide, diglutaric acid peroxide and dilaurylperoxide, and further water soluble per-acids and water soluble salts thereof such as e.g. ammonium, sodium or potassium salts. Examples of per-acids include peracetic acid. Esters of the peracid can be used as well and examples thereof include tert.-butylperoxyacetate and tert.-butylperoxypivalate. A further class of initiators that can

be used are water soluble azo-compounds. Suitable redox systems for use as initiators include for example a combination of peroxodisulphate and hydrogen sulphite or disulphite, a combination of thiosulphate and peroxodisulphate or a combination of peroxodisulphate and hydrazine. Further initiators that can be used are ammonium- alkali-
5 or earth alkali salts of persulfates, permanganic or manganic acid or manganic acids. The amount of initiator employed is typically between 0.03 and 2 % by weight, preferably between 0.05 and 1 % by weight based on the total weight of the polymerization mixture. The full amount of initiator may be added at the start of the polymerization or the initiator can be added to the polymerization in a continuous way during the polymerization until a
10 conversion of 70 to 80%. One can also add part of the initiator at the start and the remainder in one or separate additional portions during the polymerization. Accelerators such as for example water-soluble salts of iron, copper and silver may preferably also be added.

15 During the initiation of the polymerization reaction, the sealed reactor kettle and its contents are conveniently pre-heated to the reaction temperature. Polymerization temperatures are from 20°C to 150°C, preferred from 30°C to 110°C and most preferred from 40°C to 100°C. The polymerization pressure is typically between 4 and 30 bar, in particular 8 to 20 bar. The aqueous emulsion polymerization system may further
20 comprise auxiliaries, such as buffers and complex-formers. It was found, that the fluorinated allyl ethers can be beneficially copolymerized at high temperatures (> 70°C) producing fewer polar end groups, e.g. -COOH or -COF, as compared to a polymerization under identical polymerization conditions but using a fluorinated vinyl ether instead of a fluorinated allyl ether. The presence of a large amount of polar end groups is generally
25 undesirable as such groups negatively impact the processability of the fluoropolymer.

The amount of polymer solids that can be obtained at the end of the polymerization is typically between 10% and 45% by weight, preferably between 20% and 40% by weight and the average particle size of the resulting fluoropolymer is typically between 50 nm
30 and 500 nm.

The amorphous fluoropolymer includes a cure site component. To introduce a cure site component into the amorphous fluoropolymer, a monomer comprising the particular cure-site may be used or the polymerization may be conducted by using a chain transfer agent or initiator that is capable of introducing the cure site at the terminal ends of the polymer chain.

For example, in order to introduce halogens, which are capable of participation in the peroxide cure reaction, along the chain, the copolymerization of the basic monomers of the fluoropolymer may be carried out with a suitable fluorinated cure-site monomer. In one embodiment, the cure-site monomer can be an ethylenically unsaturated monomer that corresponds to the formula:



wherein each X independently represents H, F or Cl, R_f represents a perfluorinated aliphatic group that may contain one or more oxygen atoms and Z represents Br or I that may be in terminal position of the perfluorinated aliphatic group or that may be on a carbon atom along the perfluorinated aliphatic group.

Further examples of comonomers can be selected for instance from:

(a) bromo- or iodo- (per)fluoroalkyl-perfluorovinylethers having the formula:



wherein Y¹, Y² and Y³ are F or H, Z is Br or I, R_f is a (per)fluoroalkylene C₁-C₁₂, optionally containing chlorine and/or ether oxygen atoms; for example: BrCF₂-O-CF=CF₂, BrCF₂CF₂-O-CF=CF₂, BrCF₂CF₂CF₂-O-CF=CF₂, CF₃CFBrCF₂-O-CF=CF₂, and the like;

(b) bromo- or iodo (per)fluoroolefins such as those having the formula:



wherein Z' is Br or I, R_f' is a (per)fluoroalkylene C₁-C₁₂, optionally containing chlorine atoms; for instance: 4-bromo-perfluorobutene-1, or 4-bromo-3,3,4,4-tetrafluorobutene-1;



(c) (per)fluorinated olefins having a Br or I atom on the olefin double bond such as bromotrifluoroethylene (BTFE);

5 (d) non-fluorinated bromo- olefins such as 4-bromo-1-butene.


In replacement of or in addition to the cure site comonomer, the fluoropolymer can contain a cure site component in terminal position, deriving from a suitable chain transfer agent introduced in the reaction medium during the polymer preparation, as described in
10 U.S. Pat. No. 4,501,869 or derived from a suitable initiator. Examples of useful initiators include X(CF₂)_nSO₂Na with n=1 to 10 (where X is Br or I) or an initiator composition comprising ammonium persulfate and potassium bromide.

Examples of chain transfer agents include those having the formula R_fBr_x, R_fI_x or R_fI/Br_x,
15 wherein R_f is a x-valent (per)fluoroalkyl radical C₁-C₁₂, optionally containing chlorine atoms, while x is 1 or 2. Examples include CF₂Br₂, Br(CF₂)₂Br, Br(CF₂)₄Br, CF₂ClBr, CF₃CFBrCF₂Br, and the like. Further examples of suitable chain transfer agents are disclosed in US 4,000,356.

20 Alternatively, or additionally, the fluoropolymer may comprise cure site components that have a nitrile group. To introduce such nitrile containing cure site components, a nitrile group containing cure site monomer may be used in the polymerization process. In one embodiment useful nitrile group-containing cure site monomers include nitrile-containing fluorinated olefins and nitrile-containing fluorinated vinyl ethers, such as depicted below:



30




where, in reference to the above formulas: $L=2-12$; $g=0-4$; $k=1-2$; $v=0-6$; and $u=1-4$, R_f is a perfluoroalkylene or a bivalent perfluoroether group. Representative examples of such a monomer include perfluoro(8-cyano-5-methyl-3,6-dioxo-1-octene), $CF_2=CFO(CF_2)_5CN$, and $CF_2=CFO(CF_2)_3OCF(CF_3)CN$.

5

Nitrile groups may also be introduced in the fluoropolymer at the terminal ends by initiating the polymerization in the presence of a nitrile group containing salt or pseudohalogen. Suitable nitrile group containing salts include those that have the nitrile group in the anion of the salt and in particular correspond to the formula:

10



wherein M represents a mono- or multi-valent cation including a metal cation or an ammonium, X is O, S, Se or N, a has a value of 0 or 1 and n corresponds to the valence of the cation. Suitable cations M include organic (e.g. tetraalkylammonium cations) and inorganic cations. Particularly useful cations are ammonium and metal cations including mono-valent cations such as sodium and potassium as well as divalent cations such as calcium and magnesium. Examples of potassium salts include potassium cyanide, potassium cyanate and potassium thiocyanate. The salts wherein X is O or S and the cyanides are generally preferred.

15

20

In order to cure the fluoropolymer a cure composition can be used that comprises one or more peroxides. Suitable organic peroxides are those which generate free radicals at curing temperatures. A dialkyl peroxide or a bis(dialkyl peroxide) which decomposes at a temperature above 50°C is especially preferred. In many cases it is preferred to use a di-tertiarybutyl peroxide having a tertiary carbon atom attached to peroxy oxygen. Among the most useful peroxides of this type are 2,5-dimethyl-2,5-di(tertiarybutylperoxy)hexyne-3 and 2,5-dimethyl-2,5-di(tertiarybutylperoxy)hexane. Other peroxides can be selected from such compounds as dicumyl peroxide, dibenzoyl peroxide, tertiarybutyl perbenzoate, α,α' -bis(t-butylperoxy-diisopropylbenzene), and di[1,3-dimethyl-3-(t-butylperoxy)-butyl]carbonate. Generally, about 1-3 parts of peroxide per 100 parts of fluoropolymer is used.

25

30


Another component which is usually included in a cure composition based on an organic peroxide, is a coagent composed of a polyunsaturated compound which is capable of cooperating with the peroxide to provide a useful cure. These coagents can be added in an amount equal to 0.1 and 10 parts per hundred parts fluoropolymer, preferably between 2 to 5 parts per hundred parts fluoropolymer. Examples of useful coagents include triallyl cyanurate; triallyl isocyanurate; triallyl trimellitate; tri(methylallyl) isocyanurate; tris(diallylamine)-s-triazine; triallyl phosphite; N,N-diallyl acrylamide; hexaallyl phosphoramidate; N,N,N',N'-tetraalkyl tetraphthalamide; N,N,N',N'- tetraallyl malonamide; trivinyl isocyanurate; 2,4,6-trivinyl methyltrisiloxane; N,N'-m-phenylenebismaleimide; diallyl-phthalate and tri(5-norbornene-2-methylene)cyanurate. Particularly useful is triallyl isocyanurate. Other useful coagents include the bis-olefins disclosed in EPA 0 661 304 A1, EPA 0 784 064 A1 and EPA 0 769 521 A1.

Further, if the cure site component comprises a nitrile, any cure composition suitable for curing nitrile components can also be used. For example, such nitrile cure composition may comprise one or more ammonia-generating compounds. "Ammonia-generating compounds" include compounds that are solid or liquid at ambient conditions but that generate ammonia under conditions of cure. Such compounds include, for example, hexamethylene tetramine (urotropin), dicyan diamide, and metal-containing compounds of the formula:



where A^{w+} is a metal cation such as Cu^{2+} , Co^{2+} , Co^{3+} , Cu^+ , and Ni^{2+} ; w is equal to the valence of the metal cation; Y^{w-} is a counterion, typically a halide, sulfate, nitrate, acetate or the like; and v is an integer from 1 to about 7.

Also useful as ammonia-generating compounds are substituted and unsubstituted triazine derivatives such as those of the formula:



wherein R is a hydrogen or a substituted or unsubstituted alkyl, aryl, or aralkyl group having from 1 to about 20 carbon atoms. Specific useful triazine derivatives include hexahydro-1,3,5-s-triazine and acetaldehyde ammonia trimer.

5

The curable fluoroelastomer composition may contain further additives, such as carbon black, stabilizers, plasticizers, lubricants, fillers, and processing aids can be incorporated into the compositions, provided they have adequate stability for the intended service conditions. The compositions may be prepared by mixing the fluoropolymer, a cure
10 composition and other additives in conventional rubber processing equipment. Such equipment includes rubber mills, internal mixers, such as Banbury mixers, and mixing extruders.

The curable fluoroelastomer compositions can be used to provide a fluoroelastomer upon
15 curing. In one particular embodiment, the curable fluoroelastomer composition is extruded and cured to obtain a fluoroelastomer article, for example a tube. In another embodiment, the curable fluoroelastomer composition may be used in injection molding and cured to provide an injection molded article such as a gasket or O-ring.

20 The invention will now be further illustrated by the following examples without however the intention to limit the invention thereto.

EXAMPLES

25 **Example 1**

Preemulsion A for precharge:

169 g MA-1 fluorinated allyl ether monomer (4,7,9,11,13,15-hexaoxaperfluorohexadec-1-en, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{O}-\text{CF}_2-\text{CF}_2-\text{O}-\text{CF}_2-\text{O}-\text{CF}_2-\text{O}-\text{CF}_2-\text{O}-\text{CF}_2-\text{O}-\text{CF}_3$) was emulsified in 415 g deionised water together with 20 g perfluorooctanoate ammonium salt (APFOA). For the emulsification an *Ultraturrax* stirrer was used first for 1 min at 24.000 rpm stirrer speed, which was followed by three passes in a *Microfluidizer* high shear homogenisator. This preemulsion had a turbid appearance and was stable for at least 12 h.

Preemulsion B for feed:

720 g MA-1 monomer and 7 g BFTB (1,1,2,2-tetrafluoro-1-bromo-but-3-en, $\text{CH}_2=\text{CH}-\text{CF}_2-\text{CF}_2\text{Br}$) were emulsified in 593 g deionised water together with 10 g perfluorooctanoate ammonium salt (APFOA). For the emulsification an *Ultraturrax* stirrer was used first for 1 min at 24.000 rpm stirrer speed, which was followed by three passes in an *Microfluidizer* high shear homogenisator.

A polymerization kettle with a total volume of 6.9 l equipped with an impeller agitator system was charged with 2140 g deionised water and was heated up to 80°C. The agitation system was set to 320 rpm and in three following cycles, the vessel was degassed and subsequently charged with nitrogen to assure that all oxygen had been removed. The kettle was further charged with the preemulsion A, with 77 g vinylidenedifluoride (VF2) and with 41 g tetrafluoroethylene (TFE) to 10.0 bar absolute reaction pressure. The polymerization was then initiated by 22 g 5 % APS solution (ammonium peroxodisulfate). As the reaction started, the reaction pressure of 10.0 bar absolute was maintained by the feeding TFE and VF2 into the gas phase with a feeding ratio TFE (kg)/VF2 (kg) of 0.52. The reaction temperature of 80°C was also maintained. The preemulsion B was charged into the kettle with a feeding ratio MA-1 preemulsion B (kg)/VF2 (kg) of 4.16. When 320 g VF2 feed was completed after 430 min the monomer valves were closed. The kettle was vented and flushed with N_2 in three cycles. The so obtained polymer dispersion had a solid content of 27.3%, the latex particle diameter was 177 nm according to dynamic light scattering.

The polymer dispersion was coagulated by adding it drop-wise to an aqueous MgCl_2 solution, filtrated and washed four times with deionized water (60-70°C). The polymer was dried overnight at 130°C in an air circulating oven. The polymer shows no discernible melting transition and a glass transition temperature of -59 °C (midpoint value). The

polymer had a Mooney viscosity (ML 1+10) of 19 and a MFI (265/5) of 83'. The copolymer contained 20.4 mol% TFE, 65.9 mol% VF2, 13.2 mol% MA-1 and 0.5 mol% BTFB.

5 Example 2-5:

In the same manner as in example 1 but using bromo-trifluoro ethylene (BTFE) instead of BTFB as cure site monomer and varying the monomer composition, polymerizations were carried out according to the procedure as described in the example 2 – 5; BTFE was fed as a gas in precharge and during polymerization. The compositions of preemulsions, precharges, and polymerization feeds, the polymerization conditions and the analytical results are listed in table 1.

Table 1:

Example #	2	3	4	5
Ether	MA-2	MA-2	MA-3	MA-2
Preemulsion A:				
- ether (g)	200	200	215	200
- water (g)	470	470	387	470
- APFOA (30%) (g)	20	20	20	20
Preemulsion B:				
- ether (g)	680	675	505	670
- water (g)	645	633	706	635
- APFOA (30%) (g)	10	10	15	10
Precharge:				
- water (g)	1330	1380	1425	2070
- TFE (g)	41	38	62	65
- VF2 (g)	77	72	—	42
- BTFE (g)	2.4	1.9	2.3	2.1
- Preemulsion	A	A	A	A
- Initiator additive	3.0 (Rongalit)	3.0 (Rongalit)	—	—
Initiator (g)	640	620	460 (5% APS)	20 g

	(0.3 % t-BuOOH)	(0.3 % t-BuOOH)		(5% APS)
Polymerization feed:				
- TFE (g)	155	155	561	275
- VF2 (g)	299	302	—	180
- BTFE (g)	8.4	5.8	8.1	—
- preemulsion (g)	1320 (B)	1280 (B)	1180 (B)	1315 (B)
pressure (bar)	8	7	4 – 5	8
temperature (°C)	50	30	85	80
run time (min)	380	290	418	330
Particle size (nm)	—	189	148	—
Solid content (%)	27.5	25.8	21.2	24.1
Mooney viscosity (ML 12 1+10)		34	36	36
MFI(265/5kg) (g/10min)	56	—	—	1.9
T _g (°C)	– 57	– 61	– 6	– 41
Copolymer composition				
- TFE (mol%)	22.3	20.6	88.3	43.9
- VF2 (mol%)	63.6	65.9	—	43.3
- Ether (mol%)	13.6	13.1	11.2	12.3
- BTFE (mol%)	0.5	0.4	0.5	0.5
Compounding	Rubber A	Rubber B		
MA-2: 4,7,9,11,13-pentaoxaperfluorotetradec-1-en				
(CF ₂ =CF-CF ₂ -O-CF ₂ -CF ₂ -O-CF ₂ -O-CF ₂ -O-CF ₂ -O-CF ₃)				
MA-3: 4,7-dioxaperfluorooct-1-en				
(CF ₂ =CF-CF ₂ -O-CF ₂ -CF ₂ -O-CF ₃)				
5 t-BuOOH : <i>t</i> -Butylhydroperoxid				

Example 6 + 7 :

In the following examples, the compositions are based on 100 parts of rubber. The curatives and other additives are listed as parts per hundred parts of rubber (phr). Percentages are weight % unless otherwise noted.

In example 6, a curable composition of invention was made by compounding the following curatives and additives into rubber A (example 2) using a two-roll mill and conventional techniques: 100 grams of rubber A, 50 grams of N-990 carbon black, 5 grams of ZnO, 1.8 grams of TAIC (98%), and 2.5 grams of DBPH-50. The cure rheology of the resulting curable composition was evaluated and the results are listed in table 2. Results of physical property testing after press curing of the sample at 177°C for 10 minutes and post curing at 230°C for 16 hours are also listed in table 2.

In example 7, a curable composition of the invention was made and evaluated in a manner similar to example 6 but using rubber B (example 3). The formulation and the other test results are also listed in table 2.

Example #	6	7
Rubber A	100	—
Rubber B	—	100
N-990 Carbon Black (phr)	50	50
ZnO (phr)	5	5
TAIC (phr)	1.8	1.8
DBPH-50 (phr)	2.5	2.5
<u>MDR @177 °C, 0.5 ° Arc, 100 cpm</u>		
MDR total time (minutes)	12	12
M_L (in-lbs)	1.6	2.1
M_H (in-lbs)	11.3	14.7
$M_H - M_L$ (in-lbs)	9.7	12.6
t_{s2} (min)	0.5	0.5
t'_{50} (min)	0.8	0.8
t'_{90} (min)	2.7	2.7
<u>physical properties after Post Cure</u>		
Tensile (psi)	850	1160

19

Elongation (%)	68	73
100 % Modulus (psi)	—	—
Shore A2 Hardness	80	74
<u>Compression Set, Method B, O-rings</u>		
70 hrs @ 200°C (%)	24	22


5

10

15


CLAIMS

1. Fluoropolymer comprising repeating units derived from one or more gaseous fluorinated olefins and having one or more cure-sites comprising (a) a halogen capable of participating in a peroxide cure reaction or (b) a nitrile group, said fluoropolymer further comprising repeating units derived from one or more fluorinated allyl ethers of the formula:



wherein Z represents F or CF₃ and R_f represents a fluorinated alkyl group that may contain one or more catenary oxygen atoms.

2. Fluoropolymer according to claim 1 wherein Z in said formula represents F and wherein R_f corresponds to the formula:



wherein n is an integer of 1 to 5, m is 0 or an integer of 1 to 10 and R^a is a perfluoroalkyl group of 1 to 7 carbon atoms or an alkyl group of 1 to 7 carbon atoms.

3. Fluoropolymer according to claim 1 or 2 wherein said fluoropolymer has a perfluorinated backbone.

4. Fluoropolymer according to any of the previous claims wherein the amount of repeating units derived from said one or more fluorinated allyl ether is between 2 and 30 mole%.

5. Fluoropolymer according to any of the previous claims wherein at least part of said cure-sites are comprised in end groups of said fluoropolymer.

6. Fluoropolymer according to any of the previous claims wherein the amount of cure-sites in said fluoropolymer is between 0.1 and 5 mole%.

7. Fluoropolymer according to any of the previous claims wherein said gaseous fluorinated olefins are selected from the group consisting of tetrafluoroethylene,

chlorotrifluoroethylene, hexafluoropropylene, vinylidene fluoride, vinyl fluoride and mixtures thereof.

8. Fluoropolymer according to any of the previous claims wherein said fluoropolymer
5 further comprises repeating units derived from a non-fluorinated olefin.

9. Fluoropolymer according to claim 8 wherein said non-fluorinated olefin is selected from ethylene and propylene.

10. Fluoropolymer according to any of the previous claims wherein said fluoropolymer
10 comprises repeating units deriving from vinylidene fluoride in an amount of not more than 45 mole%.

11. Fluoropolymer according to any of the previous claims wherein said fluoropolymer is a
15 polymer selected from the group consisting of copolymers of tetrafluoroethylene and vinylidene fluoride, copolymers of tetrafluoroethylene and ethylene or propylene, copolymers of tetrafluoroethylene and hexafluoropropylene.

12. Fluoropolymer according to any of the previous claims wherein said fluoropolymer is a
20 polymer selected from the group consisting of copolymers of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene and copolymers of tetrafluoroethylene, hexafluoropropylene and ethylene or propylene.

13. Fluoropolymer according to any of the previous claims wherein part or all of the cure-
25 sites are derived from one or more monomers having a halogen capable of participating in a peroxide cure reaction or a nitrile group.

14. Fluoropolymer according to any of the previous claims wherein said fluoropolymer has
a glass transition temperature of less than -25°C .

15. Curable fluoroelastomer composition comprising (i) a fluoropolymer as defined in any of the previous claims and (ii) a curing agent.

5 16. Curable fluoroelastomer composition according to claim 15 wherein said composition further comprises a coagent having two or more ethylenically unsaturated groups.

10 17. Method of making a fluoropolymer as defined in any of claims 1 to 14 comprising a copolymerization of said one or more gaseous fluorinated olefins and said fluorinated allyl ethers.

18. Method according to claim 17 wherein said copolymerization is an aqueous emulsion polymerization.

15 19. Method according to claim 17 or 18 wherein the polymerization is carried out at a temperature between 40 and 100°C.

20. Method of making a fluoroelastomer article comprising curing a curable fluoroelastomer composition as defined in any of claims 15 or 16.

20 21. A fluoroelastomer article obtainable by the method of claim 20.

INTERNATIONAL SEARCH REPORT

national application No
PCT/US2005/041490

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F214/18 C08K5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2 975 163 A (LO ELIZABETH S) 14 March 1961 (1961-03-14) column 7, lines 50-63; claims 1-7 -----	1-21
A	US 4 349 650 A (KRESPAN ET AL) 14 September 1982 (1982-09-14) cited in the application the whole document -----	1-21
A	WO 01/49752 A (3M INNOVATIVE PROPERTIES COMPANY; HINTZER, KLAUS; LOHR, GERNOT; MARZ,) 12 July 2001 (2001-07-12) comparative example 5claims -----	1-21
A	US 4 273 728 A (KRESPAN ET AL) 16 June 1981 (1981-06-16) utility examples A-J ----- -/--	1-21

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

26 April 2006

Date of mailing of the international search report

03/05/2006

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Baekelmans, D

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2005/041490

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 006, no. 135 (C-115), 22 July 1982 (1982-07-22) & JP 57 059921 A (DAIKIN IND LTD), 10 April 1982 (1982-04-10) abstract -----	1-21

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/US2005/041490

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2975163	A	14-03-1961	US 2856435 A	14-10-1958
US 4349650	A	14-09-1982	NONE	
WO 0149752	A	12-07-2001	AU 3635801 A	16-07-2001
			CA 2395706 A1	12-07-2001
			CN 1414977 A	30-04-2003
			DE 19964004 A1	12-07-2001
			EP 1244715 A2	02-10-2002
			PL 355906 A1	31-05-2004
			TW 553956 B	21-09-2003
			ZA 200206048 A	29-10-2003
US 4273728	A	16-06-1981	NONE	
JP 57059921	A	10-04-1982	NONE	