



US006867434B2

(12) **United States Patent**  
**Yamazaki**

(10) **Patent No.:** **US 6,867,434 B2**  
(45) **Date of Patent:** **Mar. 15, 2005**

(54) **ACTIVE MATRIX ELECTRO-LUMINESCENT DISPLAY WITH AN ORGANIC LEVELING LAYER**

(75) Inventor: **Shunpei Yamazaki, Tokyo (JP)**

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd., Atsugi (JP)**

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

4,239,346 A	12/1980	Lloyd
4,523,370 A	6/1985	Sullivan et al.
4,557,036 A	12/1985	Kyuragi et al.
4,597,637 A	7/1986	Ohta
4,618,878 A	10/1986	Aoyama et al.
4,680,580 A	7/1987	Kawahara
4,759,610 A *	7/1988	Yanagisawa ..... 257/59
4,800,174 A	1/1989	Ishihara et al.
4,818,077 A	4/1989	Ohwada et al.
4,853,760 A	8/1989	Abe et al.
4,864,376 A	9/1989	Aoki et al.
4,938,565 A	7/1990	Ichikawa

(List continued on next page.)

(21) Appl. No.: **10/137,040**

(22) Filed: **Apr. 30, 2002**

(65) **Prior Publication Data**

US 2002/0121640 A1 Sep. 5, 2002

**Related U.S. Application Data**

(63) Continuation of application No. 09/414,906, filed on Oct. 8, 1999, which is a continuation of application No. 09/360,341, filed on Jul. 22, 1999, now Pat. No. 6,169,293, which is a continuation of application No. 08/751,338, filed on Nov. 18, 1996, now Pat. No. 5,952,708.

(30) **Foreign Application Priority Data**

Nov. 17, 1995 (JP) ..... 7-323674

(51) **Int. Cl.**<sup>7</sup> ..... **H01L 29/04**

(52) **U.S. Cl.** ..... **257/72; 257/59; 257/350; 257/642**

(58) **Field of Search** ..... **257/59, 72, 350, 257/642, 435, 462**

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

3,844,908 A	10/1974	Matsuo et al.
4,103,297 A	7/1978	McGreivy et al.
4,226,898 A	10/1980	Ovshinsky et al.

**FOREIGN PATENT DOCUMENTS**

CN	1090062	7/1994
EP	0 376 648	7/1990

(List continued on next page.)

**OTHER PUBLICATIONS**

Hayashi, et al.; "Fabrication of Low-Temperature Bottom-Gate Poly-Si TFTs on Large-Area Substrate by Linear-Beam Excimer Laser Crystallization and Ion Doping Method"; *IEDM 95*; pp. 829-832; 1995.

Kim et al.; "4.4: Planarized Black Matrix on TFT Structure for TFT-LCD Monitors"; *SID 97 DIGEST*; pp. 19-22; 1997.

*Primary Examiner*—David Nelms


*Assistant Examiner*—Dao H. Nguyen

(74) *Attorney, Agent, or Firm*—Fish & Richardson P.C.

(57) **ABSTRACT**

A resin material having a small relative dielectric constant is used as a layer insulation film 114. The resin material has a flat surface. A black matrix or masking film for thin film transistors is formed thereon using a metal material. Such a configuration prevents the problem of a capacity generated between the masking film and a thin film transistor.

**27 Claims, 5 Drawing Sheets**



U.S. PATENT DOCUMENTS





4,949,141 A 8/1990 Busta  
 5,003,356 A 3/1991 Wakai et al.  
 5,012,228 A 4/1991 Masuda et al.  
 5,051,570 A 9/1991 Tsujikawa et al.  
 5,055,899 A 10/1991 Wakai et al.  
 5,056,895 A \* 10/1991 Kahn ..... 349/114  
 5,066,110 A 11/1991 Mizushima et al.  
 5,084,905 A 1/1992 Sasaki et al.  
 5,091,334 A 2/1992 Yamazaki et al.  
 5,117,278 A 5/1992 Bellersen et al.  
 5,132,821 A 7/1992 Nicholas  
 5,200,846 A 4/1993 Hiroki et al.  
 5,206,183 A 4/1993 Dennison  
 5,227,900 A 7/1993 Inaba et al.  
 5,233,211 A 8/1993 Hayashi et al.  
 5,235,195 A 8/1993 Tran et al.  
 5,286,659 A 2/1994 Mitani et al.  
 5,287,205 A 2/1994 Yamazaki et al.  
 5,289,016 A \* 2/1994 Noguchi ..... 257/57  
 5,306,651 A 4/1994 Masumo et al.  
 5,327,001 A \* 7/1994 Wakai et al. .... 257/350  
 5,371,398 A 12/1994 Nishihara  
 5,453,858 A 9/1995 Yamazaki  
 5,474,941 A 12/1995 Mitani et al.  
 5,488,000 A 1/1996 Zhang et al.  
 5,495,353 A 2/1996 Yamazaki et al.  
 5,499,123 A 3/1996 Mikoshiba  
 5,500,538 A 3/1996 Yamazaki et al.  
 5,514,879 A 5/1996 Yamazaki  
 5,568,288 A 10/1996 Yamazaki et al.  
 5,583,369 A 12/1996 Yamazaki et al.  
 5,585,951 A \* 12/1996 Noda et al. .... 349/122  
 5,604,380 A 2/1997 Nishimura et al.  
 5,612,799 A 3/1997 Yamazaki et al.  
 5,614,732 A 3/1997 Yamazaki  
 5,641,974 A 6/1997 den Boer et al.  
 5,654,203 A 8/1997 Ohtani et al.  
 5,684,365 A 11/1997 Tang et al.  
 5,686,328 A \* 11/1997 Zhang et al. .... 438/30  
 5,701,167 A 12/1997 Yamazaki  
 5,705,829 A 1/1998 Miyanaga et al.  
 5,731,628 A \* 3/1998 Terashima ..... 257/637  
 5,763,899 A 6/1998 Yamazaki et al.  
 5,818,550 A \* 10/1998 Kadota et al. .... 349/43  
 5,821,138 A 10/1998 Yamazaki et al.  
 5,837,619 A 11/1998 Adachi et al.  
 5,844,254 A \* 12/1998 Manning et al. .... 257/67  
 5,849,043 A 12/1998 Zhang et al.  
 5,849,601 A 12/1998 Yamazaki  
 5,859,445 A 1/1999 Yamazaki  
 5,899,547 A 5/1999 Yamazaki et al.  
 5,905,555 A 5/1999 Yamazaki et al.  
 5,933,205 A 8/1999 Yamazaki et al.  
 5,946,059 A 8/1999 Yamazaki et al.  
 5,952,708 A 9/1999 Yamazaki  
 5,963,278 A 10/1999 Yamazaki et al.  
 5,990,542 A 11/1999 Yamazaki




6,011,277 A 1/2000 Yamazaki  
 6,023,075 A 2/2000 Yamazaki  
 6,239,470 B1 \* 5/2001 Yamazaki ..... 257/350  
 6,252,249 B1 6/2001 Yamazaki  
 6,281,520 B1 8/2001 Yamazaki  
 6,441,468 B1 8/2002 Yamazaki  
 6,445,059 B1 9/2002 Yamazaki  
 6,501,097 B1 \* 12/2002 Zhang ..... 257/72  
 2002/0117736 A1 8/2002 Yamazaki et al.




FOREIGN PATENT DOCUMENTS




EP 0 603 866 A1 6/1994  
 EP 2 274 723 8/1994  
 JP 52-4496 2/1977  
 JP 52-5010 2/1977  
 JP 55-32026 3/1980  
 JP 57-20778 2/1982  
 JP 58-2871 1/1983  
 JP 59-072745 4/1984  
 JP 59-172627 9/1984  
 JP 61-141174 6/1986  
 JP 61-223721 10/1986  
 JP 63-284522 11/1988  
 JP 1-124824 5/1989  
 JP 01-156725 6/1989  
 JP 1-183854 \* 7/1989 ..... 257/59  
 JP 01-283839 11/1989  
 JP 02-144525 6/1990  
 JP 02-171721 7/1990  
 JP 02-179615 7/1990  
 JP 2-234134 9/1990  
 JP 02-263474 10/1990  
 JP 03-159250 7/1991  
 JP 4-86601 3/1992  
 JP 04-087341 3/1992  
 JP 4-125683 4/1992  
 JP 04-220626 8/1992  
 JP 04-226040 8/1992  
 JP 04-242724 8/1992  
 JP 04-269837 9/1992  
 JP 05-034723 2/1993  
 JP 05-315360 11/1993  
 JP 6-11728 1/1994  
 JP 6-67009 3/1994  
 JP 6-138484 5/1994  
 JP 06-148684 5/1994  
 JP 6-175156 6/1994  
 JP 6-186578 7/1994  
 JP 07-064110 3/1995  
 JP 07-099324 4/1995  
 JP 7-128688 5/1995  
 JP 07-140485 6/1995  
 JP 07-211635 8/1995  
 JP 08-068990 3/1996  
 JP 9-90425 4/1997





\* cited by examiner











1

# ACTIVE MATRIX ELECTRO-LUMINESCENT DISPLAY WITH AN ORGANIC LEVELING LAYER

## CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. application Ser. No. 09/414,906, filed Oct. 8, 1999, which is a continuation of U.S. application Ser. No. 09/360,341, filed Jul. 22, 1999, now U.S. Pat. No. 6,169,293, which is a continuation of U.S. application Ser. No. 08/751,338, filed Nov. 18, 1996, now U.S. Pat. No. 5,952,708.

## BACKGROUND OF THE INVENTION

### 1. Field of the Invention

The present invention relates to a configuration applicable to flat panel displays represented by active matrix liquid crystal displays and EL type displays.

### 2. Description of Related Art

Conventional known flat panel displays include active matrix liquid crystal displays having a configuration wherein a thin film transistor for switching is provided to each of a number of pixels provided in the form of a matrix and wherein charge going in and out each pixel electrode is controlled by the thin film transistor.

In such a configuration, a masking means (a light shielding means) must be provided to prevent light from entering the thin film transistors provided in a pixel region.

A metal film is currently chosen as the masking means (the light shielding means) from the viewpoint of dispersion of impurities and stability. Further, such a masking means for thin film transistors is generally provided to serve also as a black matrix which covers peripheral edge regions of pixel electrodes.

Such a configuration has the following problems. The first problem is that a capacity is generated between the masking film and the thin film transistors, and this adversely affects the operation of the thin film transistors. The second problem is that since the masking film is generally formed on a substrate having irregularity thereon which can make the masking function insufficient.

The problem associated with the masking function equally applies to the black matrix provided so as to overlap with the edges of pixels.

It is an object of the invention disclosed in this specification to provide a configuration which solves the problems associated with a masking film for shading thin film transistors to achieve high performance as an active matrix display.

## SUMMARY OF THE INVENTION

A configuration according to the invention disclosed in this specification is characterized in that it comprises:

thin film transistors having outputs connected to pixel electrodes;

a layer insulation film made of a resin material provided on the thin film transistors; and

a masking film for shading the thin film transistors provided on the layer insulation film.

Another configuration according to the present invention is characterized in that it comprises:

a layer insulation film made of a resin material formed on thin film transistors; and

2

a masking film for shading the thin film transistors formed on the layer insulation film made of a resin material.

Still another configuration according to the present invention is characterized in that it comprises: a plurality of pixel electrodes provided in the form of a matrix; and a black matrix for covering at least a part of peripheral regions of the pixel electrodes, the black matrix being provided on a layer insulation film made of a resin material.

## BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1A through 1D illustrate steps of producing a pixel portion of an active matrix circuit.

FIGS. 2A through 2C illustrate steps of producing a pixel portion of an active matrix circuit.

FIGS. 3A through 3C illustrate steps of producing a pixel portion of an active matrix circuit. FIGS. 4A through 4C illustrate steps of producing a pixel portion of an active matrix circuit.

FIGS. 5A through 5D illustrate steps of producing a pixel portion of an active matrix circuit.

## DETAILED DESCRIPTION OF PREFERRED EMBODIMENT

A first embodiment of the present invention will now be described. FIGS. 1A through 1D and FIGS. 2A through 2C illustrate steps of producing a pixel portion of an active matrix liquid crystal display to be described in the present embodiment.

As shown in FIG. 1A, a silicon oxide film **102** having a thickness of 3000 Å as a backing film is first formed on a glass substrate **101** using a plasma CVD process.

Next, an amorphous silicon film (not shown) is formed which will later serve as a starting film made of a thin film semiconductor for forming an active layer of a thin film transistor. The amorphous silicon film (not shown) is formed to a thickness of 500 Å using a plasma CVD process.

The amorphous silicon film is then crystallized using a heating process or irradiating it with laser beams or using a process which is a combination of the heating process and irradiation with laser beams to obtain a crystalline silicon film (not shown).

The crystalline silicon film (not shown) is patterned to obtain an active layer **103** of a thin film transistor.

Next, a plasma CVD process is performed to form a silicon oxide film **104** having a thickness of 1000 Å which serves as a gate insulation film by covering the active layer **103** as shown in FIG. 1A. Thus, the state as shown in FIG. 1A is realized.

Next, an aluminum film (not shown) including 0.1% scandium by weight is formed to a thickness of 4000 Å using a sputtering process. This aluminum film will serve as a gate electrode later.

After forming the aluminum film, a dense anodic oxide film (not shown) is formed on the surface thereof to a thickness of 100 Å. This anodization is carried out by using the aluminum film as an anode in an electrolyte obtained by neutralizing an ethylene glycol solution including 3% tartaric acid with aqueous ammonia.

Further, patterning is performed by providing a resist mask (not shown). A gate electrode **105** is formed as a result of the patterning.

After the formation of the gate electrode **105**, anodization is carried out again with the resist mask (not shown) left in place. This anodization is carried out using an aqueous solution including 3% oxalic acid as an electrolyte.

This anodization selectively takes place only on side faces of the gate electrode **105** because of the leftover resist mask (not shown). The anodic oxide film formed in this step has a porous structure.

Thus, a porous anodic oxide film **106** is formed on the side faces of the gate electrode **105**.

This porous anodic oxide film can be grown to a thickness on the order of several  $\mu\text{m}$ . The size of this growth can be controlled by the duration of the anodization.

Here, the thickness of the anodic oxide film **106** is 6000  $\text{\AA}$ .

Next, anodization is carried out again using an electrolyte obtained by neutralizing an ethylene glycol solution including 3% tartaric acid with aqueous ammonia. In this anodizing step, since the electrolyte penetrates the porous anodic oxide film **106**, a dense anodic oxide film **107** is formed around the gate electrode **105**.

The thickness of this dense anodic oxide film **107** is 500. The primary function of this dense anodic oxide film **107** is to cover the surface of the gate electrode to prevent generation of hillocks and whiskers in subsequent steps.

It also has a function of protecting the gate electrode **105** so that it is not etched at the same time when the porous anodic oxide film **106** is removed later.

It also has a function of contributing to formation of an offset gate region which is formed later using the porous anodic oxide film **106** as a mask.

Thus, the state as shown in FIG. 1B is realized.

In this state, impurity ions are implanted. P (phosphorus) ions are implanted here to obtain an N-channel type thin film transistor.

When implantation of impurity ions is carried out in the state as shown in FIG. 1B, the impurity ions are selectively implanted in regions indicated by **108** and **111**. That is, the regions **108** and **111** become high density impurity regions.

The impurity ions are not implanted in a region **109** directly under the gate electrode **105** because the gate electrode **105** serves as a mask. This region **109** serves as a channel formation region.

The impurity ions are not implanted also in a region indicated by **110** because the porous anodic oxide film **105** and the dense anodic oxide film **107** serve as a mask. The region indicated by **107** serves as an offset gate region which functions neither as a source/drain region nor as a channel formation region.

Particularly, the offset gate region has a function of moderating the strength of an electric field formed between the channel formation region and the drain region. The presence of the offset gate region allows the OFF current value of the thin film transistor to be reduced and suppresses deterioration of the same.

Thus, the source region indicated by **108**, the channel formation region indicated by **109**, the offset gate region indicated by **110** and the drain region indicated by **111** are formed on a self-alignment basis.

When the implantation of impurity ions is completed, the porous anodic oxide film **106** is selectively removed. Then, an annealing process is performed by means of irradiation with laser beams. Since laser beams can be directed to the vicinity of the interface between the high density impurity region and the offset gate region, the junction portion which has been damaged by the implantation of impurity ions can be sufficiently annealed.

When the state as shown in FIG. 1B is realized, a silicon oxide film **112** having a thickness of 2000 is formed as a first layer insulation film.

A silicon nitride film or a multi-layer film consisting of a silicon oxide film and a silicon nitride film may be used as this first layer insulation film.

Next, a contact hole is formed in the first layer insulation film **112** to form a source electrode **113** which contacts with the source region of the thin film transistor. Thus, the state as shown in FIG. 1C is realized.

Then, a second layer insulation film **114** is formed using transparent polyimide resin or acrylic resin. The layer insulation film **114** made of a resin material is formed to have a flat surface. Thus, the state as shown FIG. 1D is realized.

Next, as shown in FIG. 2A, a chromium film is formed and patterned into a masking film **115** which serves as a masking film and also as a black matrix for the thin film transistor

A material having a relative dielectric constant equal to or smaller than 3 is chosen as the resin material for forming the second layer insulation film **114**. The film is to be made as thick as several  $\mu\text{m}$ . A resin material is advantageous for such an application because it does not prolong the time required for the production steps even when it is made thick.

Such a configuration makes it possible to prevent generation of a capacity between the masking film **115** made of chromium and the thin film transistor located thereunder.

Further, the surface of the second layer insulation film **114** can be easily flattened if it is formed from a resin material. This makes it possible to prevent leakage of light originating from surface irregularity.

When the state as shown in FIG. 2A is realized, a third layer insulation film **116** is formed using a resin material, silicon oxide film, or silicon nitride film. Here, the same resin material as for the second layer insulation film **114** is used for this third layer insulation film **116**.

The use of a resin material as the third layer insulation film advantageously solves the problem of generation of a capacity between a pixel electrode to be formed later and the masking film **115** and flattens the surface on which the pixel electrode is to be formed.

Thus, the state as shown in FIG. 2B is realized. Then, a pixel electrode **117** is formed by forming a contact hole, forming an ITO electrode which constitutes the pixel electrode, and performing patterning.

This completes the configuration as shown in FIG. 2C. In the configuration shown in FIG. 2C, the layer insulation film provided between the thin film transistor (especially the source electrode **113**) and the masking film (and/or black matrix) **115** can be formed to have a small relative dielectric constant and a large thickness. This makes it possible to prevent generation of an unnecessary capacity.

The configuration as described above can be realized because of the fact that the formation of a thick resin film is a simple industrial process which does not involve an increase in processing time as described above.

A second embodiment of the present invention will now be described.

The present embodiment is characterized in that it employs a configuration which is an improvement over the configuration described in the first embodiment to provide higher reliability.

As described above, a metal material such as chromium is used for the masking film and black matrix. From the viewpoint of long term reliability, however, concern exists about dispersion of impurities from the metal material and a short-circuit between the metal material and other electrodes or wiring.

5

Especially, if there is a pin hole in the layer insulation film **116** in the state as shown in FIG. 2C, a problem arises in that a short-circuit occurs between the masking film **115** (which may simultaneously serve as a black matrix) and the pixel electrode **117**.

A possible method for eliminating the influence of a pin hole present in the layer insulation film **116** is to form the layer insulation film **116** as a special multi-layer film.

However, such a method is unfavorable because it can increase the number of production steps and manufacturing cost.

A configuration according to the present embodiment addresses this situation by employing a material which can be anodized for the masking film for shading the thin film transistor and by forming an anodic oxide film thereon in the configuration described in the first embodiment.

Aluminum or tantalum may be used as the material which can be anodized.

Especially, the use of aluminum will provide a preferable masking film because it allows the anodic oxide film to be colored in black or a similar dark color utilizing an anodizing technique used for industrial products such as aluminum sashes.

FIGS. 3A through 3C schematically show production steps according to the present embodiment. First, the state as shown in FIG. 1D is realized by the steps shown in FIGS. 1A through 1D. Then, a masking film **115** is formed as shown in FIG. 2A.

Here, aluminum is used as the masking film **115**. Anodization is performed in an electrolyte to form an anodic oxide film **301** on the surface of the masking film **115** as shown in FIG. 3A.

FIG. 3A shows the masking film **301** as a masking film for shading a thin film transistor. However, it is normally extended further to also form a black matrix.

When the state as shown in FIG. 3A is realized, a third layer insulation film **116** is formed by a silicon oxide film or silicon nitride film or formed from a resin material as shown in FIG. 3B.

Further, a pixel electrode **117** is formed using ITO as shown in FIG. 3C.

Even if a pin hole exists in the layer insulation film **116**, the presence of the anodic oxide film **301** prevents the pixel electrode **117** and masking film **115** from being short-circuited.

In addition, since the anodic oxide film **301** is chemically stable, it is preferable from the viewpoint of long term reliability in that it can prevent impurities in the masking film **115** from being dispersed in the neighborhood thereof.

A third embodiment of the present invention will now be described.

The present embodiment relates to a configuration in which an aperture ratio of a pixel is improved. There is a general need for a configuration of a pixel that makes the aperture ratio as large as possible. In order to obtain a large aperture ratio of a pixel, the pixel electrode must be provided to have an area which is as wide as possible.

However, a severe limitation is placed on such an attempt in that if the pixel electrode overlaps the thin film transistor or wiring, a capacity is generated therebetween.

The present embodiment provides a configuration which reduces the problem of generation of a capacity.

FIGS. 4A through 4C show steps of producing the configuration according to the present embodiment. The steps shown in FIGS. 4A and 4B are the same as those in FIGS. 3A and 3B.

6

First, a masking film **115** made of aluminum is formed as shown in FIG. 4A. An anodic oxide film indicated by **301** is formed on the surface of the masking film **115**.

Further, a third layer insulation film **116** is formed as shown in FIG. 4B. The layer insulation film **116** is formed from a resin material.

A pixel electrode **117** is then formed using ITO as shown in FIG. 4C. The pixel electrode **117** is overlaid on the thin film transistor. This maximizes the aperture ratio of the pixel.

With the configuration as shown in FIG. 4C, layer insulation films **114** and **116** can be formed from a resin material having a small relative dielectric constant (as compared to a silicon oxide film or silicon nitride film) with an increased thickness. This makes it possible to reduce the problem of a capacity as described above.

Further, the area of the pixel electrode can be increased to obtain a larger aperture ratio for the pixel.

Although a top gate type is employed for a thin film transistor in the foregoing embodiments, in this embodiment 4 is described a method for manufacturing a bottom gate type thin film transistor in which a gate electrode is closer to a substrate than an active layer is.

The manufacturing steps in accordance with this embodiment 4 are shown in FIGS. 5(A) to 5(D). First, as shown in FIG. 5(A), a silicon oxide film **202** as a base film is formed on a glass substrate **201** by sputtering. Then, a gate electrode **203** is formed from aluminum.

In this gate electrode, scandium is contained in aluminum at 0.18 weight %. Concentration of other impurities should be made as low as possible. The foregoing is for suppressing formation of protrusion called hillock or whisker formed due to extraordinary growth of aluminum in the subsequent step.

Then, a silicon oxide film **204** functioning as a gate insulating film is formed to a thickness of 500Å by plasma CVD.

Then, an amorphous silicon film (to become a crystalline silicon film **205** later) not shown in the drawings is formed by plasma CVD as a starting film for forming an active layer of a thin film transistor. Low pressure thermal CVD may be used instead of plasma CVD.

Then, by a laser light irradiation, the amorphous silicon film not shown in the drawings is crystallized. A crystalline silicon film **205** is then obtained. Thus, a structure shown in FIG. 5(A) is obtained.

After a structure shown in FIG. 5(A) is obtained, an active layer **206** is formed by conducting a patterning.

Then, a silicon nitride film not shown in the drawings is formed, and is shaped into a mask pattern **207** made of the silicon nitride film, by irradiating a light thereto from a rear surface side of the substrate using the gate electrode.

The mask pattern **207** is formed as follows.

At first, a resist mask pattern is formed by light irradiation from a rear surface side of the substrate **201** using the gate electrode pattern. Further, the resist mask pattern is retreated by ashing. A pattern designated by a reference numeral **207** is obtained by patterning the silicon nitride film using the retreated resist mask pattern not shown in the drawings. Thus, the structure shown in FIG. 5(B) is obtained.

Then, an impurity doping is conducted using the mask pattern **207**. For example, P(phosphorus) is used as a dopant, and plasma doping is used as a doping method.

In this step, regions **208** and **209** are doped with P. A region **210** is not doped with P.

After completion of the doping, a laser light irradiation is conducted from above to conduct activation of the doped regions and to conduct annealing of damages caused due to impact of the dopant ions.

Thus, as shown in FIG. 5(C), a region **208** is formed as a source region. Also, a region **209** is formed as a drain region. Also, a region **210** is formed as a channel region.

Then, a silicon nitride film is formed as a first interlayer insulating film **211** to a thickness of 2000 Å by plasma CVD.

A silicon oxide film, silicon oxinitride film, or a multi-layer film comprising a silicon oxide film and a silicon nitride film (any one of them can be formed on the other) can be used instead of the silicon nitride single film, as the first interlayer insulating film used herein.

Then, a contact hole is formed for the source region **208** in the first interlayer insulating film **211**, and a source electrode is formed to provide a contact to the source region **208**. Thus, the structure shown in FIG. 5(C) is obtained.

Then, as shown in FIG. 5(D), a second interlayer insulating film **213** having a flat surface is formed from a transparent polyimide resin or acrylic resin. For example, a spin coating can be employed as a film formation method.

Then, a chromium film is formed on the second interlayer insulating film **213**, and is patterned to form a light-shielding film **214** which serves as both a light-shielding film and a black matrix for a thin film transistor. Then, a third interlayer insulating film **215** is formed from the same resin material film as the second interlayer insulating film **213**.

A contact hole which reaches the drain region **209** is formed in the first to third interlayer insulating films **211**, **213**, **215**. Then, ITO (indium tin oxide) film is formed on a surface of the third interlayer insulating film **215**, and is patterned into a pixel electrode **216**.

A thin film transistor shown in FIG. 5(D) is completed through the foregoing steps.

Using the invention disclosed in this specification, an effective masking film can be provided in a configuration of a pixel of an active matrix display, and an active matrix display having high performance can be configured. The invention disclosed in this specification is applicable not only to active matrix liquid crystal displays but also to EL type displays and the like of the active matrix type.

While particular embodiments of the present invention have been shown and described, it will be obvious to those skilled in the art that changes and modifications may be made without departing from this invention in its broader aspects and, therefore, the appended claims are to encompass within their scope all such changes and modifications as fall within the true spirit and scope of this invention.

What is claimed is:

1. An active matrix electro-luminescent display comprising:

a thin film transistor comprising a semiconductor film, a gate insulating film and gate electrode, provided over a substrate;

a first insulating film comprising silicon oxide provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising silicon nitride over said second insulating film; and

a pixel electrode provided over said third insulating film.

2. An active matrix electro-luminescent display according to claim 1, wherein said organic film comprises polyimide resin or acrylic resin.

3. An active matrix electro-luminescent display according to claim 1, wherein said pixel electrode comprises ITO.

4. An active matrix electro-luminescent display comprising:

a thin film transistor comprising a semiconductor film, a gate insulating film and gate electrode, provided over a substrate;

a first insulating film comprising silicon nitride provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising silicon nitride over said second insulating film; and

a pixel electrode provided over said third insulating film.

5. An active matrix electro-luminescent display according to claim 4, wherein said organic film comprises polyimide resin or acrylic resin.

6. An active matrix electro-luminescent display according to claim 4, wherein said pixel electrode comprises ITO.

7. An active matrix electro-luminescent display comprising:

a thin film transistor provided over a substrate;

a first insulating film comprising a multi-layer film comprising a silicon oxide film and a silicon nitride film provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising silicon nitride over said second insulating film; and

a pixel electrode provided over said third insulating film.

8. An active matrix electro-luminescent display according to claim 7, wherein said organic film comprises polyimide resin or acrylic resin.

9. An active matrix electro-luminescent display according to claim 7, wherein said pixel electrode comprises ITO.

10. An active matrix electro-luminescent display comprising:

a thin film transistor provided over a substrate and comprising a gate insulating film, a gate electrode and a semiconductor film having a source region, a drain region, a channel region provided between said source region and said drain region;

a first insulating film comprising silicon oxide provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising silicon nitride over said second insulating film; and

a pixel electrode provided over said third insulating film and connected with one of said source region and said drain region.

11. An active matrix electro-luminescent display according to claim 10, wherein said transparent organic film comprises polyimide resin or acrylic resin.

12. An active matrix electro-luminescent display according to claim 10, wherein said pixel electrode comprises ITO.

13. An active matrix electro-luminescent display comprising:

a thin film transistor provided over a substrate and comprising a gate insulating film, a gate electrode and a semiconductor film having a source region, a drain

region, a channel region provided between said source region and said drain region;  
 a first insulating film comprising silicon nitride provided over and covering said thin film transistor;  
 a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;  
 a third insulating film comprising silicon nitride over said second insulating film; and  
 a pixel electrode provided over said third insulating film and connected with one of said source region and said drain region.

14. An active matrix electro-luminescent display according to claim 13, wherein said organic film comprises polyimide resin or acrylic resin.

15. An active matrix electro-luminescent display according to claim 13, wherein said pixel electrode comprises ITO.

16. An active matrix electro-luminescent display comprising:

a thin film transistor provided over a substrate and comprising a gate insulating film, a gate electrode and a semiconductor film having a source region, a drain region, a channel region provided between said source region and said drain region;

a first insulating film comprising a multi-layer film comprising a silicon oxide film and a silicon nitride film provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising silicon nitride over said second insulating film; and

a pixel electrode provided over said third insulating film and connected with one of said source region and said drain region.

17. An active matrix electro-luminescent display according to claim 16, wherein said organic film comprises polyimide resin or acrylic resin.

18. An active matrix electro-luminescent display according to claim 16, wherein said pixel electrode comprises ITO.

19. An active matrix electro-luminescent display comprising:

a thin film transistor comprising a semiconductor film, a gate insulating film and a gate electrode, provided over a substrate;

a first insulating film comprising silicon oxide provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising nitride over said second insulating film; and

a pixel electrode provided over said third insulating film.

20. An active matrix electro-luminescent display according to claim 19, wherein said organic film comprises polyimide resin or acrylic resin.

21. An active matrix electro-luminescent display according to claim 19, wherein said pixel electrode comprises ITO.

22. An active matrix electro-luminescent display comprising:

a thin film transistor comprising a semiconductor film, a gate insulating film and gate electrode, provided over a substrate;

a first insulating film comprising silicon nitride provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising nitride over said second insulating film; and

a pixel electrode provided over said third insulating film.

23. An active matrix electro-luminescent display according to claim 22, wherein said organic film comprises polyimide resin or acrylic resin.

24. An active matrix electro-luminescent display according to claim 22, wherein said pixel electrode comprises ITO.

25. An active matrix electro-luminescent display comprising:

a thin film transistor comprising a semiconductor film, a gate insulating film and a gate electrode, provided over a substrate;

a first insulating film comprising a multi-layer film comprising a silicon oxide film and a silicon nitride film provided over and covering said thin film transistor;

a second insulating film comprising an organic resin film provided over said first insulating film to provide a leveled upper surface over said thin film transistor;

a third insulating film comprising nitride over said second insulating film; and

a pixel electrode provided over said third insulating film.

26. An active matrix electro-luminescent display according to claim 25, wherein said organic film comprises polyimide resin or acrylic resin.

27. An active matrix electro-luminescent display according to claim 25, wherein said pixel electrode comprises ITO.