

(19) **DANMARK**



Patent- og
Varemærkestyrelsen

(10) **DK/EP 2804841 T3**

(12) Oversættelse af
europæisk patentskrift

-
- (51) Int.Cl.: **C 03 C 3/12 (2006.01)** **C 03 C 3/14 (2006.01)** **C 03 C 8/04 (2006.01)**
C 03 C 8/14 (2006.01) **C 03 C 8/18 (2006.01)** **C 03 C 8/24 (2006.01)**
C 03 C 27/06 (2006.01) **E 06 B 3/66 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2021-06-21**
- (80) Dato for Den Europæiske Patentmyndigheds
bekendtgørelse om meddelelse af patentet: **2021-04-07**
- (86) Europæisk ansøgning nr.: **13701522.8**
- (86) Europæisk indleveringsdag: **2013-01-10**
- (87) Den europæiske ansøgnings publiceringsdag: **2014-11-26**
- (86) International ansøgning nr.: **US2013020968**
- (87) Internationalt publikationsnr.: **WO2013109456**
- (30) Prioritet: **2012-01-20 US 201213354963**
- (84) Designerede stater: **AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV
MC MK MT NL NO PL PT RO RS SE SI SK SM TR**
- (73) Patenthaver: **Guardian Glass, LLC, 2300 Harmon Road, Auburn Hills MI 48326, USA**
- (72) Opfinder: **DENNIS, Timothy A., 4226 Bloomdale Road, Bloomdale, OH 44817, USA**
- (74) Fuldmægtig i Danmark: **Chas. Hude A/S, H.C. Andersens Boulevard 33, 1780 København V, Danmark**
- (54) Benævnelse: **VARMEEKSPANSIONSKOEFFICIENTFYLDSTOF TIL VANADIUMBASEREDE FRITTEMATERIALER
OG/ELLER FREMGANGSMÅDER TIL FREMSTILLING OG/ELLER ANVENDELSE AF SAMME**
- (56) Fremdragne publikationer:
EP-A1- 1 065 183
WO-A1-2012/115796
WO-A1-2013/043340
WO-A1-2013/101748
US-A- 4 221 604
US-A1- 2005 233 885
US-A1- 2006 003 883
US-A1- 2012 213 954
US-A1- 2012 308 747
**DATABASE WPI Week 201003 Thomson Scientific, London, GB; AN 2009-S58685 -& JP 2009 298673 A (NIPPON
ELECTRIC GLASS CO) 24 December 2009 (2009-12-24)**
**DATABASE WPI Week 200966 Thomson Scientific, London, GB; AN 2009-P25052 -& JP 2009 221047 A (NIPPON
ELECTRIC GLASS CO) 1 October 2009 (2009-10-01)**
**DATABASE WPI Week 200966 Thomson Scientific, London, GB; AN 2009-P25051 -& JP 2009 221048 A (NIPPON
ELECTRIC GLASS CO) 1 October 2009 (2009-10-01)**
DATABASE WPI Week 201130 Thomson Scientific, London, GB; AN 2011-E36875 -& JP 2011 086518 A (NIPPON

Fortsættes ...

ELECTRIC GLASS CO) 28 April 2011 (2011-04-28)

DESCRIPTION

FIELD OF THE INVENTION

[0001] Certain example embodiments of this invention relate to coefficient of thermal expansion (CTE) fillers for glass frit materials. More particularly, certain example embodiments relate to fillers that are usable with vanadium-based frit materials. In certain example embodiments the fillers and frit materials may be used for glass articles (e.g., for use in vacuum insulated glass or VIG units), and/or methods of making the same, as well as articles including such frit materials and fillers and/or methods of making the same. In certain example embodiments, frits with CTE filler(s) are used in connection with vacuum insulated glass (VIG) units, and/or a method is provided for sealing VIG units with the frits/seals. In certain example embodiments, material(s) in certain forms and/or particle sizes of for a CTE filler may be used.

BACKGROUND AND SUMMARY OF EXAMPLE EMBODIMENTS OF THE INVENTION

[0002] Vacuum IG units are known in the art. For example, see U.S. Patent Nos. 5,664,395, 5,657,607, and 5,902,652.

[0003] Further, US 2005 233 885 A1 suggests a lead-free glass material for use in sealing. The glass composition includes a network-former oxide composed of any one of or both of B_2O_3 and V_2O_5 of 20-80% by weight, ZnO of 0-60% by weight and BaO of 0-80% by weight, wherein at least one of ZnO and BaO is included as an essential ingredient.

[0004] Figs. 1-2 illustrate a conventional vacuum IG unit (vacuum IG unit or VIG unit). Vacuum IG unit 1 includes two spaced apart glass substrates 2 and 3, which enclose an evacuated or low pressure space 6 there between. Glass sheets/substrates 2 and 3 are interconnected by peripheral or edge seal of fused solder glass 4 and an array of support pillars or spacers 5.

[0005] Pump out tube 8 is hermetically sealed by solder glass 9 to an aperture or hole 10 which passes from an interior surface of glass sheet 2 to the bottom of recess 11 in the exterior face of sheet 2. A vacuum is attached to pump out tube 8 so that the interior cavity between substrates 2 and 3 can be evacuated to create a low pressure area or space 6. After evacuation, tube 8 is melted to seal the vacuum. Recess 11 retains sealed tube 8. Optionally, a chemical getter 12 may be included within recess 13.

[0006] Conventional vacuum IG units, with their fused solder glass peripheral seals 4, have been manufactured as follows. Glass frit in a solution (ultimately to form solder glass edge seal 4) is initially deposited around the periphery of substrate 2. The other substrate 3 is brought down over top of substrate 2 so as to sandwich spacers 5 and the glass frit/solution there between. The entire assembly including sheets 2, 3, the spacers, and the seal material is then

heated to a temperature of approximately 500°C, at which point the glass frit melts, wets the surfaces of the glass sheets 2, 3, and ultimately forms hermetic peripheral or edge seal 4. This approximately 500°C temperature is maintained for from about one to eight hours. After formation of the peripheral/edge seal 4 and the seal around tube 8, the assembly is cooled to room temperature. It is noted that column 2 of U.S. Patent No. 5,664,395 states that a conventional vacuum IG processing temperature is approximately 500°C for one hour. Inventors Lenzen, Turner and Collins of the '395 patent have stated that "the edge seal process is currently quite slow: typically the temperature of the sample is increased at 200°C per hour, and held for one hour at a constant value ranging from 430°C and 530°C depending on the solder glass composition." After formation of edge seal 4, a vacuum is drawn via the tube to form low pressure space 6.

[0007] The composition of conventional edge seals are known in the art. See, for example, U.S. Patent Nos. 3,837,866; 4,256,495; 4,743,302; 5,051,381; 5,188,990; 5,336,644; 5,534,469; 7,425,518, and U.S. Publication No. 2005/0233885.

[0008] Unfortunately, the aforesaid high temperatures and long heating times of the entire assembly utilized in the formulation of edge seal 4 are undesirable. This is especially the case when it is desired to use a heat strengthened or tempered glass substrate(s) 2, 3 in the vacuum IG unit. As shown in Figs. 3-4, tempered glass loses temper strength upon exposure to high temperatures as a function of heating time. Moreover, such high processing temperatures may adversely affect certain low-E coating(s) that may be applied to one or both of the glass substrates in certain instances.

[0009] Fig. 3 is a graph illustrating how fully thermally tempered plate glass loses original temper upon exposure to different temperatures for different periods of time, where the original center tension stress is 8128 $\mu\text{m}/\text{cm}$ (3200 μm per inch). The x-axis in Fig. 3 is exponentially representative of time in hours (from 1 to 1,000 hours), while the y-axis is indicative of the percentage of original temper strength remaining after heat exposure. Fig. 4 is a graph similar to Fig. 3, except that the x-axis in Fig. 4 extends from zero to one hour exponentially.

[0010] Seven different curves are illustrated in Fig. 3, each indicative of a different temperature exposure in degrees Fahrenheit (°F). The different curves/lines are 400°F (across the top of the Fig. 3 graph), 500°F, 600°F, 700°F, 800°F, 900°F, and 950°F (the bottom curve of the Fig. 3 graph). A temperature of 900°F is equivalent to approximately 482°C, which is within the range utilized for forming the aforesaid conventional solder glass peripheral seal 4 in Figs. 1-2. Thus, attention is drawn to the 900°F curve in Fig. 3, labeled by reference number 18. As shown, only 20% of the original temper strength remains after one hour at this temperature (900°F or 482°C). Such a significant loss (i.e., 80% loss) of temper strength may be undesirable.

[0011] As seen in Figs. 3-4, the percentage of remaining tempering strength varies based on the temperature that is exposed to the tempered glass. For example, at 900°F only about 20% of the original temper strength remains. When the temperature that the sheet is exposed to is

reduced to 800°F, about 428°C, the amount of strength remaining is about 70%. Finally, a reduction in temperature to about 600°F, about 315°C, results in about 95% of the original temper strength of the sheet remaining. As will be appreciated, it is desirable to reduce any temper strength losses as a result of exposing a tempered sheet of glass to high temperatures.

[0012] As noted above, the creation of VIG units includes the creation of a hermetic seal that can withstand the pressure applied from the vacuum created on inside of the unit. As also discussed above, the creation of the seal may conventionally involve temperatures of at or above 500°C. These temperatures are required in order to obtain a high enough temperature in order for the frit material used for the seal to melt and form the required seal for the VIG units. As shown above, such a temperature can result in a strength reduction for VIG units using tempered glass.

[0013] One conventional solution to sealing glass substrates together is to use an epoxy. However, in the case of VIG units, epoxy compositions may be insufficient to hold a seal on a vacuum. Furthermore, epoxies may be susceptible to environmental factors that may further reduce their effectiveness when applied to VIG units.

[0014] Another conventional solution is to use a frit solution that contains lead. As is known, lead has a relatively low melting point. Accordingly, temperatures for sealing the VIG units may not need to be as high for other frit materials, and thus the tempering strength of tempered glass substrates may not be reduced by the same amount required for other frit based materials. However, while lead based frits may resolve the above structural issues, the usage of lead in the frit may create new problems. Specifically, the health consequences to the population for products that contain lead. Additionally, certain countries (e.g., in the European Union) may impose strict requirements on the amount of lead that can be contained in a given product. Indeed, some countries (or customers) may require products that are completely lead-free.

[0015] As is known in the art, when a frit or sealing material is disposed onto a substrate, the coefficient of thermal expansion (CTE) of the sealing material may be different than that of the underlying substrate. This may create a CTE mismatch between the two materials. In such situations, as the temperature of the underlying substrate and the sealing material increases/decreases, the materials may respectively expand/shrink at different rates. This may cause structural problems in a product in which the sealing material is disposed (e.g., bound or adhered) against a substrate. For example, the sealing material may end up delaminating from the underlying substrate and causing the product to fail (e.g., as the VIG loses vacuum). As such failure is undesirable, a CTE filler may be added to the sealing material to adjust its expansion rate to bring it closer to (or match) that of the underlying substrate.

[0016] For certain applications (e.g., a given frit/substrate combination), an appropriate CTE filler may be known and may simply be added to the frit to obtain a CTE match. However, certain types of frits/glass articles may not have known or acceptable CTE fillers (e.g., a known CTE filler may contain lead above a certain amount), thus making it generally unsuitable for

some markets and/or non-compliant with certain standards. Accordingly, it will be appreciated that CTE fillers for certain types of frit material, for example, a vanadium based frit material, may be desirable.

[0017] It will also be appreciated that techniques for creating improved seals for glass articles are continuously sought after.

[0018] Furthermore, frit materials may sometimes include binder agents that are used to, for example, facilitate binding the various materials that make up the frit. However, in certain instances the materials used in a frit may have a melting temperature that is less than a burn out point for a binder that is used in the frit. In such situations, the incomplete burn off of a binder may result in a porous frit seal, reduced frit to glass bonding due to, for example, carbon contamination in the frit, or other characteristics that may be undesirable for frit based seals.

[0019] EP 1065183 A1 discloses a double glazing having a plurality of sheet glass juxtaposed in the direction of thickness with spacers arranged in between, peripheries of these sheet glasses being sealed throughout the circumference thereof. Reinforced sheet glass is employed for at least one of the plurality of sheet glasses, and the peripheries of the sheet glasses are sealed by a sealing material having a sealing temperature below 400°C.

[0020] WO 2013/043340 A1 discloses certain example embodiments related to improved seals for glass articles. Furthermore, certain example embodiments are discussed related to a composition used for sealing an insulated glass unit. In certain example embodiments the composition includes in mol % 45-50 vanadium oxide, 20-23 barium oxide, 9-12 zinc oxide, and at least four additional additives. In certain example embodiments, a vacuum insulated glass unit includes first and second glass substrates that are sealed together with a seal that includes the above-described composition.

[0021] WO 2013/101748 A1 discloses certain example embodiments related to seals for glass articles. Certain example embodiments relate to a composition used for sealing an insulated glass unit. In certain example embodiments the composition includes vanadium oxide, barium oxide, zinc oxide, and at least one additional additive. For instance, another additive that is a different metal oxide or different metal chloride may be provided. In certain example embodiments, a composition may be combined with a binder solution that substantially or completely burns out by the time the composition is melted. In certain example embodiments, a vacuum insulated glass unit includes first and second glass substrates that are sealed together with a seal that includes the above-described composition.

[0022] WO 2012/115796A1 discloses certain example embodiments related to improved seals for glass articles. Certain example embodiments relate to a composition used for sealing an insulated glass unit. In certain example embodiments the composition includes vanadium oxide, barium oxide, zinc oxide, and at least one additional additive in particular the fit material comprises in weight%: V₂O₅, 50-60, BaO, 27-33, ZnO 9-12 and one additive selected from:

Ta₂O₅, Ti₂O₃, SrCl₂, GeO₂, CuO, AgO, Nb₂O₅, MgO, B₂O₃, SiO₂, Ti₂O₃, Y₂O₃, SnF₂, SnO₂, CuCl, SnCl₂, CeO₂, AgCl, In₂O₃, SnO, SrO and Al₂O₃. For instance, another additive that is a different metal oxide or different metal chloride may be provided. In certain example embodiments, a vacuum insulated glass unit includes first and second glass substrates that are sealed together with a seal that includes the above-described composition.

[0023] US 2006/0003883 A1 discloses a lead-free glass material for use in sealing, which has a glass composition being free of lead and exhibits high performance in the range of choices for the material to be sealed, the sealing processability, the sealing quality and the like, has a glass composition including four types of metal oxides of V₂O₅, ZnO, BaO and P₂O₅ as essential ingredients.

[0024] Accordingly, it will be appreciated that there exists a need in the art for binders, solvents, CTE fillers, etc., that may be used with frit materials, e.g., with frit materials that have a relatively reduced melting point such as vanadium based frits (e.g., VBZ frits).

[0025] It also will be appreciated that there exists a need in the art for improved seals and the like that can be integrated with tempered glass units, such as, for example, VIG units. The seals may be designed to allow for reduced temperature sealing such that annealed or tempered glass can be sealed without detrimental impact on the properties of the glass.

[0026] The present invention provides methods as defined in claims 1, 9 and 11, a material as defined in claim 5, as well as a vacuum insulated glass (VIG) unit as defined in claim 8.

[0027] In certain example embodiments, a frit material may provide glass to frit bonding sufficient for VIG purposes (e.g., in terms of structural strength). In certain example embodiments, the provided frit may provide proper glass wetting properties. In certain example embodiments, the frit may seal and have structural strength and a homogenous glassy structure to provide an adequate barrier to prevent vacuum degradation in example VIG units over a period of time.

[0028] In certain instances, improvements in melt flow may enable improved frit matching to glass expansion and/or increase process tolerances to frit bead variations. Improved wetting and bonding properties of a frit material may increase VIG yield by reducing bonding failures of the frit to the glass. A reduction in crystallization may additionally or alternatively facilitate a selected composition to meeting different heating environments (e.g., an internal seal, an external seal, etc).

[0029] In certain example embodiments, a method of making a vacuum insulated glass (VIG) unit is provided. First and second glass substrates are provided in substantially parallel, spaced apart relation to one another, with a gap being defined between the first and second substrates. A material is disposed proximate to the first and/or second glass substrates, with the material comprising at least a frit material and a coefficient of thermal expansion (CTE) material. Energy is applied to the material so as to melt the material at a melting temperature.

The CTE material comprises elements that are spherical in form, and said elements are between 60 and 100 microns in size. The frit material is formed from a base composition includes ~45-50% (Normalized Mole %) vanadium oxide,

[0030] US4221604 A discloses the forming of hermetic seals suitable for sealing materials having dissimilar thermal expansions which are formed by reacting an effective amount of a metal powder, selected from the group consisting of aluminum, antimony and zirconium, with glass frit having a softening point of $<750^{\circ}\text{C}$. and a coefficient of thermal expansion sufficiently compatible with the materials being sealed to yield seals characterized by a coefficient of thermal expansion closely matching or similar to those of the materials being sealed and a use temperature equal to or greater than 1000°C . The seals disclosed are particularly suitable for bonding ceramic to ceramic.

[0031] JP 2009298673 A discloses a sealing material characterized in that (1) it is used for forming a sealing layer having a thickness of $\leq 35\text{ }\mu\text{m}$, (2) it contains 50-99% of powdered glass and 1-50% of a powdered heat resistant filler by volume%, (3) the maximum particle size of the powdered heat resistant filler is below $2.5\text{-}35\text{ }\mu\text{m}$, and (4) the maximum particle size of the powdered heat resistant filler is smaller than the thickness of the sealing layer.

[0032] JP 2009221047 A and JP 2009221048 A disclose a vanadium-based glass composition and a vanadium-based material suitable for sealing a display or the like. Specifically, these disclose a fluorescent display tube (hereinafter referred to as VFD), a plasma display panel (hereinafter referred to as PDP), various types of field emission displays (hereinafter referred to as FED), and an organic electroluminescence display (hereinafter referred to as organic ELD). These further relate to a vanadium-based glass composition and a vanadium-based material that are suitable for sealing such as the above.

[0033] JP 2011086518 A discloses a glass composition for the dye-sensitized solar cell which contains 20-50% V_2O_5 , 15-45% P_2O_5 , 5-35% ZnO , and 15-40% BaO at mol% in terms of oxide as glass formation. Furthermore, the material for the dye-sensitized solar cell contains 50-100 vol.% of glass powder made of a glass composition for the dye-sensitized solar cell, and 0-50 vol.% of fireproof filler.

[0034] ~20-23% (Normalized Mole %) barium oxide, and ~19-22% (Normalized Mole %) zinc oxide.

[0035] In certain example embodiments, a material is provided. A coefficient of thermal expansion (CTE) material is substantially lead-free. A frit material has a composition that includes: ~45-50% (Normalized Mole %) vanadium oxide, ~20-23% (Normalized Mole %) barium oxide, and ~19-22% (Normalized Mole %) zinc oxide. The material has a first CTE value that is within 15% of soda lime silicate glass by virtue of the CTE material's composition.

[0036] In certain example embodiments, a vacuum insulated glass (VIG) unit is provided. First and second substantially parallel, spaced apart glass substrates are provided. An edge seal is

provided around a periphery of the first and/or second substrates to form a hermetic seal therebetween and at least partially defines a gap between the first and second substrates. The gap is provided at a pressure less than atmospheric. The edge seal is formed from the material, at least initially, according to the techniques disclosed herein, e.g., so as to include vanadium, barium, and zinc, as well as at least 4 additives, and a CTE matching material.

[0037] In certain example embodiments, a method of making a material is provided. A composition is provided to a holder, the composition comprising ~45-50% (Normalized Mole %) vanadium oxide, ~20-23% (Normalized Mole %) barium oxide, and ~19-22% (Normalized Mole %) zinc oxide. The composition is melted. The melted composition is cooled and/or allowed to cool so as to form an intermediate article. A base frit material is created from the intermediate article. The base frit material is combined with a CTE filler material that is comprised of particles that are 150-170 mesh and spherical in shape.

[0038] In certain example embodiments, a method of bonding a frit material to a glass substrate is provided. The frit material is combined with a CTE material to form a combined material. The combined material is disposed on the substrate. The combined material is heated to a temperature of less than 400 degrees C. A coefficient thermal expansion associated with the combined material is within 10% of a coefficient of thermal expansion for the glass substrate when heat is applied to the combined material. The frit material includes a composition comprising: ~45-50% (Normalized Mole %) vanadium oxide, ~20-23% (Normalized Mole %) barium oxide, and ~19-22% (Normalized Mole %) zinc oxide.

[0039] The features, aspects, advantages, and example embodiments described herein may be combined in any suitable combination or sub-combination to realize yet further embodiments.

BRIEF DESCRIPTION OF THE DRAWINGS

[0040] These and other features and advantages may be better and more completely understood by reference to the following detailed description of exemplary illustrative embodiments in conjunction with the drawings, of which:

FIGURE 1 is a cross-sectional view of a conventional vacuum IG unit;

FIGURE 2 is a top plan view of the bottom substrate, edge seal, and spacers of the Fig. 1 vacuum IG unit taken along the section line illustrated in Fig. 1;

FIGURE 3 is a graph correlating time (hours) versus percent tempering strength remaining, illustrating the loss of original temper strength for a thermally tempered sheet of glass after exposure to different temperatures for different periods of time;

FIGURE 4 is a graph correlating time versus percent tempering strength remaining similar to that of Fig. 3, except that a smaller time period is provided on the x-axis;

FIGURE 5 is cross-sectional view of a vacuum insulated glass unit according to certain example embodiments;

FIGURE 6 is a flowchart illustrating a process for making a vacuum insulated glass unit with a frit material according to certain example embodiments;

FIGURES 7A-7D are graphs summarizing properties of compositions according to certain example embodiments;

FIGURES 8A-8C are graphs summarizing the quality of compositions according to certain exemplary embodiments;

FIGURE 9 is a graph showing results when additional elements are added to compositions according to certain example embodiments;

FIGURES 10A-10C show graphs summarizing impacts of additives being added to vanadium based frits according to certain example embodiments;

FIGURES 11A-11C show graphs summarizing absorption in the visible and infrared wavelengths for vanadium based frits according to certain example embodiments;

FIGURES 12A-12C are graphs summarizing flow characteristics of example frit materials according to certain example embodiments;

FIGURE 13 is a graph showing thermogravimetric analysis of certain example binding agents;

FIGURES 14A and 14B respectively show a heating profile graph and the example frit materials melted according to the heating profile;

FIGURES 15A and 15B respectively show another heating profile graph and the example frit materials melted according to the heating profile;

FIGURE 16 shows yet another heating profile graph;

FIGURES 17-20 show example frit materials melted according to certain example embodiments;

FIGURE 21 is a flowchart illustrating a process for melting a frit material onto a substrate according to certain example embodiments;

FIGURE 22 shows a graph illustrating the delamination properties of certain example materials;

FIGURES 23A-23C show microscope images of example particles of certain example CTE fillers; and

FIGURE 24 is a flowchart illustrating a process for creating an article according to certain example embodiments.

DETAILED DESCRIPTION OF EXAMPLE EMBODIMENTS OF THE INVENTION

[0041] The following description is provided in relation to several example embodiments which may share common characteristics, features, etc.

[0042] Certain example embodiments may relate to glass units (e.g., VIG units) that include two glass substrates sealed with an improved seal, e.g., of or including a vanadium-based frit material. In certain example embodiments an improved seal may include the following materials: vanadium oxide, barium oxide, and zinc oxide. In addition, certain example embodiments may include one or more of the following compounds: Ta_2O_5 , Ti_2O_3 , SrCl_2 , GeO_2 , CuO , AgO , Nb_2O_5 , B_2O_3 , MgO , SiO_2 , TeO_2 , Ti_2O_3 , Y_2O_3 , SnF_2 , SnO_2 , CuCl , SnCl_2 , CeO_2 , AgCl , In_2O_3 , SnO , SrO , MgO , MoO_3 , CsCO_3 , CuCl_2 , and Al_2O_3 .

[0043] Fig. 5 is cross-sectional view of a vacuum insulated glass unit according to certain example embodiments. VIG unit 500 may include first and second glass substrates 502a and 502b that are spaced apart and define a space therebetween. The glass substrates 502a and 502b may be connected via an improved seal 504, of or including a vanadium-based frit. Support pillars 506 may help maintain the first and second substrates 502a and 502b in substantially parallel spaced apart relation to one another. It will be appreciated that the CTE of the improved seal 504 and the glass substrates 502a and 502b may substantially match one another. This may be advantageous in terms of reducing the likelihood of the glass cracking, etc. Although Fig. 5 is described in relation to a VIG unit, it will be appreciated that the improved seal 504, of or including a vanadium-based frit may be used in connection with other articles and/or arrangements including, for example, insulating glass (IG) units and/or other articles.

[0044] Fig. 6 is a flowchart illustrating a process for preparing a frit material to be used in making a vacuum insulated glass unit according to certain example embodiments. In step 600, base compounds are combined and disposed into an appropriate container (e.g., a heat resistant container such as, for example, a ceramic container). In step 602, the combined compound is melted. Preferably, the temperature to melt the combined material may be at least 1000°C . In certain exemplary embodiments, the combined compound is melted at 1000°C for between 30 to 60 minutes. In certain exemplary embodiments, the combined compound is melted at 1100°C for 60 minutes. In certain exemplary embodiments, the combined compound is melted at 1200°C for 60 minutes. In certain exemplary embodiments, the melting temperature is a cycle that includes 500°C for 15 minutes, 550°C for 15 minutes, 600°C for 15 minutes, and a ramp up to 1000°C for 60 minutes.

[0045] After the combined compounds are melted, the material may be cooled in step 604, e.g., to form a glass sheet. After cooling, the glass may be crushed or ground into fine particulates in step 606. In certain example embodiments, the size of the particulates may be

no larger than about 100 mesh. Once the glass is ground into a powder, it may be disposed between the substrates in step 608. In certain example embodiments, the powder may be dispensed as a paste with a binder. Additional details on binding and/or solvent agents that may be used in certain example embodiments are provided in greater detail below. Heat may then be applied in step 610 to the glass substrate and the powder. In certain example embodiments, the heat may be between 300°C and 400°C, or more preferably between 325°C and 375°C. It will be appreciated that when heat of the above temperatures is applied to tempered glass that the tempered glass may lose a reduced amount of strength versus when heat of in excess of 350°C is applied to the tempered glass. Thus, certain example embodiments preferably involve a frit melting temperature of less than 500°C, more preferably less than 425°C, and sometimes less than 350°C.

[0046] In certain example embodiments, the combined compounds include the following materials: vanadium oxide, barium oxide, and zinc oxide.

[0047] Figs. 7A-7D show graphs summarizing properties of compositions according to certain example embodiments.

[0048] The table below corresponds to the data shown in Fig. 7A with those compositions with a melt quality of less than 4 (on a scale of 0 to 5) omitted from the table.

Table 1, Normalized Moles of Batch Composition								
V ₂ O ₅	BaO	ZnO	BaO/ZnO	Bi ₂ O ₃	B ₂ O ₃	Tg(C)	Tx1(C)	Rating
43.66%	9.87%	46.47%	0.21			320	410	4
39.01%	13.25%	37.37%	.35	2.18%	8.20%	312	430	4
47.33%	12.96%	24.41%	0.53	9.95%	5.53%	305	380	4
50.24%	23.38%	21.39%	1.33			320	425	4
51.54%	26.26%	16.46%	1.60	5.75%		320	410	4.5

[0049] The melts shown in Fig. 7A were applied to a microscope glass slide with a temperature of 375°C applied for 15 minutes. Fig. 7B shows a graph that includes the crystallization temperature (first crystallization peak - Tx1 - of the above table) of the above melts. According to certain exemplary embodiments, a preferred temperature for Tx1 may be between about 375°C and 425°C, preferably about 400°C.

[0050] Fig. 7C shows the transition glass temperatures, Tg, compared the above melts. The graph showing exemplary data shows that Tg values between about 290C and 335C may be preferred for the above compositions.

[0051] Fig. 7D includes the above melts in a graph showing the melt quality versus the barium/zinc ratio.

[0052] Figs. 8A-8C show graphs that summarize the quality of compositions according to certain exemplary embodiments. Fig. 8A summarizes the V_2O_5 percentage used in certain exemplary compositions. Fig. 8B summarizes the BaO percentage used in certain exemplary compositions. Fig. 8C summarizes the ZnO percentage used in certain exemplary compositions. As shown in the illustrative graphs, a vanadium percentage of between about 51% and 53% may be preferable according to certain example embodiments.

[0053] Below, tables 2A-2C show exemplary compositions according to certain example embodiments. Additionally, examples 7-15 in the tables correspond to graphs 8A-8C. For the compositions shown in the below tables, $BaCO_3$ factor of 1.287027979 was used to convert to a BaO resulting compound.

Table 2A										
	Weight Percentage				Weights of Batch Composition for 25 grams			Normalized Weight Percentage		
Ex.	V_2O_5	BaO	ZnO	Weight Normal	V_2O_5	BaO	ZnO	V_2O_5	BaO	ZnO
1	60	30	10	0.23	13.800	8.880	2.300	55.24	35.55	9.21
2	52.5	25	10	0.27	14.175	8.687	2.700	55.45	33.99	10.56
3	45	20	10	0.31	13.950	7.980	3.100	55.73	31.88	12.39
4	45	10	20	0.32	14.400	4.118	6.400	57.79	16.53	25.68
5	52.5	10	25	0.28	14.700	3.604	7.000	58.09	14.24	27.66
6	60	10	30	0.25	15.000	3.218	7.500	58.33	12.51	29.16
7	52.5	25	10	0.24	12.600	7.722	2.400	55.45	33.99	10.56
8	57.5	25	10	0.25	14.375	8.044	2.500	57.69	32.28	10.03
9	47.5	25	10	0.28	13.300	9.009	2.800	52.97	35.88	11.15
10	52.5	27.5	10	0.26	13.650	9.202	2.600	53.63	36.15	10.22
11	57.5	27.5	10	0.25	14.375	8.848	2.500	55.88	34.40	9.72
12	47.5	27.5	10	0.27	12.825	9.556	2.700	51.13	38.10	10.77
13	52.5	22.5	10	0.28	14.700	8.108	2.800	57.40	31.66	10.93
14	57.5	22.5	10	0.26	14.950	7.529	2.600	59.61	30.02	10.37
15	47.5	22.5	10	0.29	13.775	8.398	2.900	54.94	33.49	11.57

Table 2B							
	Moles of Batch			Normalized Moles			
Ex.	V_2O_5	BaO	ZnO	V_2O_5	BaO	ZnO	Glass Type
1	0.3037	0.1801	0.1132	50.87%	30.17%	18.95%	amorphous
2	0.3049	0.1722	0.1298	50.24%	28.38%	21.39%	glassy
3	0.3064	0.1616	0.1522	49.41%	26.05%	24.54%	amorphous
4	0.3177	0.0838	0.3156	44.31%	11.68%	44.01%	amorphous

Table 2B							
	Moles of Batch			Normalized Moles			
Ex.	V ₂ O ₅	BaO	ZnO	V ₂ O ₅	BaO	ZnO	Glass Type
5	0.3194	0.0722	0.3400	43.66%	9.87%	46.47%	amorphous
6	0.3207	0.0634	0.3584	43.19%	8.54%	48.27%	amorphous
7	0.3049	0.1722	0.1298	50.24%	28.38%	21.39%	glassy
8	0.3172	0.1636	0.1233	52.51%	27.08%	20.41%	glassy
9	0.2912	0.1818	0.1370	47.74%	29.80%	22.46%	glassy
10	0.2949	0.1832	0.1255	48.85%	30.35%	20.80%	glassy
11	0.3073	0.1743	0.1194	51.12%	29.00%	19.87%	glassy
12	0.2811	0.1931	0.1323	46.35%	31.83%	21.81%	glassy
13	0.3156	0.1604	0.1344	51.70%	26.28%	22.01%	glassy
14	0.3278	0.1521	0.1274	53.97%	25.05%	20.98%	glassy
15	0.3021	0.1697	0.1421	49.20%	27.65%	23.15%	glassy

[0054] The rating shown in Table 2C is based off of depositing the ground composition on a microscope glass slide and heating the composition at about 375°C for between 10 and 30 minutes.

Table 2C						
Example	T _g (C°)	T _{x2} (C°)	T _{x2} (C°)	T _{x1} - T _g	Rating	
1	280	330	540	50	0.0	
2	320	425	525	105	4.0	
3	280	430	550	150	0.0	
4	280	320	365	40	0.0	
5	320	410	560	90	4.0	
6	285	425	560	140	0.0	
7	315	390	530	75	4.5	
8	295,325	415	535	90	5.0	
9	320	420	525	100	4.5	
10	325	410	540	85	4.5	
11	315	395	530	80	4.5	
12	330	415	560	85	4.0	
13	315	400	530	85	5.0	
14	305	395	530	90	4.0	
15	320	395	525	75	4.5	

[0055] Fig. 9 shows a graph with results of adding additional elements (e.g., Bi_2O_3 and B_2O_3) to a vanadium based frit. Corresponding data shown in Fig. 9 is also displayed below in Table 3.

Table 3								
Ex.	V2O5	BaO	ZnO	Bi2O3	B2O3	Tg(C)	Tx1(C)	DSC Responses
1	65.39%	14.87%	12.46%	0.00%	7.28%	320	430	medium weak
2	60.96%	13.86%	11.61%	0.00%	13.57%	240	415	very weak
3	69.71%	15.85%	13.28%	1.16%	0.00%	315	405	strong peaks
4	64.69%	14.71%	12.32%	1.08%	7.20%	325	440	very weak
5	68.91%	15.67%	13.13%	2.29%	0.00%	320	410	medium weak
6	64.00%	14.56%	12.19%	2.13%	7.12%	320	425	very weak
7	59.74%	13.59%	11.38%	1.99%	13.30%	315	410	very weak
8	60.34%	13.72%	11.49%	1.00%	13.43%	315	400	very weak
9	70.53%	16.04%	13.43%	0.00%	0.00%	315	380	strong peaks

[0056] In certain example embodiments, a strong DSC response may correspond to a good remelt quality. In certain example embodiments, the addition of bismuth in concentrations of between about 0% and 3% may result in increased remelt flow quality.

[0057] In certain example embodiments, a frit that includes V_2O_5 , BaO, and ZnO may further include one or more additives. In certain example embodiments, the additives may be between about 0.5% and 15% weight. According to certain example embodiments, the additives may be added to a base composition that includes between about 50% and 60% weight V_2O_5 , 27% and 33% weight BaO, and 9% and 12% weight ZnO.

[0058] Below, Tables 4A-4D show results of including additives to the base composition of V_2O_5 , BaO, and ZnO. Table 4D shows the melt quality on a scale of about 0 to 5 for each of the compositions. Figs. 10A-10C show graphs corresponding to the data shown in the below tables. A BaCO_3 factor of 1.2870 was used to form the BaO used for the following examples.

Table 4A									
Ex	Weights (gm)					Normalized Weights			
	V2O5	BaO	ZnO	Additive Type	Amount	V2O5	BaO	ZnO	Additive
1	52.5	22.5	10	TeO2	2	14.175	7.819	2.700	0.540
2	52.5	22.5	10	TeO2	4	13.650	7.529	2.600	1.040
3	52.5	22.5	10	Ta2O5	5	13.650	7.529	2.600	1.300

Table 4A									
Ex	Weights (gm)					Normalized Weights			
	V2O5	BaO	ZnO	Additive Type	Amount	V2O5	BaO	ZnO	Additive
4	52.5	22.5	10	Ta2O5	10	13.125	7.240	2.500	2.500
5	52.5	22.5	10	Ti2O3	5	13.650	7.529	2.600	1.300
6	52.5	22.5	10	Ti2O3	10	13.125	7.240	2.500	2.500
7	52.5	22.5	10	SrCl2	2	14.175	7.819	2.700	0.540
8	52.5	22.5	10	SrCl2	4	13.650	7.529	2.600	1.040
9	52.5	22.5	10	GeO2	1	14.175	7.819	2.700	0.270
10	52.5	22.5	10	GeO2	2	14.175	7.819	2.700	0.540
11	52.5	22.5	10	CuO	1	14.175	7.819	2.700	0.270
12	52.5	22.5	10	CuO	2	14.175	7.819	2.700	0.540
13	52.5	22.5	10	AgO	1.5	14.175	7.819	2.700	0.405
14	52.5	22.5	10	AgO	3	14.175	7.819	2.700	0.810
15	52.5	22.5	10	Nb2O5	3	14.175	7.819	2.700	0.810
16	52.5	22.5	10	Nb2O5	6	13.650	7.529	2.600	1.560
17	52.5	22.5	10	B2O3	.8	14.175	7.819	2.700	0.216
18	52.5	22.5	10	B2O3	1.6	14.175	7.819	2.700	0.432

Table 4B								
Ex	Normalized Weight Percentage				Moles of Batch Composition			
	V2O5	BaO	ZnO	Additive	V2O5	BaO	ZnO	Additive
1	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.013
2	55.00	30.34	10.48	4.19	0.302	0.154	0.129	0.026
3	54.43	30.02	10.37	5.18	0.299	0.152	0.127	0.012
4	51.75	28.54	9.86	9.86	0.285	0.145	0.121	0.022
5	54.43	30.02	10.37	5.18	0.299	0.152	0.127	0.011
6	51.75	28.54	9.86	9.86	0.285	0.145	0.121	0.022
7	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.013
8	55.00	30.34	10.48	4.19	0.302	0.154	0.129	0.026
9	56.78	31.32	10.82	1.08	0.312	0.159	0.133	0.010
10	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.020
11	56.78	31.32	10.82	1.08	0.312	0.159	0.133	0.014
12	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.027
13	56.48	31.15	10.76	1.61	0.311	0.158	0.132	0.013
14	55.58	30.66	10.59	3.18	0.306	0.155	0.130	0.026

Table 4B								
	Normalized Weight Percentage				Moles of Batch Composition			
Ex	V2O5	BaO	ZnO	Additive	V2O5	BaO	ZnO	Additive
15	55.58	30.66	10.59	3.18	0.306	0.155	0.130	0.012
16	53.87	29.71	10.26	6.16	0.296	0.151	0.126	0.023
17	56.91	31.39	10.84	0.87	0.313	0.159	0.133	0.012
18	56.42	31.12	10.75	1.72	0.310	0.158	0.132	0.025

Table 4C								
	Normalized Moles							
Ex	V2O5	BaO	ZnO	Additive	Tg(C)	(Tx1(C)	Tx2(C)	Tx1-Tg
1	50.57%	25.71%	21.53%	2.20%	315	400	525	85
2	49.48%	25.16%	21.07%	4.30%	315	420	530	105
3	50.68%	25.76%	21.58%	1.99%	320	450		130
4	49.69%	25.26%	21.16%	3.90%	320	450	530	130
5	50.71%	25.78%	21.59%	1.92%	305	390	495	85
6	49.75%	25.29%	21.18%	3.77%	295	390	470	95
7	50.56%	25.70%	21.53%	2.21%	315	405	530	90
8	49.47%	25.15%	21.06%	4.32%	315	400	530	85
9	50.83%	25.84%	21.64%	1.68%	315	395	530	80
10	49.99%	25.41%	21.28%	3.31%	315	400	530	85
11	50.56%	25.71%	21.53%	2.20%	315	385	525	70
12	49.47%	25.15%	21.06%	4.31%	320	395	545	75
13	50.61%	25.73%	21.55%	2.12%	305	390	525	85
14	49.55%	25.19%	21.10%	4.16%	300	380		80
15	50.68%	25.76%	21.58%	1.98%	315	425	550	110
16	49.69%	25.26%	21.16%	3.89%	325	440	465	115
17	50.66%	25.75%	21.57%	2.02%	315	410	540	95
18	49.66%	25.25%	21.14%	3.95%	320	405	545	85

Table 4D		
Example	Melt Quality @ 375C, 15min	Melt Quality at 350C, 15min
1	5.0	4.0
2	4.5	4.0
3	4.5	2.0
4	5.0	2.0
5	4.5	4.5

Table 4D		
Example	Melt Quality @ 375C, 15min	Melt Quality at 350C, 15min
6	5.0	5.0
7	5.5+	5.0
8	5.0	4.5
9	4.5	4.5
10	4.5	4.5
11	4.5	2.0
12	4.0	2.0
13	4.0	5.0
14	3.5	4.0
15	4.5	2.0
16	5.0	2.0
17	4.0	4.5
18	3.5	2.0

[0059] In certain example embodiments, the molar composition of an additive to a base composition higher than is shown in tables 4A-4D. Table 5A shows additives with an increased additive amount (on a % mole basis). The base composition used with the additive amount may be based on, for example, the base composition shown in Row 1 of Tables 4A-4D. The additives shown in Table 5, in the selected quantities displayed, may improve melt quality when compared to the above base composition. A melt type of Glassy indicates that a "button" of the compound melted onto a glass plate, forming a homogenous glassy structure. Sinter indicates that the compound (in a powder form) fused together, but remained in a powder form.

Table 5				
Example	Additive Type	Amount	Melt Type (350C for 20 minutes)	Adhesion to glass substrate.
1	CuCl	4.00%	Glassy	No Stick
2	SnCl ₂	3.99%	Glassy	No Stick
3	SnCl ₂	5.99%	Glassy, Slight Flow	Slight stick
4	SiO ₂	6.02%	More Glassy	No Stick
5	Al ₂ O ₃	6.00%	Glassy	No Stick
6	CeO ₂	4.00%	Sinter	No Stick
7	TeO ₂	3.99%	Glassy	Slight stick
8	TeO ₂	6.01%	Glassy	Slight stick
9	Ti ₂ O ₃	3.99%	Glassy, Slight Flow	No Stick
10	Ti ₂ O ₃	6.01%	Glassy, Slight Flow	No Stick

[0060] Accordingly, in certain example embodiments, additives of a relatively increased amount (e.g., versus those shown in Fig. 4) may be added to a base composition. In certain example embodiments, the additives may include, for example, CuCl, SnCl₂, SiO₂, Al₂O₃, and TeO₂. It will be appreciated that toxic nature of thallium oxide (Tl₂O₃) may preclude its use in certain instances.

[0061] In certain example embodiments, two or more additives may be included in a base compound. Table 6 shows the results of adding two additives to an exemplary base composition. Table 6 includes example melts at 375 and 350. Additionally, 13mm buttons of the exemplary compounds were tested on a glass plate. The structural strength of the resulting exemplary compound are also shown in the far right column.

Table 6								
Ex	Add 1	Add 2	Amount 1 (Mole %)	Amount 2 (Mole %)	Melt Quality (375C 15-20 Min)	Melt Quality (350C 15-20 Min)	13mm Button 350C 20 Min	Strength
1	TeO ₂	Al ₂ O ₃	3.01	3.01	4.5	5.5	glassy	Fractures
2	TeO ₂	Al ₂ O ₃	2.99	5.01	5	4	glassy	Fractures
3	TeO ₂	Al ₂ O ₃	4.02	3.01	6	5.5	glassy	Fractures
4	TeO ₂	Al ₂ O ₃	3.99	5.00	5	4.5	glassy	Fractures
5	TeO ₂	Al ₂ O ₃	5.01	2.99	4.5	4.5	glassy	Fractures
6	TeO ₂	Al ₂ O ₃	5.00	5.00	5	4.5	glassy	Fractures
7	TeO ₂	SiO ₂	3.01	3.00	5	5.5	glassy	Fractures
8	TeO ₂	SiO ₂	2.99	5.02	5	4.5	glassy	Fractures
9	TeO ₂	SiO ₂	4.00	2.99	5	4	glassy	Fractures
10	TeO ₂	SiO ₂	3.99	4.99	5	4.5	Less glassy	Fractures
11	TeO ₂	SiO ₂	5.00	2.99	4.5	4.5	Less glassy	Hard
12	TeO ₂	SiO ₂	5.00	4.99	4.5	4.5	Less glassy	Hard
13	SnCl ₂	Al ₂ O ₃	3.01	3.01	5	6	more glassy	Hard
14	SnCl ₂	Al ₂ O ₃	3.00	5.01	5	5.5	glassy	Hard
15	SnCl ₂	Al ₂ O ₃	4.01	3.01	4.5	6	glassy	Hard
16	SnCl ₂	Al ₂ O ₃	4.00	4.99	5.5	6	glassy	Hard
17	SnCl ₂	Al ₂ O ₃	5.00	2.99	5.5	5.5	glassy	Fractures
18	SnCl ₂	Al ₂ O ₃	5.00	5.00	5.5	5.5	more	Hard

Table 6								
Ex	Add 1	Add 2	Amount 1 (Mole %)	Amount 2 (Mole %)	Melt Quality (375C 15- 20 Min)	Melt Quality (350C 15-20 Min)	13mm Button 350C 20 Min	Strength
							glassy	
19	SnCl ₂	SiO ₂	3.00	3.00	4.5	4.5	glassy	Hard
20	SnCl ₂	SiO ₂	3.00	4.99	5	6	glassy	Hard
21	SnCl ₂	SiO ₂	4.00	2.99	6	6	glassy	Fractures
22	SnCl ₂	SiO ₂	4.01	4.99	5.5	5.5	glassy	Fractures
23	SnCl ₂	SiO ₂	5.00	2.99	5	5.5	glassy	Hard
24	SnCl ₂	SiO ₂	5.00	4.99	5.5	5.5	glassy	Fractures
25	Al ₂ O ₃	SiO ₂	3.01	3.00	4.5	4	less glassy	Hard
26	Al ₂ O ₃	SiO ₂	2.99	4.99	5	5.5	less glassy	Hard
27	Al ₂ O ₃	SiO ₂	4.00	2.99	4.5	4.5	less glassy	Hard
28	Al ₂ O ₃	SiO ₂	4.00	4.99	5	4.5	less glassy	Hard
29	Al ₂ O ₃	SiO ₂	5.01	2.99	5	4.5	less glassy	Hard
30	Al ₂ O ₃	SiO ₂	5.01	4.99	4	2	less glassy	Hard

[0062] Accordingly, certain example may include two additives similar to those found in examples 3, 16, and 21 as shown in Table 6 (e.g., TeO₂ with SiO₂, SnCl₂ with Al₂O₃, and SnCl₂ with SiO₂). In certain example embodiments, the addition of two or more additives may have beneficial results on an exemplary base composition. For example the addition of SiO₂ to another additive may increase the strength of the overall frit. Alternatively, or in addition, TeO₂ combined with other additives may increase the melt flow and glass wetting qualities of the frit when compared to a base frit.

[0063] In certain example embodiments, the combination of SnCl₂ with SiO₂ and/or Al₂O₃ may result in an increase in structural strength for the resulting frit material.

[0064] In certain example embodiments, one or more additives may be added to a base composition where the amount is between 1% and 10% by weight or between about 1% and 6% normalized moles for a batch. In certain example embodiments, additives may be added in a smaller amount, for example between about 0.1% and 1% by weight. In certain example embodiments a batch for a base composition (in grams) may include V₂O₅ at 52.5, BaO at

22.5, ZnO at 10. In certain example embodiments, additives added to the above base composition may include: 1) TeO₂ at 3.85gm and Al₂O₃ at 1.84gm; 2) SnCl₂ at 4.65gm and Al₂O₃ at 3.12gm; 3) SnCl₂ at 4.55gm and SiO₂ at 1.08gm. Correspondingly, the additives may then have a normalized weight percentage of: 1) TeO₂ at 1.00 and Al₂O₃ at .48; 2) SnCl₂ at 1.21 and Al₂O₃ at .81; 3) SnCl₂ at 1.18 and SiO₂ at .28. These examples may correspond to examples 3, 16, and 21 in the above table 6.

[0065] Figs 11A-11C show graphs illustrating absorption in the visible and infrared wavelengths for vanadium based frits according to certain example embodiments. As shown in the graphs, example vanadium based frits may have absorption of at least 90% across a substantial breadth of the visible and IR spectrum. In certain example embodiments the absorption may be about 95%. As discussed in co-pending application Serial No. 12/929,874, filed on February 22, 2011, entitled "IMPROVED FRIT MATERIALS AND/OR METHOD OF MAKING VACUUM INSULATING GLASS UNITS INCLUDING THE SAME" frit materials with high visible/IR absorption may be advantageous.

[0066] Fig. 11A shows the absorption properties of a vanadium based frit with TeO₂ and Al₂O₃ used as additives (e.g., Ex. 3 of Table 6). Fig. 11B shows the absorption properties of a vanadium based frit with SnCl₂ and Al₂O₃ used as additives (e.g., Ex. 16 of Table 6). Fig. 11C shows the absorption properties of a vanadium based frit with SnCl₂ and SiO₂ used as additives (e.g., Ex. 21 of Table 6).

[0067] In certain example embodiments, the application of IR energy to a frit material may be based on a heating profile where the IR energy applied to the frit varies over time. Exemplary heating profiles may be found in co-pending application Serial No. 12/929,874.

[0068] In certain example embodiments, a base composition may be augmented by 3 or 4 additives. For example, a batch for a base composition (in grams) may include V₂O₅ at 52.5, BaO at 22.5, ZnO at 10. Accordingly, three and/or more additives from among TeO₂, SnCl₂, Al₂O₃, and SiO₂ may be selected to augment the base composition. The ranges (in grams) for the additives may vary between 0 to 7.5 grams per additive. Thus, on a normalized molar percentage the above additives may be included at between 0% and 6%. Thus, the normalized molar percentage of a base composition may be V₂O₅ at between about 43% and 50%, BaO between about 22% and 26%, ZnO between about 18% and 22%. In certain example embodiments, additives (on a normalized molar basis) of TeO₂ at around 2%, SnCl₂ around 2%, Al₂O₃ around 2%, and SiO₂ around 4% may be added to the base composition.

[0069] The techniques, compositions, etc disclosed herein may be used other methods and/or systems for forming a VIG unit. For example, a vanadium based frit may be used to form an edge seal of a VIG unit. Systems, apparatuses, and/or methods used for creating a VIG unit may be described in co-pending application 12/929,876, filed on February 22, 2011, entitled "LOCALIZED HEATING TECHNIQUES INCORPORATING TUNABLE INFRARED ELEMENT(S) FOR VACUUM INSULATING GLASS UNITS, AND/OR APPARATUSES FOR THE SAME".

[0070] Certain example embodiments may include three or more additives to a base composition that includes vanadium pentoxide; barium carbonate that converts in whole or in part to barium oxide; and zinc oxide. The above three "base" frit elements may be included at 35-55% molar for V_2O_5 , 15-35% for BaO, and 15-25% molar for ZnO or, more preferably, 40-50% molar for V_2O_5 , 20-30% for BaO, and 18-22% molar for ZnO.

[0071] Along with an example base frit composition, one or more additives may be added. The additives may include, for example:

1. 1) $SnCl_2$ at between 1-10% molar, which may help reduce glass softening temperatures and/or reduce crystallization in certain example embodiments;
2. 2) $CuCl_2$ at between 1-5% molar, which may help reduce glass softening temperature in certain example embodiments;
3. 3) MoO_3 at between 1-6% molar, which may help reduce glass softening temperatures in certain example embodiments;
4. 4) TeO_2 at between 1-10% molar, which may help increase glass flow ability and/or wetting to a substrate glass in certain example embodiments;
5. 5) Ta_2O_5 at between 0.5-5% molar, which may help increase softening temperature and/or increase crystallization temperature in certain example embodiments;
6. 6) Nb_2O_5 at between 0.5-6% molar, which may help increase softening temperature and/or increase crystallization temperature in certain example embodiments;
7. 7) Al_2O_3 at between 0.5-5% molar, which may help increase softening, weathering ability, chemical durability, and/or mechanical strength in certain example embodiments;
8. 8) SiO_2 at between 0.5-5% molar, which may help increase softening, weathering ability, chemical durability, and/or mechanical strength in certain example embodiments; and
9. 9) $CsCO_3$ at between 0.5-4% molar, which may help increase melt flow and/or reduce wetting ability in certain example embodiments.

[0072] In certain example embodiments, four or more additives, more preferably six or more additives may be added to the above base composition. It will be appreciated that as the number of the additives increases, the interactions between the various additives may produce different results based on the relative weighting of one or more additives (or the base composition). It also will be appreciated that the increased number of additives may create synergistic effects (e.g., in terms of glass softening temperature, flowability, and/or other adjustments) that otherwise might not be observable.

[0073] In certain example embodiments, one or more additives may be introduced through the frit creation process rather than being expressly introduced. For example, additive ingredients may be introduced into a frit material as a result of firing the frit material in a crucible. For instance, some ingredients may be "leached" from the crucible and into the frit material. In

certain example embodiments, Al_2O_3 and SiO_2 may be leached by this process.

[0074] Tables 7-10 show example frit compositions according to certain example embodiments. The different tables each include one or more additives that are varied while the other ingredients are kept substantially the same between the example compounds of the give table.

[0075] In tables 7A-7C, molybdenum oxide is varied between the example compounds; in tables 8A-8C tellurium oxide is varied between the example compounds; in tables 9A-9C cesium carbonate is varied between the example compounds; and in tables 10A-10D tantalum oxide and niobium oxide are varied between the example compounds.

[0076] Tables 7A, 8A, 9A, and 10A show the example frit compositions by normalized weight percentage. Tables 7B, 8B, 9B, and 10B show the example frit compositions by normalized mole percent. The values given in tables 7-10 A and B are normalized to approximately 100% for shown compositions. For example, V_2O_5 from example 1 in table 7A is 54.88% by weight of the frit composition for the frit composition. Similarly, V_2O_5 for the same example frit composition is shown as 49.76% mole of the resulting frit composition (e.g., from Table 7B). Thus, the normalized weight and mole percentages may add up to about 100% for the example frit compositions shown in the various tables herein. Tables 7C, 8C, 9C, 10C, and 10D show exemplary results for the example frit compositions. As can be seen in the results of the above noted tables (e.g., tables 7-10), performance of one or more of the above examples may be improved over a base frit material, or a frit material with only one additive as discussed above. For example, example frit materials 9 and 11 shown in Table 8 show good flow at 375 degrees C (5 and 6.5, respectively).

Table 7A - MoO_3 Examples									
	Normalized Weight Percentage								
Example	V_2O_5	BaO	ZnO	MoO_3	TeO_2	Ta_2O_5	Al_2O_3	SiO_2	Nb_2O_5
1	54.88	26.61	10.45	0.87	4.15	1.38	0.00	0.00	1.65
2	54.64	26.49	10.41	1.31	4.13	1.37	0.00	0.00	1.64
3	54.39	26.38	10.36	1.75	4.11	1.37	0.00	0.00	1.64
4	54.15	26.26	10.31	2.19	4.10	1.36	0.00	0.00	1.63
5	53.91	26.14	10.27	2.63	4.08	1.36	0.00	0.00	1.62
6	53.67	26.02	10.22	3.07	4.06	1.35	0.00	0.00	1.62
Table 7B - MoO_3 Examples									
	Normalized Moles of Batch Composition								
Ex.	V_2O_5	BaO	ZnO	MoO_3	TeO_2	Ta_2O_5	Al_2O_3	SiO_2	Nb_2O_5
1	49.76%	22.24%	21.18%	0.99%	4.29%	0.51%	0.00%	0.00%	1.02%
2	49.50%	22.12%	21.08%	1.50%	4.27%	0.51%	0.00%	0.00%	1.02%

Table 7B - MoO ₃ Examples									
	Normalized Moles of Batch Composition								
Ex.	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
3	49.25%	22.01%	20.97%	2.00%	4.24%	0.51%	0.00%	0.00%	1.01%
4	49.00%	21.90%	20.86%	2.50%	4.22%	0.51%	0.00%	0.00%	1.01%
5	48.75%	21.79%	20.75%	3.00%	4.20%	0.50%	0.00%	0.00%	1.00%
6	48.50%	21.67%	20.65%	3.50%	4.18%	0.50%	0.00%	0.00%	1.00%

Table 7C - MoO ₃ Examples						
	Test Results					
Ex.	Slides 350C 15 min	Slides 375C 15 min	375C 13mm button 20 min	Results	400C 13mm button 20 min	Results
1	5.0	5.5	12.39	glass	13.76	light haze
2	3.0	4.5	12.80	glass	14.06	light haze
3	4.0	5.5	12.51	glass	14.14	light haze
4	4.5	5.0	13.08	glass	14.22	light haze
5	5.5	5.0	12.93	glass	14.26	light haze
6	5.5	5.5	12.88	glass	14.50	light haze

Table 8A - TeO ₂ Examples									
	Normalized Weight Percentage								
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
7	54.84	26.59	10.45	2.67	2.42	1.38	0.00	0.00	1.65
8	54.56	26.46	10.39	2.66	2.91	1.37	0.00	0.00	1.64
9	54.29	26.33	10.34	2.65	3.39	1.37	0.00	0.00	1.63
10	54.02	26.19	10.29	2.63	3.88	1.36	0.00	0.00	1.63
11	53.74	26.06	10.24	2.62	4.37	1.35	0.00	0.00	1.62
12	53.47	25.93	10.18	2.61	4.86	1.34	0.00	0.00	1.61
13	53.20	25.80	10.13	2.59	5.34	1.34	0.00	0.00	1.60
14	52.92	25.66	10.08	2.58	5.83	1.33	0.00	0.00	1.59

Table 8B - TeO ₂ Examples									
	Normalized Moles of Batch Composition								
Ex.	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
7	49.61%	22.17%	21.12%	3.06%	2.50%	0.51%	0.00%	0.00%	1.02%
8	49.36%	22.06%	21.01%	3.04%	3.00%	0.51%	0.00%	0.00%	1.02%
9	49.11%	21.95%	20.91%	3.03%	3.50%	0.51%	0.00%	0.00%	1.01%
10	48.85%	21.83%	20.80%	3.01%	4.00%	0.51%	0.00%	0.00%	1.01%
11	48.59%	21.72%	20.69%	2.99%	4.50%	0.50%	0.00%	0.00%	1.00%
12	48.34%	21.60%	20.58%	2.98%	5.00%	0.50%	0.00%	0.00%	1.00%
13	48.09%	21.49%	20.47%	2.96%	5.50%	0.50%	0.00%	0.00%	0.99%
14	47.83%	21.38%	20.36%	2.95%	6.00%	0.49%	0.00%	0.00%	0.98%

Table 8C - TeO ₂ Examples						
	Test Results					
Ex.	Slides 350C 15 min	Slides 375C 15 min	375C 13mm button 20 min	Results	400C 13mm button 20 min	Results
7	5.5	6.0	12.89	glass	14.37	haze
8	3.0	6.5	13.08	glass	14.63	light haze
9	3.0	5.0	13.38	glass	14.93	light haze
10	6.5	5.0	13.17	glass	14.66	light haze
11	4.5	6.5	13.04	glass	14.72	glass
12	6.0	6.5	12.72	glass	14.53	light haze
13	5.5	5.0	12.94	glass	14.59	light haze
14	5.5	6.0	13.24	glass	14.92	light haze

Table 9A - CsCO ₃ Examples										
	Normalized Weight Percentage									
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅	CsCO ₃
15	52.95	25.68	10.09	2.58	4.31	1.33	0.00	0.00	1.59	1.47
16	52.69	25.55	10.04	2.57	4.29	1.32	0.00	0.00	1.59	1.97
17	52.43	25.43	9.99	2.56	4.26	1.32	0.00	0.00	1.58	2.44
18	52.17	25.30	9.94	2.54	4.24	1.31	0.00	0.00	1.57	2.92
19	51.91	25.17	9.89	2.53	4.22	1.31	0.00	0.00	1.56	3.41

Table 9A - CsCO ₃ Examples										
	Normalized Weight Percentage									
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅	CsCO ₃
20	51.65	25.05	9.84	2.52	4.20	1.30	0.00	0.00	1.55	3.89

Table 9B - CsCO ₃ Examples										
	Normalized Moles of Batch Composition (%)									
Ex.	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅	CsCO ₃
15	48.23	21.55	20.53	2.97	4.47	0.50	0.00	0.00	0.99	0.75
16	48.11	21.50	20.48	2.96	4.46	0.50	0.00	0.00	0.99	1.00
17	47.99	21.45	20.43	2.96	4.45	0.50	0.00	0.00	0.99	1.25
18	47.87	21.39	20.38	2.95	4.44	0.50	0.00	0.00	0.99	1.50
19	47.74	21.34	20.33	2.94	4.43	0.49	0.00	0.00	0.98	1.75
20	47.62	21.28	20.27	2.93	4.41	0.49	0.00	0.00	0.98	2.00

Table 9C - CsCO ₃ Examples						
	Test Results					
Ex.	Slide 350C - 15 min	Slide 375C - 15 min	13mm button - 375C 20 min	Results	13mm button - 400C 20 min	Results
15	5.5	6.5	13.40	glass	14.88	haze
16	5.5	5.5	13.05	glass	15.40	glass
17	4.0	6.5	13.60	glass	15.17	light haze
18	4.5	6.5	13.33	glass	14.81	haze
19	6.0	4.5	13.28	glass	14.59	haze
20	4.5	7.0	13.97	glass	16.36	light haze

Table 10A - Ta ₂ O ₅ and Nb ₂ O ₅ Examples										
	Normalized Weight Percentage									
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅	
21	53.87	26.12	10.26	2.63	3.37	1.34	0.00	0.00	2.41	
22	53.42	25.90	10.18	2.60	3.34	1.34	0.00	0.00	3.22	
23	52.98	25.69	10.09	2.58	3.31	1.33	0.00	0.00	4.01	
24	53.59	25.99	10.21	2.61	3.35	2.65	0.00	0.00	1.60	
25	53.15	25.77	10.12	2.59	3.32	2.65	0.00	0.00	2.39	
26	52.71	25.56	10.04	2.57	3.29	2.65	0.00	0.00	3.18	
27	52.28	25.35	9.96	2.55	3.27	2.63	0.00	0.00	3.97	

Table 10A - Ta₂O₅ and Nb₂O₅ Examples

	Normalized Weight Percentage								
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
28	52.86	25.63	10.07	2.58	3.30	3.97	0.00	0.00	1.59
29	52.43	25.43	9.99	2.56	3.28	3.94	0.00	0.00	2.38
30	52.00	25.21	9.90	2.54	3.25	3.94	0.00	0.00	3.16
31	51.57	25.01	9.82	2.51	3.22	3.93	0.00	0.00	3.93

Table 10B - Ta₂O₅ and Nb₂O₅ Examples

	Normalized Moles of Batch Composition								
Ex.	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
21	48.87%	21.84%	20.81%	3.01%	3.48%	0.50%	0.00%	0.00%	1.50%
22	48.61%	21.73%	20.70%	3.00%	3.46%	0.50%	0.00%	0.00%	2.00%
23	48.37%	21.62%	20.59%	2.98%	3.44%	0.50%	0.00%	0.00%	2.50%
24	48.87%	21.84%	20.81%	3.01%	3.48%	1.00%	0.00%	0.00%	1.00%
25	48.62%	21.73%	20.70%	3.00%	3.46%	1.00%	0.00%	0.00%	1.50%
26	48.37%	21.62%	20.59%	2.98%	3.44%	1.00%	0.00%	0.00%	2.00%
27	48.12%	21.51%	20.49%	2.96%	3.43%	1.00%	0.00%	0.00%	2.50%
28	48.62%	21.73%	20.70%	3.00%	3.46%	1.50%	0.00%	0.00%	1.00%
29	48.37%	21.62%	20.59%	2.98%	3.44%	1.50%	0.00%	0.00%	1.50%
30	48.12%	21.50%	20.49%	2.96%	3.43%	1.50%	0.00%	0.00%	2.00%
31	47.87%	21.39%	20.38%	2.95%	3.41%	1.50%	0.00%	0.00%	2.50%

Table 10C - Ta₂O₅ and Nb₂O₅ Examples

	Test Results					
Ex.	Slide 350C - 15 min	Slide 375C - 15 min	13mm button - 375C 20 min	Results	13mm button - 400C 20 min	Results
21	4.5	6.5	13.24	glass	15.21	glass
22	4.0	6.5	12.42	glass	14.50	glass
23	2.5	6.0	12.24	glass	14.55	glass
24	4.5	6.5	12.56	glass	14.47	glass
25	3.0	5.0	12.35	glass	14.16	glass
26	4.5	6.0	12.19	glass	14.88	glass
27	4.5	5.0	12.30	glass	14.48	glass
28	3.0	5.5	12.16	glass	14.34	glass
29	3.0	5.5	11.62	glass	14.07	glass
30	3.0	5.5	11.79	glass	14.20	glass

Table 10C - Ta ₂ O ₅ and Nb ₂ O ₅ Examples						
Test Results						
Ex.	Slide 350C - 15 min	Slide 375C - 15 min	13mm button - 375C 20 min	Results	13mm button - 400C 20 min	Results
31	3.0	6.0	11.77	glass	13.96	glass

Table 10D - Ta ₂ O ₅ and Nb ₂ O ₅ Examples		
Test Results Continued		
Example	13mm button - 425C 20 min	Result
21	16.07	Haze
22	15.86	Haze
23	16.08	light haze
24	14.79	Haze
25	15.99	Glass
26	16.40	light haze
27	16.15	light haze
28	15.33	Haze
29	15.55	Glass
30	15.71	light haze
31	14.57	Haze

[0077] In certain example embodiments, the use of Ta₂O₅ and/or Nb₂O₅ may help reduce the crystallization of the frit material. As the percentage of contribution by such additives increases, the softening temperature (e.g., a temperature at which the frit material may flow) may also increase. In certain example embodiments, such properties may be desirable for a tip off seal in a VIG unit (e.g., sealing the vacuum hole in a VIG unit).

[0078] Frit materials used for tipping off a vacuum hole may have different desirable properties than frit materials for a perimeter seal for a VIG unit. For example, a frit material used in a tip off seal may be completely or substantially exposed to IR and therefore may reach a higher temperature than that of a perimeter seal. Conversely, the perimeter seal may have the glass absorb some percentage of the SWIR directed at the frit of a perimeter seal (e.g., 10%-30% of the SWIR). Thus, an exemplary frit material (e.g., example 21) may be used for a perimeter seal while example 26 may be used for tip off seal.

[0079] As shown in Table 10D, the example frit compositions may provide increased resistance, or greater tolerance, to crystallization. The example compositions shown in Tables 7-10 were done in an alumina crucible. With such a crucible, a certain amount of Al₂O₃ and SiO₂ may be "leached" from the crucible during the frit preparation process. Thus, while Al₂O₃

and SiO₂ may not be shown in the above tables 7 - 10, these additives (or others depending on the crucible type) may yet be present in the frit composition due to the leaching process from the crucible. The leaching of Al₂O₃ and SiO₂ may be a result of melting or firing the frit compositions at certain temperatures (e.g., 800C degrees C, 1000 degrees C, etc). Different firing temperatures and/or different lengths of time of firing may affect the amount of material leached from the crucible. The variation of Al₂O₃ and SiO₂ may change the frit performance for sealing at 375 degrees C and 400 degrees C.

[0080] In certain example embodiments, Al₂O₃ may be included in a frit material at between 0% and 2% normalized moles by composition, or at a normalized weight percentage between 0% and 1.2%, or more preferably about 0.8%. SiO₂ may be included at between 1 and 5% normalized mole by composition and/or between about 0.5 and 2% by weight, and more preferably about 1.2% by normalized weight. The inventor has determined that in certain instances, having SiO₂ or Al₂O₃ in amount greater than about 2-5%, resulted in undesirable flow qualities of the frit composition. In particular, when bonding to an example glass substrate, in certain instances, higher percentages of SiO₂ or Al₂O₃ (e.g., in excess of 2 or 4%) resulted in concrete like qualities for the final frit composition.

[0081] Table 11 shows example results in a platinum crucible. Such a crucible may reduce or even prevent the leaching of excess additives during the firing process of the frit material.

Table 11									
Platinum Crucible - Normalized Moles (%)									
V ₂ O ₅	BaO	ZnO	CuCl	SnCl ₂	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
44.56	21.96%	18.21%	1.42%	4.66%	3.88%	0.47%	1.19%	2.73%	0.93%
44.25	21.81%	18.09%	1.41%	4.62%	3.85%	0.46%	1.20%	3.38%	0.92%
43.95	21.66%	17.96%	1.40%	4.59%	3.83%	0.46%	1.19%	4.05%	0.91%
44.38	21.87%	18.14%	1.41%	4.64%	3.86%	0.46%	1.60%	2.71%	0.92%
44.08	21.72%	18.02%	1.40%	4.61%	3.84%	0.46%	1.59%	3.36%	0.92%
43.78	21.57%	17.89%	1.39%	4.57%	3.81%	0.46%	1.58%	4.03%	0.91%
44.20	21.78%	18.07%	1.41%	4.62%	3.85%	0.46%	1.99%	2.70%	0.92%
43.89	21.63%	17.94%	1.40%	4.59%	3.82%	0.46%	1.99%	3.38%	0.91%
43.60	21.48%	17.82%	1.39%	4.56%	3.80%	0.46%	1.98%	4.01%	0.91%

[0082] Figs. 12A-12C are graphs summarizing flow characteristics of example frit materials according to certain example embodiments.

[0083] Fig. 12A shows that, at 375 degrees C, increasing Ta₂O₅ percentage may cause an increase in the initial softening temperature and resulting reduction in the flow (e.g., the diameter of the 13mm button) for the example frit material. In certain example embodiments,

increasing Nb₂O₅ percentage may provide less of a reduction in flow. As noted above, a frit (e.g., Ex. 21) with this composition may be used for a perimeter seal of a VIG unit.

[0084] Fig. 12B shows that, at 400 degrees C, Ex. 21 has improved flow characteristics. For example, with 1.0% Ta₂O₅, the frit flows well.

[0085] Fig. 12C shows, at 425 degrees C, Ex. 21 continuing to flow at higher temperatures, although, as shown above in Table 10D, the frit composition may become crystallized at such a temperature. However, Ex. 26 may continue to have good flow and has only a slight crystallization. Accordingly, Ex. 26 may continue to flow at higher temperatures.

[0086] As discussed herein, a binding agent may be applied to (or combined with) a frit material (e.g., a frit material based on the materials described herein). The inventor of the instant application has recognized that the reduced melting temperatures of certain example frit materials may provide for melting points that are less than the burnout temperature for certain types of binding agents that may be used in conjunction with the frit material. It is noted the following tests were performed using Ex. 26 as the frit composition, although the other frit compositions disclosed herein are expected to have similar performance characteristics, unless otherwise specifically noted below. It also is noted that a CTE matching material may be added in certain instances. One example is GM31682 available from Schott, which was added at 6.9 wt. % in conducting the following tests.

[0087] Fig. 13 is a graph showing a thermogravimetric analysis (TGA) of certain example binding agents. The TGA analysis was performed in nitrogen and, as can be seen, the example "QPAC" binding agents (discussed in more detail below) has a burn range that is approximately 100°C lower than other binders in the cellulose family of compounds.

[0088] In certain example embodiments, the following example binder materials may be used in conjunction with certain frit materials.

Example 1: A methyl cellulose polymer binder. Example 1 included 0.75 wt% methyl cellulose (400 cps molecular weight polymer) in DI water. TGA analysis of this material indicated a burn out of the binder at around 320-380°C.

Example 2: A polyethylene carbonate binder, for example, [CH₂CH₂OCO₂]_n or C₃H₄O₃. One example of such a binder is available under the material trade name QPAC® 25 from Empower Materials Inc. It will be appreciated that other carbonate inclusive binder materials may be used in certain example embodiments.

Example 3: A polypropylene carbonate binder, for example, [CH₃CHCH₂OCO₂]_n or C₄H₆O₃. One example of such a binder is available under the material trade name QPAC® 40 from Empower Materials Inc. As noted above, in Fig. 13, TGA analysis of these examples 2 and 3 indicated that the burnout of the binder material may be around 250-275°C.

[0089] The examples shown in Figs. 14B, 15B, 16B, and 17-19 included a 5:1 (gram) ratio frit-to-binder solution. These were dried into layers on microscope slides, and the slides were placed on a 71/38 coated glass. It will be appreciated that this ratio of frit to binder solution is given by way of example and that other ratios may be used. For example, the ratio may be between ratios of 4:1 and 6:1.

[0090] Figs. 14A, 15A, and 16 are temperature vs. time graphs that each show various temperatures at varying times of an example frit material, a duct temperature (e.g., where the IR energy is applied), and two glass substrates that are respectively coated (e.g., with a low-E coating) and non-coated (e.g., "clear").

[0091] Figs. 14A and 14B respectively show a heating profile graph and example frit materials melted according to the heating profile of Fig. 14A. The heating profile reflected in the graph of Fig. 14A included an approximately 1 minute hold time 1402 at around 270-275°C. Subsequent to this hold time, the temperature was increased to a frit melting temperature. The ramp time for this increase may be between 1.8 and 2.3 minutes or, more preferably, about 2.1 minutes.

[0092] Fig. 14B shows example frit materials that include different binding agents. The melted frit material 1410 included the above noted example 2 binding agent, whereas the melted frit material 1412 included the above noted example 1 binding agent. Frit 1410 had properties that included being fused and porous, not glassy, and/or delaminating from the substrate. Frit 1412 had properties that included being rough and poorly fused, not glassy, and and/or delaminating from the substrate.

[0093] Figs. 15A and 15B respectively show another heating profile graph and the example melted frit materials according to the heating profile. The heating profile reflected in the graph of Fig. 15A included an approximately 1 minute hold time 1502 at around 265-275°C. Subsequent to this hold time, the temperature was increased to a frit melting temperature. The ramp time for this increase may be between 4.3 and 5.7 minutes, more preferably between about 4.5 and 5.2, and even more preferably between about 4.7 and 5 minutes. It will be appreciated that such an increased ramp time (e.g., over the example shown in Fig. 14A) may be achieved by reducing the IR voltage related to the energy applied to the frit material. For example, the voltage may be reduced from about 80% to around 50%. It will be appreciated that such percentages may be adjusted depending on the energy output of the heating elements involved in the melting process.

[0094] Fig. 15B shows example frit materials that include different binding agents. The melted frit material 1510 included the above noted example 2 binding agent, whereas the melted frit material 1512 included the above noted example 1 binding agent. Frit 1410 had properties that included having a glossy appearance (e.g., an increase over the frits shown in Fig. 14B) while being rough with no flowed look and delaminating from the substrate. Frit 1512 had properties that included being rough and cracking (e.g., indicating the binding agent is still

present) and/or delaminating from the substrate. Such results may indicate that the binding agent is still present in the example frit material.

[0095] Fig. 16 shows yet another heating profile graph that may be used for applying energy to a frit material disposed onto a substrate. The heating profile reflected in the graph of Fig. 16A included an approximately 5 minute hold time 1602 at around 270-275°C. According to certain example embodiments, the hold time may be between about 235-290°C. Subsequent to this hold time, the temperature was increased to a frit melting temperature (e.g., 380-400°C or less than 400°C). The ramp time for this increase may be between 2 and 3 minutes, more preferably between about 2.2 and 2.8, and even more preferably about 2.4 minutes.

[0096] Figs. 17-20 shows example frit materials that include different binding agents melted as a result of applying exemplary heating profiles. Frit materials 1702, 1802, 1902, and 2002 are based on a frit material that includes the above noted example 2 binding agent. Frit materials 1704, 1804, 1904, and 2004 are based on a frit material that includes the above noted example 3 binding agent. Frit materials 1706, 1806, 1906 and 2006 are based on a frit material that includes the above noted example 1 binding agent.

[0097] In Fig. 17, the heating profile used included about a 5 minute hold time at around 275°C with a subsequent 5 minute ramp time to seal (e.g., to the melting temp of the frit material) was used. Frit materials 1702 and 1704 both had good flow and solid bonds to the respective substrates. However, frit material 1706 was rough and not glassy and delaminated from the substrate.

[0098] In Fig. 18, the heating profile used included about a 5 minute hold time at around 275°C with a subsequent 5 minute ramp time to seal (e.g., to the melting temp of the frit material) was used. Frit materials 1802 and 1804 both had good flow, but delaminated some from the substrate. Frit material 1806 completely delaminated from the substrate. Also, while the edges of the frit may have melted, the roughness of the frit still was present in the melted version.

[0099] In Fig. 19, the heating profile used included about a 5 minute hold time at around 275°C. A subsequent 2.3 minute ramp time to seal (e.g., to the melting temp of the frit material) was used. Frit materials 1902 and 1904 both had a good melt along with a good bond to the respective substrates. Frit material 1906 had some melting along the edges, but still lifted off the substrate. Frit materials 1 and 2 may then, along with the heating profile used in Fig. 19, be applied to a glass substrate and may be used to form a VIG unit.

[0100] In Fig. 20, the heating profile used included about a 10 minute hold time at around 275°C. A subsequent 2.3 minute ramp time to seal (e.g., to the melting temp of the frit material) was used. Frit materials 2002 and 2004 both had good melts and adhesion to the substrate. Frit material 2006 had a relatively poor melt and completely lifted off the substrate slide.

[0101] While certain example embodiments may use a holding temperature of around 275°C, other temperatures between about 235°C to 325°C, or more preferably between about 260°C and 285°C may be used. In certain example embodiments, a holding temperature may be less than about 300°C. In one example, a holding temperature of about 267°C was used. In certain example embodiments, the temperature may vary, or slowly increase during this time period (e.g., to hold under a certain temperature or within a certain range for a period of time).

[0102] Furthermore, hold times using these and other hold temperatures may be used. For example, a hold time may be between 1 and 30 minutes, more preferably between about 2 and 15 minutes, and even more preferably between about 5 and 10 minutes may be used. In certain example embodiments, the hold time may be less than 5 or 10 minutes.

[0103] The named inventor of the instant application determined that in certain instances a burnout time that is too short (e.g., less than a minute) may lead to leftover carbon residue. Such a characteristic may be undesirable under certain conditions. The named inventor also determined that in certain conditions, an increased hold time (e.g., in excess of 30 minutes) may result in the frit material having a reduced bond strength to an underlying substrate. Accordingly, it will be appreciated that a length of time used to "burn out" a binder solution may influence a quality of the frit (e.g., the frit to substrate seal). For example, certain example timeframes as disclosed herein may be used to reduce (or in some cases eliminate) the negative effects of the above undesirable characteristics.

[0104] Also, in certain example embodiments, the ramp time to the sealing temperature may vary between about 1 minute and 10 minutes, more preferably between about 2 and 5 minutes. Certain example embodiments may employ a ramp time of less than 5 minutes, or more preferably less than 3 minutes. Accordingly, certain example embodiments may use relatively reduced ramp times (e.g., times that are less than the holding temperature).

[0105] Fig. 21 is a flowchart illustrating a process for melting a frit material onto a substrate according to certain example embodiments. In step 2102, a frit that includes a binder is applied to a substrate. In step 2104, the substrate is then disposed in an environment that raises the temperature of the frit material applied to the substrate to a first level. Such a temperature may be between about 200°C and 350°C, or more preferably between about 250°C and 300°C, or even more preferably about 275°C.

[0106] In step 2106 the temperature of the frit material is held at a relatively stable level for a period of time, e.g., between about 1 and 10 minutes, or about 5 minutes. The temperature of the frit is then raised to the melting temperature of the frit in step 2108. This may happen over a period of less than about 5 minutes, more preferably less than about 3 minutes, or even more preferably about 2.3 minutes. In step 2110, the substrate, frit, and other entities are then cooled. As a result, the frit material may be bonded to the substrate, and the binder material that was originally included with the frit may be substantially or completely burned off.

[0107] It will be appreciated by those skilled in the art that CTE adjustments may be carried out

on the overall frit material (e.g., the compound) for the glass wetting and bonding properties of the frit to cooperate with an underlying substrate (e.g., a glass substrate). In certain example embodiments, CTE matching compounds may be added for these and/or other purposes.

[0108] One traditional CTE filler material that may be used with certain example frit materials may be lead titanate. However, as discussed above, usage of lead as a CTE filler may be commercially impractical, e.g., due to laws concerning the presence of lead in certain products (e.g., windows). Accordingly, non-lead based CTE filler material may be desirable in some cases.

[0109] In certain example embodiments, CTE filler material may be mixed in the form of a powder (e.g., spherical silica - vacuum bubbles) or microspheres with a frit material to form a sealing material that is used on one or more substrate(s).

[0110] For example, the following glass bubbles were tested with an example vanadium based frit material. The type in table 12 refers to a type of glass sphere available from the 3M Company.

Table 12				
Example Glass Bubbles				
Type	Crush Strength (psi)	Density (gm/cm ³)	Thermal Conductivity	Particle Size
K37	3,000	0.37	0.124	45
S60	10,000	0.6	0.2	30
S60 H	18,000	0.6	0.2	29
IM30K	28,000	0.6	0.2	15

[0111] As will be appreciated, the larger the bubble size the weaker mechanically the glass is (e.g., as shown in the crush strength). The inventor of the instant application determined that the IM30K example achieved results that were improvements over the other types in table 12. Further, the inventor determined that increasing the ratio of glass bubble volume to frit material may reduce the amount of delaminating of the sealing material from a substrate. In other words, as the amount of glass bubbles (e.g., in grams) to frit material is increased, the amount of delaminating to an example glass substrate may decrease. Fig. 22 shows an example of the above noted materials and how they delaminate when applied to a substrate. The data points from left to right in the graph represent increases in volume of the filler material used. In certain instances, by percent of volume, the glass sphere volume may be greater than that of the frit volume. For example, the spheres (by volume) may be 100% to 150% of the frit material.

[0112] In certain example embodiments, a CTE filler that is based on molybdenum (Mo) may be used. Molybdenum may have a linear ppm CTE of about 4.8. The inventor of the instant

application determined that molybdenum in a spherical form may perform with increased efficiency than other molybdenum based particles. In certain example embodiments, shapes with a size of less than about 150 mesh or more even less than about 170 mesh may be used with certain example VBZ frit materials.

[0113] A CTE filler that includes molybdenum spheres of between about 0.8 and 1.5 grams per 2.5 grams of frit material may produce improved compatibility with the base VBZ frit material and increase bond strength to an example glass substrate. In certain example embodiments, 1.0 grams of CTE filler per 2.5 grams of frit material may be used. In certain preferred embodiments, a frit material may be combined with about a 1.2 grams of molybdenum spheres (e.g., per 2.5 grams of frit material).

[0114] The inventor determined that use of spherical forms in CTE fillers may increase the effectiveness of restraining the frit matrix when compared to random shapes of conventional particle fillers. In such instances, spherical sizes may correlate to how a frit material with CTE filler may adhere to a glass substrate.

[0115] Figs. 23A - 23C show example microscope images of the spheres of certain example molybdenum materials. Such materials may be obtained from, for example, H.C. Starck and/or Alfa Aesar (a Johnson Matthey Company). Fig. 23A shows molybdenum spheres that are approximately 80 microns in diameter or major distance with some small variation in sizes, and the shapes being mostly round (e.g., spherical) and/or oblong. Fig. 23B shows spheres that are larger than those in Fig. 23A and that generally are in the 280-340 micron diameter or major distance range. As can be seen, the shapes in this molybdenum sphere example may be increasingly erratic, ragged, and/or sharp. Fig. 23C shows molybdenum spheres that are smaller than those of Fig. 23A. Here, the spheres are generally round and between about 40 and 70 microns in diameter or major distance.

[0116] In certain instances, the size of a sphere may affect the CTE matching properties of a CTE material. It has been observed that small particles (e.g., <5 microns in diameter or major distance) tend to dissolve into the frit during firing and contaminate the frit glass. It is noted that typical CTE fillers tend to have a significant amount of particles <5 microns in size. Additional dissolved compounds can upset the composition of the frit glass and change its sealing properties for the worse, unless it has a high tolerance for such contaminants (such as traditional lead frits). On the other hand, larger particles tend to have less surface area per mass, so the amount of dissolved contaminate tends to be significantly less. Thus, for example, a sphere size in the approximate range of those spheres shown in Fig. 23A may be preferred. Accordingly, CTE fillers have spheres in a size range between between 70 and 90 microns or, for example, 80 microns in sphere diameter or major distance size.

[0117] It will be appreciated that not all of the spheres or material within a given portion of CTE filler may fit such criteria (e.g., smaller/larger particles or non-sphere shaped particles). Thus, certain example embodiments may be comprised of between 80% and 100% of the above identified sphere sizes, with the remainder of the particles and/or spheres being outside such a

sphere size (e.g., spheres/particles that are greater than 100 microns or particles/spheres less than 60 microns). Additionally, not all of the "spheres" may be perfectly spherically shaped. Indeed, as shown in Fig. 23A some of the "spheres" may be partially or substantially spherically shaped. Thus, the particles that are used in certain CTE fillers may be "substantially" spherical. For example, more than half or 60% of the objects in a given CTE filler material may be "substantially" spherical, more preferably at least 80%, and even more preferably at least 95%. In certain instances, a percentage of spherically shaped elements in a CTE filler that are within a range of 60 to 100 microns may comprise at least 90% by volume of the CTE filler, more preferably at least 95%, and even more preferably at least 98%.

[0118] It will be appreciated that small particles sizes (e.g., <1 micron) may also be present in the initial CTE filler material. Thus, in certain instances for metals, heat may be used to consolidate the powdered metals into spherical or oblong shapes. This process may decrease or otherwise eliminate the finer powder, e.g., <1 micron particles. In other words, tiny particles may dissolve in the frit glass matrix and have negative impacts on the sealing properties. Larger particles with less surface area per weight may have a more controlled and enhanced effect on CTE expansion properties. Further, less spherical material may be needed to obtain a similar CTE value than would a powder of the same material.

[0119] In certain instances, the surface chemistry of the spheres (or other shapes) may be modified to improved CTE matching properties and/or the mechanical strength of the spheres (e.g., to withstand the stress of a VIG article).

[0120] In certain example embodiments, the following materials may be used in conjunction with a frit material for CTE matching the frit to a glass substrate: $\text{Cu}_2\text{P}_2\text{O}_7 \times \text{H}_2\text{O}$ (e.g., Copper Pyrophosphate Hydrate); $\text{Mg}_2\text{P}_2\text{O}_7$ (e.g., Magnesium Pyrophosphate); SnP_2O_7 (e.g., Tin Pyrophosphate - improved compatibility with at lower additions (e.g., 0.2-0.5 gm per 2.5 gm of frit material)); W (Tungsten powder - improved compatibility with frit materials at high addition levels (e.g., 1 to 1.5 gm per 2.5 gm of frit material)); Fe/Ni 65:35 wt% (e.g., Invar Alloy - improved compatibility with frit materials at higher addition levels (e.g., 0.6-0.8 gm per 2.5 gm of frit material)). Such materials (e.g., Invar) may be spherical in shape as the molybdenum material discussed above. Further, certain materials (e.g., Invar) may have decreased CTE - 1.2 ppm - and may therefore lower the additional weight added to a frit to obtain CTE matching. In certain instances, ceramic fillers may be used that are in spherical form. In certain example embodiments, quartz may be used. The quartz may be provided in the form of the spheres described herein. As the CTE of quartz is about 0.6, less material than other materials described herein may be needed in order to obtain a CTE match against a given substrate. One aspect of certain example embodiments relates to a filler that is inert and does not react with the molten frit glass during firing.

[0121] In certain example embodiments, Zirconium Tungstenate (e.g., Zirconium Tungsten Oxide or ZrW_2O_8) powder may provide acceptable CTE matching for certain example frit materials with a soda lime float glass (e.g., with linear CTE for the glass being between about 7.0-11.0 ppm). However, as ZrW_2O_8 may be relatively expensive, such a CTE filler may be

commercially impractical for some mainstream applications. However, it will be appreciated that where cost is not an issue (or the overall price of the CTE filler decreases), such a CTE filler may be used in conjunction with certain example frit materials described herein. In certain example embodiments, a Zirconium Tungstenate based filler may use spherical shapes instead of particles (e.g., powder).

[0122] In certain example embodiments molybdenum spheres may be combined with glass bubbles (e.g., other particles). For example, 0.3-0.5 gm by weight of molybdenum spheres combined with 0.2-0.3 gm by weight of IM30K or between 0.15-0.35 by weight of ZrW_2O_8 and 0.2-0.3 gm of IM30K may be used according to certain example embodiments. In certain example embodiments, two or more of the discussed CTE fillers may be combined to form a combined CTE filler material.

[0123] Fig. 24 is a flowchart illustrating a process for creating an article according to certain example embodiments. A CTE filler is combined with an exemplary frit material (e.g., a VBZ frit) in step 2402. The combined material is then disposed on a substrate in step 2404. For example, the substrate may be a soda lime float glass substrate. In certain instances, e.g., the creation of the VIG unit, another substrate may be applied with a gap between the two substrates. In any event, energy (e.g., IR energy) may be applied to the glass and/or the combined material to thereby melt the material in step 2406. After melting, the combined material, and the substrate(s) or article may be cooled or allowed to cool in step 2408.

[0124] In certain example embodiments, the CTE of a frit material including an exemplary CTE filler may be within about 15% of the CTE of a substrate, more preferably within about 10%, even more preferably within about 5%, and even more preferably within about 3%. For instance, it is known that glass has a CTE of 8.6 ppm, e.g., over a temperature range of about 25-300 degrees C. It would be desirable to provide a CTE filler material that is less than or equal to this value. For instance, a CTE of 8.0 ppm over the same or similar range would be desirable. Doing so will keep the glass in a state of compression, which is desirable.

[0125] Although certain example embodiments have been described as relating to spherical or generally spherical CTE fillers, other shapes may be used in place of or together with such shapes. For instance, football, eye-shaped, cylindrical, elongated, whisker-shaped, and/or other type particles may be used. Such shapes may be symmetrical and/or symmetrically curved in some example cases. In certain example embodiments, the shapes shown in Figs. 23B and/or 23C may be used with sizes between, for example, 60-100 microns.

[0126] Moreover, it is to be understood that there may be some variation in a particular size and/or shape material. However, in the aggregate, the material distributions should generally have the specified sizes/shapes.

[0127] The example embodiments described herein have been observed as exhibiting good compatibility with the specific example frit systems disclosed herein. For instance, the combination of the example CTE matchers with the example frit materials disclosed herein

have been observed as having good sealing properties such as glassy fired appearance and good frit-to-glass wetting and bond strength. Mechanical strength also has been found to be good. Some other commercially available CTE matching materials do not exhibit the same compatibility, strengths, etc., with the example frit materials disclosed herein.

[0128] It will be appreciated that one or more metal oxide, chloride, and/or fluoride additives may be used as additives in different embodiments of this invention. Furthermore, in certain example implementations, the metal oxide, chloride, and/or fluoride additives may be stoichiometric or sub-stoichiometric.

[0129] It is noted that the example embodiments discussed herein may be used in connection with other applications such as, for example, MEMS applications. In the MEMS context, the CTE filler may be increased to lower overall expansion to silicon and/or alumina. For example, 3 ppm CTE matcher with 40 wt % ZrW_2O_8 may be sufficient for the former, and 8 ppm CTE with 35 wt % molybdenum-based spheres may be sufficient for the latter.

[0130] As used herein, the terms "on," "supported by," and the like should not be interpreted to mean that two elements are directly adjacent to one another unless explicitly stated. In other words, a first layer may be said to be "on" or "supported by" a second layer, even if there are one or more layers there between.

[0131] While the invention has been described in connection with what is presently considered to be the most practical and preferred embodiment, it is to be understood that the invention is not to be limited to the disclosed embodiment, but on the contrary, is intended to cover various modifications.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- [US5664395A \[0002\] \[0006\]](#)
- [US5657607A \[0002\]](#)
- [US5902652A \[0002\]](#)
- [US2005233885A1 \[0003\]](#)
- [US3837866A \[0007\]](#)

- US4256495A [0007]
- US4743302A [0007]
- US5051381A [0007]
- US5188990A [0007]
- US5336644A [0007]
- US5534469A [0007]
- US7425518B [0007]
- US20050233885A [0007]
- EP1065183A1 [0019]
- WO2013043340A1 [0020]
- WO2013101748A1 [0021]
- WO2012115796A1 [0022]
- US20060003883A1 [0023]
- US4221604A [0030]
- JP2009298673A [0031]
- JP2009221047A [0032]
- JP2009221048A [0032]
- JP2011086518A [0033]
- WO12929874A [0065]
- US12929874B [0067]
- WO12929876A [0069]

Patentkrav

1. Fremgangsmåde til fremstilling af en vakuumisoleret glashed, VIG, (500), hvilken fremgangsmåde omfatter:

- 5
- at tilvejebringe første og andet glassubstrater (502a, 502b) der er i det væsentlige parallelle og adskilt med afstand fra hinanden, hvilket definerer et mellemrum mellem det første og andet substrat (502a, 502b);
- at anbringe et materiale tæt på det første og/eller andet glassubstrat (502a, 502b), hvilket materiale omfatter mindst et frittemateriale og et varmeeekspansionskoefficientmateriale, CTE; og
- 10
- at tilføre energi til materialet for at smelte materialet ved en smeltetemperatur, hvilket CTE-materialet omfatter elementer, der er af perfekt, delvist og/eller i det væsentlige sfæriske i form, hvilke elementer har en gennemsnitlig diameter eller større afstand på mellem 70 og 90 mikrometer, og
- 15
- hvilket frittemateriale er dannet af en basissammensætning, der inkluderer:

Ingrediens	Normaliseret mol-%
vanadiumoxid	~45-50%,
bariumoxid	~20-23% og
zinkoxid	~19-22%.

2. Fremgangsmåden ifølge krav 1, hvor elementerne der er kugleformede, omfatter mere end 90 vol.-% CTE-materialer.

3. Fremgangsmåden ifølge krav 1, hvor materialet inkluderer en bindemiddelopløsning, der inkluderer polypropylencarbonat eller polyethylencarbonat.

4. Fremgangsmåden ifølge krav 1, hvor basissammensætningen inkluderer mindst fire oxid-, chlorid- og/eller fluoridbaserede additiver.

5. Materiale der omfatter:

et varmeeekspansionskoefficientmateriale, CTE, der i det væsentlige er blyfrit, hvor 80 % til 100 % af elementerne i CTE-materialet er mellem 70 og 90 mikrometer i diameter eller større afstand; og

et frittemateriale der har en sammensætning, som inkluderer:

Ingrediens	Normaliseret mol-%
vanadiumoxid	~45-50%,
bariumoxid	~20-23% og
zinkoxid	~ 19-22%; og

5

hvilket materiale har en første CTE-værdi, der er inden for 15 % af soda-kalk-silikat-floatglas, hvilket glas har en lineær CTE-værdi mellem 7,0 og 11,0 ppm/K i sammensætningen af CTE-materialet,

10

hvilket CTE-materiale omfatter partikler, der er af perfekt, delvist og/eller i det væsentlige sfærisk form.

6. Materialet ifølge krav 5, hvor CTE-materialet inkluderer molybdæn.

7. Materialet ifølge krav 5, hvor sammensætningen yderligere inkluderer mindst seks additiver, som er valgt fra gruppen, der består af: Ta₂O₅, Ti₂O₃, SrCl₂, GeO₂, CuO, AgO, Nb₂O₅, B₂O₃, MgO, SiO₂, TeO₂, Tl₂O₃, Y₂O₃, SnF₂, SnO₂, SnCl₂, CeO₂, AgCl, In₂O₃, SnO, SrO, MoO₃, CsCO₃ og Al₂O₃.

8. Vakuumisoleret glasehed, VIG, (500) der omfatter:

20 første og andet i det væsentlige parallelle, adskilte glassubstrater (502a, 502b); og

en kantforsegling der er tilvejebragt omkring en periferi af det første og/eller andet substrat (502a, 502b) for at danne en hermetisk tætning derimellem, og som mindst delvist definerer et mellemrum mellem det

25 første og andet substrat,

hvilket mellemrum er tilvejebragt ved et tryk, der er mindre end atmosfærisk tryk, og hvilken kantforsegling er dannet af materialet ifølge krav 5.

9. Fremgangsmåde til fremstilling af et materiale, hvilken fremgangsmåde omfatter:

at tilvejebringe en sammensætning til en holder, hvilken sammensætningen omfatter:

Ingrediens	Normaliseret mol-%
vanadiumoxid	~45-50%,
bariumoxid	~20-23% og
zinkoxid	~ 19-22%; og

5

at smelte sammensætningen; og

at afkøle den smeltede sammensætning og/eller lade den smeltede sammensætning afkøle for at danne et mellemprodukt;

at danne et basisfrittemateriale fra mellemproduktet; og

10

at kombinere basisfrittematerialet med et CTE-materiale, der omfatter partikler, som har en gennemsnitlig diameter på mellem 70 og 90 mikrometer og er af perfekt, delvist og/eller i det væsentlige sfærisk form.

15 **10.** Fremgangsmåden ifølge krav 9, hvor sammensætningen inkluderer mindst fire additiver, som er valgt fra gruppen, der består af: Ta₂O₅, Ti₂O, SrCl₂, GeO₂, CuO, AgO, Nb₂O₅, B₂O₃, MgO, SiO₂, TeO₂, Tl₂O₃, Y₂O₃, SnF₂, SnO₂, SnCl₂, CeO₂, AgCl, In₂O₃, SnO, SrO, MoO₃, CsCO₃ og Al₂O₃.

20 **11.** Fremgangsmåde til binding af et frittemateriale til et glassubstrat, hvilken fremgangsmåde omfatter:

at kombinere frittematerialet med et varmeeekspansionskoefficientmateriale, CTE, for at danne et kombineret materiale, hvilket CTE-materiale omfatter elementer, der er af perfekt, delvist og/eller i det væsentlige sfærisk form, og hvilke elementer har en gennemsnitlig diameter eller større afstand på mellem 70 og 90 mikrometer;

25

at anbringe det kombinerede materiale på substratet;

at opvarme det kombinerede materiale til en temperatur på mindre end 400 grader C;

hvor en varmeeekspansionskoefficient der er forbundet med det kombinerede materiale, er inden for 10 % af en varmeeekspansionskoefficient for glassubstratet, når der påføres varme til det kombinerede materiale;

5


hvilket frittemateriale inkluderer en sammensætning, der omfatter:

Ingrediens	Normaliseret mol-%
vanadiumoxid	~45-50%,
bariumoxid	~20-23% og
zinkoxid	~19-22%.

12. Fremgangsmåden ifølge krav 11, hvor CTE-materialet omfatter molybdæn.

10 **13.** Fremgangsmåden ifølge krav 1, hvor elementer af CTE-materialet inkluderer molybdæn.

DRAWINGS






FIG. 3




FIG. 4




Fig. 6




Fig. 7A




Fig. 7B




Fig. 7C

Transition Glass Temperature Compared to Slide Melt Quality




Fig. 7D




Fig. 8A




Fig. 8B




Fig. 8C




Fig. 9




Fig. 10A




Fig. 10B




Fig. 10C




Fig. 11A




Fig. 11B




Fig. 11C




Fig. 12A




Fig. 12B




Fig. 12C


425C 13mm Button for Ta₂O₅ and Nb₂O₅ Matrix

Fig. 13





Fig. 14A

1402




1404

Fig. 14B



Fig. 15A

1502



minutes


1504

Fig. 15B



Fig. 16

1602



1604





Fig. 18






Fig. 20




Fig. 21




Fig. 22




Fig. 23A




Fig. 23B




Fig. 23C




Fig. 24

