

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
25 June 2020 (25.06.2020)



(10) International Publication Number
WO 2020/126818 A1

(51) International Patent Classification:

C08K 5/17 (2006.01) C09J 4/00 (2006.01)

(21) International Application Number:

PCT/EP2019/084878

(22) International Filing Date:

12 December 2019 (12.12.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

18214799.1 20 December 2018 (20.12.2018) EP

(71) Applicant: **HUNTSMAN ADVANCED MATERIALS LICENSING (SWITZERLAND) GMBH** [CH/CH]; Klybeckstraße 200, 4057 Basel (CH).

(72) Inventors: **FRAPSAUCE, Astrid**; 11 rue Dom Calmet, 57000 Metz (FR). **BARON, Catherine**; 23 rue de la forêt, 68510 Magstatt-le-Bas (FR).

(74) Agent: **WEIDNER STERN JESCHKE PATENTANWÄLTE PARTNERSCHAFT MBB**; Universitätsallee 17, 28359 Bremen (DE).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ADHESIVE COMPOSITION WITH RETARDING ADDITIVE

(57) Abstract: The present disclosure relates to an adhesive composition comprising one or more (meth)acrylate ester monomers, a catalyst system and a retarding additive, wherein the retarding additive is a secondary amine; and to the use of secondary amines as retarding agents for adhesive compositions comprising methacrylate monomers.



WO 2020/126818 A1

Adhesive Composition with Retarding Additive

Technical Field

[01] The present disclosure generally relates to adhesive compositions, in particular adhesive compositions comprising one or more methacrylate monomers, a catalyst system and a retarding additive.

Background of the Invention

[02] Adhesive formulations based on methyl methacrylate (MMA) have been extensively investigated over the past decades resulting in a number of improvements as disclosed, for example, in EP 2 275 507 A1, WO 2006/119469 A2 and US 7,776,963 B2.

[03] One remaining problem of adhesive formulations containing MMA is the pungent odor and flammability of MMA.

[04] EP 1 609 831 A1 discloses compositions using low odor methacrylate monomers instead of MMA to solve this problem.

[05] To replace MMA while maintaining desired adhesion and mechanical properties, mixtures of methacrylate esters need to be used. Catalyst packages to properly cure such monomer mixtures are known from the prior art. US 4,348,503, for example, discloses adhesive compositions with a catalyst system based on an aromatic perester free-radical precursor (preferably together with an amine/aldehyde adduct activator), an organic acid capable of cyclic tautomerism and a transition metal cure accelerator.

[06] However, due to the high reactivity of certain methacrylate monomers, there is a need to slow down reactivity in order to achieve a long open time (as defined below) without impacting mechanical and adhesion
5 properties.

[07] US 6,291,593 B1 discloses retarding additives for methacrylate adhesives on the basis of non-protonic Lewis acids and zinc salts. However, such retarding agents are usually hygroscopic which has a negative impact on the
10 handling of the retarding agents. Such retarding agents usually also have a negative impact on storage stability of the adhesive such as elongation at break.

[08] Therefore, there is a continuous need for retarding agents for adhesive compositions based on methacrylate
15 monomers to slow down the reactivity without any negative impact on the mechanical and adhesion properties.

Disclosure of the Invention

[09] Unless otherwise defined herein, technical terms used
20 in connection with the present disclosure shall have the meanings that are commonly understood by those having ordinary skill in the art. Further, unless otherwise required by context, singular terms shall include pluralities and plural terms shall include the singular.

[10] All patents, published patent applications, and non-patent publications mentioned in the specification are indicative of the level of skill of those skilled in the
25 art to which the present disclosure pertains. All patents,

published patent applications, and non-patent publications referenced in any portion of this application are herein expressly incorporated by reference in their entirety to the same extent as if each individual patent or publication
5 was specifically and individually indicated to be incorporated by reference to the extent that they do not contradict the instant disclosure.

[11] All of the compositions and/or methods disclosed herein can be made and executed without undue
10 experimentation in light of the present disclosure. While the compositions and methods of the present disclosure have been described in terms of preferred embodiments, it will be apparent to those having ordinary skill in the art that variations may be applied to the compositions and/or
15 methods and in the steps or sequences of steps of the methods described herein without departing from the concept, spirit, and scope of the present disclosure. All such similar substitutes and modifications apparent to those skilled in the art are deemed to be within the
20 spirit, scope, and concept of the present disclosure.

[12] As utilized in accordance with the present disclosure, the following terms, unless otherwise indicated, shall be understood to have the following meanings.

[13] The use of the word "a" or "an", when used in
25 conjunction with the term "comprising", "including", "having", or "containing" (or variations of such terms) may mean "one", but it is also consistent with the meaning of "one or more", "at least one", and "one or more than one".

[14] The use of the term "or" is used to mean "and/or" unless clearly indicated to refer solely to alternatives and only if the alternatives are mutually exclusive.

5 [15] Throughout this disclosure, the term "about" is used to indicate that a value includes the inherent variation of error for the quantifying device, mechanism, or method, or the inherent variation that exists among the subject(s) to be measured. For example, but not by way of limitation, when the term "about" is used, the designated value to
10 which it refers may vary by plus or minus ten percent, or nine percent, or eight percent, or seven percent, or six percent, or five percent, or four percent, or three percent, or two percent, or one percent, or one or more fractions therebetween.

15 [16] The use of "at least one" will be understood to include one as well as any quantity more than one, including but not limited to, 1, 2, 3, 4, 5, 10, 15, 20, 30, 40, 50, 100, etc. The term "at least one" may extend up to 100 or 1000 or more depending on the term to which it
20 refers. In addition, the quantities of 100/1000 are not to be considered as limiting since lower or higher limits may also produce satisfactory results.

[17] As used herein, the words "comprising" (and any form of comprising, such as "comprise" and "comprises"),
25 "having" (and any form of having, such as "have" and "has"), "including" (and any form of including, such as "includes" and "include") or "containing" (and any form of containing, such as "contains" and "contain") are inclusive

or open-ended and do not exclude additional, unrecited elements or method steps.

[18] The phrases "or combinations thereof" and "and combinations thereof" as used herein refers to all permutations and combinations of the listed items preceding the term. For example, "A, B, C, or combinations thereof" is intended to include at least one of: A, B, C, AB, AC, BC, or ABC and, if order is important in a particular context, also BA, CA, CB, CBA, BCA, ACB, BAC, or CAB. Continuing with this example, expressly included are combinations that contain repeats of one or more items or terms such as BB, AAA, CC, AABB, AACC, ABCCCC, CBBAAA, CABBB, and so forth. The skilled artisan will understand that typically there is no limit on the number of items or terms in any combination, unless otherwise apparent from the context. In the same light, the terms "or combinations thereof" and "and combinations thereof" when used with the phrases "selected from" or "selected from the group consisting of" refers to all permutations and combinations of the listed items preceding the phrase.

[19] The phrases "in one embodiment", "in an embodiment", "according to one embodiment", and the like generally mean the particular feature, structure, or characteristic following the phrase is included in at least one embodiment of the present disclosure, and may be included in more than one embodiment of the present disclosure. Importantly, such phrases are non-limiting and do not necessarily refer to the same embodiment but, of course, can refer to one or more preceding and/or succeeding embodiments. For example,


in the appended claims, any of the claimed embodiments can be used in any combination.

[20] "Open time", as used herein, is meant to be the amount of time after the adhesive is applied onto a first substrate, that the adhesive maintains sufficient tack to bond effectively to a second substrate.

[21] The objective of the present disclosure is solved by an adhesive composition comprising one or more (meth)acrylate ester monomers, a catalyst system and a retarding additive, wherein the retarding additive is a secondary amine.


[22] Preferably, the secondary amine is a secondary amine comprising more than one secondary amine groups, more preferably, a secondary aryl amine.

[23] In a specifically preferred embodiment of the present disclosure, the secondary aryl amine is selected from compounds having formula (1)




wherein R1 and R2 are independently selected from C₆-C₁₈ alkyl groups,

formula (2)



wherein R1 is selected from C₆-C₁₈ alkyl groups and R2 is selected from hydrogen or C₁-C₆ alkyl groups, or

formula (3)



5 wherein R1 and R2 are independently selected from hydrogen or C₁-C₆ alkyl groups.

[24] In another specifically preferred embodiment of the present disclosure, the retarding additive is selected from cyclic secondary amines, most preferably a 2,2,4-trimethyl-1,2-dihydroquinoline polymer.

[25] In one embodiment of the present disclosure, the adhesive composition comprises an amount of 1 % to 5 % by weight of the retarding additive, based on the total weight of the adhesive composition.

15 [26] In another preferred embodiment of the present disclosure, the adhesive composition comprises an amount of 10 % to 90 % by weight of the one or more methacrylate ester monomers, based on the total weight of the adhesive composition.

20 [27] The present disclosure is also related to the use of a secondary amine or a mixture of secondary amines as a retarding additive for an adhesive composition comprising methacrylate monomers.

[28] The compounds used as retarding additives in the compositions of the present disclosure are known per se in the art, for example, as antioxidants in the rubber industry. Surprisingly, it has now been found that they are very effective in extending the open time of methacrylate-based adhesive compositions without affecting the mechanical and adhesive properties or the storage stability.

[29] The following Table 1 shows preferred compositions for an adhesive composition in accordance with the present disclosure (with both part A (resin part) and part B (hardener part)). Any preferred, more preferred or most preferred weight percentages or weight percentage ranges of any component can be combined with any preferred, more preferred or most preferred weight percentage or weight percentage range of any of the other components.

Table 1

Component	Weight Percent		
	Preferred	More preferred	Most preferred
Ester monomer	10 - 90	40-60	52-58
Acid monomer	1-12	2-6	2-3
Polymeric modifier	5-50	10-30	10-15
Antioxidant	0.001-0.2	0.005-0.1	0.05-0.1
Catalyst system	0.001-10	0.1-4	0.5-2
Inhibitor	0.1-5	1-3	1-1.5

Toughening agent	10-40	20-30	20-25
Retarding additive of the present disclosure	0.5-5	1-3	2-2.5

[30] The (meth)acrylate ester monomer is usually a mixture of (meth)acrylate ester monomers. These may be methacrylates selected from, for example, hydroxyethyl methacrylate (HEMA), hydroxypropyl methacrylate (HPMA), 2-ethylhexyl methacrylate (EHMA), tetrahydrofuryl methacrylate (THFMA), cyclohexyl methacrylate (CHMA), benzyl methacrylate (BMA), isobornyl methacrylate (IBOMA), isodecyl methacrylate (IDMA), phenoxyethyl methacrylate (PEMA) and butyl methacrylate (BMA), or acrylates selected from, for example, methyl acrylate (MA), butyl acrylate (BA), cyclohexyl acrylate (CHA), hexyl acrylate (HA), 2-ethylhexyl acrylate (EHA), lauryl acrylate (LA) and ethyl acrylate (EA), or mixtures of the above methacrylates, acrylates or both.

[31] Less preferably, (meth)acrylate ester monomers may be used wherein the alcohol portion of the ester groups contains 1 to 8 carbon atoms. Even less preferably, other (meth)acrylate ester monomers known in the art may be used.

[32] The acid monomer, which is a preferred optional component of the adhesive composition of the present disclosure, is preferably methacrylic acid (MAA), less preferably acrylic acid, maleic acid, crotonic acid, and

fumaric acid, less preferably other free-radical polymerizable acid monomers known in the art.

[33] The polymeric modifier, which is another preferred optional component of the adhesive composition of the present disclosure, is preferably a core-shell impact modifier, less preferably nitro-rubber particles or powder or polymeric resin which acts as a thixotropic agent and/or toughener. The core-shell impact modifier is preferably a graft copolymer of the "core-shell" type. Preferred core-shell graft copolymers are acrylonitrile-butadiene-styrene (ABS), methacrylate-butadiene-styrene (MBS), and methacrylate-acrylonitrile-butadiene-styrene (MABS). Another preferred core-shell impact modifier is the so-called Acrylic Impact Modifier (AIM), a core-shell product with a butylacrylate rubber core and a polymethylmethacrylate (PMMA) shell.

[34] The antioxidant, another preferred optional component of the adhesive composition of the present disclosure, is preferably an antioxidant from the IRGANOX® series available from BASF, such as IRGANOX® 1098 (N,N'-1,6-hexanediyldis[3,5-bis(1,1-dimethylethyl)-4-hydroxy]-benzenepropanamide] or IRGANOX® 1330 (a 3,3',3',5,5',5'-hexa-tert-butyl-a,a',a'-(mesitylene-2,4,6-triyl)tri-p-cresol), less preferably other antioxidants known in the art.

[35] The inhibitor, which is another preferred optional component of the adhesive composition of the present disclosure, is a free-radical polymerization inhibitor,

which increases shell life and prevents or inhibits premature polymerization and is preferably hydroquinone (HQ) or methylhydroquinone, less preferably butylated hydroxytoluene (BHT) or other known free-radical
5 polymerization inhibitors.

[36] The toughening agent, another preferred optional component of the adhesive composition of the present disclosure, is selected from polymers from the group consisting of polychloroprene, copolymers of butadiene and
10 other monomers, such as acrylonitrile, copolymers of isoprene with styrene, acrylonitrile, acrylate esters, methacrylate esters, copolymers of ethylene and acrylate esters, homopolymers of epichlorohydrine and copolymers of epichlorohydrine and ethylene, polychloroprene with block-
15 copolymers of styrene and butadiene or isoprene and block-copolymers of styrene, diene monomers and mixtures thereof.

[37] Any catalyst system useful for initiation and activation of the polymerization reaction in the adhesive
20 composition of the present disclosure which is known for (meth)acrylate adhesive systems can be used. Preferred catalyst systems to be used with the adhesive composition of the present disclosure may be the ones as described in US 4,348,503. The use of known accelerators and promoters
25 can be advantageous.

[38] Further details can be seen from the following examples.

Examples

[39] The following materials were used in preparation of the example formulations:

- 5 THFMA: tetrahydrofurfuryl methacrylate, obtained as Sartomer® SR203H available from Sartomer
- EHMA: ethylhexyl methacrylate, obtained as VISIOMER® EHMA available from Evonik
- MAA: methacrylic acid, obtained available from Sigma Aldrich
- 10 Silquest A174: vinyl silane, obtained from Momentive
- Maleic acid: obtained from DSM
- VULKANOX® BHT: butylated hydroxytoluene, obtained from Lanxess
- 15 PARALOID TMS2670J: MBS core shell impact modifier, obtained from Dow
- PARALOID EXL 2300G: AIM core shell, obtained from Dow
- Sartomer® SR348C: ethoxylated bisphenol A dimethacrylate, obtained from Sartomer
- CAB-O-SIL® TS720: treated fumed silica, obtained from Cabot
- 20 Trigonox® C: t-butyl peroxybenzoate, obtained from AkzoNobel
- Soligen copper: obtained from Borchers

VULKANOX® HS LG: 2,2,4-trimethyl-1,2-dihydroquinoline polymer, obtained from Lanxess

KGL097: 3,5-diethyl-1,2-dihydro-1-phenyl-2-propylpyridine, obtained from Lake Chemicals

5 The amounts shown in Table 2 are in weight %.

Resin

[40] First, maleic acid was dissolved into THFMA at room temperature (about 25°C). All components for the resin in Table 2 were added together and mixed using a speed mixer
10 (centrifugal mixer) until a homogenous product resulted.

Hardener

[41] A solution of 200 ppm of soligen copper in EHMA was prepared. All components for the hardener in Table 2 were added together and mixed using a speed mixer (centrifugal
15 mixer) until a homogenous product resulted. VULKANOX® HS LG was ground prior to addition, and then dissolved in post addition into the matrix.

20

Table 2

	<u>Example 1</u>	<u>Example 2</u>
Resin		
VISIOMER® EHMA	10.1	10.1
Methacrylic acid	3	3
Silquest A174	1	1
Solution 6% Maleic acid / 94% THFMA	42	42
VULKANOX® BHT	0.2	0.2
PARALOID TMS2670J	10	10
Sartomer® SR348 C	25	25
CAB-O-SIL® TS720	6.5	6.5
Trigonox C	2.2	2.2
Hardener		
VISIOMER® EHMA	47.5	45.5
Soligen copper solution 200ppm in Visiomer EHMA	12.5	12.5
KGL097	5	5
PARALOID EXL 2300G	8	8
Sartomer® SR348 C	25	25
CAB-O-SIL® TS720	2	2
VULKANOX® HS LG	-	2

Table 3

<u>Test</u>		<u>Example 1</u>	<u>Example 2</u>
Exotherm test	Time to 32°C	1min	3min 30s
	Maximum temperature	140°C	135°C
	Time to max exotherm	4min	7min 30s
Lap Shear Strength	Stainless Steel	23 CF /SCF	20 CF
	CFRP	13 CF	11 CF
	ABS	5 CF/SDF	5 CF
Tensile properties	Tensile strength (MPa)	32	30
	Modulus (MPa)	880	860
	Elongation at break (%)	12	10
DMA	Glass transition temperature	69°C	68°C
Tests performed on mix ratio 1:1 by weight of resin and hardener			

Exotherm test at 23°C

5 Mix 7 g resin + 7 g hardener into a cup, then transfer into a silicon mold and follow exotherm reaction over time with a thermocouple.

Record time to reach 32°C, maximum temperature, and time to reach maximum temperature.

Lap Shear strength (ISO 4587)

The CFRP (Carbon Fibre Reinforced Polymer) and ABS
5 (Acrylonitrile Butadiene Styrene) substrates were degreased
by wiping with isopropanol and abraded. The aluminum
substrates were sandblasted and rinsed with acetone. The
adhesive composition was dispensed onto one surface of the
10 substrate pair. The two surfaces were mated and held to
each other with a compressor-type tubing clamp. The overlap
area was 25.0 mm x 12.5 mm. The bonded joints were left to
cure for 24 h at 23°C. The clamps were then removed and the
bonded joints were tested for tensile shear strength (TSS)
according to ISO 4587 at crosshead speed of 10 mm/min. The
15 TSS values were recorded in megapascals (MPa). The average
value of 3 tested joints is reported.

Tensile properties (ISO 527)

A plate of 2 mm thickness was prepared under press and
cured for 1 week at room temperature (about 25°C) before to
20 be tested according to ISO 527.

Dynamic Mechanical Analysis (ISO 6721)

Samples from the same plate were tested in torsion
according to ISO 6721 from -100 to +150°C to determine
glass transition temperature.

25 The above test results show that the addition of the
retarding additive in the composition of Example 2


according to the present disclosure slows down the reactivity of the system without impacting either the adhesion, tensile properties or glass transition temperature.

5 The above-disclosed subject matter is to be considered illustrative, and not restrictive, and the appended claims are intended to cover all such modifications, enhancements, and other embodiments, which fall within the true scope of the present disclosure. Thus, to the maximum extent allowed
10 by law, the scope of the present disclosure is to be determined by the broadest permissible interpretation of the following claims and their equivalents, and shall not be restricted or limited by the foregoing detailed disclosure.

15


Claims

1. An adhesive composition comprising one or more (meth)acrylate ester monomers, a catalyst system and a retarding additive, wherein the retarding additive is a secondary amine.
2. The adhesive composition according to claim 1, wherein the secondary amine is a secondary amine comprising more than one secondary amine group.
3. The adhesive composition according to claim 2, wherein the secondary amine is a secondary aryl amine.
4. The adhesive composition according to claim 3, wherein the secondary aryl amine is selected from compounds having formula (1)




wherein R1 and R2 are independently selected from C₆-C₁₈ alkyl groups,

formula (2)



wherein R1 is selected from C₆-C₁₈ alkyl groups and R2 is selected from hydrogen or C₁-C₆ alkyl groups, or

formula (3)



wherein R1 and R2 are independently selected from hydrogen or C₁-C₆ alkyl groups.

5. The adhesive composition according to claim 1, wherein the retarding additive is selected from cyclic secondary amines.
6. The adhesive composition according to claim 5, wherein the cyclic secondary amine is a 2,2,4-trimethyl-1,2-dihydroquinoline polymer.
7. The adhesive composition according to any of the preceding claims, wherein the retarding additive is comprised in an amount of 1 % to 5 % by weight, based on the total weight of the adhesive composition.
8. The adhesive composition according to any of the preceding claims, wherein the one or more methacrylate ester monomers are comprised in an amount of 10 % to 90 % by weight, based on the total weight of the adhesive composition.
9. Use of a secondary amine or a mixture of secondary amines as a retarding additive for an adhesive composition comprising methacrylate monomers.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2019/084878

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08K5/17 C09J4/00
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C08K C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 2009 102647 A (NITTO DENKO CORP) 14 May 2009 (2009-05-14) the whole document -----	1-9

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

10 February 2020

Date of mailing of the international search report

18/02/2020

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Rinkel, Bert

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2019/084878

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2009102647	A	NONE	
