



(51) International Patent Classification:

C08F 210/16 (2006.01) C08F 4/6592 (2006.01)

(21) International Application Number:

PCT/EP2018/057922

(22) International Filing Date:

28 March 2018 (28.03.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

17163947.9 30 March 2017 (30.03.2017) EP

(71) Applicant: BOREALIS AG [AT/AT]; Wagramer Strasse
17-19, Austria, 1220 Vienna (AT).

(72) Inventors: FAIT, Anna; Borealis Polyolefine GmbH, St.-Peter-Straße 25, 4021 Linz (AT). AJELLAL, Noured-dine; Borealis Polymers Oy, PO Box 330, 06101 Porvoo (FI). RESCONI, Luigi Maria Cristoforo; Borealis Polyolefine GmbH, St.-Peter-Strasse 25, 4021 Linz (AT). IZMER, Vyatcheslav V.; apt.248, 2/19 Remezova Street, Moscow, 117186 (RU). KONONOVICH, Dmitry S.; apt. V-1016, Vorobyovy Gory, Moscow, 119234 (RU). SAMSONOV, Oleg; apt. B-1233, 1 Leninskie Gory, DS MGU, Moscow, 119234 (RU). VOSKOBOYNIKOV, Alexander Z.; apt.93 bld. 5, Korolev Street, Moscow, 129515 (RU). SABLON, Rafael; Stratumseind 54/A, 5611 Eindhoven (NL).

(74) Agent: LINDINGER, Ingrid Andrea; Borealis AG, St.-Peter-Strasse 25, 4021 Linz (AT).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,

MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: BORATE-ACTIVATED METALLOCENE CATALYSTS



(I)

(57) Abstract: Catalyst system, the catalyst system comprising (i) at least one metallocene complex of formula (I), (I) wherein Mt1 is Hf, X is a sigma-donor ligand, R¹, R², R³ are the same or different from each other and can be hydrogen or a saturated linear or branched C₁-C₁₀ alkyl, whereby the alkyl group can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, or R¹ and R² or R² and R³ can form a ring having 4 to 6 C-atoms and 1 to 3 double bonds, R⁴ and R⁵ are the same or different from each other and can be saturated linear or branched C₁-C₁₀ alkyl, C₅-C₁₀ aryl, C₆-C₂₀ alkylaryl or C₆-C₂₀ arylalkyl groups, which can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, n can be 1 to 5, Ar is a C₆-C₂₀-aryl or -heteroaryl group, which can be unsubstituted or substituted by 1 to 5 linear or branched C₁-C₁₀ alkyl group(s), and (ii) a boron containing cocatalyst.

Borate-activated metallocene catalysts

The present invention is related to a new catalyst system, which is especially able to produce polyethylene copolymers in a high temperature solution polymerization process. The new catalyst system comprises a specifically substituted, bridged hafnocene catalyst complex, comprising a cyclopentadienyl (Cp) ligand, a fluorenyl (Flu) ligand and a covalent bridge connecting the two ligands, along with a boron based cocatalyst. This combination remarkably gives rise to catalyst systems with an improved balance of comonomer incorporation ability and molecular weight capability.

Metallocene catalysts have been used to manufacture polyolefins for many years. Countless academic and patent publications describe the use of these catalysts in olefin polymerization. Metallocene catalysts are now used industrially and polypropylenes as well as polyethylenes are often produced using cyclopentadienyl based catalyst systems with different substitution patterns.

Several of these metallocene catalysts have been described for the use in solution polymerization for producing polyethylene homo- or copolymers.

For example WO 2000024792 describes a catalyst system comprising a hafnocene catalyst complex derived from A) a biscyclopentadienyl hafnium organometallic compound having i) at least one unsubstituted cyclopentadienyl ligand or aromatic fused-ring substituted cyclopentadienyl ligand not having additional substituents on said ligand, ii) one substituted or unsubstituted, aromatic fused-ring substituted cyclopentadienyl ligand, and iii) a covalent bridge connecting the two cyclopentadienyl ligands.

This bridge can be a single carbon substituted with two aryl groups, each of these aryl groups being substituted with a C₁ - C₂₀ hydrocarbyl or hydrocarbylsilyl group, whereby at least one of these substituents is a linear C₃ or greater substituent.

In addition the catalyst system comprises an activating cocatalyst, which is preferably a precursor ionic compound comprising a halogenated tetraaryl-substituted Group 13 anion.

Also US 20060161013 is related to bridged Cp-Flu metallocene complexes. The C-based bridges shown in the Examples are substituted methylene bridges, whereby the substituents are the same (e.g. dimethyl, diphenyl, dibenzyl, dicyclohexyl etc.) or are linked together to form a ring (e.g. cyclohexylidene).

EP 1768990 describes the synthesis of Cp-Flu metallocene complexes of Zr or Hf, in which the Flu-ligand is substituted in position 2 and 7. Both substituents on the bridge are aliphatic groups, whereby one can be an alkenyl.

- 5 US 2003092925 describes bridged Cp-Flu metallocene complexes wherein the C-based bridge is substituted by a terminally unsaturated hydrocarbyl substituent and by an aryl group and the Flu ligand is preferably unsubstituted. The complexes were used together with an aluminoxane cocatalyst or aluminium alkyl compound as cocatalyst in relative low temperature bulk or slurry polymerization.

10

Several researchers (literatures 1 to 5) studied the effect of ligand structure on ethylene copolymerization with various Cp-Flu metallocenes.

1. A. Yano, M. Sone, S. Hasegawa, M. Sato, A. Akimoto, *Macromol. Chem. Phys.* **1999**, 200, 933.
- 15 2. A. Yano, S. Hasegawa, T. Kaneko, M. Sone, M. Sato, A. Akimoto, *Macromol. Chem. Phys.* **1999**, 200, 1542.
3. A. Yano, M. Sone, S. Yamada, S. Hasegawa, M. Sato, A. Akimoto, *Journal of Molecular Catalysis A: Chemical* **2000**, 156, 133.
4. S. Hasegawa, M. Sone, M. Tanabiki, M. Sato, A. Yano, *Journal of Polymer Science: Part A: Polymer Chemistry* **2000**, 38, 4641.
- 20 5. Q. Yang, M. D. Jensen, and M. P. McDaniel *Macromolecules* **2010**, 43, 8836.

In none of the above cited literatures and patents the simultaneous increase of molecular weight capability and comonomer incorporation ability of the catalyst system is mentioned.

- 25 Furthermore the above cited literatures and patents do not address the possible influence of a higher polymerization temperature on the catalyst performance of a hafnium complex with an alkenyl group on the bridge, in combination with a boron based activator.

However, for a process for producing ethylene copolymers to be efficient, it is important that
30 the catalyst system used has to fulfil a set of very strict requirements. Comonomer incorporation ability for higher comonomers (comonomer reactivity), catalyst molecular weight capability (lowest achievable melt index for a given polymer density, monomer concentration and polymerization temperature) and catalyst thermal stability must ensure the production of copolymers with density down to $\sim 0.850 \text{ g/cm}^3$ and a melt index MI_2 (190°C , 2.16kg) down to
35 $\sim 0.3 \text{ g/10 min}$ with high productivity (in order to get a maximum of polyethylene produced with as low amount of catalyst as possible). This requires a reactivity ratio C_{AO}/C_2 of at least 0.1 (AO = alpha-olefin).

Although a lot of work has been done in the field of metallocene catalysts, there still remains a need to find new catalyst systems being suitable for ethylene copolymerization, which are able to produce polymers with desired properties and which have improved balance of comonomer incorporation ability and molecular weight capability.


As a consequence, the inventors set out to develop a new catalyst system having superior polymerization behaviour than the above mentioned polymerization catalyst systems with respect to comonomer incorporation ability and molecular weight capability.

The present inventors have now found a new class of olefin polymerization catalyst systems, which is able to solve the problems disclosed above. In particular, the invention combines the use of special metallocene complexes with a boron based cocatalyst.

Summary of Invention

Thus, viewed from one aspect the invention relates to a catalyst system, whereby the catalyst system comprises

- (i) at least one metallocene complex of formula (I)



wherein

Mt1 is Hf,

X is a sigma-donor ligand,

R^1 , R^2 , R^3 are the same or different from each other and can be hydrogen or a saturated linear or branched C_1 - C_{10} alkyl, whereby the alkyl group can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, or R^1 and R^2 or R^2 and R^3 can form a ring having 4 to 6 C-atoms and 1 to 3 double bonds,

R^4 and R^5 are the same or different from each other and can be saturated linear or branched C_1 - C_{10} alkyl, C_5 - C_{10} aryl, C_6 - C_{20} alkylaryl or C_6 - C_{20} arylalkyl groups, which can optionally contain up to 2 heteroatoms belonging to groups 14-16,

n can be 1 to 5,

Ar is a C₆-C₂₀-aryl or -heteroaryl group, which can be unsubstituted or substituted by 1 to 5 linear or branched C₁- C₁₀ alkyl group(s),

- 5 and
(ii) a boron containing cocatalyst.

Viewed from another aspect the invention provides the use of such catalyst systems for producing ethylene copolymers in a high temperature solution process.

10

Viewed from a further aspect the invention provides a process for the preparation of an ethylene copolymer comprising polymerizing ethylene and a C₄₋₁₀ alpha-olefin comonomer in a high temperature solution process at a temperature greater than 100°C in the presence of a catalyst comprising:

- 15 (i) at least the metallocene complex of formula (I) as defined above and
(ii) a boron containing cocatalyst.

Viewed from yet a further aspect the invention provides an ethylene copolymer made by a process as hereinbefore defined.


20

Detailed Description of the Invention

Metallocene Complex

25 The single site metallocene complex, especially the complexes defined by the formula (I) specified in the present invention, are asymmetrical, meaning that the two ligands forming the metallocene complex are different.

The invention can be effected with a metallocene complex of formula (I)



30 wherein
Mt1 is Hf,

X is a sigma-donor ligand,

R^1 , R^2 , R^3 are the same or different from each other and can be hydrogen or a saturated linear or branched C_1 - C_{10} alkyl, whereby the alkyl group can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, or R^1 and R^2 or R^2 and R^3 can form a ring having 4 to 6 C-atoms and 1 to 3 double bonds,


5

R^4 and R^5 are the same or different from each other and can be saturated linear or branched C_1 - C_{10} alkyl, C_5 - C_{10} aryl, C_6 - C_{20} alkylaryl or C_6 - C_{20} arylalkyl groups, which can optionally contain up to 2 heteroatoms belonging to groups 14-16,

10 n can be 1 to 5,

Ar is a C_6 - C_{20} -aryl or -heteroaryl group, which can be unsubstituted or substituted by 1 to 5 linear or branched C_1 - C_{10} alkyl group(s).

15 The invention can also be effected with a mixture of the metallocene complex of formula (I) as defined above with a metallocene complex of formula (I')

20 wherein Mt2 is Zr, R^1 to R^5 and Ar are defined as for complex of formula (I), provided that the mixture contains more than 50% by moles of the complex of Formula I with Mt1 being Hf.25 In the formulas (I and I') each X, which may be the same or different, is a sigma-donor ligand, preferably a hydrogen atom, a halogen atom, a R^6 , OR^6 , OSO_2CF_3 , $OCOR^6$, SR^6 , NR^6_2 or PR^6_2 group, wherein R^6 is a linear or branched, cyclic or acyclic C_1 - C_{20} -alkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radical, optionally containing up to 2 heteroatoms belonging to groups 14-16, or is SiR^6_3 , $SiHR^6_2$ or SiH_2R^6 . R^6 is preferably C_{1-6} -alkyl, phenyl or benzyl group.

30 The term halogen includes fluoro, chloro, bromo and iodo groups, preferably chloro groups. The term heteroatoms belonging to groups 14-16 of the periodic table includes for example Si, N, O or S.

More preferably each X is independently a halogen atom or a R^6 or OR^6 group, whereby R^6 is a C_{1-6} -alkyl, phenyl or benzyl group.

Even more preferred X is C₁₋₄-alkyl or a benzyl group, most preferably X is methyl. Preferably both X groups are the same.

R¹, R², R³ are the same or different from each other and can be hydrogen or a saturated linear or branched C₁-C₁₀ alkyl, whereby the alkyl group can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, or R¹ and R² or R² and R³ can form a ring having 3 to 8 C-atoms and 1 to 3 double bonds.

Such rings include for example cyclopentenyl or phenyl.

The term heteroatoms belonging to groups 14-16 of the periodic table includes for example Si, N, O or S.

Preferably R¹, R², R³ are the same or different from each other and can be hydrogen, a saturated linear or branched C₁-C₆ alkyl group, whereby the alkyl group does not contain any heteroatoms belonging to groups 14-16, or R¹ is hydrogen and R² and R³ form a ring having 5 to 6 C-atoms and 1 to 3 double bonds.

More preferably R¹, R², R³ are the same or different from each other and can be hydrogen, a saturated linear or branched C₁-C₄ alkyl, whereby the alkyl group does not contain any heteroatoms belonging to groups 14-16 or R¹ is hydrogen and R² and R³ form a ring having 6 C-atoms and 3 double bonds. In this case the ring is a phenyl ring.

Most preferably R¹, R², R³ are the same and are all hydrogen or R¹ is hydrogen and R² and R³ form a ring having 6 C-atoms and 3 double bonds, i.e. a phenyl ring.

R⁴ and R⁵ are the same or different from each other and can be saturated linear or branched C₁-C₁₀ alkyl, C₅-C₁₀ aryl, C₆-C₂₀ alkylaryl or C₆-C₂₀ arylalkyl groups, which can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, like Si, N, O or S.

C₆-C₂₀ alkylaryl group is meant to be a C₆-C₁₀ aryl group which is substituted by one or more alkyl groups which may be the same or different, whereby the number of C-atoms in the alkyl group substituents is in a range which leads to C₆-C₂₀ alkylaryl groups.

Preferably R⁴ and R⁵ are the same or different from each other and can be a saturated linear or branched C₁-C₁₀ alkyl or C₆-C₁₀ aryl group, whereby the groups do not contain any heteroatoms belonging to groups 14-16 of the periodic table.

More preferably R^4 and R^5 are the same or different from each other and can be a saturated linear or branched C_1 - C_6 alkyl or phenyl, whereby the groups do not contain any heteroatoms belonging to groups 14-16 of the periodic table.

- 5 Most preferably R^4 and R^5 are the same and are a saturated linear or branched C_2 - C_6 alkyl.

n can be 1 to 5, preferably n is 2 to 4.

- 10 Ar is a C_6 - C_{20} -aryl or -heteroaryl group, which can be unsubstituted or substituted by 1 to 5 linear or branched C_1 - C_{10} alkyl group(s).

Preferably Ar is a C_6 - C_{10} -aryl or -heteroaryl group, which can be unsubstituted or substituted by one linear or branched C_1 - C_6 alkyl group.

- 15 More preferably Ar is an unsubstituted C_6 - C_{10} -aryl group, most preferably Ar is phenyl.

If a mixture of complexes of formula (I) and formula (I') is used it is preferred that the substituents R^1 to R^6 and Ar are the same for both complexes.

- 20 Specific examples of complexes of formula (I) are
 (phenyl)(but-3-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl,
 (phenyl)(but-3-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dibenzyl,
 25 (phenyl)(but-3-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride,
 (phenyl)(4-penten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluorenyl)hafnium dimethyl,
 (phenyl)(4-penten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluorenyl)hafnium
 30 dibenzyl,
 (phenyl)(4-penten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluorenyl)hafnium dichloride,
 (phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl,
 35 (phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dibenzyl,

(phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride,

(phenyl)(3-phenylpropyl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichlorid,

5 (phenyl)(3-phenylpropyl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl,

(phenyl)(3-phenylpropyl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dibenzyl,

and the corresponding zirconium analogues of formula (I').

10

Even more preferred are the dimethyl-complexes of formula (I) and (I').


Most preferable only complexes of formula (I) are used.

15 **Cocatalyst**

To form an active catalytic species it is normally necessary to employ a cocatalyst as is well known in the art. The present invention requires the use of a boron containing cocatalyst.

Boron based cocatalysts of interest include boron compounds containing a borate 3^+ ion, i.e.

20 borate compounds. These compounds generally contain an anion of formula:



where Z is an optionally substituted phenyl derivative, said substituent being a halo-C₁₋₆-alkyl or halo group. Preferred options are fluoro or trifluoromethyl. Most preferably, the phenyl group is perfluorinated.


25 Such ionic cocatalysts preferably contain a non-coordinating anion such as tetrakis(pentafluorophenyl)borate.

Suitable counterions are protonated amine or aniline derivatives, carbenium ions or phosphonium ions. These may have the general formula (III), (IV) or (V):

30 NQ_4^+ (III) or CQ_3^+ (IV) or PQ_4^+ (V)

where Q is independently H, C₁₋₆-alkyl, C₃₋₈-cycloalkyl, phenyl-C₁₋₆-alkylene- or optionally substituted phenyl (Ph). Optional substituents may be C₁₋₆-alkyl, halo or nitro. There may be one or more than one such substituent. Preferred substituted Ph groups include therefore para-substituted phenyl, preferably tolyl or dimethylphenyl.

35 If it is necessary that at least one Q group in (III) and (V) is H, then preferred compounds are those of formula:



Preferred phenyl-C₁₋₆-alkyl- groups include benzyl.

Suitable counterions therefore include: methylammonium, anilinium, dimethylammonium, diethylammonium, N-methylanilinium, diphenylammonium, N,N-dimethylanilinium, trimethylammonium, triethylammonium, tri-n-butylammonium, methyldiphenylammonium, p-bromo-N,N- dimethylanilinium or p-nitro-N,N-dimethylanilinium, especially dimethylammonium or N,N-dimethylanilinium. The use of pyridinium as an ion is a further option.

As Carbenium ion especially triphenylmethylcarbenium ("trityl") or tritolylcarbenium is used.

Phosphonium ions of interest include triphenylphosphonium, triethylphosphonium, diphenylphosphonium, tri(methylphenyl)phosphonium and tri(dimethylphenyl)phosphonium. A more preferred counterion is trityl (CPh₃⁺) or analogues thereof in which the Ph group is functionalised to carry one or more alkyl groups. Highly preferred borates of use in the invention therefore comprise the tetrakis(pentafluorophenyl)borate ion.

Preferred ionic compounds which can be used according to the present invention include:

tributylammoniumtetra(pentafluorophenyl)borate,

tributylammoniumtetra(trifluoromethylphenyl)borate,

tributylammoniumtetra-(4-fluorophenyl)borate,

N,N-dimethylcyclohexylammoniumtetrakis-(pentafluorophenyl)borate,

N,N-dimethylbenzylammoniumtetrakis(pentafluorophenyl)borate,

N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate,

N,N- di(propyl)ammoniumtetrakis(pentafluorophenyl)borate,

di(cyclohexyl)ammoniumtetrakis(pentafluorophenyl)borate,

triphenylcarbeniumtetrakis(pentafluorophenyl)borate,

More preferred borates are triphenylcarbeniumtetrakis(pentafluorophenyl) borate,

N,N- dimethylcyclohexylammoniumtetrakis(pentafluorophenyl)borate,

N,N- dimethylbenzylammoniumtetrakis(pentafluorophenyl)borate or

N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate.

Even more preferred borates are triphenylcarbeniumtetrakis(pentafluorophenyl) borate and

N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate.

N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate is most preferred.

Suitable amounts of cocatalyst will be well known to the skilled man.

It is further possible to add an aluminium alkyl compound. Suitable aluminium alkyl compounds are compounds of the formula (IX) AlR_3 with R being a linear or branched C_2 - C_8 -alkyl group.

Preferred aluminium alkyl compounds are triethylaluminium, tri-isobutylaluminium, tri-isohexylaluminium, tri-n-octylaluminium and tri-isooctylaluminium.

As is known to any art skilled person, the Cp-Flu complexes need to be the alkylated derivatives (e.g. X_2 is dimethyl) in order to be able to react with the boron containing cocatalyst. Thus if the complexes are originally the di-halo derivatives or other non-alkyl derivatives, they need to be pre-alkylated by reaction with an alkylating organometallic compound such as Li-alkyls, Mg-alkyls or aluminium-alkyls. Pre-alkylation procedures are well known in the art.

The molar ratio of boron to the metal ion of the metallocene may be in the range 0.5:1 to 10:1 mol/mol, preferably 1:1 to 10:1, especially 1:1 to 5:1 mol/mol.

Even more preferred is a molar ratio of boron to the metal ion of the metallocene from 1:1 to less than 2:1 mol/mol, e.g. from 1:1 to 1.8:1 or 1:1 to 1.5:1.

The metallocene complex of the present invention is preferably used in combination with the cocatalyst(s) as a catalyst system for the polymerization of ethylene and C_{4-10} alpha-olefin comonomer in a high temperature solution polymerization process.

The catalyst system of the invention may be used as a homogeneous catalyst or heterogeneous catalyst, preferably as homogeneous catalyst system.

Homogeneous or non-supported catalyst systems, suitable for the present invention can be prepared in solution, for example in an hydrocarbon solvent like hexane, cyclohexane, heptane, light naphta or toluene, by contacting the metallocene of formula (I) or a mixture of metallocene of formula (I) and (I') (as a solid or as a solution) with the boron containing cocatalyst(s), for example a borane or a borate salt as slurry in a hydrocarbon diluent or previously dissolved in an aromatic solvent, or preferably can be formed by sequentially adding the catalyst components directly into the polymerization reactor.

Polymer

The polymer to be produced using the catalyst system of the invention is a copolymer of ethylene and a C_{4-10} alpha-olefin comonomer, like 1-butene, 1-hexene, 4-methyl-1-pentene, 1-octene etc. Preferably 1-butene, 1-hexene or 1-octene and more preferably 1-octene is used as comonomer.

The comonomer content in such a polymer may be up to 45 wt%, preferably between 1 to 40 wt%, more preferably 1.5 to 35 wt% and even more preferably 2 to 25 wt%.

5 The density (measured according to ISO 1183-187) of the polymers is in the range of 0.850 g/cm³ to below 0.920 g/cm³, preferably in the range of 0.850 g/cm³ to 0.915 g/cm³ and more preferably in the range of 0.850 g/cm³ to 0.910 g/cm³.

Mw/Mn value of the polymers of the invention is less than 5, e.g. in the range of 2.0 to 4.5.

10 The melting points (measured with DSC according to ISO 11357-3:1999) of the polymers to be produced are below 130°C, preferably below 120°C, more preferably below 110°C and most preferably below 100°C.

Polymerization

15 The catalyst system of the present invention is preferably used to produce the above defined ethylene copolymers in a high temperature solution polymerization process at temperatures higher than 100°C.

20 In view of this invention such process is essentially based on polymerizing the monomer and a suitable comonomer in a hydrocarbon solvent, being liquid under the polymerization conditions and in which the resulting polymer is soluble. The polymerization is carried out at a temperature above the melting point of the polymer, as a result of which a polymer solution is obtained. This solution is flashed in order to separate the polymer from the unreacted monomer and the solvent. The solvent is then recovered and recycled in the process.

25 A solution polymerization process is known for its short reactor residence times (compared to Gas-phase or slurry processes) allowing thus, very fast grade transitions and significant flexibility in producing a wide product range in a short production cycle.

30 According to the present invention the used solution polymerization process is a high temperature solution polymerization process, using a polymerization temperature of higher than 100°C. Preferably the polymerization temperature is at least 110°C, more preferably at least 150°C. The polymerization temperature can be up to 250°C.

35 The pressure in the reactor depends on the temperature, on one hand, and the type and the amount of the comonomer, on the other hand. The pressure is suitably from 50 to 300 bar, preferably from 60 to 250 bar and more preferably from 70 to 200 bar.

The hydrocarbon solvent used is preferably a C₅₋₁₂ hydrocarbon which may be unsubstituted or substituted by C₁₋₄ alkyl groups, such as pentane, methyl pentane, hexane, heptane, octane, cyclohexane, methylcyclohexane and hydrogenated naphtha. More preferably unsubstituted C₆₋₁₀-hydrocarbon solvents are used.

5

Advantage

The new catalyst systems, comprising component (i) and (ii) can be advantageously used for ethylene copolymerization in high temperature solution polymerization process.

10 The catalyst systems according to the present invention show improved balance of comonomer incorporation ability and molecular weight capability, if used for ethylene copolymerization in high temperature solution polymerization process.

The catalyst systems according to the present invention show a reactivity ratio C_{AO}/C_2 of at least 0.1 (AO = C₄₋₁₀ alpha-olefin comonomer) in a high temperature solution polymerization process.

15

Applications

The polymers made by the catalyst system of the invention are useful in all kind of end articles such as pipes, films (cast or blown films), fibers, moulded articles (e.g. injection moulded, blow moulded, rotomoulded articles), extrusion coatings and so on.

20

The invention will now be illustrated by reference to the following non-limiting examples

Methods

DSC

Temperature modulated DSC experiments were performed in a TA Instruments Q2000 DSC operated in modulated mode and calibrated with indium, tin and zinc according to ISO 11357-1. Circa 5 mg of the sample were placed in an aluminium pan. The temperature was initially raised to 180°C and afterwards lowered to -88°C at 10°C/min as in standard DSC. Afterwards the temperature was raised by a temperature modulated scan with heating rate of 2°C/min modulated of 0.32°C every 60 seconds. The glass transition temperature was measured from the reversible heat flow thermogram as the inversion point at transition.

When the polymer composition has been estimated by Tg(DSC), the following correlation has been used: $C8(wt\%) = (Tg(^{\circ}C) + 19.16) / -1.059$

Zr and Hf determination (ICP-method)

The elementary analysis of a catalyst was performed by taking a solid sample of mass, M, cooling over dry ice. Samples were diluted up to a known volume, V, by dissolving in nitric acid (HNO₃, 65 %, 5 % of V) and freshly deionised (DI) water (5 % of V). The solution was then added to hydrofluoric acid (HF, 40 %, 3 % of V), diluted with DI water up to the final volume, V, and left to stabilise for two hours.

The analysis was run at room temperature using a Thermo Elemental iCAP 6300 Inductively Coupled Plasma – Optical Emission Spectrometer (ICP-OES) which was calibrated using a blank (a solution of 5 % HNO₃, 3 % HF in DI water), and 6 standards of 0.5 ppm, 1 ppm, 10 ppm, 50 ppm, 100 ppm and 300 ppm of Al, with 0.5 ppm, 1 ppm, 5 ppm, 20 ppm, 50 ppm and 100 ppm of Hf and Zr in solutions of 5 % HNO₃, 3 % HF in DI water.

Immediately before analysis the calibration is 'resloped' using the blank and 100 ppm Al, 50 ppm Hf, Zr standard, a quality control sample (20 ppm Al, 5 ppm Hf, Zr in a solution of 5 % HNO₃, 3 % HF in DI water) is run to confirm the reslope. The QC sample is also run after every 5th sample and at the end of a scheduled analysis set.

The content of hafnium was monitored using the 282.022 nm and 339.980 nm lines and the content for zirconium using 339.198 nm line. The content of aluminium was monitored via the 167.079 nm line, when Al concentration in ICP sample was between 0-10 ppm (calibrated only to 100 ppm) and via the 396.152 nm line for Al concentrations above 10 ppm.

The reported values are an average of three successive aliquots taken from the same sample and are related back to the original catalyst by inputting the original mass of sample and the dilution volume into the software.

Quantification of comonomer content by NMR spectroscopy

Quantitative nuclear-magnetic resonance (NMR) spectroscopy was used to quantify the comonomer content of the polymers.

Quantitative $^{13}\text{C}\{^1\text{H}\}$ NMR spectra recorded in the molten-state using a Bruker Advance III 500 NMR spectrometer operating at 500.13 and 125.76 MHz for ^1H and ^{13}C respectively. All spectra were recorded using a ^{13}C optimised 7 mm magic-angle spinning (MAS) probe-head at 150°C using nitrogen gas for all pneumatics. Approximately 200 mg of material was packed into a 7 mm outer diameter zirconia MAS rotor and spun at 4 kHz. This setup was chosen primarily for the high sensitivity needed for rapid identification and accurate quantification.^{[1],[2],[3],[4]} Standard single-pulse excitation was employed utilising the transient NOE at short recycle delays of 3s^{[5],[1]} and the RS-HEPT decoupling scheme.^{[6],[7]} A total of 1024 (1k) transients were acquired per spectrum. This setup was chosen due to its high sensitivity towards low comonomer contents.

Quantitative $^{13}\text{C}\{^1\text{H}\}$ NMR spectra were processed, integrated and quantitative properties determined using custom spectral analysis automation programs. All chemical shifts are internally referenced to the bulk methylene signal (δ^+) at 30.00 ppm.^[8]

Characteristic signals corresponding to the incorporation of 1-octene were observed^{[8],[9],[10],[11],[12]} and all comonomer contents calculated with respect to all other monomers present in the polymer.

Characteristic signals resulting from isolated 1-octene incorporation i.e. EEOEE comonomer sequences, were observed. Isolated 1-octene incorporation was quantified using the integral of the signal at 38.32 ppm. This integral is assigned to the unresolved signals corresponding to both $\ast\text{B6}$ and $\ast\beta\text{B6B6}$ sites of isolated (EEOEE) and isolated double non-consecutive (EEOEEOEE) 1-octene sequences respectively. To compensate for the influence of the two $\ast\beta\text{B6B6}$ sites the integral of the $\beta\beta\text{B6B6}$ site at 24.7 ppm is used:

$$O = I_{\ast\text{B6}+\ast\beta\text{B6B6}} - 2 \cdot I_{\beta\beta\text{B6B6}}$$

Characteristic signals resulting from consecutive 1-octene incorporation, i.e. EEOOEE comonomer sequences, were also observed. Such consecutive 1-octene incorporation was quantified using the integral of the signal at 40.48 ppm assigned to the $\alpha\alpha\text{B6B6}$ sites accounting for the number of reporting sites per comonomer:

$$OO = 2 \cdot I_{\alpha\alpha\text{B6B6}}$$

Characteristic signals resulting from isolated non-consecutive 1-octene incorporation, i.e. EEOEEOEE comonomer sequences, were also observed. Such isolated non-consecutive 1-octene incorporation was quantified using the integral of the signal at 24.7 ppm assigned to the $\beta\beta\text{B6B6}$ sites accounting for the number of reporting sites per comonomer:

$$OEO = 2 * I_{\beta\beta B6B6}$$

Characteristic signals resulting from isolated triple-consecutive 1-octene incorporation, i.e. EEOOOEE comonomer sequences, were also observed. Such isolated triple-consecutive 1-octene incorporation was quantified using the integral of the signal at 41.2 ppm assigned to the $\alpha\alpha\gamma B6B6B6$ sites accounting for the number of reporting sites per comonomer:

$$OOO = 3/2 * I_{\alpha\alpha\gamma B6B6B6}$$

With no other signals indicative of other comonomer sequences observed the total 1-octene comonomer content was calculated based solely on the amount of isolated (EEOEE), isolated double-consecutive (EEOOOEE), isolated non-consecutive (EEOEOEE) and isolated triple-consecutive (EEOOOEE) 1-octene comonomer sequences:

$$O_{total} = O + OO + OEO + OOO$$

Characteristic signals resulting from saturated end-groups were observed. Such saturated end-groups were quantified using the average integral of the two resolved signals at 22.84 and 32.23 ppm. The 22.84 ppm integral is assigned to the unresolved signals corresponding to both 2B6 and 2S sites of 1-octene and the saturated chain end respectively. The 32.23 ppm integral is assigned to the unresolved signals corresponding to both 3B6 and 3S sites of 1-octene and the saturated chain end respectively. To compensate for the influence of the 2B6 and 3B6 1-octene sites the total 1-octene content is used:

$$S = (1/2) * (I_{2S+2B6} + I_{3S+3B6} - 2 * O_{total})$$

The ethylene comonomer content was quantified using the integral of the bulk methylene (bulk) signals at 30.00 ppm. This integral included the γ and 4B6 sites from 1-octene as well as the δ^+ sites. The total ethylene comonomer content was calculated based on the bulk integral and compensating for the observed 1-octene sequences and end-groups:

$$E_{total} = (1/2) * [I_{bulk} + 2 * O + 1 * OO + 3 * OEO + 0 * OOO + 3 * S]$$

It should be noted that compensation of the bulk integral for the presence of isolated triple-incorporation (EEOOOEE) 1-octene sequences is not required as the number of under and over accounted ethylene units is equal.

The total mole fraction of 1-octene in the polymer was then calculated as:

$$fO = (O_{total} / (E_{total} + O_{total}))$$

The total comonomer incorporation of 1-octene in weight percent was calculated from the mole fraction in the standard manner:

$$O [wt\%] = 100 * (fO * 112.21) / ((fO * 112.21) + ((1-fO) * 28.05))$$

- [1] Klimke, K., Parkinson, M., Piel, C., Kaminsky, W., Spiess, H.W., Wilhelm, M., *Macromol. Chem. Phys.* 2006;207:382.
- [2] Parkinson, M., Klimke, K., Spiess, H.W., Wilhelm, M., *Macromol. Chem. Phys.* 2007;208:2128.
- 5 [3] Castignolles, P., Graf, R., Parkinson, M., Wilhelm, M., Gaborieau, M., *Polymer* 50 (2009) 2373
- [4] *NMR Spectroscopy of Polymers: Innovative Strategies for Complex Macromolecules*, Chapter 24, 401 (2011)
- [5] Pollard, M., Klimke, K., Graf, R., Spiess, H.W., Wilhelm, M., Sperber, O., Piel, C., Kaminsky, W., *Macromolecules* 2004;37:813.
- 10 [6] Filip, X., Tripon, C., Filip, C., *J. Mag. Resn.* 2005, 176, 239
- [7] Griffin, J.M., Tripon, C., Samoson, A., Filip, C., and Brown, S.P., *Mag. Res. in Chem.* 2007 45, S1, S198
- [8] J. Randall, *Macromol. Sci., Rev. Macromol. Chem. Phys.* 1989, C29, 201.
- 15 [9] Liu, W., Rinaldi, P., McIntosh, L., Quirk, P., *Macromolecules* 2001, 34, 4757
- [10] Qiu, X., Redwine, D., Gobbi, G., Nuamthanom, A., Rinaldi, P., *Macromolecules* 2007, 40, 6879
- [11] Busico, V., Carbonniere, P., Cipullo, R., Pellecchia, R., Severn, J., Talarico, G., *Macromol. Rapid Commun.* 2007, 28, 1128
- 20 [12] Zhou, Z., Kuemmerle, R., Qiu, X., Redwine, D., Cong, R., Taha, A., Baugh, D. Winniford, B., *J. Mag. Reson.* 187 (2007) 225

HT-SEC: Molecular weight averages, molecular weight distribution, and polydispersity index (M_n , M_w , M_w/M_n)

- 25 Molecular weight averages (M_w , M_n), Molecular weight distribution (MWD) and its broadness, described by polydispersity index, $PDI = M_w/M_n$ (wherein M_n is the number average molecular weight and M_w is the weight average molecular weight) of the polymer were determined by high temperature size exclusion chromatography (HT-SEC) on a Polymer Laboratories PLXT-20 Rapid GPC Polymer Analysis System (including pump, refractive index detector and
- 30 viscosity detector) at 160°C with 3 PLgel Olexis (300 × 7.5 mm, Polymer Laboratories) columns in series. 1,2,4-Trichlorobenzene containing butylated hydroxytoluene (0.5 g/L) and Irganox 1010 (20 mg/L) was used as eluent at a flow rate of 1.0 mL/min. The molecular weights were calculated with respect to polyethylene standards (Polymer Laboratories, $M_p = 5.310$ up to $M_p = 1.510.000$ g/mol). A Polymer Laboratories PL XT-220 robotic sample handling system was
- 35 used as autosampler. The concentration of the samples was between 2 and 4 mg polymer / mL of TCB.

Determination of the relative comonomer reactivity ratio R

- 40 Ethylene concentration in liquid phase can be considered constant since total pressure is kept constant by feeding ethylene during polymerization. The C_{AO}/C_2 ratio, e.g. the C_8/C_2 ratio in solution at the end of the polymerization is calculated by subtracting the amount of comonomer,

e.g. octene incorporated in the polymer from the measured composition of the latter (%wt comonomer, e.g. 1-octene)

The reactivity ratio, R , for each catalyst is then calculated as:

$$R = [(C_8/C_2)_{\text{pol}}] / [(C_8/C_2)_{\text{average in liquid phase}}]$$

5 where $(C_8/C_2)_{\text{average in liquid phase}}$ is calculated as $((C_8/C_2)_{\text{final}} + (C_8/C_2)_{\text{feed}})/2$

Chemicals

Triphenylcarbeniumtetrakis(pentafluorophenyl)borate (TB) (alternative name trityl tetrakis-(pentafluorophenyl)borate) (CAS 136040-19-2) was purchased from Acros (tritylBF₂₀).

10 N,N-Dimethylanilinium Tetrakis(pentafluorophenyl)borate (AB) (CAS 118612-00-3) was purchased from Boulder.

15 1-octene as co-monomer (99%, Sigma Aldrich) was dried over molecular sieves and degassed with nitrogen before use.

Isopar-E (from ExxonMobil, iso alkanes C7-10, CAS No: 90622-56-3,) purchased from Brenntag was purified passing it subsequently through two columns containing (i) BTS-catalyst (Cu), to remove oxygen, and (ii) molecular sieves 3Å as drying agent and Selexsorb CD (BASF) to remove polar impurities.

Chemicals used for catalyst complex synthesis:

HfCl₄, <1(mol)% Zr (Strem Chemicals), 9H-fluorene (Acros), 2.5 M ⁿBuLi in hexanes (Chemetall), KH (Aldrich), 1-bromobutane (Acros), benzophenone (Acros), 1,2-dibromoethane (Acros), chlorotrimethylsilane (Acros), 2-bromo-2-methylpropionyl bromide (Acros), ethyl benzoylacetate (Aldrich), allyl bromide (Acros), 4-bromobut-1-ene (Aldrich), 1,4-diphenylbutan-1-one (ABCR), TsOH (Aldrich), triethylamine (Acros), methyl iodide (Merck), THF (Merck), hexane (Merck), ethyl acetate (Merck), diethyl ether (Merck), dichloromethane (Merck), toluene (Merck), methanol (Merck), dimethylsulfoxide (Merck), silica gel 60, 40-63 μm (Merck), 8 M HCl (Merck), Na₂SO₄ (Akzo Nobel), K₂CO₃ (Merck), AlCl₃ (Merck), NaBH₄ (Aldrich), Na₂CO₃ (Merck), CuCN (Merck), NaHCO₃ (Merck), bromine (Merck) and KOH (Merck) were used as received.

35 Toluene and hexane for organometallic synthesis as well as CDCl₃ (Deutero GmbH) for NMR measurements of air and moisture sensitive compounds were dried over molecular sieves 4A (Acros).

THF and ether for organometallic synthesis were distilled over benzophenone ketyl.

Cyclopentadienyllithium was prepared from cyclopentadiene obtained from dicyclopentadiene (Acros) and butyllithium in hexanes according to a literature procedure [Den Besten, R.; Harderm S.; Brandsma, L. *J. Organomet. Chem.* **1990**, 385, 153].

5 Cyclopentadienylmagnesium bromide was prepared from cyclopentadiene obtained from dicyclopentadiene (Acros) and methylmagnesium bromide in ether (Aldrich) as described in [Stille, J. R.; Grubbs, R. H. *J. Org. Chem* **1989**, 54, 434].

1-Phenylhept-6-en-1-one was prepared from 5-bromo-1-pentene (Aldrich), acetophenone (Merck), N,N-dimethylhydrazine (Aldrich) and lithium diisopropylamide (Aldrich) according to the literature procedure [Motiwala, H. F.; Gülgeze, B., Aubé, J. *J. Org. Chem.* **2012**, 77, 7005].


10 2,7-Di-*tert*-butylfluorene was obtained from 9*H*-fluorene and 2,6-di-*tert*-butyl-*p*-cresole (Aldrich) as described in [Kajigaeshi, S.; Kadowaki, T.; Nishida, A.; Fujisaki, S.; Noguchi, M. *Synthesis* **1984**, 335]

Catalyst Preparation Examples

15 **Complex 1 (C-1): (Phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dimethyl**

Step 1:

1-Phenyl-1-(hex-5-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane




20 To a solution of 10.59 g (38.04 mmol) of 2,7-di-*tert*-butylfluorene in 125 ml of THF cooled to -78°C , 15.2 ml (36.5 mmol) of 2.5 M $n\text{-BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting light-orange solution was cooled to -30°C , and a solution of 9.46 g (40.03 mmol, 1.05 eq) of 6-phenyl-6-(hex-5-en-1-yl)fulvene in 125 ml of THF was added in one portion. After stirring overnight at room temperature the dark-
 25 red reaction mixture was cooled in an ice-bath and then quenched with 10% HCl to a slightly acidic pH. The resulting orange mixture was diluted with 400 ml of water and extracted with 300 ml of diethyl ether. The organic layer was separated, and the aqueous one was extracted with 150 ml of dichloromethane. The combined organic extract was dried over Na_2SO_4 and filtered through a pad of silica gel 60 (40-63 μm) which was additionally washed by 2x50 ml of

dichloromethane. Removal of the solvents under vacuum gave an orange oil which was dissolved in 125 ml of n-hexane. Crystals precipitated from this solution overnight at -30°C were collected and dried in vacuum. This procedure gave 14.61 g (75%) of a slightly yellow solid of the title product as a mixture of isomers.

5 Anal. calc. for $\text{C}_{39}\text{H}_{46}$: C, 90.99; H, 9.01. Found: C, 91.14; H, 9.07.

^1H NMR (CDCl_3): δ 7.57-6.95 (m, 11H), 6.34-5.59 (m, 4H), 4.98-4.70 (m, 3H), 2.93-2.55 (m, 2H), 2.49-2.15 (m, 2H), 2.04-1.80 (m, 2H), 1.46-0.91 (m, 22H).

Step 2: (Phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-tert-butylfluoren-9-yl)
10 hafnium dichloride




To a solution of 14.61 g (28.38 mmol) of 1-phenyl-1-(hex-5-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane in 300 ml of ether, cooled to -50°C , 22.7 ml (56.8 mmol) of 2.5 M $n\text{-BuLi}$ in hexanes was added in one portion. This mixture was stirred for 5 h at room temperature. The resulting reddish solution was cooled to -50°C , and 9.09 g (28.38 mmol) of HfCl_4 was added. The formed mixture was stirred for 24 h at room temperature and then evaporated to dryness. The residue was stirred with 200 ml of warm toluene, and the formed suspension was filtered through a glass frit (G4). The filtrate was evaporated to ca. 30 ml, and 70 ml of n-hexane was added. Yellow crystalline solid precipitated overnight at -30°C was collected and dried in vacuum. This procedure gave 12.9 g (60%) of the target complex.

Anal. calc. for $\text{C}_{39}\text{H}_{44}\text{Cl}_2\text{Hf}$: C, 61.46; H, 5.82. Found: C, 61.59; H, 6.00.

^1H NMR (CDCl_3): δ 8.01 (d, $J = 9.1$ Hz, 1H), 7.96 (d, $J = 8.9$ Hz, 1H), 7.83 (dm, $J = 7.7$ Hz, 1H), 7.69 (m, 1H), 7.66-7.59 (m, 2H), 7.59-7.52 (m, 1H), 7.5 (dd, $J = 8.9$ Hz, $J = 1.4$ Hz, 1H), 7.45-7.38 (m, 2H), 6.35-6.31 (m, 1H), 6.22-6.18 (m, 1H), 6.13 (s, 1H), 5.81-5.69 (m, 2H), 5.55-5.51 (m, 1H), 4.94 (dm, $J = 17.2$ Hz, 1H), 4.89 (dm, $J = 10.2$ Hz, 1H), 3.13-2.99 (m, 1H), 2.82-2.67 (m, 1H), 2.15-1.95 (m, 2H), 1.66-1.45 (m, 4H), 1.40 (s, 9H), 0.99 (s, 9H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 152.19, 149.61, 143.26, 138.38, 130.52, 128.51, 128.33, 127.24, 127.08, 124.22, 124.18, 124.02, 123.52, 122.63, 120.25, 119.87, 119.67, 118.84, 117.81, 116.62, 114.65, 114.52, 99.66, 77.77, 53.68, 41.16, 35.44, 34.87, 33.80, 31.13, 30.53, 29.45, 23.64.

Step 3: (Phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl



5 To a solution of 7.1 g (9.32 mmol) of [1-(η⁵-cyclopentadien-1-yl)-1-(η⁵-2,7-di-*tert*-butylfluorenyl)-1-(hex-5-en-1-yl)-1-phenylmethane]hafnium dichloride in a mixture of 90 ml of toluene and 50 ml of ether 13.0 ml (27.43 mmol) of 2.11 M MeMgBr in ether was added. The resulting mixture was refluxed for 30 min and then evaporated to ca. 40 ml. The obtained solution was heated to 80-90°C and filtered while hot through glass frit (G4) to remove insoluble

10 magnesium salts. The filter cake was additionally washed with 2x20 ml of toluene. The combined filtrate was evaporated to ca. 20 ml. This solution was heated again to 80-90°C and filtered while hot through glass frit (G4). The mother liquor was evaporated to dryness, and the residue was dissolved in 30 ml of hexane. Yellow powder precipitated from this solution

15 (phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dimethyl. In the same way, but using smaller volumes of hexane (ca. 20 ml and 5 ml), another two portions (1.18 g and 0.57 g) of the desired complex were obtained. So, the total yield of (phenyl)(5-hexen-1-yl)methylene (cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dimethyl was 4.95 g (74%).


20 Anal. calc. for C₄₁H₅₀Hf: C, 68.27; H, 6.99. Found: C, 68.44; H, 7.21.

¹H NMR (CDCl₃): δ 8.08 (d, *J* = 8.9 Hz, 1H), 7.99 (d, *J* = 8.6 Hz, 1H), 7.81 (dm, *J* = 7.8 Hz, 1H), 7.62-7.57 (m, 2H), 7.51 (dd, *J* = 8.9 Hz, *J* = 1.2 Hz, 1H), 7.50-7.44 (m, 1H), 7.39-7.30 (m, 3H), 6.28-6.21 (m, 1H), 6.15-6.08 (m, 1H), 6.03 (s, 1H), 5.74 (ddt, *J* = 17.1 Hz, *J* = 10.3 Hz, *J* = 6.6 Hz, 1H), 5.64-5.59 (m, 1H), 5.35-5.28 (m, 1H), 4.92 (dm, *J* = 17.2 Hz, 1H), 4.87 (dm, *J* = 10.0 Hz, 1H), 2.94-2.79 (m, 1H), 2.63-2.48 (m, 1H), 2.11-1.92 (m, 2H), 1.60-1.41 (m, 4H), 1.38 (s, 9H), 0.97 (s, 9H), -1.76 (s, 3H), -1.90 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 150.29, 147.84, 144.27, 138.66, 130.71, 128.09, 127.97, 127.25, 126.67, 124.53, 123.78, 122.91, 122.76, 121.05, 120.67, 119.15, 117.55, 116.38, 115.88, 114.43, 112.91, 111.14, 109.56, 100.99, 100.60, 76.51, 53.51, 41.07, 38.18, 37.42, 35.36, 34.77, 33.88, 31.38, 30.77, 29.61, 23.79.

Complex 2 (C-2): (Phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-tert-butylfluoren-9-yl) hafnium dimethyl


Step 1: 1-Phenylpent-4-en-1-one

Method A



To a solution of sodium ethoxide, obtained from 7.9 g (343.6 mmol) of sodium metal and 235 ml of dry ethanol, 67.27 g (350 mmol) of ethyl benzoyl acetate was added. The formed mixture was stirred for 15 min, and then 42.37 g (350 mmol) of allyl bromide was added dropwise at such a rate to maintain a temperature below 40°C. The resulting mixture was refluxed for 3 h and then cooled to room temperature. A solution of 37 g of KOH in 120 ml of water was added. The resulting light-orange homogeneous mixture was refluxed for 5 h leading eventually to biphasic system. After cooling to room temperature, the reaction mixture was carefully treated with 4 M HCl to slightly acidic pH (Caution! Strong gas evolution!). The resulting mixture was diluted with 700 ml of water and then extracted with 3x200 ml of ether. The combined ethereal extract was washed with a solution of 30 g of KOH in 300 ml of water, dried over K_2CO_3 , passed through a short pad of silica gel 60 (40-63 μm), and then evaporated to dryness. The residue was distilled in vacuum to give 41.58 g (74%; purity ca. 95%) of 1-phenylpent-4-en-1-one, b.p. 73-81°C/6 mm Hg.

Method B




To a solution of lithium diisopropylamide (prepared from a solution of 27.83 g (275.0 mmol) of diisopropylamine in 400 ml of THF and 110 ml (275.0 mmol) of 2.5 M $n\text{-BuLi}$ in hexanes at -78°C) a solution of 40.56 g (250 mmol) of acetophenone N,N-dimethylhydrazone in 60 ml of THF was added over 30 min at 0°C. This mixture was stirred for 4 h at 0°C, then cooled to -78°C, and a solution of 36.3 g (300 mmol) of 3-bromoprop-1-ene in 45 ml of THF was added over 30 min. The reaction was slowly warmed to room temperature and then stirred overnight at this temperature. The resulting solution was evaporated to dryness in vacuum, and the residue was diluted with 400 ml of ether. This solution cooled to 0°C (an ice-bath) was treated with an ice-cold solution of 120 ml of 96% sulfuric acid in 900 ml of water for 30 min. After

stirring this mixture for 30 min at room temperature, the organic layer was separated, and the aqueous one was extracted with 2x200 ml of ether. The combined organic extract was washed with 2x200 ml of water, dried over Na₂SO₄ and concentrated under a reduced pressure. The product was isolated by flash-chromatography on silica gel 60 (40-63 µm; eluent: hexane-ethyl acetate= 97:3, vol.). This procedure gave 40.5 g (ca. 100%) of 1-phenylpent-4-en-1-one as a colorless liquid.

Anal. calc. for C₁₁H₁₂O: C, 82.46; H, 7.55. Found: C, 82.70; H, 7.63.

¹H NMR (CDCl₃): δ 7.99-7.91 (m, 2H), 7.56-7.51 (m, 1H), 7.47-7.40 (m, 2H), 5.90 (ddt, *J* = 17.0 Hz, *J* = 10.2 Hz, *J* = 6.5 Hz, 1H), 5.08 (ddt, *J* = 17.0 Hz, *J* = 1.6 Hz, *J* = 1.6 Hz, 1H), 5.00 (ddt, *J* = 10.2 Hz, *J* = 1.6 Hz, *J* = 1.6 Hz, 1H), 3.05 (t, *J* = 7.4 Hz, 2H), 2.53-2.45 (m, 2H). ¹³C{¹H} NMR (CDCl₃): δ 199.15, 137.16, 136.81, 132.83, 128.43, 127.86, 115.12, 37.57, 27.99

Step 2: 6-Phenyl-6-(but-3-en-1-yl)fulvene



Method A

To a solution of sodium ethoxide obtained from 3.42 g (148.8 mmol) of sodium metal and 120 ml of dry ethanol, 23.7 g (147.9 mmol) of 1-phenylpent-4-en-1-one, obtained according to method A in step 1, was added. The formed mixture was cooled to 0°C, and then 25 ml of freshly cracked cyclopenta-1,3-diene was added dropwise over 40 min. The resulting mixture was stirred at room temperature for 4 h. The red reaction mixture was poured into 200 ml of water, and the formed mixture was extracted with 3x100 ml of n-hexane. The combined organic extract was dried over anhydrous K₂CO₃ and then evaporated to dryness to give a red oily liquid. Crude product was purified by flash chromatography on silica gel 60 (300 ml, 40-63 µm; eluent: hexane/EtOAc = 30/1, vol.) to give 29.17 g (93%, ca. 75% purity) of 6-phenyl-6-(but-3-en-1-yl)fulvene as a red oily liquid.

Method B

To a cooled to 0°C solution of 10.2 g (149.9 mmol) of sodium ethoxide in 100 ml of THF, 23.5 g (146.7 mmol) of 1-phenylpent-4-en-1-one, obtained according to method A in step 1, was added. Then, 25 ml of freshly cracked cyclopenta-1,3-diene was added dropwise over 40 min. The resulting mixture was stirred at room temperature for 4 h. To the dark-red reaction mixture 5 ml of water was added, and the resulting mixture was passed through a short pad of silica gel 60 (40-63 µm). The filtrate was dried over anhydrous K₂CO₃ and then evaporated to dryness to give a red oily liquid. Crude product was purified by flash chromatography on silica

gel 60 (300 ml, 40-63 μm ; eluent: hexane/ethyl acetate = 30/1, vol.) to give 29.78 g (95%, ca.75% purity) of 6-phenyl-6-(but-3-en-1-yl)fulvene as a red oily liquid.

Method C


To a solution of 41.0 g (255.9 mmol) of 1-phenylpent-4-en-1-one, obtained according to method B in step 1, in 100 ml of THF, cooled in an ice-bath, a solution of 55.0 g (324.9 mmol, 1.27 equiv.) of cyclopentadienyl magnesium bromide in 300 ml of THF was added dropwise. The resulting mixture was refluxed for 3 h, then stirred overnight at room temperature, finally, cooled in an ice-bath and quenched with 10% HCl to pH~5-6. This mixture was extracted with 4x250 ml of hexane, and the combined organic extract was dried over Na₂SO₄. Removal of the solvent under vacuum gave a dark-red oil. The product was isolated by flash-chromatography on silica gel 60 (40-63 μm ; eluent: hexane-ethyl acetate = 100:1, vol.). This procedure gave 26.98 g (51%, ca.95% purity) of 6-phenyl-6-(but-3-en-1-yl)fulvene as a red oily liquid.

Anal. calc. for C₁₆H₁₆: C, 92.26; H, 7.74. Found: C, 92.39; H, 7.88.


¹H NMR (CDCl₃): δ 7.40-7.30 (m, 5H), 6.62 (ddd, J = 5.3 Hz, J = 2.0 Hz, J = 1.5 Hz, 1H), 6.56 (ddd, J = 5.3 Hz, J = 2.0 Hz, J = 1.5 Hz, 1H), 6.47 (ddd, J = 5.3 Hz, J = 2.0 Hz, J = 1.5 Hz, 1H), 6.10 (ddd, J = 5.3 Hz, J = 2.0 Hz, J = 1.5 Hz, 1H), 5.76 (ddt, J = 17.0 Hz, J = 10.3 Hz, J = 6.6 Hz, 1H), 5.00-4.91 (m, 2H), 2.99 (t, J = 7.7 Hz, 2H), 2.20-2.12 (m, 2H).

Step 3: (Phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-tert-butylfluoren-9-yl)hafnium dichloride

Method A



To a solution of 14.07 g (50.53 mmol) of 2,7-di-*tert*-butylfluorene in 200 ml of THF cooled to -50°C , 20.2 ml (50.5 mmol) of 2.5 M $n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then cooled to -50°C , and a solution of 11.55 g (55.45 mmol) of 6-phenyl-6-(but-3-en-1-yl)fulvene, obtained according to method C in step 2, in 200 ml of THF was added in one portion. After stirring overnight at room temperature the formed dark-red reaction mixture was cooled in an ice-bath and then quenched with a solution of 5 ml of 12 M HCl in 200 ml of water to pH~5-6. The resulting yellow mixture was extracted with 400 ml of dichloromethane. The organic layer was separated, and the aqueous one was extracted with 150 ml of dichloromethane. The combined organic extract was dried over Na_2SO_4 and then filtered through a pad of silica gel 60 (40-63 μm) which was additionally washed by 2x50 ml of dichloromethane. Removal of the solvents under vacuum gave an orange oil which was dried in vacuo to afford 25.7 g of 1-phenyl-1-(but-3-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane which was further used without an additional purification. To a yellowish solution of 13.78 g (28.31 mmol) of 1-phenyl-1-(but-3-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane in 170 ml of ether cooled to -78°C , 22.7 ml (56.8 mmol) of 2.5 M $n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred for 5 h at room temperature. To the resulting orange suspension cooled to -50°C 9.07 g (28.32 mmol) of HfCl_4 was added. The formed mixture was stirred for 24 h at room temperature and then evaporated to dryness. The residue was stirred with 200 ml of warm toluene, and the formed suspension was filtered through a glass frit (G4). The filtrate was evaporated to ca. 20 ml, the orange solid precipitated from this solution was filtered off (G3), washed with 3x10 ml of a mixture of toluene and hexane (1:2, vol.), and then dried in vacuum. This procedure gave 8.7 g (42%) of (phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dichloride.

Method B

To a solution of 13.92 g (50.0 mmol) of 2,7-di-*tert*-butylfluorene in 200 ml of ether, cooled to -50°C , 20.6 ml (50.0 mmol) of 2.43 M $n\text{BuLi}$ in hexanes was added in one portion.

This mixture was stirred for 4 h at room temperature. The resulting orange solution was cooled to -50°C , and 11.09 g (53.2 mmol) of 6-phenyl-6-(but-3-en-1-yl)fulvene, obtained according to method C in step 2, was added in one portion. After stirring overnight at room temperature the orange reaction mixture was cooled to -50°C , and then 20.6 ml (50.0 mmol) of 2.43 M $n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred for 6 h at room temperature.


The resulting dark-red solution with a significant amount of brick red precipitate was cooled to -50°C , and 16.02 g (50.02 mmol) of HfCl_4 was added. The formed mixture was stirred for 24 h at room temperature. Orange precipitate was filtered, heated with 250 ml of toluene, filtered again from LiCl , and mother liquor was evaporated almost to dryness. 50 ml of *n*-hexane was added to the residue and the precipitated orange powder was filtered off (G3) and dried in vacuum. This procedure gave 16.7 g of (phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dichloride. The ethereal mother liquor (from the reaction mixture) was evaporated almost to dryness, and the residue was triturated with 25 ml of *n*-hexane. Orange precipitate was filtered off (G3) to give 3.5 g of the target complex. Thus, the total yield of (phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dichloride isolated in this synthesis was 20.2 g (55%).

Anal. calc. for $\text{C}_{37}\text{H}_{40}\text{Cl}_2\text{Hf}$: C, 60.54; H, 5.49. Found: C, 60.32; H, 5.66.

^1H NMR (CDCl_3): δ 8.02 (d, $J = 8.9$ Hz, 1H), 7.96 (d, $J = 8.9$ Hz, 1H), 7.85 (dm, $J = 7.6$ Hz, 1H), 7.69 (s, 1H), 7.66-7.61 (m, 2H), 7.61-7.54 (m, 1H), 7.51 (dd, $J = 8.9$ Hz, $J = 1.5$ Hz, 1H), 7.46-7.38 (m, 2H), 6.36-6.32 (m, 1H), 6.23-6.19 (m, 1H), 6.15 (s, 1H), 5.99-5.86 (m, 1H), 5.81-5.77 (m, 1H), 5.55-5.51 (m, 1H), 5.11 (dd, $J = 17.2$ Hz, $J = 1.5$ Hz, 1H), 5.06 (dd, $J = 10.3$ Hz, $J = 1.5$ Hz, 1H), 3.29-3.19 (m, 1H), 2.81-2.70 (m, 1H), 2.43-2.26 (m, 2H), 1.38 (s, 9H), 0.99 (s, 9H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 152.39, 149.63, 142.90, 137.61, 130.60, 128.68, 128.29, 127.40, 127.07, 124.33, 124.16, 124.05, 123.55, 122.49, 120.18, 119.86, 119.65, 118.84 (two

resonances), 117.77, 116.65, 115.23, 114.34, 99.61, 99.57, 77.31, 53.42, 39.89, 35.49, 34.87, 31.14, 30.52, 28.27.

Step 4: (Phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dimethyl



5

To a solution of 3.67 g (5.0 mmol) of (phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dichloride, obtained according to method A in step 3, in a mixture of 50 ml of toluene and 50 ml of ether 7.0 ml (14.77 mmol) of 2.11 M MeMgBr in ether was added. The resulting mixture was refluxed for 30 min and then evaporated to ca. 25 ml. The obtained solution was heated to 80-90°C, and the obtained suspension was filtered while hot through glass frit (G3) to remove insoluble magnesium salts. The filter cake was additionally washed with 2x20 ml of toluene. The combined filtrate was evaporated almost to dryness, and 20 ml of hexane was added to the residue. The resulting mixture was filtered once again through a glass frit (G4). The mother liquor was evaporated to dryness, and the residue was dissolved in 7 ml of hexane. Yellow powder precipitated from this solution overnight at -40°C was collected and dried in vacuum. This procedure gave 3.18 g (92%) of pure (phenyl)(3-buten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) hafnium dimethyl complex.

15

Anal. calc. for C₃₉H₄₆Hf: C, 67.57; H, 6.69. Found: C, 67.82; H, 6.85.

20


¹H NMR (CDCl₃): δ 8.08 (d, *J* = 8.9 Hz, 1H), 8.00 (d, *J* = 8.9 Hz, 1H), 7.83 (dm, *J* = 7.9 Hz, 1H), 7.63-7.56 (m, 2H), 7.53-7.45 (m, 2H), 7.39-7.31 (m, 3H), 6.28-6.22 (m, 1H), 6.14-6.10 (m, 1H), 6.05 (s, 1H), 5.95-5.83 (m, 1H), 5.67-5.62 (m, 1H), 5.34-5.29 (m, 1H), 5.07 (dd, *J* = 17.2 Hz, *J* = 1.5 Hz, 1H), 5.01 (dd, *J* = 10.2 Hz, *J* = 1.5 Hz, 1H), 3.12-2.98 (m, 1H), 2.62-2.49 (m, 1H), 2.33-2.15 (m, 2H), 1.37 (s, 9H), 0.98 (s, 9H), -1.76 (s, 3H), -1.90 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 150.44, 147.83, 143.87, 138.19, 130.77, 128.26, 127.92, 127.20, 126.82, 124.38, 123.76, 122.94, 122.66, 121.16, 120.70, 119.09, 117.45, 116.37, 115.88, 114.73, 112.91, 111.16, 109.34, 100.91, 100.51, 75.97, 53.23, 39.73, 38.29, 37.49, 35.39, 34.76, 31.39, 30.75, 28.39.

25

30

Complex 3 (C-3): (Phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-tert-butylfluoren-9-yl)hafnium dimethyl


Step 1: 1-Phenylhex-5-en-1-one



5 To a solution of sodium ethoxide, obtained from 5.75 g (0.25 mol) of sodium metal and 175 ml of dry ethanol, 48.05 g (0.25 mol) of ethyl benzoyl acetate was added. The formed mixture was stirred for 10 min, then 42.5 g (314.8 mmol) of 4-bromobut-1-ene was added, and the resulting mixture was refluxed for 5 h. Further on, the reaction mixture was cooled to room temperature, and a solution of 37 g of KOH in 120 ml of water was added. The resulting mixture
10 was refluxed for 5 h. After cooling to room temperature, the reaction mixture was carefully treated with 4 M HCl to slightly acidic pH (Caution! Strong gas evolution!). The resulting mixture was diluted with 700 ml of water and extracted with 3x250 ml of ether. The combined ethereal extract was washed with a solution of 20 g of KOH in 200 ml of water, dried over K₂CO₃, passed through a short pad of silica gel 60 (40-63 μ m), and then evaporated to dryness. *The residue*
15 *was distilled in vacuum to give 25.91 g (60%; purity ca. 95%) of 1-phenylhex-5-en-1-one, b.p. 95-105°C/6 mm Hg.*

¹H NMR (CDCl₃): δ 8.00-7.90 (m, 2H), 7.58-7.50 (m, 1H), 7.50-7.39 (m, 2H), 5.82 (ddt, J = 17.1 Hz, J = 10.2 Hz, J = 6.7 Hz, 1H), 5.05 (dm, J = 17.1 Hz, 1H), 4.99 (dm, J = 10.2 Hz, 1H), 2.97 (t, J = 7.3 Hz, 2H), 2.16 (td, J = 7.3 Hz, J = 6.7 Hz, 2H), 1.85 (quin, J = 7.3 Hz, 2H).
20 ¹³C{¹H} NMR (CDCl₃): δ 200.09, 137.98, 137.01, 132.82, 128.47, 127.94, 115.20, 37.61, 33.11, 23.23.

Step 2: 6-Phenyl-6-(pent-4-en-1-yl)fulvene




25 To a solution of 17.4 g (100 mmol) of 1-phenylhex-5-en-1-one in 40 ml of THF cooled in an ice-bath a solution of 20.3 g (120 mmol, 1.2 equiv.) of cyclopentadienylmagnesium bromide in 120 ml of THF was added dropwise. The resulting mixture was refluxed for 3 h, then stirred overnight at room temperature, finally, cooled in an ice-bath and quenched with 10% HCl to pH~5-6. This mixture was extracted with 3x150 ml of hexane, and the combined organic extract was dried over Na₂SO₄. Removal of the solvent under vacuum gave a dark-red

oil. The product was isolated by flash-chromatography on silica gel 60 (40-63 μm ; eluent: hexane-ethyl acetate = 100:1, vol.). This procedure gave 10.23 g (46%) of 6-phenyl-6-(pent-4-en-1-yl)fulvene as a red oil.

Anal. calc. for $\text{C}_{17}\text{H}_{18}$: C, 91.84; H, 8.16. Found: C, 92.11; H, 8.35.

5 ^1H NMR (CDCl_3): δ 7.41-7.29 (m, 5H), 6.62 (ddd, $J = 5.3$ Hz, $J = 1.9$ Hz, $J = 1.5$ Hz, 1H), 6.56 (ddd, $J = 5.3$ Hz, $J = 1.9$ Hz, $J = 1.5$ Hz, 1H), 6.47 (ddd, $J = 5.3$ Hz, $J = 1.9$ Hz, $J = 1.5$ Hz, 1H), 6.10 (ddd, $J = 5.3$ Hz, $J = 1.9$ Hz, $J = 1.5$ Hz, 1H), 5.73 (ddt, $J = 17.1$ Hz, $J = 10.3$ Hz, $J = 6.7$ Hz, 1H), 5.01-4.90 (m, 2H), 2.92 (t, $J = 7.7$ Hz, 2H), 2.09-2.00 (m, 2H), 1.52 (quin, $J = 7.7$ Hz, 2H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 154.28, 143.47, 140.68, 138.01, 131.83, 131.46, 10
129.43, 128.05, 127.79, 123.83, 120.93, 115.01, 35.57, 33.37, 28.63.

Step 3: (Phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride




To a solution of 12.81 g (46.01 mmol) of 2,7-di-*tert*-butylfluorene in 250 ml of ether
15 cooled to -50°C 19 ml (46.17 mmol) of 2.43 M $n\text{-BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting orange solution was cooled to -50°C , and a solution of 10.23 g (46.01 mmol) of 6-phenyl-6-(pent-4-en-1-yl)fulvene in 150 ml of ether was added in one portion. After stirring overnight at room temperature the dark-red reaction mixture was cooled to -50°C , and 19 ml (46.17 mmol) of 2.43 M $n\text{-BuLi}$ in
20 hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting dark-red solution with a significant amount of brick red precipitate was cooled to -50°C , and 14.74 g (46.02 mmol) of HfCl_4 was added. The formed mixture was stirred for 24 h at room temperature, then it was evaporated to dryness, and the residue was treated with 100 ml of hot toluene. This mixture was filtered while hot through glass frit (G4), and the filtrate
25 was evaporated to dryness. The residue was triturated with 100 ml of *n*-hexane, the precipitated orange powder was filtered off (G3) and then dried in vacuum. This procedure gave 10.1 g of (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride. The mother liquor was evaporated to ca. 50 ml, the precipitated orange solid was filtered off and then dried in vacuum. This procedure gave extra 3.82 g of target

complex. Thus, the total yield of (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride isolated in this synthesis was 13.92 g (40%).

Anal. calc. for $C_{38}H_{42}Cl_2Hf$: C, 61.01; H, 5.66. Found: C, 61.14; H, 5.82.

1H NMR ($CDCl_3$): δ 8.01 (d, J = 8.9 Hz, 1H), 7.95 (d, J = 8.9 Hz, 1H), 7.83 (br.d, J = 7.7 Hz, 1H), 7.73 (s, 1H), 7.67-7.59 (m, 2H), 7.59-7.52 (m, 1H), 7.49 (d, J = 8.8 Hz, 1H), 7.45-7.38 (m, 2H), 6.34 (br.s, 1H), 6.21 (br.s, 1H), 6.10 (s, 1H), 5.86-5.70 (m, 2H), 5.55 (br.s, 1H), 5.05 (br.d, J = 17.1 Hz, 1H), 5.00 (br.d, J = 10.3 Hz, 1H), 3.01-2.87 (m, 2H), 2.34-2.21 (m, 1H), 2.19-2.06 (m, 1H), 1.75-1.48 (m, 2H), 1.39 (s, 9H), 0.98 (s, 9H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 152.19, 149.66, 143.23, 138.17, 130.20, 128.67, 128.37, 127.26, 127.15, 124.21, 124.05, 123.52, 122.64, 120.26, 119.89, 119.57, 118.89, 118.81, 117.98, 116.72, 115.46, 114.15, 99.74, 99.68, 53.64, 40.32, 35.44, 34.86, 34.02, 31.13, 30.52, 23.41.

Step 4: (Phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl




To a solution of 5.24 g (7.0 mmol) of (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride in a mixture of 50 ml of toluene and 15 ml of ether, 10 ml (27 mmol) of 2.7 M MeMgBr in ether was added. The resulting mixture was stirred overnight at room temperature. Most of ether was distilled off, and the resulting mixture was filtered through glass frit (G4) to remove insoluble magnesium salts. The filtrate was evaporated almost to dryness, the residue was dissolved in 30 ml of n-hexane, the formed suspension was filtered through glass frit (G3), and the mother liquor was evaporated to ca. 10 ml. Yellow powder precipitated from this solution overnight at $-30^\circ C$ was collected and dried in vacuum. This procedure gave 1.17 g of (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl. The mother liquor was evaporated to ca. 5 ml. Yellow powder precipitated from this solution overnight at $-30^\circ C$ was collected and dried in vacuum to give extra 1.03 g of the target complex. Thus, the total yield of (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl isolated in this synthesis was 2.21 g (44%). The analogous synthesis starting from 8.65 g of (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride afforded (phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl in 64% yield.

Anal. calc. for C₄₀H₅₀Hf: C, 67.92; H, 6.84. Found: C, 67.84; H, 6.99.

¹H NMR (CDCl₃): δ 8.08 (d, *J* = 8.9 Hz, 1H), 7.99 (d, *J* = 8.8 Hz, 1H), 7.81 (dm, *J* = 7.7 Hz, 1H), 7.64-7.57 (m, 2H), 7.53-7.44 (m, 2H), 7.39-7.31 (m, 3H), 6.27-6.23 (m, 1H), 6.14-6.10 (m, 1H), 6.00 (br.d, *J* = 0.8 Hz, 1H), 5.76 (ddt, *J* = 17.1 Hz, *J* = 10.1 Hz, *J* = 6.8 Hz, 1H), 5.63-5.57 (m, 1H), 5.36-5.30 (m, 1H), 5.01 (dm, *J* = 17.1 Hz, 1H), 4.96 (dm, *J* = 10.1 Hz, 1H), 2.82-2.67 (m, 2H), 2.28-2.16 (m, 1H), 2.13-2.01 (m, 1H), 1.66-1.40 (m, 2H), 1.38 (s, 9H), 0.97 (s, 9H), -1.77 (s, 3H), -1.91 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 150.24, 147.84, 144.25, 138.51, 130.42, 128.29, 127.96, 127.31, 126.68, 124.56, 123.76, 122.90, 122.77, 121.04, 120.67, 119.05, 117.69, 116.37, 115.86, 115.08, 112.90, 111.16, 109.23, 101.03, 100.63, 76.68, 53.46, 40.31, 38.15, 37.43, 35.35, 34.76, 34.19, 31.40, 30.76, 23.52.

Complex 4 (C-4): (Phenyl)(pent-4-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl

Step 1: 6-Phenyl-6-(3-phenylpropyl)fulvene




To a solution of sodium ethoxide obtained from 1.15 g (50 mmol) of sodium metal and 40 ml of dry ethanol 50 ml of THF was added followed by 11.2 g (49.9 mmol) of 1,4-diphenylbutan-1-one (ABCR, 98%). The formed dark-red solution was cooled to 0°C, and then 8.4 ml of freshly cracked cyclopenta-1,3-diene was added dropwise over 15 min. The resulting mixture was stirred at room temperature for 4 h. The reaction mixture was poured into 500 ml of water, and the formed mixture was extracted with 150 ml of dichloromethane. The organic layer was separated, and the aqueous phase was extracted with 2 x 75 ml of dichloromethane. The combined organic extract was dried over anhydrous K₂CO₃ and then evaporated to dryness to give a dark-red oily liquid. This crude product was purified by flash chromatography on silica gel 60 (300 ml, 40-63 μm; eluent: hexane/ethyl acetate = 100/1, vol.) to give 7.89 g (58%) of 6-phenyl-6-(3-phenylpropyl)fulvene as a light orange liquid.

Anal. calc. for C₂₁H₂₀: C, 92.60; H, 7.40. Found: C, 92.79; H, 7.60.

¹H NMR (CDCl₃, 400 MHz, 27°C): δ 7.42-7.29 (m, 5H), 7.27-7.19 (m, 2H), 7.19-7.12 (m, 1H), 7.11-7.04 (m, 2H), 6.58-6.53 (m, 2H), 6.47 (ddd, *J* = 5.2 Hz, *J* = 1.5 Hz, *J* = 1.5 Hz, 1H), 6.11 (ddd, *J* = 5.2 Hz, *J* = 1.5 Hz, *J* = 1.5 Hz, 1H), 2.94 (t, *J* = 7.7 Hz, 2H), 2.60 (t, *J* = 7.7 Hz, 2H), 1.75 (quin, *J* = 7.7 Hz, 2H). ¹³C{¹H} NMR (CDCl₃): δ 154.18, 143.52, 141.71, 140.56, 131.89,

131.53, 129.45, 128.34, 128.26, 128.12, 127.84, 125.80, 123.86, 120.89, 35.69, 35.54, 30.99.

Step 2: [1-(η^5 -Cyclopentadien-1-yl)-1-(η^5 -2,7-di-*tert*-butylfluorenyl)-1-(3-phenylpropyl)-1-phenylmethane]hafnium dichloride




To a solution of 8.07 g (28.98 mmol) of 2,7-di-*tert*-butylfluorene in 200 ml of ether cooled to -50°C 12 ml (29.16 mmol) of 2.43 M *n*-BuLi in hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting orange solution was cooled to -50°C, and a solution of 7.89 g (28.97 mmol) of 6-phenyl-6-(3-phenylpropyl)fulvene in 25 ml of ether was added in one portion. After stirring for 5 h at room temperature the orange reaction mixture was cooled to -50°C, and 11.9 ml (28.92 mmol) of 2.43 M *n*-BuLi in hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting orange solution with a significant amount of orange precipitate was cooled to -50°C, and 9.28 g (28.97 mmol) of HfCl₄ was added. The formed mixture was stirred for 24 h at room temperature and then evaporated to ca. 100 ml. The formed orange precipitate was filtered off (G3), heated with 70 ml of toluene, filtered again from LiCl, the and mother liquor was evaporated to ca. 10 ml. Red crystals precipitated overnight at room temperature were filtered off (G3) and then dried in vacuum. This procedure gave 7.56 g of [1-(η^5 -cyclopentadien-1-yl)-1-(η^5 -2,7-di-*tert*-butylfluorenyl)-1-(3-phenylpropyl)-1-phenylmethane]-hafnium dichloride. The mother liquor was combined with the ethereal mother liquor (from evaporated reaction mixture), the resulting mixture was evaporated almost to dryness, and the residue was triturated with 60 ml of *n*-hexane. The formed orange precipitate was filtered off (G3) to give 3.71 g of the target complex. Thus, the total yield of [1-(η^5 -cyclopentadien-1-yl)-1-(η^5 -2,7-di-*tert*-butylfluorenyl)-1-(3-phenylpropyl)-1-phenylmethane]hafnium dichloride isolated in this synthesis was 11.27 g (49%).

Anal. calc. for C₄₂H₄₄Cl₂Hf: C, 63.20; H, 5.56. Found: C, 63.38; H, 5.59.

¹H NMR (CDCl₃): δ 7.98 (d, *J* = 8.9 Hz, 1H), 7.93 (d, *J* = 8.9 Hz, 1H), 7.85 (d, *J* = 7.3 Hz, 1H), 7.67 (s, 1H), 7.61 (d, *J* = 8.5 Hz, 2H), 7.59-7.52 (m, 1H), 7.48 (d, *J* = 8.5 Hz, 1H), 7.45-7.36 (m, 2H), 7.30-7.21 (m, 2H), 7.21-7.03 (m, 3H), 6.29 (s, 1H), 6.19 (s, 1H), 6.08 (s, 1H), 5.58-5.51 (m, 2H), 3.06-2.80 (m, 3H), 2.69-2.36 (m, 1H), 1.99-1.85 (m, 1H), 1.85-1.71 (m, 1H),

1.38 (s, 9H), 0.97 (s, 9H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 152.11, 149.61, 143.18, 141.56, 130.16, 128.74, 128.46, 128.32, 127.26, 127.17, 126.01, 124.15, 124.02, 123.45, 122.56, 120.24, 119.84, 119.53, 118.84, 118.72, 117.84, 116.65, 114.07, 99.69, 99.56, 77.90, 53.61, 40.15, 35.89, 35.39, 34.83, 31.19, 30.51, 25.91


5 *Step 3: [1-(η^5 -Cyclopentadien-1-yl)-1-(η^5 -2,7-di-tert-butylfluorenyl)-1-(3-phenylpropyl)-1-phenylmethane]hafnium dimethyl*



To a solution of 3.7 g (5.0 mmol) of [1-(η^5 -cyclopentadien-1-yl)-1-(η^5 -2,7-di-*tert*-butylfluorenyl)-1-(3-phenylpropyl)-1-phenylmethane]hafnium dichloride in a mixture of 40 ml of
 10 toluene and 30 ml of ether 7.0 ml (18.9 mmol) of 2.7 M MeMgBr in ether was added. The resulting mixture was refluxed for 30 min and then evaporated to ca. 30 ml. The obtained solution was heated to 80-90°C and filtered while hot through glass frit (G3) to remove insoluble magnesium salts. The filter cake was additionally washed with 10 ml of warm toluene. The combined filtrate was evaporated to ca. 15 ml, heated to 80-90°C, and then filtered while hot
 15 through glass frit (G3). The mother liquor was evaporated to ca. 10 ml, and then 10 ml of *n*-hexane was added. Yellow powder precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 2.11 g (60%) of pure [1-(η^5 -cyclopentadien-1-yl)-1-(η^5 -2,7-di-*tert*-butylfluorenyl)-1-(3-phenylpropyl)-1-phenylmethane]hafnium dimethyl.

20 Anal. calc. for $\text{C}_{44}\text{H}_{50}\text{Hf}$: C, 69.78; H, 6.65. Found: C, 69.86; H, 6.83.

^1H NMR (CDCl_3): δ 8.07 (d, J = 8.7 Hz, 1H), 7.98 (d, J = 8.7 Hz, 1H), 7.82 (dm, J = 7.7 Hz, 1H), 7.62-7.54 (m, 2H), 7.53-7.44 (m, 2H), 7.39-7.29 (m, 3H), 7.27-7.19 (m, 2H), 7.19-7.08 (m, 3H), 6.24-6.19 (m, 1H), 6.13-6.08 (m, 1H), 5.99 (br.d, J = 0.9 Hz, 1H), 5.48-5.41 (m, 1H), 5.34-5.30 (m, 1H), 2.89-2.76 (m, 2H), 2.71 (td, J = 13 Hz, J = 4.3 Hz, 1H), 2.58 (dt, J = 14
 25 Hz, J = 8.0 Hz, 1H), 1.91-1.76 (m, 1H), 1.76-1.62 (m, 1H), 1.37 (s, 9H), 0.96 (s, 9H), -1.80 (s, 3H), -1.92 (s, 3H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 150.24, 147.86, 144.20, 141.95, 30.42, 128.36, 127.97, 127.34, 126.72, 125.83, 124.50, 123.76, 122.88, 122.77, 121.03, 120.69, 119.06, 117.57, 116.38, 115.86, 112.87, 111.16, 109.13, 101.02, 100.60, 53.47, 40.26, 38.14, 37.45, 36.10, 35.33, 34.76, 31.46, 30.77, 25.96

Complex for Comparison (CC-1)**(Phenyl)(hex-5-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)zirconium dimethyl***Step 1: 1-Phenyl-1-(hex-5-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane*


5

To a solution of 13.92 g (50.0 mmol) of 2,7-di-*tert*-butylfluorene in 170 ml of THF cooled to -78°C 20.0 ml (50.0 mmol) of 2.5 M $n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting light-orange solution was cooled to -50°C , and a solution of 12.44 g (52.6 mmol, 1.05 eq) of 6-phenyl-6-(hex-5-en-1-yl)fulvene in 170 ml of THF was added in one portion. After stirring overnight at room temperature the dark-red reaction mixture was cooled in an ice-bath and then quenched with 10% HCl to a slightly acidic pH. The resulting orange mixture was diluted with 400 ml of water and extracted with 500 ml of diethyl ether. The organic layer was separated, and the aqueous one was extracted with 150 ml of dichloromethane. The combined organic extract was dried over Na_2SO_4 and filtered through a pad of silica gel 60 (40-63 μm) which was additionally washed by 2x50 ml of dichloromethane. Removal of the solvents under vacuum gave semicrystalline yellow mass which was triturated with 50 ml of *n*-hexane, filtered off and dried in vacuo to afford 16.62 g of 1-phenyl-1-(hex-5-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane as a white solid. The mother liquor was evaporated to dryness, and the residue was dissolved in 100 ml of hot *n*-hexane. Solid precipitated from this solution overnight at -30°C was filtered off, washed with 30 ml of cold *n*-hexane, and dried in vacuo. This procedure gave 7.82 g of a slightly yellow solid of the title product as a mixture of isomers. Thus, the total yield of 1-phenyl-1-(hex-5-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-*tert*-butylfluorenyl)methane isolated in this synthesis was 24.44 g (94.8%).

Anal. calc. for $\text{C}_{39}\text{H}_{46}$: C, 90.99; H, 9.01. Found: C, 91.15; H, 9.20.

^1H NMR (CDCl_3): δ 7.57-6.95 (m, 11H), 6.34-5.59 (m, 4H), 4.98-4.70 (m, 3H), 2.93-2.55 (m, 2H), 2.49-2.15 (m, 2H), 2.04-1.80 (m, 2H), 1.46-0.91 (m, 22H).

Step 2: (Phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-tert-butylfluoren-9-yl) zirconium dichloride




To a solution of 16.51 g (32.07 mmol) of 1-phenyl-1-(hex-5-en-1-yl)-1-cyclopentadienyl-1-(2,7-di-tert-butylfluoren-9-yl)methane in 300 ml of ether, cooled to -50°C , 25.7 ml (64.25 mmol) of 2.5 M $n\text{BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature. The resulting yellow solution with yellow precipitate was cooled to -50°C , and 7.48 g (32.1 mmol) of ZrCl_4 was added. The resulting mixture was stirred for 24 h at room temperature and then evaporated to dryness. The residue was stirred with 150 ml of warm toluene, and the formed suspension was filtered through a glass frit (G4). The filtrate was evaporated to ca. 40 ml, and 70 ml of n-hexane was added. Red solid precipitated overnight at -30°C was collected and dried in vacuum. This procedure gave 19.7 g (91%) of (Phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-tert-butylfluoren-9-yl) zirconium dichloride as 1 to 1 solvate with toluene.

Anal. calc. for $\text{C}_{39}\text{H}_{44}\text{Cl}_2\text{Zr}^*\text{C}_7\text{H}_8$: C, 72.03; H, 6.83. Found: C, 72.24; H, 7.09.

^1H NMR (CDCl_3): δ 8.04 (d, $J = 8.7$ Hz, 1H), 7.98 (d, $J = 8.7$ Hz, 1H), 7.82 (dm, $J = 7.7$ Hz, 1H), 7.67 (s, 1H), 7.66 (dd, $J = 9.4$ Hz, $J = 1.4$ Hz, 1H), 7.64-7.60 (m, 1H), 7.59-7.51 (m, 2H), 7.44-7.38 (m, 2H), 6.41-6.37 (m, 1H), 6.28-6.24 (m, 1H), 6.09 (m, 1H), 5.84-5.80 (m, 1H), 5.80-5.68 (m, 1H), 5.59-5.55 (m, 1H), 4.97-4.86 (m, 2H), 3.10-2.97 (m, 1H), 2.82-2.69 (m, 1H), 2.15-1.96 (m, 2H), 1.64-1.44 (m, 4H), 1.39 (s, 9H), 0.98 (s, 9H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 152.50, 149.95, 143.09, 138.34, 130.47, 128.56, 128.36, 127.26, 127.09, 124.58, 124.32, 124.29, 123.84, 123.63, 121.45, 121.38, 120.51, 120.03, 119.77, 118.32, 117.64, 114.67, 111.87, 102.14, 77.73, 53.80, 40.88, 35.48, 34.90, 33.76, 31.11, 30.50, 29.43, 23.57.

Step 3: (Phenyl)(hex-5-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) zirconium dimethyl



To a solution of 3.37 g (4.99 mmol) of (phenyl)(hex-5-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) zirconium dichloride in a mixture of 50 ml of toluene and 25 ml of ether, 7.0 ml (14.77 mmol) of 2.11 M MeMgBr in ether was added. The resulting mixture was refluxed for 30 min and then evaporated to ca. 25 ml. The obtained suspension was heated to 80-90°C and filtered while hot through glass frit (G3) to remove insoluble magnesium salts. The filter cake was additionally washed with 2x15 ml of toluene. The combined filtrate was evaporated to ca. 10 ml. The obtained solution was heated again to 80-90°C and filtered while hot through glass frit (G3). The mother liquor was evaporated to dryness, and the residue was dissolved in 12 ml of n-hexane. Yellow powder precipitated from this solution overnight at -40°C was collected and dried in vacuum. This procedure gave 1.68 g (53.1%) of pure (phenyl)(hex-5-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl) zirconium dimethyl.

Anal. calc. for C₄₁H₅₀Zr: C, 77.66; H, 7.95. Found: C, 77.62; H, 8.19.

¹H NMR (CDCl₃): δ 8.10 (d, *J* = 8.6 Hz, 1H), 8.00 (d, *J* = 8.9 Hz, 1H), 7.79 (dm, *J* = 7.9 Hz, 1H), 7.61-7.54 (m, 2H), 7.52 (dd, *J* = 8.9 Hz, *J* = 1.2 Hz, 1H), 7.50-7.44 (m, 1H), 7.37 (dd, *J* = 8.9 Hz, *J* = 1.6 Hz, 1H), 7.35-7.30 (m, 2H), 6.35-6.29 (m, 1H), 6.22-6.15 (m, 1H), 5.97 (s, 1H), 5.80-5.63 (m, 2H), 5.36-5.30 (m, 1H), 4.92 (dm, *J* = 17.2 Hz, 1H), 4.87 (dm, *J* = 10.0 Hz, 1H), 2.89-2.74 (m, 1H), 2.60-2.45 (m, 1H), 2.11-1.92 (m, 2H), 1.58-1.39 (m, 4H), 1.38 (s, 9H), 0.97 (s, 9H), -1.57 (s, 3H), -1.71 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 150.24, 147.86, 144.21, 138.65, 130.62, 128.09, 127.96, 127.22, 126.63, 125.03, 123.57, 123.27, 122.78, 121.01, 120.57, 119.42, 117.91, 117.31, 117.09, 114.42, 113.10, 111.42, 106.37, 102.02, 101.49, 74.70, 53.59, 40.88, 35.35, 34.77, 33.86, 32.24, 31.55, 31.43, 30.80, 29.60, 23.70.

Complex elemental analysis (ICP method):

Complex	Hf (mol%)	Zr (mol%)
C1	99.62	0.38
C2	99.68	0.32

b) Polymerization procedure

Polymerization tests have been performed in 125mL reactors equipped with a bottom valve, at 160°C and different C8/C2 weight ratios in the liquid phase. Different catalyst loadings have been tested to find the optimal amount to guarantee almost constant temperature and pressure during the 10 minutes of polymerization. TEA (7×10^{-2} mol/kg in Isopar E) has been used as the scavenger for all the experiments.

- Activation procedure

Two different borate activators have been tested, trityl tetrakis(pentafluorophenyl)borate (TB) for Inventive Example IE-3 and N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate (AB) for all others experiments. In all cases a B/Hf molar ratio of 1.25 has been used. The complex and the activator were dissolved separately in 4 mL of toluene. The borate solution was then injected in the reactor feeding line followed by the complex solution and the two were let in contact for few seconds before the injection into the reactor by nitrogen overpressure.

- Polymerization procedure

The reactor was filled with the desired amount (57-73 mL of solvent (isopar E), see Table 1), scavenger (0.035 mmol TEA) and 1-octene. Solvent and monomers amounts were chosen to have an initial liquid volume at the polymerization conditions of 80mL.

The reactor was then heated up and carefully pressurised with ethylene (25-28 bar-g). When conditions were stable, the ethylene pressure was adjusted to 30 bar-g and the mixture was allowed to stir at 750 rpm during 10 minutes in order to determine the residual ethylene uptake. After this time the catalyst (dissolved with 4mL of toluene) and the cocatalyst (also dissolved with 4 mL toluene) were combined in the injection line and immediately injected in the reactor by nitrogen overpressure. Pressure was then kept constant by feeding ethylene and after 10 minutes polymerization was quenched by adding a killing agent in large molar excess with respect to the transition metal complex (CO₂). Immediately after, the reactor was vented, the temperature was decreased and the vessel was opened. The solution was discharged in an aluminium pan containing few milligrams (~500 ppm related to the copolymer produced) of Irganox 1076. The pan was then placed under a well-ventilated fume hood until the volatiles were evaporated. The collected residual material was analysed by HT-SEC and DSC according to the methods reported in the polymer characterisation paragraph.

Table 1: C2/C8 copolymerization results

Inventive Examples IE1 – IE5 and Comparative Example CE1

Ex	Complex	isopar E	C8 feed	Productivity	Average C8/C2 ratio in solution	C8 in polymer (NMR or Tg)	Reactivity ratio C8/C2	HT-SEC	
unit		ml	ml	kg PE/g _{cat} in 10 min	wt/wt	%wt		Mw kDa	PDI
IE1	C1	73	7	18.5	1.3	24.7(NMR)	0.23	98	3.1
IE2	C2	68	8	23.0	1.8	25.4(NMR)	0.19	172	3.2
IE3	C2	68	8	14.6	1.8	21.9(Tg)	0.16	157	2.8
IE4	C3	68	8	53.3	1.7	26.1 (NMR)	0.21	112	3.0
IE5	C4	68	8	35.2	1.8	25.3(NMR)	0.19	154	3.4
CE1	CC1	57	23	170.4	5.0	19.8(NMR)	0.05	47	2.4

For all Examples Cocatalyst AB was used, except for IE3, where TB was used as cocatalyst.

5

Table 1 shows that, despite the higher activity of the zirconium complex:

a) The hafnium complexes according to the invention have much higher comonomer reactivity compared to zirconium analogues

b) The hafnium complexes have much higher molecular weight capability compared to zirconium analogues, even for copolymers with higher octene content (lower density)

10


That is, the hafnium complexes have overall a better performance than their zirconium analogues for the production of low density, high molecular weight C2/ α -olefin (preferably octene) copolymers.

15

Claims:

1. Catalyst system, whereby the catalyst system comprises

(i) at least one metallocene complex of formula (I)



wherein

Mt1 is Hf,

X is a sigma-donor ligand,

10
R¹, R², R³ are the same or different from each other and can be hydrogen or a saturated linear or branched C₁-C₁₀ alkyl, whereby the alkyl group can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table, or R¹ and R² or R² and R³ can form a ring having 4 to 6 C-atoms and 1 to 3 double bonds,

15
R⁴ and R⁵ are the same or different from each other and can be saturated linear or branched C₁-C₁₀ alkyl, C₅-C₁₀ aryl, C₆-C₂₀ alkylaryl or C₆-C₂₀ arylalkyl groups, which can optionally contain up to 2 heteroatoms belonging to groups 14-16 of the periodic table,


20
n can be 1 to 5,

Ar is a C₆-C₂₀-aryl or -heteroaryl group, which can be unsubstituted or substituted by 1 to 5 linear or branched C₁-C₁₀ alkyl group(s),

25
and

(ii) a boron containing cocatalyst.

2. Catalyst system according to claim 1, wherein the catalyst system comprises a mixture of the metallocene complex of formula (I) as defined in claim 1 with a metallocene complex of formula (I')



wherein Mt2 is Zr, R¹ to R⁵ and Ar are defined as for complex of formula (I), provided that the mixture contains more than 50% by moles of the complex of Formula I with Mt1 being Hf.

5

3. Catalyst system according to claim 1 or 2, wherein in the formula (I)

Mt1 is Hf,

10

X is independently a hydrogen atom, a halogen atom, a R⁶, OR⁶, OSO₂CF₃, OCOR⁶, SR⁶, NR⁶₂ or PR⁶₂ group wherein R⁶ is a linear or branched, cyclic or acyclic, C₁-C₂₀-alkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-alkynyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl or C₇-C₂₀-arylalkyl radical, optionally containing up to 2 heteroatoms belonging to groups 14-16 of the periodic table or is SiR⁶₃, SiHR⁶₂ or SiH₂R⁶,

15

R¹, R², R³ are the same or different from each other and can be hydrogen or a saturated linear or branched C₁-C₆ alkyl, whereby the alkyl group does not contain any heteroatom belonging to groups 14-16 of the periodic table or R¹ is hydrogen and R² and R³ form a ring having 5 to 6 C-atoms and 1 to 3 double bonds,

20

R⁴ and R⁵ are the same or different from each other and can be a saturated linear or branched C₁-C₁₀ alkyl or C₆-C₁₀ aryl, whereby the groups do not contain any heteroatom belonging to groups 14-16 of the periodic table,

25

Ar is a C₆-C₁₀-aryl or -heteroaryl group, which can be unsubstituted or substituted by one linear or branched C₁-C₆ alkyl group,

and n is 2 to 4.

4. Catalyst system according to claim 3, wherein in the formula (I)

30

Mt1 is Hf,

X is independently a halogen atom or a R⁶ or OR⁶ group, whereby R⁶ is a C₁₋₆-alkyl, phenyl or benzyl group

35

R¹, R², R³ are the same or different from each other and can be hydrogen, a saturated linear or branched C₁-C₄ alkyl, whereby the alkyl group does not contain any heteroatom

belonging to groups 14-16 of the periodic table, or R¹ is hydrogen and R² and R³ form a ring having 6 C-atoms and 3 double bonds,

R⁴ and R⁵ are the same or different from each other and can be a saturated linear or branched C₁-C₆ alkyl or phenyl, whereby the groups do not contain any heteroatoms belonging to groups 14-16 of the periodic table,

Ar is an unsubstituted C₆-C₁₀-aryl group and n is 2 to 4.

5. Catalyst system according to claim 4, wherein in the formula (I)

Mt1 is Hf,

X is independently a C₁-C₄-alkyl or a benzyl group,

R¹, R², R³ are the same and are all hydrogen or R¹ is hydrogen and R² and R³ form a ring having 6 C-atoms and 3 double bonds,

R⁴ and R⁵ are the same and are a saturated linear or branched C₂-C₆ alkyl,

n is 2 to 4 and Ar is phenyl.

6. Catalyst system according to anyone of the preceding claims, wherein the metallocene complex of formula (I) is selected from the group comprising

(phenyl)(but-3-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl,

(phenyl)(but-3-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dibenzyl,

(phenyl)(but-3-en-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride,

(phenyl)(4-penten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluorenyl)hafnium dimethyl,

(phenyl)(4-penten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluorenyl)hafnium dibenzyl,

(phenyl)(4-penten-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluorenyl)hafnium dichloride,

(phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl,

(phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dibenzyl,

(phenyl)(5-hexen-1-yl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride,

5 (phenyl)(3-phenylpropyl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dimethyl,


(phenyl)(3-phenylpropyl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dibenzyl,

10 (phenyl)(3-phenylpropyl)methylene(cyclopentadienyl)(2,7-di-*tert*-butylfluoren-9-yl)hafnium dichloride,

and which is optionally mixed with the corresponding metallocene complex of formula (I'), wherein Mt₂ is Zr, provided that the mixture contains more than 50% by moles of the complex of Formula I with Mt₁ being Hf.

15 7. Catalyst system according to any of preceding claims, whereby the catalyst system is a homogeneous or non-supported catalyst systems, which can be prepared in solution, by contacting the metallocene complex of Formula (I) or a mixture of the metallocene complex of formula (I) as defined in claim 1 with a metallocene complex of formula (I') as defined in claim 2, provided that the mixture contains more than 50% by moles of the complex of
20 Formula I with Mt₁ being Hf, as a solid or as a solution, with the boron containing cocatalyst in a hydrocarbon diluent or previously dissolved in an aromatic solvent, or which can be formed by sequentially adding the catalyst components directly into the polymerization reactor.

25 8. A catalyst system as claimed in any preceding claim wherein said boron containing cocatalyst comprises an anion of formula:



where Z is an optionally substituted phenyl derivative, said substituent being a halo-C₁₋₆-alkyl or halo group.

30 9. A catalyst system as claimed in claim 8, wherein the boron containing cocatalyst is a borate selected from the group comprising

triphenylcarbeniumtetrakis(pentafluorophenyl) borate,

N,N-dimethylcyclohexylammoniumtetrakis(pentafluorophenyl)borate,

35 N,N- dimethylbenzylammoniumtetrakis(pentafluorophenyl)borate or

N,N-dimethylaniliniumtetrakis(pentafluorophenyl)borate.

10. A catalyst system as claimed in any of the preceding claim, wherein the system shows a reactivity ratio C_{AO}/C_2 of at least 0.1, wherein AO is C₄₋₁₀ alpha-olefin comonomer, in a high temperature solution process for producing ethylene copolymers.
- 5 11. Use of a catalyst system as defined in claim 1 to 10 in a high temperature solution process at a temperature greater than 100°C for polymerizing ethylene and a C₄₋₁₀ alpha-olefin comonomer.
- 10 12. Process for the preparation of an ethylene copolymer comprising polymerizing ethylene and a C₄₋₁₀ alpha-olefin comonomer in a high temperature solution process at a temperature greater than 100°C in the presence of a catalyst comprising:
- (i) a metallocene complex of formula (I) as defined in any of preceding claims 1, 3 to 10 or a mixture of a metallocene complex of formula (I) and a metallocene complex of formula (I') as defined in claim 2 and
 - 15 (ii) a boron containing cocatalyst.
13. Process according to claim 12, wherein the polymerization is performed
- a) at a polymerization temperature of at least 110°C,
 - b) a pressure in the range of 50 to 300 bar and
 - 20 c) in a hydrocarbon solvent selected from the group of C₅₋₁₂-hydrocarbons, which may be unsubstituted or substituted by C₁₋₄ alkyl group and being liquid under the above defined polymerization conditions.
14. Ethylene copolymer obtained by a polymerization process according to claim 12 or 13,
- 25 wherein the ethylene is a copolymer of ethylene and a C₄₋₁₀ alpha-olefin comonomer, having
- (i) a comonomer content of up to 45 wt%,
 - (ii) a density (measured according to ISO 1183-187) in the range of 0.850 g/cm³ to below 0.920 g/cm³,
 - 30 (iii) Mw/Mn value in the range of 2.0 to 4.5, preferably in the range of 2.5 to 4.5 and
 - (iv) a melting point (measured with DSC according to ISO 11357-3:1999) below 110°C.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2018/057922

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F210/16 C08F4/6592
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, CHEM ABS Data, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007/043176 A1 (MARTIN JOEL L [US] ET AL) 22 February 2007 (2007-02-22) cited in the application paragraph [0155] - paragraph [0152] paragraph [0224] - paragraph [0268] claims 1,3,7,8,42,50 -----	1-13
X	US 2007/060722 A1 (JAYARATNE KUMUDINI C [US] ET AL) 15 March 2007 (2007-03-15) paragraph [0125] - paragraph [0128] paragraph [0201] - paragraph [0245] claims 1,7,20,22 -----	1-13
X	US 2014/128563 A1 (MCDANIEL MAX P [US] ET AL) 8 May 2014 (2014-05-08) paragraph [0093] - paragraph [0095] paragraph [0170] - paragraph [0175] claim 1 ----- -/-	1-13



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

2 May 2018

Date of mailing of the international search report

09/05/2018

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Nikolai, Joachim

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2018/057922

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	ANNIINA LAINE ET AL: "Elemental Reactions in Copolymerization of [alpha]-Olefins by Bis(cyclopentadienyl) Zirconocene and Hafnocene: Effects of the Metal as a Function of the Monomer and the Chain End", ORGANOMETALLICS, vol. 30, no. 6, 28 March 2011 (2011-03-28) , pages 1350-1358, XP055372959, US ISSN: 0276-7333, DOI: 10.1021/om100761p page 1350 - page 1351 page 1359	1-13
X	----- AKIHIRO YANO ET AL: "Effect of ligand structures on high temperature homo- and copolymerization of ethylene by cationic hafnocene catalysts based on tetrakis(pentafluorophenyl)borate", JOURNAL OF MOLECULAR CATALYSIS A: CHEMICAL., vol. 156, no. 1-2, 1 May 2000 (2000-05-01) , pages 133-141, XP055372757, NL ISSN: 1381-1169, DOI: 10.1016/S1381-1169(99)00431-8 table 6	1-13
X	----- EP 2 933 275 A1 (BOREALIS AG [AT]) 21 October 2015 (2015-10-21) paragraph [0064] - paragraph [0067] -----	14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2018/057922

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2007043176	A1	22-02-2007	AU 2006283495 A1 01-03-2007 BR PI0614936 A2 26-04-2011 CA 2619967 A1 01-03-2007 CN 101283000 A 08-10-2008 EP 1917281 A1 07-05-2008 ES 2537556 T3 09-06-2015 JP 2009504901 A 05-02-2009 KR 20080050428 A 05-06-2008 US 2007043176 A1 22-02-2007 WO 2007024773 A1 01-03-2007
US 2007060722	A1	15-03-2007	AT 528071 T 15-10-2011 AU 2006295292 A1 05-04-2007 BR PI0615803 A2 24-05-2011 CA 2621475 A1 05-04-2007 CA 2824482 A1 05-04-2007 CN 101300075 A 05-11-2008 EP 1933980 A2 25-06-2008 EP 2329882 A1 08-06-2011 ES 2395095 T3 08-02-2013 ES 2430816 T3 21-11-2013 HK 1119996 A1 25-05-2012 JP 2009508980 A 05-03-2009 KR 20080057279 A 24-06-2008 KR 20130069880 A 26-06-2013 KR 20130124593 A 14-11-2013 US 2007060722 A1 15-03-2007 US 2008004460 A1 03-01-2008 US 2009198078 A1 06-08-2009 US 2011190460 A1 04-08-2011 US 2013053523 A1 28-02-2013 WO 2007037836 A2 05-04-2007
US 2014128563	A1	08-05-2014	BR 112015010241 A2 11-07-2017 CA 2890027 A1 15-05-2014 CN 104781319 A 15-07-2015 EP 2917267 A1 16-09-2015 ES 2606684 T3 27-03-2017 SG 11201503462T A 28-05-2015 US 2014128563 A1 08-05-2014 US 2015175726 A1 25-06-2015 WO 2014074622 A1 15-05-2014
EP 2933275	A1	21-10-2015	NONE