

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : D06M 11/00, 11/71, 11/72, 11/82, 13/192	A1	(11) International Publication Number: WO 94/23112
		(43) International Publication Date: 13 October 1994 (13.10.94)
(21) International Application Number: PCT/US93/02635 (22) International Filing Date: 26 March 1993 (26.03.93) (71) Applicant: ORTEC, INC. [US/US]; 201 Pickens Highway, Easley, SC 29640 (US). (72) Inventors: FUNG, Kwok-Wing; 100 Sherwood Drive, Easley, SC 29642 (US). WONG, Kam, Han; 502 Huntington Road, Easley, SC 29642 (US). BROTHERTON, David, Larry; 524 Sheffield Road, Easley, SC 29640 (US). (74) Agent: FLINT, Cort; P.O. Box 10827, Greenville, SC 29603-0827 (US).		(81) Designated States: JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>With amended claims.</i>
(54) Title: PROCESS FOR REDUCING DISCOLORATION CELLULOSIC FIBERS		
(57) Abstract		
A process for reducing discoloration of fibrous cellulosic material, treated at temperatures above about 175 °C with a treating solution of a polycarboxylic acid and a phosphate salt curing catalyst, comprises adding to the treating solution an inorganic boron-oxygen compound.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

-1-

Description**PROCESS FOR REDUCING DISCOLORATION CELLULOSIC FIBERS**Technical Field

5 This invention relates to an improved process for imparting wrinkle resistance or durable press properties to cellulosic fabrics, wherein addition of an inorganic boron-oxygen compound to a polycarboxylic acid treating solution, reduces discoloration of fibrous cellulosic materials, treated with the polycarboxylic acid solutions at temperatures above about 175° C.

10 Background Art

Numerous processes have been proposed for imparting wrinkle resistance, shrinkage resistance and smooth-drying properties to fabrics and garments, made from cotton or other cellulosic fibers. The treated garments or fabrics retain their dimensions, smooth appearance and normal shape while being worn and after
15 numerous cycles of domestic washing with an alkaline detergent in a washing machine and drying in a tumble dryer.

In many processes, a solution of formaldehyde or a formaldehyde adduct and an acidic catalyst is applied to the textile and the treated fabric or textile is heated to bring about crosslinking of the cellulose molecules of the textile. Owing
20 to the toxicity associated with formaldehyde and its adducts, alternative methods of imparting durable press characteristics to cellulose are of considerable interest.

Welch et al., in U.S. Patent 4,820,307, herein incorporated by reference, have proposed a process for formaldehyde-free durable press finishing of cotton textiles,
25 in which the textile is treated with a solution of a polycarboxylic acid at elevated temperatures. Catalysts for the process include alkali metal dihydrogen phosphates and alkali metal salts of phosphorous, hypophosphorous and polyphosphoric acids. Cotton fabrics, thus treated with citric acid as the polycarboxylic acid,

-2-

using sodium dihydrogen phosphate catalyst, discolor significantly upon treatment at 180°C for 90 sec. The discoloration can be removed by post-treatment with various materials, of which the most effective are magnesium monoperoxyphthalate, sodium perborate, sodium borohydride, hydrochloric acid and sodium hypochlorite. Sodium tetraborate and boric acid are relatively ineffective for improving the whiteness of the fabrics.

Andrews, "Non-Formaldehyde Durable Press Finishing of Cotton with Citric Acid," 1989 International Conference and Exhibition, American Association of Textile Chemists and Colorists, pages 176-183, has proposed using citric acid, as at least a partial substitute for more expensive 1,2,3,4-butanetetracarboxylic acid, in compositions for imparting durable press properties to cellulosic fabrics. Yellowing of fabrics, treated with citric acid, is recognized as a problem, particularly in the case of treating solutions containing sodium dihydrogen phosphate or sodium hypophosphite catalyst, cured at 190°C or 200°C. Use of lower curing temperatures resulted in generally improved whiteness indices, but decreased durable press ratings.

Welch et al., "Ester Crosslinks: A Route to High Performance Nonformaldehyde Finishing of Cotton," Textile Chemist and Colorist, vol. 21 (1989), pages 13-17, disclose using various polycarboxylic acids for the cross-linking of celluloses. Sodium hypophosphite was judged the most effective catalyst for producing good durable press properties, without undue yellowing, even in the case of citric acid.

It is an object of this invention to provide an improved method for decreasing the yellowing of cellulosic fabrics, treated at a high temperature with one or more polycarboxylic acids in the presence of a phosphorus-containing catalyst.

Disclosure of Invention

This invention relates to a process for reducing discoloration or yellowing of fibrous cellulosic materials, treated at temperatures above about 175°C, with a treating solution of a polycarboxylic acid and a phosphate salt curing catalyst, comprising adding to the treating solution an inorganic boron-oxygen compound.

This invention is applicable to fibrous cellulosic materials, containing at least 30% by weight of cellulosic fibers. Included among cellulosic fibers are cotton, flax, jute, hemp, ramie and regenerated unsubstituted wood cellulose, such as rayon. The process can be used for treating cellulosic materials in the form of knit

-3-

or woven or nonwoven fabrics, as well as for treating fibers, linters, roving, slivers and paper. The process is preferably used for treating fibrous cellulosic materials in the form of knit, woven or nonwoven fabrics. Preferably, the process is used for the treatment of textile materials, containing 50-100% of cotton fibers.

5 The invention is based on the discovery that addition of an inorganic boron-oxygen compound to a polycarboxylic acid treating solution for cellulosic materials markedly reduces the tendency of the materials, treated at temperatures above about 175° C, to discolor or turn yellow.

10 The inorganic boron-oxygen compound is selected from alkali metal borates, including metaborates, tetraborates and pentaborates. Typical alkali metal borates include sodium metaborate, sodium tetraborate, potassium metaborate, potassium tetraborate, potassium pentaborate, lithium metaborate, lithium tetraborate and lithium pentaborate in the form of anhydrate, tetrahydrate, pentahydrate, octahydrate or decahydrate. Another boron-oxygen compound, which can be added to
15 the treating solutions, is boric acid. Preferably, the inorganic boron-oxygen compound is boric acid or sodium tetraborate or a hydrate thereof. Most preferably, the inorganic boron-oxygen compound is boric acid or borax (sodium tetraborate decahydrate), or a mixture thereof.

20 The amount of inorganic boron-oxygen compound, added to the polycarboxylic acid treating solution, is from about 0.5% to about 10% by weight of the solution. It has been found that addition of 1-5% by weight of borax or boric acid to the treating solutions markedly reduces yellowing resulting from high temperature treatment of cellulosic textiles, impregnated with the solutions. Preferably, the amount of inorganic boron-oxygen compound, added to the treating solution, is 1-
25 5% by weight of the treating solution. Most preferably, 1-3% by weight of borax or boric acid is added to the treating solution.

30 Included within polycarboxylic acids in the treating solutions are aliphatic, alicyclic and aromatic acids, containing at least two carboxy groups. The aliphatic and alicyclic acids can be saturated or unsaturated. Preferred members of the reactive group of compounds are saturated acids having at least three carboxylic acid groups or alpha,beta-unsaturated acids, having at least two carboxy groups. Most preferred polycarboxylic acids include, but are not limited to, maleic acid, citraconic acid (methylmaleic acid), citric acid (2-hydroxy-1,2,3-propanetricarboxylic acid), tricarballic acid (1,2,3-propanetricarboxylic acid), trans-aconitic acid
35 (trans-1-propene-1,2,3-tricarboxylic acid), 1,2,3,4-butanetetracarboxylic acid, all-

-4-

cis-1,2,3,4-cyclopentanetetracarboxylic acid, mellitic acid (benzenehexacarboxylic acid) and oxydisuccinic acid (2,2'-oxybis(butanedioic acid)), or mixtures thereof. The concentration of polycarboxylic acid in the treating solutions can be from about 0.5% by weight to about 20% by weight of the solution.

5 In the case of 1,2,3,4-butanetetracarboxylic acid (BTCA), it has been found that excellent durable press properties are obtained when the treating solution contains 3-7% by weight of BTCA.

The method of this invention is particularly preferred for use with treating solutions containing mixtures of 1,2,3,4-butanetetracarboxylic acid and citric acid (CA), the latter being considerably cheaper than the former. Preferred mixtures
10 are those containing 10:1 to 1:3 parts by weight of BTCA:CA. When a mixture of acids is used in the treating solutions, the amount of acids is 3-7% by weight of the treating solution.

Addition of oxalic acid to replace some of the BTCA in the treating solutions
15 is also contemplated. Textiles, impregnated with solutions containing a mixture of BTCA and oxalic acid, can be cured at temperatures as high as 250° C. The treated textiles have acceptable durable press and whiteness ratings.

Phosphate salt curing catalysts include, but are not limited to, alkali metal hypophosphites, alkali metal phosphites, alkali metal salts of polyphosphoric acids
20 and alkali metal salts of orthophosphoric acid, including, as appropriate, hydrates thereof. The amount of phosphate salt curing catalyst in the treating solutions is from about 0.25% by weight to about 10% by weight of the treating solution.

Alkali metal hypophosphites can be represented by the formula MH_2PO_2 , wherein M is an alkali metal cation. Sodium hypophosphite is preferred as a
25 catalyst in the treating solutions. An observation in connection with the method of this invention is that addition of the inorganic boron-oxygen compound to treating solutions, containing a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acids, not only markedly reduced discoloration of treated cellulosic textiles, but also reduced the amount of sodium hypophosphite catalyst required by permitting
30 replacement of up to half of the hypophosphite with disodium hydrogen phosphate.

For example, treating solutions containing 3.2% by weight of sodium hypophosphite, 2% by weight of borax and a mixture of BTCA and CA, cured on cellulosic textiles at 200° C or 210° C, give products with wrinkle recovery angles and tensile strength, similar to those of textiles treated under the same conditions

-5-

with 6.4% of sodium hypophosphite, without borax, and the samples treated with borax-hypophosphite are considerably whiter. Therefore, use of borax in the treating compositions both improves whiteness of the treated textiles and reduces the required amount of an expensive catalyst in the treating solution.

Alkali metal phosphites can be represented by the formulas M_2HPO_3 and MH_2PO_3 , wherein M is an alkali metal cation. Preferably, M is sodium. These phosphite salt curing catalysts are used in the same concentration as the hypophosphites.

Alkali metal salts of polyphosphoric acids include sodium, potassium and lithium salts of linear and cyclic condensed phosphoric acids. The cyclic oligomers of particular interest are trimetaphosphoric acid and tetrametaphosphoric acid. Linear condensed phosphoric acids include pyrophosphate, tripolyphosphates, and hexametaphosphates. Sodium salts are preferred. The amount of alkali metal polyphosphates used in the treating solutions is as above.

Alkali metal salts of orthophosphoric acid include monobasic, dibasic and tribasic salts, represented by the formulas MH_2PO_4 , M_2HPO_4 and M_3PO_4 , respectively, wherein M is an alkali metal cation. Preferred members of this group are monosodium dihydrogen phosphate and disodium hydrogen phosphate. Disodium hydrogen phosphate is particularly preferred. It has been found that inclusion of the inorganic boron-oxygen compound in the treating solutions reduces the amount of orthophosphate salt required. The orthophosphate salts, particularly disodium hydrogen phosphate, can also be used in combination with an alkali metal hypophosphite, to reduce the amount of hypophosphite required.

Preferred phosphate salt curing catalysts are selected from among alkali metal hypophosphites, phosphites, pyrophosphates, tripolyphosphates or hexametaphosphates; alkali metal monohydrogen or dihydrogen phosphates, or a mixture thereof.

Addition of either borax or boric acid to treating solutions, containing 1,2,3,4-butanetetracarboxylic acid as crosslinking agent and disodium hydrogen phosphate as sole phosphate salt catalyst permits curing at 190-200°C, without loss of whiteness, as determined by the CIE whiteness index.

A further advantage of this invention is that durable press properties can be imparted to dyed cellulosic textiles, without significant damage to the shade of the dyed textile. In addition, utilization of the process of this invention produces

-6-

textiles with good durable press and whiteness properties in one step, rather than requiring post-treatment to bleach the treated textile material. The process is accordingly useful for imparting durable press properties to white or dyed, knit, woven or nonwoven fabrics or textiles.

5 The method of this invention is preferably used at temperatures above 180° C, up to as high as 250° C. The duration of the high temperature treatment can be determined by routine experimentation and is selected so as to give maximum throughput in a commercial textile finishing operation.

Preferred embodiments of this invention include:

10 (a) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof;

15 (b) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof;

20 (c) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate or a hydrate thereof and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof;

25 (d) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of disodium hydrogen phosphate and sodium hypophosphite or hydrates thereof and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof;

30 (e) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is boric acid;

35 (f) a process wherein the cellulosic material is treated at a 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is boric acid;

-7-

(g) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate or hydrates thereof and the inorganic boron-oxygen compound is boric acid; and

(h) a process wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof and the inorganic boron-oxygen compound is boric acid.

10 Best Mode for Carrying Out the Invention

In a most preferred embodiment, the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate and the inorganic boron-oxygen compound is borax.

Without further elaboration, it is believed that one skilled in the art can, using the preceding description, utilize the present invention to its fullest extent. The following preferred specific embodiments are, therefore, to be construed as merely illustrative and not limitative of the remainder of the disclosure in any way whatsoever.

In the following examples, temperatures are set forth uncorrected in degrees Celsius. Unless otherwise indicated, all parts and percentages are by weight.

Test specimens were 100% 78 x 78 cotton fabric print cloth, weighing 3.2 oz/yd², obtained from TEST FABRICS, Inc., P.O. Box 420, Middlesex, N. J. 08846. The fabric was desized, scoured and bleached before testing. Unless otherwise indicated, reagents are reagent grade.

Conditioned wrinkle recovery angle was measured by the method of ATCC-66-1984. Tensile strength was measured according to ASTM-D-1682-64. Whiteness index (CIE) was measured using a MacBeth Color-Eye Spectrophotometer.

-8-

Example 1Effect of Boron Compounds on the Color and Wrinkle Recovery of Cotton Treated with 1,2,3,4-Butanetetracarboxylic Acid in the Presence of Disodium Hydrogen Phosphate Curing Catalyst

5 Aqueous solutions containing 6.4% by weight of reagent grade 1,2,3,4-butanetetracarboxylic acid, 2.0-4.2% by weight of disodium hydrogen phosphate catalyst, 1.0% by weight of emulsified nonionic polyethylene fabric softener, 0.1% by weight of nonylphenol deca(ethylene oxide) wetting agent and a boron-containing decolorizing agent, were prepared. The compositions were used in the
10 fabric treating bath.

 Samples of desized cotton fabric were immersed in the treating solution and pad dried by being passed through the squeeze rolls of a wringer to give a wet pick-up of 90-110% by weight of treating solution on the fabric, based on the original dry weight of the fabric. The fabric was dried and cured in a forced-draft oven at the
15 temperature specified for 4 min.

 The treated fabric was evaluated for whiteness index (CIE) before laundering and for wrinkle recovery angle and tensile strength after one typical domestic laundering and drying cycle. The results are shown in Table 1.

 As shown in Table 1, increasing the drying and curing temperature from 180°
20 to 200° C for control (no borax or boric acid) specimens increased the wrinkle recovery angle, but resulted in a decrease in the whiteness index and in tensile strength. Inclusion of borax gave a higher wrinkle recovery angle, with retention of a high whiteness index at the higher temperature cure. Similar results were observed when boric acid was added.

25 Example 2Effect of Boron Compounds on the Color and Wrinkle Recovery of Cotton Treated with Technical Grade 1,2,3,4-Butanetetracarboxylic Acid in the Presence of Disodium Hydrogen Phosphate Curing Catalyst

 Treating solutions were prepared as in Example 1, except that technical grade
30 1,2,3,4-butanetetracarboxylic acid was used. Results are shown in Table 2. Addition of borax or boric acid to the treating solutions improved the whiteness index of the treated specimens, even at drying and curing at 190° C or 200° C.

Table I
Effect of Boron Compounds on the Whiteness and Wrinkle Recovery Angle
of Cotton Treated with Reagent Grade 1,2,3,4-Butanetetra-carboxylic Acid
(Disodium Hydrogen Phosphate Catalyst)

<u>Boron Compound</u>	<u>% Na₂HPO₄</u>	<u>Dry/Cure Temp. (° C)</u>	<u>Wrinkle Recovery Angle</u>	<u>Tensile Strength (lbs)</u>	<u>Whiteness Index (CIE)</u>
none	4.2	180	264	24.7	68.0
none	4.2	190	268	26.0	67.4
none	4.2	200	270	23.6	66.6
2.0% Na ₂ B ₄ O ₇ ·10H ₂ O	4.2	190	275	29.3	75.7
3.0% Na ₂ B ₄ O ₇ ·10H ₂ O	4.2	190	261	30.8	76.7
1.0% H ₃ BO ₃	4.2	190	261	29.0	75.6
2.0% Na ₂ B ₄ O ₇ ·10H ₂ O	4.2	200	268	24.2	74.3
3.0% Na ₂ B ₄ O ₇ ·10H ₂ O	4.2	200	260	28.5	74.3
1.0% H ₃ BO ₃	4.2	200	261	29.0	75.6
untreated fabric				47.2	78.8

Table 2
Effect of Boron Compounds on the Whiteness and Wrinkle Recovery Angle
of Cotton Treated with Technical Grade 1,2,3,4-Butanetetra-carboxylic Acid
(Disodium Hydrogen Phosphate Catalyst)

<u>Boron Compound</u>	<u>% Na₂HPO₄</u>	<u>Dry/Cure Temp. (° C)</u>	<u>Wrinkle Recovery Angle</u>	<u>Tensile Strength (lbs)</u>	<u>Whiteness Index (CIE)</u>
none	3.0	180	261	28.2	60.8
none	4.0	190	269	29.7	58.9
none	4.2	200	267	23.3	55.3
3.0% Na ₂ B ₄ O ₇ ·10H ₂ O	3.0	180	258	33.0	71.7
3.0% H ₃ BO ₃	3.0	180	243	33.0	71.2
2.0% H ₃ BO ₃	4.0	190	252	27.7	65.6
2.0% Na ₂ B ₄ O ₇ ·10H ₂ O	4.2	200	270	24.5	64.8
untreated fabric				47.2	78.8

-11-

Example 3Effect of Sodium Tetraborate on the Properties of Cotton Fabrics Crosslinked with a Mixture of 1,2,3,4-Butanetetracarboxylic Acid and Citric Acid in the Presence of Disodium Hydrogen Phosphate and Sodium Hypophosphite Curing Catalysts

5 Aqueous solutions of 3.2-4.2% by weight of 1,2,3,4-butanetetracarboxylic acid (BTCA) mixed with 2.1-3.2% by weight of citric acid, 0-4.2% by weight of disodium hydrogen phosphate and 0-3.2% by weight of sodium hypophosphite monohydrate catalysts, 1.0% by weight of emulsified nonionic polyethylene fabric softener, 0.1%
10 by weight of nonylphenol deca(ethylene oxide) wetting agent and 0-2.0% by weight of sodium tetraborate decahydrate decolorizing agent.

 The treating solution was applied as in Example 1 and the specimens were dried and cured at 200° C or 210° C. The whiteness index (CIE) was determined before laundering and tensile strength and wrinkle recovery angle were determined after one domestic washing and drying cycle. Results are presented in Table 3.

15 As shown in Table 3, specimens treated with baths containing no borax had low whiteness indexes, particularly when dried and cured at 210° C. Relatively good whiteness indexes were observed for specimens, treated with a mixture of BTCA and citric acid, notwithstanding the reputation of citric acid for causing yellowing of cotton fabrics. In addition, specimens treated with solutions contain-
20 ing both borax and citric acid had high wrinkle recovery angles and good tensile strength values.

 Inclusion of borax in treating solutions, containing sodium hypophosphite and disodium hydrogen phosphate, resulted in good whiteness, high tensile strength and high wrinkle recovery angles, even at lower concentrations of sodium hypophos-
25 phite than generally required (6.4%) to produce acceptable results. Therefore, treating solutions containing disodium hydrogen phosphate and borax, require less sodium hypophosphite than previously required for crosslinking cotton and give an undiscolored product.

-12-

Table 3
Effect of Sodium Tetraborate on the Properties of Cotton Fabric Treated with 1,2,3,4-Butanetetracarboxylic
and Citric Acids (Disodium Hydrogen Phosphate and Sodium Hypophosphite Catalysts)

$\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$ (%)	Catalyst (%)		CA	BTCA (%)	Dry/Cure		Wrinkle Recovery Angle (°)	Tensile Strength (lb)	Whiteness Index (CIE)
	Na_2HPO_4	$\text{NaH}_2\text{PO}_4 \cdot \text{H}_2\text{O}$			Temp. (°C)	Angle (°)			
none	4.2	none	2.1	4.5	200	289	23.3	64.3	
none	4.2	none	2.1	4.5	210	288	24.0	50.0	
2.0	4.2	none	2.1	4.5	200	264	26.0	73.9	
2.0	4.2	none	2.1	4.5	210	280	24.0	68.4	
none	none	6.4	2.1	4.5	200	294	20.5	47.8	
none	none	6.4	2.1	4.5	210	300	20.3	39.0	
none	2.1	3.2	2.1	4.5	200	307	25.3	63.8	
none	2.1	3.2	2.1	4.5	210	302	22.8	54.0	
2.0	2.1	3.2	2.1	4.5	200	284	25.8	74.8	
2.0	2.1	3.2	2.1	4.5	210	294	24.0	73.2	
2.0	none	3.2	2.1	4.5	200	268	22.8	62.2	
2.0	none	3.2	2.1	4.5	210	276	21.7	58.8	
none	4.2	none	3.2	3.2	200	252	20.1	45.4	
none	4.2	none	3.2	3.2	210	263	22.6	19.1	
2.0	4.2	none	3.2	3.2	200	246	20.0	68.0	
2.0	4.2	none	3.2	3.2	210	255	22.5	57.3	
none	2.1	3.2	3.2	3.2	200	263	20.7	60.3	
none	2.1	3.2	3.2	3.2	210	262	20.4	48.9	
2.0	2.1	3.2	3.2	3.2	200	249	20.7	73.2	
2.0	2.1	3.2	3.2	3.2	210	262	21.3	67.6	

-13-

Example 4Effect of Sodium Tetraborate on the Properties of Cotton Crosslinked with 1,2,3,4-Butanetetracarboxylic Acid in the Presence of Disodium Hydrogen Phosphate and Oxalic Acid Catalysts

5 Aqueous solutions, containing 6.4% by weight of BTCA crosslinking agent, 4.2% by weight of disodium hydrogen phosphate and 1.0-2.0% by weight of oxalic acid catalyst, 1.0% by weight of emulsified nonionic polyethylene fabric softener, 0.1% by weight of nonylphenol deca(ethylene oxide) and 2.0% by weight of sodium tetraborate decahydrate decolorizing agent, were prepared and applied to cotton
10 specimens as in the foregoing examples. Results are presented in Table 4.

 These results show that cellulose, cured with BTCA and oxalic acid in a treating solution containing sodium tetraborate decahydrate, at a very high temperature (210° C) have good wrinkle recovery angle and reasonable tensile strength and whiteness.

15 Example 5Effect of Sodium Tetraborate on the Shade of Dyed Fabrics, Treated with 1,2,3,4-Butanetetracarboxylic Acid and Citric Acid Crosslinking Agents in the Presence of Disodium Hydrogen Phosphate and Sodium Hypophosphite Catalysts

 Aqueous solutions, containing 4.5-6.4% by weight of 1,2,3,4-butanetetracarboxylic acid, 0-4.2% by weight of disodium hydrogen phosphate, 0-6.4% by
20 weight of sodium hypophosphite monohydrate, 0-2.1% by weight of citric acid, 1.0% by weight emulsified nonionic polyethylene fabric softener, 0.1% by weight of nonylphenol deca(ethylene oxide) wetting agent and 0-3.0% by weight of sodium tetraborate decahydrate, were prepared. The solutions were used to impart
25 wrinkle resistance to samples of 100% cotton fabric, dyed with representative sulfur dyes, vat dyes, fiber-reactive dyes or naphthol dyes. The dyed samples were immersed in the treating solution and pad dried by being passed through the squeeze rolls of a wringer to a wet pick-up of 90-110% by weight of treating
 solution on the fabric specimen. The fabric specimens were dried and cured in a
30 forced draft oven at the temperature specified for 4 min. The color shades of treated and untreated fabrics are compared in the results of Table 5.

 Specimens treated with BTCA and sodium hypophosphite exhibit marked changes in color shade. Addition of borax to the treating composition markedly

-14-

Table 4
Effect of Sodium Tetraborate on the Properties of Cotton Fabric Treated with 1,2,3,4-Butanetetra-carboxylic Acid
(Disodium Hydrogen Phosphate or Oxalic Acid Catalysts)

$\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$ (%)	Catalyst (%)		Dry/Cure Temp. ($^{\circ}\text{C}$)	Wrinkle Recovery		Tensile Strength (lb)	Whiteness Index (CIE)
	Na_2HPO_4	Oxalic Acid		Angle ($^{\circ}$)	Angle ($^{\circ}$)		
2.0	4.2	none	200	268	268	24.2	74.3
2.0	4.2	2.0	200	258	258	24.3	70.1
2.0	4.2	1.0	200	254	254	27.3	67.4
2.0	4.2	none	215	265	265	24.3	61.7
2.0	4.2	2.0	215	281	281	20.7	57.4
2.0	4.2	1.0	215	268	268	25.0	66.6

-15-

Table 5
Effect of Sodium Tetraborate on the Shade of Dyed Fabrics, Crosslinked with
1,2,3,4-Butanetetra-carboxylic and Citric Acids
(Disodium Hydrogen Phosphate and/or Sodium Hypophosphite Catalysts)

BTCA (%)	6.4	6.4	4.5	4.5	4.5	4.5
$\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$ (%)	none	2.0	none	2.0	3.0	2.0
Na_2HPO_4 (%)	none	4.2	2.1	2.1	2.1	4.2
$\text{NaH}_2\text{PO}_4 \cdot \text{H}_2\text{O}$ (%)	6.4	none	3.2	3.2	3.2	none
Citric acid (%)	none	none	2.1	2.1	2.1	2.1
Dry/cure temp. ($^{\circ}\text{C}$)	193	193	193	193	193	193
Sulfur dye (green)	OC*	NC	OC	SC	SC	NC
Vat dye (Blue No. 6)	OC	NC	OC	SC	SC	NC
Fiber reactive dye (violet)	OC	NC	OC	SC	NC	NC
Naphthol dye (red)	OC	NC	SC	NC	NC	NC

*OC = obvious change in color shade, compared to untreated dyed fabric

SC = slight change

NC = no visible change

-16-

reduced the changes in color shade, compared to an untreated control. Similar improvement in dye shade retention resulted from addition of borax to a treating solution, containing BTCA, citric acid, sodium hypophosphite and disodium hydrogen phosphate.

- 5 The preceding examples can be repeated with similar success by substituting the generically or specifically described reactants and/or operating conditions of this invention for those used in the preceding examples.

- 10 From the foregoing description, one skilled in the art can easily ascertain the essential characteristics of this invention and, without departing from the spirit and scope thereof, can make various changes and modifications of the invention to adapt it to various usages and conditions.

-17-

Claims:

1. A process for reducing discoloration of fibrous cellulosic material treated at temperatures above about 175° C. with a treating solution of a polycarboxylic acid and a phosphate salt curing catalyst, comprising adding to the treating solution an inorganic boron-oxygen compound.
2. The process of claim 1, wherein the cellulosic material is treated at 180-250° C.
3. The process of claim 1, wherein the polycarboxylic acid is maleic acid, citraconic acid, citric acid, itaconic acid, tricarballic acid, trans-aconitic acid, 1,2,3,4-butanetetracarboxylic acid, all-cis-1,2,3,4-cyclopentanetetracarboxylic acid, mellitic acid, oxydisuccinic acid or oxalic acid or a mixture thereof.
4. The process of claim 1, wherein the phosphate salt curing catalyst is an alkali metal hypophosphite, phosphite, pyrophosphate, tripolyphosphate, hexametaphosphate, monohydrogen phosphate or dihydrogen phosphate or a mixture thereof.
5. The process of claim 1, wherein the inorganic boron-oxygen compound is boric acid.
6. The process of claim 1, wherein the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.
7. The process of claim 1, wherein the phosphate salt curing catalyst is disodium hydrogen phosphate.
8. The process of claim 1, wherein the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof.
9. The process of claim 1, wherein the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid.

-18-

10. The process of claim 1, wherein the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid.

11. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

12. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

13. The process of claim 1, wherein the cellulosic material is treated at 180-250° C; the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate or hydrates thereof and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

14. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

15. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is boric acid.

16. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is boric acid.

-19-

17. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate or hydrates thereof and the
5 inorganic boron-oxygen compound is boric acid.

18. The process of claim 1, wherein the cellulosic material is treated at 180-250° C, the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof and the inorganic boron-oxygen compound is boric acid.

19. The process of claim 1, wherein the phosphate salt curing catalyst is a mixture of disodium hydrogen phosphate and sodium hypophosphite or a hydrate thereof.

20. The process of claim 1, wherein the inorganic boron-oxygen compound is a mixture of boric acid and sodium tetraborate or a hydrate thereof.

21. The process of claim 1, wherein the cellulosic material contains at least 30% by weight of cellulosic fibers, selected from the group consisting of cotton, flax, jute, hemp, ramie and regenerated unsubstituted wood cellulose.

22. The process of claim 1, wherein the cellulosic material is in the form of knit, woven or nonwoven fabrics.

23. The process of claim 1, wherein the cellulosic material contains 50-100% of cotton fiber.

24. The process of claim 1, wherein the cellulosic material is white or dyed knit, woven or nonwoven fabric.

25. The process of claim 1, wherein the treating solution contains from about 0.5% to about 20% by weight of polycarboxylic acid.

-20-

26. The process of claim 1, wherein the treating solution contains from about 0.25% to about 10% by weight of the phosphate salt curing catalyst.

27. The process of claim 1, wherein the treating solution contains from about 0.5% to about 10% by weight of the inorganic boron-oxygen compound.

[received by the International Bureau on 26 July 1993 (26.07.93):
original claims 1-27 replaced by amended claims 1-27 (3 pages)]

1. A process for reducing the formation of discoloration in fibrous cellulosic material treated at temperatures above about 1750C with an aqueous durable-press treating solution of a polycarboxylic acid selected from aliphatic, alicyclic and aromatic acids, containing at least two carboxylic acid groups; a phosphate salt curing catalyst selected from alkali metal hypophosphites, alkali metal phosphites, alkali metal salts of orthophosphoric acid and hydrates thereof; comprising adding to the aqueous durable-press treating solution an inorganic boron-oxygen compound selected from alkali metal metaborates, alkali metal tetraborates, alkali metal pentaborates and boric acid and heating the fibrous cellulosic material in the resulting treating bath at a temperature above about 1750 to block the formation of said discoloration while imparting durable-press properties to thus-treated cellulosic fibrous material.

2. The process of claim 1, wherein the cellulosic material is treated at 180-2050C.

3. The process of claim 1, wherein the polycarboxylic acid is maleic acid, citraconic acid, citric acid, itaconic acid, tricarballic acid, transaconitic acid, 1, 2, 3, 4-butanetetracarboxylic acid, all-cis-1, 2, 3, 4-cyclopentanetetracarboxylic acid, mellitic acid or oxydisuccinic acid or a mixture thereof.

4. The process of claim 1 wherein the phosphate salt curing catalyst is an alkali metal hypophosphite, phosphite, pyrophosphate, tripolyphosphate, hexametaphosphate, monohydrogen phosphate or dihydrogen phosphate or a mixture thereof.

5. The process of claim 1, wherein the inorganic boron-oxygen compound is boric acid.

6. The process of claim 1, wherein the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

7. The process of claim 1, wherein the phosphate salt curing catalyst is disodium hydrogen phosphate.

8. The process of claim 1, wherein the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof.

9. The process of claim 1, wherein the polycarboxylic

acid is 1,2,3,4-butanetetracarboxylic acid.

10. The process of claim 1, wherein the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid.

11. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C., the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

12. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C., the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

13. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C.; the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate or hydrates thereof and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

14. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C., the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof and the inorganic boron-oxygen compound is sodium tetraborate or a hydrate thereof.

15. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C., the polycarboxylic acid is 1,2,3,4-butanetetracarboxylic acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is boric acid.

16. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C., the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is disodium hydrogen phosphate and the inorganic boron-oxygen compound is boric acid.

17. The process of claim 1 wherein the cellulosic material is treated 1800-25-0C., the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is a mixture of sodium hypophosphite and disodium hydrogen phosphate or hydrates thereof and the inorganic boron-oxygen compound is boric acid.

18. The process of claim 1 wherein the cellulosic material is treated at 1800-2500C., the polycarboxylic acid is a mixture of 1,2,3,4-butanetetracarboxylic acid and citric acid, the phosphate salt curing catalyst is sodium hypophosphite or a hydrate thereof and the inorganic boron-oxygen compound is boric acid.

19. The process of claim 1 wherein the phosphate salt curing catalyst is a mixture of disodium hydrogen phosphate and sodium hypophosphite or a hydrate thereof.

20. The process of claim 1 wherein the inorganic boron-oxygen compound is a mixture of boric acid and sodium tetraborate or a hydrate thereof.

21. The process of claim 1 wherein the cellulosic material contains at least 30% by weight of cellulosic fibers, selected from the group consisting of cotton, flax, jute, hemp, ramie and regenerated unsubstituted wood cellulose.

22. The process of claim 1 wherein the cellulosic material is in the form of knit, woven or nonwoven fabrics.

23. The process of claim 1 wherein the cellulosic material contains 50-100% of cotton fiber.

24. The process of claim 1 wherein the cellulosic material is white or dyed knit, woven or nonwoven fabric.

25. The process of claim 1 wherein the treating solution contains from about 0.5% to about 20% by weight of polycarboxylic acid.

26. The process of claim 1 wherein the treating solution contains from about 0.25% to about 10% by weight of the phosphate salt curing catalyst.

27. The process of claim 1 wherein the treating solution contains from about 0.5% to about 10% by weight of the inorganic boron-oxygen compound.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/02635

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :D06M 11/00, 11/71,11/72,11/82,13/192

US CL :8/120,115.68,116.1,127.1

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : NONE

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
NONE**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,E	US,A, 5,199,953 (FUNG ET AL) 06 APRIL 1993 See claims 1-27 at cols 11-12	1-27
Y	US,A, 4,820,307 (WELCH ET AL) 11 APRIL 1989 See col. 3, lines 14-49; col. 4, lines 44-60; col. 5, lines 9-23; and col. 7, line 37 through col. 8, line 2	1-27
A	US,A, 3,526,048 (ROWLAND ET AL) 01 SEPTEMBER 1970 See col. 2, lines 36-48; and col. 3, lines 34-67	1-27

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* "A"	Special categories of cited documents: document defining the general state of the art which is not considered to be part of particular relevance	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"E"	earlier document published on or after the international filing date	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O"	document referring to an oral disclosure, use, exhibition or other means	"Z"	document member of the same patent family
"P"	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

26 APRIL 1993

Date of mailing of the international search report

30 JUN 1993

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

Nguyen Nguyen
ALAN DIAMONDEGUYEN NGOC HO
INTERNATIONAL DIVISION
Telephone No. (703) 308-2517

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/02635

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A, 5,042,986 (KITCHENS ET AL) 27 AUGUST 1991 See col. 2, lines 51-61; and col. 3, lines 9-22	1-27
A	US,A, 5,145,485 (MICHNA ET AL) 08 SEPTEMBER 1992 See Abstract	1-27
A	US,A, 5,190,563 (HERRON ET AL) 02 MARCH 1993 See Abstract	1-27