



(22) Date de dépôt/Filing Date: 1993/09/29
(41) Mise à la disp. pub./Open to Public Insp.: 1994/04/02
(45) Date de délivrance/Issue Date: 2004/04/27
(30) Priorité/Priority: 1992/10/01 (07/955,065) US

(51) Cl.Int.⁵/Int.Cl.⁵ C09J 133/00
(72) Inventeur/Inventor:
CHAO, HUNG YA, US
(73) Propriétaire/Owner:
MOORE WALLACE, INC., US
(74) Agent: SMART & BIGGAR

(54) Titre : ADHESIF AUTOCOLLANT
(54) Title: PRESSURE SENSITIVE ADHESIVE

(57) **Abrégé/Abstract:**

A pressure sensitive adhesive is disclosed that is tack-free to the touch, but forms a permanent bond under moderate pressure. The pressure sensitive adhesive contains a tacky adhesive latex, a non-tacky latex or polymer, and an inert filler. The tacky adhesive latex provides the sealing properties, the non-tacky latex or polymer provides blocking properties and the filler absorbs oil that may adversely affect the sealing properties. The adhesive tack-free to the touch yet becomes activated to form a permanent bond under moderate sealing pressure.



2107264

Abstract of the Disclosure

A pressure sensitive adhesive is disclosed that is tack-free to the touch, but forms a permanent bond under moderate pressure. The pressure sensitive adhesive contains a tacky adhesive latex, a non-tacky latex or polymer, and an inert filler. The tacky adhesive latex provides the sealing properties, the non-tacky latex or polymer provides blocking properties and the filler absorbs oil that may adversely affect the sealing properties. The adhesive is tack-free to the touch yet becomes activated to form a permanent bond under moderate sealing pressure.

LAW OFFICES

WENEGAN, HENDERSON
FARABOW, GARRETT
& DUNNER

1300 I STREET, N. W.
WASHINGTON, DC 20005
1-202 408-4000

-1A-

1 Background of the Invention

 The present invention relates to a pressure sensitive adhesive composition and its application.

5 The majority of pressure sensitive adhesives disclosed by the prior art are tacky to the touch and present difficulties in storage and handling because they tend to exhibit "blocking" properties, i.e., they tend to adhere to themselves when stored on a reel. Thus, there exists a need for a pressure sensitive adhesive that is initially tack-free, but forms a permanent bond
10 upon moderate sealing pressure.

 U.S. Patent No. 4,889,884 to Dust et al. discloses an adhesive that is capable of forming a seal to itself with application of pressure, yet resists blocking. However, Dust et al. does not disclose the presence of a filler. As a result,
15 silicone oil, often used in the nip for cut sheet forms to protect the fused roll, would be expected to migrate to the surface of the adhesive and interfere with the sealing operation. Thus, there is an additional need for a pressure sensitive adhesive whose adhesive properties will not be
20 adversely affected by contact with silicone oil.

Summary of the Invention

 Accordingly, it is an object of the present invention to overcome these and other disadvantages of the prior art.

LAW OFFICES

FINNEGAN, HENDERSON
25 RABOW, GARRETT
& DUNNER

1300 I STREET, N. W.
WASHINGTON, DC 20005
1-202-408-4000

72049-109

It is another object of the invention to provide a pressure sensitive adhesive that is tack-free to the touch, but forms a permanent bond under moderate bonding pressure.

It is another object of the invention to provide a
5 pressure sensitive adhesive that will not be adversely affected by contact with silicone or other oils.

These and other objects are achieved by the pressure sensitive adhesive of the invention which comprises a tacky adhesive latex, a non-tacky latex or polymer, and an
10 inert filler. The adhesives prepared according to this invention are tack-free to the touch yet become activated to form a permanent bond under moderate sealing pressure.

More particularly according to the present invention, there is provided a pressure sensitive adhesive
15 composition comprising a tacky adhesive latex, a non-tacky latex or polymer, and an inert filler, wherein said components are present in an amount effective to create an adhesive that is tack-free to the touch but forms a permanent bond upon the application of pressure and wherein
20 said inert filler is present in an amount effective to absorb oil; said tacky adhesive latex present in an amount ranging from about 54 to about 84% by weight, said non-tacky latex or polymer present in an amount ranging from about 2 to about 25% by weight, and said inert filler present in
25 an amount ranging from about 8 to about 35% by weight (the weight ratios based on the total composition).

Additional objects and advantages of the invention will be set forth in part in the description which follows, and in part will be apparent from the description, or may be

72049-109

learned by practice of the invention. The objects and advantages of the invention will be realized and attained by means of the compounds, composition and processes particularly pointed out in the written description and
5 appended claims.

Detailed Description of the Preferred Embodiments

The first component of the adhesive of the present invention, a tacky adhesive latex, is generally a permanent acrylic-type adhesive latex. Acrylic emulsions such as
10 Robond* PS-60, Robond* PS-61, and Rhoplex* N-619 (marketed by Rohm & Haas Co., Philadelphia, PA) and Gelva* RA 2397, RA 2404, and RA 2373 (marketed by Monsanto Co., St. Louis, MO) are examples of the tacky adhesive latex that may be used in accordance with the invention. Generally,
15 these adhesives are copolymers of (1) a flexible alkyl acrylate or methacrylate having about 4 to about 12 carbon atoms, (2) a hard alkyl acrylate or methacrylate having 1 to about 4 carbon atoms, and (3) a functional monomer such as acrylic acid, methacrylic acid or vinyl pyrrolidone, or
20 multifunctional monomers such as difunctional or trifunctional acrylates or methacrylates. The tacky material is the main ingredient, incorporated to produce a fiber tearing bond when sealing pressure is applied.

The second component of the composition of the
25 invention may be either a non-tacky latex or a non-tacky polymer, or combinations thereof. Appropriate examples of non-tacky latexes that may be used include acrylate latexes, such as Rhoplex* P-376 and B-85 (marketed by Rohm & Haas Co., Philadelphia, PA) and styrene-butadiene latexes such as

*Trade-mark

72049-109

Dow latex* 620, 640 and 650 (marketed by Dow Chemical, Midland, MI). Appropriate examples of non-tacky polymers that may be used include adhesive-compatible, water-soluble polymers such as polyvinyl alcohol, starch and cellulose derivatives. The non-tacky material is incorporated to provide the anti-block characteristics of the adhesives during form handling and storage. Too much of this non-tacky material will reduce the sealing properties, while too little will result in blocking of the forms together.

10 The final component of the composition is an inert filler. Examples of appropriate fillers that may be used include high capacity oil-absorbing silicate powder, silica, titanium dioxide, clays, and mixtures thereof. The inert filler is incorporated to absorb oil. Generally, when
15 silicone oil is used in the nip for sheet cut forms to protect the fuser roll, migration of the material to the adhesive surface will interfere with the sealing operation. The high oil-absorbing filler is incorporated to absorb this oil. The adhesive strength is greatly decreased if the
20 filler is overdosed. However, the oil-absorbing capability will be insufficient if it is underdosed.

A small amount of pigment or dye may also be added to make the adhesive-coated substrate more appealing to the eye.

25 The composition of the present invention preferably contains about 54 to about 84 parts of tacky adhesive latex, about 2 to about 25 parts of non-tacky latex or polymer and about 8 to about 35 parts of inert filler based upon 100 total parts, on a weight basis.

*Trade-mark

72049-109

The composition according to the invention generally has a solids content of about 25 to about 40%, a pH of about 7 to about 10 and a viscosity of about 200 to about 2000 cps.

5 The composition of the invention can be coated on a substrate such as a sheet of about 12 to about 28 # bond paper at about 3.5 to about 15 microns thickness. Lab wire wound coating rod or production roll coaters can be adapted to perform the coating. Spraying, dipping or printing
10 methods can also be

1 employed. Other substrates may be coated besides paper, such as
metal foil, polymer fibers such as cellophane, polyethylene
terephthalate, olefin polymers and the like. After the adhesive
5 mixture has been drawn onto the substrate, the sheet is allowed
to dry or is passed through a heated oven to obtain a tack-free
sheet.

The following examples are illustrative. Unless otherwise
indicated, amounts shown are in parts by weight. The following
testing procedures were used to determine % seal and % blocking.

10 Sealing Test Procedure

1. Coated sheets were cut into 3" by 8" rectangles.
2. The coated sheets were positioned adhesive-to-adhesive
-- 10 sets were tested.
3. Coated sheets were sealed on a lab sealer at the
15 conditions specified in the examples.
4. The sealed samples were slowly peeled apart and the %
of samples with fiber tearing seals was recorded. This number
was the % seal.

20 Blocking Test Procedure

This test measures paper to pressure-seal adhesive
blocking. The test requires one 4 x 5 inch (1/4 inch thick)
piece of stainless steel for a base, one 1 x 3 inch (1 inch
thick) piece of aluminum for the top, and a 6 pound weight.

1. 1 x 3 inch samples were cut from identical areas from
20 identical samples of sheets coated with adhesive.

72049-109

2. The sample strips were stacked and aligned.

3. The aligned stack was placed on the stainless steel base and placed into the preheated oven (220°F).

4. The top piece of aluminum was carefully placed
5 onto the stack.

5. The 6-pound weight was placed on top of the stack and the oven door was closed.

6. After 30 minutes, the samples were removed from the oven and checked for any blocking (sticking
10 together). The % of samples with blocking was recorded. This number was the % blocking.

Example 1

56.6 parts of Robond* PS-61 Latex (an acrylic latex, from Rohm and Haas) was compounded with 8 parts of
15 dry Cabosil* 5M (a silica from Peltz Rowley Chemicals) and 24 parts of Dow latex* 620 (50% solid). The resultant mixture was drawn down onto a 24# OCR bond paper and dried to 10-12 microns thickness. The coating is tack-free to the touch, yet it forms a good fiber tearing bond on a blank
20 bond paper under 200 psi seal pressure.

Examples 2-5

Robond* PS-60 acrylate latex was compounded with Rhoplex* latex B-85, and Cab-o-sperse* (a colloidal silica from Cabot Corp.) and coated on 24# bond paper. The coating
25 was assembled with a blank sheet and sealed under 100 psi pressure. The assembled sheets were placed in a 65°C oven

*Trade-mark

72049-109

for 7 days, after which % seal was tested and recorded.
Results are shown below.

<u>Ex.</u>	<u>PS-60</u>	<u>B-85</u>	<u>Silica</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
2	73	12	15	6.5	some	100
3	77	8	15	6.0	some	100
4	68	12	20	7.9	0	100
5	72	8	20	5.5	0	100

Examples 6-9

5 Robond* PS-60 acrylate latex was compounded with
Rhoplex* latex P-376, and Cab-o-sperse* and coating on
24# bond paper. The coating was assembled with a blank
sheet and sealed under 100 psi pressure. The assembled
sheets were placed in a 65°C oven for 7 days, after which
10 % seal was tested and recorded. Results are shown below.

<u>Ex.</u>	<u>PS-60</u>	<u>B-376</u>	<u>Silica</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
6	80	10	10	5.1	0	100
7	72	6	22	4.6	0	100
8	68	16	16	5.5	0	100
9	72	8	20	5.5	0	100

Examples 10-11

Robond* PS-60 acrylate latex was compounded with
Dow latex* 620, and Exsilon* (a silicate powder from
15 Engelhard Chemicals) and coated on 24# bond paper. The

*Trade-mark

72049-109

coating was assembled with a blank sheet and sealed under 100 psi pressure. The assembled sheets were placed in a 65°C oven for 7 days, after which % seal was tested and recorded. Results are shown below.

<u>Ex.</u>	<u>PS-60</u>	<u>Exsilon*</u>	<u>Dow* 620</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
10	70	10	20	9.1	0	100
11	64	30	6	8.9	0	100

5

Examples 12-14

Robond* PS-60 acrylate latex was compounded with Dow latex* 620 and titanium dioxide and coated on 24# bond paper. The coating was assembled with a blank sheet and sealed under 100 psi pressure. The assembled sheets were placed in a 65°C oven for 7 days, after which % seal was tested and recorded. Results are shown below.

<u>Ex.</u>	<u>PS-60</u>	<u>Titanium Dioxide</u>	<u>Dow 620</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
12	70	20	10	7.3	0	100
13	64	30	6	6.7	0	100
14	84	12	4	5.9	0	100

Examples 15-27

Robond* PS-60 acrylate latex was compounded with Dow latex* 620 and Cab-o-sperse* and coated on 24# bond paper. % Seal was tested after 7 days of aging at 95%

*Trade-mark

72049-109

humidity, 37°C. Sealing pressure was set at 60 psi.
Results are shown below.

<u>Ex.</u>	<u>PS-60</u>	<u>Latex</u>	<u>Silica</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
15	54	12	34	5.2	0	5
16	54	12	34	4.5	0	0
17	60	6	34	5.9	0	5
18	60	6	34	4.8	0	50
19	64	9	27	4.1	0	100
20	64	9	27	5.0	0	100
21	68	12	20	4.6	10	80
22	68	12	20	3.7	0	55
23	72	6	22	6.5	0	100
24	74	6	20	4.1	0	100
25	74	6	20	4.2	0	100
26	75	10	15	7.5	0	100
27	80	10	10	8.8	0	100

At 100 psi sealing pressure, every sample sealed.

5 Examples 28-30

Gelva* 2397 (from Monsanto) was compounded with Rhoplex* B-85 and Cab-o-sperse* and coated on 24# bond paper. The coating was assembled with a blank sheet and sealed under 100 psi pressure. The assembled sheets were placed in a 65°C oven for 7 days, after which % seal was tested and recorded. Results are shown below.

*Trade-mark

72049-109

<u>Ex.</u>	<u>Gelva*</u> <u>2397</u>	<u>Silicate</u>	<u>B-85</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
28	70	24	6	6.7	0	100
29	68	24	8	5.3	0	100
30	66	24	10	7.1	0	100

Examples 31-33

Robond* PS-60 acrylate latex was compounded with Vinol* 523 (a partially hydrolyzed polyvinyl alcohol from 5 Air Products and Chemicals), and Nipsil* (a Japanese colloidal silica) and coated on 24# bond paper. % Seal was tested after 7 days of aging at 60°C. Sealing pressure was set at 100 psi. Results are shown below.

<u>Ex.</u>	<u>PS-60</u>	<u>Vinol</u>	<u>Silica</u>	<u>Caliper (u)</u>	<u>% Blocking</u>	<u>% Seal</u>
31	78	2	20	5.1	0	100
32	74	2	24	5.1	0	100
33	76	3	21	5.7	0	100

*Trade-mark

2107264

1 Other embodiments of the invention will be apparent to
those skilled in the art from consideration of the specification
and practice of the invention disclosed herein. It is intended
that the written description of the specification and examples
5 be considered exemplary only, with the true scope and spirit of
the invention being indicated by the appended claims.

LAW OFFICES

FINNEGAN, HENDERSON
FARABOW, GARRETT
& DUNNER

1300 I STREET, N. W.
WASHINGTON, DC 20005
1-202 408-4000

72049-109

CLAIMS:

1. A pressure sensitive adhesive composition comprising a tacky adhesive latex, a non-tacky latex or polymer, and an inert filler, wherein said components are present in an amount effective to create an adhesive that is tack-free to the touch but forms a permanent bond upon the application of pressure and wherein said inert filler is present in an amount effective to absorb oil; said tacky adhesive latex present in an amount ranging from about 54 to about 84% by weight, said non-tacky latex or polymer present in an amount ranging from about 2 to about 25% by weight, and said inert filler present in an amount ranging from about 8 to about 35% by weight (the weight ratios based on the total composition).
2. The composition of claim 1, wherein said tacky adhesive latex is an acrylic-type latex.
3. The composition of claim 2, wherein said tacky adhesive latex is a copolymer of (a) a flexible alkyl acrylate or methacrylate having from 4 to 12 carbon atoms, (b) a hard alkyl acrylate or methacrylate having 1 to 4 carbon atoms, and (c) a functional or multifunctional monomer.
4. The composition of claim 3, wherein said functional monomer is selected from the group consisting of acrylic acid, methacrylic acid, and vinyl pyrrolidone; and said multifunctional monomer is selected from the group consisting of difunctional acrylates, trifunctional acrylates, and methacrylates.
5. The composition of any one of claims 1 to 4, wherein said non-tacky latex or polymer is selected from the

72049-109

group consisting of acrylate latexes, styrene-butadiene latexes, polyvinyl alcohol, starch, cellulose, and derivatives thereof.

6. The composition of any one of claims 1 to 5,
5 wherein said inert filler is selected from the group consisting of silica, silicate powders, titanium dioxide, clays, and mixtures thereof.

7. The composition of any one of claims 1 to 6, further comprising a pigment or dye.

SMART & BIGGAR
OTTAWA, CANADA

PATENT AGENTS