

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 714 757 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

25.10.2006 Bulletin 2006/43

(51) Int Cl.:

B27K 3/15 (2006.01)

(21) Application number: **06251971.5**

(22) Date of filing: **07.04.2006**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI
SK TR**

Designated Extension States:

AL BA HR MK YU

(30) Priority: **21.04.2005 US 673556 P**

08.03.2006 US 780431 P

(71) Applicant: **Rohm and Haas Company**

Philadelphia, PA 19106-2399 (US)

(72) Inventors:

- **Ashmore, John William
Lansdale, PA 19446 (US)**
- **Ghosh, Tirthankar
Oreland, PA 19075 (US)**
- **Lalas, Jose Pineda
Harleysville, PA 19438 (US)**

(74) Representative: **Kent, Venetia Katherine et al**

**Rohm and Haas (UK) Ltd.
European Patent Department
4th Floor, 22 Tudor Street
London EC4Y 0AY (GB)**

(54) **Wood preservatives**

(57) A method for preserving wood by contacting wood with a composition comprising an aqueous polymer dispersion, at least one surfactant, and a wood preservative.

EP 1 714 757 A1

Description

[0001] The present invention relates to a method for treating wood to impart protection from wood-decaying organisms.

[0002] Use of waterborne polymers and biocides to treat wood has been reported, for example in WO 96/27483, which discloses a combination of surface treatment and implantation of biocide. However, implantation of biocide is not cost-effective nor practical, especially when treating large quantities of wood at a commercial treating facility.

[0003] The problem addressed by this invention is the need for a wood treatment method capable of imparting active ingredients further below the surface of wood than previously known methods without mechanical implantation of material.

STATEMENT OF THE INVENTION

[0004] The present invention is directed to a method for preserving wood by contacting wood with a composition comprising: (a) an aqueous polymer dispersion having an average particle size less than 1000 nm, in which the polymer has a T_g less than 75°C; (b) at least one surfactant selected from among nonionic and anionic surfactants; and (c) at least one wood preservative selected from among halogenated isothiazolone biocides, halogenated carbamate fungicides and azole fungicides.

[0005] The present invention is further directed to a method for preserving wood; said method comprising contacting wood with a composition comprising: (a) a polymer; (b) an organic solvent; and (c) at least one wood preservative selected from among halogenated isothiazolone biocides, halogenated carbamate fungicides and azole fungicides.

DETAILED DESCRIPTION OF THE INVENTION

[0006] All percentages and ppm values are on the basis of total weight of the composition, unless otherwise indicated. When the wood preservative is a halogenated isothiazolone biocide it preferably comprises a 3-isothiazolone having a C_4 - C_{12} N-alkyl substituent, more preferably a chlorinated 3-isothiazolone, and most preferably 4,5-dichloro-2-n-octyl-4-isothiazolin-3-one ("DCOIT"). The halogenated carbamate fungicide preferably comprises an iodopropargyl carbamate, such as IPBC, N n-butyl iodopropargyl carbamate. The term azole fungicide preferably comprises a triazole fungicide, more preferably Tebuconazole ((RS)-1-p-chlorophenyl-4,4-dimethyl -3-(1H-1,2,4-triazol-1-ylmethyl)pentan-3-ol) or Propiconazole (cis-trans-1-[2-(2,4-dichlorophenyl)-4-propyl-1,3-dioxolan-2-ylmethyl]-1H-1,2,4-triazole). Mixtures of wood biocides may be used. The term "acrylic polymers" refers to polymers comprising at least 50% monomer units derived from among acrylonitrile (AN); acrylamide (AM) and its N-substituted derivatives; acrylic acid (AA), methacrylic acid (MAA), and their esters; and itaconic acid (IA). Esters of AA and MAA include, but are not limited to, methyl methacrylate (MMA), ethyl methacrylate (EMA), butyl methacrylate (BMA), ethylhexyl methacrylate (EHMA), lauryl methacrylate (LMA), hydroxyethyl methacrylate (HEMA), methyl acrylate (MA), ethyl acrylate (EA), butyl acrylate (BA), ethylhexyl acrylate (EHA) and hydroxyethyl acrylate (HEA), phosphoethyl methacrylate (PEM) as well as other esters of AA or MAA, e.g., alkyl, hydroxyalkyl and aminoalkyl esters. Derivatives of acrylamide include, e.g., methylol acrylamide (MLAM). Acrylic polymers also may contain monomer units derived from other ethylenically unsaturated monomers, e.g., styrene or substituted styrenes; other α,β -unsaturated carboxylic acids, esters and amides; vinyl esters or halides; etc. Preferably, an acrylic polymer contains less than 30% of these other monomer units, more preferably less than 10%, and most preferably the acrylic polymers are substantially free of monomer units other than those of AA, MA and their esters. An "acrylic-styrene copolymer" is a polymer at least 50% of whose monomer units are derived from among AA, MAA, esters of AA and MAA, AN, and styrene monomers. Styrene monomers include styrene (Sty) and substituted styrenes, e.g., α -methylstyrene (AMS). Preferably, acrylic-styrene copolymers contain less than 20% of monomer units other than styrene or acrylic monomer units, more preferably less than 10%, and most preferably less than 5%. An "acrylic-vinyl acetate copolymer" is a polymer at least 50% of whose monomer units are derived from among AA, MAA, esters of AA and MAA, and vinyl acetate (VA). Preferably, acrylic-vinyl acetate copolymers contain less than 20% of monomer units other than acrylic or vinyl acetate monomer units, more preferably less than 10%, and most preferably less than 5%.

[0007] Polyurethane polymers also are suitable for use in this invention. Polyurethane polymers typically are formed from reaction of isocyanates with polyols, but may contain other functional groups derived from reaction of isocyanates with other monomers, e.g., amide groups derived from carboxylic acids, and ureas derived from amines, e.g. ethylene diamine (EDA) or other polymers, such as polyesters, e.g., polyesters derived from adipic acid and 1,6-hexanediol, 1,4-butanediol and/or neopentyl glycol, or polycarbonates, e.g. polycarbonates derived from poly 1,6-hexanediol carbonate. Suitable isocyanates include, e.g., methylene bis(4-cyclohexylisocyanate) (MCI), methylene bis(4-phenylisocyanate) (MDI), hexamethylene diisocyanate (HDI), isophorone diisocyanate (IPDI) and toluene diisocyanate (TDI).

[0008] In the composition of this invention, more than one polymer may be present in the aqueous polymer dispersion. A polymer useful in this invention preferably has a T_g less than 65°C, most preferably less than 60°C. T_g for the polymer is measured using Differential Scanning Calorimetry with standard linear techniques for calculation of T_g values. Pref-

erably, a polymer is an acrylic polymer, acrylic-styrene copolymer, an acrylic-vinyl acetate copolymer or a polyurethane polymer. The aqueous dispersion of the polymer preferably has a pH no greater than 9.5, more preferably no greater than 8.5. Preferably, the average particle size of the aqueous dispersion is less than 1000 nm, more preferably less than 500 nm, more preferably less than 400 nm. In one embodiment of the invention, the average particle size is less than 340 nm. Average particle size is the average diameter of the polymer particles, as determined by BI-90 light scattering measurements.

[0009] Typical anionic surfactants include but are not limited to: alkali or ammonium alkyl sulfates, alkyl sulfonates, alkylaryl sulfonates (e.g., sodium dodecylbenzenesulfonate (DBS)), salts of alkyl or aryl or alkylarylethoxy sulfonates, salts of fatty acids, esters of sulfosuccinic acid salts, alkyl diphenylether disulfonates, and salts or free acids of complex organic phosphate esters. Typical nonionic surfactants include but are not limited to: polyethers, e.g. ethylene oxide and propylene oxide condensates which include straight and branched chain alkyl and alkylaryl polyethylene glycol and polypropylene glycol ethers and thioethers, alkyl phenoxypoly(ethyleneoxy) ethanols having alkyl groups containing from about 7 to about 18 carbon atoms and having from about 3 to about 100 ethyleneoxy units, and polyoxyalkylene derivatives of hexitol, including sorbitans, sorbitides, mannitans, mannides and alkyl polyglucosides. Amine oxides are also suitable surfactants for use in this invention. Suitable amine oxides are disclosed, e.g., in U.S. Pat. Nos. 6,448,279 and 6,485,790. Ethoxylated amines and ethoxylated quaternary ammonium compounds can also be suitable surfactants.

[0010] The aqueous composition used to treat wood preferably contains from 100 ppm to 10,000 ppm wood preservative, more preferably from 200 ppm to 6,000 ppm, and most preferably from 300 ppm to 5,000 ppm. Preferably, the composition contains from 0.001% to 3% surfactant, more preferably from 0.005% to 1%, and most preferably from 0.01% to 0.7%. In one embodiment of the invention, the surfactant level is from 0.01% to 0.4%. Preferably, the polymer solids content of the composition is from 0.03% to 10%, more preferably from 0.05% to 6%, and most preferably from 0.06% to 4%. Preferably, the polymer solids to biocide ratio is from 2:1 to 20:1, more preferably from 3:1 to 10:1.

[0011] In another embodiment of this invention, the aqueous composition used to treat wood preferably contains from 100 ppm to 10,000 ppm of an azole fungicide, more preferably from 150 ppm to 6,000 ppm, and most preferably from 200 ppm to 5,000 ppm. Preferably, the composition contains from 0.001% to 3% surfactant, more preferably from 0.002% to 1%, and most preferably from 0.005% to 0.7%. In one embodiment of the invention, the surfactant level is from 0.005% to 0.4%. Preferably, the polymer solids content of the composition is from 0.01% to 10%, more preferably from 0.02% to 6%, and most preferably from 0.03% to 4%. Preferably, the polymer solids to biocide ratio is from 1:1 to 20:1, more preferably from 2:1 to 10:1.

[0012] In another embodiment of this invention, the aqueous composition used to treat wood preferably contains from 200 ppm to 10,000 ppm halogenated carbamate biocide, more preferably from 250 ppm to 6,000 ppm, and most preferably from 300 ppm to 5,000 ppm. Preferably, the composition contains from 0.001% to 3% surfactant, more preferably from 0.005% to 1%, and most preferably from 0.01% to 0.7%. In one embodiment of the invention, the surfactant level is from 0.01% to 0.4%. Preferably, the polymer solids content of the composition is from 0.02% to 10%, more preferably from 0.025% to 6%, and most preferably from 0.03% to 4%. Preferably, the polymer solids to biocide ratio is from 1:1 to 20:1, more preferably from 2:1 to 10:1.

[0013] The aqueous composition optionally contains a non-aqueous solvent. Preferably, the amount of solvent is from 0.01% to 10%, more preferably from 0.05% to 7%, and most preferably from 0.1% to 4%. Suitable solvents include ester and ether solvents having a boiling point of at least 150°C, and preferably a flash point of at least 60°C. Examples of such solvents include glycols, and their ethers and esters, e.g., TEXANOL (2,2,4-trimethyl-1,3-pentanediol, mono-isobutyrate ester; available from Eastman Co., Kingsport TN), DOWANOL DPM (dipropylene glycol, methyl ether; available from Dow Chemical Co.), DOWANOL PPH (propylene glycol phenyl ether), propylene glycol (PG), dipropylene glycol, dipropylene glycol butyl ether, dipropylene glycol propyl ether, alkyl ethers of tripropylene glycol, such as tripropylene glycol methyl ether, alkyl ethers of ethylene glycol, such as ethylene glycol monobutyl ether and alkyl ethers of diethylene glycol, such as diethylene glycol monobutyl ether, and crop oil esters, such as Archer RC sunflower oil ester.

[0014] The aqueous compositions used in the present invention may optionally contain additional components including but not limited to stabilizers, dyes, water repellents, other wood biocides, fungicides and insecticides, antioxidants, metal chelators, radical scavengers, etc. Stabilizers include, e.g., organic and inorganic UV stabilizers, such as, copper oxide or other copper salts or complexes that resist leaching; zinc oxide; iron salts, iron oxide, iron complexes, transparent iron oxide and nanoparticle iron oxide; titanium dioxide; benzophenone and substituted benzophenones; cinnamic acid and its esters and amides; substituted triazines, such as triphenyl triazine and substituted phenyl triazine UV absorbers, benzotriazole and substituted benzotriazole UV absorbers; hindered amine light stabilizers, used individually or in combination. Water repellents include, e.g., various wax-type water repellents, e.g., paraffin, carnauba, and polyethylene waxes with particle sizes <250 nm; and silicones. Other wood biocides, fungicides, such as bethoxazin and cyproconazole, and insecticides include, e.g., those listed in U.S. Pat. No. 6,610,282, e.g., imidacloprid, thiacloprid, permethrin, and etofenprox. Antioxidants include any commercially available antioxidant compounds, e.g., phosphite antioxidants such as IRGAFOS; lactone antioxidants; phenolic antioxidants such as BHT; ascorbic acid; and IRGANOX and the like. Metal chelators include, e.g., EDTA, NTA, 1,10-phenanthroline, ACUMER 3100, DEQUEST, TAMOL 731, tripolyphos-

phate and other inorganic and organic compounds and polymers useful in chelating or dispersing metal salts. Radical scavengers include, e.g., TEMPO.

[0015] Treatment of wood is performed by contacting the wood with the aqueous composition described herein, preferably under conditions specified in AWP Standards C1, C2, C5, C14, C15, C22, C36, etc.

[0016] In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% DCOIT, 0-15% surfactant(s), and the remainder water. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, or polyurethane that is dispersible in water. Preferably, the surfactant is nonionic.

[0017] In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% DCOIT in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is dispersible in water, 0-20% surfactant, and the remainder water. Preferably the surfactant is nonionic. For either of these preferred embodiments the preferred concentration of DCOIT contacting the wood is from 0.01-0.5%.

[0018] In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% Propiconazole or Tebuconazole, 0-25% surfactant(s), and the remainder water. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, or polyurethane that is dispersible in water. Preferably, the surfactant is nonionic.

[0019] In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% Propiconazole or Tebuconazole in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is dispersible in water, 0-20% surfactant, and the remainder water. Preferably the surfactant is nonionic. For either of these preferred embodiments the preferred concentration of Propiconazole or Tebuconazole contacting the wood is from 0.005-0.5%.

[0020] In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% IPBC, 0-15% surfactant(s), and the remainder water. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, or polyurethane that is dispersible in water. Preferably, the surfactant is nonionic.

[0021] In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% IPBC in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is dispersible in water, 0-20% surfactant, and the remainder water. Preferably the surfactant is nonionic. For either of these preferred embodiments the preferred concentration of IPBC contacting the wood is from 0.02-0.5%.

[0022] In another embodiment of the invention, a mixture comprising a halogenated isothiazolone biocide, a polymer, and at least one organic solvent is used to treat wood via, dip, spray, brush, vacuum or vacuum-pressure processes. Preferably, the halogenated isothiazolone biocide comprises a 3-isothiazolone having a C₄-C₁₂ N-alkyl substituent, more preferably a chlorinated 3-isothiazolone, and most preferably DCOIT. Preferably, suitable organic solvents include, e.g., esters, glycols, glycol ethers or esters, hydrocarbons and oils. In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% DCOIT, 0-35% surfactant(s), and the remainder solvent. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, polyurethane, alkyd resin, silanol or polymeric methylene diphenylisocyanate or derivatives. Preferably, the surfactant is nonionic. In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% DCOIT in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is soluble or dispersible in an organic solvent, 0-20% surfactant, and the remainder organic solvent. Preferably the surfactant in the polymer container is nonionic. For either of these preferred embodiments the preferred concentration of DCOIT contacting the wood is from 0.01-0.5%.

[0023] In order to provide long term protection, the preservative needs to "fix" in the wood and not deplete too rapidly by volatilization or by leaching when the wood gets wet. It might be expected that enhanced penetration or enhanced movement of the preservative deep into the wood during treatment might also lead to reduced fixation of the organic wood preservative. However, it was discovered that the polymers used to provide enhanced penetration also effectively fix the organic biocide in the wood. Two different measures of fixation were used, a dislodgeable residue assay and a very aggressive leaching assay. The dislodgeable residue assay measures how much preservative can be removed or dislodged from the surface of the wood. This is a good assay to determine how much preservative is available or has migrated to the surface of the wood. It is surprising how significant the reduction in dislodgeable residues are as seen in Table 5. All of the polymers provided exceptional control of dislodgeable residues except for one water soluble polymer that probably redissolves under the assay conditions. Another measure of fixation is resistance to leaching. A very aggressive leaching assay, the AWP E11-97 assay was used. DCOIT is considered a low leaching organic biocide as is seen by the cumulative % of DCOIT leached in Table 6 with the xylene formulation which doesn't contain any added surfactant. Nonionic surfactants can facilitate the leaching of organic preservatives. Even with the added nonionic surfactants, the polymers provided good leaching resistance, demonstrating cumulative leaching values comparable or lower than DCOIT in xylene, again demonstrating enhanced fixation of the organic preservatives when used in the

polymer formulation of this invention.

[0024] The aqueous polymer composition used to fix organic preservatives in wood preferably contains from 100 ppm to 10,000 ppm of an organic wood preservative, such as a halogenated isothiazolone biocide, a halogenated carbamate or an azole fungicide, more preferably from 200 ppm to 6,000 ppm, and most preferably from 300 ppm to 5,000 ppm. Preferably, the composition contains from 0.001% to 3% surfactant, more preferably from 0.005% to 1%, and most preferably from 0.01% to 0.7%. In one embodiment of the invention, the surfactant level is from 0.01% to 0.4%. Preferably, the polymer solids content of the composition is from 0.01% to 10%, more preferably from 0.02% to 6%, and most preferably from 0.03% to 4%. Preferably, the polymer solids to biocide ratio is from 1:1 to 20:1, more preferably from 2:1 to 10:1.

[0025] In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% DCOIT, 0-15% surfactant(s), and the remainder water. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, or polyurethane that is dispersible in water. Preferably, the surfactant is nonionic.

[0026] In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% DCOIT in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is dispersible in water, 0-20% surfactant, and the remainder water. Preferably the surfactant is nonionic. For either of these preferred embodiments the preferred concentration of DCOIT contacting the wood is from 0.01-0.5%.

[0027] In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% Propiconazole or Tebuconazole, 0-25% surfactant(s), and the remainder water. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, or polyurethane that is dispersible in water. Preferably, the surfactant is nonionic.

[0028] In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% Propiconazole or Tebuconazole in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is dispersible in water, 0-20% surfactant, and the remainder water. Preferably the surfactant is nonionic. For either of these preferred embodiments the preferred concentration of Propiconazole or Tebuconazole contacting the wood is from 0.005-0.5%.

[0029] In one preferred embodiment, the treatment mixture is formulated as a concentrate in a single container, with 10-60% polymer solids, 5-30% IPBC, 0-15% surfactant(s), and the remainder water. Preferably, the polymer is an acrylic, styrene-acrylic, vinyl-acetate-acrylic, or polyurethane that is dispersible in water. Preferably, the surfactant is nonionic.

[0030] In another preferred embodiment, the wood treatment mixture is formulated as a concentrate in two separate containers, with one container comprising 10-50% IPBC in an organic solvent, with 0-35% nonionic surfactant, preferably 5-25%; and the other container comprising 10-60% polymer which is dispersible in water, 0-20% surfactant, and the remainder water. Preferably the surfactant is nonionic. For either of these preferred embodiments the preferred concentration of IPBC contacting the wood is from 0.02-0.5%.

EXAMPLES

Treatment Solutions

Preparation of the wood treatment solution from DCOIT/DOWANOL PPH:

[0031] 3000 g of treatment solution was prepared by diluting 90 g (50% solids) of polymer with 2000 g of tap water containing 3 drops of Tego Foamex 805 defoamer with stirring for 20 minutes. (Tap water optionally containing additional surfactant, such as a metal salt of dodecylbenzene sulfonic acid or an alkyl ethoxylate) (0.06%) To the well stirred solution was slowly added 22.5 g (20% DCOIT dissolved in propylene glycol phenyl ether with 0.04% PG, for a final concentration of 1500 ppm DCOIT). Tap water was added to make 3000 g of total solution and the solution was stirred for 60 minutes, and used as is to treat wood.

[0032] Optionally, the amount of polymer (50% solids) can be varied from 9.0 g to 180 g equally effectively in the above preparation and used to treat wood.

Prepare treatment solution with DCOIT technical material:

[0033] In the DOWANOL PPH preparation above, substitute 4.5 g of DCOIT technical material (99+%, final concentration 1500 ppm) instead of the DCOIT solution and stir the treatment solution for several days at ambient temperature, then use treatment solution as is to treat wood.

EP 1 714 757 A1

Alternative Preparation of treatment solution with DCOIT technical material.

5 **[0034]** To a heated (45°C) suspension of 95g of polymer G (25% polymer solids) containing 12% Tergitol 15-S-40 (70% solids) was added 5.0g of molten DCOIT. The mixture was stirred for 15 minutes then allowed to cool to room temperature.

[0035] The wood treatment solution was prepared by diluting the above mixture with water to obtain the desired concentration of DCOIT in the treatment solution.

10 Preparation of the wood treatment solution from DCOIT/Dowanol DPM:

[0036] In the DOWANOL PPH preparation above, substitute 18 g of 25% DCOIT in DOWANOL DPM (final concentration of 1500 ppm DCOIT) stirring as directed.

15 Preparation of 5.4% DCOIT Single Pack Formulation

20 **[0037]** To a well stirred, 70°C suspension of 564.2g of polymer G (47.5% solids) and 328.6 g of water was slowly added a 60°C solution of 53.6g of DCOIT dissolved in 53.6 g of Tergitol 15-S-5. The suspension was stirred at 70°C for 1 hour. (If another surfactant and/or co-solvent was to be added, they were slowly added at this time and stirring continued for an additional 20 minutes.) The stirred suspension was allowed to cool to 35°C then it was packed out. The formulation was diluted to the desired concentration and used as is to pressure treat wood.

[0038] Similarly, the 6.7% DCOIT single pack formulations can be prepared by the above procedure using the following ingredients:

25 702.1g of polymer G, 145.3g of water, 67 g of DCOIT, 67g of Tergitol 15-S-5, and 18.6g of Tergitol 15-S-40, or

702.1g of polymer G, 145.3g of water, 67 g of DCOIT, 67g of Texanol, and 18.6g of Tergitol 15-S-40

Procedure to treat wood:

30 **[0039]** The above prepared treatment solutions can be used to treat wood by either pressure treatment or vacuum treatment.

Pressure treatment procedure:

35 **[0040]** Two 5.5x5.5x1 inch (14x14x2.5 cm) pieces of Southern Yellow Pine are loaded into a 2 L pressure vessel equipment with an inlet tube, gas/vacuum inlet, pressure sensors, dropout valve and level indicators. The vessel is sealed and the pressure is reduced to 26-27 inches of Hg (88-91 kPa) and held for 15-20 minutes. The vacuum is turned off and sufficient treatment solution is drawn into the vessel to completely cover the wood. The vessel is pressurized to approximately 150 psig (1136 kPa). A pump is used to maintain the liquid level above the wood. When no more treatment solution is taken up by the wood, the pressure is released and the vessel drained via the dropout valve. The wood can be removed at this point (full cell treatment) or a vacuum can be pulled on the vessel again for approximately 5 minutes, the vessel again drained and then the wood removed (full cell with final vacuum treatment) to partially remove some of the surface moisture from the treated wood. All of the wood reported here was treated via the full cell with final vacuum procedure.

45 Vacuum treatment procedure:

50 **[0041]** One piece of 5.5x5.5x1 inch Southern Yellow Pine is placed in a vacuum desiccator, weighted down with a stainless steel bolt to prevent it from floating and put under vacuum, 25-27 inches of Hg (85-91 kPa), and held for 15-30 minutes. Enough treatment solution is added to fully cover the wood while the wood is under vacuum. The vacuum soak is held for 30-60 minutes, then the vacuum is released and the wood is soaked in the treatment solution at atmospheric pressure for an additional 15-30 minutes before removal.

Analysis of the treatment solution and wood:

55 **[0042]** A 2 g sample of the as is treatment solution is analyzed for DCOIT by HPLC. The treatment solution was found to contain 1500 ppm of DCOIT.

EP 1 714 757 A1

Analysis of DCOIT in latex formulations:

[0043] An aliquot of well-mixed sample was weighed into a one-ounce screw cap vial. Into the vial was pipetted 20 mL of methanol. The contents were sonicated for one hour in an ultrasonic bath. The sample was filtered through a 0.2 μ m filter into an auto-sampler for analysis. The sample preparation was analyzed using a reverse phase HPLC procedure with UV detection according to the wood analysis method below.

[0044] A 3 g sample of as is treatment solution was centrifuged at 10,000 RPM for 10 minutes to precipitate any gelled polymer or other particulates. No solid precipitated. The treatment solution sample was further centrifuged at 100,000 RPM for 20 minutes to precipitate the polymer. The precipitated polymer plug and the clear supernatant were analyzed for DCOIT by HPLC. The supernatant contained 34 ppm of DCOIT and the polymer plug contained 38,000 ppm of DCOIT, demonstrating that the DCOIT had fully partitioned into the polymer. Analysis of DCOIT in Treated Wood

[0045] Once the treated wood sample had dried to a constant weight, it was placed in a constant temperature and humidity room, and then was analyzed for DCOIT content. Using a drill press containing a 3/4 inch (19 mm) Forstner bit, three holes were drilled in the wood. The location of the holes were on one face, at least 1/4 inch (6.4 mm) from the sides and ends and where the grain angle was the most vertical between the two faces. One millimeter sections from each hole at depths of 1, 3 and 10 millimeters were collected, combined and analyzed for DCOIT.

[0046] A known weight of wood shaving sample is extracted in methanol by sonication for two hours. The extract is then allowed to cool to room temperature. The cooled extract is analyzed by a reverse phase high performance liquid chromatography. The DCOIT is separated from sample matrix using a 25 cm C18 column using water and methanol as mobile phase. The DCOIT is detected using ultraviolet detector set at 280 nanometers. Concentration of DCOIT in sample is determined by comparing peak area of the DCOIT peak in sample with the DCOIT peak in a standard solution using an external standard calculation method.

Particle Size Measurements:

[0047] Particle sizes were measured on a Brookhaven Instruments Corporation Zeta Plus: Zeta Potential Analyzer. The instrument parameters used are as follows: temperature 25°C, set the dust cutoff to on, set the wavelength to 633 nm and set the angle to 90 degrees. The polymer was diluted with 0.01M NaCl which contained a few ppm of Proclin antibacterial in reagent grade water. The solution for analysis was prepared by placing 2-3 drops of an emulsion polymer into 20 mL of the salt solution and inverting to mix. A clean cuvette was rinsed with the appropriate solvent and filled to 3/4 capacity with salt solution. 3-5 drops of the diluted polymer emulsion was added to the cuvette, the cap is placed on top, and inverted to mix. The amount of polymer in the cuvette was adjusted so that the total counts were between 500 and 1000 kcps.

Prep of IPBC/Propiconazole/Tebuconazole + polymer formulations:

[0048] To make 3 liters of treatment formulation, a 56.25g aliquot of 40% polymer G, containing 1.6% Tergitol 15-S-40, was diluted with sufficient water with stirring to obtain close to the final desired concentration. To the resulting formulation was added 18g of a 25% IPBC/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate solution with stirring. (Similarly, 18 g of a 25% Propiconazole/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate or 22.5g of a 20% Tebuconazole/26.67% Tergitol 15-S-5/26.67% dipropylene glycol monomethyl ether/26.67% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate could be used instead). A small amount of additional water may be added, if needed, to make the desired final treatment formulation concentration. The treatment formulation was stirred overnight then used as is to pressure treat wood.

Prep of DCOIT + Propiconazole/Tebuconazole formulations:

[0049] To make 3 liters of treatment formulation, a 33.75g aliquot of 40% polymer G, containing 1.6% Tergitol 15-S-40, was diluted with sufficient water with stirring to obtain close to the final desired concentration. To the resulting formulation was added 7.2g of a 25% DCOIT/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate solution with stirring. Next, 4.5g of 20% Tebuconazole/26.67% Tergitol 15-S-5/26.67% dipropylene glycol monomethyl ether/26.67% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate solution was added with stirring. (Similarly, 3.6 g of a 25% Propiconazole/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate can be substituted for the Tebuconazole solution.) A small amount of additional water may be added, if needed, to make the desired final treatment formulation concentration. The treatment formulation was stirred overnight then used as is to pressure treat wood.

EP 1 714 757 A1

Prep of DCOIT + IPBC formulation:

[0050] To make 3 liters of treatment formulation, an 18g aliquot of 40% polymer G, containing 1.6% Tergitol 15-S-40, was diluted with sufficient water with stirring, to obtain close to the final concentration. To the resulting formulation was added 8.11g of a 22.2% DCOIT/11.1%IPBC/22.2% Tergitol 15-S-5/22.25% dipropylene glycol monomethyl ether/22.2% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate with stirring. A small amount of additional water may be added, if needed, to make the desired final treatment formulation concentration. The treatment formulation was stirred overnight then used as is to pressure treat wood.

Dislodgeable Residue Assay:

[0051] The dislodgeable residue assay was conducted by placing a piece of cotton fabric that is slightly larger than the wood and moistened with 2 ml of water on the wood. A piece of aluminum foil was placed over the cotton fabric and a 12.5kg rolling pin was rolled back and forth over the foil covered wood ten times being careful not to exert any downward nor upward pressure on the rolling pin during the rolling process. The fabric was removed and extracted with methanol in a sonication bath for 1 hour. The methanol was analyzed by HPLC for DCOIT.

Analysis of Propiconazole and Tebuconazole in Treated Wood:

[0052] A weighed aliquot of 0.36 to 0.58 mg of wood shavings was placed into a one-ounce vial and 10.0 mL of 30 water/70 ACN solution added. The sample were sonicated for 1 hour and the solvent was filtered through a 0.45 μ m PALL Acrodisc® LC 25 mm syringe filter. The filtrate was transferred to an autosampler vial and 5 μ L injections were made on the HPLC system for analysis. (See AWP Standard A28-01 for HPLC conditions for analyzing Propiconazole and Tebuconazole.)

Analysis of IPBC in Treated Wood:

[0053] A known weight of wood shaving sample was extracted in methanol by sonication for two hours. The extract was then allowed to cool to room temperature. The cooled extract was analyzed by a HPLC method reported in AWP A5-00, section 14 for IPBC.

Leaching assay

[0054] The AWP E11-97 leaching assay was used with the following modifications:

- A single treatment rate, as indicated in the table, was used.
- The Southern yellow pine cubes were pressure treated to ensure maximum uptake of the treatment solution.
- An aqueous methanol solution was used to rinse out the flask and combined with each aliquot of water leachate to ensure that all of the actives were dissolved in the leachate for analysis.

Prep of the Solvent Borne Treatment Formulations:

[0055] The polymers were diluted in either xylene or 20% xylene in mineral spirits depending on the polymer's compatibility in mineral spirits and a solution of 30% DCOIT in xylene added with stirring until the desired treatment solution concentration was obtained. The treatment formulation was used as is to treat the wood.

Single and Double Dip Application:

[0056] A 5.375 inch square by 1 inch thick piece of wood was submerged in the treatment solution for 10 minutes for the single dip application and for the double dip experiment, the wood was submerged for 2 minutes, drained for 1 minute then submerged for an additional 10 minutes.

[0057] Table 1 presents the compositions of the polymers used in the wood treatment solutions. Table 2 presents penetration data for DCOIT in wood, obtained using wood treatment solutions prepared from DCOIT/DOWANOL PPH. "% retained @ 10 mm" is the amount of biocide at 10 mm as a percentage of the amount at 1 mm. Table 3 presents the effect on penetration depth of co-solvents and surfactants, with data presented for treatment solutions containing polymers M and G; the polymer:biocide ratio was 10:1, unless otherwise specified in Table 3. Table 4 presents the penetration data for IPBC, Propiconazole and Tebuconazole. Table 5 presents the dislodgeable residue data for the waterborne polymers with DCOIT. Table 6 presents the leaching results. Table 7 presents the solvent borne polymer compositions

EP 1 714 757 A1

and their dislodgeable residue results.

Table 1: Polymer Compositions

Polymer	Composition
A	40.7 Sty/29.5 EHA/24.7 AN/4.9 MAA
B	52.9 MMA/33.5 BA/10.4 HEMA/3.0 MAA
C	52.4 MMA/45.6 BA/1 MAA/1 UMA ¹
D	60.2 EA/39.7 MAA
E	65.6 BA/31.8 Sty/2.5 MAA
F	85 VA/15 BA
G	47 Sty/46 EHA/4 MLAM/3 MAA
H	67 BA/29 Sty/1.9 HEMA/1.7 AM/0.1 MAA
I	39.3 BMA/29.0 Sty/21.8 EHA/5 MAA/4.6 MMA
J	33.5 MMA/25.1 Sty/25.1 BA/16.1 MAA
K	49.9 BA/25.0 MMA/15.0 MAA/9.9 Sty
L	59.8 MMA/36.1 BA/3.9 MLAM
M	67 BA/29 Sty/2.7 MAA
N	53 MMA/45.6 BA/1.3 MAA
O	75.9 BA/18.9 Sty/3.5 AA/1.5 IA
P	40.7 MMA/35.4 Sty/23.7 BA
Q	52 BA/46.6 MMA/1.3 MAA
R	51.3 MMA/27.3 EHA/18.7 BA/2.5 MAA
S	75.9 BA/13.9 Sty/6.9 AN/1.9 MLAM/1.0 AA
T	60.0 BA/38.6 MMA/1.3 AA
U	39.8 Sty/30.1 EHA/25.0 AN/4.9 MAA
V	34.9 LMA/32.0 BA/31.4 MMA/1.5 MAA
W	76.9 BA/19.5 Sty/2 MAA/1.4 MLAM
X	52.6 MMA/46.0 BA/1.2 MAA
Y	93.1 MMA/4.9 BA/1.6 MLAM/0.2 MAA
Z	60 MMA/40 MAA
AA	42.5 BA/42.5 MMA/5 AA/10 TMPTA ²
AB	51 PTMEG ³ /36.7 MCI/9.8 DMPA ⁴ /2.5 EDA
AC	50.9 Sty/31.2 BA/11.8 AN/6.0 MAA
AD	52.8 BA/28.7 Sty/15.0 AN/2.3 PEM/1.0 AA
AE	68.6 Sty/27.8 BA/3.5 MAA
AF	42.4 BA/37.4 Sty/13.6 MMA/5.0 HEMA/1.5 IA
AG	46.5 Sty/42.5 BA/9.4 HEMA/1.4 MAA
AH	IPDI/adipic acid/1,6-hexanediol
AI	IPDI/adipic acid/1,6-hexanediol
AJ	TDI/adipic acid/1,6-hexanediol/neopentyl glycol/1,4-butanediol
AK	HDI/polypropylene glycol/1,6-hexanediol carbonate

EP 1 714 757 A1

(continued)

Polymer	Composition
AL	50 AM/50 HEMA
1. ureidomethacrylate 2. trimethylolpropane trimethacrylate 3. polytetramethylene ether glycol 4. dimethylolpropionic acid	

Table 2: Biocide Penetration Data

Polymer	T _g , °C	particle size	pH	biocide @ 1 mm	biocide @ 3 mm	biocide @ 10 mm	% retained @ 10 mm
A	56	95	7.6	774	713	692	89
B	39	135	7.5	709	913	567	80
C	19	135	9.5	1046	885	715	68
D	51	114	2.8	1120	918	749	67
E	0	125	7.5	1174	893	713	61
F	21	350	4.8	853	581	516	60
G	20	125	6.8	1206	806	704	58
G*				1335	1498	1283	96
H	-2	72.5	7.5	876	823	499	57
I	29	48	7.8	794	1021	452	57
J	62	60	6.9	977	951	516	53
K	29	48	7.2	872	1050	428	49
L	39	135	8.3	1131	1051	538	48
M	-1	250	7.5	1194	1293	527	44
N	25	178	9.5	929	513	409	44
O	-12	155	7	906	957	327	36
P	52	275	8.75	443	188	124	28
Q	17	563	9.5	674	489	187	28
R	20	100	8	1151	610	316	27
S	-8	150	6.5	1326	1243	330	25
T	6	55	8.8	863	572	214	25
U	56	93	7.4	1017	674	252	25
V	-8	345	7	1022	1136	251	25
W	-12	360	9.5	752	758	169	22
X	24	453	8.9	946	416	124	13
Y	78	150	9	1441	251	40	3
Z	111	114	2.8	897	126	22	2
AA	58	1000		139	109	12	9
AB			7.5	1030	486	189	18
AC**	54	98	7	1853	932	410	22

EP 1 714 757 A1

(continued)

Polymer	T _g , °C	particle size	pH	biocide @ 1 mm	biocide @ 3 mm	biocide @ 10 mm	% retained @ 10 mm
AD**	24	200	9	2635	1287	1445	55
AE**	49	195	7	2225	1337	1203	54
AF**	28	130	7.5	1303	1232	1124	86
AG**	26	137	4	2624	1356	940	36
AH**	-50	45/110	8	2965	1596	1159	39
AI**	-52	35/68	8	2373	1756	1688	71
AJ**	-33	179	7	1773	1368	1250	71
AK**	-48 /	73/204/1140	6	2043	1610	1206	59
*4:1 polymer to biocide ratio used							
** 5:1 polymer to biocide ratio used							

Table 3: Effect of Co-Solvents and Surfactants on Penetration Depth

DCOIT source	co-solvent	surfactant #1	surfactant #2	biocide @ 1 mm	biocide @ 3 mm	biocide @ 10 mm	% retained @10 mm
<u>Polymer M</u>							
PPH, 20%	0.04% PG	0.06% MDBS		1194	1293	527	44
PPH 20% (*3)	0.04% PG	0.06% M DBS		1295	1712	1451	130
Tex, 30%				256	110	83	32
Tex, 30%		OT, 0.09%		919	686	679	74
Tex, 30%		15540, 0.01%		370	241	206	56
<u>Polymer G</u>							
P9 oil, 20%		0.19% Nopco		1268	1571	488	38
PPH, 20%	0.04% PG	0.06% MDBS		742	509	316	43
PPH, 20%	0.04% PG	0.06% MDBS	15S40, 0.18%	1145	1465	679	59
PPH, 20%	*1	0.06% MDBS	15S40, 0.04%	1270	1259	662	52
PPH, 20% (*3)	0.04% PG	0.06% MDBS	15S40, 0.05%	1222	1258	1659	136
PPH, 20% (*4)	0.04% PG	0.06% MDBS	15S40, 0.04%	1548	1369	1283	83
PPH, 20% (*6)	0.04% PG	0.06% MDBS	15S40, 0.01%	3569	458	333	9
Technical (*3)		0.09% 15S40		1332	1284	1333	100
technical				1039	586	45	4

EP 1 714 757 A1

(continued)

	DCOIT source	co-solvent	surfactant #1	surfactant #2	biocide @ 1 mm	biocide @ 3 mm	biocide @ 10 mm	% retained @10 mm
5	technical	0.45% DPM	OT, 0.06%		908	767	615	68
	technical	0.45% DPM	0.06% NaDBS		999	891	383	38
10	DPM, 30%		0.06% NaDBS		265	281	175	66
	DPM, 25%		15S12, 0.06%		638	607	271	42
15	*2		15S40, 0.06%	15S5, 0.3%	1558	1886	854	55
	*2		15S40, 0.06%	15S9, 0.3%	1100	1389	850	77
20	6.7%, *3	0.15% Tex	0.03% 15S40		1712	1434	932	54
	6.7%, *3				2340	1641	1324	57
	5.4%, *3				1462	1506	1322	90
25	25% in *2, *5		15S40, 0.024%	15S5, 0.15%	1622	1404	1353	83
	25% in Aromatic 200 ND, *5		15S40, 0.024%	15S7, 0.01%	1474	1323	1286	87
30	Polymer A							
	PPH, 20% (*3)	0.04% PG	0.06% MDBS		1481	1497	1926	130
35	<u>Polymer F</u>							
	PPH, 20% (*3)	0.04% PG	0.06% MDBS		1225	557	450	37
	Polymer S							
40	PPH, 20% (*3)	0.04% PG	0.06% MDBS		2198	1416	2057	94
	25% in *2, *4		15S40, 0.02%	1585, 0.15%	2417	2058	1476	61
45	PPH, 20% (*3)	0.04% PG	0.06% MDBS		2198	1416	2057	94

50

55

EP 1 714 757 A1

(continued)

DCOIT source	co-solvent	surfactant #1	surfactant #2	biocide @ 1 mm	biocide @ 3 mm	biocide @ 10 mm	% retained @ 10 mm
25% in *2, *4		15S40, 0.02%	1585, 0.15%	2417	2058	1476	61
Notes: *1 - 0.19% Tex + 0.04% PG *2 - 1:1, 25% DCOIT in DPM:25% DCOIT in Tex *3 - 5:1 Polymer to DCOIT ratio *4 - 3:1 Polymer to DCOIT ratio *5 - 4:1 Polymer to DCOIT ratio *6 - 1:1 Polymer to DCOIT ratio <u>Solvents</u> - "PG" is propylene glycol; "PPH" is DOWANOL PPH; "DPM" is DOWANOL DPM; "Tex" is TEXANOL; "P9 oil" is a high-boiling hydrocarbon oil similar to #2 diesel fuel. Listings are % DCOIT in solvent, e.g., "PPH, 20%" means a 20% solution of DCOIT in PPH. <u>Surfactants</u> - "MDBS" is a metal salt of DBS; "Nopco" is NOPCOCATOR, a sulfonated castor oil; "OT" is AEROSOL OT, a dioctyl sulfosuccinate ester; "15S[n]" is TERGITOL 15-S-[n], a branched C₁₃ alkyl with n ethylene oxide units, e.g., TERGITOL 15-S-40, which has 40 ethylene oxide units							

Table 4: Penetration of IPBC, Propiconazole and Tebuconazole

Active	Treatment solution concentration (ppm)	Bio.	Polymer and ratio polymer to active	Added surfact	biocide @ 1 mm	biocide @ 3 mm	biocide @ 10 mm	% retained @ 10 mm
<u>IPBC</u>	1500	*1	G, 5:1	0.03% 15S40	2090	1342	1608	77
Propiconazole	1500	*2	G, 5:1	0.03% 15S40	2614	1594	1090	42
Tebuconazole	1500	*3	G, 5:1	0.03% 15S40	2394	1690	1098	46
IPBC + DCOIT	300 + 600	*4	G, 2.67: 1	0.01% 15S40				
Propiconazole + DCOIT	300 + 600	*2, *5	G, 5:1	0.02% 15S40	434 (Propi) 573 (DCOIT)	328 (Propi) 517 (DCOIT)	238 (Propi) 380 (DCOIT)	55 (Propi) 66 (DCOIT)
Tebuconazole + DCOIT%	300 + 600	*3, *5	G, 5:1	0.02% 15S40	397 (Teb) 560 (DCOIT)	294 (Teb) 540 (DCOIT)	216 (Teb) 486 (DCOIT)	54 (Teb) 87 (DCOIT)
*1 - 25% IPBC/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate *2 - 25% Propiconazole/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate *3 - 20% Tebuconazole/26.67% Tergitol 15-S-5/26.67% dipropylene glycol monomethyl ether/26.67% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate *4 - 22.2% DCOIT/11.1%IPBC/22.2% Tergitol 15-S-5/22.25% dipropylene glycol monomethyl ether/22.2% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate *5 - 25% DCOIT/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate 15S40 refers to Tergitol 15-S-40								

EP 1 714 757 A1

Table 5: Percent Reduction in Dislodgeable Residues (10:1 Polymer to DCOIT Ratio unless otherwise noted, 1500ppm DCOIT)

	Polymer	Added Surfactant	Biocide Formulation	% Reduction
5	---	---	*1	0
	A	---	*1	100
	B	---	*1	99.9
10	C	---	*1	99.9
	D	---	*1	99.8
	E	---	*1	99.7
15	F	---	*1	99.9
	G	---	*1	99.9
	G**	0.06% 15S40	*1	99.8
	G**		*3	99.2
20	G**		*4	98.7
	G**		*5	98.7
	G****	0.04% 15S40	*1	99.4
25	G*****	0.01% 15S40	*1	89.7
	G***	0.02% 15S40	*2	95.8
	H	---	*1	99.9
	H****	0.04% 15S40	*1	99.3
30	H**	0.03% 15S40	*2	83.3
	I	---	*1	100
	J	---	*1	99.8
35	K	---	*1	100
	L	---	*1	99.9
	M	---	*1	99.6
	N	---	*1	99.8
40	O	---	*1	100
	P	---	*1	98.3
	Q	---	*1	99.9
45	R	---	*1	98.7
	S	---	*1	100
	S****	0.04% 15S40	*1	99.1
	S****	0.02% 15S40	*2	96.7
50	T	---	*1	99.9
	U	---	*1	99.5
	V	---	*1	100
55	W	---	*1	99.9
	X	---	*1	99.7
	Y	---	Unstable formulation	

EP 1 714 757 A1

(continued)

Polymer	Added Surfactant	Biocide Formulation	% Reduction
Z	- - -	1*	99.2
AA	- - -	1*	99.6
AB	- - -	1*	99.9
AC	0.06%15S40	1*	99.5
AD	0.03%, 15S40	*2	94.1
AD****	0.04% 15S40	*1	97.7
AE	0.03% 15S40	*2	95.0
AF	0.03% 15S40	*1	99.9
AG	0.03% 15S40	*2	97.1
AH	- - -	*2	98.3
AI	- - -	*2	98.7
AJ	- - -	*2	98.7
AK	- - -	*2	98.7
AL	- - -	*1	-1
*1 20% DCOIT/67% Dowanol PPH/5% propylene glycol/8% MDBS *2 25% DCOIT/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate *3 6.7% DCOIT/6.7% Tergitol 15-S-5/1.3% Tergitol 15-S-40/33.4% Polymer G *4 6.7% DCOIT/6.7% Tergitol 15-S-5/1.3% Tergitol 15-S-40/33.4% Polymer G *5 5.4% DCOIT/5.4% Tergitol 15-S-5/26.8% Polymer G ** 5:1 Polymer to DCOIT *** 4:1 Polymer to DCOIT **** 3:1 Polymer to DCOIT ***** 1:1 Polymer to DCOIT 15S40 refers to Tergitol 15-S-40			

Table 6: Leaching Results (Modified AWPA E11-97 Protocol)

Polymer	Ratio, Polymer to biocide,	Added surfactant (% in treatment sol'n)	Biocide Concentration and Formulation	% Biocide Leached (cumulative)
- - -	- - -	- - -	1000 ppm, 3*	4.4%
G	4:1	0.03% 15S40	800 ppm, 1*	2.9%
G	4:1	0.01%, 15S40	800 ppm, 2*	4.6%
G	4:1	0.02% 15S40	1000 ppm, 4*	2.4%
S	5:1	0.02%, 15S40	1000 ppm, 4*	2.1%
H	5:1	0.02%, 15S40	1000 ppm, 4*	2.2%
AD	5:1	0.02%, 15S40	1000 ppm, 4*	2.1%
AG	5:1	0.02%, 15S40	1000 ppm, 4*	2.2%
AF	5:1	0.02%, 15S40	1000 ppm, 4*	2.2%
AE	5:1	0.02%, 15S40	1000 ppm, 4*	2.3%
A	5:1	0.02%, 15S40	1000 ppm, 4*	2.3%
G	4:1	0.01%, 15S40	800 ppm, 4*	2.6%

EP 1 714 757 A1

(continued)

Polymer	Ratio, Polymer to biocide,	Added surfactant (% in treatment sol'n)	Biocide Concentration and Formulation	% Biocide Leached (cumulative)
G	4:1	0.01%, 15S40	800 ppm, 4*	1.9%
*1 20% DCOIT/67% Dowanol PPH/5% propylene glycol/8% MDBS *2 25% DCOIT/7% Tergitol 15-S-7/68% Aromatic 200ND *3 30% DCOIT in xylene *4 25% DCOIT/25% Tergitol 15-S-5/25% dipropylene glycol monomethyl ether/25% 2,2,4-trimethyl-3-hydroxypentanol monoisobutyrate 15S40 refers to Tergitol 15-S-40				

Table 7: Solvent borne Polymers

	Compositions	Tg	Biocide Source	Application	% Reduction of dislodgeable residues
AL	Silanol	- - -	30% DCOIT in Xylene	Vac	99.6%
AL		- - -	30% DCOIT in Xylene	Dbl Dip	99.6%
AM	polymeric MDI	54	30% DCOIT in Xylene	Vac	99.6
AM		54	30% DCOIT in Xylene	Dbl Dip	99.6%
AN	97.8 BMA / 1.9 BA / 0.1 MAA	18	30% DCOIT in Xylene	Vac	97.1
AN			30% DCOIT in Xylene	Double dip	54.4
AO	49.8 BA/24.9 STY/10.6 HEMA/9.9 MMA/4.5 MAA	19	30% DCOIT in Xylene	Vac	96.7
AO			30% DCOIT in Xylene	Dip	98.7
AP	68 EA/27 STY/4.9 MAA	18	30% DCOIT in Xylene	Vac	93.7
AP			30% DCOIT in Xylene	Dip	98.7
AQ	54.0 BA/40.9 STY/5.0 MAA	17	30% DCOIT in Xylene	Vac	95.8
AQ			30% DCOIT in Xylene	Dip	98.3
AR	52.0 STY/29.9 BA /15.0 HEMA/2.9 AA	41	30% DCOIT in Xylene	Vac	97.5
AR			30% DCOIT in Xylene	Dip	98.3
AS	37.8 HEMA/33.7 STY /25.8 EHA/2.4 MMA	34	30% DCOIT in Xylene	Vac	97.9
AS			30% DCOIT in Xylene	Dip	97.1

Bioefficacy Studies

[0058] DCOIT formulations were tested for efficacy against a typical brown-rot fungus. Wafers measuring 5 mm x 18 mm x 18 mm (1 x r x t) were cut from defect-free southern pine sapwood. The soil block decay test method was carried out in accordance with AWP Standard E10, with the following modifications:

1. Radial compression strength rather than weight loss was used to measure the extent of decay.
2. Wafers were used rather than 19 mm cubes.
3. Plastic cups holding four wafers each were used as decay chambers.
4. The incubation time was 5 weeks rather than 12 weeks.
5. The toxic threshold ranges were obtained by statistical analysis of the compression strength values for each of the biocide retention levels.

[0059] In the initial decay test, the approximate toxic threshold value for DCOIT was established for Gloeophyllum

EP 1 714 757 A1

trabeum. Following this, DCOIT P9 oil formulation (see Table 3) and 9 sets of DCOIT formulations were run in a decay test with 10 sets of pine wafers cut from a single board. The formulation for each set contained 7 retention levels of DCOIT (0.02, 0.03, 0.04, 0.05, 0.06, 0.075, 0.09 lb/ft³) (0.32, 0.48, 0.64, 0.80, 0.96, 1.2, 1.44 kg/m³, respectively). The concentration of DCOIT in these formulations bridged the toxic threshold value of DCOIT so that the effect of the additives on the efficacy of DCOIT could be determined.

[0060] The approximated toxic threshold ranges ("TTR") for the various formulations are shown in Table 8. The compression strength data for formulations 4 and 6 was questionable due to erratic fungal activity so the threshold ranges were based on an evaluation of the strength loss data.

Table 8

No.	Polymer	polymer:biocide weight ratio	Additives	TTR, lb/ft ³ (kg/m ³)
1	none	N/A	P9 oil, 0.19% Nopcocaster	0.05-0.06 (0.8-0.96)
2	G	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.02-0.03 (0.32-0.48)
3	G	20:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.03-0.04 (0.48-0.64)
4	M	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.03-0.05* (0.48-0.8)
5	M	20:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.06-0.075 (0.96-1.2)
6	F	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.04-0.06* (0.64-0.96)
7	A	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.05-0.06 (0.8-0.96)
8	E	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.04-0.05 (0.64-0.8)
9	C	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	>0.09 (>1.44)
10	none	N/A	P9 oil, 0.19% Nopcocaster	0.06-0.08 (0.96-1.28)
11	I	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.04-0.05 (0.64-0.8)
12	H	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.04-0.05 (0.64-0.8)
13	V	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.04-0.05 (0.64-0.8)
14	B	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.04-0.05 (0.64-0.8)
15	K	10:1	Dowanol PPH, 0.04% PG, 0.06% MDBS	0.05-0.06 (0.8-0.96)

Claims

1. A method for preserving wood; said method comprising contacting wood with a composition comprising:

- (a) an aqueous polymer dispersion having an average particle size less than 1000 nm, in which the polymer has a T_g less than 75°C;
- (b) at least one surfactant selected from among nonionic and anionic surfactants; and
- (c) at least one wood preservative selected from among halogenated isothiazolone biocides, halogenated carbamate fungicides and azole fungicides.

EP 1 714 757 A1

2. The method of claim 1 in which the wood preservative is 4,5-dichloro-2-n-octyl-4-isothiazolin-3-one.
3. The method of claim 2 in which the polymer is a styrene-acrylic polymer.
- 5 4. The method of claim 3 in which said at least one surfactant comprises a nonionic surfactant containing at least 15 ethylene oxide monomer units.
5. The method of claim 3 in which the polymer has a T_g less than 65°C.
- 10 6. The method of claim 5 in which the composition comprises 0.05% to 6% polymer solids, 0.01% to 1% of said at least one surfactant, and 500 ppm to 6000 ppm 4,5-dichloro-2-n-octyl-4-isothiazolin-3-one.
7. The method of claim 2 in which said at least one surfactant comprises a nonionic surfactant containing at least 15 ethylene oxide monomer units.
- 15 8. The method of claim 7 in which the composition comprises 0.05% to 6% polymer solids, 0.01% to 1.0% of said at least one surfactant, and 500 ppm to 6000 ppm 4, 5-dichloro-2-n-octyl-4-isothiazolin-3-one.
9. The method of claim 8 in which the polymer has a T_g less than 65°C.
- 20 10. A method for preserving wood; said method comprising contacting wood with a composition comprising:
 - (a) a polymer having a T_g less than 75°C;
 - (b) an organic solvent; and
 - 25 (c) at least one wood preservative selected from among halogenated isothiazolone biocides, halogenated carbamate fungicides and azole fungicides.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 06 25 1971

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	US 2003/012883 A1 (YU BING ET AL) 16 January 2003 (2003-01-16) * paragraphs [0004], [0018], [0024], [0030] - [0032], [0034], [0054], [0057], [0059]; claims 1,4,5 *	1-10	INV. B27K3/15
X	WO 93/14630 A (NC DEVELOPMENT, INC) 5 August 1993 (1993-08-05) * page 5, line 21 - page 6, line 29 * * page 8, lines 19-21 * * page 15, line 32 - page 16, line 3 *	1,10	
A	* claims 1,3,5-7,9,14,15; examples 4,5 *	1-10	
X	US 5 874 456 A (MCDADE ET AL) 23 February 1999 (1999-02-23) * sentences 5-7,62 * * column 2, lines 16-42,60-63 * * column 3, lines 17-26 *	10	
A	US 5 049 383 A (HUTH ET AL) 17 September 1991 (1991-09-17) * the whole document *	1-10	TECHNICAL FIELDS SEARCHED (IPC)
A	US 4 683 260 A (WICKERT ET AL) 28 July 1987 (1987-07-28) * the whole document *	1-10	B27K
A	WO 99/01522 A (RHODIA INC) 14 January 1999 (1999-01-14) * the whole document *	1-10	
A	US 3 870 557 A (FINK ET AL) 11 March 1975 (1975-03-11) * the whole document *	1-10	
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 31 July 2006	Examiner Nissen, V
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

1
EPO FORM 1503 03/82 (P04/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 06 25 1971

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

31-07-2006

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2003012883 A1	16-01-2003	NONE	
WO 9314630 A	05-08-1993	AU 3456893 A	01-09-1993
US 5874456 A	23-02-1999	NONE	
US 5049383 A	17-09-1991	AU 609461 B2 AU 1430388 A CA 1331725 C DE 3711680 A1 DK 185488 A EP 0286009 A2 FI 881560 A JP 63264502 A NO 881469 A PT 87172 A ZA 8802371 A	02-05-1991 13-10-1988 30-08-1994 27-10-1988 08-10-1988 12-10-1988 08-10-1988 01-11-1988 10-10-1988 01-05-1988 23-09-1988
US 4683260 A	28-07-1987	NONE	
WO 9901522 A	14-01-1999	AT 242793 T AU 8270498 A DE 69815539 D1 DE 69815539 T2 DK 1015523 T3 EP 1015523 A1	15-06-2003 25-01-1999 17-07-2003 06-05-2004 06-10-2003 05-07-2000
US 3870557 A	11-03-1975	AT 316710 B BE 785700 A1 CA 991487 A1 DD 97906 A5 DE 2135828 A1 FR 2146220 A1 GB 1374901 A IT 959079 B NL 7209697 A	25-07-1974 16-10-1972 22-06-1976 20-05-1973 01-02-1973 02-03-1973 20-11-1974 10-11-1973 19-01-1973

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 9627483 A [0002]
- US 6448279 B [0009]
- US 6485790 B [0009]
- US 6610282 B [0014]