




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁵ : C08B 37/08	A1	(11) International Publication Number: WO 91/04279 (43) International Publication Date: 4 April 1991 (04.04.91)
(21) International Application Number: PCT/JP90/01168 (22) International Filing Date: 12 September 1990 (12.09.90) (30) Priority data: 1/236731 12 September 1989 (12.09.89) JP (71) Applicant (for all designated States except US): SHISEIDO COMPANY LTD. [JP/JP]; 7-5-5, Ginza, Chuo-ku, Tokyo 104 (JP). (72) Inventors; and (75) Inventors/Applicants (for US only) : AKASAKA, Hidemichi [JP/JP]; YAMAGUCHI, Toshijiro [JP/JP]; Shiseido Laboratories, 1050, Nippa-cho, Kohoku-ku, Yokohama-shi, Kanagawa 223 (JP). (74) Agents: AOKI, Akira et al.; Seiko Toranomon Bldg., 8-10, Toranomon 1-chome, Minato-ku, Tokyo 105 (JP).		(81) Designated States: AT (European patent), BE (European patent), CA, CH (European patent), DE (European patent)*, DK (European patent), ES (European patent), FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent), US. Published <i>With international search report.</i>

(54) Title: PROCESS OF PRODUCTION OF LOW-MOLECULAR WEIGHT HYALURONIC ACID**(57) Abstract**

A process for producing hyaluronic acid having a viscosity average molecular weight of 500,000 or less by mechanically degrading a high molecular hyaluronic acid solution by a shear treatment.



DEGRADATION OF HA BY MANTON GAULIN

DESIGNATIONS OF "DE"

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MC	Monaco
AU	Australia	FI	Finland	MG	Madagascar
BB	Barbados	FR	France	ML	Mali
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Fasso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GR	Greece	NL	Netherlands
BJ	Benin	HU	Hungary	NO	Norway
BR	Brazil	IT	Italy	PL	Poland
CA	Canada	JP	Japan	RO	Romania
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
DE	Germany	LU	Luxembourg	TD	Chad
DK	Denmark			TG	Togo
				US	United States of America

DESCRIPTION

Process of Production of Low-Molecular Weight
Hyaluronic Acid

TECHNICAL FIELD

The present invention relates to a process for the
5 production of low-molecular weight hyaluronic acid
(hereinafter referred to as "HA"). More specifically,
it relates to a process for the production of a low
molecular hyaluronic acid which is stable against heat
and which can be industrially produced in a large
10 production scale.

BACKGROUND ART

HA is produced by extracts from rooster combs,
umbilical cord, skin, synovial fluid, and other
biological tissues or by the fermentation method using
15 bacteria of genus Streptococcus and is used for
cosmetics and pharmaceuticals. Heretofore, in this
field, high molecular weight HA has been mainly used due
to the fact that the higher the molecular weight and
viscosity of the HA, the more noticeable the effect.
20 However, high-molecular weight HA has many problems in
the application thereof. For example, high molecular
weight HA is poor in heat stability and is required to
storage at low temperatures. Furthermore, HA cannot be
heat sterilized. This has limited the development of
25 applications of HA.

On the other hand, it has been found that
low-molecular HA differs from the high-molecular HA in
that it easily dissolves in water and is low in
viscosity. Accordingly, there are such advantageous
30 effect that cosmetics including it do not give an
unpleasant feeling such as stickiness to the skin or
stinginess. Thus, the use of low-molecular HA as a
cosmetic material has been expected. Further, low
molecular HA has a healing effect on wounds and,
35 therefore, is considered applicable as, for example, eye

drops, skin ointments, anti-adhesion agents.

It has been heretofore known to obtain low-molecular HA by treating high-molecular weight HA (for example, an average molecular weight of 700,000 or more) by hyaluronidase and also heat, strong acid, strong alkali, and other chemical methods (Japanese Unexamined Patent Publication (Kokai) No. 62-79790 and Japanese Unexamined Patent Publication (Kokai) No. 63-57602).

However, the conventional processes for production of low-molecular HA have suffered from difficulties in control of the degree of decomposition and have given various molecular weight of hyaluronic acids, in addition to the HA of the desired molecular weight, and, as a result, an extremely broad distribution of molecular weights of the HA (in other words, an uneven molecular weight of the hyaluronic acid) is produced. Further, it is difficult to remove the hyaluronidase, acid, or alkali added for the treatment, and also there are problems such as a low yield. In addition, research on the heat stability of the resultant low-molecular weight HA has not yet been done.

DISCLOSURE OF INVENTION

Accordingly, the objects of the present invention are to eliminate the above-mentioned disadvantages of the prior art and to provide a process for producing a low-molecular weight hyaluronic acid having a viscosity average molecular weight of 500,000 or less and having a narrow molecular weight distribution at a high production yield.

Other objects and advantages of the present invention will be apparent from the following description.

In accordance with the present invention, there is provided a process for producing hyaluronic acid having a viscosity average molecular weight of 500,000 or less, preferably 15,000 to 500,000, by mechanically

degradating (or depolymerizing) a high-molecular weight hyaluronic acid solution by a shear treatment.

BRIEF DESCRIPTION OF DRAWINGS

5 The present invention will be better understood from the description set forth below with reference to the accompanying drawings, in which:

Figure 1 shows the relation between the times of treatment of high-molecular weight HA by a MANTONGAULIN and the resultant molecular weight;

10 Fig. 2 shows the results of a heat stability test at 40°C and 60°C of an aqueous low-molecular weight HA solution;

Fig. 3 shows the results of a heat stability test at 40°C and 60°C of an aqueous high-molecular weight HA solution; and

15 Fig. 4 shows the gel filtration chromatogram of low-molecular weight HA by Sephacryl S-1000.

BEST MODE FOR CARRYING OUT THE INVENTION

20 According to the present invention, the low-molecular weight HA having an average molecular weight of 500,000 or less, preferably 15,000 to 500,000 can be obtained by mechanically treating high-molecular weight HA (average molecular weight of 700,000 or more, preferably 700,000 to 2,500,000) by a shear treatment.

25 The resultant low-molecular weight HA has an extremely narrow distribution of molecular weights (i.e., gives a substantially uniform molecular weight) and further is stable with respect to heat.

30 The molecular weight distribution of the low-molecular weight HA produced according to the present invention is 1.7 or less using the Mw/Mn ratio as the index of the molecular weight distribution (Mw: weight average molecular weight, Mn: number average molecular weight).

35 In the present invention, the mechanical shear treatment is used for the method of degradating or depolymerizing high-molecular weight HA to a low-

molecular weight. This shear treatment under a high shear rate gives HA of an extremely narrow molecular weight distribution, a substantially uniform molecular weight, compared with treatment by conventional chemical methods (e.g., ultraviolet rays, electron beams, free radicals, alkali, acid, heat, enzymes). Further, there is no need for removal of, for example, hyaluronidase, acid, or alkali, which is considered difficult in the past, and also the yield is high and a large scale industrial production can be carried out.

The shear treatment under a high shearing force or a high shear rate according to the present invention means the share rate is 10^5 dyne/cm² or more.

The shear treatment by a high shearing force according to the present invention can be effected by an emulsifier capable of applying a stronger shear than the mixers usually used for emulsification (e.g., homomixers, Disper mixers, propeller agitators). Examples of such emulsifiers are a MANTONGAULIN, French press, microfluidizer, colloid mill.

In the treatment using a shearing force of the present invention, the higher the pressure applied to the HA solution or the smaller the sectional area of the small spaces for passage, the higher the shear force created. In general, however, since the flow rate of the solution passing through the small spaces is large, the reduction in the molecular weight by a single treatment is insufficient and, therefore, it is desirable that the same operation be repeated or that multiple stage apparatuses is used to reduce the molecular weight to the desired level.

The starting HA used in the present invention may be any commercially available fowl tumor derived HA, microorganism desired HA, or relatively uniform high molecular weight HA obtained by cultivating HA producing bacteria under strictly controlled conditions and harvesting the same, so long as it is an HA of a high

molecular weight or a relatively high molecular weight (for example, an average molecular weight of 700,000 or more, preferably 700,000 to 2,500,000).

5 The production of HA according to the present invention is performed in an aqueous solution state. The concentration of HA in the solution is not particularly limited, but usually up to 2% by weight is preferable. When the concentration is more than 2% by weight, the viscosity becomes large and handling becomes
10 inconvenient, which is not preferable from the viewpoint of commercialization.

In the present invention, the temperature of the solution during the shear treatment of HA has a large effect on the effect of the degradation to a low
15 molecular weight. However, when a temperature is too high, a browning reaction and the like may occur and, therefore, the temperature is usually selected to be from room temperature to 100°C.

The starting HA is dissolved in water or a suitable
20 saline solution and when degraded to the desired average molecular weight, separation and purification are performed by the usual, known operations such as organic solvent fractionation, salting out, dialysis, ultrafiltration, whereby it is possible to obtain HA
25 having a narrow distribution of molecular weights with any average molecular weight below 500,000 and stable with respect to heat.

The low-molecular weight HA according to the present invention obtained in this way has in itself a
30 wound curing effect, and, therefore, can be applied to eye drops, skin ointment, anti-adhesion agents, and other pharmaceuticals and cosmetics.

The HA obtained according to the present invention has an extremely narrow distribution of molecular weight
35 and a substantially uniform molecular weight. Further, it is superior in heat stability. Further, there is no need for removal of the hyaluronidase, acid, or alkali,

which is considered difficult in the conventional chemical methods, the yield is high, and a large scale industrial production can be carried out.

EXAMPLES

5 The present invention will now be further illustrated by, but is by no means limited to, the following Examples.

Example 1

10 HA having a viscosity average molecular weight of 1,800,000 was dissolved in water to prepare two liters of a 0.3% by weight aqueous solution. This aqueous solution was degraded into low molecular form by a MANTONGAULIN of APV Gaulin Co. The pressure was set to 8,000 psi for 5 minutes and 4,000 psi for 10 minutes and
15 the treatment was repeated under the same conditions to find the relationship between the number of treatments and the molecular weight. The results are shown in Fig. 1. The molecular weight was calculated by measuring the intrinsic viscosity $[\eta]$ and the formula of
20 Laurent $h = 36 \times Mw^{0.78} \times 10^{-5}$ (wherein Mw is a weight average molecular weight). As a result, for example, with 30 treatments at 8,000 psi, it was possible to produce HA having any average molecular weight up to a molecular weight of 500,000 or less.

25 Example 2

 A heat stability test was performed at 40°C and 60°C for a 0.1% by weight aqueous solution of the low molecular HA obtained in Example 1. The results are shown in Fig. 1. HA's having an average molecular
30 weight of 97,000, 155,000, 276,000, and 485,000 were stable for over six months. HA with an average molecular weight of over 1,800,000 (i.e., Comparative Example, Fig. 3), however, clearly fell in molecular weight.

35 Example 3

 The Sephacryl S-1000 chromatograms of HA having an average molecular weight of 155,000 obtained in

Example 1 and HA having an average molecular weight of 162,000 obtained by heat decomposition (Comparative Example) are shown in Fig. 4.


As clear from the figures, the HA obtained by
5 degradation to low molecular form by the shear treatment had a narrower distribution of molecular weight and more uniform molecular weight compared with HA obtained by heat treatment.

CLAIMS

1. A process for producing hyaluronic acid having a viscosity average molecular weight of 500,000 or less by mechanically degradating a high-molecular weight hyaluronic acid solution by a shear treatment.
- 5 2. A process as claimed in claim 1, wherein the shear treatment is carried out at a shear rate of 10^5 dyne/cm² or more.
3. A process as claimed in claim 1, wherein the viscosity average molecular weight of the high-molecular weight hyaluronic acid to be treated is 700,000 or more.
- 10 4. A process as claimed in claim 1, wherein the viscosity average molecular weight of the resultant hyaluronic acid is 15,000 to 500,000.
5. A process as claimed in claim 1, wherein the molecular weight distribution of the resultant hyaluronic acid is 1.7 or less in terms of the Mw/Mn ratio.
- 15


1/4

Fig. 1



DEGRADATION OF HA BY MANTON GAULIN

Fig. 2



RESULT OF HEAT STABILITY TEST
AT 40°C AND 60°C OF AQUEOUS
LOW-MOLECULAR WEIGHT HA SOLUTION





Fig. 4



INTERNATIONAL SEARCH REPORT

PCT/JP 90/01168

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all)⁶

According to International Patent Classification (IPC) or to both National Classification and IPC

Int.Cl. 5 C08B37/08

II. FIELDS SEARCHED

Minimum Documentation Searched⁷

Classification System

Classification Symbols

Int.Cl. 5

C08B

Documentation Searched other than Minimum Documentation
to the Extent that such Documents are Included in the Fields Searched⁸III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹

Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
Y	FR,A,2521569 (KAKEN PHARMACEUTICAL CO.) 19 August 1983 see page 1, lines 30 - 36 see page 2, lines 21 - 23 see page 3, lines 14 - 31 see page 4, lines 4 - 5, 19 - 21 ---	1-4
Y	EP,A,216453 (FIDIA S.P.A.) 01 April 1987 see page 41, lines 11 - 22 see page 42, lines 5 - 15 ---	1-4
A	EP,A,138572 (FIDIA S.P.A.) 24 April 1985 see page 2, lines 15 - 17 see page 3, lines 15 - 19 see page 4, lines 20 - 22 see page 5, line 23 - page 6, line 2 see page 15, lines 1 - 3 --- -/--	1

¹⁰ Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search

27 NOVEMBER 1990

Date of Mailing of this International Search Report

20. 12. 90

International Searching Authority

EUROPEAN PATENT OFFICE

Signature of Authorized Officer

R.J. Eernisse

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category °	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP,A,239335 (INTERNATIONAL PHARMACEUTICAL PRODUCTS, INC.) 30 September 1987 see column 2, lines 19 - 22 see column 2, line 45 - column 3, line 6 see column 4, lines 9 - 12 ---	1

ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.

JP 9001168
SA 40041

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 12/12/90

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2521569	19-08-83	JP-A, B, C58140094	19-08-83
		CH-A- 653689	15-01-86
		DE-A- 3304775	25-08-83
		GB-A, B 2116576	28-09-83
EP-A-216453	01-04-87	AU-B- 591501	07-12-89
		AU-A- 5983686	26-02-87
		JP-A- 62064802	23-03-87
		US-A- 4965353	23-10-90
		US-A- 4851521	25-07-89
EP-A-138572	24-04-85	AU-A- 3414884	18-04-85
		BE-A- 900810	11-04-85
		CA-A- 1205031	27-05-86
		CH-A- 666897	31-08-88
		FR-A- 2553099	12-04-85
		LU-A- 85582	04-06-85
		JP-A- 61028503	08-02-86
EP-A-239335	30-09-87	AU-B- 600257	09-08-90
		AU-A- 6955887	24-09-87
		JP-A- 62295901	23-12-87
		ZA-A- 8701748	31-08-87