



(86) Date de dépôt PCT/PCT Filing Date: 2000/06/16
(87) Date publication PCT/PCT Publication Date: 2000/12/21
(45) Date de délivrance/Issue Date: 2005/04/26
(85) Entrée phase nationale/National Entry: 2001/02/14
(86) N° demande PCT/PCT Application No.: JP 2000/003977
(87) N° publication PCT/PCT Publication No.: 2000/077271
(30) Priorité/Priority: 1999/06/16 (11/169469) JP

(51) Cl.Int.⁷/Int.Cl.⁷ C22C 38/04, C22C 38/54, C22C 38/00

(72) Inventeurs/Inventors:
YAMADA, WATARU, JP;
NISHIDA, SEIKI, JP;
SUGIMARU, SATOSHI, JP;
HIKITA, NAOSHI, JP;
TAKAHASHI, HIROMI, JP

(73) Propriétaire/Owner:
NIPPON STEEL CORPORATION, JP

(74) Agent: GOUDREAU GAGE DUBUC

(54) Titre : TIGE DE FIL D'ACIER A TENEUR ELEVEE EN CARBONE PRESENTANT UNE EXCELLENTE CAPACITE
D'ETIRAGE ET DE RESISTANCE A LA FATIGUE APRES ETIRAGE DU FIL
(54) Title: HIGH CARBON STEEL WIRE EXCELLENT IN WIRE DRAWABILITY AND IN FATIGUE RESISTANCE AFTER
WIRE DRAWING

(57) **Abrégé/Abstract:**

The present invention provides a high carbon steel wire remarkably excellent in wire-drawability and fatigue resistance after wire drawing with a low cost due to reduced use of costly alloys. A high carbon steel wire according to the present invention is one excellent in wire-drawability and fatigue resistance after wire drawing, characterized in that; the total oxygen content is 15 to 50 ppm; among non-metallic inclusions included therein, the number of inviscid inclusions is 1.5 pieces/mm² or less in average under the visual field of an optical microscope; among the inviscid inclusions, the number of those having a composition falling within composition A specified below accounts for more than 20% and the total number of those having a composition falling within composition A or B specified below accounts for 80% or more; and the thickness of the inviscid inclusions having a composition falling within composition A specified below is 40µm or less; composition A: containing over 70% of SiO₂, composition B: containing 25 to 70% of SiO₂, 8 to 30% of MnO, 40% or less of MgO, 35% or less of Al₂O₃, 25% or less of CaO and 6% or less of TiO₂, and at least 5% of one or both of Al₂O₃ and MgO, and additionally at least 2% of one or both of CaO and TiO₂.



- 26 -

ABSTRACT

The present invention provides a high carbon steel wire remarkably excellent in wire-drawability and fatigue resistance after wire drawing with a low cost due to reduced use of costly alloys. A high carbon steel wire according to the present invention is one excellent in wire-drawability and fatigue resistance after wire drawing, characterized in that; the total oxygen content is 15 to 50 ppm; among non-metallic inclusions included therein, the number of inviscid inclusions is 1.5 pieces/mm² or less in average under the visual field of an optical microscope; among the inviscid inclusions, the number of those having a composition falling within composition A specified below accounts for more than 20% and the total number of those having a composition falling within composition A or B specified below accounts for 80% or more; and the thickness of the inviscid inclusions having a composition falling within composition A specified below is 40μm or less;

composition A: containing over 70% of SiO₂,
composition B: containing 25 to 70% of SiO₂, 8 to 30% of MnO, 40% or less of MgO, 35% or less of Al₂O₃, 25% or less of CaO and 6% or less of TiO₂, and at least 5% of one or both of Al₂O₃ and MgO, and additionally at least 2% of one or both of CaO and TiO₂.

DESCRIPTION

HIGH CARBON STEEL WIRE EXCELLENT IN WIRE-DRAWABILITY AND
IN FATIGUE RESISTANCE AFTER WIRE DRAWING

5

FIELD OF ART

The present invention relates to a high carbon steel wire for wire drawing excellent in wire-drawability and in fatigue resistance after wire drawing, which steel wire is used for, for example, bridge cables, various wires for aircraft, long rubber belts, cords for steel tires, etc., after wire drawing.

15

BACKGROUND ART

High carbon steel wire for wire drawing is generally required to withstand high-speed drawing and to have excellent fatigue resistance after wire drawing. Hard oxide type non-metallic inclusions are one of the factors adversely affecting these properties.

Among oxide type inclusions, inclusions of a single composition such as Al_2O_3 , SiO_2 , CaO , TiO_2 and MgO , etc. are generally hard and inviscid. It is widely known, therefore, that it is necessary to enhance the cleanliness of molten steel and soften oxide type inclusions to manufacture a high carbon steel wire having excellent wire-drawability.

As methods to enhance the cleanliness of steel and soften inviscid inclusions, Japanese Examined Patent Publication No. S57-22969 discloses a method to manufacture a high carbon steel excellent in wire-drawability, and Japanese Unexamined Patent Publication No. S55-24961 discloses a method to manufacture an ultrafine wire. The basic concept of these technologies, however, is limited to the composition control of oxide type non-metallic inclusions in the ternary compound

system of Al_2O_3 - SiO_2 - MnO .

Meanwhile, Japanese Unexamined Patent Publication No. S50-71507 proposes to improve wire-drawability of a product by having the composition of non-metallic
5 inclusions fall within the range of spessartite in the ternary compound system phase diagram of Al_2O_3 , SiO_2 and MnO , and Japanese Unexamined Patent Publication No. S50-81907 discloses a method to improve wire-drawability by decreasing harmful inclusions through the control of the
10 Al amount added to molten steel.

Additionally, Japanese Examined Patent Publication No. S57-35243 proposes, in relation to manufacturing steel cords for tires with an inviscid inclusion index of 20 or below, to soften inclusions by injecting alloys
15 containing one or more of Ca, Mg and REM after preliminary deoxidation by injecting a flux containing CaO with a carrier gas (inert gas) into molten steel in a ladle with the complete control of Al.

In above proposed methods, in case of reforming
20 ternary system non-metallic inclusions, stable composition control is not easy while, in case of controlling multi-component non-metallic inclusions, the reduction of the size and number of inclusions and the security of ductility are hard to achieve and, thus, an
25 improvement in wire-drawability and fatigue resistance after wire drawing cannot be expected. In Japanese Examined Patent Publication No. H4-8499, a high carbon steel wire having remarkably excellent wire-drawability and fatigue resistance after wire drawing has been
30 realized by; specifying the total oxygen content within a prescribed range and controlling the amount and composition of inviscid inclusions; obtaining favorable distribution of the amount and size of inviscid inclusions by securing the reduction of the size and
35 number of inviscid inclusions and their ductility; and softening inclusions by reforming the composition of inclusions into oxide type inclusions of multi-component

- 3 -

system containing SiO_2 and MnO and selectively containing Al_2O_3 , MgO , CaO and TiO_2 .

5 In the invention disclosed in Japanese Examined Patent Publication No. H4-8499, a secondary deoxidizer containing Al and two or more of Mg, Ca, Ba, Ti, V, Zr and Na is added to molten steel, for the purpose of reforming inclusions into oxide type inclusions of multi-component system containing SiO_2 and MnO and selectively containing Al_2O_3 , MgO , CaO and TiO_2 . However, these alloys
10 for deoxidation are expensive and thus it is desirable, for the reduction of production cost, to reduce the use of these costly alloys.

DISCLOSURE OF THE INVENTION

15 The object of the present invention is to provide a high carbon steel wire remarkably excellent in wire-drawability and fatigue resistance after wire drawing at a low cost by reducing the use of the above-mentioned expensive alloys.

20 Namely, the gist of the present invention is as follows:

(1) A high carbon steel wire excellent in wire-drawability and fatigue resistance after wire drawing, characterized in that; the total oxygen content is 15 to
25 50 ppm; among non-metallic inclusions included therein, the number of inviscid inclusions is 1.5 pieces/ mm^2 or less in average under the visual field of an optical microscope; among the inviscid inclusions, the number of those having a composition falling within composition A
30 specified below accounts for more than 20% and the total number of those having a composition falling within composition A or B specified below accounts for 80% or more; and the thickness of the inviscid inclusions having a composition falling within composition A specified
35 below is 40 μm or less;

composition A: containing over 70% of SiO_2 ,

composition B: containing 25 to 70% of SiO_2 , 8 to 30% of

- 4 -

MnO, 40% or less of MgO, 35% or less of Al₂O₃, 25% or less of CaO and 6% or less of TiO₂, and at least 5% of one or both of Al₂O₃ and MgO and, additionally, at least 2% of one or both of CaO and TiO₂.

5

(2) A high carbon steel wire excellent in wire-drawability and fatigue resistance after wire drawing according to item (1), characterized in that the inclusions having composition B specified above contain 5% or less of other oxides (one or more of the oxides of V, Ba, Zr and Na and trace amount of other oxides inevitably included, hereunder referred to as "other oxides").

15

(3) A high carbon steel wire excellent in wire-drawability and fatigue resistance after wire drawing according to item (1) or (2), characterized in that the number of inviscid inclusions having a composition falling within composition A is 1 piece/mm² or less in an observation visual field.

20

(4) A high carbon steel wire excellent in wire-drawability and fatigue resistance after wire drawing according to any one of items (1) to (3), characterized by containing 0.4 to 1.2% of C, 0.1 to 1.5% of Si and 0.1 to 1.5% of Mn in weight.

25

(5) A high carbon steel wire excellent in wire-drawability and fatigue resistance after wire drawing according to any one of items (1) to (3), characterized by containing, in weight, 0.4 to 1.2% of C, 0.1 to 1.5% of Si and 0.1 to 1.5% of Mn, additionally P and S controlled not to exceed 0.02%, respectively, and one or more of 0.05 to 1.0% of Cr, 0.05 to 1.0% of Ni, 0.05 to 1.0% of Cu, 0.001 to 0.01% of B, 0.001 to 0.2% of Ti, 0.001 to 0.2% of V, 0.001 to 0.2% of Nb, 0.05 to 1.0% of Mo and 0.1 to 2% of Co.

30

35

- 5 -

Here, inviscid inclusions denote inclusions whose length or thickness is $5\mu\text{m}$ or more and the length (l) and the thickness (d) of each of them satisfy the formula $l/d \leq 5$, under optical microscope observation of a longitudinal section including the center line of a wire.

It is generally known that, when inclusions contain the oxides of simple composition or specific oxides in high quantity, they are hard and their plasticity is poor. The most significant feature of the present invention is a discovery of the fact that the inclusions having a high content of SiO_2 are softer than those having high content of Al_2O_3 and MgO and that, even if inclusions having high content of said SiO_2 account for more than 20%, the wire-drawability and fatigue resistance after wire drawing of a steel wire are not adversely affected so long as the thickness (d) of said inclusions is controlled not to exceed $40\mu\text{m}$.

20

BEST EMBODIMENT FOR CARRYING OUT THE INVENTION

On specifying total oxygen content in the range of 15 to 50 ppm

When the total oxygen content of steel is high, blowholes are generated during the solidification of molten steel causing surface defects and the amount of inviscid inclusions increases in a steel wire having a total oxygen content exceeding 50 ppm. For this reason, the upper limit of the total oxygen content is set at 50 ppm. On the other hand, though it is easy to reduce the total oxygen content to 15 ppm or less when a strong deoxidizer such as Al and Mg is used abundantly, a total oxygen content of 15 ppm or more is required for the composition control of inviscid inclusions in a steel wire of the present invention. A yet preferable range of the total oxygen content is from 17 to 40 ppm. Further,

when the total oxygen content is below 15 ppm or more than 50 ppm, the service life of the wire drawing dies deteriorates drastically and, for this reason, the range of the total oxygen content is set at 15 to 50 ppm.

5 On specifying the number of invisid inclusions

10 The amount of invisid inclusions among oxide type non-metallic inclusions in a steel wire affects its wire-drawability and fatigue resistance after wire drawing. From this viewpoint, for the present invention too, it is necessary to reduce the amount of invisid inclusions to as little as possible. By controlling the number of invisid inclusions to 1.5 pieces/mm² or less, excellent wire-drawability and fatigue resistance after wire drawing can be obtained through combined effects with the other requirements claimed herein. When the number of invisid inclusions exceeds 1.5 pieces/mm², the wire disconnection rate rises markedly high and the die service life becomes shorter. It is preferable yet to control the number of the non-metallic inclusions to 1.0 piece/mm² or less.

20 On the composition of invisid inclusions

25 In conventional technologies, invisid inclusions are softened by compounding the composition of the inclusions. In those technologies, the SiO₂ content of inclusions is specified to be 70% or less because it is understood that hard SiO₂ inclusions form when SiO₂ concentration exceeds the percentage figure.

30 The present inventors have discovered, as a result of intensive studies, that, even if invisid inclusions have a high SiO₂ content, they do not cause any harm even in a succeeding wire drawing process so long as their size is small. It is true that SiO₂ type inclusions are hard, but they are softer than MgO or Al₂O₃ type inclusions. Therefore, wire-drawability and fatigue resistance after wire drawing are sufficiently good so long as the size of the inclusions is controlled to $d \leq$

- 7 -

40 μ m. It is more preferable to control the size of
inviscid inclusions having a high SiO₂ content to $d \leq$
20 μ m.

5 In the present invention, composition B denotes the
composition range of inclusions which are sufficiently
soft and rendered harmless by being broken down and
minutely dispersing during wire drawing, while
composition A denotes the composition range of inclusions
10 having a higher SiO₂ content than the inclusions
conforming to the composition B. It has been specified
that the number of invisid inclusions conforming to
composition A accounts for 20% or more and the total
number of those conforming to composition A or B accounts
for 80% or more.

15 The reason why the total number of inclusions
conforming to composition A or B must account for 80% or
more is that inclusions having composition not falling
within any of compositions A and B are, for example, MgO
and Al₂O₃ type inclusions and they are hard, and that
20 these hard inclusions deteriorate wire-drawability and
fatigue resistance after wire drawing when their
proportion exceeds 20%.

Further, the reason why the number of inclusions
conforming to composition A must account for 20% or more
25 is that inclusions conforming to composition A increase
as the addition amount of ferroalloys of Ca, Al, Mg and
Ti in molten steel is decreased, and that, when the
addition amount of these ferroalloys is decreased to the
extent of raising the proportion of inclusions conforming
30 to composition A to 20% or more, the cost reduction
effect, which is an object of the present invention, can
be achieved.

In the present invention, the range of the
composition B is defined as follows:

35 ① containing 25 to 70% of SiO₂, 8 to 30% of MnO,
40% or less of MgO, 35% or less of Al₂O₃, 25% or less of

- 8 -

CaO and 6% or less of TiO_2 , and at least 5% of one or both of Al_2O_3 and MgO , and additionally at least 2% of one or both of CaO and TiO_2 ,

② containing 5% or less of other oxides (one or more of the oxides of V, Ba, Zr and Na and trace amount of other oxides inevitably included, hereunder referred to as "other oxides").

The reason why the range of composition B is limited will be explained hereunder.

To reduce the number of inviscid inclusions and soften them, which is an object of the present invention, the combination of oxide compositions in a multi-component system as specified above is required. One combination is oxides of a quaternary or higher compound system containing SiO_2 and MnO firstly and inevitably, then one or both of Al_2O_3 and MgO , and additionally one or both of CaO and TiO_2 . Another combination is oxides of a quaternary or higher compound system containing 5% or less of the other oxides in addition to above oxides. Here, the addition of 5% or less of the other oxides contribute to softening the inviscid inclusions yet further. The steel according to the present invention does not fail to be a steel wire excellent in wire-drawability and fatigue resistance after wire drawing if inviscid inclusions conforming to composition B have either of the combinations according to the present invention.

When SiO_2 content is below 25%, a good combination with the other oxides as inclusions of multi-component system oxides cannot be obtained. The range of SiO_2 content of over 70% coincides with the range of composition A, which has conventionally been avoided as the one where hard inclusions are formed.

Since MnO is displaced or compounded by the oxidation with Al and Mg, 30% or more of MnO is not formed. When its content is below 8%, on the other hand, the inviscid inclusions become hard. For this reason, the

range of MnO is set at 8 to 30%.

With MgO content exceeding 40%, hard MgO inclusions are formed and thus its content is limited to 40% or less. A preferable range is from 5 to 25%.

5 With Al_2O_3 content exceeding 35%, well-balanced combination of multi-component system oxides is disturbed, causing the other oxide elements in inclusions to relatively lower, resulting in the formation of hard inclusions. The upper limit of Al_2O_3 to avoid this
10 problem is 35%, more preferably 25%.

 With regard to the combination of Al_2O_3 and MgO, in the manufacture of a steel wire according to the present invention, wherein SiO_2 type oxides suspended in molten steel are combined with Ca, Mg and Al, etc. during a
15 secondary deoxidation process to form compound inclusions, inviscid inclusions become soft and are rendered harmless when the total content of one or both of Al_2O_3 and MgO in inviscid inclusions formed in a steel wire is 5% or more. For this reason, the lower limit of
20 one or both of Al_2O_3 and MgO is set at 5%.

 With regard to CaO, when the CaO content is high, generally speaking, spherical inviscid inclusions are formed. However, when CaO content is 25% or less and the inclusions are of multi-component system as in the
25 present invention, CaO also contributes to decreasing the hardness of oxide type inclusions and reducing the number of inviscid inclusions. The upper limit of CaO content is, therefore, set at 25%. A more preferable content range of CaO is from 1 to 20%.

30 Ti is an element generally used for the control of austenite crystal grain size. However, it is also effective for softening non-metallic inclusions of multi-component system oxides like in the present invention. It is particularly effective for softening when TiO_2 content
35 is 6% or less in the inviscid inclusions of the multi-component system. Hence, the TiO_2 content range is set at 6% or less. A more preferable range is 4% or less.

- 10 -

With regard to the combination of CaO and TiO_2 , when the content of one or both of them is 2% or more, the inviscid inclusions are softened yet further.

5 Lastly, the content of the other oxides limited to 5% or less is described hereunder.

10 The composition described above is essential for obtaining the multi-component system inviscid inclusions according to the present invention. Further, V, Ba, Zr and Na, etc. are added in addition to secondary deoxidation elements. These oxides and other oxides such as oxides of Cr and K, etc. inevitably included in steel in very small quantities are collectively called the other oxides. When the content of the other oxides is 5% or less, they contribute to softening inviscid
15 inclusions. For this reason, the upper limit of the combined content of one or more of the other oxides is set at 5%.

Now, combinations of the oxides described above are explained hereunder.

20 Firstly, the reason is given as to why SiO_2 and MnO are indispensable in any case.

The inviscid inclusions comprising multi-component system oxides according to the present invention can be obtained, as described in examples, by forming a
25 deoxidation product of $\text{SiO}_2 + \text{MnO}$ at primary deoxidation and, thereafter, forming a compound SiO_2 deoxidation product at secondary deoxidation. Thus, as a matter of course, SiO_2 and MnO , which form the basis of the deoxidation products, must not fail to exist in inviscid
30 inclusions.

Then, the combination of Al_2O_3 and MgO is described hereunder.

35 As one of the deoxidation technologies to form non-metallic inclusions of multi-component system oxides according to the present invention, an important technology is the utilization of strong deoxidation effects of Al and Mg and the coagulation and floating

effects of said inclusions in molten steel. With regard to said inclusions remaining in molten steel after refining of molten steel, there is a relationship between Al_2O_3 and MgO in the same refined molten steel that, in the composition range of inviscid inclusions according to the present invention, MgO content tends to be low when Al_2O_3 content is high and, reciprocally, Al_2O_3 content tends to be low when MgO content is high. For this reason, the present invention prescribes that one or both of Al_2O_3 and MgO must be contained.

Next, a reason is given to explain why it is prescribed that one or both of CaO and TiO_2 must be contained.

The non-metallic inclusions of multi-component system oxides like those according to the present invention show widely varied composition changes depending on deoxidation conditions. In this background, one or both of CaO and TiO_2 must be present in inviscid inclusions, especially in order to reduce the number of inviscid inclusions of multi-component system inclusions and soften them.

An important point of the present invention is to control the size of inviscid inclusions conforming to composition A so that $d \leq 40\mu\text{m}$ holds true. This is because the inclusions conforming to composition A do not hinder the inclusion softening effect when the formula $d \leq 40\mu\text{m}$ is satisfied, although they are somewhat harder than the inclusions whose composition falls within composition B.

Large inclusions whose d exceeds $40\mu\text{m}$ are mainly ladle deoxidation products formed in molten steel in a ladle after deoxidation. When compound deoxidation involving Ca , Al , Mg and Ti is carried out so that most inviscid inclusions have compositions conforming to composition B as in the present invention, said deoxidation products in a ladle are softened, and most of

- 12 -

the large inclusions having d exceeding $40\mu\text{m}$ are stretched to satisfy $l/d > 5$. In this case, since most of those SiO_2 -rich inclusions conforming to composition A are those formed during steel solidification, they cannot grow large and the formula $d \leq 40\mu\text{m}$ remains true. Thus, d of the inviscid inclusions whose composition falls within compositions A and B can be controlled not to exceed $40\mu\text{m}$.

As explained above, it is necessary in the present invention to control the number of inviscid inclusions to 1.5 pieces/ mm^2 or less. By the present invention wherein a compound deoxidation is carried out so that the total number of inviscid inclusions conforming to composition A and those conforming to composition B is 80% or more, it is possible, as a consequence, to stably maintain the number of inviscid inclusions at 1.5 pieces/ mm^2 or less. Preferably, by controlling the number of inviscid inclusions to 1.0 piece/ mm^2 or less, the wire-drawability and fatigue resistance after wire drawing of a steel wire stabilize.

The present invention can secure excellent wire-drawability and fatigue resistance after wire drawing by controlling the composition, size and number of inclusions as described above. In addition, the service life of wire drawing dies can be extended by the present invention by reducing the number of inviscid inclusions conforming to composition A to 1.0 piece/ mm^2 or less in average, and more preferably, to 0.5 piece/ mm^2 or less.

As described above, the present invention achieves excellent results in the applications where wire-drawability and fatigue resistance after wire drawing as severe as conventional cases are required. Recently, however, larger diameter cords are used in some tire cord applications, wherein the required wire-drawability is a little more relaxed than before. With regard to the service life of wire drawing dies, also, improvements in

- 13 -

lubrication and other factors have made it possible to continue drawing operations not affected by deterioration in inclusion levels in steel materials. The super-clean steel according to the present invention has an excellent effect especially in these applications.

The specification of the steel chemical composition according to the present invention is explained hereunder. Killed steels for piano wire rods and hard steel wire rods under the Japanese Industrial Standard (JIS) G3502 and G3506 are widely used as the steels for high carbon steel wires. On the basis of these JIS steel grades and in consideration of ease of manufacturing and actual applications, the present invention specifies steel chemical composition, in weight, as follows: said steel containing 0.4 to 1.2% of C, 0.1 to 1.5% of Si and 0.1 to 1.5% of Mn, and containing one or more of 0.05 to 1.0% of Cr, 0.05 to 1.0% of Ni, 0.05 to 1.0% of Cu, 0.001 to 0.01% of B, 0.001 to 0.2% of Ti, 0.001 to 0.2% of V, 0.001 to 0.2% of Nb, 0.05 to 1.0% of Mo and 0.1 to 2% of Co as required.

C is an economical and effective element to strengthen steel, and 0.4% or more of it is required to obtain the strength required for a hard steel wire. When its content exceeds 1.2%, however, the ductility of steel decreases, resulting in embrittlement and difficulty in secondary working. For this reason, the content is set at 1.2% or less.

Si and Mn, on the other hand, are necessary for deoxidation and the control of the composition of inclusions. Either of them is ineffective when added below 0.1%. Both the elements are also effective for strengthening steel, but steel becomes brittle when either of them exceeds 1.5%.

Cr has to be controlled within a range from 0.05 to 1.0% because the least necessary amount for securing its effect to refine pearlite lamella and enhance steel strength is 0.05% and thus the addition of Cr in the

- 14 -

amount of 0.05% or more is desirable. However, when added beyond 1.0%, ductility deteriorates. For this reason, the upper limit is set at 1.0%.

5 Ni strengthens steel through an effect similar to that of Cr, hence the addition amount of 0.05% or more, where the effect is demonstrated, is desirable, but its content has to be 1.0% or less so as not to cause the deterioration of ductility.

10 Since Cu improves scale properties and corrosion fatigue properties of a wire, the addition amount of 0.05% or more, where the effect is demonstrated, is desirable, but its content has to be 1.0% or less so as not to cause deterioration of ductility.

15 B is an element to enhance hardenability of steel. In case of the present invention, it is possible to enhance steel strength by adding B, but its excessive addition deteriorates steel toughness through increased boron precipitation, and for this reason, its upper limit is set at 0.01%. Too small an addition amount of B does
20 not bring about any effect, and hence its lower limit is set at 0.001%.

Ti, Nb and V enhance the strength of a steel wire through precipitation hardening. None of them is effective when added below 0.001%, but they cause
25 precipitation embrittlement when added beyond 0.2%. For this reason their respective contents have to be 0.2% or less. Addition of these elements is also effective for fining γ grains during patenting.

Mo is another element to enhance steel
30 hardenability. In case of the present invention, it is possible to enhance steel strength by adding Mo, but its excessive addition raises steel hardness excessively resulting in poor workability and, for this reason, the range of its addition amount is specified as 0.05 to
35 1.0%. Co enhances steel ductility by suppressing the formation of pro-eutectoid cementite of supereutectoid steel.

- 15 -

In addition, in high carbon steels, it is preferable to control the content of each of P and S to 0.02% or less since either of them deteriorates not merely wire-drawability but also ductility after wire drawing.

5 Note that the present invention can be applied not only to a steel wire but also to any hot-rolled steel product.

10 EXAMPLE

 The refining of molten steel for the examples was carried out using an LD converter and the slag spillage from the converter into a ladle at tapping was minimized (50 mm or less in thickness) by the use of a slag stopper
15 ball.

 A recarburizer and deoxidizing ferroalloys such as Fe-Mn, Fe-Si, and Si-Mn were added at the tapping to adjust the contents of C, Mn and Si, then argon was injected into molten steel from the bottom a ladle.

20 The molten steel in the ladle after the tapping was a killed steel deoxidized with Si and Mn, etc. The ladle was then transferred to a refinery position and, then, after a slag composition adjustment process, secondary deoxidizer, in the form of ferroalloys and containing Al
25 and two or more of Mg, Ca, Ba, Ti, V, Zr, Na and REM, was added into the molten steel. The alloy was fed into the molten steel through a bare steel surface cleared of slag by argon bottom bubbling.

 At the ferroalloy addition, the total Al input
30 amount including Al from the ferroalloys for deoxidation and other purposes was controlled to 5.0 to 9.5 g/t-molten steel. In conventional steel for comparison, Mg and Ca ferroalloys were added as appropriate.

 After the addition of ferroalloy, the molten steel
35 further underwent a fine composition adjustment before the completion of ladle refining. The molten steel was then continuously cast from the ladle via a tundish,

- 16 -

heated in a reheating furnace, rolled into billets, surface-conditioned, then rolled into wires of 5.5 mm in diameter via another reheating furnace and a wire-rod mill.

5 In the examples, the number and composition of
inviscid inclusions were examined in the following
manner: a sample of 0.5 m long was cut out from a coil of
steel wire of 5.5 mm in diameter; small specimens of 11
mm long each were cut out from 10 places chosen at random
10 along the length of each of the samples; and the entire
surface of a longitudinal section of each of the small
specimens including its longitudinal center line was
inspected. The number of the inviscid inclusions used in
the examples is the mean value of all samples.

15 After that, the 5.5-mm diameter wires were drawn
into fine wires of 0.175 mm or less in diameter to
investigate their wire drawing properties and die service
life. The wire drawing properties were evaluated by
converting the frequency of wire disconnection per each
20 prescribed wire drawing tonnage into a wire disconnection
index. A wire disconnection index of 5 or less means
good. The die service life was evaluated using an index
wherein a minimum allowable die service life with
conventional materials is 100 and the index value is
25 larger as the service life becomes longer. A die service
life index of 100 or larger means good.

 Tables 1 and 2 show the examination results of the
materials according to the present invention and Tables 3
and 4 those of the comparative materials. Tables 2 and 4
30 show the evaluation results of the non-metallic
inclusions of the materials evaluated in Tables 1 and 3,
respectively, classified into average composition,
composition A and composition B.

Table 1

	No.	Chemical composition (wt %)															ppm	Number of total inclusions	Number of inclusions of composition	Rate of inclusions (%)		Max. d (µm)	Wire dis-connection index	Die life index
																				A	A + B			
		C	Si	Mn	P	S	Cr	Ni	Cu	B	Ti	V	Nb	Mo	Co	Total oxygen content								
Invented materials		1	0.72	0.18	0.51	0.018	0.022	-	-	-	-	-	-	-	-	-	24	0.13	0.05	35	100	16	0	150
		2	0.82	0.18	0.51	0.010	0.021	-	-	-	-	-	-	-	-	-	22	0.07	0.02	28	98	17	0	190
		3	0.92	0.20	0.30	0.012	0.019	0.50	-	-	-	-	-	-	-	-	23	0.19	0.08	41	100	19	0	200
		4	0.96	1.20	0.30	0.011	0.015	0.20	-	-	-	-	-	-	-	-	21	0.05	0.02	39	95	18	0	180
		5	0.81	0.19	0.31	0.015	0.021	0.24	-	-	-	-	-	-	-	-	15	0.07	0.02	31	100	18	0	240
		6	0.42	0.25	0.31	0.021	0.015	-	-	-	-	-	-	-	-	-	48	0.83	0.71	85	98	28	0	110
		7	0.72	0.10	0.11	0.024	0.018	-	-	-	-	-	-	-	-	-	35	0.50	0.48	95	100	18	0	130
		8	1.18	0.20	0.70	0.012	0.025	-	-	-	-	-	-	-	-	-	16	0.07	0.01	21	82	25	0	160
		9	0.75	1.50	0.75	0.013	0.023	-	-	-	-	-	-	-	-	-	26	0.60	0.37	62	95	29	0	170
		10	0.82	0.25	1.49	0.018	0.019	-	-	-	-	-	-	-	-	-	22	0.07	0.03	38	100	14	0	270
		11	0.62	0.18	0.49	0.022	0.024	-	-	-	-	-	-	-	-	-	38	1.48	0.96	65	100	35	0	100
		12	0.77	0.18	0.53	0.010	0.018	-	-	-	-	-	-	-	-	-	29	0.80	0.44	55	97	38	0	150
		13	0.82	0.18	0.53	0.015	0.022	-	-	-	-	-	-	-	-	-	22	0.27	0.12	45	98	16	0	140
		14	0.73	0.22	0.70	0.016	0.021	0.18	-	0.24	-	-	-	-	-	-	28	0.20	0.08	38	92	19	0	180
		15	0.83	0.19	0.50	0.022	0.018	0.24	-	-	-	-	-	-	-	-	32	0.40	0.31	77	85	19	0	180
		16	0.71	0.30	0.49	0.010	0.025	-	-	-	-	-	-	-	-	-	25	0.13	0.05	34	94	16	0	230
		17	0.81	0.22	0.51	0.009	0.023	-	0.92	0.22	0.002	-	-	-	-	-	29	0.10	0.04	40	88	18	0	150
		18	0.95	0.18	0.50	0.016	0.018	-	-	-	-	-	-	-	-	-	21	0.10	0.03	32	93	20	0	190

*1 Number density of inviscid inclusions. Mean number in all fields of vision
(pieces/mm²)

*2 Number density of inviscid inclusions conforming to composition A. Mean number in all fields of vision (pieces/mm²)

*3 Rate of inviscid inclusions conforming to composition A and rate of those conforming to composition A or B to all inviscid inclusions.

*4 Max d of inviscid inclusions conforming to composition A.

Table 2

No.	Average composition of non-metallic inclusions (wt %) *5							Composition A: average composition of inclusions (wt %) *6							Composition B: average composition of inclusions (wt %) *7						
	SiO ₂	MnO	Al ₂ O ₃	MgO	CaO	TiO ₂	Others	SiO ₂	MnO	Al ₂ O ₃	MgO	CaO	TiO ₂	Others	SiO ₂	MnO	Al ₂ O ₃	MgO	CaO	TiO ₂	Others
1	59.1	9.3	11.5	5.9	13.2	1.0	0.0	76	8	5	2	8	1	0	50	10	15	8	16	1	0
2	58.8	5.9	14.6	4.2	13.9	2.0	0.7	94	1	2	0	1	2	0	45	8	20	6	18	2	1
3	70.2	8.5	11.0	5.4	3.5	1.4	0.0	92	2	1	3	0	2	0	55	13	18	7	6	1	0
4	64.1	8.2	14.1	2.6	7.8	0.4	2.9	89	1	3	1	2	1	3	48	14	23	4	8	0	3
5	39.6	6.1	26.6	4.4	12.8	3.8	6.8	72	2	8	3	10	1	4	25	8	35	5	14	5	8
6	89.8	2.3	3.1	1.8	2.9	0.0	0.1	95	1	2	1	1	0	0	62	11	11	7	8	0	1
7	83.6	12.9	1.2	1.2	0.2	1.0	0.1	85	12	1	1	0	1	0	57	30	4	5	3	0	1
8	51.6	6.3	11.7	4.5	23.9	0.6	1.4	78	1	15	1	4	0	1	43	10	14	7	23	1	2
9	71.5	10.8	4.5	4.3	7.0	1.0	1.0	82	11	3	0	2	1	1	55	12	8	13	10	1	1
10	56.7	23.7	2.2	5.7	7.6	3.4	0.6	71	20	1	2	2	4	0	48	26	3	8	11	3	1
11	83.1	2.5	4.9	1.8	4.8	2.1	1.0	96	0	1	0	2	0	1	59	7	12	5	10	6	1
12	70.6	3.8	2.4	12.2	8.4	0.6	2.2	92	3	2	0	1	1	1	44	5	3	29	15	0	4
13	62.0	5.0	14.2	3.8	12.1	1.1	1.9	85	4	2	6	0	0	3	43	6	25	2	21	2	1
14	69.8	5.4	4.3	9.4	8.3	0.5	2.2	95	0	0	2	0	0	3	55	10	8	16	8	1	2
15	84.1	0.3	2.7	0.5	7.8	0.5	4.1	93	0	2	0	0	0	5	62	4	15	6	4	6	3
16	60.3	8.1	14.5	2.4	11.7	0.9	2.0	91	1	2	0	1	1	4	44	13	23	4	14	1	1
17	69.0	5.1	9.0	2.9	10.8	0.5	2.7	95	2	1	0	0	0	2	52	9	18	6	10	1	4
18	67.0	3.4	4.0	8.6	15.7	0.3	0.9	88	1	5	2	2	1	1	58	5	4	13	19	0	1

*5 Average composition of all inviscid inclusions in field of observation.

*6 Average composition of inviscid inclusions conforming to composition A among all inviscid inclusions in field of observation.

*7 Average composition of inviscid inclusions conforming to composition B among all inviscid inclusions in field of observation.

Table 3

No.	Chemical composition (wt %)														ppm		Number of total inclusions	Number of inclusions of composition A	Rate of inclusions (%)		Max. d (µm)	Wire dis-connection index	Die life index
	C	Si	Mn	P	S	Cr	Ni	Cu	B	Ti	V	Nb	Mo	Co	Total oxygen content								
Comparative materials	19	0.81	0.25	0.55	0.010	0.015	-	-	-	-	-	-	-	-	-	14	0.25	0.01	5	51	35	41	70
	20	0.72	0.20	0.50	0.025	0.023	-	-	-	-	-	-	-	-	-	55	0.58	0.56	96	100	24	0	10
	21	0.82	0.09	0.50	0.013	0.021	-	-	-	-	-	-	-	-	-	18	0.33	0.02	5	42	38	25	80
	22	0.62	0.19	0.11	0.012	0.016	-	-	-	-	-	-	-	-	-	28	0.37	0.03	8	35	34	10	60
	23	0.75	1.52	0.80	0.009	0.018	-	-	-	-	-	-	-	-	-	19	0.42	0.39	94	94	51	10	130
	24	0.82	0.19	1.53	0.011	0.023	-	-	-	-	-	-	-	-	-	28	0.17	0.04	23	38	36	15	130
	25	0.73	0.34	0.49	0.022	0.024	-	-	-	-	-	-	-	-	-	38	1.55	1.24	80	96	26	10	10
	26	0.75	0.19	0.48	0.009	0.024	-	-	-	-	-	-	-	-	-	45	0.47	0.46	98	100	42	15	20

*1 Number density of inviscid inclusions. Mean number in all fields of vision (pieces/mm²)

*2 Number density of inviscid inclusions conforming to composition A. Mean number in all fields of vision (pieces/mm²)

*3 Rate of inviscid inclusions conforming to composition A and rate of those conforming to composition A or B to all inviscid inclusions.

*4 Max d of inviscid inclusions conforming to composition A.

Table 4

No.	Average composition of non-metallic inclusions (wt %) *5										Composition A: average composition of inclusions (wt %) *6						Composition B: average composition of inclusions (wt %) *7						Inclusions of other compositions
	SiO ₂	MnO	Al ₂ O ₃	MgO	CaO	TiO ₂	Others	SiO ₂	MnO	Al ₂ O ₃	MgO	CaO	TiO ₂	Others	SiO ₂	MnO	Al ₂ O ₃	MgO	CaO	TiO ₂	Others	Al ₂ O ₃ or MgO type inclusions	
Comparative materials	19	26.3	4.7	34.3	16.3	13.0	2.0	3.5	71	1	10	3	10	2	3	8	33	2	25	3	4	Al ₂ O ₃ type inclusions	
	20	94.8	0.8	1.2	0.0	3.0	0.2	0.0	96	0	1	0	3	0	0	21	5	1	3	4	1		
	21	33.4	4.6	38.2	8.4	14.8	0.4	0.3	73	2	5	4	11	0	5	9	32	5	15	1	0	Al ₂ O ₃ type inclusions	
	22	52.1	2.2	32.2	2.8	8.2	1.4	1.2	93	0	1	0	4	2	0	8	30	8	5	2	2	Al ₂ O ₃ type inclusions	
	23	95.1	0.9	0.0	0.0	3.9	0.0	0.0	98	1	0	0	1	0	0	-	-	-	-	-	-		
	24	56.5	36.3	2.4	2.0	2.5	0.2	0.2	95	4	0	0	1	0	0	29	8	9	7	1	1	SiO ₂ -MnO inclusions	
	25	84.1	1.3	2.9	1.6	5.2	3.8	1.1	93	0	1	1	0	4	1	8	13	5	20	4	2		
	26	89.5	5.1	2.1	0.2	2.1	0.0	2.1	89	5	2	0	2	0	2	10	6	8	8	0	5		

*5 Average composition of all inviscid inclusions in field of observation.

*6 Average composition of inviscid inclusions conforming to composition A among all inviscid inclusions in field of observation.

*7 Average composition of inviscid inclusions conforming to composition B among all inviscid inclusions in field of observation.

All the materials according to the present invention, Nos. 1 to 18 shown in Tables 1 and 2, demonstrated good results.

5 The examination results of the comparative materials shown in Tables 3 and 4 are described hereafter. No. 19 is a case that the oxygen content is lower than the range according to the present invention. Due to strong deoxidation, hard inclusions comprising high
10 concentrations of Al_2O_3 and MgO are formed and, as a consequence, the wire disconnection index is high. No. 20 is a case that the oxygen content is higher than the range according to the present invention. Here the number of inclusions is large and the die service life is poor.
15 In Nos. 21 and 22, the contents of Si and Mn, respectively, are lower than the ranges according to the present invention. In either case, the rate of the inclusions having high Al_2O_3 concentration (not falling within the composition A or B) exceeds 20%, and the wire
20 disconnection index is high. In No. 23, the content of Si is higher than the range according to the present invention, and, as a result of the formation of inclusions consisting only of SiO_2 during deoxidation and those of large sizes, the wire disconnection index is
25 high. In No. 24, Mn content is higher than the range according to the present invention, and, the rate of SiO_2 -MnO binary inclusions is high due to too strong an effect of Si-Mn compound deoxidation, resulting in a high wire disconnection index. In No. 25, the number of
30 inclusions is too large due to insufficient inclusion removal during the refining processes, resulting in somewhat higher wire disconnection index in addition to a poor die service life. No. 26 is a case that the maximum diameter of inviscid inclusions conforming to composition
35 A is larger than the range according to the present invention, and, the wire disconnection index is high.

The fatigue resistance was evaluated regarding the

- 22 -

materials according to the present invention and the comparative materials. Material No. 2 according to the present invention shown in Tables 1 and 2 and comparative material No. 19 shown in Tables 3 and 4 were hot rolled into steel wires of 5.5 mm in diameter, drawn into a diameter of 1.6 mm, heat-treated at 950°C to form γ grains, and then immersed in a lead bath at 560°C for final patenting, to make steel wires having a pearlite structure. The wires thus obtained were then continuously drawn into a diameter of 0.3 mm, and the fatigue properties of the product wires were compared through Hunter fatigue testing. Table 5 shows results of tensile tests and Hunter fatigue tests of the 0.3-mm diameter wires.

As shown in Table 5, there is no difference of tensile strength between material No. 2 according to the present invention and material No. 19 for comparison. In contrast, with regard to fatigue limit stress based on the Hunter fatigue tests, material No. 2 according to the present invention showed a higher fatigue limit stress than material No. 19 for comparison, as seen in the same table.

25

Table 5

	No.	Tensile test result			Fatigue test result
		Diameter (mm)	Tensile strength (MPa)	Reduction of area (%)	Fatigue limit stress / Tensile strength
Invented material	2	0.302	3425	39.8	0.291
Comparative material	23	0.301	3483	38.6	0.253

INDUSTRIAL APPLICABILITY

A high carbon steel wire according to the present invention can be manufactured at a reduced cost due to

30

- 23 -

reduced use of costly alloys and maintains the same excellent wire-drawability and fatigue resistance after wire drawing as conventionally enjoyed.

- 24 -

CLAIMS

1. A high carbon steel wire excellent in wire
drawability and fatigue resistance after wire drawing,
comprising a steel wire rod containing, in weight, 0.4 to
5 1,2% of C, 0.1 to 1.5% of Si and 0.1 to 1.5% of Mn, a
total oxygen content comprised between 15 and 50 ppm, and
a balance being Fe and unavoidable impurities, and
further containing non-metallic inclusions, a total Al
input amount being controlled in a range between 5.0 and
10 9.5 g/t-molten steel during a compound oxidation process,
and a number of inviscid inclusions being at most 1.5
pieces per mm² in average under a visual field of an
optical microscope; among the inviscid inclusions, a
number of those having a composition as specified below
15 accounts for more than 20% and a total number of those
having a composition falling within a composition in the
group consisting of a composition A and a composition B
specified below accounts for at least 80%; and a
thickness of the inviscid inclusions having a composition
20 falling within composition A specified below is at most
40 μm ;

composition A: containing over 70% of SiO₂,

composition B: containing 25 to 70% of SiO₂, 8 to 30%
of MnO, 40% or less of MgO, 35% or
25 less of Al₂O₃, 25% or less of CaO and
6% or less of TiO₂, and at least 5% of
one in the group consisting of Al₂O₃,
MgO and a combination thereof, and
additionally at least 2% of one in
30 the group consisting of CaO, TiO₂ and
a combination thereof.

- 25 -

2. The high strength carbon steel wire rod excellent in wire drawability and fatigue resistance after wire drawing according to claim 1, wherein the steel wire rod further contains P and S in such amounts that an amount
5 of each thereof does not exceed 0.02%.

3. The high strength carbon steel wire rod excellent in wire drawability and fatigue resistance after wire drawing according to any one of claims 1 and 2, said steel wire rod further containing at least one of 0.05 to
10 1.0% of Cr, 0.05 to 1.0% of Ni, 0.05 to 1.0% of Cu, 0.001 to 0.01% of B, 0.001 to 0.02% of Ti, 0.001 to 0.2% of V, 0.001 to 0.2% of Nb, 0.05 to 1.0% of Mo and 0.1 to 2% of Co.

4. The high strength carbon steel wire excellent in
15 wire drawability and fatigue resistance after wire drawing according to any one of claims 1 to 3, characterized in that the inclusions having said composition B contain at most 5% of other oxides.

5. The high strength carbon steel wire excellent in
20 wire drawability and fatigue resistance after drawing according to any one of claims 1 to 3, wherein the other oxides comprise essentially at least one selected in the group consisting of V, Ba, Zr and Na oxides, a trace amount of other oxides being inevitably included.

25 6. The high strength carbon steel wire rod excellent in wire drawability and fatigue resistance after drawing according to any one of claims 1 to 3, characterized in that the number of the inviscid inclusions having a composition falling within the composition A is at most 1
30 piece/mm² in an observation visual field.