

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
1 March 2007 (01.03.2007)

PCT

(10) International Publication Number
WO 2007/024643 A2

(51) International Patent Classification:

C08J 7/04 (2006.01)

(71) Applicants and

(72) Inventors: KANG, Gary Y., M. [—/US]; 46754 Winema Common, Fremont, CA 94539 (US). LIU, John, Hanan [CN/US]; 637 Kirkland Drive, # 5, Sunnyvale, CA 94087 (US). CHAUG, Yi-Shung [US/US]; 10142 Bilich Place, Cupertino, CA 95014 (US).

(21) International Application Number:

PCT/US2006/032251

(74) Agent: KUNG, Viola, T.; Howrey Llp, 2941 Fairview Park Drive, Box 7, Falls Church, Virginia 22042 (US).

(22) International Filing Date: 15 August 2006 (15.08.2006)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:


60/710,477	22 August 2005 (22.08.2005)	US
60/716,817	13 September 2005 (13.09.2005)	US
60/772,261	10 February 2006 (10.02.2006)	US
11/498,529	2 August 2006 (02.08.2006)	US

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH,

[Continued on next page]

(54) Title: EMBOSSED ASSEMBLY AND METHODS OF PREPARATION



(57) Abstract: The invention is directed to an embossing assembly comprising an embossing sleeve having a three-dimensional pattern formed thereon, an expandable insert; and a drum over which said sleeve and said expandable insert are mounted. The present invention is also directed to a method for preparing an embossing drum or an embossing sleeve. The present invention is further directed to a method for controlling the thickness of a plating material over the surface of a drum or sleeve in an electroplating process.

WO 2007/024643 A2



GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

EMBOSSING ASSEMBLY AND METHODS OF PREPARATION

BACKGROUND OF THE INVENTION

Field of the Invention

5 The invention is directed to an embossing assembly and methods for its preparation.

Description of Related Art

US Patent No. 4,923,572 (hereinafter referred to as the '572 patent) discloses a generally cylindrical image embossing tool that can be used for embossing a material on a web. The method for the manufacture of the image embossing tool involves multiple steps, including (1) placing an embossable material around the surface of a rigid cylinder, followed by coating a thin metal, such as silver, over it, (2) stamping a desired image or pattern onto the embossable layer with a stamper, (3) electroforming to form a nickel electroform on the outer surface of the embossable layer, (4) applying a reinforcement layer over the electroform, (5) removing the rigid cylinder; (6) stripping the embossable layer to form a plating mandrel, (7) forming a second electroform on the interior of the plating mandrel and (8) separating the plating mandrel from the second electroform. According to the '572 patent, multiple copies of the second electroform can be prepared in the same manner and then be placed over a carrier cylinder or a plurality of rollers to form an embossing tool to allow continuous embossing. This embossing tool and its manufacturing process, however, suffer several disadvantages. For example, the process requires the stamping surface of the stamper to have a curvature same as that of the embossable material on the rigid cylinder. This is difficult to accomplish in practice. Secondly, if there are defects on the stamper, the defects will be carried over to copies of the electroforms prepared from the same stamper. Thirdly, it is also difficult to achieve defect-free joint lines between two adjacent stamps.

US Patent 5,327,825 (hereinafter referred to as the '825 patent) discloses a method for making a die through embossing or microembossing. More specifically,

the method involves embossing a pattern or design onto a silver layer coated on a cylindrical surface, via the use of a concave-shaped stamping surface which carries the pattern or design to be imparted onto the silver layer and has a radius matching the radius of the cylindrical surface. This microembossing step is carried out multiple 5 times so that the die prepared from the method has a repeated pattern or design from the concave-shaped stamping surface. This method has disadvantages similar to those of the process of the '572 patent, e.g., difficulty in matching the curvature of the stamping surface and the cylindrical surface; repeated defects resulted from an imperfect stamping surface; and difficulty in achieving defect-free joint lines between 10 adjacent stamps.

US Patent No. 5,156,863 (hereinafter referred to as the '863 patent) discloses a method for manufacturing a continuous embossing belt. The method involves combining a series of "masters" or "copies" in a cluster to provide a desired pattern in a fixture and an electroform strip made of the cluster. The embossing belt is formed 15 after multiple electroforming steps starting from a master cluster fixture. One of the drawbacks of this method is the difficulty to generate individual masters or copies for the cluster with same thickness. Therefore, there will be height differences between adjacent masters or strips that will result in formation of defect lines on the final embossed product. In addition, it is also difficult to avoid damage on the sleeve-type 20 mandrel and the shim during their separation, particularly when a complicated microstructure with a deep 3D profile is involved.

US Patent No. 5,881,444 and 6,006,415 disclose a method for forming print rolls bearing holograms. The hologram pattern is formed by laser etching on the surface of a photoresist coated on a piece of flat glass or metal substrate. Mother 25 shim and subsequent sister shims are electroformed as a flat plate. Then, a sister shim is mounted on the print roll to obtain an embossing tool. The disadvantages of the method include formation of defective joint lines resulted from rolling and welding a flat shim to a cylinder, and the difficulty in the adjustment of concentricity of the sister shim and the print roll. If the shim and roll are not concentric, the embossing 30 pressure will not be uniform which will produce embossed microstructures with poor fidelity.

SUMMARY OF THE INVENTION

The present invention is directed to an embossing assembly and methods for its manufacture.

5 The first aspect of the present invention is directed to a method for preparing an embossing drum or embossing sleeve having a three-dimensional pattern formed on its outer surface. The method, combining photolithography and deposition (e.g., electroplating, electroless plating, physical vapor deposition, chemical vapor deposition or sputtering deposition), produces an embossing drum or embossing
10 sleeve which has no repeating defective spots, no defective joint lines and no separation defects because the three-dimensional pattern is formed directly on the drum or sleeve.

15 The second aspect of the present invention is directed to an embossing sleeve having a three-dimensional pattern formed on its outer surface which embossing sleeve may be used in an embossing assembly.

20 The third aspect of the present invention is directed to an embossing assembly which comprises an embossing sleeve having a three-dimensional pattern formed on its outer surface, an expandable insert and a drum having the embossing sleeve and the expandable insert mounted thereon.

25 The fourth aspect of the present invention is directed to electroplating mechanisms that can provide a uniform deposit thickness on an embossing drum or sleeve.

BRIEF DESCRIPTION OF THE DRAWINGS

25 Figure 1 (A-F) illustrates a method for forming a three-dimensional pattern on an embossing drum or sleeve.

Figure 2 shows an electroplating mechanism that includes a non-conductive thickness uniformer inserted between a cathode and an anode.

30 Figure 3 shows an alternative electroplating mechanism that includes a small-sized anode.

Figure 4 illustrates a chart of ampere x hour vs. position in the L-direction.

Figure 5A shows an array of micro-posts on the outer surface of an embossing drum or sleeve.

Figure 5B shows an array of micro-bars on the outer surface of an embossing drum or sleeve.

5 Figure 5C illustrates a photomask which may be used in a stepwise or continuous exposure process.

Figure 6 shows stepwise exposure of a photosensitive material.

Figures 7A and 7B illustrate alternative light sources for the exposure process.

10 Figure 8A shows an embossing drum or embossing sleeve having micro-posts on its outer surface, where the y-axis of the micro-posts has a projection angle of 45° from the longitudinal axis of the drum or sleeve.

15 Figure 8B shows an embossing drum or embossing sleeve having micro-posts on its outer surface, where the y-axis of the micro-posts has a 0° projection angle from the longitudinal axis of the drum or sleeve.

Figure 8C illustrates angled exposure of a photosensitive material.

Figure 9 shows a photolithography method using a mask material.

Figures 10A and 10B show expandable inserts.

20 Figure 10C illustrate an embossing assembly of the present invention in a three-dimensional view.

DETAILED DESCRIPTION OF THE INVENTION

I. Method for Formation of a Pattern on an Embossing Drum or Sleeve

25 The method is illustrated in Figure 1. The method produces embossing drums or sleeves which have a three-dimensional pattern formed on their outer surface.

30 While only the preparation of an embossing sleeve is demonstrated in Figure 1, it is understood that the method can be used for the preparation of an embossing drum as well. The term "embossing" drum or "embossing" sleeve refers to drums or sleeves which have a three-dimensional pattern on their outer surface. The term "embossing drum" or "embossing sleeve" is used so as to distinguish it from a plain

drum or a plain sleeve, which does not have a three-dimensional pattern on its outer surface. When the embossing drums or embossing sleeves are applied to a surface to be embossed, three-dimensional patterns complementary to the three-dimensional patterns on the outer surface of the embossing drums or embossing sleeves are formed on the embossed surface

5

The embossing drum may be used directly as an embossing tool (also referred to as an embossing assembly). When the embossing sleeve is used for embossing, it is usually mounted on a plain drum to allow rotation of the embossing sleeve.

10 The embossing drum or embossing sleeve (11) is usually formed of a conductive material, such as a metal (e.g., aluminum, copper, zinc, nickel, chromium, iron, titanium, cobalt or the like), an alloy derived from any of the aforementioned metals, or stainless steel. Different materials may be used to form a drum or sleeve. For Example, the center of the drum or sleeve may be formed of
15 steel and a nickel layer is sandwiched between the steel and the outermost layer which may be a copper layer.

20 Alternatively, the embossing drum or embossing sleeve (11) may be formed of a non-conductive material with a conductive coating or a conductive seed layer on its outer surface. Further alternatively, the embossing drum or embossing sleeve (11) may be formed of a non-conductive material without a conductive material on its outer surface.

Before coating a photosensitive material (12) on the outer surface of a drum or sleeve (11), as shown in the step of Figure 1B, precision grinding and polishing may be used to ensure smoothness of the outer surface of the drum or sleeve.

25 In the step of Figure 1B, a photosensitive material (12), e.g., a photoresist, is coated on the outer surface of the drum or sleeve (11). The photosensitive material may be of a positive tone, negative tone or dual tone. The photosensitive material may also be a chemically amplified photoresist. The coating may be carried out using dip, spray, drain or ring coating. The thickness of the photosensitive material
30 is preferably greater than the depth or height of the three-dimensional pattern to be formed. After drying and/or baking, the photosensitive material is subjected to

exposure as shown in Figure 1C. Alternatively, the photosensitive material (12) can be a dry film photoresist (which is usually commercially available) that is laminated onto the outer surface of the drum or sleeve (11).

In the step of Figure 1C, a suitable light source (13), e.g., IR, UV, e-beam or 5 laser, is used to expose the photosensitive material (12) coated on the drum or sleeve (11). A photomask (14) is optionally used to define the three-dimensional pattern to be formed on the photosensitive material. Depending on the pattern, the exposure can be step-by-step, continuous or a combination thereof, the details of which are given below.

10 After exposure, the photosensitive material (12) may be subjected to post-exposure treatment, e.g., baking, before development. Depending on the tone of the photosensitive material, either exposed or un-exposed areas will be removed by using a developer. After development, the drum or sleeve with a patterned photosensitive material (15) on its outer surface (as shown in Figure 1D) may be 15 subjected to baking or blanket exposure before deposition (e.g., electroplating, electroless plating, physical vapor deposition, chemical vapor deposition or sputtering deposition).

20 A variety of metals or alloys (e.g., nickel, cobalt, chrome, copper, zinc, iron, tin, silver, gold or an alloy derived from any of the aforementioned metals) can be electroplated and/or electroless plated onto the drum or sleeve. The plating material (16) is deposited on the outer surface of the drum or sleeve in areas that are not 25 covered by the patterned photosensitive material. The deposit thickness is preferably less than that of the photosensitive material, as shown in Figure 1E. The thickness variation of the deposit over the whole drum or sleeve area can be controlled to be less than 1%, by adjusting plating conditions, e.g., the distance between the anode and the cathode (i.e., drum or sleeve) if electroplating is used, the rotation speed of the drum or sleeve and/or circulation of the plating solution.

30 Alternatively, in the case of using electroplating to deposit the plating material (16), the thickness variation of the deposit over the entire surface of the drum or sleeve may be controlled by inserting a non-conductive thickness uniformer (20) between the cathode (i.e., the drum or sleeve) (21) and the anode (22), as shown in

Figure 2. The uniformer (20) may be of a flat or curved layer or of a circular shape (i.e., in the shape of a sleeve), depending on the layout of the cathode and the anode. The uniformer has a narrow opening or openings (23). During the electroplating step, the uniformer moves in the longitudinal direction of the drum or sleeve back and forth while the drum or sleeve rotates. Since the uniformer is formed of a non-conductive material, e.g., PVC (polyvinyl chloride), only the areas of the drum or sleeve that are directly exposed to the anode almost vertically through the openings (23) are electroplated. In other words, the outer surface areas of the drum or sleeve that are not covered by the patterned photosensitive material (15 in Figure 1) continuously take turns to be electroplated. By using such a uniformer (20), the current distribution over the entire surface of the drum or sleeve is homogenized, thus ensuring a uniform deposit of the plating material.

Further alternatively, an anode (30) of a relatively small size as shown in Figure 3 may be used to homogenize the deposit thickness. The anode is covered with a non-conductive material (31) except the side facing the cathode (i.e., the drum or sleeve) (32). Alternatively, only two sides of the anode are covered with the non-conductive material and in this case the side facing the cathode and its opposite side are not covered by the non-conductive material. During the electroplating step, the anode moves together with the non-conductive material in the longitudinal direction of the drum or sleeve back and forth while the drum or sleeve rotates. The anode may have a flat or curved side facing the cathode.

Figure 4 shows a monitoring chart the data of which are received from an ampere-hour meter and an anode position gauge or transducer during electroplating. For the electroplating process, the value of the ampere-hour is proportional to the deposit thickness. The monitoring chart is continuously updated during electroplating; therefore the thickness uniformity over the entire drum or sleeve may be monitored *in situ* and adjusted, if necessary. For example, Figure 4 indicates that the plated deposit in zone1 and zone3 is thicker than that of zone2. When such a situation is detected, the uniformer (20 in Figure 2) or the anode (30 in Figure 3) used in the two processes may be adjusted to move faster in zone1 and zone3 and/or to move slower in zone2 to homogenize the deposit thickness over the entire

drum or sleeve.

It is understood that the plating can be carried out on a drum or sleeve that is made of a conductive material or a non-conductive material with a conductive coating or a conductive seed layer on its outer surface. For a non-conductive drum or sleeve, the three dimensional pattern may be prepared by a method combining photolithography and etching, the details of which are given below.

After plating, the patterned photosensitive material (15) can be stripped by a stripper (e.g., an organic solvent or aqueous solution).

A precision polishing may be optionally employed to ensure acceptable thickness variation and degree of roughness of the deposit over the entire drum or sleeve.

Figure 1F shows a cross-section view of an embossing drum or embossing sleeve with a three-dimensional pattern formed thereon. If the plated material is relatively soft or susceptible to humidity, e.g., copper or zinc, a relatively wearable or inert layer, e.g., nickel or chrome, may be subsequently deposited. The deposition of the second layer may be carried out by electroplating, electroless plating, physical vapor deposition, chemical vapor deposition or sputtering deposition, over the entire outer surface of the drum or sleeve.

Alternatively, if the height (or thickness) of the three-dimensional pattern on the outer surface of an embossing drum or embossing sleeve is relative small, e.g., less than 1 microns, the plating step of Figure 1E may be replaced by physical vapor deposition, chemical vapor deposition or sputtering deposition. The deposition is performed on the entire outer surface of the drum or sleeve. Since the deposit is so thin, the material deposited on top of the photosensitive material may be removed together with the photosensitive material in the stripping step.

Further alternatively, the embossing drum or embossing sleeve may be prepared by a method combining photolithography and etching instead of photolithography and deposition. After coating, exposing and developing (i.e., removal of selective areas of the photosensitive material) of a photosensitive material, an etching step is subsequently performed in areas not covered by the photosensitive material. The depth of etching may be controlled by the

concentration of the etchant used, if a liquid type etchant is used (such as a ferric chloride solution to etch a copper drum or sleeve) or by etching flux intensity, if dry etching (chemical plasma etching, synergistic reactive ion etching or physical ion-beam etching) is used. The depth of etching may also be controlled by temperature 5 and etching time. Alternatively, the depth of etching may be controlled to be uniform by using a selective etching method. For example, in such a method, a nickel layer is plated on the sleeve or drum first and then a copper layer with a desired thickness is plated on the top of the nickel layer. Since nickel will not be attacked by any of the copper etchants, e.g., ferric chloride, the etching depth can be well controlled. After 10 the etching step, the remaining photosensitive material is removed by using a stripper, and subsequently a relatively wearable or inert layer, e.g., nickel or chrome, may be optionally deposited, as described above, over the entire outer surface of the drum or sleeve.

In practice, a three-dimensional pattern on the embossing drum or embossing 15 sleeve prepared from the process as described above involving an additive (i.e., electroplating, electroless plating, physical vapor deposition, chemical vapor deposition or sputtering deposition) step would be structurally complementary to a three-dimensional pattern prepared from the process as described above involving a subtractive (i.e., etching) step.

As mentioned above, the exposure step of Figure 1C may be carried out step-by-step, continuous or a combination thereof. To simplify the drawings, the curvature of the outer surface of the drum or sleeve is not shown in Figures 5A and 20 5B. Figure 5A shows an array of micro-posts on the embossing drum or embossing sleeve. To fabricate the micro-posts on the embossing drum or embossing sleeve, a photomask as shown in Figure 5C may be used to stepwise expose the 25 photosensitive material coated on the outer surface of the drum or sleeve. There are a number of ways for stepwise exposure.

One of the methods involves the use of a pulse type light source. In this 30 method as shown in Figure 6, the photomask (60) remains stationary throughout the process. The drum or sleeve (not shown), however, rotates in a stop-and-go fashion. The exposure of the photosensitive material (61, curvature not shown)

coated on the outer surface of the drum or sleeve, through the photomask occurs when the drum or sleeve is in the "stop" mode and the pulse type light source is on. As a result, the areas (1a)-(1d) on the photosensitive material are exposed corresponding to the openings (a)-(d) of the photomask. The drum or sleeve is then 5 rotated to allow exposure of (2a)-(2d). However, during the interval when the drum or sleeve is moving (i.e., rotating) from the position where the openings (a)-(d) of the photomask are aligned with column 1 (i.e., (1a)-(1d)) to the position where the same openings of the photomask are aligned with column 2 (i.e., (2a)-(2d)), the pulse light source is off. Following the cycle of stop-and-go of the drum or sleeve in conjunction 10 with the on and off states of the pulse light source, the photosensitive material is stepwise exposed.

If the light source can not cover the openings (a)-(d) of the photomask at the same time, scanning of the light source may be implemented for exposure while the pulse type light source is on.

15 Alternatively, a shutter may also be used to control the on and off states of the light source.

If the pattern on the drum or sleeve is parallel micro-bars as shown in Figure 5B, the same photomask of Figure 5C may be used for exposure. However, in this case, the exposure is continuous while the embossing drum or embossing sleeve is 20 rotating.

25 While micro-posts and micro-bars are shown in the figures, it is understood that the three-dimensional pattern on the embossing drum or embossing sleeve may be of any shapes or sizes. A wide variety of sizes may be achieved for the elements (such as the micro-posts) on the three-dimensional pattern, ranging from sub-microns to much larger.

In addition to the methods mentioned above, there are several combinations 30 of light source and photomask which may be used to more precisely control the dimension of the three-dimensional pattern. If a collimated light source (73A) (e.g., laser) is used for exposure as shown in Figure 7A, an opaque patterned thin layer (75) (e.g., chrome) on one side of a transparent substrate (74) (e.g., glass) may be employed. If the shape and spot size of the collimated light source (73A) can be

controlled by the combination of mirrors and lenses, there will be no need to use a photomask for exposure of the photosensitive material (72) coated on the drum or sleeve (71). If the light source (73B) is divergent, the transparent substrate (74) may be sandwiched between two opaque patterned thin layers (75A and 75B) to collimate 5 the impinging light as shown in Figure 7B. The photomask may also be made of a single opaque layer with suitable openings to allow the light to go through.

When the three-dimensional pattern is micro-posts, it is also possible to form the micro-posts on the outer surface of a drum or sleeve by "angled" exposure. In the case of micro-posts prepared by "angled exposure", the y axis of the micro-posts 10 has a projection angle from the longitudinal axis (L) of the drum or sleeve. The projection angle (θ) is an oblique angle, preferably about 10° to about 80°, more preferably about 30° to about 60° and most preferably about 45°.

Figure 8A shows micro-posts having a projection angle of 45°. In contrast, Figure 8B shows micro-posts having a projection angle of 0° (i.e., the y axis of the 15 micro-posts is parallel to the longitudinal axis of the drum or sleeve).

The angled exposure is illustrated in Figure 8C. In the figure, a continuous spiral line (81) is formed on a photosensitive material coated on the outer surface of a drum or sleeve via exposure of the photosensitive material to a light source (80). The photosensitive material is preferably of a negative tone. When a photosensitive 20 material of a negative tone is used, the subsequent step of developing the photosensitive material will remove the areas which are not covered by the spiral line. In other words, the area of the spiral line corresponds to the groove between the micro-posts eventually formed. Therefore, the width of the spiral line (81) should be substantially equal to the width of the grooves between the micro-posts.

25 In contrast to the formation of micro-posts having protruding elements by "angled exposure", it is also possible to form micro-cavities by using a photosensitive material of a positive tone. When a photosensitive material of a positive tone is used, the step of developing the photosensitive material will remove the areas which are covered by the spiral lines. In other words, the areas of the spiral lines 30 correspond to the partition walls between the cavities eventually formed on the embossing drum or embossing sleeve.

It should be noted that the steps of Figures 1E and 1F may be modified. In some cases, the thickness of the plating material (16) may exceed the height of the photosensitive material (15). In such a case, the top area of the plating material beyond the photosensitive material may be wider than the bottom area because in 5 the top area there is no photosensitive material to limit the width of the plating material. A structure prepared from such a method is useful for other applications, such as cell wells on a gravure cylinder to transfer printing ink to a substrate.

As an example, the continuous spiral line (81) in Figure 8C has a 45° projection angle from the longitudinal axis (L) of the drum or sleeve. In one of the 10 methods for forming the spiral line, the light source (80) steadily moves in the direction of the longitudinal axis (either left to right or right to left) of the drum or sleeve and the drum or sleeve simultaneously rotates (either clockwise or counter clockwise). In an alternative method, the exposure can be accomplished by moving the drum or sleeve in the direction of the longitudinal axis of the drum or sleeve and 15 simultaneously rotating the drum or sleeve while the light source (80) is kept stationary. In a further alternative method, the light source may be rotating around the sleeve or drum while the drum or sleeve moves in the direction of the longitudinal axis.

For the formation of the second or subsequent spiral line (81a) in the same 20 direction, the starting point of exposure is shifted one pitch distance away from the previous spiral line (81) already exposed. After all the spiral lines in one direction are exposed, the spiral lines (82 and 82a) in an opposite direction (minus 45° from the longitudinal axis of the drum or sleeve) are formed by exposure in a manner similar to the process for the exposure of lines 81 and 81a, except that the light 25 source or the drum or sleeve moves in an opposite direction during exposure. The lines 82 and 82a are perpendicular to the lines 81 and 81a.

As an example, the spiral lines 81 and 81a may be exposed by moving the light source in one direction, left to right, at a certain speed and simultaneously 30 rotating the drum or sleeve, counter clockwise, at a certain speed and the spiral lines 82 and 82a may then be exposed by changing the moving direction of the light source (from "left to right" to "right to left"); but maintaining the same rotation

direction of the drum or sleeve (counter clockwise). Alternatively, the spiral lines 82 and 82a may be exposed by changing the rotation direction of the drum or sleeve (from counter clockwise to clockwise); but maintaining the moving direction of the light source (left to right).

5 In the above process, if the spot size of light source is smaller than the width of the grooves between adjacent micro-posts, the spiral lines may be exposed by several overlapping light scans. If the spot size of light source is larger than the width of the grooves, a photomask may be needed to confine the exposure.

10 In any case, if a photomask is used, the movement of the photomask must be synchronized with the movement of the light source.

An embossing drum or embossing sleeve having micro-posts prepared by angled exposure has the advantage that the angle assists the flow of the embossable composition used in the embossing process, thus eliminating trapped air on cross web directions.

15 In addition to using a single layer of a photosensitive material as mentioned above, an additional layer of a mask material (90) may be placed over the photosensitive material (91), as shown in Figure 9A, by using ring coating, drain coating, spray coating, physical vapor deposition, chemical vapor deposition or sputtering deposition. The photosensitive material (91) is coated over the surface 20 (92) of the drum or sleeve (curvature not shown). The mask material may also be a photosensitive material that, on the one hand, can be imaged by using a light source with a wavelength different from that needed for the exposure of the photosensitive material (91), and on the other hand, has a high optical density at the wavelength range used to expose the photosensitive material (91). After exposing and 25 developing of the mask material, the patterned mask material (90a) serves as a photomask to expose the photosensitive material (91) underneath. A silver-halide coating and an i-line photoresist may be used together as the mask material (90) and the photosensitive material (91), respectively. The silver-halide coating can be imaged using a laser diode with a wavelength of 670 nm, and the i-line photoresist 30 can only be imaged using UV light with a wavelength of 365 nm. After exposure and development, the silver-halide coating is transferred to a patterned metallic silver

layer that is opaque and can be used as a photomask for the exposure of the i-line photoresist underneath. Alternatively, the mask material may be a laser ablative material (90 in Figure 9A) that includes a polymeric matrix having a carbon pigment and an ultraviolet absorbing dye. The patterned ablative material (90a) is used as 5 a photomask for the exposure of the photosensitive material (91) underneath. The examples of possible materials useful for the process are disclosed in US patent 6,828,067, the content of which is incorporated herein by reference in its entirety. After the development of the photosensitive material, a plating material (93) is 10 deposited on the outer surface of the drum or sleeve in areas that are not covered by the patterned photosensitive material (91a).

In some instances, a barrier layer may be coated between the photosensitive material (91) and the mask material (90). The purpose of the barrier layer is to avoid the possible attack on the photosensitive material (91) by the solvent in the mask material (90) during the coating process. For instance, a layer of PVOH (polyvinyl 15 alcohol) that is water-soluble may be used as a barrier layer to prevent the attack of the mask material on the photosensitive material, because the solvent in the mask material solution is not miscible with PVOH. In this case, the solvent in the mask material cannot penetrate the barrier layer to attack the photosensitive material.

20 **II. Embossing Sleeve**

When the embossing sleeve is used for embossing, it is usually mounted on a plain drum to allow rotation of the sleeve. Therefore the embossing sleeve preferably has an inside diameter which is slightly larger than the outside diameter of the plain drum in order to allow the sleeve to be mounted on the drum.

25 The fact that the 3-dimensional pattern is formed on an embossing sleeve has many advantages over having the pattern directly formed on an embossing drum. First of all, the sleeve is much lighter than a drum, only about one tenth or less of the weight of a drum; therefore it is much easier to handle. Secondly, there 30 may be electrical heating coil or fluidic heating tube inside an embossing drum in order to provide a suitable high temperature to the surface of the embossing drum when it is used for embossing. If the three-dimensional pattern is formed directly on

the outer surface of the embossing drum, the electrical heating coil or fluidic heating tube would need to be protected during preparation of the embossing drum.

Another advantage of using an embossing sleeve is that different sleeves may be fitted to be used on the same plain drum, which effectively reduces the number of drums required, thus saving manufacturing costs.

5 The thickness of the embossing sleeve preferably may range from 1mm to 100 mm, more preferably from 3mm to 50 mm.

When an embossing sleeve is used for embossing, the sleeve must be snugly fitted over the plain drum. The tight fitting may be accomplished by pressure fit 10 involving different materials having different thermal expansion coefficients. Alternatively, the tight fitting may be accomplished by mechanical taper fit.

III. Embossing Assembly

An expandable insert may be used to ensure tight fitting and concentricity 15 between an embossing sleeve and a drum. Figures 10A and 10B illustrate such an expandable insert (100). The insert is a layer of a circular shape which may have one or multiple gaps (101) as shown in the figures. At both ends of the insert, there are tightening means (102), such as screws, to secure the insert over the drum. By 20 tightening or loosening the screws, the diameter of the insert may be adjusted to ensure tight fitting of the embossing sleeve over the insert and simultaneously the concentricity of the embossing sleeve over the drum. For best results, there are at least 3 screws spreading around the circle, preferably having an equal distance between each other.

The insert is formed of a material, such as a metal (e.g., aluminum, copper, 25 zinc, nickel, iron, titanium, cobalt or the like), an alloy or metal oxide derived from the aforementioned metals or stainless steel. If the insert material is relatively susceptible to humidity or chemical, e.g., copper or iron, a relatively inert layer may be employed to protect it. The deposition of the inert material may be carried out by electroplating, electroless plating, physical vapor deposition, chemical vapor 30 deposition or sputtering deposition, over the entire surface of the insert.

Alternatively, the insert may be formed of a plastic material, e.g., PVC (polyvinyl

chloride) or ABS (acrylonitrile butadiene styrene).

The thickness of the expandable insert preferably may range from 1mm to 100 mm, more preferably from 3mm to 50 mm.

5 The insert (100) is placed between a plain drum (103) and an embossing sleeve (104) as shown in Figure 10C. The insert (100) and the sleeve (104) may be sequentially mounted onto the drum (103). As also shown in Figure 10C, the embossing sleeve is shorter than the insert so that the sleeve will not cover the areas on the insert where the screws (102) are present.

10 The expansion of the insert is controlled by the adjustment of screws (102), preferably with a torque wrench, to ensure proper tightness of the screws. When the screws are tightened (i.e., screwed down), the insert will expand to cause more contact between the inner surface of the sleeve and the outer surface of the insert, thus tightly holding the sleeve in position. The tightness of all of screws must be carefully oriented so that the concentricity of the embossing sleeve over the plain 15 drum (103) may be simultaneously maintained. As explained earlier, the concentricity of the embossing sleeve over the plain drum is critically important to the quality of the embossed microstructures prepared from the embossing assembly.

20 Although the foregoing invention has been described in some detail for purposes of clarity of understanding, it will be apparent that certain changes and modifications may be practiced within the scope of the appended claims. It should be noted that there are many alternative ways of implementing both the process and apparatus of the present invention. Accordingly, the present embodiments are to be considered as illustrative and not restrictive, and the invention is not to be limited to the details given herein, but may be modified within the scope and equivalents of the 25 appended claims.

WHAT IS CLAIMED IS:

1. An embossing assembly, which comprises:
 - a) an embossing sleeve having a three-dimensional pattern formed thereon;
 - b) an expandable insert; and
 - c) a drum over which said sleeve and said expandable insert are mounted.

10 2. The embossing assembly of Claim 1 wherein said embossing sleeve is prepared by a method of photolithography in combination with deposition.

15 3. The embossing assembly of Claim 1 wherein said embossing sleeve is prepared by a method of photolithography in combination with etching.

20 4. The embossing assembly of Claim 2 wherein said deposition is electroplating, electroless plating, physical vapor deposition, chemical deposition or sputtering deposition.

25 5. The embossing assembly of Claim 2 wherein said embossing sleeve is prepared by stepwise exposure or continuous exposure.

6. The embossing assembly of Claim 1 wherein said three-dimensional pattern has micro-posts.

25 7. The embossing assembly of Claim 6 wherein the y-axis of said micro-posts has a projection angle from the longitudinal axis of the embossing sleeve.

30 8. The embossing assembly of Claim 7 wherein the projection angle is about 0°.

9. The embossing assembly of Claim 7 wherein the projection angle is about 10° to about 80°.

10. The embossing assembly of Claim 7 wherein the projection angle is
5 about 45°.

11. The embossing assembly of Claim 1 wherein said expandable insert has at least one gap.

10 12. The embossing assembly of Claim 11 wherein said expandable insert has multiple tightening means.

13. A method for preparing an embossing drum or an embossing sleeve, which method comprises:

15 a) coating or laminating a photosensitive material over the outer surface of a drum or sleeve;

b) selectively exposing the photosensitive material;

c) removing the photosensitive material either in areas that are exposed or in areas that are not exposed;

20 d) depositing a metal or alloy onto the outer surface of the drum or sleeve where there is no photosensitive material present; and

e) removing the photosensitive material remaining between the metal or alloy.

25 14. The method of Claim 13 wherein said photosensitive material in step (a) is of a positive tone, negative tone or dual tone.

15. The method of Claim 13 wherein said photosensitive material is a chemically amplified photoresist.

30

16. The method of Claim 13 wherein said exposing of step (b) is carried

out stepwise or continuous.

17. The method of Claim 13 wherein said exposing of step (b) is carried out by IR, UV, e-beam or laser.

5

18. The method of Claim 13 wherein said metal or alloy is nickel, cobalt, chrome, copper, zinc, iron, tin, silver, gold or an alloy derived therefrom.

19. The method of Claim 13 wherein step (e) is carried out by a stripper.

10

20. The method of Claim 13 wherein step (b) is carried out by coating a mask material over the photosensitive material, patterning the mask material to form a patterned mask material and exposing the photosensitive material through the patterned mask material.

15

21. The method of Claim 20 wherein said patterning is carried out by photolithography or ablation.

20

22. The method of Claim 20 further comprising coating a barrier layer between the mask material and the photosensitive material.

25

23. A method for controlling the thickness of a plating material over the surface of a drum or sleeve in an electroplating process, which method comprises:

- a) inserting a non-conductive thickness uniformer between the drum or sleeve and anode(s) wherein said uniformer has at least one opening;
- b) moving the uniformer in the longitudinal direction of the drum or sleeve and simultaneously rotating the drum or sleeve; and
- c) electroplating only the areas of the drum or sleeve that are directly exposed to the anode(s) through the opening(s) of the uniformer.

30

24. A method for controlling the thickness of a plating material over the

surface of a drum or sleeve in an electroplating process, which method comprises:

- a) providing at least an anode each of which is covered with a non-conductive material except the side facing the cathode or the side facing the cathode and its opposite side; and
- 5 b) moving the anode(s) in the longitudinal direction of the drum or sleeve back and forth and simultaneously rotating the drum or sleeve.




Figure 1




Figure 2






Figure 3




Position in L-direction


Figure 4



5A



5B



5C

Figure 5





Figure 6




Figure 7A




Figure 7B




Figure 8A




Figure 8B




Figure 8C




Figure 9




Figure 10A




Figure 10B




Figure 10C