



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁵ : C10G 11/05, B01J 37/04</p>	<p>A1</p>	<p>(11) International Publication Number: WO 94/13755</p> <p>(43) International Publication Date: 23 June 1994 (23.06.94)</p>
<p>(21) International Application Number: PCT/US93/11812</p> <p>(22) International Filing Date: 7 December 1993 (07.12.93)</p> <p>(30) Priority Data: 07/987,519 8 December 1992 (08.12.92) US</p> <p>(71) Applicant: ENGELHARD CORPORATION [US/US]; 101 Wood Avenue, Iselin, NJ 08830 (US).</p> <p>(72) Inventors: DEEBA, Michel; 2501 North Oaks Boulevard, North Brunswick, NJ 08902 (US). MACAOAY, John, M.; 3009 Fedor Avenue, Linden, NJ 07036 (US). SUTCH, Paul, R.; 220 South Liberty Street, Milledgeville, GA 31061 (US). VON BALLMOOS, Roland; 52 Livingston Drive, Belle Mead, NJ 08502 (US).</p> <p>(74) Agents: MILLER, Stephen, I. et al.; Engelhard Corporation, 101 Wood Avenue, Iselin, NJ 08830 (US).</p>	<p>(81) Designated States: AU, BR, CA, JP, KR, RU, UA, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: COMPOSITION FOR PASSIVATING VANADIUM IN CATALYTIC CRACKING AND PREPARATION THEREOF</p>		
<p>(57) Abstract</p> <p>Disclosed is a vanadium trap for use in FCC which comprises a major amount of calcined kaolin clay, free magnesium oxide and an <i>in situ</i> formed magnesium silicate cement binder. Also disclosed are procedures for the preparation of the trap by forming a slurry in water of hydrous kaolin clay, magnesium oxide or magnesium hydroxide and sodium silicate, aging the slurry to form magnesium silicate <i>in situ</i>, optionally adding additional kaolin, colloidal silica or both, spray drying, and calcining the resulting spray dried microspheres without forming appreciable amounts of crystalline magnesium silicates or crystalline magnesium aluminates.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	MN	Mongolia	US	United States of America
FI	Finland			UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

COMPOSITION FOR PASSIVATING VANADIUM IN
CATALYTIC CRACKING AND PREPARATION THEREOF

BACKGROUND OF THE INVENTION

5 This invention relates to magnesium oxide based
compositions in the form of attrition-resistant fluidizable
microspheres which are circulated with microspheres of
zeolitic fluidizable cracking catalysts. The magnesium
oxide based particles minimize or prevent poisoning and
10 deactivation of the zeolitic cracking catalysts by vanadium
contained in oil feedstock used in the catalytic cracking
process. The invention relates also to processes for
producing such compositions by spray drying a slurry
containing magnesium oxide, kaolin clay and in situ formed
15 inorganic cement.

Poisoning and deactivation of catalyst in FCC (fluid
catalytic cracking) by vanadium in the oil feedstock is one
of the most prominent problems faced by operators of oil
20 refineries. Patents including disclosure of the use of
alkaline earth compounds, including magnesium oxide, to
mitigate the effects of vanadium include US 4,465,779, US
4,549,548, US 4,944,865, WO 82/00105, GB 218314A, EP-A-
020151 and EP-A-0189267. In some of these references, the
25 magnesium oxide is contained in discrete particles,
separate from the particles of zeolite cracking catalyst.
EP-A-270,211 discloses discrete particles in which
magnesium is present as a crystalline magnesium silicate,
preferably fosterite. The material containing crystalline
30 magnesium silicate may be produced by spray during a slurry
containing magnesium carbonate and kaolin clay, followed by
high temperature calcination to react the magnesium with
silica in the clay, forming the crystalline magnesium
silicate. Other disclosures of crystalline magnesium
35 containing silicates (clays such as sepiolite) appear in US
4,549,548 supra.

Efforts to develop products and processing modifications to mitigate vanadium passivation are by no means limited to the use of alkaline earth material. To
5 the best of our knowledge, however, no magnesium based additive has enjoyed widespread commercial success. Certain perovskites such as barium titanate are employed commercially. Perovskites are expensive. Perovskites are not considered to be very effective in reducing SOx
10 emissions in regenerator flue gas. Alkaline earth material, especially magnesium oxide, offers the additional benefit of reducing SOx in regenerator flue gas from cracking units. See, for example, WO 82/00105GB (supra).

15 There is strong motivation to utilize the inherent vanadium binding and SOx capturing capacity of magnesium oxide in FCC operations utilizing feedstocks having a high content of vanadium. References cited above give some indication of past efforts to produce magnesium oxide based
20 vanadium passivating particles adapted for co-circulating with zeolite cracking catalysts. Commercial success has not measured up to the motivation. One primary challenge was to provide a metals passivator in a physical form of particles sufficiently attrition-resistant for use in FCC,
25 while maintaining the magnesium in most reactive form (oxide). This problem was addressed in EP-A-270,211. The solution proposed in that patent application resulted in particles that were attrition-resistant in fresh form but lost hardness when subjected to steaming in testing.

30

Magnesium oxide without a binder/matrix is unsuitable for use in an FCC unit when it must be circulated through the reactor and regenerator of an FCC unit along with cracking catalyst particles. This is because particles of
35 magnesium oxide readily break down into a powder when subjected to attritive forces. Note that in one of the earliest proposals to use magnesia in an FCC unit to combat

SOx (US 3,699,037), the material was circulated in the regenerator to bind SOx. The magnesia attrited during such use, eventually to be withdrawn from the regenerator with flue gas without circulating in the cracker, as would be 5 required to achieve vanadium passivation. Because of the friable nature of magnesium oxide particles, the material did not circulate with the catalyst during the FCC cycle.

Numerous patents, including several of those cited 10 above, disclose formulations based on composites of magnesia with kaolin clay. Kaolin clay is a widely used matrix component for cracking catalyst because it is inexpensive and has potential binding properties. Also, it is relatively catalytically inert in calcined form and is 15 a prime candidate as a matrix/diluent for a vanadium passivator based on magnesia, wherein catalytic activity is not desired. An advantage of using kaolin clay as a matrix/diluent is that it can readily be formed into substantially catalytically inert particles by forming a 20 dispersed concentrated fluid slurry to form microspheres, followed by spray drying. When dried, especially when calcined, kaolin also serves as a binding function.

Several of the references noted above provide examples 25 of MgO/kaolin microspheres prepared by means including spray drying, but they do not disclose the composition of the feed slurry to the spray dryer. They do not provide information about attrition-resistance. There is no indication that the inventors were concerned with 30 attrition-resistance or steam stability of the products. In the case of WO 82/00105GH, the matrix was a mixture of kaolin and silica-alumina gel, a conventional matrix for zeolite crystals in an active cracking catalyst. Silica-alumina is a material known to possess catalytic activity.

EP-A-270211, supra, refers to difficulties encountered in achieving attrition-resistance by mixing magnesia with kaolin clay, spray drying and calcination.

5 Those skilled in the art of handling clays are aware that introduction of magnesium ions into clay slurries causes the slurry to flocculate and thicken. This has been used with benefit in the formulation of various clay-based drilling mud. However, flocculation and thickening causes 10 formidable problems in producing magnesia/kaolin clay products useful for FCC wherein particles of appreciable magnesium oxide content are produced in spray dryers. It is a simple matter to provide a dispersed kaolin slurry that is sufficiently fluid at a high enough concentration 15 (e.g., 50% solids) to produce coherent microspheres. However, if kaolin is spray dried at low solids, e.g., 10%, the microspheres will fall apart before they can be hardened by calcination. If magnesium is added to such a high solids fluid dispersed slurry of kaolin in more than 20 a trace amount, the slurry will flocculate and thicken. If enough magnesium ions are introduced, a solid gel forms and the slurry cannot be formed into microspheres by spray drying using known technology. Addition of magnesium oxide to a kaolin slurry in amount sufficient to produce spray 25 dried particles having a sufficiently high MgO content for effective vanadium passivation will result in a slurry that cannot be spray dried in continuous commercial spray drying equipment. This problem plagued the inventors of the subject patent application in their pursuit of developing 30 attrition-resistance spray dried microspheres containing magnesia with a clay diluent which meet the criteria for a good vanadium trap: attrition-resistance; high capacity for vanadium trapping; good vanadium passivation; and very high trapping efficiency (i.e., fast vanadium uptake).

35

To produce such particles it was necessary to overcome the difficulty caused by flocculation of a dispersed slurry

of kaolin clay by the incorporation magnesium ions, resulting in thickening or even gelation of the slurry and, ultimately, the inability to formulate a slurry of sufficiently high solids content to produce attrition-resistant spray dried microspheres. The need to control flocculation and thickening to achieve hardness was counter-balanced by the need to product microspheres that were sufficiently porous to function as an effective magnesium passivator.

10

SUMMARY OF THE INVENTION

Novel vanadium passivation particles of the present invention are in the form of spray dried attrition-resistant microspheres composed of a minor amount of magnesium oxide, a major amount of calcined kaolin clay admixed therewith and a small amount, relative to the magnesium of oxide, of an in situ formed amorphous magnesium silicate cement. The particles have a low surface area and have minimal cracking activity.

Vanadium traps of the invention can be used with commercially available zeolitic catalysts in FCC units where vanadium levels are high, thereby avoiding rapid catalyst deactivation. These traps permit refiners to operate at lower catalyst make-up rates and will also reduce coke and gas associated with catalytic dehydrogenation by vanadium. The vanadium capacity of traps of the present invention is very high; the sulfate tolerance is excellent, is evidenced by the fact that essentially no sulfur remains on equilibrium vanadium traps of this invention. In the near future, many more refiners will be using residual feeds which will increase the vanadium concentration on the catalyst. The necessity to use efficient vanadium traps will therefore increase. Frequently feedstock with a high vanadium concentration also contain high levels of sulfur. The SO_x binding

capability of products of the invention is an added benefit.

Products of this invention are obtained by processing
5 steps comprising mixing magnesium oxide or magnesium hydroxide, hydrous (uncalcined) kaolin clay and sodium silicate with water to form a dispersed fluid slurry which is aged. During aging, the basic magnesium compound reacts with sodium silicate to produce magnesium silicate which
10 functions as a binder in the finished product. Optionally colloidal silica, additional kaolin clay or both are added to the aged slurry. The proportion of magnesium oxide relative to sodium silicate is controlled to assure that only a small amount of magnesium silicate is formed,
15 leaving the bulk of the magnesium oxide unreacted and available in the product to passivate metals and, if desired, to bind SOx. The slurry is spray dried to form microspheres which are calcined under conditions sufficiently mild to dehydrate the kaolin while preventing
20 or minimizing the formation of crystalline magnesium silicate and/or magnesium aluminates.

One key manufacturing parameter which the inventors believe is crucial is the avoidance of large amounts of
25 magnesium silicate formation in such a way that only marginal reaction between the two components can take place. Another key parameter is a moderate calcination temperature which avoids the formation of significant amounts of crystalline magnesium silicate and aluminate,
30 thereby preserving the bulk of the MgO throughout the process. A significant amount of crystalline magnesium silicate or aluminate would be a quantity such that more than about half of the magnesium oxide is consumed in forming that crystalline material. Still another key
35 parameter is assuring that the magnesium oxide is well dispersed from the time it is mixed with other ingredients to form a slurry until spray drying takes place. Thus, in

order to produce these microspheres in a form sufficiently attrition-resistant for use in FCC involves careful selection of starting materials (MgO, clay and binder) and making a careful selection of slurry preparation procedures
5 prior to spray drying.

In one presently preferred embodiment of the invention, the vanadium passivator particles are obtained by spray drying a concentrated (high solids) slurry of
10 dispersed kaolin clay, dispersed magnesium oxide or magnesium hydroxide, or mixtures thereof, sodium silicate, and, optionally colloidal silica, wherein the kaolin clay is introduced in stages. In the initial stage, only a portion of the total kaolin clay included in the spray
15 dryer feed slurry is mixed with magnesium oxide or hydroxide to form a low solids slurry, e.g., 30% solids. This slurry is permitted to age and consumes only a small amount of the added magnesium oxide or hydroxide. This results in the formation of a magnesium silicate cement by
20 reaction of a small portion of the magnesia content of the slurry with silica introduced as sodium silicate. Solids are sufficiently low in this slurry so that it is fluid in spite of the fact that it contains both kaolin clay and magnesium oxide. The remaining kaolin is injected into the
25 first stage slurry using high shear static mixing (as by an inline mixer) to form a fluid high solids slurry (e.g., at least 50% solids). This slurry is immediately spray dried. The spray dried microspheres are then calcined at a time and temperature sufficient to dehydrate the kaolin and
30 harden the particles. It is not necessary to wash the particles to remove solubles. Calcination conditions are controlled to minimize the formation of crystalline magnesium silicates or other crystalline magnesium compounds such as magnesium aluminates. Some mullite may
35 be present in an x-ray diffraction pattern of the product. Calcination converts the hydrous kaolin to the metakaolin state.

In another preferred embodiment, all of the kaolin is added to the slurry containing magnesium oxide. This slurry is aged to form some magnesium silicate. Colloidal silica is preferably added and the resulting slurry is 5 spray dried to form microspheres which are carefully calcined.

DESCRIPTION OF PREFERRED EMBODIMENT

Typical properties of the spray-dried and calcined 10 vanadium trap microspheres of the invention are as follows:

	BROAD RANGE	PREFERRED RANGE	ESPECIALLY PREFERRED RANGE
<u>15</u> Bulk MgO ⁽¹⁾ , wt%	2-40	5-25	7-20
Free MgO ⁽²⁾ , wt%	3-35	4-20	5-15
<u>20</u> BET surface area, m ² /g	0.1-25	1-20	2-15
Pore volume cc/g	0.1-0.4	0.15-0.35	0.15-0.30
<u>25</u> EAI (attrition resistance), wt%	0.1-2.0	0.2-1.5	0.3-1.3
Roller attrition, wt%	2-40	4-30	5-20
<u>30</u> Average particle size, microns	50-120	55-100	55-90
Average particles < 0-40 microns	5-50	7-40	10-35

35

- (1) By chemical analysis
(2) By x-ray

40 Magnesium oxide in the crystalline form of periclase has been used in practice of the invention. Another form of magnesium oxide that may be used is brucite. It is necessary to use a reactive form of magnesium oxide but the reactivity will be selected with regard to the specific 45 processing conditions employed, as explained hereinafter.

One procedure for making products of the invention on a laboratory scale involves making down a slurry of hydrous kaolin (75 to 85 wt %, VF basis), MgO (7 - 15 wt%, VF), sodium silicate solution (preferably having a $\text{Na}_2\text{O}/\text{SiO}_2$ mole ratio of 0.35), and water on a high shear mixer such as a Cowles mixer to form a fluid slurry having a total solids content of 25-35% by weight, expressed on a VF solid weight basis. After the initial blending, this mixture is allowed to mix from 6 to 12 hours in a slowly rotating container. During this "aging" step, magnesium oxide reacts with sodium silicate and silica in the slurry to form magnesium silicate which ultimately serves as a binder in the calcined microspheres. Only a portion of the magnesium oxide reacts, whereby free magnesium oxide (detectable by X-ray diffraction) is present in the product. The pH of the slurry increases during the reaction between magnesium and silica. Aging may be carried out at ambient temperature and pressure. After aging, colloidal silica (which serves as a co-binder) is added to the slurry (1-5 wt % VF SiO_2) with enough water to maintain a Brookfield viscosity of < 1000 centipoises. The slurry is then spray dried, preferably immediately to avoid thickening and gelation. Spray drying converts the slurry into microspheres with an average particle size equivalent to FCC catalyst (for example, average particle size of about 75 microns). These microspheres are then calcined in covered silica trays for 2 hrs. at 1800°F. Calcination "sets" the binder(s), converts the hydrous kaolin to metakaolin and leaves free magnesia in the microspheres.

30

This procedure has been employed using water-washed, high purity Georgia hydrous kaolin with particle sizes ranging from 60 to 90 % by weight finer than 2 microns, preferably from 75 to 80 % finer than 2 microns. In this procedure, improved attrition due to finer clay particles and the use of colloidal silica is off-set by a corresponding decrease in macropore volume.

35

The MgO used in this procedure has a surface area (BET, nitrogen) from 1 to 25 m²/g, with a median particle size from 1-10 microns. Preferred specifications are 1 to 10 m²/g surface area and a median particle size of from 4 to 5 5 microns. When carrying out this processing, higher surface area MgO reacts too quickly in the clay slurry, producing soft microspheres upon spray drying. Reduced amounts of MgO improve attrition but also reduce the effectiveness of the MgO for vanadium passivation. The 10 preferred amount is about 15 wt% in the finished product. Magnesium should not be used in the form of magnesium hydroxide or magnesium carbonate. Both give rise to problems due to particle shrinkage, ultimately resulting in vanadium traps having poor attrition resistance.

15

Sodium silicate binder as N[®] Brand (27% SiO₂, 9% Na₂O = 0.32 Na₂O/SiO₂) increases particle attrition properties at higher levels but also significantly reduces macroporosity. The preferred level is 1.25 % as SiO₂, when using N Brand 20 sodium silicate. Increased sodium silicate levels increased attrition resistance of the particles up to a point. Higher levels of sodium silicate, however, undesirably reduced macroporosity. Colloidal silica levels of from 1 to 5 wt%, preferably 1.25 to 3.75 % as SiO₂, are 25 preferred. After addition of colloidal silica to the clay/MgO/sodium silicate slurry, the resulting colloidal silica enriched slurry should be immediately spray dried to prevent thixotropic gelation.

30

The primary processing variable affecting hardness in this (as well as other variants of processes of the invention) is aging. The term aging refers to the stage of processing wherein magnesium oxide or hydroxide reacts with sodium silicate in the clay/MgO/sodium silicate slurry. 35 Excessive aging due to either undesirably high MgO reactivity (10 m²/g surface area preferred), or excessively

high initial slurry solids (< 30 % solid preferred) results in relatively soft particles.

The slurry may be spray dried in a conventional spray
5 dryer (wheel or nozzle) and calcined. Typical spray dryer conditions are inlet temperatures of 650-820°F and outlet temperatures of 190-230°F. Typical bed temperature during calcination is about 1800°F. Calcination conditions used are sufficient to dehydrate the kaolin but insufficient to
10 cause the characteristic kaolin exotherm to take place.

In another procedure, which is especially amenable to continuous commercial implementation, addition of kaolin clay is staged to control the viscosity of the feed
15 throughout processing and the grade of magnesia is selected to assure controlled aging. In this procedure, aging of the clay/MgO slurry is controlled by making the initial MgO slurry using only a portion of the hydrous kaolin clay of the total kaolin, e.g., 5 - 20% to be present in the feed
20 charged to the spray dryer. Preferably ultrafine kaolin, e.g., 90-100% by weight finer than 2 microns is used. A preferred level of hydrous clay is about 15% of the total hydrous kaolin. A lignosulfate dispersant should be used to maintain the MgO in dispersed condition when using this
25 procedure. In preparing the first, relatively low solids slurry, it is preferable to cofeed lignosulfonate dispersant and clay and then incorporate magnesium oxide. This slurry is then aged, resulting in formation of magnesium silicate. The pH increases during aging and the
30 viscosity of the slurry increases. The remainder of the clay, preferably an ultrafine grade, is added immediately before spray drying so as to assure minimal contact time between the additional clay and the initial slurry. The remainder of the clay is preferably added as a concentrated
35 fluid dispersion, e.g., a slurry containing 68-70% solids, to assure that the spray dryer operates with a high enough solids slurry to assure an attrition-resistant product.

These microspheres are formed by spray drying, as described above, and are then calcined in covered trays for 2 hrs. at 1800°F in laboratory scale operations. Using commercial rotary calciners a bed temperature of about 1800°F is
5 suitable.

For this two stage kaolin clay addition procedure, a more reactive (light burned) MgO is desired with a surface area of from about 5 to 70 m²/g. The preferred surface area
10 is 35 to 65 m²/g. High surface area MgO is suitable in this procedure because of the minimized contact time with the bulk of the clay slurry prior to spray drying.

Using this two stage kaolin addition procedure, a
15 sodium silicate binder precursor with a molar ratio of SiO₂/Na₂O of 2.88 has proved better than sodium silicates with a 3.12-3.25 molar ratio. Levels of the preferred sodium silicate are from 0.75 to 2.5 wt% as SiO₂. A preferred level is of about 2% SiO₂. [All weights of SiO₂,
20 referred to are reported on a VF weight basis.]

The addition of colloidal silica in this two stage kaolin addition procedure is optional. The benefit of enhanced attrition achievable by adding colloidal silica
25 (which is made to the first slurry for this procedure) is weighed against the increase in the solids and increase in viscosity of the initial MgO/kaolin clay slurry. Lower solids prevent premature aging of the slurry and softer particles.

30

Passivator microspheres of the invention are used to prevent vanadium poisoning of zeolitic cracking catalyst used to crack gas oil and resids. The active catalyst particles contain one or more zeolites, usually including
35 at least one of the Y type, in a matrix/diluent, typically silica-alumina. The catalysts may be prepared by in situ procedures, e.g., processes described in US 4,493,902, or

by procedures in which previously crystallized zeolite is mixed with matrix components, e.g., kaolin and silica-alumina gel. Generally particles of zeolitic cracking catalyst and passivator are similar in size, although they 5 can be different if desired.

Passivator microspheres of the invention may be blended with separate zeolite catalyst particles before introducing the catalyst to an FCC unit. Alternatively, 10 the passivator particles can be charged to circulatory catalyst inventory in the cracking unit. Typically the particles are mixed in amounts within the range of 2 to 50% by weight, preferably 10 to 40% by weight, and most preferably 20 to 30% by weight of the mixture. When used 15 in insufficient amounts, improvements in vanadium passivation may not be sufficient. When employed in excessive amounts, cracking activity and/or selectivity may be impaired. Optimum proportions vary with vanadium level of feed and the proportion of magnesia in the passivator 20 particles.

In the specification and illustrative examples, the following procedures for measuring and characterizing materials were used.

25

All proportions are on a weight basis.

The term "VF" weight refers to volatile free weight and is determined by heating a sample to constant weight at 30 1800°F.

Surface area measurements were by the known BET method using nitrogen as adsorbate.

35

The particle sizes of clay materials used in preparing samples were determined by conventional sedimentation procedure.

Attrition resistance is reported by EAI and Roller attrition values. The Roller Procedure is described in US 5,082,814, the teachings of which regarding this test procedure are incorporated herein by cross-reference. The 5 EAI procedures is described in US 4,493,902, incorporated herein by cross-reference.

Catalytic activity was measured by the MAT procedure described in US 4,493,902, the teachings of which are 10 incorporated herein by cross-reference. Porosity measurements are made by mercury porosimetry as set forth in this patent.

Percent "free" MgO was determined by conventional X-15 ray diffraction by measuring and adding the integrated peak intensity of the three MgO XRD lines at 42.9°, 62.3° and 78.6° 2 θ , using Cu K-alpha radiation and comparing the values to those of a pure MgO standard.

20 In all of the illustrative examples, MgO was in periclase form.

The following procedure was used in some of the illustrative examples to deposit vanadium prior to 25 catalytic evaluation. This procedure is believed to give more realistic results than the known Mitchell method because it takes into account transfer of vanadium from zeolitic cracking catalyst particles to vanadium trap particles during the FCC cycle. In this method, a neutral 30 body (kaolin clay particles calcined at 2150^oF for 2 hours) was first impregnated with vanadium. The surface area of these particles was less than 3 m²/g; the particles had no activity for catalytic cracking. Vanadium migration from these particles to blended FCC catalyst particles was 35 measured after steaming at 1450^oF for 4 hours in a 90% steam/10% air atmosphere. In a blend containing 70% of a regular FCC catalyst (sample B described below) with mesh

size of 230-325 (US Standard) and V impregnated on neutral particles (A), only 5% of the V was retained by sample A. This indicates the V would be released from sample A to the FCC catalyst (sample B) during steaming which would mimic 5 the FCC operation more accurately than the Mitchell impregnation method.

To prepare sample A, vanadium containing particles, vanadium from vanadium naphthenates was deposited over a 10 chemically neutral microspheres by using vanadium naphthenates of 1.5% concentration in hexane over 500 grams of a highly calcined clay (2100°F) to obtain a loading of about 1500 ppm vanadium. The impregnated particles were then dried overnight and calcined first at 700°F and then 15 1100°F. Vanadium analysis of these particles showed the presence of 7500 ppm. Vanadium was analyzed by inductively coupled plasma spectroscopy (ICP).

To prepare sample B, a commercial FCC catalyst 20 manufactured by Engelhard Corporation was used. The catalyst contained (40%) Y-zeolite and was exchanged to a rare-earth oxide level of 0.8%.

Neutral particles with no V sink were highly calcined 25 kaolin clay particles (2150°F) that had less than 3 m²/g surface area and nil catalytic cracking activity.

Vanadium trap microspheres are described in illustrative examples.

30

In carrying out the new procedure, 15 grams of the FCC catalyst (sample B) were blended with 20 % (by weight) of sample C and 30 % of sample A so that the finished catalyst contained 50% FCC catalyst with a vanadium level of 2500 35 ppm. The blended material was then steamed in 90% steam/10% air at 1450°F for 4 hours in a closed reactor. The catalyst blend was then analyzed before and after

steaming to confirm that the composition of the blend did not change during steaming.

Example #1

5 Procedure for Testing Unreacted Magnesium Oxide

Tests were carried out to determine parameters for preserving magnesium oxide while forming a binder of magnesium oxide in situ. The components used were as follows:

10

Hydrous Clay	814. g
MgO AM94	140.7 g
N ^o Brand Sodium Silicate	37.9 g
H ₂ O	1298.7 g
<u>15</u> Colloid Silica (added)	248.0 g

A slurry consisting of a hydrous (ASP^o-600 supplied by Engelhard Corporation), MgO (American Mineral's AM 94, surface area of 10 m²/g), N^oBrand sodium silicate and water were made down using a high shear drill press mixer. This 20 mixture was then allowed to age over night in a slowly rotating container. After aging, a colloidal silica solution (Nalco #2326) was added to the mixture with enough water to maintain a flowable mixture (< 1000 CPS Brookfield viscosity, #2 spindle). This slurry was then screened to 25 remove any agglomerates, and spray dried to a particle size similar to FCC catalyst (~70u APS). Calcination of the spray dried microspheres was performed at temperatures of from 1500 - 1900^oF @ 2 hrs. The following table indicates that as the calcination temperature is increased, pore 30 volume decreases, attrition improves and the formation of periclase (as measured by XRD) is decreased.

Calcination Temp.	PV	Free MgO	Roller
<u>F</u>	<u>(600-20K)</u>	<u>%</u>	<u>Attrition, %</u>
1500	0.3346	12.5	> 30
<u>35</u> 1800	0.2115	10.8	17
1900	0.1047	8.3	10
2100	---.---	7.0	--

Example #2

Preparation and Testing of Control Microspheres

A slurry consisting of a hydrous clay (ASP®600 supplied by Engelhard Corporation), tetrasodium pyrophosphate clay dispersant (10 lb/ton) and water were made down to a clay solids content of 60% by weight using a high shear drill press mixer. This grade of kaolin is approximately 80% by weight finer than 2 microns. The slurry was screened to remove any agglomerates, and spray dried to a particle size similar to FCC catalyst (~70u APS). The spray dried particles were then calcined at 2150°F for 2 hours and designated sample C. The kinetic activity of sample C was less than < .1.

Kinetic activity is calculated as follows:

$$\frac{\text{MAT conversion}}{100 - \text{MAT conversion}}, \text{ wherein conversion is on a weight basis}$$

The effectiveness of these particles as a vanadium trap was tested by the new procedure described above. Fifteen (15) grams of FCC catalyst was blended with 6 grams of sample C and 9 grams of sample A, whereby the final catalyst contained 2500 ppm V. After steaming in 90% steam/10% air for 4 hours at 1450°F, the sample was tested for catalytic activity by the MAT procedure: The kinetic activity of the steamed catalyst was 1.0.

30

This procedure was used for comparing blends in which the inert particles C were substituted by samples which contained MgO as a vanadium trap.

Example #3

This example further demonstrates the importance of providing free magnesium oxide in clay-based vanadium passivator particles. In this example, the magnesium oxide 5 starting material was converted to crystalline magnesium compounds as a result of the use of excessively high temperature during final calcination.

Hydrous kaolin clay microspheres made according to 10 Example 2 were calcined at 1300°F for 1 hour to transform the clay to the metakaolin form. 100 grams of the metakaolin microspheres was impregnated with 100 grams of magnesium nitrate solution containing 10% MgO. The microspheres were dried at 250°F and calcined at 2100°F in 15 a muffle furnace for 2 hours. These microspheres were designated sample G.

The surface area of the calcined microspheres was less than 1 m²/g; XRD analysis showed the presence primarily of 20 mullite, fosterite, (crystalline magnesium silicate) cristobalite, anatase, rutile and spinel (MgAlO₃). No free MgO was observed in these microspheres.

These microspheres, tested as a V trap, had an activity 25 of only 1.1 which is only 10% better than the control.

Example #4

In this example, magnesium carbonate was used as the source of magnesium. Colloidal silica was used as a binder. Calcination was at relatively high temperature
5 (2100°F).

A slurry consisting of a hydrous kaolin clay (ASP®600 supplied by Engelhard Corporation), MgO (Premier's 33 MgCO₃), N®Brand sodium silicate and water was made down using a high shear drill press mixer. This mixture was then
10 allowed to age overnight in a slowly rotating container. After aging, colloidal silica (Nalco #2326) was added to the mixture with enough water to maintain a flowable mixture (< 1000 CPS Brookfield viscosity). This slurry was then screened to remove any agglomerates, and
15 spray dried to a particle size similar to FCC catalyst (~70u APS).

Specific amounts of reagents were as follows:

	Hydrous clay	814.0g
	MgCO ₃ (50% slurry)	630.0g
<u>20</u>	N®Brand sodium silicate	43.9g
	Water	550.0g
	Colloidal Silica solution	254.4 g
	(15% SiO ₂ , by Wt)	

25 Spray drying conditions were as follows:

	Inlet Temp	600 - 650°C
	Outlet Temp	240 - 260°C
	Air Pressure	40 psig
	Pump Rate	1

The dried microspheres were then calcined at a temperature of 2100^oF @ 2 hrs. These microspheres were designated sample H.

<u>5</u>	<u>Sample</u>	<u>Surface Area, m²/g</u>	<u>Pore Volume 600-20KA, cc/g</u>	<u>Roller Attrition, %</u>
	H	2.2	0.25	> 30
	I	13.5	0.38	6

10 Sample H was tested for vanadium control. Activity was 1.2 which is 20% better than the control, sample C.

Example #5

15 This example further demonstrates the desirability of maintaining appreciable free MgO in a vanadium trap.

A portion of the spray dried microspheres of Example 4 were calcined at 1800^oF. This material was sample I. An X-ray diffraction pattern of the calcined microspheres 20 showed high level of free MgO, which the inventors consider a necessary component for an effective vanadium trap. These microspheres tested in the same manner as described in Example #1, showed an activity of 1.5, about 50% higher activity than the control.

25

Example #6

This example illustrates an embodiment of the process of the invention carried out in plant-scale equipment.

30 Processing of the spray dryer slurry consisted of initially mixing N Brand sodium silicate, water, carboxyl methyl cellulose (used as a suspending agent for magnesium oxide) and a slurry of hydrous kaolin clay in a high shear mixer. The kaolin clay was nominally 80% by weight finer 35 than 2 microns. This was followed by the addition of American Mineral's AM 94 MgO (surface area of 50 m²/g) to achieve 12% MgO in the product. Prior to spray drying, Nalco colloidal silica (15% silica) was added to the slurry using an inline mixer. The solids content of the slurry

was 33% by weight prior to addition of the colloidal silica and 31% after addition of the silica. The material was spray dried to a particle size slightly coarser than an FCC catalyst, averaging about 80 microns.

5 Component ratios were as follows:

	<u>wt.</u>
Hydrous Clay Slurry	100
N Brand sodium silicate solution	2.07
MgO	7.86
<u>10</u> H ₂ O	76.87
CMC	6.16
Colloidal Silica	15.39

The spray dried microspheres were calcined in a 15 commercial rotary calciner at a furnace temperature of about 2100°F (which corresponds to a laboratory calcination at 1700 to 1800°F. These calcined microspheres were designated sample J and were tested as in Example 1. They exhibited about 35% higher activity than particles C with 20 no vanadium trap.

Example #7

This example further shows the necessity for controlling calcination temperature to maintain free magnesium oxide in 25 the passivator particles.

Processing was the same as in Example #6 except with a high calcination temperature of 2300°F was used in operating the rotary calciner. This corresponds to a 30 laboratory calcination temperature of from 2000-2200°F. The material calcined at 2300°F was designated sample K.

Testing of sample K indicated similar activity maintenance to sample C and 35% lower than Example #6, 35 sample J.

The Mitchell procedure for testing vanadium tolerance was used in the following example. Twenty-eight (28) grams of an FCC catalyst containing about 35% zeolite and 1.2% rare-earth oxide was blended with 12 grams of either
5 neutral microspheres (no vanadium trap, sample C) or with samples containing MgO as a V trap. The blended particles were then impregnated with a solution of Ni and V naphthenates in cyclohexane solution. The impregnated material was then dried in air overnight and then calcined
10 in a muffle furnace at 700°F for 2 hours followed by calcination at 1100°F for another 2 hours. Two levels of naphthenate solutions were impregnated over the blended particle to give finished products containing (1) Ni/V of 1000/2000 ppm and (2) 2500/5000 ppm. The samples were then
15 steamed in a 90% steam/10% air for 4 hours at 1450°F. The samples were analyzed before and after steaming to demonstrate that similar compositions were maintained during steaming. Microactivity testing was then performed.

20

Example #8

This example shows the calcination temperature sensitivity as tested under the Mitchell method protocol.

25 Twenty-eight (28) grams of commercial FCC catalyst from Engelhard Corporation containing about 35% zeolite and a rare-earth oxide level of 1.2% was blended with 12 grams of either of the following components: inert kaolin particles (C), highly calcined MgO/clay particles K (from Example 7),
30 or low-temperature calcined MgO/clay particles J (from Example 6). The three mixtures were then impregnated with metals, using the Mitchell method.

35 At metals levels of 2000 ppm V/1000 ppm Ni, the mixture containing particles K had the same activity maintenance as the reference sample; the mixture containing particles of [J] had 23% better activity maintenance. At 8000 ppm V/2500

ppm Ni, the activity maintenance improvements over sample C were 20% for the mixture containing particles K, and 50% for the mixture containing particles J.

5 The results clearly show that the lower level of calcination which retains high level of unreacted MgO in the particles had better performance than the control, sample C.

10 **Example #9**

This example illustrates a presently preferred method for practicing the invention.

For this process, the spray dryer feed slurry was 15 prepared as two separate components which were combined in a static mixer immediately prior to spray drying. The first component "A" is composed of an ultrafine particle size Georgia Kaolin (100% finer than 1 micron) made into a 59.34% VF slurry with water and tetrasodium pyrophosphate 20 (TSPP) as a dispersant. These high solids were achieved by blending a 44.7% solids clay slurry with sufficient spray dried kaolin and optimum TSPP in a high shear Cowles mixer.

The second component "B" consisted of MgO, as supplied 25 by Martin Marietta Corporation as MagChem 40, #14 Grade sodium silicate provided by Power Silicates (41% solids, 2.88 molar SiO₂:Na₂O Ratio), HP-100, a dispersant supplied by Martin Marietta and believed to be a lignosulfonate, the same ultrafine particle size clay used in component "A" 30 supplied as a 44.7% VF solids slurry and sufficient water to a total VF solids of this component of 27.87%.

Component "B" was produced in a series of high shear Cowles mixers. In the first mixer, all the components 35 except the MgO were added in the proportions listed below; in the second, the dry MgO was introduced and its addition rate was controlled by solids measurement.

MIXER #1

	Clay Slurry	23.49%
	#14 Silicate	7.97%
	HP-100	.10%
<u>5</u>	H ₂ O	68.44%

Target = 14.04% VF solids and 2.55% SiO₂ from #14 Silicate

MIXER #2

<u>10</u>	Mixer #1 Slurry	83.91%
	MgO	19.18%
	Target = 27.87% VF solids	

15 Component "B" slurry was then allowed to age in an agitated tank for a minimum of 6 hrs. prior to spray drying. Sufficient agitation was required to maintain the viscosity of this component at ~1000 centipoises by Brookfield measurement.

20 For spray drying, component "A" (the high solids clay slurry) and component "B" (the aged MgO slurry) were combined in a static mixer in the ratio of 1.337:1 respectively, and immediately pumped directly to the spray dryer atomizer. Target VF solids of the spray dryer slurry was 45.9%. Component ratios of the microsphere on a VF 25 weight bases are: 15% MgO, 2.0% SiO₂ (provided from #14 silicate binder), 0.29% HP-100.

30 The spray dryer inlet temperature was regulated to maintain an outlet temperature of from 200 - 205°F and the atomizer speed used to control particle size distribution of the spray dried microspheres. Calcination on a direct fired rotary calciner followed spray drying with inlet temperatures of from 2000 - 2200°F to meet targeted finished product parameters.

Claims:

1. A spray drying process for manufacturing microspheres useful in fluid cracking of vanadium containing oil feedstock with separate fluidizable
5 microspheres containing a zeolitic cracking component, said process comprises mixing kaolin clay, magnesium oxide or magnesium hydroxide, and sodium silicate with water to form a slurry, aging said slurry to react a portion of the magnesium oxide or hydroxide with silica to form a
10 magnesium silicate, spray drying the aged slurry after optionally adding colloidal silica, kaolin clay or a combination thereof, to form microspheres comprising magnesium oxide, kaolin clay and in situ formed magnesium silicate, and calcining said microspheres for a time and
15 temperature sufficient to dehydrate the kaolin clay but insufficient to form a significant amount of crystalline magnesium silicates or aluminates.

20 2. The process of claim 1 wherein all of the kaolin in the slurry that is spray dried is added prior to aging and colloidal silica is added to the aged slurry before spray drying.

25

3. The process of claim 1 wherein a portion of the kaolin clay in the slurry that is spray dried is added before aging and additional kaolin clay is added to the aged slurry in an inline mixer.
30

4. A spray drying process for manufacturing attrition-resistant fluidizable microspheres comprising magnesium oxide in a kaolin clay matrix, said particles being useful
35 in fluid cracking of oil feedstock with a separate fluidizable microspheres containing a zeolitic cracking component to passivate vanadium originally contained in oil feedstock which comprises: forming a first fluid dispersed slurry (A) comprising water, kaolin clay, sodium silicate

and magnesium oxide and a dispersant for magnesium oxide; aging said slurry; adding additional kaolin clay to said aged slurry to form a second slurry (B) having higher solids content than slurry (A) using high shear agitation 5 sufficient to maintain said slurry fluid in spite of its higher content of solids; immediately spray drying said slurry B while it is still fluid; recovering the resulting microspheres comprising free magnesium oxide and kaolin clay; and calcining the microspheres for a time and 10 temperature sufficient to dehydrate the kaolin but insufficient to cause the kaolin to undergo the characteristic kaolin exotherm or to form crystalline magnesium silicates or aluminates.

15

5. The process of claim 1 wherein the calcined microspheres contain from 2 to 40% by weight MgO.

20

6. The process of Claim 1 wherein the calcined microspheres contain from 5 to 25% by weight MgO.

25

7. The process of claim 1 wherein the calcined microspheres contain from 7 to 20% by weight MgO.

30

8. The process of claim 4 wherein said slurry A and said slurry B have an apparent viscosity below 1000 cp when measured by a Brookfield viscometer using a #2 spindle.

35

9. The process of Claim 4 wherein said additional kaolin is added to said slurry B by an inline mixer which provides the high shear agitation.

40

10. The process of Claim 4 wherein all of the kaolin clay is about 100% by weight finer than 1 microns.

11. The process of Claim 4 wherein said sodium silicate has a mole ratio of $\text{SiO}_2/\text{Na}_2\text{O}$ of about 2.88.

5 12. Attrition-resistant microspheres useful as a vanadium trap in fluid catalytic cracking, said microspheres comprising particles of free MgO in amount of at least 2% by weight, determined by X-ray, in admixture with particles of fine particle size anhydrous, X-ray
10 amorphous kaolin clay, and a small amount of a magnesium silicate cement, the anhydrous kaolin being the predominating component of said microspheres; said microspheres having a BET surface area below $15 \text{ m}^2/\text{g}$, being free from substantial amounts of crystalline magnesium
15 silicate and crystalline magnesium aluminate phases, and having an EAI below 2% by weight before and after steaming at 1480°F for 4 hours with 100% steam, and a total pore volume in the range of 0.1 to 0.4 cc/g.

20

13. The microspheres of claim 12 wherein the free MgO content is from 5 - 25% by weight.

25

14. The microspheres of claim 12 wherein the free MgO content is from 7 - 20% by weight.

30

15. The microspheres of claim 12, which have a total pore volume in the range of 0.15 to 0.35 cc/g.

35

16. The microspheres of claim 12 which have a total pore volume in the range of 0.15 to 0.3 cc/g.

40

17. The microspheres of claim 12 which have a surface area below $10 \text{ m}^2/\text{g}$.

18. A process for catalytically cracking a hydrocarbon feedstock contaminated with vanadium which comprises

contacting said feedstock under catalytic cracking conditions with a physical mixture of fluidizable microspheres of zeolitic cracking catalyst and the microspheres of claim 12.

5

19. The process of claim 18 wherein the microspheres comprising free MgO are present in amount within the range of 2 to 50% by weight of said mixture.

10

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 93/11812

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: C10G 11/05, B01J 37/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: C10G, B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, CLAIMS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP, A2, 0270211 (ENGELHARD CORPORATION), 8 June 1988 (08.06.88), see page 5 --	1-19
A	US, A, 4515903 (JAN-ERIK A. OTTERSTEDT ET AL.), 7 May 1985 (07.05.85) --	1-19
A	EP, A1, 0312981 (PHLLIPS PETROLEUM COMPANY), 26 April 1989 (26.04.89) --	1-19
A	US, A, 4904627 (A. BHATTACHARYYA), 27 February 1990 (27.02.90) -- -----	1-19

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

16 March 1994

Date of mailing of the international search report

13. 04. 94

Name and mailing address of the International Searching Authority/Authorized officer



European Patent Office, P.B. 5818 Patentlaan 2
NL-2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

CAROLINA GOMEZ LAGERLÖF

INTERNATIONAL SEARCH REPORT
Information on patent family members

28/01/94

International application No.
PCT/US 93/11812

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A2- 0270211	08/06/88	AU-B- 602163	04/10/90
		AU-A- 7844087	09/06/88
		JP-A- 63185455	01/08/88
		ZA-A- 8706932	16/05/88
US-A- 4515903	07/05/85	AT-E,T- 11425	15/02/85
		AU-B- 545095	27/06/85
		AU-A- 7370381	02/02/82
		CA-A- 1165301	10/04/84
		EP-A,B- 0043358	06/01/82
		SE-B,C- 438449	22/04/85
		SE-A- 8004825	31/12/81
		WO-A- 8200105	21/01/82
		EP-A1- 0312981	26/04/89
JP-B- 5000433	05/01/93		
US-A- 4781816	01/11/88		
US-A- 4904627	27/02/90	AU-B- 602065	27/09/90
		AU-A- 1304188	15/09/88
		CA-A- 1318907	08/06/93
		DE-A- 3880179	19/05/93
		EP-A,B- 0281993	14/09/88
		JP-A- 63291640	29/11/88
		US-A- 4830840	16/05/89