



US010658361B2

(12) **United States Patent**
Tsai et al.

(10) **Patent No.:** **US 10,658,361 B2**
(45) **Date of Patent:** **May 19, 2020**

(54) **METHODS OF INTEGRATING MULTIPLE GATE DIELECTRIC TRANSISTORS ON A TRI-GATE (FINFET) PROCESS**

(75) Inventors: **Curtis Tsai**, Beaverton, OR (US); **Chia-Hong Jan**, Portland, OR (US); **Jeng-Ya David Yeh**, Portland, OR (US); **Joodong Park**, Portland, OR (US); **Walid M. Hafez**, Portland, OR (US)

(73) Assignee: **Intel Corporation**, Santa Clara, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/997,624**

(22) PCT Filed: **Dec. 28, 2011**

(86) PCT No.: **PCT/US2011/067681**

§ 371 (c)(1),
(2), (4) Date: **Jun. 24, 2013**

(87) PCT Pub. No.: **WO2013/101007**

PCT Pub. Date: **Jul. 4, 2013**

(65) **Prior Publication Data**

US 2014/0319623 A1 Oct. 30, 2014

(51) **Int. Cl.**

H01L 27/092 (2006.01)

H01L 29/66 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC .. **H01L 27/0922** (2013.01); **H01L 21/823431** (2013.01); **H01L 21/823456** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC **H01L 21/823456**; **H01L 21/823431**; **H01L 21/823462**; **H01L 27/0886**; **H01L 27/088**;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,054,354 A * 4/2000 Nowak H01L 21/8236 257/204

6,407,435 B1 6/2002 Ma et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 102024819 A 4/2011

CN 102214579 A 10/2011

(Continued)

OTHER PUBLICATIONS

International Search Report dated Jul. 18, 2012 for PCT/US2011/067681, filed Dec. 28, 2011, 3 pages.

(Continued)


Primary Examiner — Brigitte A Paterson

(74) *Attorney, Agent, or Firm* — Schwabe, Williamson & Wyatt, P.C.

(57) **ABSTRACT**

Two or more types of fin-based transistors having different gate structures and formed on a single integrated circuit are described. The gate structures for each type of transistor are distinguished at least by the thickness or composition of the gate dielectric layer(s) or the composition of the work function metal layer(s) in the gate electrode. Methods are also provided for fabricating an integrated circuit having at least two different types of fin-based transistors, where the transistor types are distinguished by the thickness and composition of the gate dielectric layer(s) and/or the thickness and composition of the work function metal in the gate electrode.

8 Claims, 24 Drawing Sheets



- (51) **Int. Cl.**
H01L 29/40 (2006.01)
H01L 29/78 (2006.01)
H01L 21/8234 (2006.01)
H01L 27/088 (2006.01)
H01L 29/49 (2006.01)
H01L 29/423 (2006.01)
H01L 29/51 (2006.01)

TW	200532915	10/2005
TW	200917484	4/2009
WO	WO 2010/068530 A2	7/2006
WO	WO 2010/068530 A2	6/2010

OTHER PUBLICATIONS

First Office Action from the Taiwan IPO for Taiwan Patent Application No. 101149334 dated May 27, 2015 and English Summary thereof.

First Office Action from the Chinese Patent Office for Chinese Patent Application No. 201180076461.1 dated May 5, 2016.

Second Office Action (7 pages) dated Jan. 20, 2017 from the State Intellectual Property Office (SIPO) for Chinese Patent Application No. 201180076461.1 and English Translation (9 pages) thereof.

Taiwan IPO Notice of Allowance for Taiwan Application No. 101149334, dated Apr. 25, 2017, with translation, 3 pages.

Taiwan Official Letter for Taiwan Application No. 105101077, dated Apr. 25, 2017, (no translation), 15 pages.

Second Office Action (7 pages) dated Jan. 20, 2017 from the Chinese Patent Office for Chinese Patent Application No. 201180076461.1.

Office Action from U.S. Appl. No. 14/977,367, dated Feb. 6, 2018, 13 pages.

Office Action from Taiwan Patent Application No. 106124016, dated Apr. 11, 2018, 9 pages.

Notice of Allowance from Chinese Patent Application No. 201180076461.1, dated Jun. 29, 2017, 4 pgs.

International Preliminary Report on Patentability for International Patent Application No. PCT/US2011/067681, dated Jul. 10, 2014, 6 pgs.

Office Action from Taiwan Patent Application No. 101149334, dated Oct. 17, 2014, 8 pgs.

Notice of Allowance from Patent Application No. 105101077, dated Sep. 7, 2017, 4 pgs.

Office Action from Taiwan Patent Application No. 107125899, dated Jun. 19, 2019, 7 pgs.

Notice of Allowance from Taiwan Patent Application No. 107125899, dated Aug. 29, 2019, 3 pgs.

Notice of Allowance from Taiwan Patent Application No. 106124016, dated Sep. 17, 2018, 3 pgs.

Notice of Allowance from Chinese Patent Application No. 201610006987.7, dated Sep. 26, 2018, 4 pgs.

Office Action from U.S. Appl. No. 14/977,367, dated Dec. 1, 2016, 13 pgs.

Office Action from U.S. Appl. No. 14/977,367, dated Apr. 13, 2017, 23 pgs.

Official Letter and Search Report (7 pages) dated Nov. 16, 2016 from the Taiwan Intellectual Property Office for Taiwan Patent Application No. 101149334 and English Summary (4 pages) thereof.

Official Letter and Search Report (9 pages) dated Nov. 17, 2016 from the Taiwan Intellectual Property Office for Taiwan Patent Application No. 105101077 and English Summary (4 pages) thereof.

Office Action (9 pages) from the German Patent and Trademark Office dated Dec. 14, 2016 for German Patent Application No. 112011106052.1 and English Translation (9 pages) thereof.

Non-Final Office Action from U.S. Appl. No. 14/977,367 dated Sep. 8, 2017, 17 pgs.

Office Action from Taiwan Patent Application No. 106124016, dated Dec. 5, 2017, 14 pages.

English Summary of Office Action from Taiwan Patent Application No. 106124016, 2 pages.

Office Action from Chinese Patent Application No. 201610006987.7, dated Feb. 2, 2018, 5 pages.

Notice of Allowance from Taiwan Patent Application No. 106104796, dated Jan. 8, 2020, 3 pgs.

Office Action from Taiwan Patent Application No. 108129862, dated Mar. 23, 2020, 9 pgs.

- (52) **U.S. Cl.**
 CPC .. *H01L 21/823462* (2013.01); *H01L 27/0886* (2013.01); *H01L 27/0924* (2013.01); *H01L 29/401* (2013.01); *H01L 29/408* (2013.01); *H01L 29/42364* (2013.01); *H01L 29/4966* (2013.01); *H01L 29/66484* (2013.01); *H01L 29/66795* (2013.01); *H01L 29/7855* (2013.01); *H01L 29/512* (2013.01); *H01L 29/513* (2013.01); *H01L 29/517* (2013.01); *H01L 29/518* (2013.01); *H01L 29/7831* (2013.01); *H01L 29/7851* (2013.01)

- (58) **Field of Classification Search**
 CPC *H01L 27/115*; *H01L 29/42392*; *H01L 29/4966*; *H01L 29/513*; *H01L 29/94*; *H01L 29/76*
 See application file for complete search history.

- (56) **References Cited**
 U.S. PATENT DOCUMENTS

7,071,048	B2	7/2006	Son et al.	
7,361,958	B2	4/2008	Brask et al.	
7,550,332	B2	6/2009	Yang	
7,902,014	B2	3/2011	Doyle et al.	
7,948,037	B2	5/2011	Chen et al.	
7,994,037	B2	8/2011	Trentzsch et al.	
2005/0093082	A1	5/2005	Son et al.	
2006/0017113	A1	1/2006	Xu et al.	
2006/0263966	A1*	11/2006	Kim et al.	438/218
2007/0080380	A1*	4/2007	Chang	257/274
2007/0111448	A1*	5/2007	Li et al.	438/264
2007/0290223	A1	12/2007	Yagishita	
2008/0308861	A1	12/2008	Nawaz	
2009/0170267	A1	7/2009	Shah et al.	
2009/0243941	A1	10/2009	Guthoerl et al.	
2009/0294800	A1*	12/2009	Cheng et al.	257/192
2010/0025770	A1	2/2010	Trentzsch et al.	
2010/0065892	A1*	3/2010	Hwang et al.	257/253
2010/0072553	A1	3/2010	Xu et al.	
2010/0276753	A1	11/2010	Greene et al.	
2010/0317181	A1	12/2010	Chung et al.	
2010/0320545	A1	12/2010	Jagannathan et al.	
2011/0034020	A1*	2/2011	Johnson	438/595
2011/0156166	A1	6/2011	Huang et al.	
2011/0159678	A1	6/2011	Hsu et al.	
2012/0018730	A1*	1/2012	Kanakasabapathy	H01L 29/66795 257/66
2012/0119299	A1*	5/2012	Iizuka	H01L 21/823456 257/368
2012/0286372	A1*	11/2012	Lavoie et al.	257/410
2013/0020630	A1*	1/2013	Lee	H01L 21/823842 257/324
2013/0082332	A1	4/2013	Liu et al.	
2013/0161707	A1	6/2013	Huang et al.	

FOREIGN PATENT DOCUMENTS

DE	10 2008 035 805	A	2/2010
JP	2006-006438	A	1/2006
KR	10-2011-0071198	A	6/2011
TW	200412626	A	7/2004

* cited by examiner




FIG. 1A




FIG. 1B




FIG. 1C




FIG. 1D




FIG. 2A




FIG. 2B




FIG. 3A




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E




FIG. 4F




FIG. 4G




FIG. 4H




FIG. 4I




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E




FIG. 5F




FIG. 5G





FIG. 5H






FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 6F




FIG. 6G




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 7E

714




FIG. 8

METHODS OF INTEGRATING MULTIPLE GATE DIELECTRIC TRANSISTORS ON A TRI-GATE (FINFET) PROCESS

CROSS-REFERENCE TO RELATED APPLICATION

This patent application is a U.S. National Phase Application under 35 U.S.C. § 371 of International Application No. PCT/US2011/067681, filed Dec. 28, 2011, entitled METHODS OF INTEGRATING MULTIPLE GATE DIELECTRIC TRANSISTORS ON A TRI-GATE (FINFET) PROCESS.

TECHNICAL FIELD

The present invention relates generally to the manufacture of semiconductor devices, semiconductor logic devices, and transistors. In particular, embodiments of the present invention relate to processes for fabricating a multiple fin-based devices with varied gate structures on the same chip.

BACKGROUND

The desire for ever-smaller integrated circuits (IC) places enormous demands on the techniques and materials used to construct the devices. Components of IC chips include solid-state logic devices (transistors) such as CMOS (complementary metal oxide semiconductor) devices. Recently developed fin-based transistors enable increased performance for a smaller device footprint. Different transistor applications have different structure and performance requirements, for example, high speed logic operations, low power usage, high voltage input output (I/O), and extremely high voltage. Novel processes are required to enable fabrication of multiple types of new fin-based transistors on a single chip.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1A-1D illustrate embodiments of dual-gate transistors, wherein each transistor has a different gate stack configuration.

FIGS. 2A-2B illustrate embodiments of triple-gate transistors, wherein each transistor has a different gate stack configuration.

FIGS. 3A-3B illustrate embodiments of quad-gate transistors, wherein each transistor has a different gate stack configuration.

FIGS. 4A-4I illustrate methods for forming a single IC having multiple transistors with different gate stack configurations.

FIGS. 5A-5I illustrate additional methods for forming a single IC having multiple transistors with different gate stack configurations.

FIGS. 6A-6G illustrate additional methods for forming a single IC having multiple transistors with different gate stack configurations.

FIGS. 7A-7E illustrate additional methods for forming a single IC having multiple transistors with different gate stack configurations.

FIG. 8 illustrates a computing device in accordance with one embodiment of the invention.

DETAILED DESCRIPTION

An integrated circuit (IC) structure comprising two or more fin-based field effect transistors, having different types

of gate structures, and a method for forming the different types of transistors on a single chip are described. The present invention has been described with respect to specific details in order to provide a thorough understanding of the invention. One of ordinary skill in the art will appreciate that the invention can be practiced without these specific details. In other instances, well known semiconductor processes and equipment have not been described in specific detail in order to not unnecessarily obscure the present invention. Additionally, the various embodiments shown in the figures are illustrative representations and are not necessarily drawn to scale.

Embodiments of the present invention provide an integrated circuit housing a plurality of fin-based transistors having different types of gate structures, and methods for manufacturing these different types of devices on a single circuit. The formation of ICs having a plurality of transistor types can address divergent circuit requirements, such as, for example, high speed logic operation, low power usage, high voltage input output (I/O), and extremely high voltage, which are desirable attributes for components of system-on-a-chip (SOC) integrated circuits. System-on-a-chip devices integrate a wide variety of circuit functions, such as processor cores, analog functions, and mixed signal blocks, onto a single integrated circuit chip. Embodiments of the invention provide ICs with transistors having different types of gate structures, each comprising one or two high k material gate dielectric layers, an oxide (SiO₂) layer, one or two work-function metal layers, a fill metal, and combinations thereof. Transistors with different gate structures are capable of providing performance characteristics that span a wide range of operating speeds, leakage characteristics, and high voltage tolerances. Methods of forming circuits comprising transistors with different gate structures are also disclosed.

FIGS. 1A-1D illustrate embodiments of fin-based transistors located in an integrated circuit. Each integrated circuit has at least two different transistor types that are distinguished at least by the thickness or composition of the gate dielectric and/or the composition of the work function metal(s) employed in the gate electrode. The transistors may have other distinguishing features. Typically, an integrated circuit having a plurality of different transistor types will have a large number of instances of each type of transistor arranged in various formats (e.g., arrays). For simplicity, one instance of each type of transistor is shown in FIGS. 1A-1D as an isolated transistor, although the transistors illustrated are typically found in various places and arrangements in the integrated circuit chip in which they are located.

FIG. 1A illustrates a three-dimensional perspective view of two transistors **101** and **102** formed on the same IC. FIG. 1B illustrates a cross-sectional view of transistors **101** and **102** as shown in FIG. 1A, taken through the channel regions **116** and gate structures **111A** and **111B** along line A-A'. Fins **112** extend from semiconductor substrate **110** and, in embodiments, run the full length of substrate **110**. In an embodiment, each transistor comprises one or more fins **112** separated by isolation regions **114**. In an embodiment, each transistor comprises a gate structure **111** that wraps around the side and top surfaces of a portion of each fin **112**, defining a channel region **116**. In an embodiment, transistor **101** comprises gate structure **111A**, and transistor **102** comprises gate structure **101B**, as shown in FIG. 1A. Each fin **112** has a pair of source/drain regions **118** disposed on opposite sides of channel region **116**, as shown in the embodiment illustrated by FIG. 1A. For a PMOS device, the source/drain regions are p-type doped and the channel region is n-type doped. For an NMOS device, the source/

drain regions are n-type doped and the channel region is p-type doped. The height of fins **112** above isolation regions **114** ranges from 20 to 100 Å, and the width of fins **112** range from 5 to 20 Å.

Each transistor gate structure **111A** and **111B** comprises a gate dielectric **113** and a gate electrode **115**, as shown in FIG. 1A. Each gate dielectric **113** may comprise one or more dielectric layers, for example, a silicon dioxide layer or a high k dielectric layer. The gate dielectric **113** insulates the channel region **116** from the gate electrode **115** to reduce leakage and to set the device threshold voltage. Each gate electrode **115** includes one or more work-function metal layers and may also include a conductive fill metal **140**. A work function metal layer manages the barrier height between the dielectric material and the fill metal, minimizing resistance at the metal-semiconductor interface, and setting the work function of the device. The fill metal carries the bulk of the charge that controls the transistor state, and typically is a lower-resistance material than the work function metal(s).

The integrated circuit shown in FIGS. 1A-D has at least two different types of transistors, **101** and **102** that are distinguished by the composition of the dielectric layers employed in the transistor gate structure. In an embodiment of the invention, the gate structure of transistor **101** comprises a gate dielectric having a high k dielectric layer **121** and a gate electrode having both a work function metal layer **131** and a fill metal **140**, as shown in FIG. 1B. The type of gate structure in transistor **101** enables use of the transistor for high performance cores.

In an embodiment of the invention, high k dielectric layer **121** conforms to the side and top surfaces of the fins **112** and isolation regions **114** that comprise transistor **101**. In general, a high k dielectric layer is a dielectric material having a dielectric constant greater than that of silicon dioxide. The dielectric constant of silicon dioxide is 3.9. Exemplary high k dielectric materials that may be used in high-k dielectric layer **121** include hafnium dioxide (HfO₂), hafnium silicon oxide, lanthanum oxide, lanthanum aluminum oxide, zirconium dioxide (ZrO₂), zirconium silicon oxide, titanium dioxide (TiO₂), tantalum oxide, barium strontium titanium oxide, barium titanium oxide, strontium titanium oxide, yttrium oxide, aluminum oxide, lead scandium tantalum oxide, lead zinc niobate, and other materials known in the semiconductor art. High k dielectric layer **121** ranges from 10 to 50 Å thick. In an embodiment, high k dielectric layer is 30 Å thick.

Work function metal layer **131** conforms to the surface of high k dielectric layer **121**. Exemplary metals that may be used in work function metal layer **131** include titanium nitride, tungsten nitride, tantalum nitride, titanium aluminum, tungsten, silicides and other materials known in the semiconductor art. Work function metal layer **131** ranges from 10 to 50 Å thick. In an embodiment, work function metal layer **131** is 30 Å thick.

Fill metal **140** fills the gate structure opening defined by work function metal layer **131**. Fill metal **140** may comprise materials including, for example, metal gate materials, such as, hafnium, zirconium, titanium, titanium nitride, tantalum, aluminum, and combinations thereof. Additional materials include, metal carbides, such as, for example, titanium carbide, zirconium carbide, tantalum carbide, hafnium carbide and aluminum carbide. Further materials that may be used include ruthenium, palladium, platinum, cobalt, nickel, and conductive metal oxides, such as, for example, ruthenium oxide. Other materials are possible.

In an embodiment, the gate structure of transistor **102** has a gate dielectric comprising both a silicon dioxide layer **125** and high k dielectric layer **121**, and a gate electrode comprising both work function metal layer **131** and fill metal **140**. In an embodiment, silicon dioxide layer **125** is grown from the surfaces of fins **112**. In another embodiment, silicon dioxide layer **125** is conformally deposited on fins **112** and isolation region **114**. Silicon dioxide layer **125** may be from 5 to 100 Å thick. In an embodiment, silicon dioxide layer **125** is 30 Å thick. In an embodiment, high k dielectric layer **121** covers silicon dioxide layer **125** within the gate structure, and together the two layers form the gate dielectric. In an embodiment, work function metal **131** covers high k dielectric layer **121**, and fill metal **140** fills the opening lined by work function metal **131**. As compared to the gate structure in transistor **101**, the addition of silicon dioxide layer **125** to the gate dielectric enables use of transistor **102** for high voltage, input output (I/O) circuit applications.

Typically, transistor structures **101** and **102** are at least partially surrounded by a dielectric material **150**, as shown in FIG. 1B. In some embodiments dielectric material **150** is an interlayer dielectric (ILD) material, such as silicon dioxide or low k dielectric materials. Additional dielectric materials that may be used include carbon doped oxide (CDO), silicon carbide, silicon nitride, organic polymers such as perfluorocyclobutane or polytetrafluoroethylene, fluorosilicate glass (FSG), and organosilicates such as silsesquioxane, siloxane, or organosilicate glass.

In an embodiment, spacers **135** are located on sidewalls of the gate structure **111**. Spacers **135** are formed on the gate structure **111** sidewalls adjacent to the source/drain regions **118**, as shown in FIG. 1A, in order to isolate the gate structure **111** from epitaxial material grown on fins **112**, and also to protect the channel region **116** during heavy doping of the source/drain regions. Spacers **135** may additionally be formed on the ends of each gate structure **111**, as shown in FIG. 1B. Spacers **135** may be comprised of a suitable dielectric material, such as, for example, silicon nitride, silicon dioxide, silicon oxynitride, or other material known in the semiconductor art.

Another embodiment of the invention comprises at least two different types of fin-based transistors, **101** and **103**, where each transistor is distinguished by the composition of the dielectric layers employed in the gate structures, as shown in FIG. 1C. In an embodiment of the invention, the gate structure of transistor **101** comprises a gate dielectric having a high k dielectric layer **121** and a gate electrode having both a work function metal layer **131** and a fill metal **140**.

The gate structure of transistor **103** comprises a gate dielectric having both a high k dielectric layer **122** and high k dielectric layer **121**, and a gate electrode having both work function metal layer **131** and fill metal **140**. In an embodiment, high k dielectric layer **122** is formed on the fin surface. In an embodiment, high k dielectric layer **121** covers high k dielectric layer **122**. In an embodiment, work function metal layer **131** covers high k dielectric layer **121**. In an embodiment, fill metal **140** completes the gate structure by filling in the gate structure opening defined by work function metal layer **131**. In an embodiment, high k dielectric layer **122** has a different composition or thickness than high k dielectric layer **121**. As compared to the gate structure in transistor **101**, the addition of high k dielectric material **122** reduces gate leakage while increasing the threshold voltage, enabling use of transistor **103** for low-power circuits or applications. High k dielectric layer **122** may be any of the materials listed above with respect to high k dielectric layer

121. High k dielectric layer **122** ranges from 10 to 50 Å thick. In an embodiment, high k dielectric layer **122** is 30 Å thick.

Another embodiment of the invention comprises at least two different types of fin-based transistors, **101** and **104**, located on a single integrated circuit, where each type of transistor has a different gate structure, as illustrated by FIG. 1D. In an embodiment of the invention, transistors **101** and **104** are distinguished by the composition of the work-function metal(s) employed in each gate electrode. In a specific embodiment, the gate structure of transistor **101** comprises a gate dielectric having a high k dielectric layer **121** and a gate electrode having both a work function metal layer **131** and a fill metal **140**.

In an embodiment, the gate structure in transistor **104** comprises a gate dielectric having high k dielectric layer **121** and a gate electrode having a work function metal layer **132**, work function metal layer **131** and fill metal **140**. In an embodiment, high k dielectric layer **121** covers the fins **112**. In an embodiment, work function metal layer **132** covers high k dielectric layer **121**. In an embodiment, work function metal layer **131** covers work function metal layer **132**. In an embodiment, fill metal **140** fills the gate structure opening defined by work function metal layer **131**. In an embodiment, work function metal layer **132** in transistor **104** has a different work function than work function metal layer **131**. The addition of work function metal **132**, as compared to the gate structure in transistor **101**, increases the threshold voltage for transistor **104** and reduces gate leakage, enabling use of transistor **104** for low-power circuits or applications. Work function metal layer **132** may be any of the materials listed above with respect to work function metal layer **131**. Work function metal layer **132** may be from 10 to 50 Å thick. In an embodiment, work function metal layer **132** is 30 Å thick.

The embodiments illustrated by FIGS. 2A-B comprise three or more types of fin-based transistors on a single integrated circuit, where each type of transistor has a different gate structure. Typically, an integrated circuit having a plurality of different types of transistors will have a large number of instances of each type of transistor arranged in various formats (e.g., arrays). For simplicity, one instance of each type of transistor is shown in the figures as an isolated transistor, although the illustrated transistors are typically found in various places and arrangements on the integrated circuit chip in which they are located.

The integrated circuit shown in FIG. 2A has at least three different types of transistors, **201**, **202**, and **203** that are distinguished by the thickness or composition of the dielectric layers employed in the gate structure, according to an embodiment of the invention. In an embodiment, the gate structure in transistor **201** comprises a gate dielectric having high k dielectric layer **221** and a gate electrode having both a work function metal layer **231** and a fill metal **240**. Transistor **201** may be used for high performance processor cores. In an embodiment, the gate structure in transistor **202** comprises a gate dielectric having both a silicon dioxide layer **225** on the fin surface and high k dielectric layer **221** over silicon dioxide layer **225**. In an embodiment, transistor **202** further comprises a gate electrode having work function metal layer **231** and fill metal **240**. The addition of silicon dioxide layer **225** reduces leakage and increases the threshold voltage, as compared to transistor **201**, enabling use of transistor **202** for high-voltage input output (I/O) circuits or applications. In an embodiment, the gate structure of transistor **203** comprises a gate dielectric having both a high k dielectric layer **222** on fins **212** and high k dielectric layer

221 over high k layer **222**. In an embodiment, transistor **202** further comprises a gate electrode having both work function metal layer **231** and fill metal **240**. In an embodiment, high k dielectric layer **222** has a different composition than high k dielectric layer **221**. In another embodiment, high k dielectric layer **222** has a different thickness than high k dielectric layer **221**. The addition of high k dielectric layer **222** to the gate structure reduces leakage, as compared to transistor **201**, enabling use of transistor **203** for low-power circuits.

The integrated circuit illustrated in FIG. 2B has at least three different types of transistors, **201**, **202** and **204**, that are distinguished by the composition or thickness of the dielectric layers and/or the composition of the work-function metals employed in the transistor gate structure. In an embodiment, the gate structure in transistor **201** comprises a gate dielectric having high k dielectric layer **221** and a gate electrode having both a work function metal layer **231** and a fill metal **240**. Transistor **201** is designed to be used for high performance processor cores. In an embodiment, the gate structure in transistor **202** comprises a gate dielectric having both a silicon dioxide layer **225** on fins **212** and high k dielectric layer **221** on silicon dioxide layer **225**. In an embodiment, transistor **202** further comprises both a gate electrode having work function metal layer **231** and fill metal **240**. The addition of silicon dioxide layer **225** reduces leakage and increases the threshold voltage, as compared to transistor **201**, enabling use of transistor **202** for high-voltage input output (I/O) circuits or applications. In an embodiment, the gate structure of transistor **204** comprises a gate dielectric having high k dielectric layer **221** and a gate electrode having a work function metal layer **232**, work function metal layer **231** on work function metal layer **232**, and fill metal **240**. In an embodiment, work function metal **232** has a different work function than work function metal layer **231**. The addition of work function metal layer **232** reduces leakage, as compared to transistor **201**, enabling use of transistor **204** for low power circuits or applications.

Circuits comprising at least four types of fin-based transistors, where each type of transistor has a different gate structure, are illustrated in FIGS. 3A-C, according to embodiments of the invention. The embodiments comprising four types of transistor gate structures, as illustrated in FIGS. 3A-B, are extensions of the three-type transistor embodiments illustrated in FIGS. 2A-B, and may be fabricated without incurring additional processing steps.

The integrated circuit shown in FIG. 3A has at least four different types of transistors, **301**, **302**, **303** and **305** that are distinguished by the thickness or composition of the dielectric layers employed in the gate structure. In an embodiment, the gate structure in transistor **301** comprises a gate dielectric having a high k dielectric layer **321**, and a gate electrode having both a work function metal layer **331** and a fill metal **340**. Transistor **301** is designed to be used for high performance processor cores. In an embodiment, the gate structure in transistor **302** comprises a gate dielectric having both a silicon dioxide layer **325** grown on fins **312** and high k dielectric layer **321** over the silicon dioxide layer **325**. In an embodiment, transistor **302** further comprises a gate electrode having both work function metal layer **331** and fill metal **340**. Transistor **302** is designed to be used for high-voltage input output (I/O) circuits. In an embodiment, the gate structure in transistor **303** comprises a gate dielectric having both a high k dielectric layer **322** on the fin surface and high k dielectric layer **321** over high k dielectric layer **322**, and a gate electrode having both work function metal layer **331** and fill metal **340**. In an embodiment, the com-

position of high k dielectric layer **322** is different than that of high k dielectric layer **321**. In another embodiment, the thickness of high k dielectric layer **322** is different than that of high k dielectric layer **321**. Transistor **303** is designed to be used for low-power circuits.

In an embodiment, the gate structure of transistor **305** comprises a gate dielectric having silicon dioxide layer **325** on the fins, high k dielectric layer **322** over silicon dioxide layer **325**, and high k dielectric layer **321** over high k dielectric layer **322**. In an embodiment, high k dielectric layer **322** has a different composition than that of high k dielectric layer **321**. In another embodiment, high k dielectric layer **322** has a different thickness than that of high k dielectric layer **321**. In an embodiment, transistor **305** further comprises a gate electrode having work function metal layer **331** and fill metal **340**. As compared to the high-performance gate structure in transistor **301**, the additions of silicon dioxide layer **325** and high k dielectric layer **322** increase the threshold voltage of transistor **305**, such that transistor **305** may be used for circuits requiring extremely high voltages.

Another embodiment of a circuit having multiple types of transistors is illustrated by FIG. **3B**. The integrated circuit has at least four types different transistors, **301**, **302**, **304** and **306**, that are distinguished at least by the thickness or composition of the dielectric layers and/or the composition of the work function metals employed in the gate structure. In an embodiment, the gate structure in transistor **301** comprises a gate dielectric having a high k dielectric layer **321** and a gate electrode having both a work function metal layer **331** and a fill metal **340**. Transistor **301** is designed to be used for high performance processor cores. In an embodiment, the gate structure in transistor **302** comprises a gate electrode having both a silicon dioxide layer **325** grown on fins **312** and high k dielectric layer **321** over silicon dioxide layer **325**. In an embodiment, transistor **302** further comprises a gate electrode having both work function metal layer **331** and fill metal **340**. Transistor **302** is designed to be used for high-voltage input output (I/O) circuits. In an embodiment, the gate structure in transistor **304** comprises gate dielectric having a high k dielectric layer **321** and a gate electrode having a work function metal layer **332** layer, work function metal **331** layer over the work function metal layer **332** layer, and fill metal **340**. In an embodiment, work function metal layer **332** has a different work function than work function metal **331**. Transistor **304** is designed to be used for low-power circuits.

In an embodiment, the gate structure in transistor **306** comprises a gate dielectric having both silicon dioxide layer **325** grown on fins **312** and high k dielectric layer **321** over silicon dioxide layer **325**. In an embodiment, transistor **306** further comprises a gate electrode having work function metal layer **332**, work function metal layer **331** over work function metal layer **332**, and fill metal **340**. In an embodiment, work function metal layer **332** has a different work function than work function metal layer **331**. As compared to the high-performance gate structure in transistor **301**, the additions of silicon dioxide layer **325** and work function metal layer **332** increase the threshold voltage of transistor **306**, such that transistor **306** may be used for circuits requiring extremely high voltages.

With respect to the previously described embodiments, it should be noted that it is also possible to vary other device characteristics such as the width of the gate, the width of the channel region, and the types of sources and drains used to achieve specific transistor properties, as is understood by those of skill in the art.

In manufactured devices, layers of materials can deviate in appearance from the simplified illustrations provided herein for clarity, and can be, for example, slightly thicker or thinner in areas. Additionally, what is described here as a “layer” of material may be made up of a plurality of layers of the material that essentially function as one layer.

FIGS. **4A-I** describe an embodiment of a method for the formation of multiple types of fin-based transistor gate structures. The method is useful for forming integrated circuits comprising different types of fin-based transistors on the same chip, wherein the transistors have at least two different gate dielectric structures. An integrated circuit chip typically comprises multiple copies of the same transistor in various locations on the substrate, however, one of each type of transistor is shown in FIGS. **4A-I** for clarity.

A substrate **410** having fins **412** is provided. In an embodiment of the invention, fins **412** are formed from a bulk monocrystalline substrate. Substrate **410** and fins **412** can be formed of any well known semiconductor material, such as but not limited to silicon, germanium, silicon germanium, and III-V combinations including GaAs, InSb, GaP, and GaSb. The lower portions of fins **412** are separated by isolation regions **414** to prevent leakage from the fins, as shown in FIG. **4A**. In an embodiment, isolation regions **414** comprise a dielectric material such as silicon dioxide. In another embodiment, fins **412** are formed from a semiconductor-on-insulator (SOI) substrate comprising a lower bulk substrate, a middle insulation layer, and a top monocrystalline layer. Fins **412** are formed from the top monocrystalline layer, and the middle insulation layer forms an isolation region. The height of fins **412** extending above isolation regions **414** range from 20 to 100 Å. The width of fins **412** range from 5 to 20 Å.

Next, silicon dioxide layer **425** is formed on the surface of fins **412** extending above isolation regions **414**. In an embodiment, silicon dioxide layer **425** will form a portion of the gate dielectric for the transistor formed on gate region **492**. In an embodiment, silicon dioxide layer **425** will subsequently be removed from gate region **491** prior to forming additional gate structure components. In a specific embodiment, silicon dioxide layer **425** is grown from the surfaces of fins **412**. In another specific embodiment, silicon dioxide layer **425** is blanket deposited by any method that enables conformal deposition on the fins **412** in the gate regions, such as chemical vapor deposition (CVD) or atomic layer deposition (ALD). Silicon dioxide layer **425** may be grown or deposited to a uniform thickness. In an embodiment, silicon dioxide layer **425** is 30 Å thick.

The subsequent etching process to remove silicon dioxide layer **425** from gate region **491** involves two sacrificial layers that protect portions of silicon dioxide layer **425** that will form active components of the device formed in gate region **492**. In an embodiment of the invention, an embedded etch stop layer **442** is blanket deposited over the surface of the substrate, and a sacrificial silicon dioxide layer **443** is conformally formed over embedded etch stop layer **442**. In an embodiment of the invention, embedded etch stop layer **442** and sacrificial silicon dioxide layer **443** will not form active components of the transistors. Embedded etch stop layer **442** and silicon dioxide layer **443** may each be deposited by any method suitable for forming a conformal layer, such as CVD or ALD. In an embodiment, embedded etch stop layer **442** is a material that is etched at a slower rate as compared to that of silicon dioxide when both are etched by a selected etch chemistry. In an embodiment, embedded etch stop layer **442** is silicon nitride.

Both embedded etch stop layer **442** and silicon dioxide layer **443** are each formed to a uniform thickness. The thicknesses of the embedded etch stop layer **442** and silicon dioxide layer **443** are each selected such that a timed etch will remove each layer in approximately the same time. In an embodiment, an HF etching process is used. HF etches silicon dioxide at a faster rate than silicon nitride, and therefore, in an embodiment, sacrificial silicon dioxide layer **443** is thicker than embedded etch stop layer **442**. In an embodiment, sacrificial silicon dioxide layer **443** is the same thickness as silicon dioxide layer **425**. In an embodiment, embedded etch stop layer **442** is 10 Å thick. In an embodiment, silicon dioxide layer **443** is 30 Å thick.

Next, sacrificial silicon dioxide layer **443** is removed from the surface of gate region **491** using a photolithographic etch process. In an embodiment, a photoresist material is formed over the structure surface. The photoresist is photolithographically patterned so that photoresist **455** covers gate region **492**, as shown in FIG. 4C, where a gate structure comprising silicon dioxide layer **425** will subsequently be formed. The exposed portion of silicon dioxide layer **443** is then etched from gate structure **491**. Silicon dioxide layer **443** may be etched by any suitable etching process, such as a wet etch. The wet etch comprises, for example, HF. The HF etch may have a concentration from 50:1-200:1. In an embodiment, silicon dioxide layer **443** is fully or nearly fully etched from the surface of gate region **491** in 50 seconds.

After the etching of silicon dioxide layer **443**, photoresist **455** is removed from the structure surface, as shown in FIG. 4D. In general, photoresists are removed by well known processes in the semiconductor industry. Photoresists can be removed, for example, through dry plasma processes. The resist is removed in an oxygen plasma processes, frequently called ashing, designed to remove organic residues. The plasma is generated, for example, by microwave, RF (radio frequency), or UV ozone sources. Alternately, the photoresist can be removed using a solvent or mixture of solvents.

Next, sacrificial gate material **454** is blanket deposited over the structure surface, according to the embodiment illustrated in FIG. 4E. Sacrificial gate material **454** is formed to a thickness desired for the gate height. Sacrificial gate material **454** is then patterned and etched to form sacrificial gate structures **456** over gate regions **491** and **492**, so that active gate structures may subsequently be formed by a gate replacement process. Deposition, patterning, and etching of sacrificial gate material are well known in the semiconductor art. The sacrificial gate structures **456** are patterned into the same shape and at the same location where the subsequently formed gate electrode and gate dielectric are to be formed. In an embodiment of the present invention, the sacrificial gate electrode material is formed from a material such as silicon nitride or polysilicon. Following the formation of sacrificial gate structures **456**, fins **412** may be doped, for example, by tip implantation or halo implantation, as is well-known in the art.

Next, if desired, dielectric sidewall spacers **435** may be formed on the sidewalls of sacrificial gate structures **456**. Sidewall spacers are used to isolate the gate structure from epitaxial semiconductor material that may be grown on the source/drain regions of the fins, as shown in FIG. 1A, but spacer material may additionally form on other sidewalls of the gate structure, as shown in FIG. 4F. Sidewall spacers **435** can be formed by any well known technique, such as, for example, by blanket depositing a conformal sidewall spacer dielectric over the substrate, and then anisotropically etching to remove the dielectric spacer material from horizontal surfaces while leaving spacer material on vertical surfaces.

The spacers **453** may be silicon nitride, silicon oxide, silicon oxynitride, silicon carbide, CDO or a combination thereof. In an embodiment, an overetch is used to remove spacer material from the sidewalls of fins **412** to enable subsequent growth of an epitaxial layer on the fin surface, doping of the source/drain region, and/or formation of source/drain contacts.

Next, a dielectric material **450** is blanket deposited over the substrate. The dielectric material is formed to a thickness sufficient to completely cover the substrate including sacrificial gate structure **456**. The dielectric **450** is formed of a material that can be selectively etched with respect to the sacrificial gate material. That is, the dielectric is formed of a material whereby the sacrificial gate structure **456** can be removed without significantly etching away the dielectric **450**. After blanket deposition, the dielectric material **450** is planarized, such as by chemical mechanical planarization (CMP), until the top surface is planar with the sacrificial gate structure **456**.

The sacrificial gate structure **456** is then etched away to enable formation of the gate structures in gate regions **491** and **492**. Sacrificial gate structures **456** may be removed using a wet or dry etch process. The etch process exposes underlying embedded etch stop layer **442** surface on gate region **491** and underlying sacrificial silicon dioxide layer **443** surface on gate region **492**, as shown in FIG. 4G.

In an embodiment, an additional etch process removes embedded etch stop layer **442** and silicon dioxide layer **425** from gate region **491** and also sacrificial silicon dioxide layer **443** and embedded etch stop layer **442** from gate region **492**. In an embodiment, a selective etch is used. In another embodiment, a timed wet etch is used. In an embodiment, the timed wet etch may comprise HF. In a specific embodiment, the HF etches embedded etch stop layer **442** material at a faster rate over the sacrificial silicon dioxide **443** material. The etch process has, in an embodiment, a selectivity of 3:1. The HF etch may have a concentration from 50:1-200:1. Because the thickness of each sacrificial layer has been selected based on the rate at which HF etches the material, both embedded etch stop layer **442** and silicon dioxide layer **425** on gate region **491** are etched completely or nearly completely by the HF in the same amount of time that sacrificial silicon dioxide layer **443** and embedded etch stop layer **442** are etched by the HF from gate region **492**.

In an embodiment, silicon dioxide layer **425** remains on gate region **492**, where it will form part of the gate dielectric. As such, silicon dioxide layer **425** has been formed on gate region **492**, without being exposed photoresist, which may contaminate active device layers. This formation of a pristine silicon dioxide layer will improve the performance and reliability of the device over that of devices where active layers are patterned directly using a photolithography process.

Next, a high-k dielectric layer **421** is conformally deposited over the substrate surface to a uniform thickness according to an embodiment of the invention. In an embodiment, high k dielectric material **421** covers the top surface and sidewalls of fins **412** in gate region **491** and conforms to the silicon dioxide layer **425** surface on gate region **492**. In an embodiment, high k dielectric layer **421** will form part of the gate dielectric in the gate structures formed in both gate regions **491** and **492**. In an embodiment, the high k dielectric material is formed by a conformal process, such as CVD or ALD, to ensure contact with the fin surfaces in gate region **491** and the underlying silicon dioxide layer **425** in gate region **492**. High k dielectric layer **421** may be any suitable high k dielectric material, such as described above with

respect to high k dielectric layer **121** in FIG. 1A. High k dielectric layer **421** may be from 10 to 50 Å thick. In an embodiment, high k dielectric material **421** is 30 Å thick.

Next, a gate electrode is formed in each gate region, over the gate dielectric. The gate electrode may comprise one or more work function metal layers and a fill metal. In an embodiment, work function metal **431** is conformally deposited over the substrate to a uniform thickness. Work function metal **431** sets the work function for the device, and minimizes resistance at the metal-semiconductor interface between the gate dielectric and the gate electrode. Work function metal **431** is formed by a conformal process, such as CVD or ALD to ensure contact with the underlying high k dielectric layer **421** in both gate regions **491** and **492**. Work function metal layer **431** may be any suitable work function metal, such as described above with respect to work function metal layer **131** in FIG. 1A. Work function metal layer **431** may be from 10 to 50 Å thick. In an embodiment, work function metal layer **431** is 30 Å thick.

A fill metal **440** is then blanket deposited over work function metal **431** to a thickness sufficient to fill the gate structure openings in gate regions **491** and **492**. Metal gate **440** may be formed by any suitable process, such as CVD, ALD, or physical vapor deposition (PVD). The metal gate material may be any suitable gate electrode material, such as described above with respect to FIG. 1A.

The metal gate **440**, work function material **431**, and high k dielectric layer **421** are then chemically mechanically planarized until the top surface of the dielectric layer **450** is revealed as shown in FIG. 4I. Once the gate electrode material and gate dielectric material are polished back or removed from the top dielectric material **450**, a gate structure has been formed.

Thus, two transistors **401** and **402** are formed, each with a different gate structure. In an embodiment, Transistor **401** comprises a gate dielectric having a high-k material **421** and a gate electrode having both a work function metal **431** and fill metal **440**. Transistor **401** may be used for high-performance processor cores. In an embodiment, transistor **402** comprises a gate dielectric having both a silicon dioxide layer **425** and high k dielectric layer **421** and a gate electrode having work function metal layer **431** and fill metal **440**. The addition of silicon dioxide layer **425** to the gate dielectric, as compared to the gate dielectric of transistor **401**, enables use of transistor **402** for high voltage input-output (I/O) circuits or applications.

FIGS. 5A-I illustrate another method for forming integrated circuits comprising two types of transistors that have different gate structures. An integrated circuit chip typically comprises multiple copies of the same transistor in various locations, however, one of each type of transistor is shown in FIGS. 5A-I for clarity.

A substrate **510** having fins **512** is provided, as shown in FIG. 5A. In an embodiment, substrate **510** and fins **512** are monocrystalline silicon. Fins **512** are separated by isolation regions **514**, which may comprise a dielectric material such as, for example, silicon dioxide. Methods for forming the structure shown in FIG. 5A are known in the art of semiconductor manufacturing.

Next, silicon dioxide layer **525** is formed on the surface of the structure. In an embodiment of the invention, silicon dioxide layer **525** will form part of the gate structure subsequently formed in gate region **592**. In a specific embodiment, silicon dioxide layer **525** is grown from the surfaces of fins **512**. In another specific embodiment, silicon dioxide layer **525** is deposited by any method that enables conformal deposition on the horizontal and vertical surfaces

of the gate region, such as CVD or ALD. In an embodiment, silicon dioxide layer **525** is 30 Å thick.

Sacrificial gate structures are then formed so that active gate structures may subsequently be formed by a gate replacement process, according to an embodiment of the invention. In an embodiment, sacrificial gate material **554** is blanket deposited over silicon dioxide layer **525**, as shown in FIG. 5B. Sacrificial gate material **554** is formed to a thickness desired for the gate height. Sacrificial gate material **554** is then patterned and etched to form sacrificial gate structures **556** over gate regions **591** and **592**. Deposition, patterning, and etching of sacrificial gate material are well known in the semiconductor art. The sacrificial gate structures **556** are patterned into the same shape and at the same location where the subsequently formed gate electrode and gate dielectric are to be formed. In an embodiment of the present invention, sacrificial gate structure **556** is formed from a material such as silicon nitride or polysilicon. Following the formation of sacrificial gate structures **556**, fins **512** may be doped, for example, by tip implantation or halo implantation, as is well-known in the art.

Next, if desired, dielectric sidewall spacers **535** may be formed on the sidewalls of sacrificial gate structures **556**. Sidewall spacers are used to isolate the gate structure from epitaxial semiconductor material that may be grown on the source/drain regions of the fins, as shown in FIG. 1A, but spacer material may additionally form on other sidewalls of the gate structure, as shown in FIG. 5C. Sidewall spacers **535** can be formed by any well known technique, such as, for example, by blanket depositing a conformal sidewall spacer dielectric over the substrate, and then anisotropically etching to remove the dielectric spacer material from horizontal surfaces while leaving spacer material on vertical surfaces. The spacers **535** may be silicon nitride, silicon oxide, silicon oxynitride, silicon carbide, CDO or a combination thereof. In an embodiment, an overetch is used to remove spacer material from the sidewalls of fins **512** to enable subsequent growth of an epitaxial layer on the fin surface, doping of the source/drain region, and/or formation of source/drain contacts.

Next, a dielectric material **550** is blanket deposited over the substrate. The dielectric layer is formed to a thickness sufficient to completely cover the substrate including sacrificial gate structure **556**. The dielectric layer **550** is formed of a material that can be selectively etched with respect to the sacrificial gate material. That is, the dielectric material is formed of a material whereby the sacrificial gate structure **556** can be removed without significantly etching away the dielectric layer **550**. After blanket depositing the dielectric, the dielectric layer is planarized, for example, by CMP, until the top surface of the dielectric film is planar with the sacrificial gate structure **556**.

Next, the sacrificial gate structures **556** are etched away to enable formation of gate structures within gate regions **591** and **592**. Sacrificial gate structures **556** may be etched using a wet or dry etch process. Etching sacrificial gate structures **556** exposes silicon dioxide layer **525** within gate regions **591** and **592**, as shown in FIG. 5D. In an embodiment, the gate dielectric formed in gate region **592** will comprise silicon dioxide layer **525**, but the gate structure formed in gate region **592** will not comprise silicon dioxide layer **525**. Thus, silicon dioxide layer **525** is subsequently patterned to remove the portion within gate region **591**, while protecting the portions within gate region **592**. In another specific embodiment of the invention, all exposed portions of silicon dioxide layer **525** are etched away from the surface, and a fresh silicon dioxide layer is either grown from the fins or

deposited over the substrate, in order to have pristine silicon dioxide with which to form active components of a subsequently formed gate structure.

A hardmask **534** is then blanket deposited over silicon dioxide layer **525**, as illustrated in FIG. **5E**. In an embodiment, hardmask **534** will protect the portion of silicon dioxide layer **525** within gate region **592** from exposure to photoresist during etching of the portion of silicon dioxide layer **525** within gate region **591**. Hardmask **534** may comprise, for example, a work function metal resistant to etching by HF, such as, but not limited to titanium nitride, tungsten nitride, and tantalum nitride. In an embodiment, hardmask **534** is formed by ALD. Hardmask **534** is formed to a uniform thickness sufficient to protect underlying materials during the subsequent etching processes, from 10 to 50 Å thick. In an embodiment, hardmask **534** is 30 Å thick.

Next, hardmask **534** is patterned to remove the portion covering silicon dioxide layer **525** within gate region **591**, as shown in FIG. **5F**. In an embodiment, hardmask **534** is patterned by a photolithography process. In an embodiment, a photoresist layer **555** is deposited and patterned such that hardmask **534** on gate region **592** is covered by photoresist. In an embodiment, hardmask **534** is then etched from regions not covered by the photoresist, exposing the underlying silicon dioxide layer **525** on gate region **591**. In an embodiment, hardmask **534** is etched using a wet etch process which is highly selective to the underlying oxide, such as peroxide and sulfuric acid.

Next, the photoresist layer **545** is removed, leaving hardmask **534** on gate region **592**. In an embodiment, silicon dioxide layer **525** is then etched from gate region **591**. By removing photoresist layer **545** prior to etching silicon dioxide layer **525**, the etching bath used to etch silicon dioxide layer **525** is not contaminated by the photoresist material. In an embodiment, etching silicon dioxide layer **525** over gate region **591** exposes the surfaces of fins **512** and isolation regions **514** in gate region **591**. Any etch selective to the hardmask material over silicon dioxide may be used to etch silicon dioxide layer **525**. In an embodiment, silicon dioxide layer **525** is etched using HF. In an embodiment, hardmask **534** is then removed from gate region **592** to expose silicon dioxide layer **525**, as shown in FIG. **5H**. In an embodiment, hardmask **534** is removed by a wet etch process, such as peroxide and sulfuric acid.

The gate structure is then formed by depositing additional gate dielectric layers and gate electrode materials. In an embodiment, a high k dielectric layer **521** is conformally deposited over the substrate, covering the top surface and sidewalls of the fins in gate region **591** and conforming to the silicon dioxide layer **525** surface on gate region **592**. The high k dielectric material is formed by a conformal process, such as CVD or ALD, to ensure contact with the fins in gate region **591** or with underlying first silicon dioxide layer **525** in gate region **592**. High k dielectric layer **521** may be any suitable high k dielectric material, such as described above with respect to high k dielectric layer **121** in FIG. **1A**. High k dielectric layer **521** may be from 10 to 50 Å thick. In an embodiment, high k dielectric material **521** is 30 Å thick.

Next, the gate electrodes are formed. Each gate electrode may comprise one or more work function metal layers and a fill metal. In an embodiment, work function metal **531** is conformally deposited over the substrate. Work function metal **531** is formed by a conformal process, such as CVD or ALD to ensure contact with underlying high k dielectric layer **521**. Work function metal layer **531** may be any suitable work function metal, such as described above with respect to work function metal layer **131** in FIG. **1A**. Work

function metal layer **531** may be from 10 to 50 Å thick. In an embodiment, work function metal layer **531** is 30 Å thick.

Next, the fill metal **540** material is blanket deposited over work function metal **531** to a thickness sufficient to fill the gate structure openings within gate regions **591** and **592**. Fill metal **540** may be formed by any suitable process, such as CVD, ALD, or PVD. The fill metal material may be any suitable gate electrode material, such as described above with respect to fill metal **140** in FIG. **1A**.

The fill metal **540**, work function material **531**, and high k dielectric layer **521** are then chemically mechanically planarized until the top surface of the dielectric layer **550** is revealed as shown in FIG. **5I**. Once the gate electrode material and gate dielectric material are polished back or removed from the top dielectric material **550**, a gate structure has been formed.

Thus, two transistors **501** and **502** are formed, each with a different gate structure. In an embodiment, transistor **501** comprises a gate dielectric having high k dielectric material **521** and a gate electrode having both work function metal **531** and fill metal **540**. The gate structure of transistor **501** may be used for high-performance processor cores. In an embodiment, transistor **502** comprises a gate dielectric having a silicon dioxide layer **525** and high k dielectric layer **521** over silicon dioxide layer **525**, and a gate electrode having both work function metal **531** and fill metal **540**. As compared to transistor **501**, the additional silicon dioxide material in the gate dielectric of transistor **502** enables use for high voltage input-output (I/O) circuits.

FIGS. **6A-G** provide an additional embodiment of a method for forming integrated circuits comprising two types of transistors, where each transistor type has a different gate dielectric structure. An integrated circuit chip typically comprises multiple copies of the same transistor in various locations, however, one of each type of transistor is shown in FIGS. **6A-G** for clarity.

A structure comprising substrate **610** with fins **612** separated by isolation regions **614** and gate structure openings above the fins defined by a dielectric **650** having spacers **635** is provided. Methods for forming the structure are known in the art of semiconductor manufacturing. The structure may be formed, for example, by first following the process shown in FIGS. **5A-5D** and described above, and then removing the portions of the silicon dioxide layer **625** that cover gate regions **691** and **693**, as shown in FIG. **6A**. In an embodiment, silicon dioxide layer **625** is removed from gate regions **691** and **693** by wet or dry etch.

Next, a high k dielectric layer **622** is blanket deposited over the substrate. High k dielectric material **622** is formed by a conformal process, such as CVD or ALD, to ensure contact with the fins in each gate region. In an embodiment, high k dielectric layer **622** will form part of the gate dielectric for the transistor formed in gate region **693**. In an embodiment, high k dielectric layer **622** will be removed from gate region **691**. High k dielectric layer **622** may be any suitable high k dielectric material, such as described above with respect to high k dielectric layer **122** in FIG. **1B**. High k dielectric layer **622** may be from 10 to 50 Å thick. In an embodiment, high k dielectric material **622** is 30 Å thick.

A hardmask **634** is then blanket deposited over high k dielectric layer **622**, as illustrated in FIG. **6B**. In an embodiment, hardmask **634** will protect the portion of high k dielectric layer **622** within gate region **693** from exposure to photoresist during the subsequent etching of high k dielectric layer **622** from gate region **691**. Hardmask **634** may comprise, for example, a work function metal resistant to etching by HF, such as, but not limited to titanium nitride,

tungsten nitride, and tantalum nitride. In an embodiment, hardmask 634 is formed by ALD. Hardmask 634 is formed to a uniform thickness sufficient to protect underlying materials during the subsequent etching processes, from 10 to 50 Å thick. In an embodiment, hardmask 634 is 30 Å thick.

Next, hardmask 634 is patterned to remove the portion covering high k dielectric layer 622 within gate region 691, as shown in FIG. 6C. In an embodiment, hardmask 634 is patterned by a photolithography process. In an embodiment, a photoresist layer 655 is deposited and patterned such that hardmask 634 on gate region 693 is covered by photoresist. Hardmask 634 is then etched to expose high k dielectric layer 622 in gate region 691. In an embodiment, hardmask 634 is etched using a wet etch process that is highly selective to the underlying oxide, such as peroxide and sulfuric acid.

The photoresist layer 655 is then removed, leaving hardmask 634 on gate region 693. The exposed portion of high k dielectric layer 622 over gate region 691 is then etched to expose the surfaces of fins 612 and isolation regions 614 in gate region 691, as shown in FIG. 6D. By removing photoresist layer 655 prior to etching high k dielectric layer 622 on gate region 691, the etching bath used to etch high k dielectric layer 622 is not contaminated by the photoresist material. Any etch selective to the hardmask material over the high k dielectric material may be used to etch high k layer 622. In an embodiment, high k dielectric layer 622 is etched using HF. In an embodiment, hardmask 634 is then removed from gate region 693 to expose the surface of high k dielectric layer 622, as shown in FIG. 6E. In an embodiment, hardmask 634 is removed by a wet etch process, such as peroxide and sulfuric acid.

Next, a high k dielectric layer 621 is conformally deposited over the structure. In an embodiment, high k dielectric layer 621 will form part of the gate dielectric for each of the transistors formed in gate regions 691 and 693. In gate region 691, high k dielectric material 621 covers the fins 612 and isolation regions 614 within the gate structure opening, and in gate region 693, high k dielectric layer 621 conforms to high k dielectric layer 622. High k dielectric material 621 is formed by a conformal process, such as CVD or ALD, to ensure contact with underlying materials in the gate region. In an embodiment, high k dielectric layer 621 has a different composition than high k dielectric layer 622. In another embodiment, high k dielectric layer 621 has a different thickness than high k dielectric layer 622. High k dielectric layer 621 comprises a high k dielectric material such as described above with respect to high k dielectric layer 121 in FIG. 1A. High k dielectric layer 621 may be from 10 to 50 Å thick. In an embodiment, high k dielectric material 621 is 30 Å thick.

Next, a gate electrode is formed. The gate electrode may comprise one or more work function metal layers and a fill metal. In an embodiment, work function metal layer 631 is deposited over the substrate to a uniform thickness. Work function metal layer 631 is formed by a conformal process, such as CVD or ALD, to ensure contact with underlying high k dielectric layer 621. Work function metal layer 631 may be any suitable work function metal, such as described above with respect to work function metal layer 131 in FIG. 1A. Work function metal layer 631 may be from 10 to 50 Å thick. In an embodiment, work function metal layer 631 is 30 Å thick.

Next, the fill metal 640 is blanket deposited over work function metal 631 to a thickness sufficient to fill the gate structure openings over gate regions 691 and 693. Fill metal 640 may be formed by any suitable process, such as CVD,

ALD, or PVD. The fill metal may be any suitable gate electrode material, such as described above with respect to fill metal 140 in FIG. 1A.

The fill metal 640, work function material 631, high k dielectric layer 621 and high k dielectric layer 622 are then chemically mechanically planarized until the top surface of the dielectric layer 650 is revealed as shown in FIG. 6G. Once the gate electrode materials and gate dielectric materials are polished back or removed from the top of dielectric material 650, a gate structure has been formed.

Thus, two different transistors 601 and 603 are formed, each with a different gate structure. In an embodiment, transistor 601 comprises a gate dielectric having high k material 621 and a gate electrode having work function metal 631 and fill metal 640. The gate structure of transistor 601 enables use for high-performance processor cores. In an embodiment, transistor 603 comprises a gate dielectric having a high k dielectric layer 622 and high k dielectric layer 621, and a gate electrode having work function metal layer 631 and fill metal 640. The dual high k materials enable use of transistor 603 for low-power circuits or applications.

FIGS. 7A-E provide an additional embodiment of a method for forming integrated circuits comprising two types of transistors, where each transistor type has a different gate electrode structure. An integrated circuit chip typically comprises multiple copies of the same transistor in various locations, however, one of each type of transistor is shown in FIGS. 7A-E for clarity.

A structure comprising substrate 710 with fins 712 separated by isolation regions 714 and gate structure openings above the fins, defined by dielectric material 750 and spacers 735 is provided. Methods for forming the structure are known in the art of semiconductor manufacturing. The structure may be formed, for example, by first following the process shown in FIGS. 5A-5D and described above, and then removing the portions of the silicon dioxide layer 725 that cover gate regions 791 and 794, as shown in FIG. 7A.

Next, portions of the gate structures are formed by depositing a gate dielectric layer in gate regions 791 and 794. A high k dielectric layer 721 is blanket deposited on the structure surface, as illustrated in FIG. 7B, covering fins 712 and isolation regions 714 within gate regions 791 and 794. The high k dielectric material 721 is formed by a conformal process, such as CVD or ALD, to ensure uniform formation on the surface of fins 712. High k dielectric layer 721 comprises a high k dielectric material such as described above with respect to high k dielectric layer 121 in FIG. 1A. High k dielectric layer 721 may be from 10 to 50 Å thick. In an embodiment, high k dielectric material 721 is 30 Å thick.

Next, work function metal 732 is blanket deposited over the structure, as shown in FIG. 7B. In an embodiment, work function metal layer 732 will form part of the gate electrode for the transistor gate structure formed in gate region 794. In an embodiment, work function metal layer 732 will be subsequently removed from gate region 791. In an embodiment, work function metal 732 conforms to the surface of high k dielectric material 721. The work function metal may be deposited by a conformal process, such as CVD or ALD. Work function metal layer 732 may be any suitable work function metal, such as described above with respect to FIG. 1A. In an embodiment, work function metal layer 732 is nitridized after deposition to alter the work function of the material. Work function metal layer 732 may be from 10 to 50 Å thick. In an embodiment, work function metal layer 732 is 30 Å thick.

Work function metal layer **732** is then patterned to remove the portion within gate region **791**. In an embodiment, work function layer **732** is patterned using photolithography. In an embodiment, photoresist layer **755** is deposited and patterned such that the portion of work function metal layer **732** in gate region **794** is covered by photoresist. In an embodiment, work function metal layer **732** is then etched away from gate region **791** to expose the underlying high k dielectric material **721**, as shown in FIG. 7C. Work function metal layer **732** may be etched with either a dry etch or a wet etch process.

Next, photoresist **755** is removed and work function metal layer **731** is blanket deposited over the substrate. Work function metal layer **731** is formed by a conformal process, such as CVD or ALD to ensure contact with the underlying high k dielectric layer **721** on gate region **791** and the work function metal layer **732** on gate region **794**. Work function metal layer **731** may be any suitable work function metal, such as described above with respect to FIG. 1A. In an embodiment, work function metal **731** has a different work function than work function metal layer **732**. Work function metal layer **731** may be from 10 to 50 Å thick. In an embodiment, work function metal layer **731** is 30 Å thick.

Next, fill metal **740** is blanket deposited over work function metal **731** to a thickness sufficient to fill the gate structure openings over gate regions **791** and **794**. Fill metal **740** may be formed by any suitable process, such as CVD, ALD, or PVD. The fill metal may be any suitable gate electrode material, such as described above with respect to FIG. 1A.

Fill metal **740**, work function metal **731**, work function metal **732**, and high k dielectric layer **721** are then chemically mechanically planarized until the top surface of the dielectric **750** is revealed as shown in FIG. 7E. Once the gate electrode materials and gate dielectric materials are polished back or removed from the top dielectric material **750**, a gate structure has been formed.

Thus, two different transistors **701** and **704** are formed, each with a different gate structure. In an embodiment, the gate structure of transistor **701** comprises a gate dielectric having high k material **721** and a gate electrode having both work function metal layer **731** and fill metal **740**. Transistor **701** may be used for high-performance processor cores. In an embodiment, the gate structure of transistor **704** comprises a gate dielectric having high k material **721** and a gate electrode having work function metal **732**, work function metal **731**, and fill metal **740**. Transistor **704** may be used in low-power circuits or applications.

The above processes, as described with reference to FIGS. 4A-I, 5A-I, 6A-G, and 7A-E can be used in combination to form integrated circuits with three or more types of transistors, each having a different gate structure.

FIG. 8 illustrates a computing device **800** in accordance with one implementation of the invention. The computing device **800** houses a board **802**. The board **802** may include a number of components, including but not limited to a processor **804** and at least one communication chip **806**. The processor **804** is physically and electrically coupled to the board **802**. In some implementations the at least one communication chip **806** is also physically and electrically coupled to the board **802**. In further implementations, the communication chip **806** is part of the processor **804**.

Depending on its applications, computing device **800** may include other components that may or may not be physically and electrically coupled to the board **802**. These other components include, but are not limited to, volatile memory (e.g., DRAM), non-volatile memory (e.g., ROM), flash

memory, a graphics processor, a digital signal processor, a crypto processor, a chipset, an antenna, a display, a touchscreen display, a touchscreen controller, a battery, an audio codec, a video codec, a power amplifier, a global positioning system (GPS) device, a compass, an accelerometer, a gyroscope, a speaker, a camera, and a mass storage device (such as hard disk drive, compact disk (CD), digital versatile disk (DVD), and so forth).

The communication chip **806** enables wireless communications for the transfer of data to and from the computing device **800**. The term “wireless” and its derivatives may be used to describe circuits, devices, systems, methods, techniques, communications channels, etc., that may communicate data through the use of modulated electromagnetic radiation through a non-solid medium. The term does not imply that the associated devices do not contain any wires, although in some embodiments they might not. The communication chip **806** may implement any of a number of wireless standards or protocols, including but not limited to Wi-Fi (IEEE 802.11 family), WiMAX (IEEE 802.16 family), IEEE 802.20, long term evolution (LTE), Ev-DO, HSPA+, HSDPA+, HSUPA+, EDGE, GSM, GPRS, CDMA, TDMA, DECT, Bluetooth, derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond. The computing device **800** may include a plurality of communication chips **806**. For instance, a first communication chip **806** may be dedicated to shorter range wireless communications such as Wi-Fi and Bluetooth and a second communication chip **806** may be dedicated to longer range wireless communications such as GPS, EDGE, GPRS, CDMA, WiMAX, LTE, Ev-DO, and others.

The processor **804** of the computing device **800** includes an integrated circuit die packaged within the processor **804**. In some implementations of the invention, the integrated circuit die of the processor includes two or more fin-based transistors in accordance with implementations of the invention. The term “processor” may refer to any device or portion of a device that processes electronic data from registers and/or memory to transform that electronic data into other electronic data that may be stored in registers and/or memory.

The communication chip **806** also includes an integrated circuit die packaged within the communication chip **806**. In accordance with another implementation of the invention, the integrated circuit die of the communication chip includes two or more fin-based transistors in accordance with implementations of the invention.

In further implementations, another component housed within the computing device **800** may contain an integrated circuit die that includes two or more fin-based transistors in accordance with implementations of the invention.

In various implementations, the computing device **800** may be a laptop, a netbook, a notebook, an ultrabook, a smartphone, a tablet, a personal digital assistant (PDA), an ultra mobile PC, a mobile phone, a desktop computer, a server, a printer, a scanner, a monitor, a set-top box, an entertainment control unit, a digital camera, a portable music player, or a digital video recorder. In further implementations, the computing device **800** may be any other electronic device that processes data.

What is claimed is:

1. A device comprising:

a substrate having a plurality of semiconductor fins;
a first transistor having a first gate structure that wraps around a first semiconductor fin, wherein the first gate structure comprises a first gate dielectric structure in direct contact with the first semiconductor fin and a first

gate electrode structure comprising a first metal layer, the first metal layer in direct contact with the first gate dielectric structure, wherein the first gate dielectric structure comprises a first gate dielectric layer and a second gate dielectric layer on the first gate dielectric layer, the first transistor having a first pair of n type doped source/drain regions on opposite sides of the first gate structure; and

a second transistor isolated from the first transistor, the second transistor having a second gate structure that wraps around a second semiconductor fin wherein the second gate structure comprises a second gate dielectric structure in direct contact with the second semiconductor fin and a second gate electrode structure comprising a second metal layer, the second metal layer in direct contact with the second gate dielectric structure, the second transistor having a second pair of n type doped source/drain regions on opposite sides of the second gate structure, wherein the second gate dielectric structure comprises the second gate dielectric layer but not the first gate dielectric layer, wherein the second gate dielectric structure is different in composition from the first gate dielectric structure, and wherein the second gate electrode structure is different in composition than the first gate electrode structure.

2. The device of claim 1 wherein the first gate dielectric layer comprises silicon dioxide and wherein the second gate dielectric layer is a first high k dielectric layer.

3. The device of claim 1 wherein the first semiconductor fin comprises the same semiconductor material as the second semiconductor fin.

4. A device comprising:

a substrate having a plurality of semiconductor fins, the semiconductor fins comprising a semiconductor material;

a first transistor having a first gate structure that wraps around one or more of the semiconductor fins, wherein the first gate structure comprises a first gate dielectric structure in direct contact with the semiconductor material of a top surface of the one or more semiconductor fins that the first gate structure wraps around and a first gate electrode structure comprising a first work function metal layer, the first work function metal layer in direct contact with the first gate dielectric structure, the first transistor having a first pair of n type doped source/drain regions on opposite sides of the first gate structure, wherein the first gate dielectric structure comprises a first high k dielectric layer and wherein the first gate electrode structure comprises the first work function metal layer and a fill metal; and

a second transistor isolated from the first transistor, the second transistor having a second gate structure that wraps around one or more of the semiconductor fins, wherein the second gate structure comprises a second gate dielectric structure in direct contact with the semiconductor material of a top surface of the one or more semiconductor fins which the second gate structure wraps around and a second gate electrode structure comprising a second work function metal layer, the second work function metal layer in direct contact with the second gate dielectric structure, the second transistor having a second pair of n type doped source/drain regions on opposite sides of the second gate structure, wherein the second gate dielectric structure is different in composition from the first gate dielectric structure along the top surface and sidewalls of the corresponding one or more of the semiconductor fins, and wherein

the second gate electrode structure is different in composition than the first gate electrode structure, wherein the second gate electrode structure comprises the first work function metal layer and the second work function metal layer, wherein the second work function metal layer is different in composition than the first work function metal layer.

5. A device comprising:

a substrate having a plurality of semiconductor fins, the semiconductor fins comprising a semiconductor material;

a first transistor having a first gate structure that wraps around one or more of the semiconductor fins, wherein the first gate structure comprises a first gate dielectric structure in direct contact with the semiconductor material of a top surface of the one or more semiconductor fins that the first gate structure wraps around and a first gate electrode structure comprising a first work function metal layer, the first work function metal layer in direct contact with the first gate dielectric structure, the first transistor having a first pair of n type doped source/drain regions on opposite sides of the first gate structure, wherein the first gate dielectric structure comprises a first high k dielectric layer and wherein the first gate electrode structure comprises the first work function metal layer and a fill metal;

a second transistor isolated from the first transistor, the second transistor having a second gate structure that wraps around one or more of the semiconductor fins, wherein the second gate structure comprises a second gate dielectric structure in direct contact with the semiconductor material of a top surface of the one or more semiconductor fins which the second gate structure wraps around and a second gate electrode structure comprising a second work function metal layer, the second work function metal layer in direct contact with the second gate dielectric structure, the second transistor having a second pair of n type doped source/drain regions on opposite sides of the second gate structure, wherein the second gate dielectric structure is different in composition from the first gate dielectric structure along the top surface and sidewalls of the corresponding one or more of the semiconductor fins, and wherein the second gate electrode structure is different in composition than the first gate electrode structure; and

a third transistor, wherein the third transistor has a third gate structure comprising a third gate dielectric structure and the first gate electrode structure wherein the third gate dielectric structure is different in composition than the first gate dielectric structure.

6. The device of claim 5, further comprising a fourth transistor, wherein the fourth transistor has a fourth gate structure comprising a fourth gate dielectric structure and the first gate electrode structure, wherein the fourth gate dielectric structure comprises a silicon dioxide layer, the first high k dielectric layer, and a second high k dielectric layer.

7. A device comprising:

a substrate having a plurality of semiconductor fins, the semiconductor fins comprising a semiconductor material;

a first transistor having a first gate structure that wraps around one or more of the semiconductor fins, wherein the first gate structure comprises a first gate dielectric structure in direct contact with the semiconductor material of a top surface of the one or more semiconductor fins that the first gate structure wraps around and a first gate electrode structure comprising a first work func-

21

tion metal layer, the first work function metal layer in direct contact with the first gate dielectric structure, the first transistor having a first pair of n type doped source/drain regions on opposite sides of the first gate structure, wherein the first gate dielectric structure comprises a first high k dielectric layer and wherein the first gate electrode structure comprises the first work function metal layer and a fill metal;

a second transistor isolated from the first transistor, the second transistor having a second gate structure that wraps around one or more of the semiconductor fins, wherein the second gate structure comprises a second gate dielectric structure in direct contact with the semiconductor material of a top surface of the one or more semiconductor fins which the second gate structure wraps around and a second gate electrode structure comprising a second work function metal layer, the second work function metal layer in direct contact with

22

the second gate dielectric structure, the second transistor having a second pair of n type doped source/drain regions on opposite sides of the second gate structure, wherein the second gate dielectric structure is different in composition from the first gate dielectric structure along the top surface and sidewalls of the corresponding one or more of the semiconductor fins, and wherein the second gate electrode structure is different in composition than the first gate electrode structure; and

a third transistor, wherein the third transistor has a third gate structure comprising the first gate dielectric structure and the second gate electrode structure.

8. The device of claim 7, further comprising a fourth transistor, wherein the fourth transistor has a fourth gate structure comprising the second gate dielectric structure and the second gate electrode structure.

* * * * *