



(86) Date de dépôt PCT/PCT Filing Date: 2000/05/02
 (87) Date publication PCT/PCT Publication Date: 2000/11/23
 (45) Date de délivrance/Issue Date: 2007/05/01
 (85) Entrée phase nationale/National Entry: 2001/11/13
 (86) N° demande PCT/PCT Application No.: US 2000/011896
 (87) N° publication PCT/PCT Publication No.: 2000/069620
 (30) Priorité/Priority: 1999/05/13 (US09/311,053)

(51) Cl.Int./Int.Cl. *B29D 11/00* (2006.01)
 (72) Inventeurs/Inventors:
 BISHOP, JOSEPH ANDREW, US;
 FOSTER, CHARLES, US
 (73) Propriétaire/Owner:
 ESSILOR INTERNATIONAL (COMPAGNIE GENERALE
 D'OPTIQUE), FR
 (74) Agent: OGILVY RENAULT LLP/S.E.N.C.R.L.,S.R.L.

(54) Titre : PROCÉDE DE FABRICATION DE LENTILLES OPHTALMIQUES
 (54) Title: METHOD FOR MANUFACTURING OPHTHALMIC LENSES

(57) **Abrégé/Abstract:**

The invention provides a method for manufacturing an ophthalmic lens. The method includes the step of applying one or more resin beads at the periphery of a mold assembly. The viscosity of the one or more resin beads is about 50,000 to about 100,000 centipoise. The invention provides a means to contain the resin that avoids the problems inherent in the use of mechanical components for containing the resin.

Abstract

The invention provides a method for manufacturing an ophthalmic lens. The method includes the step of applying one or more resin beads at the periphery of a mold assembly. The viscosity of the one or more resin beads is about 50,000 to about 100,000 centipoise. The invention provides a means to contain the resin that avoids the problems inherent in the use of mechanical components for containing the resin.

METHOD FOR MANUFACTURING OPHTHALMIC LENSES

Field of the Invention

5 The present invention relates to methods for manufacturing ophthalmic lenses. In particular, the invention provides a method for manufacturing lenses by casting.

Background of the Invention

 Ophthalmic lenses may be made by any of a wide variety of processes. In
10 one such process, one or more resin layers is cast onto an optical preform to form the desired lens. In certain methods for casting a layer onto a preform, the mold assembly is made of a first mold and the optical preform that serves as the second mold. The preform and first mold are positioned in relation to each other, a polymerizable resin is dispersed between the preform and first mold, and the resin is
15 polymerized to produce a lens from the cast layer and the preform.

 A number of mechanical components, such as gaskets, O-rings, and the like have been used to contain the polymerizable resin within the mold assembly. However, the known mechanical components for resin containment are
20 disadvantageous because of the need to clean the components. Additionally, the component size required may vary with variations in the size and shape of the optical preform and mold. Therefore, a need exists for a means to contain the resin that avoids the problems inherent in the use of mechanical components for containing the resin.

25

Description of the Invention and its Preferred Embodiments

 The present invention provides a method for producing an ophthalmic lens by casting one or more resin layers onto an optical preform in which resin containment in the mold assembly is achieved by the use of a resin bead. The
30 method of the invention eliminates the need for the use of a mechanical component to contain the resin thereby reducing the cost and complexity of the machinery necessary to carry out the casting process.

In one embodiment, the invention provides a method for manufacturing a lens comprising, consisting essentially of, and consisting of applying one or more resin beads at the periphery of a mold assembly. By "lens" is meant any ophthalmic lens including, without limitation, spectacle lenses, contact lenses, intraocular lenses and the like. Preferably, the lens of the invention is a spectacle lens. By "mold assembly" is meant an optical preform, casting resin, and at least one mold half. By "optical preform" is meant a shaped, optically transparent article capable of refracting light and possessing a convex and a concave surface, which article is suitable for use in producing a spectacle lens.

It is a discovery of the invention that containment of a resin within a mold assembly may be achieved by the use of one or more resin beads at the periphery of the mold assembly. Preferably, the resin bead or beads are placed along the circumference or edge of the optical preform.

The resin useful to form the one or more beads is of a viscosity effective for the one or more beads to maintain its shape and contain the casting resin within the mold assembly. Typically, resin forming the one or more resin beads will have a viscosity of about 50,000 centipoise to about 100,000 centipoise, preferably about 75,000 to about 100,000 centipoise.

Suitable resins useful for forming resin beads are any resins that will not adversely affect the optical preform or resin cast onto the preform. Preferably, the resins used to form the resin beads are the same as or similar to that used for casting the layer onto the preform. Such resins include, without limitation, acrylates and methacrylates. Exemplary acrylates and methacrylates include, without limitation, di-, tri-, tetra-, and penta-acrylates, ethylene glycol diacrylate, ethoxylated aliphatic diacrylates, ethoxylated trimethylol propane triacrylate, bisphenol A diacrylate, allyl methacrylate, bisphenol A dimethacrylate, and the like and combinations thereof.

Preferably, the resin used for the resin beads has a viscosity that is greater than that of the resin cast onto the preform.

5

One ordinarily skilled in the art will recognize that any useful additive may be added to the resin formulation forming the resin beads. Suitable additives include, without limitation, photoinitiators such as 1-hydroxy cyclohexyl phenyl ketone and 2-hydroxy-2-methyl-1-phenyl-propan-1-one and thermal initiators such as organic peroxides, hydroperoxide, percarbonate peracetate and the like and combinations thereof.

The one or more resin beads may be applied to the mold assembly periphery or to the periphery of the optical preform alone. The bead or beads are applied by any convenient means including, without limitation, a positive displacement dispensing pump. The one or more beads may be of any size or shape, but preferably are configured, and are of an amount effective, so as to substantially contain the resin to be cast onto the preform within the mold assembly. The one or more beads may be placed at any point around the periphery of the mold assembly or preform. In an embodiment in which two beads are used, the beads are placed at points on the about the 90° and 270° axis points of the preform and spread towards the 0° and 180° points. Preferably, one or more voids are left so that the resin bead or beads do not completely encircle the preform.

The mold assembly used in the process of the invention may include first and second molds. One of the molds may be, and preferably is, the optical preform. One ordinarily skilled in the art will recognize that the method of the invention may be used whether a layer is cast onto the optical preform's convex surface, concave surface, or both the concave and convex surfaces. Additionally, the invention may be used for the casting of more than one layer onto one or more surfaces of the preform. Suitable methods for casting a lens using an optical preform are disclosed

in United States Patent Nos. 5,147,585, 5,178,800, 5,219,497, 5,316,702,
5,358,672, 5,470,892, 5,480,600, 5,512,371, 5,531,940, 5,702,819, 5,793,465,
5 5,859,685, and 5,861,934.

Generally, to form the lens, a mold assembly is provided by placing the first
mold in a relation to the second mold, or optical preform, so that, upon
polymerization of the resin, the optical preform and cast layer provide the desired
10 lens. The optical preform may be made of any suitable material used in the
manufacture of lenses including, without limitation, polycarbonates, allyl diglycol
carbonates, allylic esters, diallyl phenyl phosphonates, acrylic esters, acrylates,
methacrylates, styrenics, lexan, polyesters, polyarylene ethers, and the like, and
combinations thereof. The preform may be produced by any convenient means
15 including, without limitation, molding, thermoforming, casting, injection-
compression molding, and the like.

The mold and the preform may be aligned and oriented by any convenient
means. The preform and mold may be rotated or displaced in relation to one another
20 to meet the requirements of the lens to be produced. The polymerizable resin to be
cast onto the optical preform may be dispensed into the cavity formed by the first
mold and the optical preform. Alternatively, the cast resin may be first dispensed
onto a surface of the mold or preform prior to placing the mold and preform in the
desired relation. The resin may be partially hardened prior to its dispensing. The
25 dispensing may be carried out by any convenient means including, without
limitation, injection.

The cast resin is then cured by any desired, known method, such as by the
use of irradiation, heat, visible light, or a combination thereof. One ordinarily
30 skilled in the art will recognize that the resin bead or beads will be polymerized
along with the cast resin. After the casted resin is cured to the desired degree, the

lens is removed from the mold and the portion formed by the polymerized one or more resin beads is removed from the lens by any convenient means, such as edging.

5

The invention will be clarified by the following, non-limiting examples.

Examples

10

Example 1

An optical preform of -2.25 diopters was loaded onto a tray having a ring to support the preform at its periphery and a resin bead was applied to the preform periphery. The resin bead was composed of an acrylate resin and initiator, DAROCUR™ 1173. The viscosity of the resin bead was approximately 80,000 cp.

15 An acrylate casting resin was then dispensed onto the preform's exposed surface and a mold half was lowered onto the cast resin. The cast resin was then UV cured by exposing the mold assembly for 30 secs to UV light of approximately 300 nm. The mold was separated from the polymerized cast layer and the lens edged to remove the cured resin bead. The resin bead was observed to form a good barrier for the casting

20 resin as there was no observed leak of casting resin from the mold assembly.

Example 2

The procedure of Example 1 was used except that the resin used to form the resin bead was approximately 10,000 cp. The bead viscosity was insufficient to

25 enable the bead to hold its form and contain the casting resin.

What is claimed is:

1. A method for manufacturing a lens comprising applying one or more resin beads at the periphery of a mold assembly, wherein the viscosity of the one or more resin beads is about 50,000 to 100,000 centipoise.
2. The method of claim 1, wherein the resin bead is comprised of a resin substantially the same as that forming the casting resin of the mold assembly.
3. The method of claim 2, wherein the resin bead and casting resin are selected from the group consisting of acrylates, methacrylates, and combinations thereof.
4. The method of claim 1, wherein the one or more resin beads is applied to the periphery of the optical preform.