

**(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE**

(11) Application No. AU 2004275999 B2

(54) Title
Additive mixtures

(51) International Patent Classification(s)
C08K 5/1575 (2006.01) **C08K 5/25** (2006.01)
C08K 5/24 (2006.01) C08K 5/134 (2006.01)

(21) Application No: **2004275999** (22) Date of Filing: **2004.09.22**

(87) WIPO No: **WO05/030855**

(30) Priority Data

(31)	Number	(32)	Date	(33)	Country
	03103714.6		2003.10.07		EP
	03103633.8		2003.10.01		EP
	03103871.4		2003.10.20		EP
	04102809.3		2004.06.18		EP

(43) Publication Date: **2005.04.07**
(44) Accepted Journal Date: **2010.08.12**

(71) Applicant(s)
BASF SE

(72) Inventor(s)
Hirt, Urs;Van De Langkruis, Judy;Stoll, Klaus

(74) Agent / Attorney
Davies Collison Cave, 255 Elizabeth Street, Sydney, NSW, 2000

(56) Related Art
EP 0911365 A

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
7 April 2005 (07.04.2005)

PCT

(10) International Publication Number
WO 2005/030855 A3

(51) International Patent Classification⁷: C08K 5/1575, 5/24, C08L 23/10

(74) Common Representative: CIBA SPECIALTY CHEMICALS HOLDING INC.; Patent Department, Klybeckstrasse 141, CH-4057 Basel (CH).

(21) International Application Number:
PCT/EP2004/052263

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date:
22 September 2004 (22.09.2004)

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language: English

Published:

— with international search report

(26) Publication Language: English

(88) Date of publication of the international search report:
23 June 2005


(71) Applicant (for all designated States except US): CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(72) Inventors; and

(75) Inventors/Applicants (for US only): STOLL, Klaus [DE/DE]; Am Sonnenrain 18, 79589 Binzen (DE). HIRT, Urs [CH/CH]; Langmattstrasse 1, CH-4132 Muttenz (CH). VAN DE LANGKRUIS, Judy [ZA/CH]; Gartenweg 3, CH-4145 Gempen (CH).

(54) Title: ADDITIVE MIXTURES



(57) Abstract: An additive mixture containing the components (A), (B) and optionally (C), wherein component (A) is at least one compound of the formula (I) wherein p is zero or 1; m and n are independently of one another an integer from zero to 3; and the radicals R are independently of one another C₁-C₈alkyl, C₁-C₈alkoxy, hydroxy, halogen, C₁-C₈alkylthio, C₁-C₈alkylsulfoxide or 2 radicals R form together with 2 adjacent carbon atoms of the unsaturated parent ring a 5- to 7-membered carbocyclic or heterocyclic ring; component (B) is at least one compound of the formula (II) wherein x and y are independently of one another an integer from 2 to 10; the radicals A₁, A₂ and A₃ are independently of one another C₁-C₁₀alkyl, C₅-C₁₂cycloalkyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; phenyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; or C₇-C₁₂phenylalkyl, and the radicals A₂ and A₃ are additionally hydrogen; with the proviso that at least one of the radicals A₁ and A₂ is branched C₃-C₁₀alkyl, C₅-C₁₂cycloalkyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; phenyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; or C₇-C₁₂phenylalkyl; and component (C) is a lubricant or a mixture of lubricants.

WO 2005/030855 A3

- 1 -

Additive Mixtures




The present invention relates to an additive mixture containing a sorbitol derivative, a hydrazine derivative and optionally a lubricant and / or an antioxidant, as well as to an additive mixture containing a sorbitol derivative and a lubricant, to 5 the use of said additive mixtures as clarifying agents for polypropylene homo or copolymers and to polypropylene homo or copolymers containing the described additive mixtures.

Mixtures containing nucleating agents and waxes are described for example in EP-A-476,401, US-A-5,958,319, US-B-6,300,398 and US-A-5,856,385. Phenyl-10 alkanoyl-hydrazines are described for example in US-A-3,773,722. A reaction product of dibenzylidene sorbitol with phenylhydrazine or its derivative is described for example in the abstract of JP-A-60/042,385. A polyolefin composition comprising a dibenzylidene sorbitol compound and a specific hydrazide is described for example in US-B-6,518,339. Polypropylene compositions are 15 described for example in WO-A-02/46,300.


The polypropylene homo or copolymers containing the additive mixtures of the present invention exhibit excellent optical properties at considerably reduced side effects (such as discoloration, emission of malodorants, migration or plate-out of low-molecular weight substances etc.) originating e.g. from the additives or any 20 transformation products of the same.

In a first aspect, the present invention provides an additive mixture comprising the components (A), (B) and (C), wherein component (A) is at least one compound of the formulae (I-1), (I-2) and (I-3);

- 1a -



component (B) is the compound of the formula (II-1); and



component (C) is at least one lubricant selected from the group consisting of Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene wax, metallocene polyethylene wax, Ziegler-Natta polypropylene wax and stearamide, erucamide and oleamide.

10 In a second aspect, the present invention provides a composition comprising the components (I) and (II) wherein component (I) is a polypropylene homopolymer,

- 1b -


random copolymer, alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic polymer; and component (II) is the additive mixture according to the first aspect.

In a third aspect, the present invention provides a method for clarifying a 5 polypropylene homopolymer, random copolymer, alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic polymer, which comprises incorporating therein an additive mixture according to the first aspect.

In a fourth aspect, the present invention provides a method for improving the 10 processibility of a polymer which comprises incorporating and dispersing therein an additive mixture according to the first aspect,

Disclosed herein is an additive mixture containing the components (A), (B) and optionally (C), wherein

component (A) is at least one compound of the formula (I)



15


wherein

p is zero or 1;

m and n are independently of one another an integer from zero to 3; and

the radicals R are independently of one another C₁-C₈alkyl, C₁-C₈alkoxy, hydroxy, halogen, C₁-C₈alkylthio, C₁-C₈alkylsulfoxyl or 2 radicals R form together with 2 adjacent carbon atoms of the unsaturated parent ring a 5- to 7-membered carbocyclic or heterocyclic ring;

component (B) is at least one compound of the formula (II)



wherein

x and y are independently of one another an integer from 2 to 10;

the radicals A₁, A₂ and A₃ are independently of one another C₁-C₁₀alkyl, C₅-C₁₂cycloalkyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; phenyl unsubstituted or substituted by 1 to

10 3 C₁-C₁₀alkyl; or C₇-C₁₂phenylalkyl, and

the radicals A₂ and A₃ are additionally hydrogen;

with the proviso that at least one of the radicals A₁ and A₂ is branched C₃-C₁₀alkyl,

C₅-C₁₂cycloalkyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; phenyl unsubstituted or substituted by 1 to 3 C₁-C₁₀alkyl; or C₇-C₁₂phenylalkyl; and

15 **component (C)** is a lubricant or a mixture of lubricants.

The combination of components (A) and (B) may show a synergistic effect.

The products described as component (A), (B) or (C) are commercially available and can be

20 prepared in analogy to known methods, for example as described in US-A-5,023,354, US-A-5,198,484, US-A-3,660,438 and US-A-3,773,722.

Examples of alkyl having up to 10 carbon atoms are methyl, ethyl, linear or branched propyl,

butyl, pentyl, hexyl, heptyl, octyl, nonyl and decyl. A preferred meaning of R is C₁-C₄alkyl, in

25 particular methyl. A preferred meaning of A₁ and A₂ is branched C₃-C₁₀alkyl, in particular tert-butyl or 1,1-dimethylpropyl. A₁ and A₂ as tert-butyl are especially preferred.

Preferred meanings of A₃ are hydrogen and methyl.

30 Examples of C₁-C₈alkoxy are methoxy, ethoxy, propoxy, butoxy, pentyloxy, hexyloxy, heptyloxy and octyloxy. Methoxy is particularly preferred.

Examples of C_1 - C_8 alkylthio are methylthio, ethylthio, propylthio, butylthio, pentylthio, hexylthio, heptylthio and octylthio.

Examples of C_1 - C_8 alkylsulfoxy are methylsulfoxy, ethylsulfoxy, propylsulfoxy, butylsulfoxy,

5 pentylsulfoxy, hexylsulfoxy, heptylsulfoxy and octylsulfoxy.

Examples of C_5 - C_{12} cycloalkyl unsubstituted or substituted by 1 to 3 C_1 - C_{10} alkyl are


cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl and methylcyclohexyl.

10 An example of phenyl substituted by 1 to 3 C_1 - C_{10} alkyl is methylphenyl.

Examples of C_7 - C_{12} phenylalkyl are benzyl and 2-phenylprop-2-yl.

An example of the formula (I) wherein 2 radicals R form together with 2 adjacent carbon

15 atoms of the unsaturated parent ring a 5- to 7-membered carbocyclic or heterocyclic ring is



According to a preferred embodiment of the present invention

20 p is 1;

m and n are independently of one another zero, 1 or 2; and

the radicals R are independently of one another C_1 - C_4 alkyl;

x and y are independently of one another an integer from 2 to 6;

the radicals A₁, A₂ and A₃ are independently of one another C_1 - C_5 alkyl, cyclohexyl


25 unsubstituted or substituted by one methyl; phenyl unsubstituted or substituted by one

methyl; or 2-phenylpropyl, and


A₃ is additionally hydrogen.

According to a further preferred embodiment

30 component (A) is at least one compound of the formulae (I-1), (I-2) and (I-3), and



component (B) is the compound of the formula (II-1).



The compound of the formula (I-1) is commercially available as IRGACLEAR D (RTM).

The compound of the formula (I-2) is commercially available as IRGACLEAR DM (RTM).

10

The compound of the formula (I-3) is commercially available as MILLAD 3988 (RTM).

The compound of formula (II-1) is commercially available as IRGANOX MD 1024 (RTM).

15

Component (C) is preferably at least one lubricant selected from the group consisting of synthetic or natural waxes and amides of fatty acids. A comprehensive definition and review on waxes is given, for example, in Ullmann's Encyclopedia of Industrial Chemistry, Vol. A-28, VCH Verlagsgesellschaft mbH, D-69451 Weinheim, 1996 (in particular, see pages 104 ff.

20 therein), which is incorporated herewith by reference.

Preferably suited are synthetic waxes, most preferably fully synthetic waxes of low polarity.

Examples are Fischer-Tropsch waxes, high-pressure polyethylene waxes, Ziegler-Natta polyethylene waxes, metallocene polyethylene waxes and Ziegler-Natta polypropylene

5 waxes.

A most suitable commercially available Fischer-Tropsch wax is for example AdSperse 868 (RTM), available from SASOL, Republic of South Africa.

10 Most suitable polyolefin waxes have preferably a molecular weight M_w of more than 800 g/mol and less than 20'000 g/mol.

Examples of suitable natural waxes are refined esters of montan wax and decolorized paraffin waxes.

15 Examples of fatty acid amids are stearamide, erucamide and oleamide which are commercially available as Atmer SA 1750 (RTM), Atmer SA 1753 (RTM), respectively Atmer SA 1756 (RTM), Atmer SA 1758 (RTM) and Atmer SA 1759 (RTM).

20 Component (C) is in particular at least one lubricant selected from the group consisting of Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene wax, metallocene polyethylene wax, Ziegler-Natta polypropylene wax, natural waxes and amides of fatty acids.

25 A most particularly preferred embodiment of the present invention relates to an additive mixture wherein

component (A) is at least one compound of the formulae (I-1), (I-2) and (I-3) as defined above;

component (B) is the compound of the formula (II-1) as defined above; and

30 component (C) is at least one lubricant selected from the group consisting of Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene wax, metallocene polyethylene wax, Ziegler-Natta polypropylene wax and stearamide, erucamide and oleamide.

Examples of specific additive mixtures of the present invention are

1. Compound of the formula (I-1) + compound of the formula (II-1) + a Fischer-Tropsch wax (e.g. AdSperse 868 (RTM), AdSperse 500 (RTM), AdSperse 100 (RTM), EnHance (RTM) or EnHance FG (RTM)).
- 5 2. Compound of the formula (I-1) + compound of the formula (II-1) + a Ziegler-Natta polyethylene wax (e.g. Licowax PE 130 (RTM), Licowax PE 190 (RTM) or Licowax PE 520 (RTM)).
- 10 3. Compound of the formula (I-1) + compound of the formula (II-1) + a high pressure polyethylene wax (e.g. Licowax PE 810 (RTM), Licowax PE 820 (RTM), Licowax PE 830 (RTM), Licowax PE 840 (RTM), Epolene C 10 (RTM), Epolene C 14 (RTM), Epolene C 15 (RTM), Epolene C 16 (RTM), Epolene C 17 (RTM), Epolene C 18 (RTM), Epolene N 15 (RTM), Epolene N 20 (RTM) or Epolene N 34 (RTM)).
- 15 4. Compound of the formula (I-1) + compound of the formula (II-1) + a metallocene polyethylene wax.
5. Compound of the formula (I-1) + compound of the formula (II-1) + a Ziegler-Natta polypropylene wax (e.g. Licowax PP 230 (RTM)).
6. Compound of the formula (I-1) + compound of the formula (II-1) + a montan-ester wax (e.g. Licowax E (RTM), Hostalub WE 4 (RTM) or Hostalub WE 40 (RTM)).
- 20 7. Compound of the formula (I-1) + compound of the formula (II-1) + paraffin wax (e.g. Linpar 17-20 (RTM) or Linpar 1416-V (RTM)).
8. Compound of the formula (I-1) + compound of the formula (II-1) + a fatty acid amid (e.g. Atmer SA 1750 (RTM), Atmer SA 1753 (RTM) or Atmer SA 1759 (RTM)).
9. Compound of the formula (I-2) + compound of the formula (II-1) + a Fischer-Tropsch wax (e.g. AdSperse 868 (RTM), AdSperse 500 (RTM), AdSperse 100 (RTM), EnHance (RTM) or EnHance FG (RTM)).
- 25 10. Compound of the formula (I-2) + compound of the formula (II-1) + a Ziegler-Natta polyethylene wax (e.g. Licowax PE 130 (RTM), Licowax PE 190 (RTM) or Licowax PE 520 (RTM)).
11. Compound of the formula (I-2) + compound of the formula (II-1) + a high pressure polyethylene wax (e.g. Licowax PE 810 (RTM), Licowax PE 820 (RTM), Licowax PE 830 (RTM), Licowax PE 840 (RTM), Epolene C 10 (RTM), Epolene C 14 (RTM), Epolene C 15 (RTM), Epolene C 16 (RTM), Epolene C 17 (RTM), Epolene C 18 (RTM), Epolene N 15 (RTM), Epolene N 20 (RTM) or Epolene N 34 (RTM)).
- 30

12. Compound of the formula (I-2) + compound of the formula (II-1) + a metallocene polyethylene wax.
13. Compound of the formula (I-2) + compound of the formula (II-1) + a Ziegler-Natta polypropylene wax (e.g. Licowax PP 230 (RTM)).
- 5 14. Compound of the formula (I-2) + compound of the formula (II-1) + a montan-ester wax (e.g. Licowax E (RTM), Hostalub WE 4 (RTM) or Hostalub WE 40 (RTM)).
15. Compound of the formula (I-2) + compound of the formula (II-1) + paraffin wax (e.g. Linpar 17-20 (RTM) or Linpar 1416-V (RTM)).
16. Compound of the formula (I-2) + compound of the formula (II-1) + a fatty acid amid (e.g. Atmer SA 1750 (RTM), Atmer SA 1753 (RTM) or Atmer SA 1759 (RTM)).
17. Compound of the formula (I-3) + compound of the formula (II-1) + a Fischer-Tropsch wax (e.g. AdSperse 868 (RTM), AdSperse 500 (RTM), AdSperse 100 (RTM), EnHance (RTM) or EnHance FG (RTM)).
18. Compound of the formula (I-3) + compound of the formula (II-1) + a Ziegler-Natta polyethylene wax (e.g. Licowax PE 130 (RTM), Licowax PE 190 (RTM) or Licowax PE 520 (RTM)).
19. Compound of the formula (I-3) + compound of the formula (II-1) + a high pressure polyethylene wax (e.g. Licowax PE 810 (RTM), Licowax PE 820 (RTM), Licowax PE 830 (RTM), Licowax PE 840 (RTM), Epolene C 10 (RTM), Epolene C 14 (RTM), Epolene C 15 (RTM), Epolene C 16 (RTM), Epolene C 17 (RTM), Epolene C 18 (RTM), Epolene N 15 (RTM), Epolene N 20 (RTM) or Epolene N 34 (RTM)).
- 20 21. Compound of the formula (I-3) + compound of the formula (II-1) + a metallocene polyethylene wax.
22. Compound of the formula (I-3) + compound of the formula (II-1) + a Ziegler-Natta polypropylene wax (e.g. Licowax PP 230 (RTM)).
23. Compound of the formula (I-3) + compound of the formula (II-1) + a montan-ester wax (e.g. Licowax E (RTM), Hostalub WE 4 (RTM) or Hostalub WE 40 (RTM)).
24. Compound of the formula (I-3) + compound of the formula (II-1) + paraffin wax (e.g. Linpar 17-20 (RTM) or Linpar 1416-V (RTM)).
- 30 25. Compound of the formula (I-3) + compound of the formula (II-1) + a fatty acid amid (e.g. Atmer SA 1750 (RTM), Atmer SA 1753 (RTM) or Atmer SA 1759 (RTM)).

The weight ratio of components (A) to (B) is for example 100/1 to 1/10, more preferably 20/1 to 1/1 and most preferably 5/1 to 2/1.

The weight ratio of components (A) to (C) is for example 1/200 to 100/1, more preferably

5 1/20 to 10/1 and most preferably 1/10 to 1/1.

Another embodiment of the present invention is a composition containing the components (I) and (II), wherein

10 component (I) is a polypropylene homopolymer, random copolymer, alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic polymer; and
component (II) is the additive mixture described above.

15

Component (I) as a polypropylene homopolymer also covers long chain branched polypropylene.

The polypropylene, can be prepared by different, and especially by the following, methods:

20

Catalytic polymerization using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, Ila and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

Component (I) is further e.g. a polypropylene random copolymer, alternating or segmented copolymer or block copolymer containing one or more comonomers selected from the group consisting of ethylene, C_4 - C_{20} - α -olefin, vinylcyclohexane, vinylcyclohexene, C_4 - C_{20} alkadiene, C_5 - C_{12} cycloalkadiene and norbornene derivatives; the total amount of 5 propylene and the comonomer(s) being 100 %.

Polypropylene copolymer also covers long chain branched polypropylene copolymer.

Examples of suitable C_4 - C_{20} - α -olefins are 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-10 nonene, 1-decene, 1-undecene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene and 4-methyl-1-pentene.

Examples of suitable C_4 - C_{20} alkadienes are hexadiene and octadiene.

15 Examples of suitable C_5 - C_{12} cycloalkadienes are cyclopentadiene, cyclohexadiene and cyclooctadiene.

Examples of suitable norbornene derivatives are 5-ethylidene-2-norbornene (ENB), dicyclopentadiene (DCP) and methylene-domethylene-hexahydronaphthalene (MEN).

20 A propylene/ethylene copolymer contains for example 50 to 99.9 %, preferably 80 to 99.9 %, in particular 90 to 99.9 %, by weight of propylene.

A propylene copolymer wherein the comonomer is a C_9 - C_{20} - α -olefin such as e.g. 1-nonene, 1-25 decene, 1-undecene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene or 1-eicosene; C_9 - C_{20} alkadiene, C_9 - C_{12} cycloalkadiene or a norbornene derivative such as e.g. 5-ethylidene-2-norbornene (ENB) or methylene-domethylene-hexahydronaphthalene (MEN) contains preferably more than 90 mol %, in particular 90 to 99.9 mol % or 90 to 99 mol %, of propylene.

30 A propylene copolymer wherein the comonomer is a C_4 - C_8 - α -olefin such as e.g. 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene or 4-methyl-1-pentene; vinylcyclohexane, vinylcyclohexene, C_4 - C_8 alkadiene or C_5 - C_8 cycloalkadiene contains preferably more than 80 mol %, in particular 80 to 99.9 mol % or 80 to 99 mol %, of propylene.

Further examples of component (I) are propylene/isobutylene copolymer, propylene/butadiene copolymer, propylene/cycloolefin copolymer, terpolymers of propylene with ethylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene;

5 propylene/1-olefin copolymers where the 1-olefin is generated in situ; and propylene/carbon monoxide copolymers.

Other examples of component (I) are blends of polypropylene with propylene/ethylene copolymers, propylene/butylene copolymers, polyethylene, e.g. HDPE or LDPE; polybutene, 10 polyisobutylene, poly-4-methylpentene or alternating or random polyalkylene/carbon monoxide copolymers. These blends contain preferably at least 50 % by weight, relative to the weight of the total blend, of polypropylene.

According to a further preferred embodiment component (I) is a polypropylene copolymer, 15 manufactured by copolymerisation of at least 75 % by weight of propylene with ethylene or another alpha-olefin comonomer, which is selected from linear or branched butene, linear or branched pentene, linear or branched hexene and linear or branched octene.

20 Component (A) is for example present in the compositions of the invention in an amount of 0.01 to 0.5 % by weight, relative to the weight of component (I), preferably 0.1 to 0.3 % by weight, in particular 0.15 to 0.25 % by weight.

Component (B) is for example present in the compositions of the invention in an amount of 25 0.01 to 0.5 % by weight, relative to the weight of component (I), preferably 0.01 to 0.3 % by weight, in particular 0.03 to 0.15 % by weight.

Component (C) is for example present in the compositions of the invention in an amount of 30 0.01 to 5 % by weight, relative to the weight of component (I), preferably 0.1 to 2.0 % by weight, in particular 0.2 to 1.0 % by weight.

The compositions of the present invention can be prepared according to the methods well established in the art. Examples are the incorporation of the components of the additive mixture into the polymer resin by powder blending of all components prior to the melt

processing; addition of the additive mixture as concentrate or masterbatch to the polymer resin in pellet form; melt blending of the additive mixture in pure or concentrate form, e.g. via continuous feeders or side extruders into the molten polymer resin, etc..

5 The compositions of the present invention may optionally contain further additives such as those listed below.

1. Antioxidants

10 1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-di-methylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example 15 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

20 1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

25 1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

30 1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-

methylphenol), 4,4'-thiobis(3,6-di-sec-amylphenol), 4,4'-bis(2,6-dimethyl-4-hydroxyphenyl)-disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-

5 methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)-phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α , α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methyl-phenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

20 **1.7. O-, N- and S-benzyl compounds**, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydi-benzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithiobenzoate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isoctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

25 **1.8. Hydroxybenzylated malonates**, for example dioctadecyl-2,2-bis(3,5-di-tert-butyl-2-hydroxybenzyl)malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)malonate, di-dodecylmercaptoethyl-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis[4-(1,1,3,3-tramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

30 **1.9. Aromatic hydroxybenzyl compounds**, for example 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

10 1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

15 1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-20 nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylol-propane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

25 1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylol-propane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane; 3,9-bis[2-{3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy}-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5.5]-undecane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thioglycolic acid, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospho-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thioglycolic acid, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospho-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamide, N,N'-bis[2-(3-[3,5-di-tert-butyl-4-hydroxyphenyl]-propionyloxy)ethyl]oxamide (Naugard[®]XL-1, supplied by Uniroyal).

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylaminophenol, 4-nanoylaminophenol, 4-dodecanoylaminophenol, 4-octadecanoylaminophenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylamino-methylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetra-

methyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- and dialkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- and dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- and dialkylated tert-octylphenothiazines, N-allylphenothiazine, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetra-10 methylpiperid-4-yl-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

15 **2.1. 2-(2'-Hydroxyphenyl)benzotriazoles**, for example 2-(2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis(α , α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isoctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylenabis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300; $\left[R - \text{CH}_2\text{CH}_2 - \text{COO} - \text{CH}_2\text{CH}_2 \right]_2$, where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl, 2-[2'-hydroxy-3'-(α , α -dimethylbenzyl)-5'-(1,1,3,3-tetramethylbutyl)phenyl]-

benzotriazole; 2-[2'-hydroxy-3'-(1,1,3,3-tetramethylbutyl)-5'-(α,α -dimethylbenzyl)phenyl]benzotriazole.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyl-

5 oxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, for example 4-tert-butylphenyl

salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoyl resorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzo-

10 ate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphe-

nylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinna-

15 mate, butyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carbomethoxy-p-methoxycinna-

mate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thiobis[4-(1,1,3,3-tetramethyl-

butyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-

20 butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-

butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphe-

nylundecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or with-

out additional ligands.

25

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate,

bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate,

bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperi-

30 dyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-

2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, linear or cyclic condensates of

N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-di-

chloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitrolotriacetate, tetrakis(2,2,6,6-tetra-

methyl-4-piperidyl)-1,2,3,4-butanetetracarboxylate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-tetrame-

thylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearylloxy-2,2,6,6-tetramethyl-

piperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)-malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, bis(1-octyl-oxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylene-5-diamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)-ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidine-2,5-dione, 10 a mixture of 4-hexadecyloxy- and 4-stearyloxy-2,2,6,6-tetramethylpiperidine, a condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensate of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. 15 [136504-96-6]); a condensate of 1,6-hexanediamine and 2,4,6-trichloro-1,3,5-triazine as well as N,N-dibutylamine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [192268-64-7]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimide, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimide, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4.5]decane, a reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-20 3,8-diaza-4-oxospiro-[4.5]decane and epichlorohydrin, 1,1-bis(1,2,2,6,6-pentamethyl-4-piperidyl)oxycarbonyl)-2-(4-methoxyphenyl)ethene, N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine, a diester of 4-methoxymethylenemalonic acid with 1,2,2,6,6-pentamethyl-4-hydroxypiperidine, poly[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]siloxane, a reaction product of maleic acid anhydride- α -olefin copolymer with 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture 30 with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide, mixtures of o- and p-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-

(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyl-oxophenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-

5 [2-hydroxy-4-(2-hydroxy-3-butyloxypropoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxypropoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxyphenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxypropoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine, 2-[2-hydroxy-4-[3-(2-ethylhexyl-1-oxy)-2-hydroxypropoxy]phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.



15 **3. Metal deactivators**, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl)hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyldihydrazide, oxanilide, isophthaloyl dihydrazide, sebacyl bisphenylhydrazide, N,N'-diacetyl adipoyl dihydrazide, N,N'-bis(salicyloyl)oxalyldihydrazide, N,N'-bis(salicyloyl)thiopropionyl dihydrazide.

20 **4. Phosphites and phosphonites**, for example triphenyl phosphite, diphenylalkyl phosphites, phenyldialkyl phosphites, tris(nonylphenyl) phosphite, triauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite, bis(2,4-di-cumylphenyl)pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)pentaerythritol diphosphite, diisodecyloxy pentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isoctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methyl phosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethyl phosphite, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, 2,2',2"-nitrilo-[triethyltris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite], 2-ethylhexyl(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite, 5-butyl-5-ethyl-2-(2,4,6-tri-tert-butylphenoxy)-1,3,2-dioxaphosphirane.



The following phosphites are especially preferred:


Tris(2,4-di-tert-butylphenyl) phosphite (Irgafos[®]168, Ciba-Geigy), tris(nonylphenyl) phosphite,

5



10





5. Hydroxylamines, for example N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-

5 diethylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrone, for example N-benzyl-alpha-phenylnitron, N-ethyl-alpha-methylnitron, N-octyl-

10 alpha-heptylnitron, N-lauryl-alpha-undecylnitron, N-tetradecyl-alpha-tridecylnitron, N-hexadecyl-alpha-pentadecylnitron, N-octadecyl-alpha-heptadecylnitron, N-hexadecyl-alpha-heptadecylnitron, N-octadecyl-alpha-pentadecylnitron, N-heptadecyl-alpha-heptadecylnitron, N-octadecyl-alpha-hexadecylnitron, nitron derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

15

7. Thiosynergists, for example dilauryl thiodipropionate, dimistrylthiodipropionate or distearyl thiodipropionate or distearyl disulfide.

8. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl,

20 stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptopbenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example copper salts in combination with iodides and/or phos-

25 phorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl

cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids, for example calcium stearate,

zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

11. Conventional nucleating agents, for example inorganic substances, such as talcum,

5 metal oxides, such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds, such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, pimelic acid, subaric acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds, such as ionic copolymers (ionomers).

10

12. Other additives, for example plasticisers, lubricants, rheology additives, catalysts, flow-control agents, optical brighteners, flame retarding agents, antistatic agents and blowing agents.

15 **13. Benzofuranones and indolinones**, for example those disclosed in US-A-4,325,863; US-A-4,338,244; US-A-5,175,312; US-A-5,216,052; US-A-5,252,643; DE-A-4316611;

DE-A-4316622; DE-A-4316876; EP-A-0589839 or EP-A-0591102 or 3-[4-(2-acetoxyethoxy)-phenyl]-5,7-di-tert-butylbenzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]-benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one],

20 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butylbenzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butylbenzofuran-2-one, 3-(3,4-dimethylphenyl)-5,7-di-tert-butylbenzofuran-2-one, 3-(2,3-dimethylphenyl)-5,7-di-tert-butylbenzofuran-2-one.

25 The weight ratio of the above described component (A) to the total of the conventional additives is preferably 250/1 to 1/2500, more preferably 100/1 to 1/100 and most preferably 10/1 to 1/10.

Further embodiments of the present invention which are of interest are listed below:

30 1. A composition containing the components (A), (B) and (D) and optionally (C), wherein component (D) is at least one antioxidant which is different from component (B), preferably selected from the antioxidants listed above under item 1.


2. A composition containing the components (A), (B) and (D) and optionally (C)

wherein component (D) is at least one phenolic antioxidant which is different from component (B).


A phenolic antioxidant with a melting point below 200°C is particularly preferred.

5 3. A composition containing the components (A), (B) and (D) and optionally (C) wherein component (D) is at least one phenolic antioxidant selected from esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid or β -(5-tert-butyl-4-hydroxyphenyl)propionic acid or β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid, e.g. those listed above under item 1.13, 1.14 and 1.15.

10 4. A composition wherein component (A) is a compound of the formula (I-2),




component (B) is a compound of the formula (II-1),



and

component (D) is a compound of the formula (III-1).



20 5. A composition containing the components (A), (B) and (D) and optionally (C) and optionally one or more further components selected from the group consisting of metal (I) or (II) salts of fatty acids, metal (II) oxides, dihydrotalcite, phosphites, phosphonites, organic sulfides and organic disulfides, e.g. those listed above under items 4, 7, 8, 10 and 11.

In the above compositions 1 to 5, for example 100 parts by weight of component (A), 5 to 35, preferably 10 to 30 or 15 to 25, parts by weight of component (B), 5 to 40, preferably 7 to 25 or 10 to 20, parts by weight of component (D) and optionally 50 to 500, preferably 50 to 400

5 or 50 to 300, parts by weight of component (C) may be present. If desired further components may be present, for example 10 to 50, preferably 10 to 35 or 10 to 25, parts by weight of an acid scavenger such as a metal (I) or (II) salt of a fatty acid, a metal (II) oxide or a dihydrotalcite, or 10 to 80, preferably 10 to 50 or 10 to 40, parts by weight of a phosphite, a phosphonite, an organic sulfide or an organic disulfide.

10

Further embodiments of the present invention are

the use of the additive mixture described above as clarifying agent for a polypropylene


homopolymer, random copolymer, alternating or segmented copolymer, block copolymer or a

15 blend of polypropylene with another synthetic polymer; and

a method for clarifying a polypropylene homopolymer, random copolymer, alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic polymer, which comprises incorporating therein an additive mixture as described above.


20 The present invention also relates to

(1) an additive mixture containing the components (A') and (C'), wherein either component (A') is the compound of the formula (I-1); and



component (C') is at least one lubricant selected from the group consisting of synthetic

25 waxes, preferably polyolefin waxes, in particular Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene wax, metallocene polyethylene wax or Ziegler-Natta polypropylene wax; montan-ester wax, paraffin wax, stearamide and oleamide; or component (A') is the compound of the formula (I-2); and




component (C') is at least one lubricant selected from the group consisting of synthetic waxes, preferably polyolefin waxes, in particular Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene wax, metallocene polyethylene wax or Ziegler-

5 Natta polypropylene wax; montan-ester wax, paraffin wax, stearamide, erucamide and oleamide;

as well as to

(2) an additive mixture containing the components (A'') and (C'') wherein component (A'') is the compound of the formula (I-3); and



component (C'') is selected from the group consisting of stearamide and oleamide.

The particular uses and applications described herein are also applicable in appropriate manner for the latter two additive mixtures.

15

The weight ratios and concentrations given for components (A), (C) and (I) can be applied in appropriate manner for components (A'), (A''), (C'), (C''), (I') and (I'') so that component (A) corresponds to component (A') or (A''), component (C) corresponds to component (C') or (C'') and component (I) corresponds to component (I') or (I'').

20

Further examples of specific additive mixtures of the present invention are

1. Compound of the formula (I-1) + a Fischer-Tropsch wax (e.g. AdSperse 868 (RTM), AdSperse 500 (RTM), AdSperse 100 (RTM), EnHance (RTM) or EnHance FG (RTM)).
2. Compound of the formula (I-1) + a Ziegler-Natta polyethylene wax (e.g. Licowax PE 130 (RTM), Licowax PE 190 (RTM) or Licowax PE 520 (RTM)).


3. Compound of the formula (I-1) + a high pressure polyethylene wax (e.g. Licowax PE 810 (RTM), Licowax PE 820 (RTM), Licowax PE 830 (RTM), Licowax PE 840 (RTM), Epolene C 10 (RTM), Epolene C 14 (RTM), Epolene C 15 (RTM), Epolene C 16 (RTM), Epolene C 17 (RTM), Epolene C 18 (RTM), Epolene N 15 (RTM), Epolene N 20 (RTM) or Epolene N 34 (RTM)).
5
4. Compound of the formula (I-1) + a metallocene polyethylene wax.
5. Compound of the formula (I-1) + a Ziegler-Natta polypropylene wax (e.g. Licowax PP 230 (RTM)).
6. Compound of the formula (I-1) + a montan-ester wax (e.g. Licowax E (RTM), Hostalub WE 4 (RTM) or Hostalub WE 40 (RTM)).
10
7. Compound of the formula (I-1) + paraffin wax (e.g. Linpar 17-20 (RTM) or Linpar 1416-V (RTM)).
8. Compound of the formula (I-1) + stearamide, erucamide or oleamide (e.g. Atmer SA 1750 (RTM), Atmer SA 1753 (RTM) or Atmer SA 1759 (RTM)).
15. Compound of the formula (I-2) + a Fischer-Tropsch wax (e.g. AdSperse 868 (RTM), AdSperse 500 (RTM), AdSperse 100 (RTM), EnHance (RTM) or EnHance FG (RTM)).
10. Compound of the formula (I-2) + a Ziegler-Natta polyethylene wax (e.g. Licowax PE 130 (RTM), Licowax PE 190 (RTM) or Licowax PE 520 (RTM)).
20. Compound of the formula (I-2) + a high pressure polyethylene wax (e.g. Licowax PE 810 (RTM), Licowax PE 820 (RTM), Licowax PE 830 (RTM), Licowax PE 840 (RTM), Epolene C 10 (RTM), Epolene C 14 (RTM), Epolene C 15 (RTM), Epolene C 16 (RTM), Epolene C 17 (RTM), Epolene C 18 (RTM), Epolene N 15 (RTM), Epolene N 20 (RTM) or Epolene N 34 (RTM)).
25. Compound of the formula (I-2) + a metallocene polyethylene wax.
13. Compound of the formula (I-2) + a Ziegler-Natta polypropylene wax (e.g. Licowax PP 230 (RTM)).
14. Compound of the formula (I-2) + a montan-ester wax (e.g. Licowax E (RTM), Hostalub WE 4 (RTM) or Hostalub WE 40 (RTM)).
30. Compound of the formula (I-2) + paraffin wax (e.g. Linpar 17-20 (RTM) or Linpar 1416-V (RTM)).
16. Compound of the formula (I-2) + stearamide, erucamide or oleamide (e.g. Atmer SA 1750 (RTM), Atmer SA 1753 (RTM) or Atmer SA 1759 (RTM)).

The present invention further relates to a composition containing the components (I''), (A'') and (C'') wherein

component (I'') is a polypropylene homopolymer or a polypropylene copolymer,

5 manufactured by copolymerisation of at least 75 % by weight of propylene with ethylene or another alpha-olefin comonomer, which is selected from linear or branched butene, linear or branched pentene, linear or branched hexene and linear or branched octene;

component (A'') is the compound of the formula (I-3); and



10 **component (C'')** is selected from the group consisting of Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene wax, metallocene polyethylene wax, Ziegler-Natta polypropylene wax, montan-ester wax, paraffin wax, stearamide, erucamide and oleamide.

15 The weight ratios and concentrations given for components (A), (C) and (I) can be applied in appropriate manner for components (A''), (C''), and (I''). The applications and uses described herein also apply to the latter composition.

20 The polymer resin compositions according to the present invention can be advantageously used for the preparation of various shaped articles. Examples are:

I-1) Floating devices, marine applications, pontoons, buoys, plastic lumber for decks, piers, boats, kayaks, oars, and beach reinforcements.

25 I-2) Automotive applications, in particular bumpers, dashboards, battery, rear and front linings, moldings parts under the hood, hat shelf, trunk linings, interior linings, air bag covers, electronic moldings for fittings (lights), panes for dashboards, headlamp glass, instrument panel, exterior linings, upholstery, automotive lights, head lights, parking lights, rear lights, stop lights, interior and exterior trims; door panels; gas tank; glazing front side; rear windows;

30 seat backing, exterior panels, wire insulation, profile extrusion for sealing, cladding, pillar

covers, chassis parts, exhaust systems, fuel filter / filler, fuel pumps, fuel tank, body side mouldings, convertible tops, exterior mirrors, exterior trim, fasteners / fixings, front end module, glass, hinges, lock systems, luggage / roof racks, pressed/stamped parts, seals, side impact protection, sound deadener / insulator and sunroof.

5

I-3) Road traffic devices, in particular sign postings, posts for road marking, car accessories, warning triangles, medical cases, helmets, tires.

I-4) Devices for plane, railway, motor car (car, motorbike) including furnishings.

10

I-5) Devices for space applications, in particular rockets and satellites, e.g. reentry shields.

I-6) Devices for architecture and design, mining applications, acoustic quietized systems, street refuges, and shelters.

15

II-1) Appliances, cases and coverings in general and electric/electronic devices (personal computer, telephone, portable phone, printer, television-sets, audio and video devices), flower pots, satellite TV bowl, and panel devices.

20 II-2) Jacketing for other materials such as steel or textiles.

II-3) Devices for the electronic industry, in particular insulation for plugs, especially computer plugs, cases for electric and electronic parts, printed boards, and materials for electronic data storage such as chips, check cards or credit cards.

25

II-4) Electric appliances, in particular washing machines, tumblers, ovens (microwave oven), dish-washers, mixers, and irons.

II-5) Covers for lights (e.g. street-lights, lamp-shades).

30

II-6) Applications in wire and cable (semi-conductor, insulation and cable-jacketing).

II-7) Foils for condensers, refrigerators, heating devices, air conditioners, encapsulating of electronics, semi-conductors, coffee machines, and vacuum cleaners.

- III-1) Technical articles such as cogwheel (gear), slide fittings, spacers, screws, bolts, handles, and knobs.
- 5 III-2) Rotor blades, ventilators and windmill vanes, solar devices, swimming pools, swimming pool covers, pool liners, pond liners, closets, wardrobes, dividing walls, slat walls, folding walls, roofs, shutters (e.g. roller shutters), fittings, connections between pipes, sleeves, and conveyor belts.
- 10 III-3) Sanitary articles, in particular shower cubicles, lavatory seats, covers, and sinks.
- III-4) Hygienic articles, in particular diapers (babies, adult incontinence), feminine hygiene articles, shower curtains, brushes, mats, tubs, mobile toilets, tooth brushes, and bed pans.
- 15 III-5) Pipes (cross-linked or not) for water, waste water and chemicals, pipes for wire and cable protection, pipes for gas, oil and sewage, guttering, down pipes, and drainage systems.
- III-6) Profiles of any geometry (window panes) and siding.
- 20 III-7) Glass substitutes, in particular extruded plates, glazing for buildings (monolithic, twin or multiwall), aircraft, schools, extruded sheets, window film for architectural glazing, train, transportation, sanitary articles, and greenhouse.
- 25 III-8) Plates (walls, cutting board), extrusion-coating (photographic paper, tetrapack and pipe coating), silos, wood substitute, plastic lumber, wood composites, walls, surfaces, furniture, decorative foil, floor coverings (interior and exterior applications), flooring, duck boards, and tiles.
- 30 III-9) Intake and outlet manifolds.
- III-10) Cement-, concrete-, composite-applications and covers, siding and cladding, hand rails, banisters, kitchen work tops, roofing, roofing sheets, tiles, and tarpaulins.

IV-1) Plates (walls and cutting board), trays, artificial grass, astroturf, artificial covering for stadium rings (athletics), artificial floor for stadium rings (athletics), and tapes.

IV-2) Woven fabrics continuous and staple, fibers (carpets / hygienic articles / geotextiles /

5 monofilaments; filters; wipes / curtains (shades) / medical applications), bulk fibers (applications such as gown / protection clothes), nets, ropes, cables, strings, cords, threads, safety seat-belts, clothes, underwear, gloves; boots; rubber boots, intimate apparel, garments, swimwear, sportswear, umbrellas (parasol, sunshade), parachutes, paraglides, sails, "balloon-silk", camping articles, tents, airbeds, sun beds, bulk bags, and bags.

10

IV-3) Membranes, insulation, covers and seals for roofs, tunnels, dumps, ponds, dumps, walls roofing membranes, geomembranes, swimming pools, curtains (shades) / sun-shields, awnings, canopies, wallpaper, food packing and wrapping (flexible and solid), medical packaging (flexible & solid), airbags/safety belts, arm- and head rests, carpets, centre console, dashboard, cockpits, door, overhead console module, door trim, headliners, interior lighting, interior mirrors, parcel shelf, rear luggage cover, seats, steering column, steering wheel, textiles, and trunk trim.

V) Films (packaging, dump, laminating, agriculture and horticulture, greenhouse, mulch,

20 tunnel, silage), bale wrap, swimming pools, waste bags, wallpaper, stretch film, raffia, desalination film, batteries, and connectors.

VI-1) Food packing and wrapping (flexible and solid), BOPP, BOPET, bottles.

25 VI-2) Storage systems such as boxes (crates), luggage, chest, household boxes, pallets, shelves, tracks, screw boxes, packs, and cans.

30 VI-3) Cartridges, syringes, medical applications, containers for any transportation, waste baskets and waste bins, waste bags, bins, dust bins, bin liners, wheely bins, container in general, tanks for water / used water / chemistry / gas / oil / gasoline / diesel; tank liners, boxes, crates, battery cases, troughs, medical devices such as piston, ophthalmic applications, diagnostic devices, and packing for pharmaceuticals blister.

VII-1) Extrusion coating (photo paper, tetrapack, pipe coating), household articles of any kind (e.g. appliances, thermos bottle / clothes hanger), fastening systems such as plugs, wire and cable clamps, zippers, closures, locks, and snap-closures.

5 VII-2) Support devices, articles for the leisure time such as sports and fitness devices, gymnastics mats, ski-boots, inline-skates, skis, big foot, athletic surfaces (e.g. tennis grounds); screw tops, tops and stoppers for bottles, and cans.

10 VII-3) Furniture in general, foamed articles (cushions, impact absorbers), foams, sponges, dish clothes, mats, garden chairs, stadium seats, tables, couches, toys, building kits (boards / figures / balls), playhouses, slides, and play vehicles.

VII-4) Materials for optical and magnetic data storage.

15 VII-5) Kitchen ware (eating, drinking, cooking, storing).

VII-6) Boxes for CD's, cassettes and video tapes; DVD electronic articles, office supplies of any kind (ball-point pens, stamps and ink-pads, mouse, shelves, tracks), bottles of any volume and content (drinks, detergents, cosmetics including perfumes), and adhesive tapes.

20 VII-7) Footwear (shoes / shoe-soles), insoles, spats, adhesives, structural adhesives, food boxes (fruit, vegetables, meat, fish), synthetic paper, labels for bottles, couches, artificial joints (human), printing plates (flexographic), printed circuit boards, and display technologies.

25 VII-8) Devices of filled polymers (talc, chalk, china clay (kaolin), wollastonite, pigments, carbon black, TiO₂, mica, nanocomposites, dolomite, silicates, glass, asbestos).

30 Thus, a preferred embodiment of the present invention relates to shaped articles, in particular containers or boxes for food packaging and storage, containers or boxes for non-food packaging, medical devices and appliances, films for packaging, bottles and cups for beverages, any of which are based on plastic resin compositions as described above.

A molded article is preferred. The molding is in particular performed by injection-, blow-, compression- or rotational-molding, by thermoforming or extrusion.

A further preferred embodiment of the present invention relates to a monoaxially-oriented film

5 or a biaxially-oriented film which has been formed by stretching a cast film based on resin compositions as described above.

A multilayer system in which one or more layers contain a resin composition as described

10 above is also of significance in the sense of the present invention.

The presence of an additive mixture according to the instant invention facilitates the processing and improves the homogeneity of additives' distribution in a polymer.

15

Thus, further embodiments of the present invention relate to


- the use of an additive mixture as described herein as processing aid; and
- to a method for improving the processibility of a polymer which comprises incorporating and dispersing therein an additive mixture as described.

20



The following example describes the present invention in more detail. All parts and percentages are given by weight unless indicated otherwise.

25 Structural formulae of compounds used in the following examples:

Compound (I-2):



30 Compound (II-1):

Compound (III-1):

5

EXAMPLE 1:

Powdery propylene-ethylene copolymer (PP raco) with a melt flow index of 12 dg/min (measured at 230°C and 2.16 kg) is mixed with calcium stearate, IRGANOX B 215 (RTM) (= tris[2,4-di-tert-butylphenyl] phosphite and pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate] in a weight ratio of 2:1), Compound (I-2), Fischer-Tropsch wax (AdSperse 868 (RTM)) and Compound (II-1) in a Henschel mixer. Then, the formulations are compounded twice on a Berstorff ZE 25x46D (RTM) at 250°C. The granules obtained after compounding are used for injection molding on Arburg 320 S (RTM) at 240°C to produce 1 mm plaques. Haze, clarity and transmittance of the plaques are measured on a Haze-Gard plus (BYK Gardner (RTM)) according ASTM D1003 and the yellowness Index is measured on a datacolor machine according ASTM D1925.

	Formulation
PP raco	2.0 kg
Ca-stearate	750 ppm
Irganox B 215 (RTM)	1000 ppm
Compound (I-2)	2000 ppm
AdSperse 868 (RTM)	5000 ppm
Compound (II-1)	200 ppm
Haze	14.78
Yellowness Index	1.07

EXAMPLE 2:

A powdery mixture of 100 parts of compound (I-2), 20 parts of compound (II-1) and 11 parts

5 of compound (III-1) is agitated in a ball mill operated at 180 - 220 rpm under ambient conditions for 3 hours. The appearance of the resulting product as white powder differs from the originating powdery mixture by the significantly increased bulk density, better flow and feeding behavior as well as the reduced extend of dusting, bridging and agglomeration. Furthermore, its microscopic homogeneity becomes apparent in optical micrographs and,

10 particularly, by SEM (scanning electron microscope) investigations clearly illustrating the coating effect of the compound (III-1) used.

After incorporation into polypropylene by the usual means commonly known and practiced in the art (powder blending of the aforementioned composition with polypropylene fluff followed by compounding at 230°C and subsequent injection molding into 1 mm plaques), finished

15 articles are obtained with excellent clarity (i.e. low haze) without any specks or white bits, high gloss and stiffness and free from bubbles and malodorants, which had been associated before with the use of clarifiers of the sorbitol type (compounds of the formula (I)).

Since it is obvious for those skilled in the art to vary the experimental procedure given above,

20 this example exhibits just ONE possibility to practice the inventive compositions; but it is not intended herewith to limit in any way the scope of the invention. For example, alternative methods to apply coatings on the primary or agglomerated particles of sorbitol based clarifiers are well known in principal from the prior art; e.g. from EP-A-522,558 or EP-A-651,007 or EP-A-962,459, where polar or unpolar solvents are used to dissolve or

25 disperse the binding agent therein and to uniformly coat the clarifier particles subsequently. Also the teachings of DE-A-3,219,298 or EP-A-964,029, where high-speed/high-shear mixing and extrusion techniques, respectively, are recommended to produce the desired coated clarifier particles, are suited to practice the current invention. Such methods and further variations thereof can be applied on the scope of the inventive formulations and are

30 incorporated herewith by reference.

- 33a -




Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", and variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or 5 group of integers or steps.

The reference in this specification to any prior publication (or information derived from it), or to any matter which is known, is not, and should not be taken as an acknowledgment or admission or any form of suggestion that that prior publication (or information derived from it) or known matter forms part of the common general 10 knowledge in the field of endeavour to which this specification relates.


- 34 -

The claims defining the invention are as follows:

1. An additive mixture comprising the components (A), (B) and (C), wherein component (A) is at least one compound of the formulae (I-1), (I-2) and (I-3);



component (B) is the compound of the formula (II-1); and




component (C) is at least one lubricant selected from the group consisting of
10 Fischer-Tropsch wax, high-pressure polyethylene wax, Ziegler-Natta polyethylene

wax, metallocene polyethylene wax, Ziegler-Natta polypropylene wax and stearamide, erucamide and oleamide.


2. An additive mixture according to claim 1, comprising the components (A), (B), (C) and (D), wherein component (D) is at least one phenolic antioxidant which
5 is different from component (B).

3. An additive mixture according to claim 1, comprising the components (A), (B), (C) and (D), wherein component (D) is at least one phenolic antioxidant selected from esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid, β -(5-tert-butyl-4-hydroxyphenyl)propionic acid and β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid.

4. An additive mixture according to claim 1 wherein component (A) is a compound of the formula (I-2),




component (B) is a compound of the formula (II-1),



and

component (D) is a compound of the formula (III-1).



5. An additive mixture according to claim 1, comprising the components (A), (B), (C) and (D) and optionally one or more further components selected from the group consisting of: metal (I) or (II) salts of fatty acids, metal (II) oxides, dihydrotalcite, phosphites, phosphonites, organic sulfides and organic disulfides.
6. A composition comprising the components (I) and (II) wherein component (I) is a polypropylene homopolymer, random copolymer, alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic polymer; and component (II) is the additive mixture according to claim 1.
- 10 7. A composition according to claim 6 wherein component (I) is a polypropylene homopolymer.
8. A composition according to claim 6 wherein component (I) is a polypropylene random copolymer, alternating or segmented copolymer or block copolymer, containing one or more comonomers selected from the group consisting of: ethylene, C₄-C₂₀α-olefin, vinylcyclohexane, vinylcyclohexene, C₄-C₂₀alkanediene, C₅-C₁₂cycloalkandiene and norbornene derivatives.
9. A composition according to claim 6 wherein component (I) is a polypropylene copolymer, manufactured by copolymerisation of at least 75 % by weight of propylene with ethylene or another alpha-olefin comonomer, which is selected from linear or branched butene, linear or branched pentene, linear or branched hexene and linear or branched octene.
- 20 10. The use of the additive mixture according to claim 1 as clarifying agent for a polypropylene homopolymer, random copolymer, alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic

polymer.

11. An additive mixture as defined in claim 1, substantially as hereinbefore described with reference to the Examples.
12. A method for clarifying a polypropylene homopolymer, random copolymer, 5 alternating or segmented copolymer, block copolymer or a blend of polypropylene with another synthetic polymer, which comprises incorporating therein an additive mixture according to any one of claims 1 to 5 or 11.
13. A method for improving the processibility of a polymer which comprises incorporating and dispersing therein an additive mixture according to any one of 10 claims 1 to 5 or 11.