



US 20050271835A1

(19) **United States**

(12) **Patent Application Publication**
Kim

(10) **Pub. No.: US 2005/0271835 A1**

(43) **Pub. Date: Dec. 8, 2005**

(54) **LIQUID CRYSTAL DISPLAY DEVICE
HAVING THIN GLASS SUBSTRATE ON
WHICH PROTECTIVE LAYER FORMED
AND METHOD OF MAKING THE SAME**

Related U.S. Application Data

(62) Division of application No. 09/964,739, filed on Sep. 28, 2001, now Pat. No. 6,955,840, which is a division of application No. 08/954,124, filed on Oct. 20, 1997, now Pat. No. 6,327,011.

(75) Inventor: **Woong Kwon Kim**, Anyang-shi (KR)

Publication Classification

(51) **Int. Cl.⁷ C09K 19/00**

(52) **U.S. Cl. 428/1.62**

Correspondence Address:

**MORGAN LEWIS & BOCKIUS LLP
1111 PENNSYLVANIA AVENUE NW
WASHINGTON, DC 20004 (US)**

(57) **ABSTRACT**

The LCD according to present invention includes a first substrate and a second substrate, two protective layers including at least one layer formed on outer surface of the first and second substrates, a transparent electrode formed on inner surface of the first substrate or the second substrate, an alignment layer formed on the transparent electrode, and two polarizers attached on the first and second substrates.

(73) Assignee: **LG.PHILIPS LCD CO., LTD.**

(21) Appl. No.: **11/192,172**

(22) Filed: **Jul. 29, 2005**




FIG · 1a




FIG · 1b




FIG · 2




FIG. 3





FIG. 4



LIQUID CRYSTAL DISPLAY DEVICE HAVING THIN GLASS SUBSTRATE ON WHICH PROTECTIVE LAYER FORMED AND METHOD OF MAKING THE SAME

BACKGROUND OF THE INVENTION

[0001] The present invention relates to a liquid crystal display device, and more particularly to a liquid crystal display device having glass substrates uniformly and smoothly formed on its outer surface to increase the mechanical strength thereof and method of making the same.

[0002] As a display device of a television and a personal computer, etc., a large size cathode ray tube(CRT) display device has been used. However, since the screen must be separated from the electron gun more than predetermined distance for large size screen CRT, the volume is increased. Thus, this CRT cannot be applied to the thin weight, small size, and low power consumption electronic device such as a wall-mounted television, a portable television and a notebook computer, etc.

[0003] According to the purpose of display device, the flat panel display devices such as LCD(liquid crystal display), PDP(plasma display panel), ELD(electroluminescent display), and VFD(vacuum fluorescent display) have been introduced recently. Among above flat panel display device, the LCD has been dominantly researched for the good picture quality and low power consumption. The LCD-applied portable television and notebook computer are on the market resent, but there are also problems to be solved in this LCD yet. Particularly, the size and weight are important factor of the LCD investigation because of the apparatus have to be in hands of user.

[0004] For small size and light LCD, there are several methods of reducing the size and weight of the LCD element. However, the driving circuit and the thin film transistor, which are necessary element of the LCD, are so thin that the weight cannot be reduced. On the other hand, it is possible to reduce the weight of the glass substrate which is a basic element of the LCD. Specially, since the glass substrate is most heavy element of the LCD, the method of reducing the weight of the glass substrate has been continuously researched.

[0005] The light glass substrate means thin glass substrate. However, the thin glass substrate causes the damage and the surface roughness, so that the mechanical strength is weakened and the image quality of LCD is deteriorated.

[0006] In several etching methods of reducing the thickness of the glass substrate, it is representative that the substrate is etched in a case which was filled with etchant. In this etching method, however, because of impurities created in etching process, the substrate is not uniformly etched.

[0007] Therefore in proposed another etching method, the substrate is etched removing the impurities created in etching process by bubbles through a porous plate after a substrate is arranged.

[0008] In this method, however, bubbles appear on the substrate, or cracks occur by mechanical impulse, the bubbles were created in process of manufacturing glass and

diameters of several μm —several ten μm . In case that the substrate applied to a LCD desirable image quality can not be achieved because of scattering of the light in a bubble region. Further if the cracks occur on the substrate by an etching process of the glass or mechanical impulse, impurities pass into the substrate in manufacturing process of the LCD thereby a quality of the LCD is down. In addition, since the crack is intensified according to passing of time, thereby the substrate is brokendown.

[0009] Accordingly in order to decrease weight of the LCD by etching the substrate, it is very important to decrease a fault on the substrate as well as an etching method.

SUMMARY OF THE INVENTION

[0010] An object of the present invention is to provide the LCD having thin glass substrate which is light and its surface is smooth and strong from mechanical impulse.

[0011] In order to achieve this object, the LCD according to present invention includes a first substrate and a second substrate, two protective layers including at least one layer formed on outer surface of the first and second substrates, a transparent electrode formed on inner surface of the first substrate or the second substrate, an alignment layer formed on the transparent electrode, and two polarizers attached on the first and second substrates.

[0012] Each the protective layer material may be an inorganic matter having a compressive stress or an organic matter having a low viscosity coefficient, further the protective layer may be one layer including an inorganic layer or an organic layer, or a plurality of layers composed of same matter or different matter. The inorganic layer is formed by a thin layer depositing method on the substrate, while the organic layer is formed by irradiating the light such as ultraviolet, visible ray, etc., onto a thermosetting resin deposited on the substrate and curing that.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] FIGS. 1a, b are drawings showing a glass substrate having a protective layer in accordance with present invention, FIG. 1a represents a protective layer on which bubbles appear, FIG. 1b represents a protective layer on which cracks occur.

[0014] FIG. 2 is a drawing showing a liquid crystal display device having the glass substrate of the FIGS. 1a, b.

DETAILED DESCRIPTION OF THE INVENTION

[0015] Reference will now be made in detail to the present preferred embodiments of the invention, examples of which are illustrated in the accompanying drawings.

[0016] FIGS. 1a, b are drawings showing a glass substrate 1 having the protective layer, as shown in FIG. 1a, a bubble, which is formed in process of manufacturing glass and its diameter is several μm —several ten μm , is appeared on the thin substrate which is etched less than 0.7 mm. Further, since the thickness of the glass substrate 1 is very thin, a crack may be occurred by fine mechanical impulse as shown in FIG. 1b.

[0017] A transparent protective layer **8** formed on the substrate **1** includes a plurality of layer having an inorganic matter or an organic matter, or an inorganic matter and an organic matter, then a refractive index of each layer is 1.4-1.6. the inorganic layer **8** is formed on the substrate **1** by general thin layer deposition method such as sputtering method, CVD(chemical vapor deposition) method, and evaporation method. While organic layer **8** is formed by irradiating the light such as ultraviolet, visible ray, etc., onto a thermosetting resin deposited on the substrate and curing that. At this time the inorganic matter having the compressive stress and the organic matter having the low viscosity coefficient(about several cp—several ten cp).

[0018] When bubbles appear on the surface of substrate **1** as shown in FIG. 1a, an desirable image quality can not be achieved because of scattering of the light in a bubble region.

[0019] Since the protective layer **8** is formed on the bubble as well as the surface of substrate **1**, diameters of the bubbles are minimized from micrometer to angstrom. Accordingly when the substrate **1** is applied to a LCD, it is possible to prevent decreasing of an image quality by small scattering of the light in that region.

[0020] Additionally if cracks occur on the substrate **1** as shown in FIG. 1b, the substrate **1** is broken down slowly according to passing of time in manufacturing process of the LCD. Further an impurity inserted in the crack cause to decrease quality of the LCD. While the inorganic layer prevent transmission of the crack by the compressive stress, and the cured organic layer also prevent transmission of the crack, thereby a strong glass substrate for mechanical impulse can be achieved.

[0021] The protective layer **8** may be one layer with an inorganic layer or an organic layer, or a plurality of layers composed of same matter or different matter.

[0022] FIG. 2 is a drawing showing a liquid crystal display device having two glass substrates including the protective layers.

[0023] Each thickness of a first substrate **10a** and a second substrate **10b** is less than 0.7 mm, a transparent electrode **12** made of such as ITO(indium tin oxide) is formed on the first substrate. In present embodiment, although, the transparent electrode **12** is formed on the first substrate, it is possible that the transparent electrode **12** is formed on the second substrate. Further alignment layers **13a**, **13b** including polyimide or photo alignment material are formed on the transparent electrode **12**, then an alignment direction of the alignment layer is determined by using a mechanical or optical method. On the other hand a liquid crystal layer **15** is formed between the first and second substrates. The protective layer **18a**, **18b** are an inorganic layers or an organic layers, or a plurality of layers composed of same matter or different matter and formed on outside surface of both the first substrate **10a** and the second substrate **10b**. Continually a first polarizer **14a** and a second polarizer **14b** are formed on the protective layers **18a**, **18b**.

[0024] Although not showing with drawing, TFTs(thin film transistors) are formed on the first substrate **10a**, and a color filter layer is formed on the second substrate.

[0025] After etching, grinding and scribing two glasses by general etching method, the protective layers **18a**, **18b** are formed on that, and the transparent electrode **12** is formed on the protective layer **18a**, **18b** by the sputtering method. At this time, also it is possible to make the substrate **10a**, **10b** after the passivation layers **18a**, **18b** are formed on each the glass. Further the TFTs(not illustrated) are formed on the first substrate **10a** by depositing and photoetching a metal layer, and the alignment layer **13a**, **13b** are formed by mechanical depositing or injecting the alignment material. Thereafter a plurality of spacers(not illustrated) are dispersed to maintain a gap between the first and second substrate **10a**, **10b**. After pouring the liquid crystal into a region between the first and second substrates and the two substrates are sealed, and thereby the LCD according to the present invention is completed.

[0026] In the above-discussed structure, since the protective layer includes an inorganic or an organic matter, the thin glass substrate through etching is bearable from a mechanical impulse.

[0027] Further in etching process, since the inorganic or organic matter have diameters of the bubbles which a quality of the LCD is down by that decreased, it is possible to achieve the good quality LCD having soft and uniform surface.

[0028] When cracks occur on the substrate, the protective layer prevent transmission of the crack thereby the substrate is not broken down.

[0029] As a result, the present invention provides the good quality LCD having thin glass substrate light and its surface is smooth and strong from mechanical impulse.

[0030] Other embodiments of the invention will be apparent to those skilled in the art from consideration of the specification and practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the invention being indicated by the following claims.

1-16. (canceled)

17. A method of manufacturing a thin glass substrate of a liquid crystal display device, comprising the steps of:

providing a glass;

forming a substrate by processing the glass; and

forming a protective layer on the glass substrate.

18-19. (canceled)

20. The method according to claim 17, wherein the step of forming the protective layer includes the step of irradiating the light after depositing an organic matter on the glass substrate.

21. The method according to claim 20, wherein the light is an ultraviolet or a visible ray.

22. The method according to claim 17, wherein the step of forming the protective layer includes the step of coating an inorganic matter on the glass substrate.

23-27. (canceled)

* * * * *