

(19) **DANMARK**

(10) **DK/EP 1716080 T4**



(12) **Oversættelse af ændret
europæisk patentskrift**

Patent- og
Varemærkestyrelsen

-
- (51) Int.Cl.: **C 01 F 11/18 (2006.01)** **C 01 F 11/00 (2006.01)** **C 09 C 1/02 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2015-06-01**
- (80) Dato for Den Europæiske Patentmyndigheds bekendtgørelse om opretholdelse af patentet i ændret form: **2015-02-11**
- (86) Europæisk ansøgning nr.: **04821191.6**
- (86) Europæisk indleveringsdag: **2004-12-14**
- (87) Den europæiske ansøgnings publiceringsdag: **2006-11-02**
- (86) International ansøgning nr.: **EP2004053437**
- (87) Internationalt publikationsnr.: **WO2005070830**
- (30) Prioritet: **2003-12-24 BE 200300684**
- (84) Designerede stater: **AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU MC NL PL PT RO SE SI SK TR**
- (73) Patenthaver: **S.A. LHOIST RECHERCHE ET DEVELOPPEMENT, Rue Charles Dubois, 28, 1342 Ottignies-Louvain-La-Neuve, Belgien**
- (72) Opfinder: **GAMBIN, Amandine, Rue de l'Ognon 19, F-70270 Ternuay, Frankrig**
LAUDET, Alain, Rue Théodore Baron 28, Bte 4, B-5000 Namur, Belgien
FRANCOISSE, Olivier, Avenue des Vallées 35, B-1341 Cérroux-Mousty, Belgien
- (74) Fuldmægtig i Danmark: **PLOUGMANN & VINGTOFT A/S, Rued Langgaards Vej 8, 2300 København S, Danmark**
- (54) Benævnelse: **PULVERSAMMENSÆTNING PÅ BASIS AF EN CALCIUM-MAGNESIUM-FORBINDELSE**
- (56) Fremdragne publikationer:
EP-A- 0 773 912
WO-A-01/40576
US-A- 3 598 624
US-A- 3 738 938
US-A- 5 422 092
US-A- 6 136 085
DE-A1- 3 713 600
DE-A1- 3 729 482
DE-A1- 19 745 191
DE-A1- 19 901 049
DE-B4- 19 811 607
DE-B4- 19 824 237
DE-C2- 3 232 081
DE-C2- 4 034 417
DE-U1- 20 011 604
JP-A- H 101 345

Fortsættes ...

JP-A- H09 268 012

US-A- 4 051 056

US-A- 4 781 759

US-A- 5 340 558

US-A1- 2003 138 614

Römp- Lexikon Chemie; Stichwort: "Attapulgit"

Römp- Lexikon Chemie; Stichwort: "Perlite"

Römp- Lexikon Chemie; Stichwort: "Siliciumdioxid"

Römp- Lexikon Chemie; Stichwort: "Vermiculit"

<http://de.wikipedia.org>; Stichwort: "Bentonit"

Römp- Lexikon Chemie; Stichwort: "Rieselhilfen"

<http://en.wikipedia.org>; Stichwort "anticaking agent"

DIN EN ISO 14688-1:2011-06

DIN 18 550 Part 2; Janvier 1985

The present invention relates to a composition based on a powdery calco-magnesian compound.

Powdery calco-magnesian compound means a collection of solid particles, either in
 5 hydroxide form or in the form of a carbonate, complying with the following formula I:



10 in which

A is a $=(\text{OH})_2$ or $=\text{CO}_3$ group, and

x and y are molar fractions where $0 < x \leq 1$ and $0 \leq y \leq 1$.

This calco-magnesian material can obviously contain impurities, such as silica,
 15 alumina, etc, to the extent of a few percent. In general terms, the size of the particles of this powdery materials is entirely less than 1 mm and often less than 250 μm .

A particular case of a powdery calco-magnesian compound is slaked lime, also
 20 referred to as hydrated lime (calcium hydroxide – $\text{Ca}(\text{OH})_2$), which can also comprise impurities, such as silica, alumina, magnesium oxide or calcium carbonate, to the extent of a few per cent, and contain free water, namely water not chemically bound to the compound, up to approximately 5%.

25 Such a compound is renowned for its lacks of flowability in flowing during storage, handling and transport, in particular pneumatic transport in dilute phase, often used in the case of slaked lime. These problems of flowing, in particular related to the fineness of the particles of the hydrated lime, exhibit themselves mainly in the form of an agglomeration of particles together or an accumulation of these on the walls.

30 Such behaviour is detrimental to the use of said compound:

- in reducing the flow rate during pneumatic transport by progressive deposition of the compound on the walls, which may go as far as the blockage of the installations,

35 - by interfering with regulation when the compound is used as a neutraliser of acidic

compounds,

- requiring specific and regular maintenance operations at places which are sometimes not very accessible.

5

It is known how to promote the flow of powders by means of organic liquid additives, in particular surfactants [JP 08-109016, JP 09-165 216]. However, the incorporation of such organic liquids, which are sometimes toxic, to a mineral compound such as slaked lime, is often contrary to its application, in particular in the
10 case of use for the purification of flue gas (the problem of volatile organic compounds, following on from the release of organic additives).

A filler composition is also known; containing calcium carbonate and silica, precipitated under the form of fine particles (see WO 01/40576).

15

The aim of the present invention is to obtain a powdery composition based on a calco-magnesian compound, with a high purity and entirely mineral, that limits the lacks of flowability described above, without having recourse to an organic additive.

20 According to the invention the above problem is resolved by means of a powdery composition based on a calco-magnesian compound complying with formula I given above, which contains, in a quantity of less than 5% by weight of the said composition, a mineral solid flowing agent in the form of particles having a size greater than 125 μm and chosen from amongst the group consisting of vermiculite,
25 perlite, attapulgite and silica.

Size greater than a given value means that at least 95% of the particles will have this greater size as a minimum.

30 Many methods make it possible to describe the flow of powdery products such as slaked lime. These diagnosis methods are based in particular on the use of shear cells, in particular the Jenike cell, or on the determination of the flowing index, based on Carr's theory or on the dissemination of friction and fall angles.

35 However, the flow diagnosis methods referred to above, always related to a flow

under stress ("static" methods), do not make it possible to discriminate the various powdery compositions based on calco-magnesian compounds in their behaviour under flowing in pneumatic (dynamic) transport, namely during a true flow of the powder in dilute phase in an air flow.

5

It has therefore seemed necessary to develop a diagnosis method appropriate to the flow of powdery products in pneumatic transport. This method consists of applying a dynamic adhesion test (DAT) that is performed in a specific device.

10 This device is illustrated in the accompanying single figure.

It comprises a powder transport loop, formed from a succession of rectilinear conduits 1, 6 and 8 connected by elbows 2 and 7. The rectilinear conduit 1 has a length of 10 cm downstream of the powder injection point and an inside diameter of
15 2.54 cm, and the rectilinear conduit 8 a length of 27.5 cm and an inside diameter of 2.54 cm. The rectilinear conduit 6 is composed of a broadening 3 with a length of 8.90 cm and an inlet diameter of 2.54 cm, a sleeve 4 with a length of 30 cm and an inside diameter of 4.25 cm, and a reduction 5 with a length of 9.85 cm and an outlet diameter of 2.54 cm. The elbows 2 and 7 that connect them have a radius of
20 curvature of 20 cm.

The device also comprises a compressed air source, in the form of a compressor 9 that introduces compressed dry air into the conduit 0. A dosing "device" (or "apparatus") 10 provided with a conveyor screw 11 feeds the powdery substance 12
25 to be studied into the conduit 1.

The outlet from the last rectilinear conduit 8 is connected to a flexible pipe 13 that enters a reservoir 14 through a downward-directed elbow 15. A suction fan 16 with a power of 1200 W and provided with a filter 17 with a total filtering surface of 1.2
30 m² is arranged at the top of the reservoir 14. The powdery substance that is passed through the conduits accumulates at the bottom of the reservoir 18.

The powder, fed by means of a dosing device 10, is carried in the circuit by the air flow generated therein. The total weight of powder deposited on the various walls of
35 the elements 1 to 8 is determined by weighing, after the test. This total weight of

powder deposited is referred to the integral of the measured weight and is an inverse measurement of the quality of the flow of the powder by pneumatic transport in dilute phase in air.

- 5 The results of the test described above have appeared to be consistent with experience of industrial use of powdery calco-magnesian compounds, namely that this test effectively distinguishes the products presenting problems of dynamic flowing from those that have satisfactory behaviour.
- 10 It is found in particular that, all other things being equal, a calco-magnesian compound will have a dynamic flow in dilute phase that is less good, the finer the size of its particles.

- In order to improve the dynamic flowing of calco-magnesian compounds, the
- 15 mineral solid additive was initially chosen from amongst powdery compounds deemed to prevent the formation of clots, to prevent agglomeration or to be "flowing agents"; mainly talc, silica, sepiolite, vermiculite, bentonite, diatomaceous earth and limestone can be cited, as well as magnesium carbonate, oxide and hydroxide.
- 20 Surprisingly, not all the additives preventing agglomeration cited above systematically improve the dynamic flow of powdery compositions based on calco-magnesian compounds, within the meaning of the problem posed by the present invention. In particular, the addition of talc, known to be a lubricating agent, does not afford any positive effect on dynamic flow, or even degrades it. The same
- 25 observation is made when sepiolite or bentonite is used as an additive.

- The use of magnesium carbonate, oxide or hydroxide as an additive results only in a slight improvement in the results of the dynamic flow test, an improvement that is insufficient to resolve the problems of flow mentioned above.

30

On the other hand, unpredictably, the addition according to the invention of vermiculite, in particular "raw", perlite or attapulgite, leads to significant improvements in the dynamic flowing of powdery compositions based on calco-magnesian compounds.

35

The powdery composition based on calco-magnesian compound according to the invention contains one or other or a combination of mineral additives from amongst vermiculite, perlite or attapulgite, at less than 5% by weight, preferably no more than 3%, and very advantageously no more than 2% by weight of the composition.

- 5 It is necessary to maintain the calco-magnesian compound purity in the composition according to the invention at a value greater than 90%, preferably greater than 92%, in order to limit the dilution of the active calco-magnesian compound and to preserve performance in the applications sought.
- 10 In addition, the aforementioned mineral additive will have a fairly coarse particle size distribution. This is because, unlike the teaching of documents that cite microsilica (fumed silicon oxide) or finely divided minerals as additives, the additive incorporated in the calco-magnesian compound according to the present invention will have to have a particle size essentially greater than 125 μm and preferably
- 15 greater than 250 μm .

- Unexpectedly, the powdery compositions based on calco-magnesian compounds according to the invention have good dynamic flowing in dilute phase, without any limitation on the fineness of their particles, contrary to the observations made in the
- 20 case of conventional calco-magnesian compounds without additive where in particular particle sizes of less than 20 μm have the effect of a rapid blocking of pneumatic installations. This property of the compounds according to the invention makes it possible to broaden their field of application. This is because a fine product will react better, in particular in many applications of hydrated lime, such as the
- 25 purification of flue gases.

The invention will now be described in more detail by means of non-limiting examples.

30 EXAMPLE 1

An industrial-production slaked lime was chosen as a reference calco-magnesian compound. Its purity is 95% by weight of $\text{Ca}(\text{OH})_2$; it has a particle size distribution of up to 250 μm and a free water content of 1%. This lime is introduced into the dosing device of the dynamic flowing test described above.

The device is supplied with dry compressed air (dew point 3°C), pre heated to 30°C, at a flow rate of 25 m³/h, which provides an initial speed of approximately 14 m/s. The reference slaked lime is apportioned at 1 kg/h. The test provides that 2 kg of material is thus measured out.

5

At the end of the experiment, the weight of slaked lime that has accumulated on the walls of all the conduits was determined and compared with the total weight measured out, namely 2 kg. In the case of the reference slaked lime, the result is 65 g/kg.

10

According to the calibration of the dynamic test of the present invention with respect to the quality of the flow of products used industrially, the compounds having as a test result less than 45 g/kg of product accumulated on the walls must be considered to have very good behaviour under dynamic flowing in dilute phase. In the same way, the compound for which the result of the test is greater than 58 g/kg of product accumulated on the walls is considered to have a behaviour in flow posing problems in industrial use, in particular during pneumatic transport in dilute phase.

EXAMPLE 2

20 In this example 2, additives that are industrial products, used as delivered, are added to the same slaked lime as in example 1.

According to the invention, "raw" vermiculite is added, to the extent of 2% by weight of the composition thus obtained, which is mixed in order to homogenise it.

25 The size of the particles of this additive is greater than 90 µm. The composition is then subjected to the dynamic flowing test, under the same conditions as in example 1.

In the case of the present mixture of slaked lime and raw vermiculite, the result of the test is 40 g/kg of product accumulated on the walls, which classifies this composition amongst those having very good behaviour in dynamic flow, according to the criterion cited in example 1 (less than 45 g/kg).

In the same way, compositions according to the invention were prepared starting from the slaked lime of example 1, so as to contain 2% by weight respectively of

35

expanded or exfoliated vermiculite, expanded perlite and attapulgite. The size of the particles of these additives is greater than 90 μm . The results of the test are respectively 31, 38 and 39 g/kg of product accumulated on the walls with respect to the measured weight, characteristic values of the compositions having very good
 5 behaviour in dynamic flow.

In order to demonstrate the benefit of the powdery compositions based on calco-magnesian compounds according to the invention on the quality of their flow, it is useful to express the results of the dynamic flowing tests in terms of percentage
 10 reduction in the quantity accumulated on the walls, compared with the case of the reference calco-magnesian compound without additive. Reductions of 38%, 52%, 42% and 40% are obtained respectively for the compounds containing respectively raw vermiculite, expanded vermiculite, expanded perlite and attapulgite.

15 On the other hand, if talc, sepiolite or bentonite are added as an additive, to the extent of 2% by weight of the final composition, the results of the test are respectively 64, 60 and 84 g/kg of product accumulated on the walls with respect to the measured weight. These additives result in the obtaining of a formula having poor behaviour in dynamic flow (results > 58 g/kg), or even a greatly degraded flow
 20 compared with the compounds without additive, in the case of bentonite.

All these results are summarised in Table 1.

Composition tested	Ratio by weight of product accumulated on the walls [g/kg]	Percentage reduction in accumulation on the walls compared with slaked lime
Reference slaked lime	65	-
2% mixture by weight of raw vermiculite	40	38%
2% mixture by weight of expanded vermiculite	32	52%
2% mixture by weight of expanded perlite	38	42%
2% mixture by weight of attapulgite	39	40%
2% mixture by weight of talc	64	2%

2% mixture by weight of sepiolite	60	8%
2% mixture by weight of bentonite	84	-30%

Table 1. Results of the dynamic flowing test for the reference slaked lime, compositions based on this lime, according to the invention, and compositions with additives not improving dynamic flow.

5

EXAMPLE 3

In this example 3, the additives of example 2 were subjected to a granulometric cut by sieving, so as to retain only particles less than 125 μm .

- 10 To the same slaked lime as in example 1, "raw" vermiculite < 125 μm is added, to the extent of 2% by weight of the composition thus obtained, which is mixed in order to homogenise it. The composition is then subjected to the dynamic flow test, under the same conditions as in example 1. The result of the test shows very severe deterioration in flow compared with the lime without additive with 122 g/kg
- 15 of material stuck to the walls.

- In the same way, compositions were prepared starting from the slaked lime of example 1 so as to obtain mixtures containing 2% by weight respectively of expanded vermiculite < 125 μm , attapulgite < 125 μm and sand < 125 μm . The
- 20 results of the test are respectively 62, 58 and 57 g/kg of product accumulated on the walls with respect to the measured mass. These formulae therefore exhibit poor behaviour in dynamic flow, with respectively only 5%, 11% and 13% reduction in sticking to the walls.
- 25 These results demonstrate the critical character of the distribution of particle sizes of the additive used in the invention, an additive which loses its efficacy if it is too fine.

All the results of example 3 are summarised in table 2.

30

Composition tested	Ratio by weight of product accumulated on the walls [g/kg]	Percentage reduction in accumulation on the walls compared with slaked lime
Reference slaked lime	65	-
2% mixture by weight of raw vermiculite < 125 μm	122	-88%
2% mixture by weight of expanded vermiculite < 125 μm	62	5%
2% mixture by weight of attapulgite < 125 μm	58	11%
2% mixture by weight of sand < 125 μm	57	13%

Table 2. Results of the dynamic flow test for the reference slaked lime and in the case of formulae based on additives < 125 μm .

5

EXAMPLE 4

IN THIS EXAMPLE 4, THE ADDITIVES OF EXAMPLE 2 WERE SUBJECTED TO A GRANULOMETRIC CUT BY SIEVING, SO AS TO RETAIN ONLY THE PARTICLES GREATER THAN 250 μm .

- 10 "RAW" VERMICULITE > 250 μm IS ADDED TO THE SAME SLAKED LIME AS IN EXAMPLE 1, TO THE EXTENT OF 2% BY WEIGHT OF THE COMPOSITION THUS OBTAINED, WHICH IS MIXED IN ORDER TO HOMOGENISE IT. THE COMPOSITION IS THEN SUBJECTED TO THE DYNAMIC FLOWING TEST, UNDER THE SAME CONDITIONS AS IN EXAMPLE 1. THE RESULT OF THE TEST SHOWS AN APPRECIABLE IMPROVEMENT IN FLOW COMPARED WITH THE LIME WITHOUT ADDITIVE WITH ONLY 39 G/KG OF
- 15 MATERIAL STUCK TO THE WALL, THAT IS TO SAY A REDUCTION OF 41% COMPARED WITH THE NON-TREATED LIME.

- IN THE SAME WAY, COMPOSITIONS WERE PREPARED STARTING FROM THE SLAKED LIME OF EXAMPLE 1, SO AS TO OBTAIN MIXTURES CONTAINING 2% BY WEIGHT, RESPECTIVELY OF EXPANDED
- 20 VERMICULITE > 250 μm , ATTAPULGITE > 250 μm AND SAND > 250 μm . THE RESULTS OF THE TEST ARE RESPECTIVELY 32, 39 AND 42 G/KG OF PRODUCT ACCUMULATED ON THE WALLS COMPARED WITH THE DOSED MASS, A SIGN OF COMPOSITIONS HAVING VERY GOOD BEHAVIOUR IN DYNAMIC FLOW. RESPECTIVELY 52%, 40% AND 35% REDUCTIONS IN STICKING TO THE WALLS

ARE OBTAINED.

THESE RESULTS CONFIRM THE DECISIVE CHARACTER OF THE SIZE DISTRIBUTION OF THE PARTICLES OF THE ADDITIVE.

5

HOWEVER, IF LIMESTONE > 250 μm OR RAW DOLOMITE (MIXED CALCIUM AND MAGNESIUM CARBONATE) > 250 μm ARE USED AS AN ADDITIVE TO THE LIME OF EXAMPLE 1, TO THE EXTENT OF 2% BY WEIGHT OF THE FINAL MIXTURE, THE MASSES STUCK TO THE WALLS DURING THE TEST WILL BE RESPECTIVELY 53 AND 52 G/KG. FOR THE RECORD, GOOD BEHAVIOUR IN DYNAMIC FLOW IS

10 CHARACTERISED BY A DEGREE OF STICKING TO THE WALLS OF LESS THAN 45 G/KG. THE LATTER FORMULAE THEREFORE DO NOT HAVE SATISFACTORY BEHAVIOUR IN DYNAMIC FLOW.

THEREFORE THE FACT OF HAVING ADDITIVES WHERE THE SIZE OF THE PARTICLES IS COARSE, THAT IS TO SAY GREATER THAN 250 μm , IS NOT A SUFFICIENT CONDITION FOR OBTAINING A

15 COMPOSITION HAVING GOOD DYNAMIC FLOW.

ALL THE RESULTS OF EXAMPLE 4 ARE SUMMARISED IN TABLE 3.

Composition tested	Ratio by weight of product accumulated on the walls [g/kg]	Percentage reduction in accumulation on the walls compared with slaked lime
Reference slaked lime	65	-
2% mixture by weight of raw vermiculite > 250 μm	39	41%
2% mixture by weight of expanded vermiculite > 250 μm	32	52%
2% mixture by weight of attapulgite > 250 μm	39	40%
2% mixture by weight of sand > 250 μm	42	35%
2% mixture by weight of lime > 250 μm	53	20%
2% mixture by weight of raw dolomite > 250 μm	52	18%

Table 3. Results of the dynamic flowing test for the reference slaked lime, and in the case of compositions based on additives > 250 μm .

5

EXAMPLE 5

THE REFERENCE SLAKED LIME OF EXAMPLE 1 WAS SELECTED IN A DYNAMIC SEPARATOR, SO AS TO KEEP ONLY THE PARTICLES LESS THAN 20 μm . THIS SELECTED SLAKE LIME WAS TESTED ON THE DYNAMIC FLOW DEVICE UNDER THE SAME CONDITIONS AS IN EXAMPLE 1. HOWEVER, THIS SELECTED LIME HAS LESS GOOD FLOW THAN THE REFERENCE LIME, BECAUSE OF ITS GREATER FINENESS; IT WAS POSSIBLE TO MEASURE OUT ONLY 0.75 KG OF LIME BEFORE TOTAL BLOCKAGE OF THE TEST DEVICE. THE MASS ACCUMULATED ON THE WALLS, REFERRED TO AS THE MEASURED MASS, IS 97 G/KG.

15

A COMPOSITION ACCORDING TO THE INVENTION WAS PREPARED STARTING FROM THIS SELECTED SLAKE LIME, SO AS TO OBTAIN RESPECTIVELY A COMPOSITION CONTAINING 2% AND 4% OF EXPANDED VERMICULITE. IN BOTH CASES, IT IS POSSIBLE TO MEASURE OUT 2 KG OF COMPOSITION WITHOUT BLOCKING THE DEVICE. MOREOVER, THE MASS ACCUMULATED ON THE WALLS, REFERRED TO THE MEASURED-OUT MASS, IS 39 G/KG FOR THE COMPOSITION WITH 2% VERMICULITE AND 22

20

G/KG FOR THAT WITH 4% VERMICULITE. THE REDUCTION IN MASS ACCUMULATED ON THE WALLS WITH RESPECT TO THE SELECTED SLAKE LIME IS RESPECTIVELY 60% AND 77%.

THE RESULTS OF EXAMPLE 5 ARE SUMMARISED IN TABLE 4.

5

Composition tested	Ratio by weight of product accumulated on the walls [g/kg]	Percentage reduction in accumulation on the walls compared with slaked lime
Selected slaked lime	97	-
2% mixture by weight of expanded vermiculite	39	60%
4% mixture by weight of expanded vermiculite	22	77%

TABLE 4. RESULTS OF THE DYNAMIC FLOW TEST FOR THE SELECTED SLAKE LIME AND THE COMPOSITIONS ACCORDING TO THE INVENTION BASED ON THIS LIME.

Patentkrav

1. Pulversammensætning på basis af en calcium-magnesium-forbindelse i overensstemmelse med formel I



5

i hvilken

A er en $=(\text{OH})_2$ eller $=\text{CO}_3$ gruppe, og

x og y er molfraktioner, hvor $0 < x \leq 1$ og $0 \leq y \leq 1$,

som, i en mængde på mindre end 5 vægtprocent af nævnte sammensætning,

10 indeholder et mineralsk strømningsmiddel i form af partikler med en størrelse der er større end $125 \mu\text{m}$ og udvalgt fra gruppen bestående af vermiculit, perlit og attapulgit.

2. Sammensætning ifølge krav 1, **kendetegnet ved, at** det indeholder

15 strømningsmidlet i en mængde på mindre end eller lig med 3 vægtprocent, fortrinsvis omkring 2 vægtprocent.

3. Sammensætning ifølge et af kravene 1 og 2, **kendetegnet ved at** det mineralske strømningsmiddel har en partikelstørrelse større end $250 \mu\text{m}$.

20

4. Sammensætning ifølge et hvilket som helst af kravene 1 til 3, **kendetegnet ved, at** det mineralske strømningsmiddel er attapulgit.

5. Sammensætning ifølge et hvilket som helst af kravene 1 til 3, **kendetegnet**

25 **ved, at** det mineralske strømningsmiddel er rå vermiculit.

6. Sammensætning ifølge et hvilket som helst af kravene 1 til 3, **kendetegnet ved, at** det mineralske strømningsmiddel er ekspanderet vermiculit.

30 7. Sammensætning ifølge et hvilket som helst af kravene 1 til 3, **kendetegnet ved, at** det mineralske strømningsmiddel er ekspanderet perlit.

8. Sammensætning ifølge et hvilket som helst af kravene 1 til 7, **kendetegnet ved at** calcium-magnesium-forbindelsen er ved en renhedsgrad større end 90%,

fortrinsvis 92 vægtprocent, i sammensætningen.

9. Sammensætning ifølge et hvilket som helst af kravene 1 til 8, **kendetegnet ved at** calcium-magnesium-forbindelsen har en partikelstørrelse på mindre end 5 20 μm .

