



(51) International Patent Classification:

D21C 3/04 (2006.01)

(21) International Application Number:

PCT/CA2021/000073

(22) International Filing Date:

20 August 2021 (20.08.2021)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

3,110,390 25 February 2021 (25.02.2021) CA

(71) Applicant: SIXRING INC. [CA/CA]; 1500, 140 - 10 Avenue SW, Calgary, AB T2G 0R1 (CA).

(72) Inventors: PURDY, Clay; #20 Chinook Place SW, Medicine Hat, AB T1A 8S1 (CA). WEISSENBERGER, Markus; 19 Copperstone Blvd, Calgary, AB T2Z 0G7 (CA). PAGELS, Markus; 657 Hawkside Mews NW, Calgary, AB T3G 3S1 (CA). WYNNYK, Kyle G.; 10 Hamlet Road SW, Calgary, AB T2V 3C8 (CA).

(74) Agent: PIGEON, Charles O.; Burnet, Duckworth & Palmer LLP, 2400, 525 - 8 Ave SW, Calgary, AB T2P 1G1 (CA).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: COMPOSITIONS COMPRISING SULFURIC ACID AND CARBONYL-CONTAINING NITROGENOUS BASE COMPOUNDS

(57) Abstract: An aqueous composition comprising: sulfuric acid; a modifying agent comprising a carbonyl-containing nitrogenous base compound; and a peroxide. Said composition being capable of delignifying biomass under milder conditions than conditions under which kraft pulping takes place.



COMPOSITIONS COMPRISING SULFURIC ACID AND CARBONYL-CONTAINING NITROGENOUS BASE COMPOUNDS

FIELD OF THE INVENTION

The present invention is directed to a method and composition useful in decomposing organic material by oxidation such as, but not limited to, the delignification of wood or plant substance, as an example and more specifically, to a method and composition for performing such under more optimal conditions than those under which the kraft process is currently conducted.

BACKGROUND OF THE INVENTION

The first step in paper production and most energy-intensive one is the production of pulp. Notwithstanding water, wood and other plant materials used to make pulp contain three main components: cellulose fibers; lignin; and hemicelluloses. Pulping has a primary goal to separate the fibers from the lignin. Lignin is a three-dimensional polymer which figuratively acts as a mortar to hold all the fibers together within the plant. Its presence in finished pulp is undesirable and adds nothing to the finished product. Pulping wood refers to breaking down the bulk structure of the fiber source, be it chips, stems or other plant parts, into the constituent fibers. The cellulose fibers are the most desired component when papermaking is involved. Hemicelluloses are shorter branched polysaccharide polymers consisting of various sugar monosaccharides which form a random amorphous polymeric structure. The presence of hemicellulose in finished pulp is also regarded as bringing no value to a paper product. This is also true for biomass conversion. The challenges are similar. Only the desired outcome is different. Biomass conversion would have the further breakdown to monosaccharides as a desired outcome while a pulp & paper process normally stops right after lignin dissolution.

There are two main approaches to preparing wood pulp or woody biomass: mechanical treatment and chemical treatment. Mechanical treatment or pulping generally consists of mechanically tearing the wood chips apart and, thus, tearing cellulose fibers apart in an effort to separate them from each other. The shortcomings of this approach include: broken cellulose fibers, thus shorter fibers and lignin being left on the cellulose fibers thus being inefficient or non-optimal. This process also consumes large amounts of energy and is capital intensive. There are several approaches included in chemical pulping. These are generally aimed at the degradation the lignin and hemicellulose into small, water-soluble molecules. These now degraded components can be separated from the cellulose fibers by washing the latter without depolymerizing the cellulose fibers. The chemical process is currently energy intensive as well as high amounts of heat and / or higher pressures are typically required; in many cases, agitation or mechanical intervention are also required, further adding inefficiencies and costs to the process.

There exist pulping or treatment methods which combine, to a various extent, the chemical aspects of pulping with the mechanical aspects of pulping. To name a few of the widely employed pulping methods referred to above, one must include thermomechanical pulping (also commonly referred to as TMP), and chemi-thermomechanical pulping (CTMP). Through a selection of the advantages provided by each general pulping method, the treatments are designed to reduce the amount of energy required by the mechanical aspect of the pulping treatment. This can also directly impact the strength or tensile strength degradation of the fibers subjected to these combination pulping approaches. Generally, these approaches involve a shortened chemical treatment (compared to conventional exclusive chemical pulping) which is then typically followed by mechanical treatment to separate the fibers.

The most common process to make pulp for paper production is the kraft process. In the kraft process, wood chips are converted to wood pulp which is almost entirely pure cellulose fibers. The multi-step kraft process consists of a first step where wood chips are impregnated / treated with a chemical solution. This is done by soaking the wood chips and then pre-heating them with steam. This step swells the wood chips and expels the air present in them and replaces the air with the liquid. This produces black liquor a resultant by-product from the kraft process. It contains water, lignin residues, hemicellulose and inorganic chemicals. White liquor is a strong alkaline solution comprising sodium hydroxide and sodium sulfide. Once the wood chips have been soaked in the various chemical solutions, they undergo cooking. To achieve delignification in the wood chips, the cooking is carried out for several hours at temperatures reaching up to 176°C. At these temperatures, the lignin degrades to yield water soluble fragments. The remaining cellulosic fibers are collected and washed after the cooking step.

US patent number 5,080,756 teaches an improved kraft pulping process and is characterized by the addition of a spent concentrated sulfuric acid composition containing organic matter to a kraft recovery system to provide a mixture enriched in its total sulfur content that is subjected to dehydration, pyrolysis and reduction in a recovery furnace. The organic matter of the sulfuric acid composition is particularly beneficial as a source of thermal energy that enables high heat levels to be easily maintained to facilitate the oxidation and reduction reactions that take place in the furnace, thus resulting in the formation of sulfide used for the preparation of cooking liquor suitable for pulping.

Caro's acid, also known as peroxymonosulfuric acid (H_2SO_5), is one of the strongest oxidants known. There are several known reactions for the preparation of Caro's acid but one of the most straightforward involves the reaction between sulfuric acid (H_2SO_4) and hydrogen peroxide (H_2O_2).

Preparing Caro's acid in this method allows one yield in a further reaction potassium monopersulfate (PMPS) which is a valuable bleaching agent and oxidizer. While Caro's acid has several known useful applications, one noteworthy is its use in the delignification of wood.

Biofuel production is another potential application for the kraft process. One of the current drawbacks of biofuel production is that it requires the use of food grade plant parts (such as seeds) in order to transform polysaccharides into fuel in a reasonably efficient process. The carbohydrates could be obtained from cellulosic fibers, by using non-food grade biomass in the kraft process; however, the energy intensive nature of the kraft process for delignification makes this a less commercially viable option. In order to build a plant based chemical resource cycle there is a great need for energy efficient processes which can utilize plant-based feedstocks that don't compete with human food production.

While the kraft pulping process is the most widely used chemical pulping process in the world, it is extremely energy intensive and has other drawbacks, for example, substantial odours emitted around pulp producing plants or general emissions that are now being highly regulated in many pulp and paper producing jurisdictions. In light of the current environmental challenges, economic challenges and climatic changes, along with emission fees being implemented, it is highly desirable to optimize the current pulping processes. In order to provide at least linear quality fibers without the current substantial detriment to the environment during the production thereof. Accordingly, there still exists a need for a composition capable of performing delignification on wood substance under reduced temperatures and pressures versus what is currently in use without requiring any additional capital expenditures.

SUMMARY OF THE INVENTION

The inventors have developed novel compositions which are capable of being used to delignify biomass under room temperature conditions (i.e. 20-25°C). While such compositions can also be used for other applications, it is noteworthy to point out that despite the fact that they contain sulfuric acid and peroxide, they present better handling qualities than conventional compositions comprising sulfuric acid and a peroxide component.

According to an aspect of the present invention, there is provided an aqueous acidic composition comprising:

- sulfuric acid;
- a carbonyl-containing nitrogenous base compound; and

- a peroxide.

According to an aspect of the present invention, there is provided an aqueous acidic composition comprising:

- sulfuric acid;
- a carbonyl-containing nitrogenous base compound; and

wherein sulfuric acid and said a carbonyl-containing nitrogenous base compound; are present in a molar ratio of no less than 1:1.

According to a preferred embodiment of the present invention, the carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; lysine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP (N-methyl-2-pyrrolidinone); histidine; DMA (N,N-dimethylacetamide); arginine; 2,3-pyridinedicarboxylic acid; hydantoin; and combinations thereof.

Preferably, the sulfuric acid and said carbonyl-containing nitrogenous base compound and are present in a molar ratio ranging from 28:1 to 2:1. More preferably, the sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 24:1 to 3:1. Preferably, the sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 20:1 to 4:1. More preferably, the sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 16:1 to 5:1. According to a preferred embodiment of the present invention, the sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 12:1 to 6:1.

Also preferably, said carbonyl-containing nitrogenous base compound has a molecular weight below 300 g/mol. Also preferably, said carbonyl-containing nitrogenous base compound has a molecular weight below 200 g/mol. More preferably, said carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; creatine; creatinine; and similar compounds.

According to a preferred embodiment of the present invention, the carbonyl-containing nitrogenous base compound is an amino acid. Preferably, the amino acid is selected from the group consisting of: glycine, arginine and histidine and other amino acids capable of achieving a stable composition when placed in a composition along with sulfuric acid and a peroxide (such as, but not limited to hydrogen peroxide).

The person skilled in the art will understand that the term 'stability' or 'stable' when associated with a composition comprising sulfuric acid, a peroxide and a carbonyl-containing nitrogenous base compound means that the composition does not readily degrade upon the addition of the carbonyl-containing nitrogenous base compound to a mixture comprising sulfuric acid and a peroxide. Preferably, the term stable or stability when associated with such a preferred composition means that the composition will retain a substantial part of its acidic character without degrading for a period of at least 24 hours. More preferably, the term stable or stability when associated with such a preferred composition means that the composition will retain a substantial part of its acidic character without degrading for a period of at least 48 hours. Even more preferably, the term stable or stability when associated with such a preferred composition means that the composition will retain a substantial part of its acidic character without degrading for a period of at least 72 hours.

Tests were conducted to assess the stability of several amino acids in solution with sulfuric acid and revealed that the following compounds showed less than desirable stability in the presence of sulfuric acid: lysine; threonine; tryptophan; and methionine. However, in the short term and in the presence of hydrogen peroxide, there weren't any stability issues encountered with blends of sulfuric acid and those amino acids.

According to another preferred embodiment of the present invention, the carbonyl-containing nitrogenous base compound is selected from the group consisting of: methylpyrrolidinone; N,N-dimethylacetamide and acetamide.

According to an aspect of the present invention, there is provided an aqueous composition for use in the delignification of biomass such as wood, wherein said composition comprises:

- sulfuric acid;
- a carbonyl-containing nitrogenous base compound; and
- a peroxide.

wherein the sulfuric acid and the carbonyl-containing nitrogenous base compound are present in a mole ratio ranging from 2:1 to 30:1.

According to an aspect of the present invention, there is provided an aqueous composition for use in the breaking down of cellulose from biomass (*i.e.* a plant source), wherein said composition comprises:

- sulfuric acid present in an amount ranging from 20 to 70 wt% of the total weight of the composition;

- a carbonyl-containing nitrogenous base compound; and
- a peroxide;

wherein the sulfuric acid and the carbonyl-containing nitrogenous base compound are present in a mole ratio ranging from 2:1 to 30:1.

Preferably, the peroxide is hydrogen peroxide.

According to an aspect of the present invention, there is provided a method of delignification of biomass / plant material, said method comprising:

- providing said plant material comprising cellulose fibers and lignin;
- exposing said plant material requiring to a composition comprising:
 - o sulfuric acid present in an amount ranging from 20 to 80 wt% of the total weight of the composition; and
 - o a carbonyl-containing nitrogenous base compound;

for a period of time sufficient to remove substantially all of the lignin present on said plant material. Preferably, the composition further comprises a peroxide. Preferably, the composition comprises sulfuric acid present in an amount ranging from 20 – 70 wt% of the total weight of the composition. More preferably, the composition comprises sulfuric acid present in an amount ranging from 30 – 70 wt% of the total weight of the composition.

Preferably, said carbonyl-containing nitrogenous base compound has a molecular weight below 300 g/mol. More preferably, said carbonyl-containing nitrogenous base compound has a molecular weight below 200 g/mol. According to a preferred embodiment of the present invention, the composition has a pH less than 1. According to another preferred embodiment of the present invention, the composition has a pH less than 0.5.

According to an aspect of the present invention, there is provided a one-pot process to separate lignin from a lignocellulosic feedstock, said process comprising the steps of:

- providing a vessel;
- providing said lignocellulosic feedstock;
- providing a composition comprising:
 - an acid;
 - a modifying agent comprising a carbonyl-containing nitrogenous base compound; and

- a peroxide;
- exposing said lignocellulosic feedstock to said composition in said vessel for a period of time sufficient to remove at least 80% of the lignin present said lignocellulosic feedstock;
- optionally, removing a liquid phase comprising dissolved lignin fragments from a solid phase comprising cellulose fibres.

According to a preferred embodiment of the present invention, the composition consists of:

- an acid;
- a modifying agent comprising a carbonyl-containing nitrogenous base compound; and
- a peroxide.

According to a preferred embodiment of the present invention, the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 50°C. Preferably, the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 40°C. More preferably, the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 30°C. Even more preferably, the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 25°C.

According to a preferred embodiment of the present invention, the process is carried out at ambient temperature. Preferably, the process is carried out at ambient pressure.

The inventors have discovered that delignification of biomass such as wood material / woody pulp (for example, but not limited to wood chips) can occur at substantially lower temperatures than those used during conventional kraft pulping process. In fact, experiments conducted at room temperature with preferred compositions according to the present invention were shown to degrade the lignin present in wood chips to free up cellulose fibers. According to a preferred embodiment of a method according to the present invention, a wood sample was dissolved at 30°C upon exposure to a composition according to a preferred embodiment of the present invention. According to a preferred embodiment of the present invention, one could substantially reduce the energy input costs involved in current pulp delignification by applying a method involving a preferred composition of the present invention.

DESCRIPTION OF THE INVENTION

The experiments carried out using an aqueous acidic composition according to a preferred embodiment of the present invention as shown that wood chips can undergo delignification under controlled reaction conditions and eliminate or at least minimize the degradation of the cellulose. Degradation is understood to mean a darkening of cellulose, which is symbolic of an uncontrolled acid attack on the cellulose and staining thereof.

The carbonyl-containing nitrogenous base compound together in the presence of sulfuric acid and the peroxide component, seems to generate a coordination of the compounds which acts as a modified sulfuric acid. In that respect, it is believed that the presence of the carbonyl-containing nitrogenous base compound forms an adduct with the sulfuric acid to generate a modified sulfuric acid, and therefore acts as a modifying agent. The strength of the modified acid is dictated by the moles of sulfuric acid to the moles of the carbonyl-containing nitrogenous base compound. Hence, a composition comprising a molar ratio of 6:1 of sulfuric acid: the carbonyl-containing nitrogenous base compound would be much less reactive than a composition of the same components in a 28:1 molar ratio.

When performing delignification of wood using a composition according to a preferred embodiment of the present invention, the process can be carried out at substantially lower temperatures than temperatures used in the conventional kraft pulping process. The advantages are substantial, here are a few: the kraft pulping process requires temperatures in the vicinity of 176 – 180°C in order to perform the delignification process, a preferred embodiment of the process according to the present invention can delignify wood at far lower temperatures, even as low as 20°C. According to a preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 0°C. According to a preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 10°C. According to a preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 30°C. According to another preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 40°C. According to yet another preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 50°C. According to yet another preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 60°C. Other advantages include: a lower input of energy; reduction of emissions and reduced capital expenditures; reduced maintenance; lower shut down / turn around costs; also there are health, safety and environment ("HSE") advantages compared to conventional kraft pulping compositions.

In each one of the above preferred embodiments, the temperature at which the processes are carried out are substantially lower than the current energy-intensive kraft process.

Moreover, the kraft process uses high pressures to perform the delignification of wood which is initially capital intensive, dangerous, expensive to maintain and has high associated turn-around costs. According to a preferred embodiment of the present invention, the delignification of wood can be performed at atmospheric pressure. This, in turn, circumvents the need for highly specialized and expensive industrial equipment such as pressure vessels / digestors. It also allows the implementation of delignification units in many of parts of the world where the implementation of a kraft plant would previously be impracticable due to a variety of reasons.

Some of the advantages of a process according to a preferred embodiment of the present invention, over a conventional kraft process are substantial as the heat / energy requirement for the latter is not only a great source of pollution but is in large part the reason the resulting pulp product is so expensive and has high initial capital requirements. The energy savings in the implementation of a process according to a preferred embodiment of the present invention would be reflected in a lower priced pulp and environmental benefits which would have both an immediate impact and a long-lasting multi-generational benefit for all.

Further cost savings in the full or partial implementation of a process according to a preferred embodiment of the present invention, can be found in the absence or minimization of restrictive regulations for the operation of a high temperature and high-pressure pulp digestors.

Experiment #1

Preparation of a composition according to a preferred embodiment of the present invention

For the H_2SO_4 : H_2O_2 :caffeine blend with a 20:20:1 molar ratio, 54.4g of concentrated sulfuric acid (93%) was mixed with 5.0g caffeine (present as a modifying agent). Then, 60.5g of a hydrogen peroxide solution in water (29%) was slowly added to the acid. As the mixing releases a large amount of heat, the beaker was placed in an ice bath. Addition of the hydrogen peroxide solution at this scale takes about 20 minutes. The pH of the resulting composition was less than 1.

Delignification experiments

After mixing, the resulting composition is split into 4 equal parts. One part was exposed to 1.5g of wood shavings, another part was exposed to commercially available lignin and another part was exposed

to commercially available cellulose respectively and stirred at ambient conditions for 3 hours. The fourth part of the blend is kept as a blend reference sample.

Control tests were run for the respective mixtures with just kraft lignin or just cellulose added instead of biomass. Commercially available lignin (Sigma-Aldrich; Lignin, kraft; Prod# 471003) was used as a control in the testing. Commercially available cellulose (Sigma-Aldrich; Cellulose, fibers (medium); Prod# C6288) was also used as a control in the testing.

The solid phase of each blend was filtered off after 3h of reaction time, rinsed with water and dried in an oven at 45°C to constant weight. An effective blend should dissolve all lignin and leave the cellulose as intact as possible. The results of the experiments conducted with several compositions are reported in Table 1 below.

Table 1 - Recovery of solids (% of initial mass) after 3h reaction time

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :Creatinine	42.2%	3.1%	94%
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :Caffeine	49.49%	6.46%	92.54%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :Caffeine	47.68%	0.00%	94.96%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :Caffeine	45.58%	1.94%	94.00%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :Creatine monohydrate	45.64%	6.32%	98.84%

A blend with a ratio of 10:10:1 of sulfuric acid (93% conc. used) to hydrogen peroxide (as 29% solution) to creatinine results in a mass recovery of over 49% from wood and over 90 % for the cellulose control. However, the remaining lignin in the lignin control sample is an indication that the composition is not optimized for complete lignin removal. The pulp produced with such a composition can still have commercial applications.

A blend with a ratio of 10:10:1 of sulfuric acid (93% conc. used) to hydrogen peroxide (as 29% solution) to caffeine results in a mass recovery of over 45% from wood and close to 95 % for the cellulose control. The lignin control sample showed is an indication that the composition is performing very well for lignin removal and produces a pulp which has a wide array of potential commercial applications.

A blend with a ratio of 10:10:1 of sulfuric acid (93% conc. used) to hydrogen peroxide (as 29% solution) to creatine monohydrate results in a mass recovery of over 45% from wood and close to 99 % for

the cellulose control. The remaining lignin in the lignin control sample is an indication that the composition is not optimized for lignin removal, but with only 6.32% of lignin control left, the composition is still deemed quite effective.

The above experiments provide clear indications that a preferred composition according to the present invention not only provides an adequate dissolving acid to delignify plant material but is also valuable in controlling the delignification to prevent the ultimate degradation of cellulosic material into carbon black residue resulting in higher yields potentially for the operators thus increasing profitability while reducing emissions and the risk to the employees, contractors and public.

Additional testing was carried out to confirm the above initial results and to explore the feasibility of using other compounds with similar features as modifying agent. The results of the experiments are set out below in Tables 2 to 14.

Table 2 - Recovery of solids (% of initial mass) after 3h reaction time using creatinine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :creatinine	57.8%	0%	95.1%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :creatinine	42.2%	3.1%	94%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :creatinine	54.3%	0%	96.50%

Table 3 - Recovery of solids (% of initial mass) after 3h reaction time using caffeine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :caffeine	49.5%	6.5%	92.5%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :caffeine	47.7%	0%	95%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :caffeine	46%	2%	98.50%

Table 4 - Recovery of solids (% of initial mass) after 3h reaction time using creatine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :creatine	60.1%	26.6%	92.8%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :creatine	45.6%	6.3%	98.8%

20:20:1	H ₂ SO ₄ :H ₂ O ₂ :creatine	62.3%	0%	98.50%
---------	---	-------	----	--------

Table 5 - Recovery of solids (% of initial mass) after 3h reaction time using glycine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :glycine	46.6%	5.9%	95.1%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :glycine	42.9%	2.0%	94.0%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :Glycine	39.6%	2.3%	86.3%

Table 6 - Recovery of solids (% of initial mass) after 3h reaction time using histidine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :histidine	49.1%	27.5%	91.96%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :histidine	46.0%	5.8%	95.8%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :histidine	35.2%	0.8%	94.7%

Table 7 - Recovery of solids (% of initial mass) after 3h reaction time using arginine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :arginine	51.6%	28.3%	95.00%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :arginine	46.7%	12.2%	95.6%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :arginine	45.3%	3.7%	93.4%

Table 8 - Recovery of solids (% of initial mass) after 3h reaction time using lysine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :lysine	71.3%	55.6%	95.0%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :lysine	46.4%	19.9%	100%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :lysine	58.2%	25.1%	92.8%

Table 9 - Recovery of solids (% of initial mass) after 3h reaction time using glutamine as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :glutamine	50.11%	0%	100%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :glutamine	49.5%	0%	99.98%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :glutamine	45.11%	0%	62.55%

Table 10 - Recovery of solids (% of initial mass) after 3h reaction time using 4-aminobenzoic acid (4-AMBZ) as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :4AMBZ	n/a	n/a	n/a
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :4AMBZ	44.1%	0%	97.1%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :4AMBZ	49.8%	0%	98.7%

Table 11 - Recovery of solids (% of initial mass) after 3h reaction time using NMP as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :NMP	45.0%	2.2%	94.4%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :NMP	39.1%	0%	95.7%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :NMP	42.3%	0%	92.3%

Table 12 - Recovery of solids (% of initial mass) after 3h reaction time using DMA as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :DMA	46.0%	4.6%	99.1%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :DMA	40.0%	2.7%	94.1%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :DMA	43.3%	1.6%	91.4%

Table 13 - Recovery of solids (% of initial mass) after 3h reaction time using 2,3-pyridinedicarboxylic acid (23PDC) as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :23PDC	45.4%	0%	96.1%

Table 14 - Recovery of solids (% of initial mass) after 3h reaction time using hydantoin as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :hydantoin	53.6%	0%	92.4%

A method to yield glucose from wood pulp would represent a significant advancement to the current process where the conversion of such is chemical and energy intensive, costly, emissions intensive and dangerous all while not resulting in highly efficient results, especially in large-scale operations. It is desirable to employ a composition which may delignify wood but also allows the operator some control in order to preserve the cellulose rather than degrading it to carbon black resulting in higher efficiencies and yields along with increased safety and reduced overall costs.

According to a preferred embodiment of the method of the present invention, the carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; lysine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP (N-methyl-2-pyrrolidinone); histidine; DMA (N,N-dimethylacetamide); arginine; 2,3-pyridinedicarboxylic acid; hydantoin; and combinations thereof. Preferably, the carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP (N-methyl-2-pyrrolidinone); histidine; DMA (N,N-dimethylacetamide); 2,3-pyridinedicarboxylic acid; hydantoin; and combinations thereof.

According to a preferred embodiment of the method of the present invention, the separation of lignin can be effected and the resulting cellulose fibers can be further processed to yield glucose monomers. Glucose chemistry has a multitude of uses including as a starting block in the preparation of widely used chemicals including but not limited to diacetonide, dithioacetal, glucoside, glucal and hydroxyglucal to name but a few.

According to another preferred embodiment of the present invention, the composition can be used to decompose organic material by oxidation such as those used in water treatment, water purification and/or water desalination. An example of this is the removal (*i.e.* destruction) of algae on filtration membranes. As such membranes can be quite expensive, it is imperative that they be used for as long as possible. However, given the difficulty to remove organic matter which accumulates on it over time, new approaches are necessary to do so efficiently and with as little damage to the membrane as possible. Mineral acids are too strong and, while they will remove the organic matter, will damage the filtration membranes. A

preferred composition of the present invention remedies this issue as it is less aggressive than the mineral acids and, as such, will remove the organic contaminants in a much milder approach, therefore sparing the membrane.

While the foregoing invention has been described in some detail for purposes of clarity and understanding, it will be appreciated by those skilled in the relevant arts, once they have been made familiar with this disclosure that various changes in form and detail can be made without departing from the true scope of the invention in the appended claims.

CLAIMS

1. An aqueous acidic composition comprising:
 - sulfuric acid;
 - a modifying agent comprising a carbonyl-containing nitrogenous base compound; and
 - a peroxide.
2. An aqueous acidic composition comprising:
 - sulfuric acid; and
 - a modifying agent comprising a carbonyl-containing nitrogenous base compound;wherein sulfuric acid and said carbonyl-containing nitrogenous base compound are present in a molar ratio of no less than 1:1.
3. The composition according to claim 1 or 2, wherein sulfuric acid, said carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 28:1 to 2:1.
4. The composition according to any one of claims 1 to 3, wherein sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 20:1 to 5:1.
5. The composition according to any one of claims 1 to 4, wherein sulfuric acid and said carbonyl-containing nitrogenous base compound are present in a molar ratio of approximately 10:1.
6. The composition according to any one of claims 1 to 5 where said carbonyl-containing nitrogenous base compound has a molecular weight below 300 g/mol.
7. The composition according to any one of claims 1 to 6 where said carbonyl-containing nitrogenous base compound has a molecular weight below 150 g/mol.
8. The composition according to any one of claims 1 to 7 where said carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; lysine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP (N-methyl-2-pyrrolidinone); histidine; DMA (N,N-dimethylacetamide); arginine; 2,3-pyridinedicarboxylic acid; hydantoin; and combinations thereof.

9. An aqueous composition for use in the delignification of wood, wherein said composition comprises:

- sulfuric acid;
- a modifying agent comprising carbonyl-containing nitrogenous base compound; and
- a peroxide.

wherein the sulfuric acid and the carbonyl-containing nitrogenous base compound are present in a mole ratio ranging from 2:1 to 28:1.

10. An aqueous composition for use in the processing and depolymerisation of cellulose from a plant source, wherein said composition comprises:

- sulfuric acid present in an amount ranging from 20 to 80 wt% of the total weight of the composition;
- a modifying agent comprising a carbonyl-containing nitrogenous base compound; and
- a peroxide;

wherein the sulfuric acid and the carbonyl-containing nitrogenous base compound are present in a mole ratio ranging from 2:1 to 28:1.

11. The composition according to any one of claims 9 and 10, wherein sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 20:1 to 5:1.

12. The composition according to any one of claims 9 to 11, wherein sulfuric acid and said carbonyl-containing nitrogenous base compound are present in a molar ratio of approximately 10:1.

13. The composition according to any one of claims 9 to 12 where said carbonyl-containing nitrogenous base compound has a molecular weight below 300 g/mol.

14. The composition according to any one of claims 9 to 13, where the peroxide is hydrogen peroxide.

15. An aqueous acidic composition comprising:

- sulfuric acid;
- a modifying agent comprising a carbonyl-containing nitrogenous base compound; and
- a peroxide;

wherein said carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; lysine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP; histidine; DMA; arginine; 2,3-pyridinedicarboxylic acid; hydantoin; and
wherein the pH of the composition is less than 1.

16. A stable aqueous acidic composition comprising:

- sulfuric acid;
- a modifying agent comprising an amino acid; and
- a peroxide;

wherein said composition has a pH of less than 1.

17. A one-pot process to separate lignin from a lignocellulosic feedstock, said process comprising the steps of:

- providing a vessel;
- providing said lignocellulosic feedstock;
- providing a composition comprising:
 - an acid;
 - a modifying agent comprising a carbonyl-containing nitrogenous base compound; and
 - a peroxide;
- exposing said lignocellulosic feedstock to said composition in said vessel for a period of time sufficient to remove at least 80% of the lignin present said lignocellulosic feedstock;
- optionally, removing a liquid phase comprising dissolved lignin fragments from a solid phase comprising cellulose fibres.

18. The process according to claim 17, wherein said acid is sulfuric acid.

19. The process according to claim 17 or 18, wherein said peroxide is hydrogen peroxide.

20. The process according to any one of claims 17 to 19, wherein the period of time is sufficient to remove at least 90% of the lignin present on said plant material.

21. The process according to any one of claims 17 to 20, wherein the period of time is sufficient to remove at least 95% of the lignin present on said plant material.

22. The process according to any one of claims 17 to 21, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 50°C.
23. The process according to any one of claims 17 to 22, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 40°C.
24. The process according to any one of claims 17 to 23, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 30°C.
25. The process according to any one of claims 17 to 24, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 25°C.
26. The process according to any one of claims 17 to 25, wherein said method is carried out at ambient temperature.
27. The process according to any one of claims 17 to 26, wherein said method is carried out at ambient pressure.
28. The process according to any one of claims 17 to 27 wherein said carbonyl-containing nitrogenous base compound has a molecular weight below 300 g/mol.
29. The process according to any one of claims 17 to 28 wherein said carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; lysine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP (N-methyl-2-pyrrolidinone); histidine; DMA (N,N-dimethylacetamide); arginine; 2,3-pyridinedicarboxylic acid; hydantoin; and combinations thereof.
30. The process according to any one of claims 17 to 29 wherein said carbonyl-containing nitrogenous base compound is selected from the group consisting of: caffeine; creatine; glutamine; creatinine; 4-aminobenzoic acid; glycine; NMP (N-methyl-2-pyrrolidinone); histidine; DMA (N,N-dimethylacetamide); 2,3-pyridinedicarboxylic acid; hydantoin; and combinations thereof
31. The process according to any one of claims 17 to 30, wherein sulfuric acid and said carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 28:1: to 2:1.

32. The method according to any one of claims 17 to 31, wherein sulfuric acid and carbonyl-containing nitrogenous base compound are present in a molar ratio ranging from 20:1: to 5:1.
33. The method according to any one of claims 17 to 32, wherein sulfuric acid and said carbonyl-containing nitrogenous base compound are present in a molar ratio of approximately 10:1.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CA2021/000073A. CLASSIFICATION OF SUBJECT MATTER
IPC: **D21C 3/04** (2006.01)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
D21C 3/04 (2006.01)

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic database(s) consulted during the international search (name of database(s) and, where practicable, search terms used)

Databases: Questel Orbit, Scopus, CaPlus

Keywords: sulfuric acid, hydrogen peroxide, caffeine, lysine, creatine, glutamine, creatinine, 4-aminobenzoic acid, glycine, N-methyl-2-pyrrolidinone, histidine, N,N-dimethylacetamide, arginine, 2,3-pyridinedicarboxylic acid, hydantoin, lignin, cellulose, biomass, wood, delignification

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CA2711182 A1 (YANG et al.) 16 July 2009 (16-07-2009) *Claims 1, 7, 8*	1-7
P,X	WO2021125362 A1 (NAKAMURA et al.) 24 June 2021 (24-06-2021) *Entire document*	1-14, 16-33
P,Y	*Machine translation provided by Questel Orbit used for understanding*	15
X	US20060014391 A1 (LEE et al.) 19 January 2006 (19-01-2006) *Abstract; Claims 1, 3, 7, 8*	16
Y	US20160244913 A1 (TSURUGA et al.) 25 August 2016 (25-08-2016) *Abstract; Claim 1; [0182]*	1-15, 17-33

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* "A" "D" "E" "L" "O" "P"	Special categories of cited documents: document defining the general state of the art which is not considered to be of particular relevance document cited by the applicant in the international application earlier application or patent but published on or after the international filing date document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) document referring to an oral disclosure, use, exhibition or other means document published prior to the international filing date but later than the priority date claimed	"I" "X" "Y" "&"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art document member of the same patent family
---	---	--------------------------	--

Date of the actual completion of the international search
24 September 2021 (24-09-2021)Date of mailing of the international search report
02 December 2021 (02-12-2021)Name and mailing address of the ISA/CA
Canadian Intellectual Property Office
Place du Portage I, C114 - 1st Floor, Box PCT
50 Victoria Street
Gatineau, Quebec K1A 0C9
Facsimile No.: 819-953-2476

Authorized officer

Erin Mulrooney

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CA2021/000073

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US20180370071 A1 (BOITOUZET et al.) 27 December 2018 (27-12-2018) *Claims 1, 3; [0083], [0106], [0143], [0144]*	1-15, 17-33

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.

PCT/CA2021/000073

Patent Document Cited in Search Report	Publication Date	Patent Family Member(s)	Publication Date
CA2711182A1	16 July 2009 (16-07-2009)	CN101475790A CN101475790B EP2236578A1 EP2236578A4 US2010258033A1 US8057892B2 WO2009086752A1	08 July 2009 (08-07-2009) 10 October 2012 (10-10-2012) 06 October 2010 (06-10-2010) 09 March 2011 (09-03-2011) 14 October 2010 (14-10-2010) 15 November 2011 (15-11-2011) 16 July 2009 (16-07-2009)
WO2021125362A1	24 June 2021 (24-06-2021)	None	
US2006014391A1	19 January 2006 (19-01-2006)	JP2006049881A KR20060005845A KR100606187B1	16 February 2006 (16-02-2006) 18 January 2006 (18-01-2006) 01 August 2006 (01-08-2006)
US2016244913A1	25 August 2016 (25-08-2016)	AR097596A1 BR112016002352A2 CN105579473A EP3045476A1 EP3045476A4 JPWO2015037424A1 TW201516060A WO2015037424A1	23 March 2016 (23-03-2016) 01 August 2017 (01-08-2017) 11 May 2016 (11-05-2016) 20 July 2016 (20-07-2016) 15 February 2017 (15-02-2017) 02 March 2017 (02-03-2017) 01 May 2015 (01-05-2015) 19 March 2015 (19-03-2015)
US2018370071A1	27 December 2018 (27-12-2018)	BR112018011430A2 CA3006341A1 CN108367451A CN108367451B EP3386697A1 EP3386697B1 EP3656520A1 FR3044577A1 FR3044577B1 JP2019505420A PL3386697T3 RU2018124803A RU2018124803A3 RU2747643C2 US2019077040A1 US10538012B2 WO2017098149A1 WO2017098149A9	27 November 2018 (27-11-2018) 15 June 2017 (15-06-2017) 03 August 2018 (03-08-2018) 06 August 2021 (06-08-2021) 17 October 2018 (17-10-2018) 01 January 2020 (01-01-2020) 27 May 2020 (27-05-2020) 09 June 2017 (09-06-2017) 22 December 2017 (22-12-2017) 28 February 2019 (28-02-2019) 01 June 2020 (01-06-2020) 09 January 2020 (09-01-2020) 19 February 2020 (19-02-2020) 11 May 2021 (11-05-2021) 14 March 2019 (14-03-2019) 21 January 2020 (21-01-2020) 15 June 2017 (15-06-2017) 31 May 2018 (31-05-2018)