



Europäisches
Patentamt
European
Patent Office
Office européen
des brevets



EP 1 728 882 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
18.09.2013 Bulletin 2013/38

(51) Int Cl.:
C22C 21/02 (2006.01) **B22D 11/06 (2006.01)**
B22D 17/00 (2006.01) **C22C 21/06 (2006.01)**
C22F 1/05 (2006.01)

(21) Application number: **05726972.2**

(86) International application number:
PCT/JP2005/005225

(22) Date of filing: **23.03.2005**

(87) International publication number:
WO 2005/090624 (29.09.2005 Gazette 2005/39)

(54) ALUMINIUM ALLOY FOR CASTING, HAVING HIGH RIGIDITY AND LOW LINER EXPANSION COEFFICIENT

ALUMINIUMGUSSLEGIERUNG MIT HOHER STEIFIGKEIT UND KLEINEM LINEAREM
AUSDEHNUNGSKOEFFIZIENTEN

ALLIAGE D'ALUMINIUM POUR LE MOULAGE, POSSEZANT UNE RIGIDITE ELEVEE ET UN
COEFFICIENT DE DILATATION LINEIQUE FAIBLE

(84) Designated Contracting States:
DE FR GB

(74) Representative: **Ahner, Philippe et al**
BREVALEX
95 rue d'Amsterdam
75378 Paris Cedex 8 (FR)

(30) Priority: **23.03.2004 JP 2004084256**

(56) References cited:
EP-A1- 0 362 086 WO-A-97/13882
FR-A1- 2 489 846 FR-A1- 2 788 788
JP-A- 1 180 938 JP-A- 2 073 935
JP-A- 3 199 336 JP-A- 2000 054 053
JP-A- 2002 206 131 SU-A1- 431 252

(43) Date of publication of application:
06.12.2006 Bulletin 2006/49

- **HATCH J E: "ALUMINUM" 1984, ALUMINUM.
PROPERTIES AND PHYSICAL METALLURGY,
OHIO, AMERICAN SOCIETY FOR METALS, US,
PAGE 350 , XP002451306 * paragraph
"Phosphorus" ***

(73) Proprietor: **Nippon Light Metal, Co., Ltd.**
Shinagawa-ku, Tokyo 140-8628 (JP)

(72) Inventors:

- **ODA, Kazuhiro,
Nikkei Res. and Dev. Center Nippon
Ihara-gun,
Shizuoka 4213203 (JP)**
- **Shioda, Masahiko,
Nippon Light Metal Company, Ltd.
Shinagawa-ku,
Tokyo 1408628 (JP)**

EP 1 728 882 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[Technical Field]

5 [0001] The present invention concerns an aluminum alloy for die casting, and particularly concerns an aluminum alloy for casting that may be used optimally for the casting of members for which high rigidity and a low linear thermal expansion coefficient are particularly required, such as ladder frames, perimeter frames, and cases for various types of vehicles such as automobiles.

10 [Background Art]

[0002] Conventionally, cast iron was used for members such as automobile frames that require particularly high rigidity, but in recent years, from the standpoint of energy conservation, the need for weight reduction of automobiles has increased, and attention has been paid to aluminum alloy as a material that can meet these needs.

15 [Disclosure of the Invention]

[Problem to be Solved by the Invention]

20 [0003] As aluminum alloys having high rigidity, aluminum alloy composites compounding Al_2O_3 , SiC, and the like as reinforcing materials are known, but these composites have the problem that the manufacturing processes thereof are complex and the cost becomes high. Additionally, there are problems such as the fact that since Al_2O_3 , SiC, and the like are contained, there are many restrictions at the time of recycling.

25 [0004] Japanese Unexamined Patent Publication No. H01-180938 discloses an aluminum alloy with improved wear resistance, but the aluminum alloy disclosed therein has the problem that when substituted for cast iron products being used for automobile frames and the like, its rigidity is low, and its linear expansion coefficient is too high. Additionally, Japanese Unexamined Patent Publication No. H03-199336 also similarly discloses an aluminum alloy with improved wear resistance, but the aluminum alloy disclosed therein also has the problem that when substituted for cast iron products being used for automobile frames and the like, its rigidity is low, and its linear expansion coefficient is too high, and further, sticking to the die occurs easily.

[Patent Document 1] Japanese Unexamined Patent Publication No. H01-180938

[Patent Document 2] Japanese Unexamined Patent Publication No. H03-199336

35 [Means for Solving the Problem]

[0005] In order to solve the abovementioned problems of conventional aluminum alloys, the present invention offers an aluminum alloy for die casting having excellent rigidity and a low linear expansion coefficient, containing 13-25% by mass of silicon, 2-8% by mass of copper, 0.5-3% by mass of iron, 0.3-3% by mass of manganese, 0.001-0.02% by mass of phosphorus, and the remainder comprising aluminum and inevitable impurities, wherein the total amount of iron and manganese is 3.0% by mass or greater. and nickel 3.0% by mass or greater.

[0006] Further, optionally one or more of 0.1- 1.0% by mass of chromium, 0.05- 1.5% by mass of magnesium, 0.01- 1.0% by mass of titanium, 0.0001- 1.0% by mass of boron, 0.1- 1.0% by mass of zirconium, 0.1- 1.0% by mass of vanadium, or 0.01- 1.0% by mass of molybdenum may be contained.

[0007] It is desirable for the alloy of the present invention to be cast at a cooling rate of 30 degrees C per second or greater, and in order to cast at a high cooling rate, it is desirable to do the casting by the die casting method.

[0008] The inventors of the present invention, as a result of keen research regarding aluminum alloy, discovered that there is a correlation between the area ratio of crystallized products and the rigidity and linear expansion coefficient of aluminum alloys, and as a result of further research, discovered that by the alloy composition described above, it was possible to disperse minute crystallized particles of $Al-Cu$, $Al-Fe-Si$, $Al-Fe-Mn$, or $Al-Si-Mn$ compounds, and the necessary high rigidity and low linear expansion coefficient was realizable. Herebelow, the effects of each component in said aluminum alloy shall be described.

[Effects of the Invention]

Silicon: 13-25 % by mass

5 [0009] Silicon crystallizes as eutectic silicon, primary silicon, and as Al-Fe-Si compounds, and has the effect of improving rigidity. This effect becomes marked at greater than 13% by mass, but at greater than 25% by mass, primary silicon becomes coarse, and the rigidity improving effect is reduced. Additionally, it is necessary to improve the casting temperature. Further, machinability becomes markedly worse due to coarse silicon. Silicon also has the effects of decreasing the linear expansion coefficient, and improving wear resistance. A more desirable range for silicon is 13-17%
 10 by mass.

Copper: 2-8% by mass

15 [0010] Copper crystallizes as Al-Cu compounds, and contributes to the improvement of rigidity. This effect becomes marked at 4% by mass or greater, but at greater than 8% by mass, the compounds become coarse and elongation is reduced, and further, corrosion resistance is also reduced. A more desirable range for Cu is 3-6 wt%.

Iron + Manganese: 3.0% by mass or greater

20 [0011] Iron and manganese, crystallize as Al- Fe- Mn, Al- Fe- Si, and Al- Si- Fe- Mn compounds, contribute to the improvement of rigidity, and have the effect of reducing the linear expansion coefficient. Additionally, they have the effect of improving heat resistance. This effect becomes marked when iron+manganese is 3% by mass or greater, but since at greater than 12% by mass, the crystallized products become coarse, and the rigidity improving effect is lessened, it is desirable to keep the total amount of iron + manganese at 12% by mass or less.

25 Phosphorus: 0.001-0.02% by mass

30 [0012] Phosphorus has the effect of miniaturizing and dispersing uniformly the primary silicon. This effect is marked at 0.001% by mass or greater, but at greater than 0.02% by mass, the viscosity of the molten metal increases, and castability becomes worse.

Magnesium: 0.05-1.5% by mass

35 [0013] Mg dissolves in solid solution in the matrix and contributes to the improvement of rigidity. This effect is marked at 0.05% by mass or greater, but at greater than 1.5% by mass, elongation is reduced, and castability markedly worsens. More desirably, magnesium should be 0.4% by mass or less.

Chromium: 0.1-1.0% by mass

40 [0014] Chromium crystallizes as Al- Si- Fe- Mn- Cr compounds, and contributes to the improvement of rigidity. Additionally, it has the effect of dispersing primary silicon minutely and uniformly. Said effect is marked for 0.1% by mass or greater of chromium, but at greater than 1.0% by mass, coarse compounds are formed, and elongation is reduced.

Titanium: 0.01-1.0% by mass

45 [0015] Titanium miniaturizes the alpha phase, and contributes to the improvement of castability, and also has the effect of preventing the coarsening of Al-Ni compounds. Such effects become marked at 0.01% by mass or greater of titanium, but at greater than 1.0% by mass, coarse compounds are formed, and elongation is reduced.

50 Boron: 0.0001-1.0% by mass, Vanadium: 0.1-1.0% by mass, Zirconium: 0.1-1.0% by mass, Molybdenum: 0.01-1.0% by mass

55 [0016] Boron, vanadium, zirconium, and molybdenum form highly rigid crystallized products, and contribute to the improvement of rigidity. For any of these elements, if greater than the upper limit is added, coarse crystallized products are formed, and elongation is reduced.

[Best Modes for Embodying the Invention]

[0017] The inventors of the invention of the present application manufactured the aluminum alloys according to the present invention, and confirmed experimentally the relationship between composition and crystalline structure, rigidity and linear expansion coefficient, and the results shall be described herebelow.

[0018] The composition of the aluminum alloys used in the experiment is shown in table 1. The aluminum alloy used in the experiment, after being cast in a 200x200x10 mm planar form at a casting temperature of 720 degrees C, was aged by maintaining at 200 degrees C for 4 hours, and then the rigidity (Young's modulus) and the linear expansion coefficient (thermal expansion coefficient) were measured. Alloys No. 9-15 are aluminum alloys according to the present invention, and alloys No. 1-8 and 16 18-24 are comparative examples that do not satisfy at least one of the conditions for the range of the compositions described above. Compositions that do not satisfy the conditions are shown underlined.

15

20

25

30

35

40

45

50

55

[Table 1]

No.	Composition (wt%)										Characteristics				
	Si	Cu	Ni	Fe	Mn	Mg	Cr	Ti	B	V	Zr	Mo	P	E (GPa)	α ($\times 10^{-6}/^{\circ}\text{C}$)
*1	13	5	3	2	1	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	96	17.8
*2	24	5	3	2	1	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	103	14.6
*3	16	3	3	2	1	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	96	17.2
*4	16	7	3	2	1	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	100	16.7
*5	16	5	1	1	1	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	93	17.5
*6	16	5	3	2	2	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	98	17.0
*7	16	5	6	2	3.5	0.5	0.4	0.4	0.4	0.4	0.4	0.4	0.01	106	16.4
*8	16	5	1	1	1	1.5	1.0	1.0	1.0	1.0	1.0	1.0	0.01	98	16.9
9	16	5	-	2	2	-	0.4	-	-	-	-	-	0.01	92	17.8
10	16	5	-	2	2	0.5	0.4	-	-	-	-	-	0.01	92	17.8
11	16	5	-	2	2	-	0.4	-	0.4	-	-	-	0.01	94	17.7
12	16	5	-	2	2	-	0.4	0.4	-	-	-	-	0.01	93	17.7
13	16	5	-	2	2	-	0.4	-	-	0.4	-	-	0.01	93	17.7
14	16	5	-	2	2	-	0.4	-	-	0.4	-	0.01	94	17.7	
15	16	5	-	2	2	-	0.4	-	-	-	0.4	0.01	94	17.7	
*16	14	4	2	2.5	1.2	-	0.5	0.5	-	0.5	-	-	0.01	94	17.6
17	16	5	-	2	2	0.5	-	-	-	-	-	-	0.01	90	17.9

5
10
15
20
25
30
35
40
45
50
55

(continued)

No.	Composition (wt%)											Characteristics			
	Si	Cu	Ni	Fe	Mn	Mg	Cr	Ti	B	V	Zr	Mo	P	E (GPa)	$\alpha \times 10^{-6}/^{\circ}\text{C}$
18	<u>12</u>	<u>1</u>	<u>1</u>	<u>0.5</u>	<u>1</u>	-	-	-	-	-	-	-	=	<u>80</u>	<u>20.0</u>
19	<u>11</u>	<u>2.5</u>	-	<u>0.8</u>	<u>0.2</u>	<u>0.2</u>	-	-	-	-	-	-	=	<u>78</u>	<u>21.0</u>
20	<u>16</u>	<u>5</u>	<u>0.5</u>	<u>1</u>	<u>0.5</u>	<u>0.5</u>	<u>0.4</u>	-	-	-	-	-	0.01	<u>87</u>	<u>17.9</u>
21	<u>16</u>	<u>5</u>	<u>2</u>	-	<u>2</u>	-	<u>0.4</u>	-	-	-	-	-	0.01	<u>91</u>	<u>17.8</u>
22	<u>16</u>	<u>5</u>	<u>2</u>	<u>2</u>	-	-	<u>0.4</u>	-	-	-	-	-	0.01	-	<u>17.4</u>
23	<u>16</u>	<u>1</u>	-	<u>2</u>	<u>2</u>	-	<u>0.4</u>	-	-	-	-	-	0.01	<u>86</u>	<u>18.5</u>
24	<u>12</u>	<u>5</u>	-	<u>2</u>	<u>2</u>	-	<u>0.4</u>	-	-	-	-	-	0.01	<u>88</u>	<u>18.9</u>

* example composition falls outside of the scope of the invention.

[0019] The abovementioned measurement results are shown in Table 1 along with compositions.

[0020] Here, regarding Young's modulus, the criterial value is taken to be 90 GPa, and any composition with a value above this is judged to satisfy the criterion, and regarding the coefficient of linear thermal expansion, the criterial value is taken to be $18 \times 10^{-6}/^{\circ}\text{C}$, and any composition with a value lower than this is judged to satisfy the criterion.

5 [0021] As shown in table 1, Alloy No. 18 has a Young's modulus of 80 GPa so has a lower value than the criterial value (90 GPa), and at the same time, its coefficient of linear thermal expansion is $20.0 \times 10^{-6}/^{\circ}\text{C}$, higher than the criterial value ($18 \times 10^{-6}/^{\circ}\text{C}$), and neither value satisfies the criteria. The cause is thought to be the fact that the contained amount of any of silicon, copper, and nickel + iron + manganese is insufficient, and therefore is below the range described above.

10 [0022] Alloy No. 19, similarly with Alloy No. 18, satisfies the criteria neither for the Young's modulus nor the coefficient of linear thermal expansion. The cause is thought to be the fact that, although the content of copper is within the range described above, the contained amount of both silicon and nickel + iron + manganese is insufficient (below the range described above).

15 [0023] Alloy No. 20 has a Young's modulus lower than the criterial value, and the cause is thought to be the fact that the total contained amount of nickel + iron + manganese is 2.0% by mass, and this is below the condition described above of a total nickel + iron + manganese content of 3.0% by mass.

[0024] Alloy No. 21 satisfies the criteria for Young's modulus and coefficient of linear thermal expansion, but caused sticking to the die. The cause is thought to be the fact that iron was not substantially added, and this did not satisfy the conditions described above.

20 [0025] Alloy No. 22 had insufficient elongation, and since the test piece broke within the elastic deformation region, the Young's modulus was not measurable. This is thought to be because manganese was not substantially added, and the conditions described above regarding the composition were not satisfied.

[0026] Alloy No. 23 does not satisfy the criteria for either Young's modulus or coefficient of linear thermal expansion. The cause is thought to be the fact that the copper content is insufficient at 1% by mass (is below the range described above).

25 [0027] Alloy No. 24 also does not satisfy the criteria for either Young's modulus or coefficient of linear thermal expansion. The cause is thought to be the fact that the silicon content is insufficient at 12% by mass (is below the range described above).

[0028] In contrast, aluminum alloys No. 1-17 of the present invention, satisfying the range of composition described above, as shown in table 1, have Young's moduli and coefficients of linear thermal expansion that satisfy the criteria.

30

[Industrial Applicability]

[0029] The aluminum alloy for die casting of the present invention may be used optimally for the casting of members particularly requiring a high rigidity and low linear expansion coefficient.

35

Claims

40 1. An aluminum alloy die cast having excellent rigidity and a low linear expansion coefficient, containing 13-25% by mass of silicon, 2-8% by mass of copper, 0.5-3% by mass of iron, 0.3-3% by mass of manganese 0.001-0.02% by mass of phosphorus and optionally at least one or more of 0.1-1.0% by mass of chromium, 0.05-1.5% by mass of magnesium, 0.01-1.0% by mass of titanium, 0.0001-1.0% by mass of boron, 0.1-10% by mass of zirconium, 0.1-1.0% by mass of vanadium, or 0.01-1.0% by mass of molybdenum, wherein the total amount of iron and manganese is 3.0% by mass or greater, and the remainder consists of aluminium and inevitable impurities.

45

Patentansprüche

50 1. Aluminiumlegierung-Druckgussteil mit exzellenter Steifigkeit und geringem linearen Ausdehnungskoeffizienten, enthaltend 13 bis 25 Massenprozent Silizium, 2 bis 8 Massenprozent Kupfer, 0,5 bis 3 Massenprozent Eisen, 0,3 bis 3 Massenprozent Mangan, 0,001 bis 0,02 Massenprozent Phosphor und optional wenigstens eines oder mehrere aus 0,1 bis 1,0 Massenprozent Chrom, 0,05 bis 1,5 Massenprozent Magnesium, 0,01 bis 1,0 Massenprozent Titan, 0,0001 bis 1,0 Massenprozent Bor, 0,1 bis 1,0 Massenprozent Zirkon, 0,1 bis 1,0 Massenprozent Vanadium oder 0,01 bis 1,0 Massenprozent Molybdän, wobei die Gesamtmenge an Eisen und Mangan 3,0 Massenprozent oder mehr ist, und der Rest aus Aluminium und unvermeidbaren Verunreinigungen besteht.

55

Revendications

1. Alliage d'aluminium coulé sous pression présentant une excellente rigidité et un faible coefficient d'expansion linéaire, contenant de 13 à 25 % en poids de silicium, de 2 à 8 % en poids de cuivre, de 0,5 à 3 % en poids de fer, de 0,3 à 5 % en poids de manganèse, de 0,001 à 0,02 % en poids de phosphore et facultativement au moins un ou plusieurs de 0,1 à 1,0 % en poids de chrome, 0,05 à 1,5 % en poids de magnésium, 0,01 à 1,0% en poids de titane, 0,0001 à 1,0 % en poids de bore, 0,1 à 1,0 % en poids de zirconium, 0,1 à 1,0 % en poids de vanadium ou 0,01 à 1,0 % en poids de molybdène, la quantité totale de fer et de manganèse étant de 3,0 % en poids ou plus, et le reste se composant d'aluminium et d'impuretés inévitables.

10

15

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP H01180938 B [0004]
- JP H03199336 B [0004]