



(22) Date de dépôt/Filing Date: 1990/08/02

(41) Mise à la disp. pub./Open to Public Insp.: 1991/02/10

(45) Date de délivrance/Issue Date: 2001/10/16

(30) Priorité/Priority: 1989/08/09 (391279) US

(51) Cl.Int.⁵/Int.Cl.⁵ C08L 61/00, C08L 81/06

(72) Inventeurs/Inventors:
MacKenzie, Paul D., GB;
Maskell, Robin K., GB

(73) Propriétaires/Owners:
IMPERIAL CHEMICAL INDUSTRIES PLC, GB;
ICI COMPOSITES INC., US

(74) Agent: MARKS & CLERK

(54) Titre : COMPOSITION POLYMERE

(54) Title: POLYMER COMPOSITION

(57) **Abrégé/Abstract:**

A curable polymer composition comprising a polymerisable cyanate ester thermoset component and a polyarylsulphone thermoplast component containing ether- and/or thioether- linked repeating units $(\text{PhSO}_2\text{Ph})_n$ and $(\text{Ph})_a$ where Ph is phenylene, a and n are independently 1 to 2 and may be on average fractional and the the phenylenes in $(\text{Ph})_a$ are linked by a single chemical bond. Preferably the polyarylsulphone carries end groups providing active hydrogen and has a molecular weight over 5000. The composition may contain reinforcing fibres. In a structure made by curing such a composition the polymers components may be combined in a network in which each extends continuously or in which islands of predominantly thermoset resin are dispersed in a continuous phase of predominantly thermoplast polymer.



ABSTRACT"POLYMER COMPOSITION"

5 A curable polymer composition comprising a polymerisable cyanate ester thermoset component and a polyarylsulphone thermoplast component containing ether- and/or thioether- linked repeating units $(\text{PhSO}_2\text{Ph})_n$ and $(\text{Ph})_a$ where Ph is phenylene, a and n are independently 1 to 2 and may be on average fractional and the the phenylenes in $(\text{Ph})_a$ are linked by a single chemical bond. Preferably the polyarylsulphone carries end groups providing active hydrogen and has a molecular weight over 5000.

10 The composition may contain reinforcing fibres. In a structure made by curing such a composition the polymers components may be combined in a network in which each extends continuously or in which islands of predominantly thermoset resin are dispersed in a continuous phase of predominantly thermoplast polymer.

Polymer Composition

This invention relates to a polymer composition and more particularly to a composition containing a thermosettable cyanate resin precursor and a thermoplast effective to make said resin tougher when cured. It relates also such a composition containing reinforcing fibres and to cured resin structures made of such a composition.

Thermoset resins have been used for many years to make strong non-metallic structures, but have had somewhat limited fields of application because they are brittle. EP-A-311349 describes a polymer composition providing a useful improvement in fracture toughness and briefly review earlier attempts to meet this requirement. Whereas that application mentions in a general way that the thermoset component of its compositions may be a cyanate resin, we have now identified particular compositions affording a significant advance in performance. EP-A-0311341 describes a curable composition comprising a blend of a polycyanate ester of a polyhydric phenol and a broadly defined aromatic thermoplastic resin soluble in the blend.


The invention provides in its first aspect a curable polymer composition comprising a polymerisable cyanate ester thermoset component and a polyarylsulphone thermoplastic component containing ether- and/or thioether- linked repeating units $(\text{PhSO}_2\text{Ph})_n$ and $(\text{Ph})_a$ where Ph is phenylene, a and n are independently 1 to 2 and may be on average fractional and the phenylenes in $(\text{Ph})_a$ are (when a exceeds 1) linked by a single chemical bond.

In the polyarylsulphone component the relative proportions of the said repeating units is such that on average at least two units $(\text{PhSO}_2\text{Ph})_n$ are in immediate mutual succession in each polymer chain present and is preferably in the range 1:99 to 99:1, especially 10:90 to 90:10, respectively. Typically the ratio is in the range 25-50 $(\text{Ph})_a$, balance $(\text{Ph SO}_2 \text{ Ph})_n$. In preferred polyarylsulphones the units are
I X Ph SO₂ Ph X Ph SO₂ Ph ("PES"); and
II X $(\text{Ph})_a$ X Ph SO₂ Ph ("PEES")
where X is O or S and may differ from unit to unit; the ratio of I to II (respectively) preferably between 10:90 and 80:20 especially between 10:90 and 55:45.

The relative proportions of the repeating units of the polyarylsulphone may be expressed in terms of the weight percent SO₂

content, defined as 100 times (weight of SO₂)/(weight of average repeat unit). A preferred SO₂ content is at least 22, preferably 23 to 25%. When a = 1 this corresponds to PES/PEES ratios of at least 20:80, preferably in the range 35:65 to 65:35.

5 The above proportions refer only to the units mentioned. In addition to such units the polyarylsulphone may contain up to 50 especially up to 25% molar of other repeating units: the preferred SO₂ content ranges (if used) then apply to the whole polymer. Such units may be for example of the formula



in which A is a direct link, oxygen, sulphur, -CO- or a divalent hydrocarbon radical. When the polyarylsulphone is the product of nucleophilic synthesis, its units may have been derived for example from one or more of the following bisphenols and/or corresponding bistiols or phenol - thiols

hydroquinone

4,4'- dihydroxybiphenyl

20 resorcinol

dihydroxynaphthalene (2,6 and other isomers)


4,4'-dihydroxydiphenyl ether or -thioether

4,4'-dihydroxybenzophenone

2,2--di-(4-hydroxyphenyl)-propane or -methane.


25 If a bis-thiol is used, it may be formed in situ, that is, a dihalide as described for examples below may be reacted with an alkali sulphide or polysulphide or thiosulphate.

Other examples of such additional units are of the formula



in which Q and Q', which may be the same or different, are CO or SO₂; Ar is a divalent aromatic radical; and n is 0, 1, 2, or 3, provided that n is not zero where Q is SO₂. Ar is preferably at least one divalent aromatic radical selected from phenylene, biphenylene or terphenylene. Particular units have the formula

35



5

where m is 1, 2 or 3. When the polymer is the product of nucleophilic synthesis, such units may have been derived from one or more dihalides, for example:

4,4'-dihalobenzophenone

10

4,4'-bis-(4-chlorophenylsulphonyl)biphenyl

1,4 -bis-(4-halobenzoyl)benzene

4,4'-bis-(4-halobenzoyl)biphenyl

They may of course have been derived partly from the corresponding bisphenols.

15

The polyarylsulphone may be the product of nucleophilic synthesis from halophenols and/or halothiophenols. In any nucleophilic synthesis the halogen if chlorine or bromine may be activated by the presence of a copper catalyst. Such activation is often unnecessary if the halogen is activated by an electron withdrawing group. In any event fluoride is usually more active than chloride. Any nucleophilic synthesis of the polyarylsulphone is carried out preferably in presence of one or more alkali metal carbonates in up to 10% molar excess over the stoichiometric and of an aromatic sulphone solvent, at a temperature in the range 150-350°C.

20

25

If desired, the polyarylsulphone may be the product of electrophilic synthesis.

30

The polyarylsulphone preferably contains end groups and/or pendant groups of formula $-A'Y$ where A' is a divalent hydrocarbon group, preferably aromatic, and Y is a group reactive with cyanate groups or with a curing agent or with like groups on other polymer molecules. Examples of Y are groups providing active hydrogen especially OH , NH_2 , NHR or $-SH$, where R is a hydrocarbon group containing up to 8 carbon atoms, or providing other cross-linking reactivity especially epoxy, cyanate, isocyanate, acetylene or ethylene, as in vinyl, allyl propenyl or maleimide. Suitable end groups are NH_2 and/or OH , to the extent of at least 70% by mols of its total end groups.

35

The number average molecular weight of the polyarylsulphone is suitably in the range 2000 to 60000. Preferably it is over 5000 especially over 10000 for example 11000 to 25000 and structurally as well as by chemical interaction increases toughness by comparison with that of the thermoset resin alone by providing zones of the tough thermoplast between cross-linked thermoset zones. Another useful sub-range is 3000-11000, especially 3000-9000 in which it acts more as a chain-extender for the thermoset resin, separating and diluting local cross-link zones and thus toughening the structure. Within the above definition of the polyarylsulphone those are preferably chosen which are miscible with suitable cyanate precursors, have high modulus and T_g and are tough.

It is convenient to use reduced viscosity (RV), measured on a solution of 1g of polymer in 100 ml of solution in dimethyl formamide at 25°C as an indication of molecular weight, the correlation being as follows:

RV	0.15	0.25	0.45	0.92
MW (number average)	5000	13000	20000	60000

(Such molecular weights were in fact measured by vapour phase osmometry and are of course subject to the usual error range of about 10%).

The cyanate ester resin component preferably contains cyanate groups linked to aromatic nuclei. Suitably it comprises one or more compounds of general formula NCOArZArOCN, where Ar is a divalent aromatic radical, especially paraphenylene, and Z is a linking group. Examples of Z are single-atom groups such as O, S, SO, SO₂ and CR₁R₂ (where R₁ and R₂ are hydrocarbon groups containing in all up to 12 carbon atoms and are possibly linked externally to form a ring). In other examples Z is larger, for example includes the residue of a cyclic diene such as dicyclopentadiene as in the compound used in Example 1 below, where m is up to 3 and can be fractional. The term "component" includes monomeric cyanic esters and also oligomeric derivatives thereof. In the curable composition according to the invention a mixture of monomeric and oligomeric cyanates, in proportions in the range 0.7:1 to 1.5:1 is preferably present.

The composition may contain a catalyst for curing the cyanate resin, for examples a compound of a metal such as copper, zinc or

cobalt. Such a catalyst should be added shortly before curing unless it is of the "latent" type, examples of which are cobalt compounds and chelates. Hydroxy compounds may also be added.

5 The curable composition may, if desired, contain one or more additional thermosettable resin components, for example epoxy resin precursors. The weight ratio of cyanate to other thermosettable components is suitably in the range 4:1 to 10:1. Suitable epoxy resin precursors have 2-4 epoxy groups in the molecule. Such additional components may be monomeric or partly condensed or a mixture of both.
10 Hardeners and catalysts appropriate to such resins may be used.

The weight proportion of the thermoplast component in the composition is typically in the range 10-60, especially 15-40, percent, calculated on the non-volatile constituents present after curing the thermoset resin.

15 The invention in a second aspect provides the composition in the cured state and structures made therefrom. In the cured state the thermoset and thermoplast components, the precursors of which were mutually miscible, form separate phases. There may be present a distinct continuous phase consisting substantially of one of the
20 components, through which particles of the other are dispersed. In a preferred composition each component is present as a phase elongated in at least one dimension, for example as a network in which each extends continuously through any mass of the composition. Such a morphology, known also as co-continuous or semi-interpenetrating is, in the
25 composition according to the invention, preferably the product of spinodal decomposition of the initial mixture as the thermoset component, in reacting with itself and any active groups on the thermoplast, becomes immiscible with the thermoplast.

30 The composition is particularly suitable for fabrication of structures, including load-bearing or impact resisting structures. For this purpose it may contain a reinforcing agent such as fibres. Fibres can be added short or chopped typically of mean fibre length not more than 2 cm, for example about 6 mm, typically at a concentration of 5 to

35, preferably at least 20%, by weight. For structural applications, it is preferred to use continuous fibre for example glass or carbon, especially at 30 to 70, more especially 50 to 70, % by volume.

5 The fibre can be organic, especially of stiff polymers such as polyparaphenylene terephthalamide, or inorganic. Among inorganic fibres glass fibres such as "E" or "S" can be used, or quartz, alumina, zirconia, silicon carbide, other compound ceramics or metals. A very suitable reinforcing fibre is carbon, especially as graphite. Organic or carbon fibre is preferably unsized or is sized with a material that is compatible with the composition according to the invention, in the
10 sense of being soluble in the liquid precursor composition without adverse reaction or of bonding both to the fibre and to the thermoset/thermoplastic composition according to the invention. In particular carbon or graphite fibres that are unsized or are sized with epoxy resin precursor or thermoplast such as polyarylsulphone are preferred.
15 Inorganic fibre preferably is sized with a material that bonds both to the fibre and to the polymer composition; examples are the organo-silane coupling agents applied to glass fibre.

20 The composition may contain for example conventional toughening agents such as liquid rubbers having reactive groups, aggregates such as glass beads, rubber particles and rubber-coated glass beads, fillers such as polytetrafluorethylene, graphite, boron nitride, mica, talc and vermiculite, pigments, nucleating agents, and stabilisers such as phosphates. The total of such materials and any fibrous reinforcing
25 agent should be such that the composition contains at least 20% by volume of the polysulphone/thermoset mixture. The percentages of fibres and such other materials are calculated on the total composition after curing at up to 200°C.

30 A further procedure comprises forming incompletely cured composition into film by for example compression moulding, extrusion, melt-casting or belt-casting, laminating such films to fibrous reinforcing agent in the form of for example a non-woven mat of relatively short fibres, a woven cloth or essentially continuous fibre in conditions of temperature and pressure sufficient to cause the mixture to flow and impregnate the
35 fibres and curing the resulting laminate.

Plies of impregnated fibrous reinforcing agent, especially as made

by the procedure of one or more of EP-A 56703, 102158 and 102159, can be laminated together by heat and pressure, for example by compression moulding or by heated rollers, at a temperature above the curing temperature of the thermosetting resin or, if cure has already taken place, above the glass transition temperature of the mixture, conveniently at least 120°C and typically about 180°C, and at a pressure in particular at least 0.1, preferably at least 5, MN/m².

The resulting multi-ply laminate may be anisotropic in which the fibres are oriented essentially parallel to one another or quasi-isotropic in each ply of which the fibres are oriented at an angle, conveniently 45° as in most quasi-isotropic laminates but possibly for example 30° or 60° or 90° or intermediately, to those in the plies above and below. Orientations intermediate between anisotropic and quasi-isotropic, and combination laminates, may be used. Suitable laminates contain at least 4 preferably at least 8, plies. The number of plies is dependent on the application for the laminate, for example the strength required, and laminates containing 32 or even more, for example several hundred, plies may be desirable. There may be aggregates, as mentioned above in interlaminar regions.

Example 1

A polymer composition was made from the following components:


25 parts by weight of polyarylsulphone:

40 mol percent PES, 60 mol percent PEES (a=1)

100% NH₂ end groups

RV 0.24; T_g 198°C

40 parts by weight of cyanate oligomer derived from the phenol-dicyclopentadiene adduct in which m = 0.2



35 parts by weight of cyanate monomer: 1,1-diphenylethane-4,4'-dicyanate. The cyanate oligomer was melted at 80-90°C and the cyanate monomer was added. A solution of the polyarylsulphone in methylene

chloride was mixed in. The solvent was boiled off down to a volatiles level of about 3%. A solution of copper acetylacetonate (1% in nonylphenol) providing 63 ppm by weight of metal per 100 parts of cyanate resin was stirred in for 5 mins at 80-90°C. The mixture was cooled to ambient temperature.

A sample of the mixture was impregnated on to unidirectional carbon fibre "HITEX 468b" (supplied by HITCO) at a resin content of 35% by weight and a fibre areal weight of 145 g/sq.m.

The tape was cured in this cycle under 100 psi pressure:

heat up at 1.1°C per min

1h hold at 121°C

4h at 177°C; followed by

2h post cure at 220-240°C

Samples of the impregnated tape were subjected to standard tests. The results are set out in the Table 1 following Example 4. A sample of neat polymer composition was subjected to the same curing cycle and examined microscopically. It was observed to have a co-continuous network structure.

Example 2

Example 1 was repeated subject to the modification that the proportions of the three components were 20:50:30 respectively, the fibre was "IM7" (supplied by Hercules Inc) and the polymer had RV 0.26, Tg 200°C.

The results of the standard tests are set out in Table 1 following Example 4.

Again a sample of cured neat polymer was observed to have a co-continuous network structure.

Example 3

Example 1 was repeated except that the polyarylsulphone had 100% hydroxy end groups and RV 0.32, Tg 203°C, and that the fibre was "IM7". Results of mechanical tests are shown in Table 1 following Example 4.

In cured neat composition a "phase-inverted" morphology was observed, with islands of predominantly thermoset resin dispersed in a continuous phase of predominantly thermoplast polymer.

Example 4

A polymer composition was made from the following component:

25 parts by weight of polyarylsulphone.

80 mol percent PES, 20 mol percent PEES (a=2)

over 90% OH end groups

RV 0.25; Mn estimated (from NMR) 9800; Tg 216°C

5 30 parts by weight of cyanate oligomer derived from

2,2-diphenylpropane - 4,4'-dicyanate

25 parts by weight of cyanate monomer as in Example 1. The procedure

for mixing, impregnation and cure were as in Example 1. A sample of

neat polymer composition was subjected to the same curing cycle and

10 examined microscopically. It was observed to have a co-continuous

morphology. Results of mechanical tests are shown in Table 1.

Table 1

	Example				
5		1	2	3	4
	Property				
	0° Tensile St MPa	2758	2303	2351	2558
10	0° Tensile Mod GPa	166.9	166.9	135.8	168.9
	0° Tensile Strain %	1.7	1.42	1.7	1.6
	CAI, MPa	255.1	234.4	206.8	213.7
15	0° Compressive St MPa				
	RT	1579	1296	1151	1234
	121°C	1103	1103	1089	1145
	121°C	999.7	1089	1034	1158
20	149°C	1117	1248	910	1062
	149°C	951	1200	951	1062
	G ₁₂ , GPa				
	RT	4.41	4.48	4.41	4.27
25	121°C/wet**	3.24	3.44	2.96	3.51
	149°C/wet**	2.90	2.69	3.51	2.69
	177°C/wet**	--	1.10	1.79	1.17

30

Notes

* Wet = 7 days immersion at 71°C

** Wet = 85% RH at 66°C to saturation.

Example 5

Environmental resistance

Sample of impregnated tape from Examples 1 and 4 were laid up in a +/-45 4 ply laminate, and subjected to the curing cycle and post-cure described in Example 1.

Specimens were treated as follows:

JP4 or MEK 6 days' immersion at ambient temperature

water 14 days' immersion at 71°C

then tested for tensile strength and modulus weight increase. Results are shown in Table 2.

Table 2

	Control	JP4	MEK	Water
Example 1				
Tensile strength MPa	177.9	174.4	180.0	137.9
Tensile modulus GPa	15.3	14.3	13.0	13.1
Weight increase, %	- 0.02	0.87	0.65
Example 4				
Tensile strength MPa	150.3	146.9	165.5	113.1
Tensile modulus GPa	14.5	14.5	12.0	14.2
Weight increase, %	0	0.71	0.81

Example 6

In a polymer composition was used a polyarylsulphone consisting of the ether-linked units (Ph SO₂ Ph)₂ 30 mol %; Ph SO₂Ph 50 mol % and Ph₂ 20 mol % (thus in the general formula n = 1.375 and a= 2), which had been made by reacting together the monomers Cl Ph SO₂ Ph Ph SO₂ Cl, Cl-Ph SO₂ Ph Cl, HO Ph SO₂ Ph OH and HO Ph Ph OH in the presence of alkali

carbonate and diphenylsulphone solvent, in proportions giving over 90 mol % OH end groups. Its RV was 0.26 and Tg 235°C. This polymer (25 parts by weight) was mixed with 45 parts by weight of cyanate oligomer derived from 2,2-diphenylpropane-4,4'-dicyanate and 35 parts by weight of a cyanate monomer 1,1-diphenylethane-4,4'-dicyanate. The procedure for mixing, impregnation and cure were as in Example 1, except the fiber used was IM7 from Hercules. A sample of neat resin was subjected to cure and examined microscopically. It was observed to have islands of predominantly thermoset resin dispersed in a continuous phase of predominantly thermoset polymer. Its mechanical properties were:

0° Tensile str, MPa 2227
 0° Tensile mod GPa 149.6
 0° Tensile stn, % 1.45

CAI,
 1500 kJm⁻² 6.18

0° Comp str, MPa	DRY	WET (7 days at 71°C)
RT	1207	N/A
121°C	1103	1131
149°C/wet	1220	1186


G ₁₂ GPa	DRY	WET (85% RH at 66°C saturation)
RT	3.93	
121°C		2.83
149°C		2.48
163°C		2.48
177°C		2.07

Claims

1 A curable polymer composition comprising:-


a) a polymerisable cyanate ester thermoset component selected from one or more compounds, or oligomeric species thereof, of the group consisting of:-

i) compounds of general formula



where Ar is a divalent aromatic radical and Z is a single atom group selected from the class consisting of O, S, SO, SO₂, and CR₁R₂ where R₁ and R₂ are hydrocarbon groups containing in all up to 12 carbon atoms and optionally are linked to form a ring structure; and

ii) compounds of general formula




where m is up to 3 and can be fractional; and

b) a polyarylsulphone thermoplast component containing ether- and/or thioether-linked repeating units



and



where Ph is phenylene, a and n are independently 1 to 2 and may on average be fractional and the phenylenes in (Ph)_a (when a exceeds 1) are linked by a single chemical bond, the relative proportions of said repeating units being such that, on average, at least two units (PhSO₂Ph)_n are in immediate mutual succession in each polymer chain present.

2. A composition according to claim 1 in which the polyarylsulphone contains the units:

I XPhSO₂PhXPhSO₂Ph (PES); and

II X(Ph)_aXPhSO₂Ph (PEES)

in a ratio of I to II between 10:90 and 55:45, wherein X is O or S and may differ from unit to unit.

3. A composition according to claim 2 in which a = 1 and the ratio of I to II is in the range 35:65 to 65:35

4. A composition as according to any one of claims 1 to 3 wherein the polyarylsulphone carries end groups providing active hydrogen.

5. A composition according to claim 4 in which the polyarylsulphone has NH₂ and/or OH end groups, to the extent of at least 70 mol percent of its total end groups.

6. A composition according to any one of claims 1 to 5 wherein the polyarylsulphone has a molecular weight over 5000

- 14 -

7. A composition according to any of claims 1 to 6 in which the cyanate ester component is a mixture of monomeric and oligomeric cyanates.
8. A composition according to any one of claims 1 to 7 which contains reinforcing fibres.
9. A structure made by curing a composition according to any one of claims 1 to 8 in which the polymer components are combined in a network in which each extends continuously or in which islands of predominantly thermoset resin are dispersed in a continuous phase of predominantly thermoplast polymer.