

(19) AUSTRALIAN PATENT OFFICE

(54) Title
Fluorochemical composition comprising a fluorinated polyether and treatment of a fibrous substrate therewith

(51)⁶ International Patent Classification(s)
C08F 290/06 65/00
 (2006.01) 20060101ALI2005100
C08G 65/00 (2006.01)^{8BMEP} **C08L**
C08L 71/02 (2006.01) 71/02
D06M 15/277 20060101ALI2005100
 (2006.01) 8BMEP **D06M**
C08F 290/06 15/277
 20060101AFI2006031 20060101ALI2006031
 0BMJP **C08G** 0BMJP
 PCT/US03/16342

(21) Application No: 2003239605 (22) Application Date: 2003.05.23

(87) WIPO No: WO03/099904

(30) Priority Data

(31) Number (32) Date (33) Country
60/383,349 2002.05.24 US

(43) Publication Date : 2003.12.12

(43) Publication Journal Date : 2004.02.05

(71) Applicant(s)
3M Innovative Properties Company

(72) Inventor(s)
Flynn, Richard M., Dams, Rudolf J., Vitcak, Daniel R., Buckanin, Richard S., Audenaert, Frans A.,

(74) Agent/Attorney
Davies Collison Cave, 255 Elizabeth Street, Sydney, NSW, 2000

(56) Related Art
US 6376572
US 5623037
US 3814741

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
4 December 2003 (04.12.2003)

PCT

(10) International Publication Number
WO 2003/099904 A3

(51) International Patent Classification⁷: C08G 65/00, G08G 18/50

(21) International Application Number: PCT/US2003/016342

(22) International Filing Date: 23 May 2003 (23.05.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 60/383,349 24 May 2002 (24.05.2002) US

(71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY (US/US); 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventors: AUDENAERT, Frans A.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). DAMS, Rudolf J.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). BUCKANIN, Richard S.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). FLYNN, Richard M.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). VITCAK, Daniel R.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: JORDAN, Robert H., et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (national): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CI, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), FR, IS, IT (utility model), IL, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK (utility model), SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EL, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report: 22 April 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 2003/099904 A3

(54) Title: FLUOROCHEMICAL COMPOSITION COMPRISING A FLUORINATED POLYETHER AND TREATMENT OF A FIBROUS SUBSTRATE THEREWITH

(57) Abstract: A fluorocchemical composition for rendering fibrous substrates oil repellent, water repellent, and/or stain repellent and comprising a fluorinated polymer dispersed in water or dissolved or dispersed in an organic solvent, the fluorinated polymer comprising units derived from (i) a mixture of two or more fluorinated polyether monomers that differ in at least their molecular weight, the fluorinated polyether monomers having an ethylenically unsaturated group and a perfluorinated polyether group and wherein at least 90% by weight of the mixture consists of fluorinated polyether monomers that have a perfluorinated polyether group having a molecular weight of at least 750g/mol and (ii) one or more units derived from one or more co-monomers other than a fluorinated polyether monomer and wherein the co-monomers comprise at least one non-fluorinated monomer. Also, method for treating fibrous substrate with such composition, fluorinated polyether monomers, and fluorinated polymers derived from such monomers.

**FLUOROCHEMICAL COMPOSITION COMPRISING A FLUORINATED POLYMER
AND TREATMENT OF A FIBROUS SUBSTRATE THEREWITH**

1. Field of the Invention

5 The present invention relates to a fluorochemical composition for rendering fibrous substrates oil repellent, water repellent and/or stain repellent. In particular, the present invention relates to fluorochemical compositions that contain a dispersion of a particular fluorinated polymer in water or a dispersion or solution thereof in an organic solvent. The invention further relates to a method of treating the fibrous substrate with the
10 fluorochemical composition. The invention also relates to particular fluorinated polyether monomers and to fluorinated polymers derived therefrom.

2. Background

15 Compositions for making substrates, in particular fibrous substrates, such as textile, oil- and water repellent have been long known in the art. When treating fibrous substrates and in particular textile such as apparel, it is desired that the textile retains its look and feel as much as possible. Therefore, the composition should normally not contain components that would affect the look of the product, i.e., the treatment should be substantially invisible to the unaided human eye. Also the feel of the substrate should
20 preferably be substantially unaffected. Typically this means that only low amounts of the solids of the composition can be applied. Accordingly, an oil- and/or water repellent composition should be highly effective in rendering a substrate repellent.

25 Commercially available oil- and/or water repellent compositions are typically based on fluorinated compounds that have a perfluorinated aliphatic group. Such compositions are also described in, for example, US 5,276,175 and EP 435 641. The commercial success of this type of compositions can be attributed to their high effectiveness. Fluorinated compounds based on perfluorinated ether moieties have also been described in the prior art for rendering fibrous substrates oil- and/or water repellent. For example, perfluorinated polyether compounds have been disclosed in EP 1 038 919, EP 273 449, JP-A-04-146917, JP-A-10-081873, US 3,536,710, US 3,814,741, US
30 3,553,179 and US 3,446,761.

35 US 3,553,179 discloses acrylate type esters of perfluoropolyoxa-alkaneamidoalkyl alcohols and homo- and copolymers derived therefrom and the treatment therewith of

fabrics to render the latter oil- and/or water repellent. According to the teaching of this patent, the best results are obtained when the polymer is derived from monomers in which the perfluorinated polyether moiety has a fairly low molecular weight. Such compounds however have the disadvantage that perfluorinated degradation products may form or 5 perfluorinated residuals from the preparation of polymer may be present that have a low molecular weight. These compounds can be present in substantial amounts and may not eliminate quickly from living organisms and are therefore environmentally less desired. Additionally, the examples in this patent indicate that fairly high levels of the fluorinated polymer need to be applied on the fabric and even then, the compositions do not always 10 seem to provide oil repellency properties.

Accordingly, it is a desire to find fluorochemical compositions based on a perfluorinated polyether compound that can provide good to excellent oil- and/or water repellency properties to a fibrous substrate. Preferably, the fluorochemical composition is capable of providing durable oil- and/or water repellency properties to a fibrous substrate 15 such that a treated fibrous substrate can substantially maintain the repellency properties even after several washing cycles. Preferably a fibrous substrate treated with the fluorochemical composition has a soft feel, preferably the feel of a treated fibrous substrate is either the same or softer compared to the untreated fibrous substrate. It is a further desire that the fluorochemical compositions can be easily and efficiently 20 manufactured at a low cost. It is further desired to find compositions that have environmentally beneficial properties.


3. Summary of the Invention

In accordance with one aspect, the present invention provides a fluorochemical 25 composition comprising a fluorinated polymer dispersed in water or dispersed or dissolved in an organic solvent, said fluorinated polymer comprising units derived from (i) a mixture of two or more fluorinated polyether monomers that differ in at least their molecular weight, said fluorinated polyether monomers having an ethylenically unsaturated group and a perfluorinated polyether group and wherein at least 90% by weight and preferably at 30 least 95% by weight of said mixture consists of fluorinated polyether monomers that have a perfluorinated polyether group having a molecular weight of at least 750g/mol and (ii) one or more units derived from one or more co-monomers other than a fluorinated

polyether monomer and wherein said co-monomers comprise at least one non-fluorinated monomer. The terms "dispersion" and "disperse" as used herein are intended to include dispersion of solids in a liquid as well as liquid in liquid dispersions, which are often called emulsions.

5 In a further aspect, the present invention also provides a method of treatment of a fibrous substrate with the fluorochemical composition. It has been found that the fluorochemical composition can provide good oil- and/or water repellency properties to the substrate even at low levels of application of for example between 0.1% by weight and 1% by weight based on the weight of the substrate. Additionally, a more environmentally friendly fluorochemical composition can be conveniently manufactured and at a reasonable cost. Indications show that perfluorinated polyether compounds that have a perfluorinated polyether moiety having a molecular weight of at least 750g/mol and perfluorinated polyether degradation products that may form therefrom would eliminate well from the body of living organisms. In particular compounds having perfluorinated 10 polyether moieties having a molecular weight of at least 750g/mol and which are based on a polycondensation of hexafluoropropylene oxide would eliminate more easily from the body of living organisms compared to long chain perfluoroaliphatic compounds. Thus, by minimizing the amount of monomers that have low molecular weight fluorinated polyether 15 moieties in the preparation of the fluorinated polymer, environmentally more friendly compositions can be made in a convenient and cost effective way.

20 In accordance with a further aspect of the present invention there are also provided monomers according to the formula:




25 wherein R^1 represents a perfluorinated alkyl group, n is an integer of 3 to 25, R represents hydrogen or an alkyl group of 1 to 4 carbon atoms, Q^2 is a divalent linking group selected from the group consisting of:



wherein L^1 represents a chemical bond or an organic divalent linking group, L^2 represents an organic divalent linking group and * indicates the position where the linking group is 30 attached to the perfluorinated polyether group.

In a still further aspect, the present invention provides monomers of the formula:



wherein PF represents a perfluorinated polyether group, L³ and L⁴ each independently represent a non-fluorinated organic divalent linking group, X³ and X⁴ independently represent O or NR^a wherein R^a is hydrogen or an alkyl group of 1 to 4 carbon atoms, Z represents a residue of a polyisocyanate having a valence p and wherein p is at least 2, and

5 R^b represents hydrogen or methyl.


In a further aspect of the invention, there are provided fluorinated polymers including homopolymers as well as copolymers that can be prepared from the aforementioned monomers of formula (II) or (III). Fluorochemical compositions of these fluorinated polymers are provided as well and have been found to yield good repellency 10 properties even if no units derived from non-fluorinated monomers are present in the polymer.

4. Detailed Description of Illustrative Embodiments of the Invention

The fluorinated polyether monomers for the preparation of the fluorinated polymer 15 preferably correspond to the formula:




wherein PF represents a perfluorinated polyether group, R is hydrogen or alkyl group of 1 to 4 carbon atoms for example methyl or ethyl and Q represents a non-fluorinated organic divalent linking group. Preferably Q is a divalent linking group selected from the group 20 consisting of:




wherein L¹ represents a chemical bond or an organic divalent linking group, L² represents an organic divalent linking group and R^a is hydrogen or an alkyl group having 1 to 4 carbon atoms and * indicates the position where the linking group is attached to the group 25 PF in formula (I). Examples of organic divalent linking groups L¹ include an oxy group, an amido group, a carboxy group, a carbonyl group, an aryl group that may be substituted and an alkylene group that may be substituted and/or that may be interrupted with one or more heteroatoms or with an amido group, a carboxy group, a urethane group or a carbonyl group. Examples of divalent linking groups L² include an aryl group that may be 30 substituted and an alkylene group that may be substituted and/or that may be interrupted with one or more heteroatoms or with an amido group, a carboxy group, a urethane group or a carbonyl group.

The perfluorinated polyether moiety PF of the fluorinated polyether monomer of formula (I) preferably corresponds to the formula:



wherein R^1_f represents a perfluorinated alkyl group, R^2_f represents a perfluorinated


5 polyalkyleneoxy group consisting of perfluorinated alkyleneoxy groups having 1, 2, 3 or 4 carbon atoms or a mixture of such perfluorinated alkylene oxy groups, R^3_f represents a perfluorinated alkylene group and q is 0 or 1. The perfluorinated alkyl group R^1_f in the above formula (Ia) may be linear or branched and may comprise 1 to 10 carbon atoms, preferably 1 to 6 carbon atoms. A typical perfluorinated alkyl group is $CF_3-CF_2-CF_2-$. R^3_f is a linear or branched perfluorinated alkylene group that will typically have 1 to 6 carbon atoms. For example, R^3_f is $-CF_2-$ or $-CF(CF_3)-$. Examples of perfluoroalkylene oxy groups of perfluorinated polyalkyleneoxy group R^2_f include:




20 The perfluoroalkyleneoxy group may be comprised of the same perfluoroalkylene oxy units or of a mixture of different perfluoroalkylene oxy units. When the perfluoroalkyleneoxy group is composed of different perfluoroalkylene oxy units, they can be present in a random configuration, alternating configuration or they can be present as blocks. Typical examples of perfluorinated polyalkylene oxy groups include:

25 - $[CF_2-CF_2-O]_r-$; - $[CF(CF_3)-CF_2-O]_n-$; - $[CF_2-CF_2-O]_i-[CF_2-O]_j-$ and - $[CF_2-CF_2-O]_l-[CF(CF_3)-CF_2-O]_m-$; wherein r is an integer of 4 to 25, n is an integer of 3 to 25 and i, l, m and j each are integers of 2 to 25. A preferred perfluorinated polyether group that corresponds to formula (Ia) is $CF_3-CF_2-CF_2-O-[CF(CF_3)-CF_2-O]_n-CF(CF_3)-$ wherein n is an integer of 3 to 25. This perfluorinated polyether group has a molecular weight of 783 when n equals 3 and can be derived from an oligomerization of hexafluoropropylene oxide. This perfluorinated polyether group is preferred because of its benign environmental properties.

Thus, in a particular embodiment of the invention, the fluorinated polyether monomer corresponds to the formula:




wherein R^1 represents a perfluorinated alkyl group, n is an integer of 3 to 25, R represents hydrogen or an alkyl group of 1 to 4 carbon atoms, Q^2 is a divalent linking group selected from the group consisting of:



wherein L^1 represents a chemical bond or an organic divalent linking group, L^2 represents an organic divalent linking group and $*$ indicates the position where the linking group is attached to the perfluorinated polyether group.

Specific examples of fluorinated polyether monomers according to formula (I) or (II) include:




wherein m is 2, 3, 4, 6, 8, 10, or 11; R is an alkyl group of 1 to 6 carbons; and R' is H or methyl;



wherein R' is H or methyl;



wherein m is 2, 3, 4, 6, 8, 10, or 11; R is an alkyl group of 1 to 6 carbons; and R' is H or methyl;



wherein m is 2, 3, 4, 6, 8, 10, or 11; R is an alkyl group of 1 to 6 carbons; and R' is H or methyl; and



wherein m is 2, 3, 4, 6, 8, 10, or 11; and R is an alkyl group of 1 to 6 carbons.

In the above exemplified compounds, PF has the meaning as defined above and is preferably CF₃CF₂CF₂O-(CF(CF₃)CF₂O)_nCF(CF₃)-


The fluorinated polyether compounds of the above formula (I) and (II) can be readily obtained starting from, e.g., acid, ester or acid halide terminated perfluorinated

polyether and reacting with an appropriate reactant to introduce the ethylenically unsaturated group and linking group Q or Q². These reactions are well-known to those skilled in the art and examples of suitable reactions and reactants to introduce the


ethylenically unsaturated group and linking group Q or Q² can be found for example in EP 870 778. For example, the following table lists some -Q-C(R)=CH₂ end groups that can be obtained from a reaction of an acid or ester terminated perfluorinated polyether with the indicated reactant:

	Reactant
5	-CONHCH ₂ -CH=CH ₂
	H ₂ NCH ₂ -CH=CH ₂
	-CONH-C ₆ H ₄ -CH ₂ CH=CH ₂
	H ₂ N-C ₆ H ₄ -CH ₂ CH=CH ₂
	-COOCH ₂ CH=CH ₂
	CH ₂ =CH-CH ₂ -OH
	-CH ₂ OCH ₂ CH=CH ₂
10	1) reduction with LiAlH ₄ to CH ₂ OH
	2) CH ₂ =CHCH ₂ Br
	-CH ₂ OOC-C(CH ₃)=CH ₂
	1) reduction with LiAlH ₄ to CH ₂ OH
	2) methacryloyl chloride
	-CH ₂ OOCNH-CH ₂ CH ₂ -OOC-CH=CH ₂
	1) reduction with LiAlH ₄ to CH ₂ OH
	2) OCN-CH ₂ CH ₂ -OOC-CH=CH ₂

15 Still further suitable fluorinated monomers include those that correspond to the following general formula (III):



wherein PF represents a perfluorinated polyether group preferably having a molecular weight of at least 750g/mol, e.g., a perfluorinated polyether group as described above, L³ and L⁴ each independently represent a non-fluorinated organic divalent linking group, X³ and X⁴ independently represent O or NR^a wherein R^a is hydrogen or an alkyl group of 1 to 4 carbon atoms, Z represents a residue of a polyisocyanate having a valence p and wherein p is at least 2, and R^b represents hydrogen or methyl. Examples of non-fluorinated divalent linking groups L³ include alkylene, arylene, carboxy alkylene, carbonamido alkylene and oxyalkylene. In a particular embodiment, L³ is an organic divalent linking group selected from



wherein * denotes the position where the linking group is attached to the perfluorinated polyether group and wherein L¹ and L² are as defined above. Examples of linking groups L⁴ include alkylene, arylene, alkyleneoxy carbonyl, alkyleneoxy, alkyleneamido. A preferred linking group L³ is carboxyalkylene and a preferred linking group L⁴ is alkyleneoxy carbonyl. L³ and/or L⁴ may contain urethane or urylene linkages.

Fluorinated polyether monomers according to formula (III) can be obtained by first condensing a di- or triisocyanate with, respectively, an equimolar or double molar amount of a perfluorinated polyether that has an isocyanate reactive group such as a hydroxy group, thiol or amine in its end-group. This reaction is typically carried out at 5 temperatures between 50 and 80 °C, by slow addition of the perfluorinated polyether alcohol, thiol or amine to a solution of the polyisocyanate in an anhydrous organic solvent without zero-witnoff hydrogens, such as ethylacetate or isobutylmethylketone, further containing small amounts of radical inhibitors such as hydroquinone monoalkylethers or phenothiazine (50 – 200 ppm). Optionally a small amount of a tin or other suitable 10 urethane catalyst can be added to accelerate the reaction. After completion of this first step an equimolar amount of a monofunctional polymerizable compound is added and reacted until all residual isocyanate groups have disappeared. For completion of the second step, sometimes additional catalyst and a slight excess of the polymerizable compound may be required. Preferred polymerizable compounds include acrylates, 15 methacrylates, acrylamides or methacrylamides, that have been functionalized with a hydroxy, carboxyl, amino or thiol group. The condensation reaction may further involve a chain extender such as a diol or a diamine. Examples of chain extenders include alkane diols and alkane diamines.

Examples of polyisocyanates for preparing the monomers of formula (III) include 20 aromatic as well as aliphatic polyisocyanates. Suitable polyisocyanates for the preparation of the blocked polyisocyanate extenders preferably are di- or triisocyanates as well as mixtures thereof. Specific examples are aromatic diisocyanates such as 4,4'-methyleneidiphenylenediisocyanate, 4,6-di-(trifluoromethyl)-1,3-benzene diisocyanate, 2,4-toluenediisocyanate, 2,6-toluene diisocyanate, o, m, and p-xylylene diisocyanate, 4,4'-diisocyanatodiphenylether, 3,3'-dichloro-4,4'-diisocyanatodiphenylmethane, 4,5'-diphenyldiisocyanate, 4,4'-diisocyanatodibenzyl, 3,3'-dimethoxy-4,4'-diisocyanatodiphenyl, 3,3'-dimethyl-4,4'-diisocyanatodiphenyl, 2,2'-dichloro-5,5'-dimethoxy-4,4'-diisocyanato diphenyl, 1,3-diisocyanatobenzene, 1,2-naphthylene diisocyanate, 4-chloro-1,2-naphthylene diisocyanate, 1,3-naphthylene diisocyanate, and 25 1,8-dinitro-2,7-naphthylene diisocyanate and aromatic tri-isocyanates such as polymethylenepolyphenylisocyanate.

Still further isocyanates that can be used include alicyclic diisocyanates such as 3-isocyanatomethyl-3,5,5-trimethylcyclohexylisocyanate; aliphatic diisocyanates such as 1,6-hexamethylenediisocyanate, 2,2,4-trimethyl-1,6-hexamethylenediisocyanate, and 1,2-ethylenediisocyanate; aliphatic triisocyanates such as 1,3,6-hexamethylenetriisocyanate; aromatic tri-isocyanates such as polymethylenepolyphenylisocyanate (PAPI); cyclic diisocyanates such as isophorone diisocyanate (IPDI) and dicyclohexylmethane-4,4'-diisocyanate. Also useful are isocyanates containing internal isocyanate-derived moieties such as biuret-containing tri-isocyanates such as that available from Bayer as DESMODUR™ N-100, isocyanurate-containing tri-isocyanates such as that available from Huls AG, Germany, as IPDI-1890, and azetidine-dione-containing diisocyanates such as that available from Bayer as DESMODUR™ TT. Also, other di- or tri-isocyanates such as those available from Bayer as DESMODUR™ L and DESMODUR™ W, and tri-(4-isocyanatophenyl)-methane (available from Bayer as DESMODUR™ R) and DDI 1410 from Henkel are suitable.

Examples of fluorinated macromonomers according to formula (III) include the following:


PF-CONR-(CH₂)_mO-CONH-(CH₂)₆-NHCO(O(CH₂)_p)_qOCOC(R')=CH₂
 wherein m is 2, 3, 4, 6, 8, 10, or 11; p is 2, 3 or 4; q is 1-20; R is an alkyl group of 1 to 6 carbons; and R' is H or methyl;

PF-CONR-(CH₂)_mO-CONH-CH₂C(Me)₂CH₂CH(Me)CH₂CH₂-NHCO(O(CH₂)_p)_qOCOC(R')=CH₂
 wherein m is 2, 3, 4, 6, 8, 10, or 11; p is 2, 3 or 4; q is 1-20; R is an alkyl group of 1 to 6 carbons; and R' is H or Me;

PF-CONR-(CH₂)_mO-CONHC₆H₁₀-CH₂-C₆H₁₀-NHCO(O(CH₂)_p)_qOCOC(R')=CH₂
 wherein m is 2, 3, 4, 6, 8, 10, or 11; p is 2, 3 or 4; q is 1-20; R is an alkyl group of 1 to 6 carbons; and R' is H or Me;

PF-CONR-(CH₂)_mO-CONH-C₆H₇-(CH₃)₃-CH₂-NHCO(O(CH₂)_p)_qOCOC(R')=CH₂
 wherein m is 2, 3, 4, 6, 8, 10, or 11; p is 2, 3 or 4; q is 1-20; R is an alkyl group of 1 to 6 carbons; and R' is H or Me;

PF-CONR-(CH₂)_mO-CONH-C₆H₁₀-NHCO(O(CH₂)_p)_qOCOC(R')=CH₂
 wherein m is 2, 3, 4, 6, 8, 10, or 11; p is 2, 3 or 4; q is 1-20; R is an alkyl group of 1 to 6 carbons; and R' is H or Me;



wherein m is 2, 3, 4, 6, 8, 10, or 11; and R is an alkyl group of 1 to 6 carbons;



wherein m is 2, 3, 4, 6, 8, 10, or 11; R is an alkyl group of 1 to 6 carbons; and R' is

5 H or Me; and



wherein m is 2, 3, 4, 6, 8, 10, or 11; R is methyl, ethyl, propyl, butyl, or hexyl; and

R' is H or Me.

In the above listed examples, PF has the meaning as defined above and is preferably

10 CF₃CF₂CF₂O-(CF(CF₃)CF₂O)_nCF(CF₃)- and Me represents methyl.

In one aspect of the invention to prepare the fluorinated polymer of the

fluorochemical composition, a mixture of two or more fluorinated polyether monomers, typically a mixture of fluorinated polyether monomers that differ in molecular weight, is copolymerized with one or more co-monomers, at least one of which is a non-fluorinated

15 monomer. Non-fluorinated monomers include for example a hydrocarbon group

containing monomer such as monomers that can be represented by formula :



wherein R_h represents an aliphatic group having 4 to 30 carbon atoms, L represents an organic divalent linking group and Z represents an ethylenically unsaturated group.

20 The hydrocarbon group is preferably selected from the group consisting of a linear, branched or cyclic alkyl group, an aralkyl group, an alkylaryl group and an aryl group.

Further non-fluorinated monomers include those wherein the hydrocarbon group in formula (IV) includes oxyalkylene groups, is interrupted with one or more heteroatoms and/or contains substituents, such as hydroxy groups, amino groups and/or cure sites. The 25 term cure sites includes functional groups that are capable of engaging in a reaction with the substrate to be treated. Examples of cure sites include acid groups such as carboxylic acid groups, hydroxy groups, amino groups and isocyanate groups or blocked isocyanate groups. A preferred cure site is a blocked isocyanate group or an isocyanate group. The linking group L is for example a carboxy group, a carbonamido group or an oxy group.

30 Examples of non-fluorinated comonomers include hydrocarbon esters of an α,β -ethylenically unsaturated carboxylic acid. Examples include n-butyl(meth)acrylate, isobutyl(meth)acrylate, octadecyl(meth)acrylate, lauryl(meth)acrylate, cyclohexyl

(meth)acrylate, cyclodecyl (meth)acrylate, isobornyl (meth)acrylate, phenyl (meth)acrylate, benzyl (meth)acrylate, adamantyl (meth)acrylate, tolyl (meth)acrylate, 3,3-dimethylbutyl (meth)acrylate, (2,2-dimethyl-1-methyl)propyl (meth)acrylate, cyclopentyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, t-butyl (meth)acrylate, cetyl (meth)acrylate, 5 stearyl (meth)acrylate, behenyl (meth)acrylate, isoctyl (meth)acrylate, n-octyl (meth)acrylate, 4-ethyl-cyclohexyl (meth)acrylate, 2-ethoxyethyl methacrylate and tetrahydropyranyl acrylate. Further non-fluorinated comonomers include allyl esters such as allyl acetate and allyl heptanoate; alkyl vinyl ethers or alkyl allyl ethers such as cetyl vinyl ether, dodecylvinyl ether, ethylvinyl ether; unsaturated acids such as acrylic acid, methacrylic acid, alpha-chloro acrylic acid, crotonic acid, maleic acid, fumaric acid, itaconic acid and their anhydrides and their esters such as vinyl, allyl, methyl, butyl, isobutyl, hexyl, heptyl, 2-ethylhexyl, cyclohexyl, lauryl, stearyl, isobornyl or alkoxy ethyl 10 acrylates and methacrylates; alpha-beta unsaturated nitriles such as acrylonitrile, methacrylonitrile, 2-chloroacrylonitrile, 2-cyanoethyl acrylate, alkyl cyanoacrylates; 15 alpha,beta-unsaturated carboxylic acid derivatives such as allyl alcohol, allyl glycolate, acrylamide, methacrylamide, n-diisopropyl acrylamide, diacetoneacrylamide, aminoalkyl (meth)acrylates such as N,N-diethylaminoethylmethacrylate, N-t-butylaminoethylmethacrylate; alkyl(meth)acrylates having an ammonium group such as (meth)acrylates of the formula $X^+ R_3N^+ - R^e - OC(O) - CR^f - CH_2$ wherein X^+ represents an 20 anion such as, e.g., a chloride anion, R represents hydrogen or an alkyl group and each R may be the same or different, R^e represents an alkylene and R^f represents hydrogen or methyl; styrene and its derivatives such as vinyltoluene, alpha-methylstyrene, alpha-cyanomethyl styrene; lower olefinic hydrocarbons which can contain halogen such as ethylene, propylene, isobutene, 3-chloro-1-isobutene, butadiene, isoprene, chloro and dichlorobutadiene and 2,5-dimethyl-1,5-hexadiene, hydrocarbon monomers comprising 25 (poly)oxyalkylene groups including (meth)acrylates of a polyethylene glycol, (meth)acrylates of a block copolymer of ethylene oxide and propylene oxide, (meth)acrylates of amino- or diamino terminated polyethers and (meth)acrylates of methoxypolyethyleneglycols and hydrocarbon monomers comprising a hydroxyl group 30 include hydroxylgroup containing (meth)acrylates, such as hydroxyethyl(meth)acrylate and hydroxypropyl(meth)acrylate. Preferably, the non-fluorinated comonomer(s) will

comprise one or more chlorine containing monomers such as vinyl chloride and vinylidene chloride.


In a particular embodiment of the invention, the fluorinated polymer includes units having one or more cure sites. These units will typically derive from corresponding co-monomers that include one or more cure sites. Examples of co-monomers from which a cure site unit may derive include (meth)acrylic acid, maleic acid, maleic anhydride, allyl methacrylate, hydroxybutyl vinyl ether, N-hydroxymethyl (meth)acrylamide, N-methoxymethyl acrylamide, N-butoxymethyl acrylamide, N-isobutoxymethyl acrylamide, glycidylmethacrylate and α,α dimethyl m. isopropenyl benzyl isocyanate. Other examples include polymerizable urethanes, that can be obtained by the reaction of a polymerizable mono-isocyanate with an isocyanate blocking agent or by the reaction of a di- or poly- isocyanate and a hydroxy or amino-functionalized acrylate or methacrylate and an isocyanate blocking agent.

The fluorinated polymer may also comprise units that derive from fluorinated co-monomers other than fluorinated polyether monomers. Such additional fluorinated monomers are preferably short chain perfluoroaliphatic containing monomers. Preferably, fluorinated co-monomers that may be used in preparing the fluorinated polymer of the fluorochemical composition include those of the following formula:



wherein R_f^4 is a perfluoroaliphatic group of 3 to 5 or 6 carbon atoms, preferably C_4F_9 -, R^e is hydrogen or a lower alkyl of 1 to 4 carbon atoms and Q^3 represents a non-fluorinated organic divalent linking group. The linking group Q^3 links the perfluoroaliphatic group to the free radical polymerizable group. Linking group Q^3 is generally non-fluorinated and preferably contains from 1 to about 20 carbon atoms. Q^3 can optionally contain oxygen, nitrogen, or sulfur-containing groups or a combination thereof, and Q^3 is free of functional groups that substantially interfere with free-radical polymerization (e.g., polymerizable olefinic double bonds, thiols, and other such functionality known to those skilled in the art). Examples of suitable linking groups Q^3 include straight chain, branched chain or cyclic alkylene, arylene, aralkylene, sulfonyl, sulfoxy, sulfonamido, carbonamido, carbonyloxy, urethylene, ureylene, and combinations thereof such as sulfonamidoalkylene.

Specific examples of fluorinated aliphatic group containing monomers include:



wherein R^d is hydrogen or methyl.

In the above described aspect of the invention, the fluorinated polymer is a copolymer that typically comprises between 5 and 95% by weight of units deriving from the fluorinated polyether monomer and between 95 and 5% by weight of units deriving from one or more co-monomers that comprise at least one non-fluorinated monomer. More preferably, the fluorinated polymer will comprise between 10% by weight and 75% by weight of units deriving from the fluorinated polyether monomer and between 90% and 15% by weight of units deriving from non-fluorinated monomers and optional fluorinated monomers other than the fluorinated polyether monomer. In a particular preferred embodiment, the fluorinated polymer will comprise from 5 to 70% by weight of units deriving from the fluorinated polyether monomer, between 1 and 30% by weight of monomers comprising a cure site and between 0 and 94% by weight of other non-fluorinated monomers and/or other fluorinated monomers.

In accordance with another aspect of the present invention, the fluorinated polymer of the fluorochemical composition may be a fluorinated polymer that comprises one or more units that are derived from a monomer according to formula (II) or (III) and optionally one or more further units derived from comonomers described above including non-fluorinated and/or fluorinated comonomers described above. Thus, in accordance with this aspect of the invention, the fluorinated polymer can be a homopolymer of a monomer of formula (II) or (III), a polymer of a mixture of monomers according to formula (II) or (III) that differ in their molecular weight and of which preferably at least 90% by weight has a perfluorinated polyether group of a molecular weight of at least 25 750g/mol, or a copolymer of one or more monomers of formula (II) or (III) and a co-monomer at least one of which is a non-fluorinated monomer.

The fluorinated polymer is typically prepared by free radical polymerisation e.g. by solution or mini-emulsion polymerisation techniques. Various surfactants such as anionic, cationic, non-ionic or amphoteric surfactants may be employed. They can be used alone or in combination. Alternatively, the polymerisation may be done in solvent.

5 The polymerisation can be a thermal or photochemical polymerisation, carried out in the presence of a free radical initiator. Useful free radical initiators are known in the art and include azo compounds, such as azobisisobutyronitrile (AIBN), azobisvaleronitrile and azobis(2-cyanovaleic acid), 2,2'-azobis(2-amidinopropane)dihydrochloride and the like, hydroperoxides such as cumene, t-butyl, and t-amyl hydroperoxide, dialkyl peroxides such as di-t-butyl and dicumylperoxide, peroxyesters such as t-butylperbenzoate and di-t-butylperoxy phtalate, diacylperoxides such as benzoyl peroxide and lauroyl peroxide.

The polymerisation may further be carried out in the presence of a chain transfer agent or a chain terminator to tailor the molecular weight and/or properties of the fluorochemical polymer. Typically, the fluorinated polymer has a weight average molecular weight between 5000 and 300 000, preferably between 5000 and 100 000.

15 The fluorochemical composition comprises a dispersion of the fluorinated polymer in water or a dispersion or solution in an organic solvent. Generally, the amount of fluorinated polymer contained in the treating composition is between 0.01 and 4% by weight, preferably between 0.05 and 3% by weight based on the total weight of the 20 fluorochemical composition. Higher amounts of fluorinated polymer of more than 4% by weight, for example up to 10% by weight may be used as well, particularly if the uptake of the fluorochemical composition by the substrate is low. Generally, the fluorochemical treating composition will be prepared by diluting a more concentrated fluorochemical composition to the desired level of fluorinated polymer in the treating composition. The 25 concentrated fluorochemical composition can contain the fluorinated polymer in an amount of up to 70% by weight, typically between 10% by weight and 50% by weight.

The weight average particle size of the fluorinated polymer particles in an aqueous or solvent dispersion is preferably not more than 400nm, more preferably is not more than 300nm. A typical range is from 50nm to 400nm.

30 An aqueous dispersion of the fluorinated polymer may be non-ionic, anionic, cationic or zwitterionic. The dispersion is preferably stabilised using non-fluorinated surfactants, such as non-ionic polyoxyalkylene, in particular polyoxyethylene surfactants,

anionic non-fluorinated surfactants, cationic non-fluorinated surfactants and zwitterionic non-fluorinated surfactants. Specific examples of non-fluorinated surfactants that can be used are nonionic types such as Emulsogen EPN 207 (Clariant) and Tween 80 (ICI), anionic types such as lauryl sulfate and sodium dodecyl benzene sulfonate, cationic types such as Arquad T-50 (Akzo), Ethoquad 18-25 (Akzo) or amphoteric types such as lauryl amineoxide and cocamido propyl betaine. The non-fluorinated surfactant is preferably present in an amount of about 1 to about 25 parts by weight, preferably about 2 to about 10 parts by weight, based on 100 parts by weight of the fluorochemical composition.


5 Alternatively, a dispersion or solution of the fluorinated polymer in an organic solvent can be used as the fluorochemical treating composition. Suitable organic solvents 10 include alcohols such as isopropanol, methoxy propanol and t.butanol, ketones such as isobutyl methyl ketone and methyl ethylketone, ethers such as isopropylcither, esters such ethylacetate, butylacetate or methoxypropanol acetate or (partially) fluorinated solvents 15 such as HCFC-141b, HFC-4310 mee and hydrofluoroethers such as HFE-7100 or HFE-7200 available from 3M Company.

10 The fluorochemical composition may contain further additives such as buffering agent, agents to impart fire proofing or antistatic properties, fungicidal agents, optical bleaching agents, sequestering agents, mineral salts and swelling agents to promote penetration. In a particular embodiment, the fluorochemical composition may contain 15 additionally a non-fluorinated organic compound, wherein the non-fluorinated organic compound is capable of improving relative to the fluorochemical composition without the non-fluorinated organic compound, the oil repellency or water repellency that can be achieved by the fluorochemical composition on a fibrous substrate or the durability of one or both of the repellency properties. Such non-fluorinated organic compounds are 20 sometimes called extenders. Suitable extenders for use in the fluorochemical composition include non-fluorinated organic compounds that have one or more blocked isocyanate groups, so called blocked isocyanate compounds, or a carbodiimide compound. Preferred blocked isocyanate extenders are blocked polyisocyanates that at a temperature of less than 150°C are capable of reacting with an isocyanate reactive group, preferably through 25 deblocking of the blocking agent at elevated temperature. Blocked isocyanate extenders can be obtained from a reaction of an isocyanate component with a isocyanate blocking agent. Preferred blocking agents include arylalcohols such as phenols, lactams such as ϵ - 30

caprolactam, δ -valerolactam, γ -butyrolactam, oximes such as formaldoxime, acetaldoxime, methyl ethyl ketone oxime, cyclohexanone oxime, acetophenone oxime, benzophenone oxime, 2-butanone oxime or diethyl glyoxime. Further suitable blocking agents include bisulfite and triazoles.

5 According to a particular embodiment of the invention, the blocked polyisocyanate may comprise the condensation product of a polyisocyanate, for example, a di- or triisocyanate, a blocking agent, and a non-fluorinated organic compound other than the blocking agent and having one or more isocyanate reactive groups such as a hydroxy, amino, or thiol group.

10 The carbodiimide compound can be an aromatic or aliphatic carbodiimide compound and may include a polycarbodiimide. Carbodiimides that can be used have been described in for, example, US 4,668,726, US 4,215,205, US 4,024,178, US 3,896,251, WO 93/22282, US 5,132,028, US 5,817,249, US 4,977,219, US 4,587,301, US 4,487,964, US 3,755,242 and US 3,450,562. Particularly suitable carbodiimides for use in 15 this invention include those corresponding to the formula :



wherein u has a value of 1 to 20, typically 1 or 2, R^1 and R^2 each independently represent a hydrocarbon group, in particular a linear, branched or cyclic aliphatic group preferably having 6 to 18 carbon atoms and R^3 represents a divalent linear, branched or cyclic 20 aliphatic group.

25 The aliphatic carbodiimide extenders can be synthesized in a 1-step process by reacting aliphatic diisocyanates with an aliphatic mono-isocyanate as a chain stopper at 130 to 170 °C in the presence of a phospholine oxide or other suitable carbodiimide formation catalyst. Preferably the reaction is carried out in the absence of solvents under inert atmosphere, but high-boiling non-reactive solvents such as methyl isobutyl ketone can be added as diluents. The mole ratio of diisocyanate to mono-isocyanate can be varied from 0.5 to 10, preferably 1 to 5.

30 Examples of aliphatic diisocyanates for the preparation of the carbodiimide compounds include isophorone diisocyanate, dimer diacid diisocyanate, 4,4' dicyclohexyl methane diisocyanate. Examples of mono-isocyanates are n.butyl isocyanate and octadecyl isocyanate. Representative examples of suitable carbodiimide formation catalysts are described in, e.g., US 2,941,988, US 3,862,989 and US 3,896,251. Examples

include 1-ethyl-3-phospholine, 1-ethyl-3-methyl-3-phospholine-1-oxide, 3-methyl-1-phenyl-3-phospholine-1-oxide and bicyclic terpene alkyl or hydrocarbyl aryl phosphine oxide. The particular amount of catalyst used depends on the reactivity of the catalyst and the isocyanates being used. A concentration of 0.2 to 5 parts of catalyst per 100 g of

5 diisocyanate is suitable.

In an alternative approach the aliphatic diisocyanates can be first reacted with monofunctional alcohols, amines or thiols followed by carbodiimide formation in a second step.

The fluorochemical composition may contain also further fluorochemical 10 compounds other than the fluorinated polymer. For example, the fluorochemical composition may contain fluorochemical compounds that are based on or derived from perfluoroaliphatic compounds. Nevertheless, it is not necessary to include such 15 compounds in the fluorochemical composition. Also, if perfluoroaliphatic based compounds are included in the composition, they are preferably compounds based on short chain perfluoroaliphatics having not more than 5 or 6 carbon atoms such as compounds containing C_4F_9 - groups.

In a preferred embodiment of the present invention, the fluorochemical 20 composition will be free of or substantially free of perfluorinated polyether moieties having a molecular weight of less than 750g/mol and/or perfluoroaliphatic groups of more than 5 or 6 carbons. By the term "perfluoroaliphatic groups" is meant groups consisting of 25 carbon and fluorine without including perfluorinated end groups of the perfluorinated polyether moieties. By the term "substantially free of" is meant that the particular perfluorinated polyether moieties are present in amounts of not more than 10% by weight, preferably not more than 5% by weight and most preferably not more than 1% by weight based on the total weight of perfluorinated polyether moieties in the composition and that the particular perfluoroaliphatic groups having more than 5 or 6 carbons are present in amounts of not more than 10% by weight, preferably not more than 5% by weight and most preferably not more than 1% by weight based on the total weight of 30 perfluoroaliphatic groups in the composition. Compositions that are free of or substantially free of these moieties or groups are preferred because of their beneficial environmental properties.

In order to affect treatment of the fibrous substrate the fibrous substrate is contacted with the fluorochemical composition. For example, the substrate can be immersed in the fluorochemical treating composition. The treated substrate can then be run through a padder/roller to remove excess fluorochemical composition and dried. The 5 treated substrate may be dried at room temperature by leaving it in air or may alternatively or additionally be subjected to a heat treatment, for example, in an oven. This heat treatment is typically carried out at temperatures between about 50°C and about 190°C depending on the particular system or application method used. In general, a temperature of about 120°C to 170°C, in particular of about 150°C to about 170°C for a period of 10 about 20 seconds to 10 minutes, preferably 3 to 5 minutes, is suitable. Alternatively, the chemical composition can be applied by spraying the composition on the fibrous substrate.

It was found that with fluorochemical compositions of this invention, good to excellent oil- and/or water repellent properties on the fibrous substrate can be achieved. Moreover, these properties can be achieved without subjecting the fibrous substrate to a 15 heat treatment, i.e. the properties can be achieved upon air drying the fibrous substrate after the application of the composition. Also, it was observed that the repellency properties are durable, i.e., even after several washing or dry cleaning cycles, the repellency properties can be substantially maintained. The compositions furthermore in many instances do not negatively affect the soft feel of the fibrous substrates or may even 20 improve the soft feel of the fibrous substrate.

The amount of the treating composition applied to the fibrous substrate is chosen so that a sufficiently high level of the desired properties are imparted to the substrate surface preferably without substantially affecting the look and feel of the treated substrate. Such amount is usually such that the resulting amount of the fluoropolymer on the treated 25 fibrous substrate will be between 0.05% and 3% by weight, preferably between 0.2 and 1% by weight based on the weight of the fibrous substrate. The amount which is sufficient to impart desired properties can be determined empirically and can be increased as necessary or desired. According to a particularly preferred embodiment, the treatment is carried out with a composition and under conditions such that the total amount of 30 perfluorinated polyether groups having a molecular weight of less than 750g/mol and/or perfluoroaliphatic groups of more than 6 carbon atoms is not more than 0.1%, preferably not more than 0.05% by weight based on the weight of the fibrous substrate.

Fibrous substrates that can be treated with the fluorochemical composition include in particular textile or carpet. The fibrous substrate may be based on synthetic fibers, e.g. polyester, polyamide and polyacrylate fibers or natural fibers, e.g. cellulose fibers as well as mixtures thereof. The fibrous substrate may be a woven as well as a non-woven
5 substrate.

The invention will now be further illustrated with reference to the following examples without the intention to limit the invention thereto. All parts and percentages are by weight unless stated otherwise.

10 EXAMPLES

Formulation and treatment procedure:

Treatment baths were formulated containing a defined amount of the
fluorochemical polymer. Treatments were applied to the test substrates by padding to
15 provide a concentration as indicated in the examples (based on fabric weight and indicated as SOF (solids on fabric)). Samples were air dried at ambient temperature for 24-48 hours followed by conditioning at 21°C and 50% relative humidity for 2 hours (air cure). Alternatively, the samples were dried and cured at 160°C during 1.5 minutes or at 150°C during 10 minutes, as indicated in the examples.

20 After drying and heat cure, the substrates were tested for their repellency properties.

Substrates used for the evaluation of treatments of this invention were commercially available and are listed below:

- 25 • IND: "Imported Nexday Twill" 100% ring spun cotton, dyed unfinished from Avondale mills in Graniteville SC, USA;
- SHIPP: "Super Hippagator" 100% ring/OE spun cotton, dyed unfinished from Avondale Mills in Graniteville SC, USA;
- PES/CO (2681.4): polyester/cotton 65/35 fabric, style no. 2681.4, available from Utexbel N.V., Ronse, Belgium;
- 30 • PA μ (7819.4): 100% polyamide microfiber, style no. 7819.4, available from Sofinal, Belgium;

- Co (1511.1): 100% cotton : bleached, mercerized cotton poplin, style no. 1511.1, available from Utexbel N.V., Ronse, Belgium; and
- PES μ (6145.3): 100% polyester microfiber, style no. 6145.3, available from Sofinal, Belgium.

5 Respective data of water and oil repellency shown in the Examples and Comparative Examples were based on the following methods of measurement and evaluation criteria:

Spray rating (SR)

10 The spray rating of a treated substrate is a value indicative of the dynamic repellency of the treated substrate to water that impinges on the treated substrate. The repellency was measured by Standard Test Number 22, published in the 1985 Technical Manual and Yearbook of the American Association of Textile Chemists and Colorists (AATCC), and was expressed in terms of ‘spray rating’ of the tested substrate. The spray 15 rating was obtained by spraying 250 ml water on the substrate from a height of 15 cm. The wetting pattern was visually rated : using a 0 to 100 scale, where 0 means complete wetting and 100 means no wetting at all.

Water Repellency Test (WR)

20 The water repellency (WR) of a substrate was measured using a series of water-isopropyl alcohol test liquids and was expressed in terms of the “WR” rating of the treated substrate. The WR rating corresponded to the most penetrating test liquid that did not penetrate or wet the substrate surface after 10 seconds exposure. Substrates which were penetrated by 100% water (0% isopropyl alcohol), the least penetrating test liquid, were 25 given a rating of 0; substrates resistant to 100% water were given a rating W and substrates resistant to 100% isopropyl alcohol (0% water), the most penetrating test liquid, were given a rating of 10. Other intermediate ratings were calculated by dividing the percent isopropylalcohol in the test liquid by 10, e.g., a treated substrate resistant to a 70%/30% isopropyl alcohol/water blend, but not to an 80%/20% blend, would be given a 30 rating of 7.

Oil Repellency (OR)

The oil repellency of a substrate was measured by the American Association of Textile Chemists and Colorists (AATCC) Standard Test Method No. 118-1983, which test was based on the resistance of a treated substrate to penetration by oils of varying surface tensions. Treated substrates resistant only to Nujol® mineral oil (the least penetrating of the test oils) were given a rating of 1, whereas treated substrates resistant to heptane (the most penetrating of the test liquids) were given a rating of 8. Other intermediate values were determined by use of other pure oils or mixtures of oils, as shown in the following table.

10

Standard Test Liquids

AATCC Oil Repellency Rating Number	Compositions
1	Nujol®
2	Nujol® /n-Hexadecane 65/35
3	n-Hexadecane
4	n-Tetradecane
5	n-Dodecane
6	n-Decane
7	n-Octane
8	n-Heptane

Glossary

Descriptor	Structure / Formula	Availability
AIBN	Azobisisobutyronitrile	Sigma-Aldrich, Milwaukee, WI
DBTDL	Dibutyl tin dilaurate	Sigma-Aldrich
DMAEMA	Dimethylamino ethylmethacrylate	Sigma-Aldrich
Ethoquad TM 18/25	Methyl polyoxyethylene(15)octadecyl ammonium chloride	Akzo, Arnhem, Netherlands
FZ-800	condcnsation product of HEMA/IPDI/MEKO (1/1/1)	
HEMA	Hydroxyethyl methacrylate	Sigma-Aldrich
HFE-7100	Perfluorobutyl methyl ether	3M, St Paul, MN
IPDI	Isophorone diisocyanate	Merck KGaA, Germany
MEHQ	Hydroquinone monomethyl ether	
MEK	Methyl ethyl ketone	Sigma-Aldrich
ODMA	Octadecyl methacrylate	Sigma-Aldrich
VCl ₂	Vinylidene Chloride	Sigma-Aldrich
V-59	2,2'-azobis(2-methyl butyronitrile)	Wako

(HFPO)_k-alc: HFPO oligomer alcohols, CF₃CF₂CF₂-O-

5 (CF(CF₃)CF₂O)_nCF(CF₃)CONHCH₂CH₂OH, consisting of a mixture of oligomers
with different chain lengths. The indexes k and n are indicative of the
mathematical average of the number of repeating HFPO-units and k = n+2. The
percentage of oligomeric alcohols with a fluorinated polyether group having a
molecular weight lower than 750 g/mol was 3.2% for (HFPO)_{11.5}-alc and 5.7 % for
10 (HFPO)_{8.8}-alc.

(HFPO)_k-methacrylate:

CF₃CF₂CF₂-O-(CF(CF₃)CF₂O)_nCF(CF₃)CONHCH₂CH₂O₂CC(Me)=CH₂, with k
and n indicative of degree of oligomerization and k = n+2

All parts, ratios, percentages etc. in the following examples are by weight unless otherwise noted.

Synthesis of fluorochemical macromers

5

1. Synthesis of HFPO-oligomer alcohol ((HFPO)_k-alc)

HFPO-oligomer alcohols

$\text{CF}_3\text{CF}_2\text{CF}_2\text{-O-(CF(CF}_3\text{)CF}_2\text{O)}_n\text{CF(CF}_3\text{)CONHCH}_2\text{CH}_2\text{OH}$, indicated as $(\text{HFPO})_k$ -alc, were made according to the procedure for the synthesis of $(\text{HFPO})_{8,8}$ -alc.

10

A 1 liter 3-necked reaction flask was equipped with a stirrer, a condenser, a dropping funnel, a heating mantle and a thermometer. The flask was charged with 1000 g $\text{CF}_3\text{CF}_2\text{CF}_2\text{-O-(CF(CF}_3\text{)CF}_2\text{O)}_{6,8}\text{CF(CF}_3\text{)COOCH}_3$. The mixture was heated to 40°C and 43.4 g ethanolamine was added via the dropping funnel, over a period of 30 minutes. The reaction mixture was kept at 65°C during 3 hours. FTIR analysis indicated complete conversion. The end product could be purified as follows: 500 ml ethyl acetate were added and the organic solution was washed with 200 ml HCl (1N), followed by 2 washings with 200 ml brine. The organic phase was dried over MgSO_4 . Ethyl acetate was evaporated with waterjet vacuum, using a Büchi rotavapor. The product was dried at 50°C during 5 hours, using oil pump vacuum (< 1mbar). An alternative purification step includes evaporation of methanol, formed during reaction, via water jet vacuum, using a Büchi rotavapor (up to 75°C =< 100 mm Hg). Residual methanol was further removed with oil pump vacuum (up to 80°C, =< 10 mbar).

The HFPO-oligomer alcohol $(\text{HFPO})_{8,8}$ -alc obtained, was a yellow coloured oil, with medium viscosity. The structure was confirmed by means of NMR.

15

The HFPO-oligomer alcohol $(\text{HFPO})_{11,5}$ -alc was made following the same procedure.

2. Synthesis of $(\text{HFPO})_k$ -methacrylate

The $(\text{HFPO})_{11,5}$ -methacrylate

$\text{CF}_3\text{CF}_2\text{CF}_2\text{-O-(CF(CF}_3\text{)CF}_2\text{O)}_{9,5}\text{CF(CF}_3\text{)CONHCH}_2\text{CH}_2\text{O}_2\text{CC(Me)=CH}_2$ was made

20

starting from the corresponding $(\text{HFPO})_{11,5}$ -alc

$\text{CF}_3\text{CF}_2\text{CF}_2\text{-O-(CF(CF}_3\text{)CF}_2\text{O)}_{9,5}\text{CF(CF}_3\text{)CONHCH}_2\text{CH}_2\text{OH}$, with M_w 1926.

725.2 g (HFPO)_{11.5}-alc were placed in a 2 liter three-necked round bottom flask, equipped with a condenser, a stirrer, a nitrogen inlet and a temperature control. 64.4 g methacrylic anhydride and 280 ml HFE 7100 were added. The mixture was stirred until the reagents were dissolved. 1 g concentrated sulfuric acid was added. An exothermic reaction was noted. The reaction was stirred at room temperature overnight after the exotherm had subsided. 1000 ml DI water were added. The mixture was shaken. After the emulsion had been allowed to separate overnight, the organic phase was separated and the solvent was removed under reduced pressure. IR analysis and gas chromatography confirmed the formation of the methacrylate ester.

10 (HFPO)_{8.8}-methacrylate was made according to the same procedure and starting from the corresponding (HFPO)_{8.8}-alcohol.

3. Synthesis of (HFPO)_{8.8}-alc/IPDI/HEMA

15 A 250 ml 3-necked reaction flask, equipped with condenser, stirrer, dropping funnel, temperature control and nitrogen inlet was charged with 11.1 gram IPDI. A solution of 75.3 g (HFPO)_{8.8}-alcohol, 23 mg Sn(octanoate)₂, 14 mg phenothiazine and 14 mg MEHQ in 31 g dry acetone was added over 1 hr via dropping funnel, while heating at 55 °C. The reaction was continued at 55°C for 4 hrs, followed by addition of 7.8 g HEMA over 3 hrs via dropping funnel. The reaction was continued overnight to obtain a clear, 20 yellowish 75% solution. Completion of the reaction was confirmed by disappearance of the NCO absorptions in the FT-IR spectrum.

4. Synthesis of fluorochemical macromers (co)polymers FM-1 to FM-4

25 100 ml polymerization bottles were charged with 75% fluorochemical (HFPO)_{8.8}-alc/IPDI/HEMA solution, comonomers and ethylacetate in amounts as indicated in the table, followed by 0.15 g V-59 initiator. The polymerization bottles were degassed using water jet vacuum, purged with nitrogen atmosphere and sealed. For FM-3 and FM-4, VCl₂ was added after degassing and purging with nitrogen. Polymerization was carried out overnight in a Launder-o-meter at 75°C. An additional 0.075 g V-59 was then charged 30 and the reaction continued for 6 hrs. All examples gave semi-viscous polymer solutions.

Polymer	g (HFPO) _{8.8} - alc/IPDI/HE MA	g ODMA	g VCl ₂	g FZ-800 (75% in ethyl acetate)	g ethyl acetate
FM-1	20	/	/	/	17.5
FM-2	13	5.25	/	/	19.3
FM-3	13	3	2.25	/	19.3
FM-4	13	2.6	2.25	0.6	19.3

For emulsification the macromer polymer solutions were heated to 65°C and added to a solution of 0.75 g Ethoquad™ 18/25 in 36.75 g deionized water, whilst stirring. The pre-mixes were subjected to ultra-sound for 2 minutes using a Branson 450 sonifier. Ethyl acetate and acetone were stripped off with a Büchi rotavapor, using waterjet vacuum at 55 °C. Milky dispersions were obtained for all examples.

5. Synthesis of HFPO macromer FM-5

25.0 grams of

10 CF₃CF₂CF₂-O-(CF(CF₃)CF₂O)_{9.5}CF(CF₃)CONHCH₂CH₂O₂CC(Me)=CH₂, 4.4 grams N,N-dimethylaminoethyl methacrylate, 29.4 grams HFE 7100, 0.3 grams AIBN and 0.05 gram tert-dodecyl mercaptane were combined in a 250 ml three-necked round bottom flask. The mixture was purged with nitrogen. The reaction was heated to 65°C under nitrogen and stirred overnight. 1.7 grams acetic acid was added and the reaction was stirred for 15 minutes. A solution of 7.0 grams 30% aqueous Ethoquad™ 18/25 in 89.6 grams DI water was slowly added keeping the temperature >= 60°C. The mixture was emulsified with an ultrasonic homogenizer. HFE 7100 was then removed by distillation under reduced pressure at 50°C.

15

Table 1: composition of fluorochemical macromer polymers

FM	Composition	Ratio
FM-1	Homopolymer of (HFPO) _{8,8} -alc/IPDI/HEMA	
FM-2	[(HFPO) _{8,8} -alc/IPDI/HEMA]/ODMA	1/1
FM-3	[(HFPO) _{8,8} -alc/IPDI/HEMA]/ODMA/VCl ₂	1/1/1
FM-4	[(HFPO) _{8,8} -alc/IPDI/HEMA]/ODMA/PZ-800/VCl ₂	1/1/1/1
FM-5	(HFPO) _{11,5} -methacrylate/DMAEMA:HOAC	1/1

Examples 1 to 4

In examples 1 to 4, different substrates were treated with fluorochemical macromer polymer compositions as indicated in table 2, so as to give 0.3% SOF. After treatment the fabrics were dried at 160 °C during 1.5 minutes. The treated substrates were tested for their oil and water repellency. The results are summarized in table 2.

Table 2: Substrates treated with fluorochemical macromer

Ex No	FM	Initial PES μ			Initial PA μ			Initial PES/Co			Initial Co
		OR	WR	SR	OR	WR	SR	OR	WR	SR	
1	FM-1	2	1	70	3.5	1	50	3.5	1	0	4
2	FM-2	1.5	1	70	4.5	2	60	4	0	0	3
3	FM-3	2	1	70	4	2	50	4	0	0	2.5
4	FM-4	2	1	70	4	1.5	60	3.5	1	50	2.5

The substrates treated with different fluorochemical polyether macromer polymers had especially good oil repellency.

Examples 5 to 7

In examples 5 to 7, cotton substrates were treated with a fluorochemical macromer polymer FM-5, so as to give %SOF as indicated in table 3. After treatment one set of samples was dried at room temperature for 24-48 hours and a second set was cured at

2003239605 17 Dec 2004

150°C for 10 minutes. The treated substrates were tested for their oil and water repellency. The results are summarized in table 3.

Table 3: Substrates treated with FC acrylic polymer

5

Ex	% SOF	Shipp (air dry)		Shipp (cure)		IND (air dry)		IND (cure)	
		OR	SR	OR	SR	OR	SR	OR	SR
5	0.2	4	0	4	0	4	0	4	0
6	0.5	4	50	4	60	4.5	60	4	50
7	1	5	50	5	70	5	50	5	70

Cotton substrates with very good oil repellency were obtained, even after air dry conditions

10 Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", and variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps.

15

The reference to any prior art in this specification is not, and should not be taken as, an acknowledgement or any form of suggestion that that prior art forms part of the common general knowledge in Australia.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A fluorochemical composition comprising a fluorinated polymer dispersed in water or dissolved or dispersed in an organic solvent, said fluorinated polymer comprising units derived from (i) a mixture of two or more fluorinated polyether monomers that differ in at least their molecular weight, said fluorinated polyether monomers having an ethylenically unsaturated group and a perfluorinated polyether group and wherein at least 90% by weight of said mixture consists of fluorinated polyether monomers that have a perfluorinated polyether group having a molecular weight of at least 750g/mol and (ii) one or more units derived from one or more co-monomers other than a fluorinated polyether monomer and wherein said co-monomers comprise at least one non-fluorinated monomer.
2. A fluorochemical composition according to claim 1 wherein said composition is free of perfluoroaliphatic groups of more than 6 carbon atoms other than perfluorinated end groups of a perfluorinated polyether moiety and/or perfluorinated polyether groups having a molecular weight of less than 750g/mol or wherein said composition contains said perfluoroaliphatic groups of more than 6 carbon atoms in an amount of not more than 10% by weight based on the total weight of perfluoroaliphatic groups other than end groups of a perfluorinated polyether moieties and/or contains said perfluorinated polyether groups having a molecular weight of less than 750g/mol in an amount of not more than 10% by weight based on the total weight of perfluorinated polyether moieties in the fluorochemical composition.
3. A fluorochemical composition according to claim 1 wherein the amount of units derived from said mixture of fluorinated polyether monomers is between 5 and 70% by weight based on the weight of said fluorinated polymer.
4. A fluorochemical composition according to claim 1 wherein one or more of said fluorinated polyether monomers correspond to the formula:



wherein PF represents a perfluorinated polyether group, R is hydrogen or alkyl group of 1 to 4 carbon atoms and Q is a divalent linking group selected from the group consisting of:

*-CH₂-L¹, *-COO-L², *-CONR^a-L²,
 wherein L¹ represents a chemical bond or an organic divalent linking group, L² represents
 an organic divalent linking group and R^a is hydrogen or an alkyl group having 1 to 4
 carbon atoms and * indicates the position where the linking group is attached to the group
 5 PF in formula (I).

5. A fluorochemical composition according to claim 4 wherein L¹ is selected from
 the group consisting of an oxy group, an amido group, a carboxy group, a carbonyl group,
 an aryl group that may be substituted and an alkylene group that may be substituted and/or
 10 that may be interrupted with one or more heteroatoms or with an amido group, a carboxy
 group, a urethane group or a carbonyl group and wherein L² is selected from the group
 consisting of an aryl group that may be substituted and an alkylene group that may be
 substituted and/or that may be interrupted with one or more heteroatoms or with an amido
 group, a carboxy group, a urethane group or a carbonyl group.

15

6. A fluorochemical composition according to claim 1 wherein one or more of
 said fluorinated monomers correspond to the formula:



wherein PF represents a perfluorinated polyether group, L³ and L⁴ each independently
 20 represent a non-fluorinated organic divalent linking group, X³ and X⁴ independently
 represent O or NR^a wherein R^a is hydrogen or an alkyl group of 1 to 4 carbon atoms, Z
 represents a residue of a polyisocyanate having a valence p and wherein p is at least 2, and
 R^b represents hydrogen or methyl.

25

7. A fluorochemical composition according to claim 1 wherein at least one of said
 co-monomers is a non-fluorinated monomer that comprises a blocked isocyanate group.

8. A fluorochemical composition according to claim 1 wherein said non-
 fluorinated monomer is selected from the group consisting of chlorine containing
 30 monomers and monomers corresponding to the formula:



wherein Z represents an ethylenically unsaturated group, L represents a chemical bond or

an organic divalent linking group and R_h represents a linear, cyclic or branched organic group selected from a hydrocarbon group, hydrocarbon groups that contain cyclic structures, hydrocarbon groups that are interrupted with one or more heteroatoms and hydrocarbon groups that contain a substituent selected from the group consisting of amino groups, hydroxy groups, carboxy groups and amido groups.

5 9. A fluorochemical composition according to claim 8 wherein said organic divalent linking group is selected from the group consisting of carboxy groups, carbonamido groups and oxy groups.

10

10. A fluorochemical composition according to claim 8 wherein said organic group R_h is selected from linear or branched aliphatic groups having 4 to 30 carbon atoms, hydroxy substituted alkyl groups and amino substituted alkyl groups.


15

11. A fluorochemical composition according to claim 1 wherein said fluorinated polymer is dispersed in water with the aid of a cationic surfactant.

12. A fluorochemical composition according to claim 1 wherein the weight average particle size of the fluorinated polymer particles is between 50nm and 400nm.

20


13. A fluorochemical composition according to claim 1, 4 or 6 wherein said perfluorinated polyether group corresponds to the formula:



wherein R¹_f represents a perfluorinated alkyl group, R²_f represents a perfluorinated polyalkyleneoxy group consisting of perfluorinated alkyleneoxy groups having 1, 2, 3 or 4 carbon atoms or a mixture of such perfluorinated alkylene oxy groups, R³_f represents a perfluorinated alkylene group and q is 0 or 1.

25

14. A fluorochemical composition according to claim 13 wherein R³_f is CF(CF₃)₂, q is 1 and R²_f corresponds to the formula:



2003239605 13 Oct 2008

wherein n is an integer of 3 to 25.

15. A fluorochemical composition according to claim 1 further comprising a non-fluorinated organic compound, wherein the non-fluorinated organic compound is capable of improving relative to the fluorochemical composition without said non-fluorinated organic compound, the oil repellency or water repellency that can be achieved by the fluorochemical composition on a fibrous substrate or the durability of one or both of the repellency properties.

16. A fluorochemical composition according to claim 1 wherein the amount of fluorinated polymer is between 0.1% by weight and 10% by weight.

17. A method of treatment, said method comprising applying to a fibrous substrate a composition as defined in any one of claims 1 to 16.

18. A method according to claim 17 wherein the composition is applied in an amount such that the amount of fluorinated polymer on the fibrous substrate is between 0.2% by weight and 3% by weight relative to the weight of the fibrous substrate.

19. Fluorochemical compositions comprising fluorinated polymers, uses of said compositions and/or fibrous substrates treated with said compositions substantially as described with reference to the Examples.