



(86) Date de dépôt PCT/PCT Filing Date: 1995/02/03

(87) Date publication PCT/PCT Publication Date: 1995/08/10

(45) Date de délivrance/Issue Date: 2002/07/30

(85) Entrée phase nationale/National Entry: 1996/07/11

(86) N° demande PCT/PCT Application No.: CA 1995/000049

(87) N° publication PCT/PCT Publication No.: 1995/021273

(30) Priorité/Priority: 1994/02/04 (191,635) US

(51) Cl.Int.⁶/Int.Cl.⁶ C22B 9/05, C22B 21/06


(72) Inventeurs/Inventors:
WAITE, PETER D., CA;
DUMONT, Robert, CA

(73) Propriétaire/Owner:
ALCAN INTERNATIONAL LIMITED, CA

(74) Agent: KIRBY EADES GALE BAKER

(54) Titre : TRAITEMENT AU GAZ DE METAUX FONDUS

(54) Title: GAS TREATMENT OF MOLTEN METALS



(57) **Abrégé/Abstract:**

A method of and apparatus for treating molten metal to achieve effective removal of such unwanted inclusions as gases, alkali metals, entrained solids, and the like. The method comprises introducing molten metal into a trough, such as the trough provided between a melting furnace and a casting machine, providing at least one mechanically movable gas injector submerged within the metal in the trough and injecting a gas into the metal in a part of the trough forming a treatment zone through the injector(s) to form gas bubbles in the metal while moving the injector(s) mechanically to minimize bubble size and maximize distribution of the gas within the metal. The injectors are preferably rotated and comprise a rotor body having a cylindrical side surface and a bottom surface, at least three openings in the side surface spaced symmetrically around the rotor body, at least one opening in the bottom surface, and at least one internal passageway for gas delivery and an internal structure for interconnecting the openings in the side surface, the openings in the bottom surface and the internal passageway. The internal structure is adapted to cause gas bubbles emanating from the internal passageway to break up into finer bubbles and to cause a metal/gas mixture to issue from the openings in the side surface in a generally horizontal and radial manner.




PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C22B 9/05, 21/06		A1	(11) International Publication Number: WO 95/21273
			(43) International Publication Date: 10 August 1995 (10.08.95)
(21) International Application Number: PCT/CA95/00049		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ).	
(22) International Filing Date: 3 February 1995 (03.02.95)			
(30) Priority Data: 191,635 4 February 1994 (04.02.94) US			
(60) Parent Application or Grant (63) Related by Continuation US 191,635 (CIP) Filed on 4 February 1994 (04.02.94)		Published With international search report.	
(71) Applicant (for all designated States except US): ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street, West, Montreal, Quebec H3A 3G2 (CA).			
(72) Inventors; and (75) Inventors/Applicants (for US only): WAITE, Peter, D. [CA/CA]; 58 de Crespieu, Chicoutimi, Quebec G7H 7M3 (CA). DUMONT, Robert [CA/CA]; 65 rue St. Philippe, Cap De La Madeleine, Quebec G8T 4Y7 (CA).			
(74) Agents: GALE, Edwin, J. et al.; Kirby, Eades, Gale, Baker, Box 3432, Station D, Ottawa, Ontario K1P 6N9 (CA).			

(54) Title: GAS TREATMENT OF MOLTEN METALS



(57) Abstract

A method of and apparatus for treating molten metal to achieve effective removal of such unwanted inclusions as gases, alkali metals, entrained solids, and the like. The method comprises introducing molten metal into a trough, such as the trough provided between a melting furnace and a casting machine, providing at least one mechanically movable gas injector submerged within the metal in the trough and injecting a gas into the metal in a part of the trough forming a treatment zone through the injector(s) to form gas bubbles in the metal. The injectors while moving the injector(s) mechanically to minimize bubble size and maximize distribution of the gas within the metal. The injectors are preferably rotated and comprise a rotor body having a cylindrical side surface and a bottom surface, at least three openings in the side surface spaced symmetrically around the rotor body, at least one opening in the bottom surface, and at least one internal passageway for gas delivery and an internal structure for interconnecting the openings in the side surface, the openings in the bottom surface and the internal passageway. The internal structure is adapted to cause gas bubbles emanating from the internal passageway to break up into finer bubbles and to cause a metal/gas mixture to issue from the openings in the side surface in a generally horizontal and radial manner.

1

TITLE: GAS TREATMENT OF MOLTEN METALS

TECHNICAL FIELD

This invention relates to a method and apparatus for the treatment of molten metals with a gas prior to casting
5 or other processes involving metal cooling and solidification. More particularly, the invention relates to the treatment of molten metals in this way to remove dissolved gases (particularly hydrogen), non-metallic solid inclusions and unwanted metallic impurities prior to
10 cooling and solidification of the metal.

BACKGROUND ART

When many molten metals are used for casting and similar processes they must be subjected to a preliminary treatment to remove unwanted components that may adversely
15 affect the physical or chemical properties of the resulting cast product. For example, molten aluminum and aluminum alloys derived from alumina reduction cells or metal holding furnaces usually contain dissolved hydrogen, solid non-metallic inclusions (e.g. TiB_2 , aluminum/
20 magnesium oxides, aluminum carbides, etc.) and various reactive elements (e.g. alkali and alkaline earth metals). The dissolved hydrogen comes out of solution as the metal cools and forms unwanted porosity in the product. Non-metallic solid inclusions reduce metal cleanliness and the
25 reactive elements and inclusions create unwanted metal characteristics.

These undesirable components are normally removed from molten metals by introducing a gas below the metal surface by means of gas injectors. As the resulting gas
30 bubbles rise through the mass of molten metal, they adsorb gases dissolved in the metal and remove them from the melt. In addition, non-metallic solid particles are swept to the surface by a flotation effect created by the bubbles and can be skimmed off. If the gas used for this
35 purpose is reactive with contained metallic impurities, the elements may be converted to compounds by chemical reaction and removed from the melt in the same way as the contained solids or by liquid-liquid separation.

This process is often referred to as "metal degassing", although it will be appreciated from the above description that it may be used for more than just degassing metals. The process is typically carried out in one of two ways: in the furnace, normally using one or more static gas injection tubes; or in-line, by passing the metal through a box situated in the trough normally provided between a holding furnace and the casting machine so that more effective gas injectors can be used. In the first case, the process is inefficient and time consuming because large gas bubbles are generated, leading to poor gas/metal contact, poor metal stirring and high surface turbulence and splashing. Dross formation and metal loss result from the resulting surface turbulence, and poor metal stirring results in some untreated metal. The second method (as used in various currently available units) is more effective at introducing and using the gas. This is in part because the in-line method operates as a continuous process rather than a batch process.

For in-line treatments to work efficiently, the gas bubbles must be in contact with the melt for a suitable period of time and this is achieved by providing a suitable depth of molten metal above the point of injection of the gas and by providing a means of breaking up the gas into smaller bubbles and dispersing the smaller bubbles more effectively through the volume of the metal, for example by means of rotating dispersers or other mechanical or non-mechanical devices. Residence times in excess of 200 seconds and often in excess of 300 seconds are required in degassers of this type to achieve adequate results. Effectiveness is frequently defined in terms of the hydrogen degassing reaction for aluminum alloys and an adequate reaction is generally considered to be at least 50% hydrogen removal (typically 50 to 60%). This results in the need for deep treatment boxes of large volume (often holding three or more tons of metal) which are unfortunately not self-draining when the metal treatment

process is terminated. This in turn gives rise to operational problems and the generation of waste because metal remains in the treatment boxes when the casting process is stopped for any reason and solidifies in the boxes if not removed or kept molten by heaters. Moreover, if the metals or alloys being treated are changed from time to time, the reservoir of a former metal or alloy in a box (unless it can be tipped and emptied) undesirably affects the composition of the next metal or alloy passed through the box until the reservoir of the former metal is depleted. Various conventional treatment boxes are in use, but these require bulky and expensive equipment to overcome these problems, e.g. by making the box tiltable to remove the metal and/or by providing heaters to keep the metal molten. As a consequence, the conventional equipment is expensive and occupies considerable space in the metal treatment facility. Processes and equipment of this type are described, for example, in U.S. Patents 3,839,019 and 3,849,119 to Bruno et al; U.S. Patents 3,743,263 and 3,870,511 to Szekeley; U.S. Patent 4,426,068 to Gimond et al; and U.S. Patent 4,443,004 to Hicter et al. Modern degassers of this type generally use less than one litre of gas per kilogram (Kg) of metal treated. In spite of extensive development of dispersers to achieve greater mixing efficiency, such equipment remains large, with metal contents of at least 0.4 m³ and frequently 1.5 m³ or more being required. One or more dispersers such as the rotary dispersers previously mentioned may be used, but for effective degassing, at least 0.4 m³ of metal must surround each disperser during operation.

To avoid problems associated with deep treatment boxes, there have been a number of attempts at metal treatment in shallow vessels such as the trough normally provided between a metal holding furnace and a casting machine. This would provide a vessel which could drain completely after use and thus avoid some of the problems associated with the deep box treatment units.

The difficulty is that this would inevitably require a reduction of the metal depth above the point of gas injection while still allowing for effective gas/metal contact times. The use of gas diffusion plates or similar devices in the bottom of such shallow vessels or troughs has been proposed to introduce the gas and create the desired gas/metal contact. These are described, for example, in U.S. Patent 4,290,590 to Montgrain and U.S. Patent 4,714,494 to Eckert. However, bubbles produced in this way still tend to be too large and, given the reduced metal depth, such vessels or troughs necessarily must be made undesirably long to achieve effective degassing, and the volume of gas introduced must be made quite high (typically over 2 litres/Kg). As a result, the apparatus takes up a lot of floor space and the volume of gas introduced creates a risk of chilling the metal so that it may be necessary to provide compensating heaters. Such trough degassers can be drained, but because of large bubble size they still require long residence times to effectively treat metal to the same degree of efficiency as obtained with other in-line methods. In addition, the introduction of large gas bubbles into a shallow metal volume results in excess surface turbulence and splashing. As a result, degassing in shallow troughs is not generally carried out on an industrial scale.

Thus there is a need for a metal treatment method and apparatus that provides effective treatment in short time periods, with correspondingly small volumes of metal, and with low gas consumption. Such processes and equipment would then be able to be carried out in metal delivery troughs with all the advantages of such devices that were noted above, but without the problems of high gas consumption or the space limitations noted.

DISCLOSURE OF INVENTION

An object of the invention is to enable gas treatment of molten metal to be carried out effectively in short time periods and correspondingly small volumes, using

relatively low amounts of treatment gas.

Another object of the invention is to provide a method and apparatus for gas treatment of molten metal that can be carried out in small volumes of metal, and in particular in metal within metal delivery troughs or
5 similar devices.

Another object of the invention is to provide a mechanical gas injection system that operates within a small volume of metal, such as found in a metal delivery
10 trough or similar device to achieve effective gas treatment.

Another object of the invention, at least in its preferred aspects, is to provide a method and apparatus for gas treatment of molten metal that allows the metal to
15 be drained substantially completely from the treatment zone after treatment is complete.

Yet another object of the invention is to provide a method and apparatus for gas treatment of molten metal that avoids the need for metal heaters and bulky
20 equipment.

These and other objects and advantages of the present invention will be apparent from the following disclosure.

It has now surprisingly been found that it is possible to operate gas injectors in such containers, e.g.
25 shallow troughs. In particular, rotary gas injectors that generate a radial and horizontal flow of metal and operate at a rotational velocity sufficient to shear the gas bubbles are effective in such applications.

Thus, according to one aspect of the invention, there
30 is provided a method of treating a molten metal with a treatment gas, comprising: continuously passing the molten metal through a section of a molten metal-conveying trough, said section having a bottom wall and opposed side

B

walls, and exhibiting a static to dynamic metal holdup of less than 50%; providing at least one mechanically movable gas injector within the metal in the section of the trough; and injecting a gas into the metal of the section of the trough via said at least one injector to form gas bubbles in the metal while moving said at least one injector mechanically.

According to another aspect of the invention, there is provided apparatus for treating a molten metal with a treatment gas, comprising: an elongated trough having a bottom wall and opposed side walls for continuously conveying a molten metal, said trough including a section for treating the molten metal with a treatment gas; at least one gas injector in use positioned in said section of said trough submerged in said metal; means for conveying gas to said at least one gas injector for injection into said metal; and means for mechanically moving said at least one gas injector to disperse treatment gas in said metal; wherein said section of said trough has a transverse vertical cross-sectional area centred on said at least one injector and a maximum width at a midpoint of said at least one injector, and wherein the product of said transverse vertical cross-sectional area and said maximum width does not exceed 0.2 m^3 .

According to yet another aspect of the invention, there is provided a device for treating molten metal in a section of an elongated metal-conveying trough having a bottom wall and opposed side walls for continuously conveying a molten metal, and exhibiting a static to dynamic metal holdup of less than 50%, said device comprising: at least one gas injector; means for conveying treatment gas to said at least one gas injector; means for mechanically moving said at least one gas

injector; support means for said at least one gas injector; and means for moving said support means for raising said at least one gas injector out of said section of said trough and lowering said at least one gas injector
5 into said section of said trough.

According to still yet another aspect of the invention, there is provided an injector for injecting gas into a molten metal, comprising: a rotor having a projection-free cylindrical side surface, a projection-free and unbroken upper surface, and a bottom surface; a
10 plurality of openings in said side surface spaced symmetrically around the rotor, said openings occupying an area of said outer surface corresponding to less than 60% of a total area swept by said openings upon rotation of
15 said rotor; at least one opening in the bottom surface; and at least one internal passageway for gas delivery and an internal structure for interconnecting said openings in said side surface, said at least one opening in said bottom surface and said at least one internal passageway;
20 said internal structure in use being at least partially filled with molten metal or metal/gas mixtures, and being adapted to cause gas emanating from said internal passageway to break up into bubbles to form a metal/gas mixture to issue from said openings in said side surface
25 in a generally horizontal and radial manner, said side surfaces causing said gas bubbles to be broken up into finer bubbles upon rotation of said rotor in said molten metal, and wherein said internal structure consists of vanes and channels separating said vanes.

30 It is a surprising and unexpected feature of this invention that it is possible to operate gas injectors in such a way as to disperse gas to generate the required gas holdup and gas-metal surface area within the constraints

of the treatment segment, and further within a trough section. Prior art degasser methods generally do not achieve the high values of gas holdup and gas-metal surface area characteristic of the present invention.

- 5 Furthermore, to maximize performance, prior art methods have relied on shear generation and mixing methods that have produced substantial splashing and turbulence which

has required operation using treatment segments of significantly larger volume than the present invention. They therefore could not achieve the overall objective of effective degassing in short time periods.

5 The present invention makes it possible to treat a molten metal with a gas using a preferably rotary gas injector while providing only a relatively small depth of metal above the point of injection of the gas and consequently permits effective treatment of metals
10 contained in small vessels and, in particular, in metal delivery troughs typically used to deliver metal from a holding furnace to a casting machine. Such metal delivery troughs are generally open ended refractory lined sections and, although they can vary greatly in size, are generally
15 about 15 to 50 cm deep and about 10 to 40 cm wide. They can generally be designed to drain completely when the metal supply is interrupted.

 The invention, at least in its preferred forms, makes it possible to achieve gas treatment efficiencies,
20 as measured by hydrogen removal from aluminum alloys, of at least 50% using less than one litre of treatment gas per Kg of metal, and to achieve reaction times of between 20 and 90 seconds, and often between 20 and 70 seconds.

 In a preferred form of the invention, a metal
25 treatment zone is provided within a metal delivery trough containing one or more generally cylindrical, rapidly rotating gas injection rotors, having at least one opening on the bottom, at least three openings symmetrically placed around the sides, and internal structure such that
30 the bottom openings and side openings are connected by means of passages formed by the internal structure wherein molten metal can freely move; at least one gas injection port communicating with the passageway in the internal structure for injection of treatment gas into metal within
35 the internal structure; wherein the internal structure causes the treatment gas to be broken into bubbles and mixed within the metal within the internal structure, and

further causes the metal-gas mixture to flow from the side openings in a radial and substantially horizontal direction. It is further preferred that each rotor have a substantially uniform, continuous cylindrical side surface except in the positions where side openings are located, and that the top surface be closed and in the form of a continuous flat or frusto-conical upwardly tapered surface; the top surface and side surfaces thereby meeting at an upper shoulder location. It is further preferred that the side openings on the surface sweep an area, when the rotor is rotated, such that the area of the openings in the side surface is no greater than 60% of the swept area.

It is further preferred that the rotors be rotated at a high speed sufficient to shear the gas bubbles in the radial and horizontal streams into finer bubbles, and in particular that the rotational speed be sufficient that the tangential velocity at the surface of the rotors be at least 2 metres/sec at the location of the side openings. Each rotor must be located in specific geometric relationship to the trough, and preferably with the upper shoulder of the rotor located at least 3 cm below the surface of the metal in the trough, and the bottom surface located at least 0.5 cm from the bottom surface of the trough. There is also defined a treatment segment surrounding the rotor with a volume defined by a length along the trough equal to the distance between the trough walls at the metal surface, and a vertical cross-sectional area equal to the vertical cross sectional area of the metal contained within the trough at the midpoint of the rotor. In some configurations, gas injectors, such as rotors, may be located sufficiently close together that the distance between the centres of the injectors is less than the distance between the trough walls at the midpoint of the injector. Therefore, the treatment segment volume may be further defined as the volume defined by the vertical cross-sectional area of the metal contained

within the trough at the midpoint of the gas injector multiplied by the smaller of the distance between the trough walls at the metal surface and the distance between the centres of adjacent gas injectors. The volume of the treatment segment is assumed to include the volume of the immersed portion of the injector itself upon which the volume is defined. The rotor and trough are further related by the requirement that the volume of metal within the treatment segment must not exceed 0.20 m^3 , and most preferably not exceed 0.07 m^3 . The treatment segment volume should, however, preferably be at least 0.01 m^3 for proper operation.

When used to treat aluminum and its alloys, the treatment segment is limited by the equivalent relationship that the amount of aluminum or aluminum alloy contained within the treatment segment must not exceed 470 Kg and most preferably not exceed 165 Kg.

The volume limitations expressed for the treatment segment create a hydrodynamic constraint on the container plus gas injectors of this invention. The container as described above may take any form consistent with such constraints but most often takes the form of a trough section or channel section. Most conveniently this trough section will have the same cross-sectional dimensions as a metallurgical trough used to convey molten metal from the melting furnace to the casting machine, but where conditions warrant, the trough may have different depths or widths than the rest of the metallurgical trough system in use. To ensure that the rotor is also in proper geometric relationship to the trough even when deeper trough sections are used, the trough depth must be limited, and this limitation may be measured by the ratio of static to dynamic metal holdup. The dynamic metal holdup is defined as the amount of metal in the treatment zone when the gas injectors are in operation, while the static metal holdup is defined as the amount of metal that remains in the treatment zone when the source of metal has

been removed and the metal is allowed to drain naturally from the treatment zone. For the desired operation the static to dynamic metal holdup should not exceed 50%. From other considerations, it is also clear that residual metal left in the trough should preferably be minimized to meet all the objectives of the invention, and therefore it is particularly preferred that the static to dynamic metal holdup be approximately zero. Where practical situations require that a non-zero ratio of static to dynamic holdup be used, it is preferred that the ratio not exceed 35%, which permits the residual metal to solidify between casts and permits relatively easy manual removal of the residue. It is most convenient that the trough have opposed sides that are straight and parallel, but other geometries, for example curved side walls, may also be used in opposition to each other.

The treatment segment defines the number of gas injectors required to effectively meet the object of the invention, once the volume flowrate of metal to be treated is known. It is surprising that although the total size of the treatment zone may be substantially less in the present invention than in prior art in-line degassers, the number of gas injectors required may actually be higher in certain circumstances. The treatment segment volume divided by the volume flowrate of metal to be treated should be less than 70 seconds. It is preferably less than 35 seconds to ensure that all the metal volume is close enough to the gas injector to ensure that the effect of gas injection is felt throughout the metal volume during the time the metal is near the injector. Treatment of metal that is flowing at a high flowrate will require a larger treatment volume, within the limits already given, than metal flowing at low flowrates. Flowrates typically fall within the range of about 0.0005 to 0.007 cubic metres per second, but may be higher or lower, if desired.

The gas injectors preferably operate with a high specific gas injection rate so that the number of

injectors required to achieve effective treatment is acceptably low. The specific gas injection rate is defined as the rate of gas injection via a gas injector divided by the treatment segment volume associated with that injector. For proper degassing by the process of this invention, a specific gas injection rate of at least 800, and more preferably at least 1000, litres of gas/minute/cubic metre of metal is preferred. Because the overall metal treatment operates within normal metallurgical requirements (less than 2345 litre gas/m³ of metal treated, equivalent to 1 litre gas/kg of aluminum for example, and more typically between 940 and 1640 litres/m³) such higher specific gas injection rates ensure that degassing can be accomplished generally with 10 injectors or less and frequently with fewer than 8 injectors.

The above embodiment may achieve a gas holdup, measured as the change in volume of the metal-gas mixture within a treatment segment with treatment gas added via the gas injection port at a rate of less than 1 litre/Kg, compared to the volume with no treatment gas flowing, of at least 5% and preferably at least 10%.

It is most preferred that the rotor have an internal structure consisting of vanes or indentations and that the side openings be rectangular in shape, formed by the open spaces between the vanes or indentations, and extending to the bottom of the rotor to be continuous with the bottom openings. The rotor as thus described preferably has a diameter of between 5 cm and 20 cm, preferably between 7.5 cm and 15 cm, and is preferably rotated at a speed of between 500 and 1200 rpm, and more preferably between 500 and 850 rpm.

Although various explanations for this invention are possible, the following is at present believed to describe the complex series of interactions necessary for the invention to meet the objective of efficient metal treatment in short time periods.

Conventional degassers of the deep box type or trough

diffuser type, for example, all require substantially longer reaction times to achieve effective reaction (such as degassing). The key feature of this invention is the means of generating high gas holdup within the metal in the treatment zone by means of using gas injectors providing mechanical motion within a defined volume of metal per injector. Because a high gas holdup is generally believed to be a result of fine bubbles dispersed throughout the metal with little coalescence, this means that the surface area of the gas in contact with the metal in a high gas holdup situation is substantially increased, and therefore, according to normal chemical principles, reaction can occur in shorter times. Gas bubble size cannot be readily measured in molten metal systems. Gas bubble sizes based on water models are not reliable because of surface tension and other differences. It is possible to estimate gas-metal surface area for a particular degassing apparatus, and by applying further assumptions to estimate gas bubble sizes.

The measurement of gas-metal surface areas can be determined from the work of Sigworth and Engh, "Chemical and Kinetic Factors Related to Hydrogen Removal from Aluminum", Metallurgical Transactions B, American Society for Metals and The Metallurgical Society of AIME, Volume 13B, September 1982, pp 447-460. The effect of alloy composition on hydrogen solubility was determined based on the method disclosed in Dupuis, et al., "An analysis of Factors Affecting the Response of Hydrogen Determination Techniques for Aluminum Alloys", Light Metals 1992, The Minerals, Metals & Materials Society of AIME, 1991, pp 1055-1067.

Basically, in order to measure gas-metal surface area, the inlet and outlet hydrogen concentrations of the metal passing through the degasser are measured (for

example using Commercial Units such as Alscan or Telegas (trade marks)) and the metal flow rate, the metal temperature, the alloy composition and the gas flow rate per rotor are noted. The hydrogen solubility in the specific alloy is then calculated as a function of temperature. Sigworth & Engh's hydrogen balance equations for a continuous reactor (equations 35 and 36, page 451, Sigworth & Engh) are solved simultaneously for each rotor of the degasser. Based on the known operating parameters and measured hydrogen removal, the gas metal contact area is obtained from the previous step. Based on this method, the present invention requires operation with a gas-metal surface area of at least $30 \text{ m}^2/\text{m}^3$ of metal within a treatment segment in order to achieve the desired degassing efficiency in short reaction times. Prior art degassers generally operate with gas-metal interfacial surface areas of less than $10 \text{ m}^2/\text{m}^3$.

The total interfacial contact area can then be used to "estimate" the volume average equivalent spherical gas bubble diameter produced by the gas injection rotor based on the following assumptions:

- 1) the gas bubbles are all of the same diameter;
- 2) the gas bubbles are all spherical;
- 3) the gas bubbles rise to the liquid metal surface vertically from the depth of gas injection;
- 4) the gas bubbles ascend through the metal at their terminal rise velocity (calculated using correlations for gas bubbles in water, e.g. according to Szekely, "Fluid Flow Phenomina in Metals Processing", Academic Press, 1979).

Finally, the volume average equivalent spherical gas bubble diameter is calculated from the corresponding area using the equation:

$$A = \frac{3 \cdot Q \cdot h_o}{R \cdot U_t}$$

wherein:

Q = volumetric gas flow rate taking into account thermal expansion

h_o = depth of gas injection

5 U_t = terminal rise velocity of gas bubbles and

R = spherical gas bubble radius.

Based on this method of estimation, gas bubble sizes are 2 to 3 times smaller in the present invention than expected in systems of the deep box type, and there are
10 fewer large bubbles present, thus supporting the explanation of the effectiveness of the present invention.

By associating a gas injector with a defined volume of molten metal (the "treatment segment" volume) it is ensured that the fine gas bubbles generated by the
15 mechanical motion are properly dispersed fully through the treatment zone and therefore the requirement to achieve high gas holdup is met. It should be noted that although the total volumes of metal within a treatment zone of the present invention are substantially reduced over those in
20 a deep box degasser for example because of reduced reaction time requirements, the number of gas injectors may at the same time be increased because of the above requirements of the treatment segment.

Without wishing to be limited to any particular
25 theory, the following is one explanation of the operation of this invention. The gas injectors within each treatment segment balance a number of requirements. The injectors generate a sufficient metal flow momentum in the streams of gas-containing metal to carry the metal and gas
30 throughout the treatment segment but without impinging on container sides or bottom in such a way as to cause bubbles to coalesce or metal to splash. Bubble coalescence at the sides or bottom of the container will be manifested by a non-uniformity of the distribution of
35 bubbles breaking the surface of the metal in the treatment segment, and such coalescence indicates that the average

bubble size has been increased and will therefore, according to the above explanation, result in reduced gas holdup and poorer performance.

In the preferred embodiment of rotary gas injectors operating within a trough and where the rotary gas injectors have side openings, bottom opening and internal structure, the flow momentum is generated in a radial direction to achieve the distribution of gas bubbles required above and this momentum is created by the rotational motion of the injector. The rotary gas injector further operates to generate the fine bubbles of high gas-metal surface area characteristic of one aspect of the invention by generating a surface tangential velocity which in turn depends on the diameter of the rotary injector. It can be appreciated therefore that although rotors can be devised to operate over a wide range of rotational speeds, the optimum performance of a rotary gas injector of this invention within the constraints of its relationship to the trough will result in a relatively narrow range of rotational speeds within which it can operate at maximum effectiveness. The user will adjust the rotational speed to achieve the desired operational results.

While a rapidly rotating gas injector represents a preferred embodiment of the invention, such injectors can generate substantial deep vortices (extending down to the rotor itself) in the metal surface when operated in small volumes of metal. This undesirable effect can be reduced by ensuring that all external surfaces of the rotor are as smooth as possible, with no projections, etc., that might increase drag and form a vortex. However, such smooth surfaces are generally poorer at creating the shear necessary to generate fine gas bubbles, and it is only by balancing the geometry of the rotor with the operating speed and the trough configuration that sufficient shear and metal circulation, with no vortex formation, can be achieved. It has further been found that the bubble

dispersing and turbulence and deep vortex reducing features of rotary gas dispersers of this invention are improved by the presence of a directed metal flow within the metal surrounding the rotary gas injectors. Such a
5 directed metal flow is obtained, for example, when the metal flows along a trough, such as a metal delivery trough as described in this disclosure.

Directed metal flows of this type have surprisingly also been found to reduce any residual vortex formation in
10 spite of the relatively low metal velocity compared to the tangential velocity of the rotary gas injector. The presence of flow directing means within the trough which direct the principal flow counter to the direction of the tangential velocity component in the metal introduced by
15 the rotary gas injector are particularly useful.

The presence of directed metal flow changes the momentum vector of the radial metal flow to an extent that the flow direction overall is more longitudinal and the problems associated with impingement on an adjacent trough
20 wall are substantially reduced. The magnitude of the directed metal flow clearly impacts on this effect.

In deep box treatment vessels using rotary gas dispersers, the preceding considerations are not important, and it is indeed felt beneficial to ensure that
25 the radial flow is as high and turbulent as possible, and has a substantial upward or downward component to create large scale stirring within the volume of metal surrounding each gas injector.

It is most preferable and metallurgically
30 advantageous in the present invention to carry out the gas treatment in a treatment zone consisting of one or more stages operated in series. This can be done in a modular fashion and it is possible, where space limitations or other considerations are important, to separate these
35 stages along a metal-carrying trough, provided the total number of stages remain the same as would be used in a more compact configuration. It is also preferred that

each stage consist of a gas injector as described above and be delimited from neighbouring stages. Each stage consists of a gas injection rotor as described above and is delimited from neighbouring stages by baffles or other
5 devices designed to minimize the risk of backflow, or bypassing of metal between stages, and to minimize the risk of disturbances in one stage being carried over to adjacent stages.

The baffles can also incorporate the flow directing
10 means described above which counter the tangential velocity component.

It should be understood that the treatment stage refers to the general part of the apparatus adjacent to a gas injector, and may be defined by baffles if they are
15 present. The treatment segment, on the other hand is a portion of the container defined in the specific hydrodynamic terms required for the proper operation of the invention. It may be the same as the treatment stage in some cases.

20 The provision of plurality of treatment stages is (based on chemical principles) a more effective method for diffusion controlled reactions and removal of non-metallic solid particles for metal treatment. The plurality of rotary gas injectors within a directed metal flow as is
25 created by the trough section operates (in chemical engineering terms) as a pseudo-plug flow reactor rather than a well-mixed reactor which is characteristic of deep box degassers.

It has been found that the effectiveness of the gas
30 bubble shearing action, and hence the effectiveness at obtaining high gas holdup required to meet the object of the invention, increases as the power input intensity to the rotors in the treatment zone increases. When measured as the average power input per unit mass of metal
35 contained within a treatment segment, and assuming that the net power available is typically 80% of installed (motor) power, typical treatment systems based on rotors

operate in the range of power input densities of 1 to 2 watts/Kg of metal. The present invention is capable of operation at power input intensities in excess of 2 watts/Kg, and most frequently in excess of 4 watts/Kg, thus ensuring the smaller more stable bubble size required for effective treatment in small quantities of metal.

It should be appreciated that within the operating ranges of number, size and specific design of rotors, rotational speeds, positions relative to the trough and metal surface, metal flowrates and trough sizes and shapes there will be combinations within these ranges which give the desired treatment efficiency in the short times required.

As a result of this the apparatus is also compact and can be operated without the need for heaters and complex ancillary equipment such as hydraulic systems for raising and lowering vessels containing quantities of molten metal. As a result, the equipment normally occupies little space and is usually relatively inexpensive to manufacture and operate.

The requirements of fine bubbles, good bubble dispersion, and avoidance of deep metal vortices can be enhanced in certain instances by the use of fixed vanes located adjacent to the smooth faced rotor and substantially perpendicular to it. The fixed vanes serve to increase the shear in the vicinity of the rotor face, and also ensure that metal is directed radially away from the rotor face thus improving bubble dispersion capability (and avoiding bubble coalescence). The fixed vanes also totally eliminate any tendency for deep metal vortex formation. The rotor/fixed vane radial distance or gap is typically 1 to 25 mm (preferably 4 to 25 mm). When vanes are employed, generally at least two fixed vanes are required per rotor, and more preferably 4 to 12 are used. When fixed vanes are used, the requirements for fine bubbles and good dispersion conditions can be met at lower rotor speeds and in essentially non-moving metal. Thus

the rotor plus fixed vane operation is effective at rotational speeds as low as 300 rpm and metal flows as low as zero Kg/min.

The lower operating speeds and the effective
5 suppression of deep metal vortices permits a wider variety of rotor designs to be used without the generation of performance limiting surface disturbances.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a side elevation of a first embodiment of
10 the rotor of this invention;

Figure 2 is an underside plan view of the rotor of Figure 1;

Figure 3 is a side elevation of another embodiment of the rotor of this invention;

15 Figure 4 is a representation view of a treatment zone consisting of a series of treatment stages containing a series of rotors and baffles;

Figure 5 is a longitudinal cross-sectional view on an arrangement as shown in Figure 4 in slightly modified
20 form;

Figure 6 is a further longitudinal cross-sectional view of an arrangement as shown in Figure 4 in slightly modified form;

Figure 7 is an underside plan view of a rotor
25 operating with fixed vanes surrounding it;

Figure 8 is a side elevation of the rotor and vanes on Figure 7 showing the assembly located in a metal delivery trough;

Figure 9 is a side elevation of another embodiment of
30 a rotor that is suitable for use with fixed vanes (not shown); and

Figure 10 is an underside plan view of the rotor of Figure 9;

Figures 11(a) and 11(b) are, respectively, a side
35 elevational view of an alternative rotor according to the invention and a plan view of the rotor positioned in a metal trough showing how certain dimensions are

calculated;

Figures 12(a), 12(b), 12(c) and 12(d) are, respectively, a side elevation of an alternative rotor according to the invention, cross-sectional plan views
5 taken on lines B and C respectively of Fig. 12(a), and underneath plan view of the rotor;

Figure 13 is a cross-section of a trough containing a rotor shown in side elevation showing how various dimensions are defined;

10 Figure 14 is a side elevation of a further embodiment of a rotor according to the invention;

Figure 15 is a cross section of a trough as used in this invention with the key dimensions labelled;

Figure 16 shows side elevations and plan views of
15 five rotary injectors as used in this invention with key dimensions labelled; and

Figure 17 is a plot showing the useful and preferred operating ranges for the rotary gas injectors of Figure 16.

20 BEST MODES FOR CARRYING OUT THE INVENTION

Figures 1 and 2 show a first embodiment of a rotary gas injector of this invention in a metal delivery trough. The injector has a smooth faced rotor body 10 submerged in a shallow trough, formed by opposed side walls (not
25 visible) and a bottom wall 31, filled with molten metal 11 having an upper surface 13.

The rotor 10 is in the form of an upright cylinder 14 having a smooth outer face, mounted on a rotatable vertical shaft 16 of smaller diameter, with the cylinder
30 portion having an arrangement of vanes extending downwardly from a lower surface 20, and the outer faces of the vanes forming continuous smooth downward extensions of the surface of cylinder 14. As can be seen most clearly from Figure 2, the rotor vanes 18 are generally triangular
35 in horizontal cross-section and extend radially inwardly from the outer surface. The vanes are arranged symmetrically around the periphery of the lower surface 20

in such a way as to define evenly spaced, diametrically-extending channels 22 between the vanes, which channels intersect to form a central space 28. An elongated axial bore 24 extends along the shaft 16, through the upright
5 cylinder 14 and communicates with an opening 26 at the central portion of the surface 20 within the central space 28. This axial bore 24 is used to convey a treatment gas from a suitable source (not shown) to the opening or injection point 26 for injection into the molten metal.

10 The rotor 10 is immersed in the molten metal in the metal delivery trough to such a depth that at least the channels 22 are positioned beneath the metal surface and normally such that the cylindrical body is fully immersed, as shown. The rotor is then rotated about its shaft 16 at
15 a suitably high speed to achieve the following effects. First of all, the rotation of the rotor causes molten metal to be drawn into the central space 28 between the rotor vanes 18 from below and then causes the metal to be ejected horizontally outwardly at high speed through the
20 channels 22 in the direction of the arrows (Figs. 1 and 2), thus forming generally radially moving streams. The speed of these radially moving streams depends on the number and shape of the vanes, the spacing between the vanes, the diameter of the cylinder and the rotational
25 speed of the rotor. The treatment gas is injected into the molten metal through the opening 26 and is conveyed along the channels 22 in a co-current direction with the moving molten metal in the form of relatively large, but substantially discrete gas bubbles.

30 The surface 20 between the vanes at their upper ends closes the channels 22 at the top and constrains the gas bubbles and molten metal streams to move generally horizontally along the channels before the bubbles can move upwardly through the molten metal as a result of
35 their buoyancy. Typically 4 to 8 vanes 18 are provided, and there are normally at least 3, but any number capable of producing the desired effect may be employed.

The rapidly rotating cylindrical rotor creates a high tangential velocity at the outer surface of the cylinder. Because the outer surface of the cylinder is smooth and surface disturbances from the inwardly directed vanes are minimized, the tangential velocity is rapidly dissipated in the body of the metal in the metal delivery trough. Consequently a high tangential velocity gradient is created near the outer smooth surface of the rotor. The rapidly moving streams of molten metal and gas exit the channels 22 at the sides of the rotor 10 and encounter the region of high tangential velocity gradient. The resulting shearing forces break up the gas bubbles into finer gas bubbles which can then be dispersed into the molten metal 11 in the trough. The shearing forces and hence the bubble size depend on the diameter of the rotor and the rotational speed of the rotor. Because there are no projections on the smooth surface of the rotor, and the outer ends of the vanes present a relatively smooth aspect, the tangential velocity is rapidly dissipated without creating a deep metal vortex within the molten metal. A small vortex (not shown) associated with the rotation of the shaft 16 will of course still be present but does not cause any operational difficulties.

To facilitate the treatment of molten metal contained in shallow troughs or vessels such as metal delivery troughs, the rotor is preferably designed to inject the gas into the molten metal at a position as close to the bottom of the trough as possible. Consequently the rotor vanes 18 may be made as short as possible while still achieving the desired effect and the rotor is normally positioned as close to the bottom of the trough as possible, e.g. within about 0.5 cm. However in some troughs of non-rectangular cross-section, the trough walls at the bottom of the trough lie sufficiently close to the rotor that the radial metal flow generated by the rotor impinges on the wall and causes excessive splashing. In such cases an intermediate location for gas injection more

widely separated from the bottom of the trough will be preferable.

The apparatus makes it possible to disperse small gas bubbles thoroughly and evenly throughout a molten metal held in a relatively shallow trough despite the use of a high speed rotation rotor since vortexing and surface splashing is effectively prevented. By correct combination of the diameter, number and dimensions of vanes and rotational speed, the dispersion of small gas bubbles is achieved without generating excessive outward metal flow that causes splashing when it reaches the sides of the metal delivery trough adjacent the rotor.

Figure 3 shows a second preferred embodiment of the rotary gas injector of the invention. This injector represents a rotor having the same underneath plan view as the preceding rotor as illustrated in Figure 2. However, the rotor 10 is in the form of a smooth surfaced upright truncated cone 17, mounted on a rotatable shaft 16 of smaller or equal diameter to the diameter of the upper surface of the cone, with the conical portion having an arrangement of vanes 18 extending downwardly from the lower surface 20, where the outer faces of the vanes form continuous smooth surfaces projecting downwardly from the intersection of the surface of the cone 17 with the vanes 18. By reducing the surface area of the surface of the cylinder 14 as described in Figure 1 to the minimum required, the tendency to form a vortex is reduced over the embodiment of Figure 1, and hence permits operations over a wider selection of conditions within the disclosed ranges.

Figure 4 shows a treatment zone consisting of four treatment stages, where each stage incorporates a rotor 10, and each stage is separated from the next and from the adjacent metal delivery trough by baffles 34 which extend laterally across the trough section containing the treatment zone from sidewall 30 to sidewall except for a gap 36. The metal flows through the treatment zone in the

pattern of flow shown by the arrows 37. The gaps 36 permit the metal to flow freely along the trough in a directed manner, but the baffles 34 prevent metal currents and disturbances from one treatment stage affecting the metal flow patterns in an adjacent treatment stage. Overall, a "plug flow" or "quasi-plug flow" is achieved, i.e. the overall movement of the metal is in one direction only along the trough, without backflow or bypassing of treatment stages, although highly localized reversed or eddy currents may be produced in the individual treatment stages.

The gaps 36 in adjacent baffles are arranged on opposite sides of the trough so that the principal molten metal flow is directed first into the regions 39 of the trough, and thence around the rotor into the regions 40 in such a way that overall the metal flows in an alternating pattern through the stages for maximum gas dispersion throughout the molten metal. The rotors rotate in the directions shown by the arrows 38, i.e. essentially counter to the direction of metal flow in regions 39 and 40 as established by the gaps 39 and thereby reduce further any tendency to form a deep vortex around the rapidly rotating rotors 10.

The illustrated equipment has good flow-through properties and low dynamic metal hold-up. The equipment thus creates only small metallostatic head loss over the length of the treatment zone, depending upon the size of the gaps 36 in the baffles 34.

Figures 5 and 6 show arrangements similar to Figure 4, except that the gaps in the baffles are arranged alternately top to bottom in the embodiment of Figure 5 and bottom to bottom in the embodiment of Figure 6. These arrangements are also suitable to effect thorough gas dispersion through the molten metal.

Figures 7 and 8 show an alternative embodiment where the rotor 10 has an adjacent set of evenly-spaced radially oriented stationary vertical vanes 12 surrounding the

rotor symmetrically about the centre of the rotor and separated from each other by radial channels 15. As will be seen from Fig. 8, the lower surfaces of the rotor vanes 18 and of the stationary vanes 12 may be shaped to follow the contours of a non-rectangular trough 31, if necessary. In this embodiment, the tangential velocity generated at the surface of the rotor 10 is substantially stopped by the adjacent stationary vanes and the resulting shearing force acting on the metal is enhanced. As the gas-containing molten metal streams emerging from the channels 22 encounter the stationary vanes, the high shear is particularly effective at creating the fine gas bubbles required for degassing and permits the effect to be achieved at lower rotational speeds of the rotor. Furthermore, the stationary vanes act to channel the molten metal streams emerging from the channels 22 further along the channels 15 to enhance the radial movement of the metal and ensure complete dispersion of the gas bubbles within the metal in the treatment zone. Finally the presence of stationary vanes completely eliminates any tendency to deep metal vortex formation, even in very shallow metal troughs, as well as low flowrates or directed metal flow that is co-current rather than counter to the direction of rotation of the rotors. The use of stationary vanes also reduces the constraints on surface smoothness of the rotor.

For effective operation with the rotors of this invention, there should preferably be at least 4 stationary vanes per rotor and preferably more than 6. The distance between the rotor and the stationary vanes is preferably less than 25 mm and usually about 6 mm, and the smaller the distance the better, provided the rotor and vanes do not touch and thus damage each other.

Any of the embodiments which use stationary vanes may if desired also used in troughs containing baffles as described in Figures 4, 5 or 6.

Figures 9 and 10 show a further embodiment of rotor

that is intended for use with stationary vanes of the type shown in Figure 7 and 8. Figures 9 and 10 show a rotor unit 10 in which two diametrical rotor vanes 18 intersect each other at the centre of the lower surface 20 of the cylinder 14. The axial gas passage extends through the intersecting portion of the vanes to the bottom of the rotor where the gas injection takes place through opening 26. This type of design in which the central area of the lower surface 20 is "closed" and where gas is injected below the upper edge of rotor vane opening 20 is less effective at radial "pumping" of the molten metal than the basic designs of Figures 1 and 2, but the manner of operation is basically the same. It falls outside the preferred open surface area requirement and gas injection point requirement for this invention, but nevertheless may be used with the stationary vanes as previously described since it has been noted above that the vanes permit a wider variety of rotors to be used.

Figures 11(a) and 11(b) show various dimensions required to determine the amount of gas holdup created by a rotor. A rotor 10 and portion of a shaft 16a are determined to have a volume V_g where the volume includes the volume of any channels 22 within the cylindrical surface 14. The central axis of the rotor is located at distances 53a and 53b from the sides 52a and 52b of the trough containing the rotor. A portion of the trough is described by vertical planes 56 lying equidistant upstream and downstream from the axis of the rotor, at a distance 55 is one-half the distance 53 where the distance 55 is the maximum of 53a and 53b. The volume of metal lying between the walls 52a and 52b, the bottom of the trough 51, the upper metal surface 50 and the two vertical planes 56 is referred to as V_m . The change 57 in V_m resulting from injection of gas into the metal via the rotor is referred to as the gas holdup.

Figures 12(a), 12(b), 12(c) and 12(d) represent, respectively, an elevational view, two sectional plan

views, and an underneath plan view of another embodiment of the rotor of this invention. The embodiment is similar to the embodiment of Figure 1 except that the cylindrical body 14 has a lower extending piece 14c in the form of a
5 cylindrical upward-facing cup with an outer surface exactly matching in diameter and curvature the surface of the downward facing vanes 18. The cup has a central opening 19 in the bottom surface. By varying the diameter of the opening 19, the effectiveness of metal pumping can
10 be controlled, thus allowing the radial and horizontal flow to be controlled without altering the tangential velocity of the cylindrical surface required to shear the gas bubbles.

Figure 13 describes the dimensional constraints as
15 disclosed in this specification. Distance 60 is the immersion of the upper edge of the side of the rotor below the metal surface and is preferably at least 3 cm. Distance 62 is the distance from the bottom of the rotor, measured from the centre of the rotor to the vertically
20 adjacent bottom of the trough and is at least 0.5 cm.

Figure 14 shows the method of determining the open area of the openings in the side of the rotor. The openings 70 in the side of the rotor 14 on rotation describe a cylindrical surface lying between lines 71 and
25 72. If the area of this cylindrical surface is referred to as A_c , then the opening area ratio is defined as A_o/A_c and should preferably not exceed 60%.

As noted above, a particular advantage of the apparatus of the present invention is that it can be used
30 in shallow troughs such as metal-delivery troughs and this can frequently be done without deepening or widening such troughs. In fact while the baffles 34 and the stationary vanes 12 (when required) may be fixed to the interior of the trough if desired, the assemblies of rotors, baffles
35 and (if used) stationary vanes may alternately all be mounted on an elevating device capable of lowering the components into the trough or raising them out of the

metal for maintenance (either of the treatment apparatus or the trough e.g. post-casting trough preparing or cleaning).

The trough lengths occupied by units of this kind are also quite short since utilization of gas is efficient because of the small bubble size and the thorough dispersion of the gas throughout the molten metal. The total volume of gas introduced is relatively small per unit volume of molten metal treated and so there is little cooling of the metal during treatment. There is therefore no need for the use of heaters associated with the treatment apparatus. A typical trough section required for a treatment zone with only one rotor would have a length to width ratio of from 1.0 to 2.0. Although a treatment zone containing a single rotor is possible, generally the treatment zone is divided into more than one treatment stages containing one rotor per treatment stage meeting the treatment segment volume limitations given above. The method and apparatus for metal treatment in a treatment zone can thereby be made modular so that more or less treatment stages and rotors can be used as required. Moreover the treatment stages which comprise the treatment zone need not be located adjacent to each other in a metal delivery trough if the design of the trough does not permit this. The usual number of rotors in a treatment zone is at least two and often as many as six or eight.

As indicated above, the metal treatment apparatus may be used for removing dissolved hydrogen, removing solid contaminants and removing alkali and alkaline earth components by reaction. Many metals may be treated, although the invention is particularly suited for the treatment of aluminum and its alloys and magnesium. The treatment gas may be a gas substantially inert to molten aluminum, its alloys and magnesium, such as argon, helium or nitrogen, or a reactive gas such as chlorine, or a mixture of inert and reactive gases. If chlorine is used for the treatment of magnesium-containing alloys, a liquid

reaction product is formed which under the high shear generated in this treatment may be broken into an emulsion of very small droplets (typically 10 μm in diameter) which are easily entrained with the liquid metal downstream of the in-line treatment unit. This is undesirable due to the negative impact these inclusions have on specific aspects of the cast metal quality. The preferred reactive gas for this application is a mixture of chlorine and a fluoride-containing gas (e.g. SF_6) as described in U.S. Patent 5,145,514 to Gariepy et al (the disclosure of which is incorporated herein by reference), which chemically converts the liquid inclusions into solid chlorides and fluorides which are more easily removed from the metal and are less chemically reactive than simple chloride inclusions and therefore have less impact on cast metal quality.

EXAMPLE 1

Molten metal treatment was carried out in a treatment zone as described in Figures 1 through 3, except that a total of six rotary gas injectors was used and all rotary gas injectors rotated in the same direction. Each rotary gas injector was as described in Figures 1 and 2 with the following specific features. The outer diameter of each rotor was 0.1 m. Eight rotary vanes were used. The outer face of the rotor had openings which covered 39.8% of the corresponding area swept by these openings when the rotor was rotated. The vanes were in the form of truncated triangles, with the outer faces having the same contour as the outer face of the overall rotor and the inner ends terminating on a circle of diameter 0.0413 m. The vanes were spaced to provide passages of constant rectangular cross-section for channelling metal and gas bubbles. The rotors were operated at 800 rpm.

The treatment zone was contained within a section of refractory trough between a casting furnace and a casting machine and had a cross-sectional area of approximately 0.06 m^2 and a length of approximately 1.7 metres. The

metal depth in the treatment zone varied from 0.24 metres at the start of the treatment zone to 0.22 metres at the end of the treatment zone. The rotors were immersed so that the point of injection of the gas into the metal stream was approximately 0.18 metres below the surface of the metal. The metal volume contained in each treatment segment, defined as the length of trough equal to the width at the surface of the metal times the vertical cross-sectional area, was approximately 0.021 m³ for each of the rotary gas injectors.

The treatment zone was fed with metal at a rate of 416 Kg/min. A mixture of Ar and Cl₂ was used in the treatment, fed at a rate of 55 litres/min per rotary gas injector, corresponding to an average gas consumption of 0.8 litres/Kg.

Although all rotary gas injectors operated without the formation of deep metal vortices, it was noted that the normal vortices present as a result of the rotation of the shafts was reduced for those injectors where the metal flow was principally directed counter to the direction of the rotation.

When an aluminum-magnesium alloy (AA5182) was treated in the treatment zone as described, a hydrogen removal efficiency of between 55 and 58% was obtained, which compares favourably with prior art degassers used under the same conditions. The treatment time (average metal residence time in the treatment zone) was 34 seconds. A conventional deep box degasser operating under similar conditions required 350 seconds treatment time, and used approximately 0.5 m³ of metal for each of the two rotors in the degasser.

EXAMPLE 2

Metal treatment was carried out in aluminum alloy AA3004 in a trough as illustrated in Figure 15. The dimensions of the trough are given in Table 1. The treatment process was carried out using five different rotary gas injectors as shown in Figure 16, with the critical rotor parameters given in Table 2. The metal depth in the trough was 8.76 inches (222 mm), and the aluminum alloy flowrate was 450 kg/min. The performance of the metal treatment apparatus was determined in terms of its ability to effectively disperse gas throughout the treatment zone without excessive splashing. Excessive splashing not only creates unsafe operation, but contributes to excessive dross formation. The rotors were tested at three immersion depths and over a range of rotational speeds. No attempt was made to acquire data at rotational speeds above 850 rpm. Figure 17 shows the operational ranges determined for each rotor type at different immersion levels. Rotors 1, 4 and 5 all represent rotors of the particularly preferred embodiment of this invention. Rotor 2 does not have the "smooth top" of the preferred embodiment, and rotor 3 has an area ratio which exceeds the preferred value of 60%. The figure indicate that while all rotors can operate within the present invention, the preferred rotors (1, 4 and 5) provide the widest operating windows within the operating ranges of the degasser.

TABLE 1

Dimensions of Trough (Figure 15)

	Top opening (80)	339 mm (13.4 inches)
	Depth (81)	381 mm (15.0 inches)
5	Bottom curvature (82)	152.4 mm (6.0 inches) radius

The bottom of the trough is in the shape of a full semi-circle.

TABLE 2

Rotor parameters (Figure 16)

10	<u>Dimension</u>	<u>Rotor Type (see Figure 16)</u>				
		1	2	3	4	5
	Overall height (90)	5.0" 127mm	5.0" 127mm	5.0" 127mm	3.0" 76mm	5.0" 127mm
15	Shoulder height (91)	1.5" 38mm	1.5" 38mm	1.5" 38mm	1.5" 38mm	1.5" 38mm
	Vane height (92)	2.0" 51mm	2.0" 51mm	2.0" 51mm	1.5" 38mm	1.5" 38mm
	Overall diameter (93)	4.0" 102mm	4.0" 102mm	4.0" 102mm	4.0" 102mm	4.0" 102mm
20	Shoulder diameter (94)	4.0" 102mm	3.0" 76mm	4.0" 102mm	4.0" 102mm	4.0" 102mm
	Open area of vanes	39.8%	39.8%	70.0%	39.8%	39.8%

CLAIMS:

1. A method of treating a molten metal with a treatment gas, comprising:

continuously passing the molten metal through a section of a molten metal-conveying trough, said section having a bottom wall and opposed side walls, and exhibiting a static to dynamic metal holdup of less than 50%;

providing at least one mechanically movable gas injector within the metal in the section of the trough; and

injecting a gas into the metal of the section of the trough via said at least one injector to form gas bubbles in the metal while moving said at least one injector mechanically.

2. A method according to claim 1, wherein said section of said trough is such that a treatment segment having a volume of less than 0.2 m^3 is formed around said at least one gas injector, and wherein said at least one gas injector is moved mechanically to such an extent that said bubbles from said at least one injector penetrate said treatment segment, said treatment segment being a volume of said metal centered on said at least one gas injector and defined by a product of a transverse vertical cross-sectional area of said trough section at a midpoint of said at least one gas injector, multiplied by a maximum width of said trough section at or below a surface of said metal at said midpoint of said injector.

3. A method according to claim 2 carried out in a trough section such that said treatment segment has a volume of 0.07 m^3 or less.

4. A method according to claim 2 wherein said at least one gas injector is operated to increase the volume of metal in each treatment segment by at least 5% due to introduction of the treatment gas compared to a condition in which the injectors are operated without gas introduction.

5. A method according to claim 2, wherein said at least one gas injector is moved mechanically such that an integrated gas metal surface area in each treatment segment is at least 30 m^2 per m^3 of metal.

6. A method according to claim 2, wherein said metal is aluminum or an aluminum alloy and said treatment segment contains 470 Kg or less of said metal.

7. A method according to claim 3, wherein said metal is aluminum or an aluminum alloy and said treatment segment contains 165 Kg of said metal.

8. A method according to claim 6, wherein gas is injected via said at least one gas injector in an amount of one liter or less of said gas for each kilogram of said metal in said treatment segment.

9. A method according to claim 1, wherein said at least one gas injector is mechanically moved by being rotated about a central vertical axis of said injector.

10. A method according to claim 9, wherein said at least one gas injector is rotated at a rotational speed to achieve a tangential velocity of at least 2 m/sec at a periphery of the injector.

11. A method according to any one of claims 1 to 10, wherein said metal is moved longitudinally through said section of said trough past said at least one gas injector as said gas is injected into said metal.

12. A method according to claim 11, wherein said metal is moved through said section of said trough at such a rate of flow that metal passes through said section of said trough in a time period of 90 seconds or less.

13. A method according to claim 9, wherein said metal is moved through said section of said trough in a pattern of flow that directs a stream of metal towards a rotating surface of said at least one gas injector in a direction countercurrent to the direction of rotation of said surface.

14. A method according to claim 2, wherein more than one said gas injector is employed, and wherein disturbances in said metal present in a treatment segment associated with one gas injector are prevented from affecting metal present in a treatment segment associated with an adjacent gas injector.

15. A method according to claim 9, wherein said at least one gas injector has a generally cylindrical rotor body having an internal structure that creates radial and horizontal metal flows as the rotor body is rotated in the metal, and that includes means for injecting gas into the metal such that it becomes dispersed as bubbles in

said radial and horizontal metal flows, and wherein said rotor body is rotated at a speed such that said gas bubbles within said radial and horizontal metal flows encounter a tangential shear gradient in said molten metal as said flows exit said rotor body effective to break up said bubbles into finer bubbles, and such that said radial and horizontal metal flows have sufficient momentum to disperse said metal flows and finer gas bubbles throughout said section of the trough, whereby bubbles breaking said metal at an upper surface of said metal are uniformly distributed without concentrations of bubbles at said gas injector or said walls of said container.

16. A method according to claim 15, wherein said rotor body has a diameter of 5 to 20 cm and is rotated at 500 to 1200 rpm.

17. A method according to claim 15 or claim 16, operated with said at least one injector in which said rotor body has a cylindrical side surface and a bottom surface, at least three openings in said side surface spaced symmetrically around the rotor body, at least one opening in the bottom surface, at least one internal passageway for gas delivery and an internal structure for interconnecting said openings in said side surface, said openings in said bottom surface and said at least one internal passageway, said internal structure being adapted to cause gas bubbles emanating from said internal passageway to break up into finer bubbles and to cause a metal/gas mixture to issue from said openings in said side surface in a generally horizontal and radial manner as said rotor body is rotated.

18. A method according to claim 15, 16 or 17, which further comprises positioning a plurality of generally vertical stationary vanes separated by channels around said at least one gas injector rotor for receiving said radial and horizontal metal flows.

19. A method according to claim 2, wherein the ratio of said volume of said treatment segment divided by the volume flowrate of metal passing through said section of said trough is less than 70 seconds.

20. Apparatus for treating a molten metal with a treatment gas, comprising:

- an elongated trough having a bottom wall and opposed side walls for continuously conveying said molten metal, said trough including a section for treating the molten metal with said treatment gas;

- at least one gas injector in use positioned in said section of said trough submerged in said metal;

- means for conveying gas to said at least one gas injector for injection into said metal; and

- means for mechanically moving said at least one gas injector to disperse treatment gas in said metal;

- wherein said section of said trough has a transverse vertical cross-sectional area centred on said at least one injector and a maximum width at a midpoint of said at least one injector, and wherein the product of said transverse vertical cross-sectional area and said maximum width does not exceed 0.2 m^3 .

21. Apparatus according to claim 20, wherein said section of said trough exhibits a static to dynamic metal holdup of less than 50%.

22. Apparatus according to claim 20 or claim 21, wherein said at least one gas injector includes a rotor having a smooth cylindrical outer surface provided with inwardly directed openings which generate metal flow in an outward radial and horizontal direction when said rotor is immersed in said molten metal and rotated; said rotor having a bottom surface provided with at least one opening communicating with said openings in said cylindrical outer surface, a gas injection port for introducing said treatment gas into said metal flow, and a channel for conveying said gas to said gas injection port.

23. Apparatus according to claim 20 or claim 21, wherein said at least one gas injector has a rotor body including a cylindrical side surface and a bottom surface, with at least one opening on said bottom surface, at least three openings in said side surface symmetrically disposed around the surface, and an internal structure providing passages within the rotor for movement of molten metal between the bottom and side openings, and at least one gas injection port located within the body of the rotor and communicating with the said passages; said internal structure in use causing gas entering by the gas injection port to mix with molten metal within the body of the rotor so as to form bubbles; and said internal structure in use also causing the molten metal and gas bubbles to flow from the side openings in a radial and horizontal manner.

24. Apparatus according to claim 23, further comprising means for rotating each said rotor such that gas bubbles within said radial and horizontal metal flows encounter a tangential shear gradient in said molten metal as said flows exit said rotor effective to breakup said bubbles into finer bubbles, such that said radial and horizontal metal flows have sufficient momentum to disperse said metal flows and finer gas bubbles throughout said treatment segment but without causing splashing at walls of said trough, and such that bubbles breaking said metal at an upper surface are uniformly distributed without concentrations of bubbles at said gas injector or said walls of said trough.

25. Apparatus according to claim 22, wherein said rotor has at least three openings in said side surface spaced symmetrically around the rotor.

26. Apparatus according to claim 22 or claim 25, wherein said rotor has a generally flat horizontal upper surface centrally connected to a shaft for supporting and rotating said rotor.

27. Apparatus according to claim 22 or claim 25, wherein said rotor has a frusto-conical, upwardly tapering surface merging with a shaft for supporting and rotating the rotor.

28. Apparatus according to claim 22, claim 25, claim 26 or claim 27, wherein said openings in said side surface occupy an area of said outer surface corresponding to less than 60% of a total area swept by said openings upon rotation of said rotor.

29. Apparatus according to any one of claims 22 to 28, wherein said rotor has a diameter in the range of 5 to 20 cm.

30. Apparatus according to claim 23, wherein said internal structure consists of vanes and passageways separating said vanes.

31. Apparatus according to claim 23, wherein said internal structure comprises at least six vanes.

32. Apparatus according to claim 22, further comprising a plurality of generally vertical stationary vanes separated by channels around each said rotor for receiving said radial and horizontal metal flows.

33. Apparatus according to any one of claims 22 to 32, wherein said section of said trough has a depth in the range of 15 to 50 cm and width in the range of 10 to 40 cm.

34. Apparatus according to any one of claims 20 to 33, wherein a plurality of said gas injectors are provided in said section of said trough and said injectors are separated by baffles arranged transversely of said section of said trough for controlling flow of metal through said trough.

35. Apparatus according to any one of claims 20 to 34, wherein said at least one gas injector is provided with support means allowing said at least one gas injector to be raised out of molten metal in said section of said trough, and to be lowered into said molten metal in said section of said trough.

36. Apparatus according to claim 21 wherein said section for treating the molten metal has a volume not exceeding 0.07 m^3 .

37. Apparatus according to claim 21 wherein said trough has a depth of less than 50 cm.

38. A device for treating molten metal in a section of an elongated metal-conveying trough having a bottom wall and opposed side walls for continuously conveying a molten metal, and exhibiting a static to dynamic metal holdup of less than 50%, said device comprising:

at least one gas injector;

means for conveying treatment gas to said at least one gas injector;

means for mechanically moving said at least one gas injector;

support means for said at least one gas injector;
and

means for moving said support means for raising said at least one gas injector out of said section of said trough and lowering said at least one gas injector into said section of said trough.

39. A device according to claim 38 for treating molten metal in said section of said trough, wherein said section of the trough has a transverse vertical cross-sectional area centred on each said injector and a maximum width at a midpoint of said injector, and wherein the product of said transverse vertical cross-sectional area and said maximum width does not exceed 0.2 m^3 .

40. A device according to claim 38 or claim 39, wherein said at least one gas injector comprises a rotor having a smooth cylindrical outer surface provided with inwardly

directed openings which generate metal flow in an outward radial and horizontal direction when said rotor is immersed in said molten metal and rotated, said rotor having a lower end surface provided with openings communicating with said openings in said smooth cylindrical outer surface; a gas injection port positioned on said rotor for introducing a treatment gas into said metal flow; and a channel for conveying said treatment gas under pressure to said gas injection port.

41. A device according to claim 38, claim 39 or claim 40, comprising a plurality of said injectors separated by baffles supported by said support means and arranged transversely of said section of said trough for controlling flow of metal through said section of said trough.

42. An injector for injecting gas into a molten metal, comprising:

- a rotor having a projection-free cylindrical side surface, a projection-free and unbroken upper surface, and a bottom surface;

- a plurality of openings in said side surface spaced symmetrically around the rotor, said openings occupying an area of said outer surface corresponding to less than 60% of a total area swept by said openings upon rotation of said rotor;

- at least one opening in the bottom surface; and

- at least one internal passageway for gas delivery and an internal structure for interconnecting said openings in said side surface, said at least one opening in said bottom surface and said at least one internal passageway;

- said internal structure in use being at least partially filled with molten metal or metal/gas mixtures,

and being adapted to cause gas emanating from said internal passageway to break up into bubbles to form a metal/gas mixture to issue from said openings in said side surface in a generally horizontal and radial manner, said side surfaces causing said gas bubbles to be broken up into finer bubbles upon rotation of said rotor in said molten metal, and

wherein said internal structure consists of vanes and channels separating said vanes.



43. An injector according to claim 42, having at least six said vanes.


44. An injector according to claim 42 or claim 43, wherein said vanes extend downwardly from the rotor with the outer faces of the vanes forming at least part of the cylindrical side surface, the vanes being arranged symmetrically in such a way as to define diametrically-extending channels between said vanes, said channels intersecting to form a central space and forming, at the outer ends of said channels, said openings in said side surface of the rotor.

45. An injector according to claim 42, claim 43 or claim 44, wherein said rotor has at least three of said openings in said side surface spaced symmetrically around the rotor.

46. An injector according to any one of claims 42 to 45, wherein said rotor has a generally flat horizontal upper surface centrally connected to a shaft for supporting and rotating said rotor.
47. An injector according to any one of claims 42 to 45, wherein said rotor has a frusto-conical, upwardly-tapering surface merging with a shaft for supporting and rotating the rotor.
48. An injector according to any one of claims 42 to 45, wherein said rotor has a diameter in the range of 5 to 20 cm.
49. An injector according to claim 44, wherein said vanes have bottom surfaces defining at least part of the bottom surface of said rotor.
50. An injector according to claim 44, wherein said bottom surface of said rotor is in the form of a continuous plate linking bottom surfaces of said vanes, with an axially-placed opening communicating with said central space.

1/12





SUBSTITUTE SHEET

2181037

3/12




FIG. 4




FIG. 5

SUBSTITUTE SHEET

4/12




FIG. 6

SUBSTITUTE SHEET

5/12




FIG. 7




FIG. 8

SUBSTITUTE SHEET

6/12




FIG. 9










FIG. 10

SUBSTITUTE SHEET

7/12



**FIG. 12a****FIG. 12b****FIG. 12c****FIG. 12d**

9/12




FIG. 13




FIG. 14

SUBSTITUTE SHEET




FIG. 15

11/12




FIG. 16

2181037

12/12




FIG. 17

SUBSTITUTE SHEET

