

(51) International Patent Classification:
H01R 13/20 (2006.01)(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.(21) International Application Number:
PCT/US2012/033177(22) International Filing Date:
12 April 2012 (12.04.2012)

(25) Filing Language: English


(26) Publication Language: English

(30) Priority Data:
61/492,868 3 June 2011 (03.06.2011) US(71) Applicant (for all designated States except US): **FRAM GROUP IP, LLC** [US/US]; UCI/FRAM Group, 1900 West Field Court, Lake Forest, Illinois 60045 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ZHENG, Jing** [US/US]; 742 Parkview Drive, Findlay, Ohio 45840 (US). **BOEHLER, Jeffrey** [US/US]; 1148 Kieswetter Road, Holland, Ohio 43528 (US).(74) Agent: **FOX, Erin, J.**; Barnes & Thornburg LLP, P.O. Box 2786, Chicago, IL 60690-2786 (US).(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).**Declarations under Rule 4.17:**

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

*[Continued on next page]***(54) Title:** SPARK PLUG**FIG. 5**

(57) Abstract: A spark plug is provided having a resistor. The resistor is made from resistor glass material containing an alkali free barium aluminosilicate glass mixed with mullite. In one embodiment, the resistor is a 15 to 30 wt% alkali free barium aluminosilicate glass and 10 to 25 wt% mullite. The resistor material provides for a greater processing kiln temperature range with reduced resistor variability and improved durability performance.



- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

Published:

- with international search report (Art. 21(3))

SPARK PLUG

BACKGROUND OF THE INVENTION

[0001] The subject matter disclosed herein relates to a spark plug and in particular to a spark plug having a resistor made with glass materials with an increased glass transition temperature.

[0002] Spark plugs are widely used to ignite fuel in internal combustion engines. Spark plugs are subject to intense heat in a highly corrosive environment of a vehicle engine. As a result, a spark plug having high durability and useful life is desireable. Further, in addition to igniting fuel, in some applications the spark plug is influencing the sensor signal acquired by the vehicle control system to monitor the operation of the engine. These applications typically require tighter electrical tolerances and lower electromagnetic interference (EMI) to reduce interference with signals from both the spark plug itself and the surrounding control circuitry.

[0003] Accordingly, while existing spark plugs are suitable for their intended purposes, there remains a need for improvements particularly in providing a spark plug with tighter resistor tolerance.

BRIEF DESCRIPTION OF THE INVENTION

[0004] According to one aspect of the invention, a spark plug is provided having a resistor made from a mixture of alkali free barium alumino-silicate glass and mullite.

[0005] According to another aspect of the invention, a spark plug is provided having an insulator having an inner bore. A center electrode extends from one end of the inner bore. An insert extends from an opposite side of the inner bore. A resistor is disposed between the center electrode and the insert, the resistor being made from a mixture of alkali free barium alumino-silicate glass and mullite.

[0006] According to yet another aspect of the invention, a method of fabricating a sparkplug is provided. The method includes mixing carbon and ceramic powder to make carbon slurry. The carbon slurry is added to a glass mixture containing an alkali free barium borate glass and Mullite. The carbon slurry-glass mixture is dried and then screened to form

a carbon resistor glass. The carbon resistor glass is loaded into a sparkplug insulator. The sparkplug insulator-carbon glass assembly is heated to transform the carbon resistor glass into a semi-melt condition.

[0007] These and other advantages and features will become more apparent from the following description taken in conjunction with the drawings.

BRIEF DESCRIPTION OF THE DRAWING

[0008] The subject matter, which is regarded as the invention, is particularly pointed out and distinctly claimed in the claims at the conclusion of the specification. The foregoing and other features, and advantages of the invention are apparent from the following detailed description taken in conjunction with the accompanying drawings in which:

[0009] FIG. 1 is a side sectional view of a spark plug in accordance with an embodiment of the invention;

[0010] FIG. 2 is a graph showing the results of a spark plug resistance test based on controlled kiln temperature

[0011] FIG. 3 is a graph showing the results of a spark plug accumulated failure rate under accelerated testing;

[0012] FIG. 4 is a graph showing the results of a spark plug resistance change based on production kiln temperature; and,

[0013] FIG. 5 is a flow chart showing a method of fabricating a spark plug in accordance with an embodiment of the invention.

[0014] The detailed description explains embodiments of the invention, together with advantages and features, by way of example with reference to the drawings.

DETAILED DESCRIPTION OF THE INVENTION

[0015] Embodiments of the present invention provide advantages in reducing the variation of resistance values for a resistor in a spark plug application. It has been found that the resistor glass materials are sensitive to kiln process temperature. This temperature

sensitivity leads to a variation in resistance during the spark plug assembly process. Embodiments of the present invention provide for a resistor material that has an improved durability, a longer useful life and may be processed at a wider range of processing temperatures while maintaining a low variation in resistance. Embodiments of the present invention further provide for a smaller electromagnetic interference range for spark plugs.

[0016] Referring to FIG. 1, a spark plug 20 is shown in accordance with the present invention. The spark plug 20 includes a metal casing or shell 22 having an externally threaded cylindrical base 24 for threadable engagement in the cylinder head of an internal combustion engine (not shown). The shell may include a generally hexagonal boss 30 thereon to allow for grasping and turning of the spark plug 20 with a suitable tool, such as a conventional spark plug socket for example. A bi-metallic ground electrode 26 is coupled, such as by welding for example, to a lower surface 28 of the threaded base 24.

[0017] The spark plug 20 further includes a ceramic insulator 32 disposed concentrically within the shell 22. A center electrode 34 is disposed concentrically within the insulator 32. The center electrode 34 may include a central core 36 made from a thermally conductive material, such as copper or a copper alloy for example. An electrode tip 38 is disposed on one end of the center electrode 34. Opposite the electrode tip 38 is an electrically conductive insert or rod 40. The insert 40 fits into the upper end of the insulator 32 and forms

[0018] Disposed between the insert 38 and the center electrode 32 is an internal resistor 42. As will be discuss in more detail herein, the resistor material and assembly process influence resistance value of the internal resistor 42, the durability, useful life and EMI emissions of the spark plug 20. In the exemplary embodiment, the resistor 42 is formed from a mixture of an alkali free barium alumino-silicate glass, Mullite, carbon, ceramic powders and other ingredients. The glass is composed of MgO 2.0wt% - Al₂O₃ 11.3wt% - SiO₂ 53.5wt% - CaO -12.0wt% - BaO - 20.5wt% in composition. In one embodiment, the mixture has 15-30 wt% glass and 10-25% Mullite and the balance is ceramic powder, carbon, borate glass and organic binders.

[0019] To form resistor glass containing the alkali free barium alumino-silicate glass, first all the components, glasses, Mullite and other materials, are weighed and a carbon slurry, containing carbon and ceramic powders (ZrO₂) is added. The components are mixed

for a predetermined amount of time. In the exemplary embodiment the components are mixed for seven minutes. Ice is added to components and further mixed for a predetermined amount of time, such as 10 minutes for example. After the components and ice are mixed, the mixture is oven dried. In the exemplary embodiment, the mixture is oven dried for 5 hours at 120C. Following the drying, the mixture is screened, such as with a #20 mesh for example. The material processed through the screen is ready to be used for assembling resistor for sparkplugs

[0020] To assemble the resistor for sparkplug, the above finished powders are loaded in the sparkplug insulator with centerwire and stud terminal. The whole assembly was then processed through a high temperature kiln with peak temperature between 1700F to 1800F.

[0021] Fig. 2 shows the low voltage resistance of the resistor 42 at different kiln processing temperatures. The standard glass formulation indicated by line 44 shows a substantial variation in resistance of 54% over a processing temperature range of 200 degrees. In contrast, the exemplary alkali free barium alumino-silicate glass/mullite resistor 42, indicated by line 46, had only a 2% variation over the same temperature range. It should be appreciated that this reduction in variation in resistance results in larger production yields. Current production processes have a target kiln temperature of 1775°F and the temperature is controlled within $\pm 50^{\circ}\text{F}$ in order to achieve a desired resistance value from the resistor 42.

[0022] Fig. 3 shows a life curves from accelerated life tests for the exemplary alkali free barium alumino-silicate glass/mullite resistor 42 and standard spark plug resistors (as a comparison) when processed at elevated temperature of 1900F. The accelerated life tests were conducted in a heated pressure bomb at engine cylinder pressure. The standard spark plug resistor had initial failures being at six hours. The exemplary alkali free barium alumino-silicate glass/mullite resistor 42 in contrast had no failures over a twenty-four hour period. The results suggest that the resistor materials containing alkali free barium alumino-silicate glass and Mullite has a wider process window to yield products with improved performance and/or longer useful life.

[0023] Fig. 4 shows a resistance change curve for another embodiment alkali free barium alumino-silicate glass/mullite resistor 42 and a standard spark plug resistor (as a comparison), processed on standard production kiln. The alkali free barium alumino-silicate glass/mullite resistor 42 shows a lower resistor variation in temperature ranges lower than

1800°F, and has a processing window with a substantially flat resistance between 1750°F to 1800°F.

[0024] Referring now to Fig. 5, a method 50 of fabricating a spark plug, such as spark plug 20 for example is shown. The method 50 starts in block 52 where carbon and ceramic powder are mixed to make carbon slurry. The carbon slurry is added to the glass mixture and Mullite in block 54. The glass mixture includes but is not limited to alkali free barium borate glass. The alkali free barium borate glass may be composed of MgO 2.0wt% - Al₂O₃ 11.3wt% - SiO₂ 53.5wt% - CaO -12.0wt% - BaO - 20.5wt% in composition. In one embodiment, the mixture has 15-30 wt% glass and 10-25% Mullite and the balance is ceramic powder, carbon, borate glass and organic binders. The mixture is then dried and screened in block 56 to form a carbon resistor glass.

[0025] The desired volume of carbon resistor glass is then loaded into sparkplug insulators, such as insulator 32 for example, in block 58. The above insulator glass assembly is then subject to high temperature environment in block 60. In one embodiment, the insulator-glass assembly is carried on a conveyor through an oven operating at a temperature of 1650F to 1850F. At the end of the firing cycle, a plunge (terminal stud), such as insert 40 for example, is pressed into the insulator in block 62 so that the glass powders (in semi-melt condition) can be compacted into dense condition and the resistor is hence formed and sealed into the sparkplugs.

[0026] While the invention has been described in detail in connection with only a limited number of embodiments, it should be readily understood that the invention is not limited to such disclosed embodiments. Rather, the invention can be modified to incorporate any number of variations, alterations, substitutions or equivalent arrangements not heretofore described, but which are commensurate with the spirit and scope of the invention. Additionally, while various embodiments of the invention have been described, it is to be understood that aspects of the invention may include only some of the described embodiments. Accordingly, the invention is not to be seen as limited by the foregoing description, but is only limited by the scope of the appended claims.

CLAIMS:

1. A spark plug comprising a resistor made from a mixture of alkali free barium alumino-silicate glass and mullite.
2. The spark plug of claim 1 wherein the resistor is made from 15 to 30 wt% alkali free barium alumino-silicate glass.
3. The spark plug of claim 2 wherein the resistor is made from 10 to 25 wt% mullite.
4. The spark plug of claim 3 wherein the alkali free barium alumino-silicate glass is comprised of MgO 2.0wt% - Al₂O₃ 11.3wt% - SiO₂ 53.5wt% - CaO -12.0wt% - BaO - 20.5wt% in composition
5. The spark plug of claim 4 wherein the resistor material containing alkali free barium alumino-silicate glass is processed in a kiln at a processing temperature between 1650°F and 1850°F.
6. A spark plug comprising:
 - an insulator having an inner bore;
 - a center electrode extending from one end of the inner bore;
 - an insert extending from an opposite side of the inner bore; and,
 - a resistor disposed between the center electrode and the insert, the resistor being made from a mixture of alkali free barium alumino-silicate glass and mullite.
7. The spark plug of claim 6 wherein the resistor is made from 15 to 30 wt% alkali free barium alumino-silicate glass.
8. The spark plug of claim 7 wherein the resistor is made from 10 to 25 wt% mullite.
9. The spark plug of claim 8 wherein the alkali free barium alumino-silicate glass is comprised of MgO 2.0wt% - Al₂O₃ 11.3wt% - SiO₂ 53.5wt% - CaO -12.0wt% - BaO - 20.5wt% in composition.

10. The spark plug of claim 9 wherein the alkali free barium alumino-silicate glass is processed in a kiln at a processing temperature between 1650°F and 1850°F.

11. A method of fabricating a sparkplug comprising:

mixing carbon and ceramic powder to make carbon slurry;

adding the carbon slurry to a glass mixture containing an alkali free barium borate glass and Mullite;

drying the carbon slurry-glass mixture;

forming a carbon resistor glass;

loading the carbon resistor glass into a sparkplug insulator; and,

heating the sparkplug insulator-carbon glass assembly to transform the carbon resistor glass into a semi-melt condition.

12. The method of claim 11 further comprising screening the carbon slurry-glass mixture after drying.

13. The method of claim 12 wherein the screening is performed with a #20 mesh.

14. The method of claim 11 further comprising mixing the glass mixture containing an alkali free barium borate glass, Mullite and carbon slurry for a first predetermined amount of time.

15. The method of claim 14 wherein the first predetermined amount of time is seven minutes.

16. The method of claim 14 further comprising mixing ice with the glass mixture containing an alkali free barium borate glass, Mullite and carbon slurry for a second predetermined amount of time.

17. The method of claim 16 wherein the second predetermined amount of time is ten minutes.

18. The method of claim 11 further comprising pressing a terminal stud into said insulator-carbon glass assembly when the carbon resistor glass is in a semi-melt condition.
19. The method of claim 18 wherein the alkali free barium alumino-silicate glass is comprised of MgO 2.0wt% - Al₂O₃ 11.3wt% - SiO₂ 53.5wt% - CaO -12.0wt% - BaO - 20.5wt% in composition.
20. The method of claim 19 wherein the carbon resistor glass is made from 15 to 30 wt% alkali free barium alumino-silicate glass.
21. The method of claim 20 wherein the carbon resistor glass is made from 10 to 25 wt% mullite.
22. The method of claim 21 wherein the heating of the sparkplug insulator-carbon glass assembly is performed in a kiln at a processing temperature between 1650°F and 1850°F.

1/4




FIG. 1

2/4




FIG. 2




FIG. 3

3/4




FIG. 4

4/4




FIG. 5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2012/033177

A. CLASSIFICATION OF SUBJECT MATTER

H01R 13/20(2006.01)i

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

H01R 13/20; H01T 13/20; H01B 1/06; C03C 27/02

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
Korean utility models and applications for utility models
Japanese utility models and applications for utility modelsElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
eKOMPASS(KIPO internal) & Keywords:spark plus,resistor,barium

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	JP 2009-245716 A (NGK SPARK PLUG CO LTD) 22 October 2009 See figure 1 and paragraphs [0022]-[0023].	1-3,6-8,11-18 4-5,9-10,19-22
A	US 6590318 B2 (NISHIKAWA; KENICHI et al.) 08 July 2003 See abstract, column 25, lines 21-24, claim 1 and figure 1.	1-22
A	US 04446058A A (SAKAI; MASAO et al.) 01 May 1984 See abstract, claims 1,2,4 and figure 2.	1-22
A	US 2001-0007196 A1 (MAKOTO SUGIMOTO et al.) 12 July 2001 See abstract, paragraphs [0047]-[0048], claim 1 and figure 1.	1-22

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:
 "A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier application or patent but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
 "&" document member of the same patent family

Date of the actual completion of the international search
19 OCTOBER 2012 (19.10.2012)

Date of mailing of the international search report

23 OCTOBER 2012 (23.10.2012)

Name and mailing address of the ISA/KR



 Korean Intellectual Property Office
 189 Cheongsa-ro, Seo-gu, Daejeon Metropolitan
 City, 302-701, Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

Lee Min Hyong

Telephone No. 82-42-481-8692



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2012/033177

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2009-245716 A	22.10.2009	CN 101897091 A EP 2214273 A1 JP 04-922980 B2 KR 10-2010-0130581 A US 2010-0264823 A1 WO 2009-122941 A1	24.11.2010 04.08.2010 10.02.2012 13.12.2010 21.10.2010 08.10.2009
US 6590318 B2	08.07.2003	CA 2339390 A1 CN 1317857 A0 CN 1326301 C0 DE 60107735 D1 DE 60107735 T2 DE 60132504 D1 DE 60132504 T2 DE 60132504 T8 DE 60138970 D1 DE 60140221 D1 EP 1130728 A2 EP 1130728 A3 EP 1130728 B1 EP 1434323 A2 EP 1434323 A3 EP 1434323 B1 EP 1434324 A2 EP 1434324 A3 EP 1434324 B1 EP 1434325 A2 EP 1434325 A3 EP 1434325 B1 JP 03-510172 B2 JP 03-632953 B2 JP 04-833526 B2 JP 2001-244043 A JP 2001-319755 A JP 2004-363112 A JP 3510172 B2 JP 4833526 B2 KR 10-2001-0085694 A KR20010085694A US 2002-0033659 A1	29.08.2001 17.10.2001 11.07.2007 20.01.2005 08.12.2005 06.03.2008 15.01.2009 16.04.2009 23.07.2009 26.11.2009 05.09.2001 02.07.2003 15.12.2004 30.06.2004 13.04.2005 16.01.2008 30.06.2004 13.04.2005 10.06.2009 30.06.2004 13.04.2005 14.10.2009 09.01.2004 30.03.2005 30.09.2011 07.09.2001 16.11.2001 24.12.2004 22.03.2004 07.12.2011 07.09.2001 07.09.2001 21.03.2002
US 04446058A A	01.05.1984	JP 1478811 C JP 58-012302 A JP 63-028322 B	10.02.1989 24.01.1983 08.06.1988
US 2001-0007196 A1	12.07.2001	CN 1050942 C CN 1179024 A CN 1179024 C0 DE 69712845 D1	29.03.2000 15.04.1998 15.04.1998 04.07.2002

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2012/033177

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		DE 69712845 T2	14.11.2002
		EP 0829936 A1	18.03.1998
		EP 0829936 B1	29.05.2002
		JP 03-813708 B2	23.08.2006
		JP 10-144448 A	29.05.1998
		US 06137211A A	24.10.2000
		US 6341501 B2	29.01.2002