

**(12) STANDARD PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

(11) Application No. **AU 2014202871 B2**

- (54) Title  
**Apparatus, system and method for compression testing of test specimens**
- (51) International Patent Classification(s)  
**G01N 3/08** (2006.01)
- (21) Application No: **2014202871** (22) Date of Filing: **2014.05.27**
- (30) Priority Data
- |                   |                   |              |
|-------------------|-------------------|--------------|
| (31) Number       | (32) Date         | (33) Country |
| <b>13/947,050</b> | <b>2013.07.20</b> | <b>US</b>    |
- (43) Publication Date: **2015.02.05**  
(43) Publication Journal Date: **2015.02.05**  
(44) Accepted Journal Date: **2017.12.07**
- (71) Applicant(s)  
**The Boeing Company**
- (72) Inventor(s)  
**Kismarton, Max U.; Griess, Kenneth H.**
- (74) Agent / Attorney  
**Spruson & Ferguson, L 35 St Martins Tower 31 Market St, Sydney, NSW, 2000, AU**
- (56) Related Art  
**US 5297441 A**  
**FR 2695207 A1**  
**Pablo Feraboli, "Development of a modified flat-plate test specimen and fixture for composite materials crush energy", doi:10.1177/0021998309343025, (20090720), pages 1967 - 1990, URL: <http://jcm.sagepub.com/content/43/19/1967>, (20141117)**

## **APPARATUS, SYSTEM AND METHOD FOR COMPRESSION TESTING OF TEST SPECIMENS**

### **ABSTRACT**

There is provided an apparatus (30) for compression testing. The apparatus (30) has a base assembly (60) having an end load element (74) attached to the base assembly (60), the base assembly (60) being rigid. The apparatus (30) has a support assembly (32) attached to the base assembly (60), and having a plurality of window portions (44). The apparatus (30) has a core assembly (46) installed within the support assembly (32), the core assembly (46) being crushable and configured to protect the support assembly (32) and the base assembly (60) from fracture loads (53) generated during compression testing. The base assembly (60), the support assembly (32), and the core assembly (46) together form an apparatus (30) for compression testing of a test specimen (80) having a notch portion (82). The apparatus (30) is configured for use with an optical strain measurement system (120). When the test specimen (80) is installed in the support assembly (32), the test specimen (80) and the notch portion (82) are visible to the optical strain measurement system (120) through the plurality of window portions (44).




FIG. 2A

# APPARATUS, SYSTEM AND METHOD FOR COMPRESSION TESTING OF TEST SPECIMENS

## Field

[0001] The disclosure relates generally to apparatus assemblies, systems and methods for compression testing of test specimens, and more particularly, to apparatus assemblies, systems and methods for compression testing of large notch compression test panels, such as panels of component parts of air vehicles.

## Background

[0002] Mechanical testing of component parts, or of test specimens of component parts, is often performed in the manufacture of air vehicles, such as aircraft, rotorcraft, spacecraft, and other air vehicles. Mechanical testing provides material property data, such as strength, hardness ductility, and other data about the material as tested under various conditions, such as compression, tension, load and temperature. In turn, the mechanical testing provides information relating to the suitability of a material for its intended application. Such information aids in the design of component parts that will perform as expected.

[0003] Mechanical testing of component parts of air vehicles may include compression testing. Compression testing determines the behavior of materials, such as composite or metal materials, under compressive load conditions. Compression testing may be conducted by loading a test specimen, such as a test panel or a flat piece of laminate referred to as a "coupon", between two support plates of a test fixture.

[0004] The test fixture is typically installed in a testing machine, for example, a universal testing machine. The testing machine may apply a compression force or load to the test specimen and may compress the test specimen in a lengthwise direction until it fractures or breaks. The testing machine may record the force required to fracture or break the test specimen. Compressive strength of the test specimen material may be measured by plotting applied force or load versus deformation of the test specimen material. As used herein, "compressive strength" means the maximum compressive load or stress the test specimen material is capable of withstanding before fracturing or breaking.

[0005] Test fixtures, apparatus assemblies, and methods for compression testing of air vehicle component parts exist. For example, FIG. 1 is an illustration of a front perspective view of an existing test fixture for compression testing, such as in the form of an existing large notch compression (LNC) test fixture. As shown in FIG. 1, the existing test fixture has a first support plate and a second support plate that sandwich a test specimen panel therebetween. The test specimen panel may be in the form of a large notch compression (LNC) panel.

[0006] As further shown in FIG. 1, the first support plate and the second support plate of the existing test fixture completely cover the test specimen panel and obstruct any view of the test specimen panel. Thus, use of such existing test fixture precludes use with existing optical strain measurement systems that may be used to optically obtain information relating to strain measurements of the test specimen panel.

[0007] Instead of using existing optical strain measurement systems, the existing test fixture requires the use of a plurality of strain gages (see FIG. 1) to measure the strain of the test specimen panel. As shown in FIG. 1, each strain gage may be positioned laterally across the first support plate, and each strain gage may be coupled to hinge attachment elements mounted on a frame portion of the existing test fixture.

[0008] However, the use of such strain gages (see FIG. 1) may involve extensive installation time and labor, which results in increased flow time. In addition, the use of such strain gages (see FIG. 1) may require precise alignment and calibration operations, as well as connection to a strain gage machine, prior to testing. This may, in turn, result in increased time and expense of testing. Due to the extensive time involved in installing the strain gages (see FIG. 1) on the existing test fixture (see FIG. 1), test specimen panels may only be tested at a test rate of one (1) or two (2) test specimen panels per day.

[0009] As further shown in FIG. 1, the existing test fixture has a base portion and a side support portion<sup>4</sup> (one on each side). However, the base portion may be thin and wear out after several compression tests. Shimming may be required to reinforce the base portion and to hold the first support plate, the second support plate, and the test specimen panel in place. For example, shims (see FIG. 1) may be installed on the existing test fixture (see FIG. 1). However, such shimming process may involve extensive installation time and labor prior to testing. This may, in turn, result in increased time and expense of testing.

[00010] Thus, existing methods for compression testing of test specimen panels, such as large notch compression panels, may be expensive and may take four (4) to ten (10) weeks or more to complete. Accordingly, there is a need in the art for an improved apparatus, system and method for compression testing of test specimens, such as large notch compression test panels of component parts of air vehicles that provide advantages over known apparatus assemblies, systems and methods.

### **Summary of Invention**

[00011] This need for an improved apparatus, system and method for compression testing of test specimens, such as large notch compression test panels of component parts of air vehicles is satisfied by this disclosure. As discussed in the below detailed description, embodiments of the improved apparatus, system and method for compression testing of test specimens, such as large notch compression test panels of component parts of air vehicles, may provide significant advantages over known apparatus assemblies, systems and methods.

[00012] In one embodiment of the disclosure, there is provided an apparatus for compression testing of a test specimen having a notch portion, the apparatus comprising: a base assembly and an end load element attached to the base assembly, the base assembly being rigid; a support assembly attached to the base assembly, the support assembly comprising a first support grid and a second support grid, wherein the first support grid and the second support grid each comprise a frame portion and a grid portion, which grid portion comprises a plurality of vertical members and a plurality of horizontal members that intersect the plurality of vertical members to form a plurality of window portions, the first support grid configured for attachment to the second support grid, and the first support grid and the second support grid configured to have a core assembly and the test specimen installed between them; and a core assembly installed within the support assembly, the core assembly being crushable and configured to stabilize the test specimen and protect the support assembly and the base assembly from fracture loads generated by the test specimen adjacent the core assembly during compression testing by absorbing energy that is released sideways from the test specimen upon fracture or breaking of the test specimen; the apparatus being configured for use with an optical strain measurement system, wherein the window portions are configured such that the test specimen and the notch portion are visible to said optical strain measurement system through the plurality of window portions when the test specimen is installed in the support assembly.

[00013] The base assembly, the support assembly, and the core assembly together comprise an apparatus for compression testing of a test specimen having a notch portion. The apparatus is configured for use with an optical strain measurement system. When the test specimen is installed in the support assembly, the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions.

[00014] In another embodiment of the disclosure, there is provided a system for compression testing. The system comprises an apparatus for compression testing. The apparatus comprises a base assembly having an end load element attached to the base assembly, the base assembly being rigid. The apparatus further comprises a support assembly attached to the base assembly, the support assembly having a plurality of window portions. The apparatus further comprises a core assembly installed within the support assembly, the core assembly being crushable and configured to protect the support assembly and the base assembly from fracture loads generated during compression testing.

[00015] The system further comprises a test specimen having a notch portion. The test specimen is installed in the support assembly of the apparatus. The system further comprises a testing machine configured to apply one or more compression loads to the test specimen when the apparatus with the test specimen is installed in the testing machine. The system further comprises a testing machine controller coupled to the testing machine and configured to control operation of the testing machine.

[00016] The system further comprises an optical strain measurement system positioned in relation to the apparatus with the test specimen installed in the testing machine, so that the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions. The system further comprises a data acquisition system coupled to the optical strain measurement system. The apparatus, the test specimen, the testing machine, the testing machine controller, the optical strain measurement system, and the data acquisition system together comprise a system for compression testing of the test specimen.

[00017] In another embodiment of the disclosure, there is provided a method for compression testing, the method comprising the steps of: forming an apparatus for compression testing of a test specimen, the apparatus comprising: a base assembly having an end load element attached to the base assembly, the base assembly being rigid; a support assembly attached to the base

assembly, the support assembly having a plurality of window portions; and, a core assembly installed within the support assembly, the core assembly being crushable and configured to protect the support assembly and the base assembly from fracture loads generated during compression testing; forming a notch portion in a test specimen; installing the test specimen within the support assembly and adjacent to the core assembly; installing the apparatus in a testing machine for compression testing; positioning an optical strain measurement system in relation to the apparatus, so that the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions; applying one or more compression loads to the test specimen; and measuring strain data of the test specimen with the optical strain measurement system.

[00018] The method further comprises the step of forming a notch portion in a test specimen. The method further comprises the step of installing the test specimen within the support assembly and adjacent to the core assembly. The method further comprises the step of installing the apparatus in a testing machine for compression testing.

[00019] The method further comprises the step of positioning an optical strain measurement system in relation to the apparatus, so that the test specimen and the notch portion are visible to



the optical strain measurement system through the plurality of window portions. The method further comprises the step of applying one or more compression loads to the test specimen. The method further comprises the step of measuring strain data of the test specimen with the optical strain measurement system.

[00020] The features, functions, and advantages that have been discussed can be achieved independently in various embodiments of the disclosure or may be combined in yet other embodiments further details of which can be seen with reference to the following description and drawings.

### **Brief Description of Drawings**

[00021] The disclosure can be better understood with reference to the following detailed description taken in conjunction with the accompanying drawings which illustrate preferred and exemplary embodiments, but which are not necessarily drawn to scale, wherein:

[00022] FIG. 1 is an illustration of a front perspective view of an existing test fixture for compression testing;

[00023] FIG. 2A is an illustration of a front perspective view of an exemplary embodiment of an apparatus for compression testing of the disclosure;

[00024] FIG. 2B is an illustration of a back perspective view of the apparatus of FIG. 2A;

[00025] FIG. 2C is an illustration of a front perspective view of a base assembly of the apparatus of FIG. 2A;

[00026] FIG. 2D is an illustration of a front perspective view of a support grid of the apparatus of FIG. 2A;

[00027] FIG. 2E is an illustration of a front perspective view of the support grid of FIG. 2D attached to the base assembly of FIG. 2C;

[00028] FIG. 2F is an illustration of a front perspective view of a core assembly used in the apparatus of FIG. 2A;

[00029] FIG. 2G is an illustration of a front perspective view of the core assembly of FIG. 2F attached to the support grid and the base assembly of FIG. 2E;

[00030] FIG. 2H is an illustration of a front perspective view of a test specimen used in the apparatus of FIG. 2A;

[00031] FIG. 2I is an illustration of a front perspective view of the test specimen of FIG. 2H installed in front of the core assembly and on the base assembly of FIG. 2E;

[00032] FIG. 2J is an illustration of a front perspective view of the apparatus of FIG. 2A showing use with load leveling devices;

[00033] FIG. 3A is an illustration of a schematic diagram of an exemplary embodiment of a system for compression testing of the disclosure;

[00034] FIG. 3B is an illustration of a front perspective view of an exemplary embodiment of a load leveling device that may be used in the system of FIG. 3A;

[00035] FIG. 3C is an illustration of a front perspective view of the apparatus of FIG. 2A installed in an exemplary embodiment of a testing machine that may be used in the system of FIG. 3A;

[00036] FIG. 4A is an illustration of a side view of an exemplary embodiment of an optical strain measurement system that may be used in the system of FIG. 3A, showing the optical strain measurement system positioned in front of the apparatus of the disclosure;

[00037] FIG. 4B is an illustration of a top view of the optical strain measurement system of FIG. 4A positioned in front of the apparatus of the disclosure;

[00038] FIG. 4C is an illustration of a front perspective view of the apparatus of FIG. 4A showing camera focal points of the optical strain measurement system of FIG. 4A;

[00039] FIG. 4D is an illustration of a close-up, front perspective view of a support grid showing a notch portion visible through window portions;

[00040] FIG. 5 is an illustration of a block diagram of an embodiment of a system and an apparatus for compression testing of the disclosure;

[00041] FIG. 6 is an illustration of a flow diagram of an exemplary embodiment of a method of the disclosure;

[00042] FIG. 7 is an illustration of a perspective view of an aircraft having one or more structures that may be tested and evaluated with embodiments of an apparatus, a system and a method of the disclosure;

[00043] FIG. 8 is an illustration of a flow diagram of an aircraft manufacturing and service method; and,

[00044] FIG. 9 is an illustration of a functional block diagram of an embodiment of an aircraft of the disclosure.

### **Description of Embodiments**

[00045] Disclosed embodiments will now be described more fully hereinafter with reference to the accompanying drawings, in which some, but not all of the disclosed embodiments are shown. Indeed, several different embodiments may be provided and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and will fully convey the scope of the disclosure to those skilled in the art.

[00046] Now referring to the Figures, FIG. 2A is an illustration of a front perspective view of an exemplary embodiment of an apparatus<sup>0</sup> for compression testing of a test specimen (see FIG. 2H) of the disclosure. FIG. 2B is an illustration of a back perspective view of the apparatus of FIG. 2A. As shown in FIGS. 2A-2B, the apparatus may be in the form of a test fixture, such as, for example, a large notch compression test fixture.

[00047] As shown in FIGS. 2A, 2H, the test specimen may be in the form of a test panel. The test panel (see FIGS. 2A, 2H) may, for example, comprise a panel (see FIG. 7), or part of a panel, of an aircraft (see FIG. 7). The test specimen, such as in the form of test panel, may be made of a composite material, or a metal material, such as aluminum or another suitable metal

material. The test specimen may also be in the form of a coupon, e.g., a flat piece of laminate, or another suitable test specimen preferably having a rectangular plan configuration and a rectangular cross section. As shown in FIG. 2H, the test specimen preferably has a notch portion, discussed in further detail below.

[00048] As further shown in FIGS. 2A-2B, the apparatus comprises a base assembly having an end load element attached to the base assembly. FIG. 2C is an illustration of a front perspective view of the base assembly of the apparatus 30 of FIG. 2A. Preferably, the base assembly (see FIG. 2A) is rigid and sturdy. Preferably, the base assembly is made of a rigid material, such as steel or another suitable rigid metal material.

[00049] As shown in FIGS. 2A-2C, the base assembly comprises a base platform. As further shown in FIGS. 2A-2C, the base platform comprises a first platform portion having a top side and a bottom side. As further shown in FIGS. 2A-2C, the base platform comprises a second platform portion having a top side and a bottom side.

[00050] As further shown in FIGS. 2A-2C, the base platform comprises base support elements, for example, a first base support element, a second base support element, and a third base support element. The base support elements are preferably positioned between the first platform portion and the second platform portion, and are preferably spaced apart from each other.

[00051] The base assembly further comprises side support portions (see FIG. 2C). The side support portions (see FIG. 2C) preferably comprise a first side support portion (see FIG. 2C) opposite to and spaced from a second side support portion (see FIG. 2C). The side support portions (see FIG. 2C) are preferably attached to the top side (see FIG. 2C) of the first platform portion (see FIG. 2C) of the base platform (see FIG. 2C).

[00052] Preferably, the side support portions are made of a rigid material, such as steel or another suitable rigid metal material. The side support portions provide support to a support assembly (see FIG. 2A), and in particular, provide direct support to a second support grid (see FIGS. 2A, 2E) of the support assembly (see FIG. 2A).

[00053] As shown in FIGS. 2A and 2G, the end load element may be attached to the base assembly between ends (see FIG. 2A) and across the top side (see FIG. 2G) of the first platform portion. As shown in FIGS. 2A and 2G, the end load element may be attached to the base

assembly with attachment elements, such as in the form of screws or other suitable attachment elements. Preferably, the end load element is in the form of an end load wear strip (see FIGS. 2A, 2G).

[00054] The end load element is preferably made of a metal material or other suitable material based on the particular compression testing conducted. For example, the end load element may comprise a soft metal such as aluminum, copper, tin, or another soft metal, which may conform more easily. Alternatively, the end load element may comprise a hard metal, which may be more durable. In addition, the end load element may be made of a ceramic material, a plastic material, wood, or another suitable material that is durable and wear resistant.

[00055] The end load element (see FIG. 2G) is preferably removable and replaceable, if damaged after testing. The end load element (see FIG. 2G) may be replaced after one or more compression tests and is preferably configured to protect the base assembly (see FIG. 2G) during compression testing. Preferably, the base assembly is designed to withstand wear and tear over numerous compression tests, as compared to thin base structures of certain existing test fixtures.

[00056] As shown in FIGS. 2A-2B, the apparatus further comprises a support assembly attached to the base assembly. Preferably, the support assembly is welded to the base assembly. However, other attachment means may be suitable.

[00057] As shown in FIGS. 2A-2B and FIGS. 2D-2E, the support assembly comprises one or more support grids. FIG. 2D is an illustration of a front perspective view of a support grid of the apparatus of FIG. 2A. FIG. 2E is an illustration of a front perspective view of the support grid of FIG. 2D attached to the base assembly of FIG. 2C. The support grids (see FIGS. 2A, 2E) are preferably made of a rigid material, such as steel or another suitably rigid metal.

[00058] As shown in FIGS. 2A, 2D, the support grids preferably comprise a first support grid and a second support grid 34b. The first support grid is preferably situated in a front position. The second support grid is preferably situated behind the first support grid in a back position. The first support grid is preferably configured for attachment to the second support grid.

[00059] The first support grid (see FIG. 2A) and the second support grid (see FIG. 2E) each comprise a frame portion (see FIGS. 2A, 2D) and a grid portion (see FIGS. 2A, 2D). As shown

in FIGS. 2A, 2D, each grid portion comprises a plurality of vertical members, and a plurality of horizontal members that intersect the plurality of vertical members. It should be appreciated that the terms "vertical" and "horizontal" describe the relative positions of the plurality of vertical members (see FIGS. 2A, 2D) and the plurality of horizontal members (see FIGS. 2A, 2D), for the sake of convenience and clarity, and may not be descriptive of their actual positions during compression testing.

[00060] As shown in FIGS. 2A-2B, the support assembly has a plurality of window portions. The plurality of vertical members (see FIGS. 2A-2B) and the plurality of horizontal members (see FIGS. 2A, 2B) form the plurality of window portions (see FIGS. 2A-2B). Preferably, the support grids (see FIGS. 2A-2B) with the plurality of window portions (see FIGS. 2A-2B) provide a see-through support system. Thus, the first support grid (see FIG. 2A) and the second support grid (see FIG. 2B) are preferably both see-through via their respective plurality of window portions (see FIGS. 2A-2B).

[00061] Preferably, the first support grid (see FIG. 2A) and the second support grid (see FIG. 2B) may each have seventy (70) to eighty (80), or more, window portions. More preferably, the first support grid (see FIG. 2A) and the second support grid (see FIG. 2B) may each have seventy-seven (77) window portions.

[00062] The plurality of window portions (see FIGS. 2A-2B) are preferably sized based on a thickness of the test specimen (see FIG. 2H) and based on a width between adjacent vertical members (see FIGS. 2A-2B). For example, each window portion (see FIG. 2A) may have a width of about two (2) inches to about three (3) inches, and may have a length of about four (4) inches to about eight (8) inches. However, each window portion may have a longer or shorter width and/or length.

[00063] The width between adjacent vertical members may aid in the minimization or elimination of buckling of the test specimen (see FIG. 2H) during compression testing. For example, a width from a centerline of one vertical member to a centerline of an adjacent vertical member may preferably be about one (1) inch to about three (3) inches apart, and more preferably, may be about one (1) inch apart.

[00064] As shown in FIGS. 2A-2B, the apparatus, such as in the form of text fixture, may comprise a plurality of hinge elements for attaching or coupling the first support grid to the

second support grid. The hinge elements (see FIG. 2A) may comprise a plurality of first side hinge elements (see FIG. 2A) and a plurality of second side hinge elements (see FIG. 2A). The hinge elements are preferably spring loaded and may be made of a rigid material such as steel or another rigid metal. The hinge elements may be configured with pins and clevis fittings so that the first support grid may be opened like a door with respect to the second support grid.

[00065] The apparatus further comprises a core assembly (see FIG. 2F) installed within the support assembly (see FIG. 2A). FIG. 2F is an illustration of a front perspective view of the core assembly used in the apparatus of FIG. 2A. The core assembly (see FIG. 2F) is preferably crushable and configured to protect the support assembly and the base assembly from fracture loads (see FIG. 5) generated during compression testing. Such fracture loads (see FIG. 5) may be generated by a test specimen (see FIG. 2H) positioned adjacent the core assembly (see FIG. 2F), when the test specimen is fractured or broken during compression testing.

[00066] The core assembly is designed to stabilize the test specimen (see FIGS. 2A, 2H) during compression testing and is designed to crush and absorb energy that is released sideways from the test specimen upon fracture or breaking of the test specimen (see FIGS. 2A, 2H), such as at a notch portion (see FIG. 2H). By absorbing fracture loads (see FIG. 5) generated or produced from the fracture or breaking of the test specimen (see FIGS. 2A, 2H) during compression testing, the core assembly primarily protects the surrounding support assembly (see FIG. 2A), and also protects the base assembly.

[00067] The core assembly (see FIG. 2F) thus protects the support assembly and the base assembly from fracture loads (see FIG. 5) or breaking loads, and in turn, may increase the life of the apparatus (see FIG. 2A), such as the test fixture (see FIG. 2A), and may allow a lighter weight apparatus design. As used herein, "fracture load" means the load generated at the fracture or breaking point of the test specimen (see FIG. 2H), and in particular, at the notch portion (see FIG. 2H) of the test specimen (see FIG. 2H), when the test specimen undergoes compression testing.

[00068] The core assembly (see FIG. 2F) and the test specimen (see FIG. 2H) are preferably installed between the first support grid (see FIG. 2A) and the second support grid (see FIG. 2A). The base assembly (see FIG. 2A), the support assembly (see FIG. 2A), and the core assembly

(see FIG. 2A) together comprise the apparatus for compression testing of the test specimen (see FIG. 2H) having a notch portion (see FIG. 2H).

[00069] As shown in FIG. 2F, the core assembly comprises a plurality of vertical core elements. It should be appreciated that the term "vertical" describes the relative position of the plurality of vertical core elements (see FIG. 2F), for the sake of convenience and clarity, and may not be descriptive of their actual position during compression testing.

[00070] As further shown in FIG. 2F, the vertical core elements may comprise end vertical core elements and central vertical core elements. FIG. 2F shows six (6) central vertical core elements between two end vertical core elements. However, more or less vertical core elements may be used, depending on the testing conditions and testing machines used.

[00071] The end vertical core elements (see FIG. 2F) preferably have a greater width than the central vertical core elements (see FIG. 2F). For example, the end vertical core elements (see FIG. 2F) may have a width of about two (2) inches to about four (4) inches, or more, and the central vertical core elements (see FIG. 2F) may each have a width of about 0.5 inch to about one (1) inch. Each of the vertical core elements may preferably have a thickness of about 0.5 inch.

[00072] In addition, as shown in FIG. 2F, each of the end vertical core elements has an elongated slot. As shown in FIG. 2F, between each of the vertical core elements is a space portion .

[00073] Each vertical core element (see FIG. 2F) may comprise a honeycomb sandwich core assembly (see FIG. 2F), comprising, for example, 0.5 inch thick aluminum facesheets and a core. Alternatively, each vertical core element (see FIG. 2F) may comprise a rigid foam material or another suitably rigid material. Preferably, the vertical core elements (see FIG. 2F) are sufficiently rigid to withstand compression loads of 300 kips (kilopounds force) per square inch of force, and more preferably, are sufficiently rigid to withstand compression loads in a range of about 300 kips (kilopounds force) per square inch of force to about 500 kips (kilopounds force) per square inch of force, or more.

[00074] As shown in FIG. 2F, the core assembly has a crush zone. As shown in FIG. 2F, the crush zone includes elongated slots of the end vertical core elements. The crush zone preferably



corresponds to a location (see FIG. 2H) of the notch portion (see FIG. 2H) in the test specimen (see FIG. 2H), when the test specimen (see FIG. 3A) is installed in an installation position (see FIG. 3A) in the support assembly (see FIG. 2A). For example, when the test specimen (see FIG. 2A) is loaded, it is designed to fracture, break, or fail at the notch portion (see FIG. 2A) and horizontally across the test specimen (see FIG. 2A). This may result in excess movement normal to the surface of the test specimen at the point of fracture, breakage, or failure. By providing a sufficient area to crush, such as with the crush zone (see FIG. 2F), the apparatus (see FIG. 2A) may be able to withstand increased loading.

[00075] The core assembly (see FIG. 2F) is preferably sufficiently stiff so that it holds the test specimen, if the test specimen starts buckling sideways during compression testing. However, when the test specimen breaks, fractures, or fails upon compression testing, the impact and force of the test specimen may locally crush one or more of the vertical core elements, particularly in the crush zone (see FIG. 2F), of the core assembly, so that load does not get induced to the apparatus (see FIG. 2A).

[00076] Each vertical core element (see FIG. 2F) may be segmented and comprise one or more segments (see FIGS. 2F, 2I), for example, one or more six (6) inch long segments, or another suitable length, that may be easily replaced with new vertical core elements (see FIG. 2F) or new segments or portions that may be connected to the undamaged remaining segments of the vertical core elements (see FIG. 2F). Thus, when the vertical core elements each have segments (see FIGS. 2F, 2I) in a segmented configuration, any damaged portion of the vertical core element (see FIG. 2F) of the core assembly (see FIG. 2F) may be easily replaced.

[00077] FIG. 2G is an illustration of a front perspective view of the core assembly of FIG. 2F attached to the support grid, such as in the form of second support grid, and attached to the base assembly of FIG. 2E. As shown in FIG. 2G, the apparatus may further comprise one or more grip plates. As further shown in FIG. 2G, the grip plate is preferably attached across the bottom of the core assembly with the bottom of the grip plate adjacent the top side of the base assembly. As shown in FIG. 2G, the grip plate may be attached to the core assembly with one or more attachment elements, such as screws or bolts, or another suitable attachment element.

[00078] The grip plate (see FIG. 2G) may be attached or coupled to the core assembly (see FIG. 2G) in a manner such that the first support grid (see FIG. 2A) and the second support grid (see FIG. 2A) may be spaced apart from each other slightly by a gap (see FIG. 2A). As shown in FIG. 2A, the gap may comprise a lower gap and an upper gap. With the presence of the gap (see FIG. 2A), a slight movement together of an upper platen (see FIG. 3A) and a lower platen (see FIG. 3A) of a testing machine (see FIG. 3A) may be allowed in order to test the compression strength of the test specimen (see FIG. 3A) and to avoid reacting any of the compression loads (see FIG. 5) through the apparatus (see FIG. 3A).

[00079] As shown in FIG. 2G, the apparatus may further comprise one or more grip fixtures, such as in the form of clamps. In order to support the test specimen (see FIG. 2A) across the gap (see FIG. 2A) and to prevent unwanted buckling of the test specimen (see FIG. 2A) at the gap (see FIG. 2A), one or more grip fixtures (see FIG. 2A) may be attached to the test specimen (see FIG. 2A).

[00080] As shown in FIG. 2A, the grip fixtures may comprise a first grip fixture and a second grip fixture. The first grip fixture (see FIG. 2A) is preferably coupled to the base assembly (see FIG. 2A) and is configured to hold a first end (see FIG. 2H) of the test specimen (see FIG. 2H), when the test specimen (see FIG. 2A) is installed in the support assembly (see FIG. 2A).

[00081] As shown in FIG. 2A, the first grip fixture may be coupled to the test specimen (see FIG. 2A) via one or more attachment elements (see FIG. 2A), such as in the form of bolts (see FIG. 2A), or another suitable attachment element. The first grip fixture is preferably configured to apply a pressure load (see FIG. 5), such as a clamp load, across the first end (see FIG. 2H) of the test specimen (see FIGS. 2A, 2H).

[00082] As shown in FIGS. 2A-2B and 2H, the second grip fixture is attached to the second end (see FIG. 2H) of the test specimen. The second grip fixture may be attached to the second end of the test specimen via one or more attachment elements, such as in the form of screws, or another suitable attachment element. The second grip fixture is preferably configured to apply a pressure load (see FIG. 5), such as a clamp load, across the second end (see FIG. 2H) of the test specimen (see FIGS. 2A, 2H).

[00083] The apparatus (see FIG. 2A) is configured for use with an optical strain measurement system (see FIG. 3A), discussed in detail below. When the test specimen (see FIGS. 2H, 3A) is

installed in the support assembly (see FIG. 2A), the test specimen (see FIGS. 2H, 3A) and the notch portion (see FIGS. 2H, 3A) are visible to the optical strain measurement system (see FIG. 3A) through the plurality of window portions (see FIG. 2A).

[00084] In another embodiment of the disclosure, there is provided a system for compression testing. FIG. 5 is an illustration of a block diagram of an embodiment of the system for compression testing that includes the apparatus for compression testing discussed above. FIG. 3A is an illustration of a schematic diagram of an exemplary embodiment of the system for compression testing of the disclosure.

[00085] As shown in FIGS. 3A and 5, the system comprises the apparatus for compression testing. The apparatus may be in the form of a test fixture (see FIG. 3A). As discussed in detail above, the apparatus (see FIGS. 3A, 5) comprises a base assembly (see FIG. 5) having an end load element (see FIG. 5) attached to the base assembly (see FIG. 5). The apparatus (see FIG. 5) further comprises a support assembly (see FIG. 5) attached to the base assembly (see FIG. 5). The support assembly has a plurality of window portions (see FIG. 5).

[00086] The apparatus (see FIG. 5) further comprises a core assembly (see FIG. 5) installed within the support assembly (see FIG. 5). The core assembly is preferably crushable and designed to absorb fracture load energy upon fracture or breaking of the test specimen (see FIGS. 2A, 2H), such as at the notch portion (see FIG. 2H). The core assembly (see FIG. 5) and the test specimen (see FIG. 5) are preferably installed between the first support grid (see FIG. 5) and the second support grid (see FIG. 5).

[00087] As shown in FIGS. 2H, 3A and 5, the system further comprises a test specimen having a notch portion. FIG. 2H is an illustration of a front perspective view of the test specimen used in the apparatus of FIG. 2A. The test specimen (see FIG. 2H) is preferably installed in the support assembly (see FIG. 5) of the apparatus (see FIG. 5). As shown in FIGS. 3A and 3C, the test specimen, is in an installed position in the apparatus and in the testing machine.

[00088] As shown in FIG. 2H, the test specimen may be in the form of a test panel. The test panel may, for example, comprise a panel (see FIG. 7), or part of a panel, of an aircraft (see FIG. 7). The test specimen, such as in the form of test panel, may be made of a composite material, or a metal material, such as aluminum or another suitable metal material. The test specimen may also be in the form of a coupon, e.g., a flat piece of laminate, or another suitable test specimen

preferably having a rectangular plan configuration and a rectangular cross section. The test specimen, such as in the form of test panel, may preferably have a width of about twenty (20) inches wide, a length of about sixty (60) inches, and a thickness of about 0.25 inch to about 0.10 inch thick. However, the test specimen may also be of another suitable width, length, or thickness, depending on the testing conditions and testing machines used.

[00089] As shown in FIG. 2H, the test specimen has a first end that is preferably adjacent the base assembly (see FIG. 2I) when the test specimen is installed in the apparatus (see FIG. 2A). As shown in FIG. 2H, the test specimen has a second end that is preferably attached to the grip fixture, such as in the form of the second grip fixture, discussed above.

[00090] As shown in FIG. 2H, the notch portion of the test specimen is formed at a location in the test specimen, preferably a central location. The notch portion (see FIG. 3C) is preferably perpendicular to a direction (see FIG. 3C) of the one or more compression loads (see FIG. 5) applied by the testing machine (see FIG. 3C) to the test specimen (see FIG. 3C). The notch portion may preferably have a width of about four (4) inches wide and a thickness of about 0.25 inch to about 0.10 inch thick. However, the notch portion may be of another suitable width or thickness depending on the testing conditions.

[00091] FIG. 2I is an illustration of a front perspective view of the test specimen of FIG. 2H installed in front of the core assembly (see FIG. 2G) and installed on the base assembly of FIG. 2E. As shown in FIG. 2I, the test specimen is installed over the core assembly (see FIG. 2G), such as in the form of honeycomb sandwich core assembly, and over the second support grid.

[00092] As shown in FIGS. 3A, 3C and 5, the system further comprises a testing machine, such as in the form of a compression machine. FIG. 3C is an illustration of a front perspective view of the apparatus of FIG. 2A installed in an exemplary embodiment of the testing machine, such as in the form of compression machine, that may be used in the system of FIG. 3A. The compression machine may comprise, for example, an MTS machine manufactured by MTS Corporation of Minneapolis, Minnesota. However, other suitable testing machines may be used.

[00093] As shown in FIGS. 3A and 3C, the testing machine, such as in the form of compression machine, comprises an upper platen, a lower platen, a frame, a load cell (see FIG. 3A), and feet (see FIG. 3C). The upper platen and the lower platen may be movable between a closed position as shown in FIG. 3A and an open position as shown in FIG. 3C.

[00094] FIG. 2J is an illustration of a front perspective view of the apparatus of FIG. 2A showing use with load leveling devices. As shown in FIG. 2J, a first load leveling device may be coupled to the second grip fixture by coupling the first load leveling device in a downward direction indicated by arrow to the second grip fixture. Alternatively, the first load leveling device (see FIG. 3B) may be used in place of the second grip fixture (see FIG. 2A) and coupled to the second end (see FIG. 2H) of the test specimen (see FIG. 2H).

[00095] As further shown in FIG. 2J, a second load leveling device may be coupled to the base assembly by coupling the second load leveling device in an upward direction indicated by arrow to the base assembly. Alternatively, the second load leveling device may be coupled to the first grip fixture, or the second load leveling device may be used in place of the first grip fixture and coupled to the first end (see FIG. 2H) of the test specimen (see FIG. 2H).

[00096] As shown in FIG. 3A, the one or more load leveling devices may be coupled to the apparatus installed in the testing machine. The load leveling devices preferably assist in self-alignment, self-balancing or self-leveling of the test specimen and the apparatus. In one embodiment, as shown in FIG. 3A, the arrangement may comprise the upper platen of the testing machine, the first load leveling device, the test fixture, the second load leveling device, and the lower platen of the testing machine.

[00097] As shown in FIG. 3A, a first load leveling device may be coupled to the top of the apparatus, such as in the form of test fixture (see FIG. 3A). Alternatively, the first load leveling device (see FIG. 3B) may be used in place of the second grip fixture (see FIG. 2A). The first load leveling device (see FIG. 3B) may be coupled or attached to the first one to two inches of the second end (see FIG. 2H) of the test specimen to keep the loaded edge of the test specimen from brooming or spreading out when compression loads (see FIG. 5) are applied to the test specimen during compression testing.

[00098] Alternatively, or in addition, to the first load leveling device, a second load leveling device may be coupled to the bottom of the apparatus, or alternatively, the second load leveling device may be coupled to the first grip fixture (see FIG. 2A) or used in place of the first grip fixture (see FIG. 2A). The load leveling devices balance the load to ensure the first end (see FIG. 2H) and second end (see FIG. 2H) of the test specimen (see FIG. 2H) are loaded at any point along the long end of the test specimen (see FIG. 2H). The load leveling devices help to

prevent or minimize the loaded edges of the test specimen from brooming or spreading out when loaded in compression during compression testing.

[00099] FIG. 3B is an illustration of a front perspective view of an exemplary embodiment of the load leveling device, such as in the form of first load leveling device, that may be used in the system of FIG. 3A. The first load leveling device may be used in place of second grip fixture (see FIG. 2A). As shown in FIG. 3B, the load leveling device comprises an alignment portion having a slot for insertion of the test specimen (see FIG. 3A). As further shown in FIG. 3B, the load leveling device may comprise openings configured for receiving attachment elements (not shown), such as screws (not shown), that may be used to clamp down on the test specimen (see FIG. 3A).

[000100] As further shown in FIG. 3B, the load leveling device may comprise one or more round elements that may allow the attachment elements (not shown) to move or float up and down. Such movement may facilitate self-alignment, self-balancing or self-leveling of the test specimen and the apparatus. As further shown in FIG. 3B, the load leveling device, such as in the form of first load leveling device, may comprise link members that assist in holding the load leveling device together during compression testing.

[000101] As shown in FIG. 3C, the testing machine, such as in the form of compression machine, is preferably configured to apply one or more compression loads (see FIG. 5) to the test specimen, in direction, when the apparatus with the test specimen is installed in the testing machine. As shown in FIG. 3C, the notch portion of the test specimen is visible.

[000102] As shown in FIGS. 3A and 5, the system further comprises a testing machine controller coupled to the testing machine and configured to control operation of the testing machine. The testing machine controller may be coupled to the testing machine by a connection element, such as a suitable wired or wireless connection.

[000103] As shown in FIGS. 3A and 5, the system may further comprise a processing unit, such as a first processing unit, coupled to the testing machine controller via a connection element. The connection element may comprise a suitable wired or wireless connection. As shown in FIGS. 3A and 5, the processing unit may comprise a computer, such as a first computer.

[000104] As shown in FIGS. 3A and 5, the system further comprises an optical strain measurement system positioned in relation to the apparatus with the test specimen installed in the apparatus and the apparatus installed in the testing machine. As shown in FIG. 3A, the apparatus with the test specimen is preferably installed in the testing machine, so that the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions (see FIG. 4C-4D). The first support grid (see FIG. 3C) of the apparatus (see FIG. 3A) preferably faces front toward the optical strain measurement system (see FIG. 3A).

[000105] The optical strain measurement system (see FIGS. 3A, 4A-4B) preferably comprises two or more optical devices (see FIGS. 4A-4B). The optical devices may comprise a first optical device (see FIG. 4A) and a second optical device (see FIG. 4A).

[000106] The optical strain measurement system is preferably a camera based system in which the optical devices are in the form of cameras (see FIGS. 4A-4B). The cameras monitor and track a plurality of locations (see FIGS. 4A-4B), such as in the form of dots or points, on the surface of the test specimen (see FIGS. 4A-4B). The cameras may comprise a first camera (see FIG. 4A) and a second camera (see FIG. 4A). However, other suitable optical devices may be used.

[000107] The optical strain measurement system preferably comprises two or more optical devices configured to both capture and scan optical measurements (see FIGS. 3A, 4A-4B) at a plurality of locations (see FIGS. 4A-4B) on the surface of the test specimen (see FIGS. 4A-4B) installed in the apparatus (see FIG. 4A). An example of an optical strain measurement system that may be used includes the Aramis Optical 3D Deformation Analysis optical strain measurement system obtained from GOM mbH of Germany. However, other suitable optical strain measurement systems may also be used.

[000108] The optical strain measurement system may be used to determine material properties of a test specimen (see FIG. 2H), may be used to obtain strain data<sup>7</sup> (see FIG. 5), such as for example, surface strain values, buckling strain, and strain rates, may be used to obtain three-dimensional displacements and surface coordinates, and may be used to obtain other suitable data. The optical strain measurement system may be used to capture and evaluate the measuring area efficiently and with good accuracy. Suitable software may be used with the optical strain

measurement system to provide results for optical measurements (see FIGS. 3A, 4A-4B) at a plurality of locations (see FIGS. 4A-4B) on the surface of the test specimen (see FIGS. 4A-4B).

[000109] FIG. 4A is an illustration of a side view of an exemplary embodiment of an optical strain measurement system that may be used in the system of FIG. 3A. FIG. 4A shows the optical strain measurement system positioned in front of the apparatus. As shown in FIG. 4A, the first optical device, such as in the form of a first camera, is positioned in front of the upper half of the first support grid of the apparatus. As further shown in FIG. 4A, the first optical device, such as in the form of first camera, is positioned to capture and scan optical measurements, such as upper horizontal optical measurements at a plurality of locations (see FIG. 4A) on the surface of the test specimen (see FIG. 4A) installed in the apparatus.

[000110] As further shown in FIG. 4A, the second optical device, such as in the form of a second camera, is positioned in front of the lower half of the first support grid of the apparatus. As shown in FIG. 4A, the second optical device, such as in the form of the second camera, is positioned to capture and scan optical measurements, such as lower horizontal optical measurements, at a plurality of locations (see FIG. 4A) on the surface of the test specimen (see FIG. 4A) installed in the apparatus.

[000111] As shown in FIG. 4A, the first camera is preferably above a centerline between the first camera and the second camera. The second camera is preferably below the centerline. The first camera and the second camera may be positioned a sufficient distance from the test specimen (see FIG. 3A) installed in the apparatus. Preferably, the first camera and the second camera may be positioned a distance (see FIG. 4B) of about ten (10) feet from the apparatus. However, the first camera and the second camera may be positioned a longer or shorter distance from the apparatus.

[000112] FIG. 4A shows the first camera positioned a distance above the second camera. Preferably, the first camera may be positioned about 15 inches above the centerline between the first camera and the second camera. Preferably, the second camera may be positioned about 15 inches below the centerline between the first camera and the second camera. However, the first camera and the second camera may be positioned a longer or shorter distance above or below the centerline.



[000113] FIG. 4B is an illustration of a top view of the optical strain measurement system of FIG. 4A positioned in front of the first support grid of the apparatus. As shown in FIG. 4B, the optical device comprising first optical device, such as in the form of camera, is positioned in front of the upper half of the first support grid of the apparatus. As further shown in FIG. 4B, the first optical device, such as in the form of camera, is positioned to capture and scan optical measurements, such as upper vertical optical measurements and lower vertical optical measurements, at a plurality of locations (see FIG. 4B) on the surface of the test specimen (see FIG. 4B) installed in the apparatus.

[000114] FIG. 4C is an illustration of a front perspective view of the apparatus of FIG. 4A showing optical devices, such as in the form of first optical device and second optical device, of the optical strain measurement system of FIG. 4A. The optical devices, preferably in the form of cameras (see FIGS. 4A-4B), are preferably focused on the test specimen0, such as in the form of test panel.

[000115] FIG. 4C shows that a load balance, such as in the form of a load balance indicated by an upper dotted circle, is viewed and measured with the first optical device, such as first camera (see FIG. 4A) or upper camera. FIG. 4C further shows that a load balance, such as in the form of a load balance indicated by a lower dotted circle, is viewed and measured with the second optical device, such as second camera (see FIG. 4A) or lower camera.

[000116] FIG. 4C shows that a load balance, such as in the form of a load balance indicated by a middle dotted circle, is viewed and measured with both the first optical device, such as first camera (see FIG. 4A) or upper camera, and the second optical device, such as second camera 124b (see FIG. 4A) or lower camera,. As shown in FIG. 4C, the notch portion is within the load balance indicated by middle dotted circle.

[000117] FIG. 4D is an illustration of a close-up, front perspective view of the support grid, such as in the form of first support grid, of the apparatus0. FIG. 4D shows the test specimen, such as in the form of test panel, and the notch portion at location, visible through the window portions. As shown in FIG. 4D, the notch portion is positioned centrally between vertical members and horizontal members.

[000118] As shown in FIGS. 3A and 5, the system further comprises a data acquisition system coupled to the optical strain measurement system via a connection element. The connection element may comprise a suitable wired or wireless connection.

[000119] As shown in FIGS. 3A and 5, the data acquisition system may comprise an optical strain measurement system controller and a processing unit, such as a second processing unit. As shown in FIGS. 3A and 5, the processing unit may comprise a computer, such as a second computer.

[000120] As shown in FIG. 3A, the strain measurement system controller may be coupled to the second processing unit via a connection element. The connection element may comprise a suitable wired or wireless connection.

[000121] The apparatus (see FIG. 5), the test specimen (see FIG. 5), the testing machine (see FIG. 5), the testing machine controller (see FIG. 5), the optical strain measurement system (see FIG. 5), and the data acquisition system (see FIG. 5) together comprise the system (see FIG. 5) for compression testing of the test specimen (see FIG. 5).

[000122] As shown in FIG. 5, the support assembly comprises a first support grid configured for attachment to a second support grid. The first support grid and the second support grid each comprise a frame portion, a plurality of vertical members, and a plurality of horizontal members. The plurality of vertical members (see FIG. 2A) and the plurality of horizontal members (see FIG. 2A) form the plurality of window portions (see FIG. 2A).

[000123] In another embodiment of the disclosure, there is provided a method (see FIG. 6) for compression testing of a test specimen (see FIG. 2H). FIG. 6 is an illustration of a flow diagram of an exemplary embodiment of the method of the disclosure. As shown in FIG. 6, the method comprises step of forming an apparatus (see FIG. 2A) for compression testing of the test specimen (see FIG. 2H).

[000124] As discussed in detail above, the apparatus (see FIG. 2A) comprises a base assembly (see FIG. 2A) having an end load element (see FIG. 2A) attached to the base assembly (see FIG. 2A). The base assembly (see FIG. 2A) is preferably rigid and sturdy.

[000125] The apparatus (see FIG. 2A) further comprises a support assembly (see FIG. 2A) attached to the base assembly (see FIG. 2A). The support assembly (see FIG. 2A) has a plurality of window portions (see FIG. 2A).

[000126] The apparatus further comprises a core assembly (see FIG. 2F) installed within the support assembly (see FIG. 2A). The core assembly (see FIG. 2F) is preferably crushable and configured to protect the support assembly and the base assembly from fracture loads (see FIG. 5) generated during compression testing. Such fracture loads (see FIG. 5) may be generated by a test specimen (see FIG. 2H) positioned adjacent to the core assembly (see FIGS. 2F, 2I), when the test specimen fractures or breaks during compression testing of the test specimen. The compression loads (see FIG. 5) that may occur during compression testing of the test specimen (see FIG. 2H) may be in a range of about 300 kips (kilopounds force) per square inch of force to about 500 kips (kilopounds force) per square inch of force. However, the compression loads may be higher or lower as suitable.

[000127] As shown in FIG. 6, the method further comprises step of forming a notch portion (see FIG. 2H) in a test specimen (see FIG. 2H). As shown in FIG. 6, the method further comprises step of installing the test specimen (see FIG. 2H) within the support assembly (see FIG. 2A) and adjacent to the core assembly (see FIGS. 2F, 2I).

[000128] As shown in FIG. 6, the method further comprises step of installing the apparatus (see FIG. 2A) in a testing machine (see FIG. 3A), such as a compression machine, for compression testing. The step of installing the apparatus (see FIG. 2A) in the testing machine (see FIG. 3A) may comprise coupling one or more load leveling devices (see FIG. 3A) to the apparatus (see FIG. 3A).

[000129] As shown in FIG. 6, the method further comprises step of positioning an optical strain measurement system (see FIG. 3A) in relation to the apparatus (see FIG. 3A). The optical strain measurement system (see FIG. 3A) is positioned so that the test specimen (see FIG. 3A) and the notch portion (see FIG. 3A) are visible to the optical strain measurement system (see FIG. 3A) through the plurality of window portions (see FIG. 4C).

[000130] As shown in FIG. 6, the method further comprises step of applying one or more compression loads (see FIG. 5) to the test specimen (see FIG. 3C) in directions (see FIG. 3C). The one or more compression loads (see FIG. 3C) are preferably applied to the test specimen

(see FIG. 3C) via the upper platen (see FIG. 3C) and the lower platen (see FIG. 3C) of the testing machine, such as in the form of compression machine.

[000131] As shown in FIG. 6, the method further comprises step of measuring strain data (see FIG. 5) of the test specimen (see FIG. 3A) with the optical strain measurement system (see FIG. 3A). The step of measuring the strain data comprises using two or more optical devices (see FIGS. 4A-4B) to capture and scan optical measurements (see FIGS. 4A-4B) at a plurality of locations (see FIGS. 4A-4B) on the test specimen (see FIGS. 4A-4B).

[000132] The method may further comprise after step, the step of processing the strain data (see FIG. 5) with the data acquisition system (see FIG. 3A) to determine additional information relating to strain, such as buckling strain, or other material characteristics, of the test specimen 80 (see FIG. 3A). After the strain data (see FIG. 5) has been processed, if additional compression testing is conducted, the end load element (see FIG. 2A) may be removed and replaced on the base assembly (see FIG. 2A), if damaged. In addition, any damaged portions of the core assembly (see FIG. 2F) may be replaced on the core assembly (see FIG. 2F).

[000133] FIG. 7 is an illustration of a perspective view of an air vehicle, such as an aircraft, having one or more structures, such as in the form of a panel, that may be tested and evaluated with embodiments of the apparatus (see FIG. 2A), the system (see FIG. 5) and the method (see FIG. 6) of the disclosure, as discussed in detail above. As shown in FIG. 7, the air vehicle, such as in the form of aircraft, comprises a fuselage, a nose, a cockpit, wings, one or more propulsion units, and a tail comprising a vertical tail portion and horizontal tail portions.

[000134] Although the aircraft shown in FIG. 7 is generally representative of a commercial passenger aircraft having one or more structures, such as in the form of panel, the teachings of the disclosed embodiments may be applied to other passenger aircraft. For example, the teachings of the disclosed embodiments may be applied to cargo aircraft, military aircraft, rotorcraft, and other types of aircraft or aerial vehicles, as well as aerospace vehicles, satellites, space launch vehicles, rockets, and other aerospace vehicles.

[000135] FIG. 8 is an illustration of a flow diagram of an aircraft manufacturing and service method. FIG. 9 is an illustration of a functional block diagram of an embodiment of an aircraft of the disclosure. Referring to FIGS. 8-9, embodiments of the disclosure may be described in the

context of the aircraft manufacturing and service method as shown in FIG. 8, and the aircraft as shown in FIG. 9.

[000136] During pre-production, exemplary aircraft manufacturing and service method may include specification and design of the aircraft and material procurement. During manufacturing, component and subassembly manufacturing and system integration of the aircraft takes place. Thereafter, the aircraft may go through certification and delivery in order to be placed in service. While in service by a customer, the aircraft may be scheduled for routine maintenance and service (which may also include modification, reconfiguration, refurbishment, and other suitable services).

[000137] Each of the processes of the aircraft manufacturing and service method may be performed or carried out by a system integrator, a third party, and/or an operator (e.g., a customer). For the purposes of this description, a system integrator may include, without limitation, any number of aircraft manufacturers and major-system subcontractors. A third party may include, without limitation, any number of vendors, subcontractors, and suppliers. An operator may include an airline, leasing company, military entity, service organization, and other suitable operators.

[000138] As shown in FIG. 9, the aircraft produced by the exemplary aircraft manufacturing and service method may include an airframe with a plurality of systems and an interior. Examples of the plurality of systems may include one or more of a propulsion system, an electrical system, a hydraulic system, and an environmental system. Any number of other systems may be included. Although an aerospace example is shown, the principles of the disclosure may be applied to other industries, such as the automotive industry.

[000139] Methods and systems embodied herein may be employed during any one or more of the stages of the aircraft manufacturing and service method. For example, components or subassemblies corresponding to component and subassembly manufacturing may be fabricated or manufactured in a manner similar to components or subassemblies produced while the aircraft is in service. Also, one or more apparatus embodiments, method embodiments, or a combination thereof, may be utilized during component and subassembly manufacturing and system integration, for example, by substantially expediting assembly of or reducing the cost of the aircraft. Similarly, one or more of apparatus embodiments, method embodiments, or a

combination thereof, may be utilized while the aircraft is in service, for example and without limitation, to maintenance and service.

[000140] Disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6) enable testing to be performed on test specimens (see FIG. 2H), such as in the form of test panels (see FIG. 2H), at a much higher test rate than testing using certain existing test fixtures. This is due to the reduced time needed for test set-up and testing.

[000141] For example, test specimens (see FIG. 2H), such as in the form of test panels (see FIG. 2H), using disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6), may be tested at a test rate of ten (10) to twenty (20) or more test specimens per day. In contrast, test specimens (see FIG. 1) using an existing test fixture (see FIG. 1), for example, an existing large notch compression test fixture (see FIG. 1), may typically be tested at a test rate of only one (1) to two (2) test specimen panels (see FIG. 1) per day.

[000142] Further, disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6), do not require the use and installation of strain gages (see FIG. 1) for testing. This reduces the labor, installation, and flow time required for testing. This, in turn, may result in an overall reduction in the time and expense of testing. Such reduction in the time and expense of testing may preferably be reduced by as much as ten (10) to twenty (20) times, as compared to the time and expense of testing using an existing test fixture (see FIG. 1), for example, existing large notch compression test fixture (see FIG. 1).

[000143] Moreover, disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6), may be used with an optical strain measurement system (see FIGS. 3A, 4A), due to the see-through configuration of the support grids (see FIG. 2A) of the apparatus (see FIG. 2A) used for the testing. In contrast, existing test fixture (see FIG. 1), for example, existing large notch compression test fixture (see FIG. 1), cannot use the optical strain measurement system (see FIGS. 3A, 4A). This is because the first support plate (see FIG. 1) and second support plate (see FIG. 1) of the existing large notch compression test fixture completely cover and obstruct any view of the test specimen panel (see FIG. 1).

[000144] In addition, disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6), utilize a base platform (see FIG. 2A) that is rigid and crushable, and utilize an end load element (see FIG. 2A) mounted on the base assembly (see

FIG. 2A). The end load element (see FIG. 2A) may be replaced after one or more compression tests and is designed to protect the base assembly (see FIG. 2A) during compression testing.

[000145] Thus, the base assembly is designed to withstand wear and tear over numerous compression tests, as compared to base structures of certain existing test fixtures. For example, the base portion (see FIG. 1) of existing test fixture (see FIG. 1), such as existing large notch compression test fixture (see FIG. 1), may be thin and wear out quickly after several compression tests.

[000146] Moreover, disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6), utilize a base platform (see FIG. 2A) that does not require shimming to reinforce the base platform. This may result in reduced time and expense to install the shimming for each test. In contrast, for example, the base portion (see FIG. 1) of an existing test fixture, such as existing large notch compression test fixture (see FIG. 1), may require the use of shims (see FIG. 1) to reinforce the base portion (see FIG. 1).

[000147] Finally, disclosed embodiments of the apparatus (see FIG. 2A), system (see FIGS. 3A, 5), and method (see FIG. 6), utilize one or more load leveling devices (see FIG. 3B) that may be used to self-level or self-balance the load during compression testing of the test specimen (see FIG. 2H).

[000148] Many modifications and other embodiments of the disclosure will come to mind to one skilled in the art to which this disclosure pertains having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. The embodiments described herein are meant to be illustrative and are not intended to be limiting or exhaustive. Although specific terms are employed herein, they are used in a generic and descriptive sense only and not for purposes of limitation.

[000149] The disclosure also describes embodiments according to the following clauses:

[000150] Clause 1. An apparatus for compression testing, the apparatus comprising:

a base assembly having an end load element attached to the base assembly, the base assembly being rigid;

a support assembly attached to the base assembly, the support assembly having a plurality of window portions; and,

a core assembly installed within the support assembly, the core assembly being crushable and configured to protect the support assembly and the base assembly from fracture loads generated during compression testing;

the base assembly, the support assembly, and the core assembly together comprising an apparatus for compression testing of a test specimen having a notch portion, the apparatus configured for use with an optical strain measurement system, wherein when the test specimen is installed in the support assembly the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions.

[000151] Clause 2. The apparatus of clause 1 wherein the support assembly comprises a first support grid configured for attachment to a second support grid, the core assembly and the test specimen being installed between the first support grid and the second support grid.

[000152] Clause 3. The apparatus of clause 2 wherein the first support grid and the second support grid each comprise a frame portion, a plurality of vertical members, and a plurality of horizontal members, the plurality of vertical members and horizontal members forming the plurality of window portions.

[000153] Clause 4. The apparatus of clause 1 wherein the core assembly comprises a plurality of vertical core elements, each vertical core element comprising a honeycomb sandwich core assembly.

[000154] Clause 5. The apparatus of clause 1 wherein the core assembly has a crush zone corresponding to a location of the notch portion in the test specimen when the test specimen is installed in the support assembly.

[000155] Clause 6. The apparatus of clause 1 further comprising a first grip fixture and a second grip fixture, the first grip fixture coupled to the base assembly and configured to hold a first end of the test specimen when the test specimen is installed in the support assembly, and the second grip fixture attached to a second end of the test specimen and configured to apply a pressure load across the second end of the test specimen.

[000156] Clause 7. The apparatus of clause 1 wherein the end load element comprises an end load wear strip that is removable, replaceable and configured to protect the base assembly during compression testing.



[000157] Clause 8. A system for compression testing, the system comprising:

an apparatus comprising:

a base assembly having an end load element attached to the base assembly, the base assembly being rigid;

a support assembly attached to the base assembly, the support assembly having a plurality of window portions; and,

a core assembly installed within the support assembly, the core assembly being crushable and configured to protect the support assembly and the base assembly from fracture loads generated during compression testing;

a test specimen having a notch portion, the test specimen installed in the support assembly of the apparatus;

a testing machine configured to apply one or more compression loads to the test specimen when the apparatus with the test specimen is installed in the testing machine;

a testing machine controller coupled to the testing machine and configured to control operation of the testing machine;

an optical strain measurement system positioned in relation to the apparatus with the test specimen installed in the testing machine, so that the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions; and,

a data acquisition system coupled to the optical strain measurement system,

the apparatus, the test specimen, the testing machine, the testing machine controller, the optical strain measurement system, and the data acquisition system together comprising a system for compression testing of the test specimen.

[000158] Clause 9. The system of clause 8 further comprising one or more load leveling devices coupled to the apparatus installed in the testing machine.

[000159] Clause 10. The system of clause 8 wherein the support assembly comprises a first support grid configured for attachment to a second support grid, the first support grid and the second support grid each comprising a frame portion, a plurality of vertical members, and a plurality of horizontal members, the plurality of vertical members and horizontal members forming the plurality of window portions.

[000160] Clause 11. The system of clause 8 wherein the core assembly has a crush zone corresponding to a location of the notch portion in the test specimen when the test specimen is installed in the support assembly of the apparatus.

[000161] Clause 12. The system of clause 8 wherein the test specimen comprises a test panel of an aircraft.

[000162] Clause 13. The system of clause 8 wherein the notch portion of the test specimen is perpendicular to a direction of the one or more compression loads applied by the testing machine to the test specimen.

[000163] Clause 14. The system of clause 8 wherein the optical strain measurement system comprises two or more optical devices configured to both capture and scan optical measurements at a plurality of locations on the test specimen.

[000164] Clause 15. The system of clause 8 further comprising a first processing unit coupled to the testing machine controller and a second processing unit of the data acquisition system, the second processing unit coupled to an optical strain measurement system controller of the data acquisition system.

[000165] Clause 16. A method for compression testing, the method comprising the steps of:  
forming an apparatus for compression testing of a test specimen, the apparatus comprising:

a base assembly having an end load element attached to the base assembly, the base assembly being rigid;

a support assembly attached to the base assembly, the support assembly having a plurality of window portions; and,

a core assembly installed within the support assembly, the core assembly being crushable and configured to protect the support assembly and the base assembly from fracture loads generated during compression testing;

forming a notch portion in a test specimen;

installing the test specimen within the support assembly and adjacent to the core assembly;

installing the apparatus in a testing machine for compression testing;

positioning an optical strain measurement system in relation to the apparatus, so that the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions;

applying one or more compression loads to the test specimen; and,

measuring strain data of the test specimen with the optical strain measurement system.

[000166] Clause 17. The method of clause 16 further comprising after the strain data measuring step, the step of processing the strain data with a data acquisition system.

[000167] Clause 18. The method of clause 17 further comprising after the step of processing the strain data, the step of replacing the end load element if damaged and replacing any damaged portions of the core assembly.

[000168] Clause 19. The method of clause 16 wherein the step of installing the apparatus in the testing machine comprises coupling one or more load leveling devices to the apparatus.

[000169] Clause 20. The method of clause 16 wherein the strain data measuring step comprises using two or more optical devices to capture and scan optical measurements at a plurality of locations on the test specimen.

## CLAIMS

1. An apparatus for compression testing of a test specimen having a notch portion, the apparatus comprising:

a base assembly and an end load element attached to the base assembly, the base assembly being rigid;

a support assembly attached to the base assembly, the support assembly comprising a first support grid and a second support grid, wherein the first support grid and the second support grid each comprise a frame portion and a grid portion, which grid portion comprises a plurality of vertical members and a plurality of horizontal members that intersect the plurality of vertical members to form a plurality of window portions,

the first support grid configured for attachment to the second support grid, and the first support grid and the second support grid configured to have a core assembly and the test specimen installed between them; and

a core assembly installed within the support assembly, the core assembly being crushable and configured to stabilize the test specimen and protect the support assembly and the base assembly from fracture loads generated by the test specimen adjacent the core assembly during compression testing by absorbing energy that is released sideways from the test specimen upon fracture or breaking of the test specimen;

the apparatus being configured for use with an optical strain measurement system, wherein the window portions are configured such that the test specimen and the notch portion are visible to said optical strain measurement system through the plurality of window portions when the test specimen is installed in the support assembly.

2. The apparatus of claim 1 wherein the core assembly comprises a plurality of vertical core elements, each vertical core element comprising a honeycomb sandwich core assembly.

3. The apparatus of claim 1 wherein the core assembly has a crush zone configured to correspond to a location of the notch portion in the test specimen when the test specimen is installed in the support assembly adjacent the core assembly.

4. The apparatus of claim 1 further comprising a first grip fixture and a second grip fixture, the first grip fixture coupled to the base assembly and configured to hold a first end of the test specimen when the test specimen is installed in the support assembly, and the second grip fixture configured to be attached to a second end of the test specimen and configured to apply a

pressure load across the second end of the test specimen.

5. The apparatus of claim 1 wherein the end load element comprises an end load wear strip that is removable, replaceable and configured to protect the base assembly during compression testing.
6. A system for compression testing, the system comprising:
  - the apparatus of claim 1;
  - a testing machine configured to apply one or more compression loads to the test specimen when the apparatus with the test specimen is installed in the testing machine;
  - a testing machine controller coupled to the testing machine and configured to control operation of the testing machine;
  - an optical stain measurement system; and
  - a data acquisition system configured to be coupled to the optical strain measurement system.
7. The system of claim 6 further comprising one or more load levelling devices coupled to the apparatus installed in the testing machine.
8. The system of claim 6 wherein the support assembly comprises a first support grid configured for attachment to a second support grid, the first support grid and the second support grid each comprising a frame portion, a plurality of vertical members, and a plurality of horizontal members, the plurality of vertical members and horizontal members forming the plurality of window portions.
9. The system of claim 6 wherein the core assembly has a crush zone corresponding to a location of the notch portion in the test specimen when the test specimen is installed in the support assembly of the apparatus.
10. A method for compression testing, the method comprising the steps of:
  - forming an apparatus for compression testing of a test specimen, the apparatus comprising:
    - a base assembly having an end load element attached to the base assembly, the base assembly being rigid;
    - a support assembly attached to the base assembly, the support assembly having a plurality of window portions; and,

a core assembly installed within the support assembly, the core assembly being crushable and configured to protect the support assembly and the base assembly from fracture loads generated during compression testing;

forming a notch portion in a test specimen;

installing the test specimen within the support assembly and adjacent to the core assembly;

installing the apparatus in a testing machine for compression testing;

positioning an optical strain measurement system in relation to the apparatus, so that the test specimen and the notch portion are visible to the optical strain measurement system through the plurality of window portions;

applying one or more compression loads to the test specimen; and,

measuring strain data of the test specimen with the optical strain measurement system.

11. The method of claim 10 further comprising after the strain data measuring step, the step of processing the strain data with a data acquisition system.

12. The method of claim 11 further comprising after the step of processing the strain data, the step of replacing the end load element if damaged and replacing any damaged portions of the core assembly.

13. The method of claim 10 wherein the step of installing the apparatus in the testing machine comprises coupling one or more load levelling devices to the apparatus.

14. The method of claim 10 wherein the strain data measuring step comprises using two or more optical devices to capture and scan optical measurements at a plurality of locations on the test specimen.

**The Boeing Company**  
**Patent Attorneys for the Applicant/Nominated Person**  
**SPRUSON & FERGUSON**






FIG. 2A






FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F







FIG. 2G



**FIG. 2H**




**FIG. 2I**



**FIG. 2J**







**FIG. 3B**




FIG. 3C




FIG. 4A




FIG. 4B




FIG. 4C









FIG. 5

**FIG. 6**




761





**FIG. 8**



**FIG. 9**