

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 December 2004 (09.12.2004)

PCT

(10) International Publication Number
WO 2004/106569 A1

(51) International Patent Classification⁷: C22C 14/00

(21) International Application Number:
PCT/US2004/011260

(22) International Filing Date: 27 April 2004 (27.04.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/443,047 22 May 2003 (22.05.2003) US

(71) Applicant (for all designated States except US): **TI-PRO, LLC** [US/US]; 1011 Industrial Road, Suite 5, Boulder City, NV 89005 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **BANIA, Paul, J.** [US/US]; 1533 Kay Court, Boulder City, NV 89005 (US).

(74) Agent: **GARRETT, Arthur, S.**; Finnegan, Henderson, Farabow, Garrett & Dunner L.L.P., 1300 I Street, N.W., Washington, DC 20005-3315 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 2004/106569 A1

(54) Title: HIGH STRENGTH TITANIUM ALLOY

(57) Abstract: An alpha-beta, titanium-base alloy with improved ductility at high strength levels compared to commercially available alloys, such as Ti-17. The alloy exhibits at least a 20% improvement in ductility at a given strength level compared to Ti-17. The alloy comprises, in weight %, 3.2 to 4.2 Al, 1.7 to 2.3 Sn, 2 to 2.6 Zr, 2.9 to 3.5 Cr, 2.3 to 2.9 Mo, 2 to 2.6 V, 0.25 to 0.75 Fe, 0.01 to 0.8 Si, 0.21 max. Oxygen and balance Ti and incidental impurities.

HIGH STRENGTH TITANIUM ALLOY

Background of the Invention:

Field of the Invention:

[001] The invention relates to an alpha-beta titanium-base alloy having an outstanding combination of tensile strength, including shear strength and ductility.

Description of the Prior Art:

[002] There have been numerous titanium alloys developed since the titanium industry started in earnest in the early 1950's. While these various alloy development efforts often had different goals for the end product alloy, some being developed with the intent of improving high temperature capability, some with improved corrosion resistance, and even some with improved forging/forming capabilities, perhaps the most common goal was simply tensile strength capability. In this case, tensile strength implies "useable" tensile strength, i.e., at an acceptable ductility level. Since strength and ductility vary inversely with each other, as is the case for virtually all hardenable metal systems, one usually has to make trade-offs between strength and ductility in order to obtain an alloy that is useful for engineering applications.

[003] Standard (uniaxial) tensile properties are usually described by four properties determined in a routine tensile test: yield strength (YS), ultimate tensile strength (UTS, commonly referred to simply as "tensile strength"), % Elongation (%EI) and % Reduction in Area (%RA). The first two values are usually reported in units such as 'ksi' (thousands of pounds per square inch) while the later two (both measures of ductility) are simply given in percentages.

[004] Another tensile property often cited, particularly in reference to fastener applications, is "double shear" strength, also reported in ksi. For this property, ductility is not determined, nor is a yield strength. In general, double shear strength of titanium alloys are approximately 60% of the uniaxial tensile strengths, as long as uniaxial ductility is sufficient.

[005] When attempting to make comparisons of tensile properties from different alloys heat treated to a range of tensile strength/ductility combinations, it is convenient to first analyze the data by regression analysis. The strength / ductility relationship can usually be described by a straight-line x-y plot wherein the ductility (expressed as either %El or %RA) is the dependent variable and the strength (usually UTS) is the independent variable. Such a line can be described by the simple equation:

[006]

Eqn 1: %RA = b - m(UTS); where m = the slope of the straight line and b is the intercept at zero strength. [Note: When determining such an equation by regression analysis, a parameter referred to as "r-squared" is also calculated, it varies between zero and one - with a value of one indicating a perfect fit with the straight line equation and a value of zero indicating no fit].

[007] Once such an equation is established, it can be used, for example, to compare 'calculated' ductilities at a constant strength level, even if there is no specific data at that strength level. This methodology has been used throughout this development effort in order to rank and compare alloys.

[008] It should also be noted that when conducting an alloy development project, it is important to recognize that tensile strength/ductility relationships are significantly affected by the amount of hot-work that can be imparted to the metal during conversion from melted ingot to wrought mill product (such as bar). This is due to the fact that macrostructure refinement occurs during ingot conversion to mill product and the greater the macrostructure refinement the better the strength/ductility relationships. It is thus well understood by those skilled in the art that tensile strength/ductility relationships of small lab heats are significantly below those obtained from full sized production heats due to the rather limited

amount of macrostructure refinement imparted to the small laboratory size heats compared to full-sized production heats. Since it is a practical impossibility to make full-size heats and convert them to mill product in order to obtain tensile property comparisons, the accepted practice is to produce smaller lab-sized heats of both the experimental alloy formulations and an existing commercial alloy formulation and compare results on a one-to-one basis. The key is to choose a commercial alloy with exceptional properties. In the development program resulting in this invention, the commercial alloy designated as "Ti-17" (Ti-5Al - 2Sn - 2Zr - 4Cr - 4Mo) was chosen as the baseline commercial alloy against which the experimental alloys would be compared. This alloy was chosen because of the exceptional strength/ductility properties demonstrated by this alloy in bar form.

Table 1: Tensile and Shear Strength Data from a commercial high strength titanium alloy (Ti-17) processed to bar*

Alloy Chemistry (wt %)	Age (Deg F / HRS)	UTS (ksi)	YS (ksi)	%EI	%RA	Double Shear (ksi)	Double Shear as % of UTS	Avg Double Shear a % of UTS
Ti-17 (Ti-5Al-2Sn- 2Zr-4Cr-4Mo)	1100 / 8	182	183	12	44	114	62%	
"	"	183	184	14	39	118	64%	
"	"	189	190	11	36	113	59%	
"	"	190	192	13	41	111	58%	
"	1050 / 8	197	200	9	34	115	58%	
"	"	198	201	9	30	116	58%	
"	"	205	209	8	22	N/A	N/A	
"	"	205	209	8	28	N/A	N/A	
"	950 / 12	211	216	9	25	N/A	N/A	
"	"	212	217	9	29	N/A	N/A	

*Material solution treated at 1480F for 10 min followed by fan air cool

Regression Analysis:

%RA = 134.5 - 0.5080 (UTS)
r-sq = 0.79
%EL = 38.76 - 0.1427 (UTS)
r-sq = 0.69

%RA @ 195 UTS = 35.4
%EL @ 195 UTS = 10.9

%RA @ 215 UTS = 25.3
%EL @ 215 UTS = 8.1

[009] Table 1 provides tensile and double shear property data for Ti-17 0.375 inch diameter bar product produced from a nominal 10,000 lb. full-sized commercial heat. The combinations of tensile strength, shear strength and ductility exhibited in this Table are clearly exceptional for any titanium alloy. Note also that the double shear strength values average very close to the 60% of UTS value cited earlier.

Summary of the Invention:

[010] The ultimate goal of this alloy development effort was to develop a heat treatable, alpha-beta, titanium alloy with improved ductility at high strength levels compared to heat treatable titanium alloys that are commercially available today, such as Ti-17. The goal could be further defined as such: to develop an alloy that exhibits at least a 20% improvement in ductility at a given elevated strength level compared to Ti-17.

[011] While there would be significant utility for a titanium alloy with the tensile properties noted above, there would be even more utility if such an alloy could also exhibit a minimum double shear strength of at least 110 ksi. It is well known that heat treated titanium (specifically Ti-6Al-4V) is used for aerospace fasteners heat treated to a guaranteed (i.e., "minimum") shear strength of 95 ksi. The next shear strength level employed by the aerospace industry is 110 ksi minimum, a level that is not achieved with any commercially available titanium alloy but is achieved with various steel alloys. Thus, in order for titanium to offer a nominal 40% weight savings by replacing steel with titanium in a high strength aerospace fastener, the titanium alloy must exhibit a minimum double shear strength of 110 ksi. In order to do so, considering the typical scatter associated with such tests, the typical values should be at least approximately 117 ksi. With the aforementioned correlation that titanium alloys exhibit a double shear strength that is typically about 60% of the tensile strength, in order to produce a double shear strength range of at least 117 ksi (to support a 110 ksi min.), one would expect this to require a tensile strength of at least 195 ksi. (hence, in the range of 195 ksi to about 215 ksi) with "acceptable ductility". Thus, the program had a secondary goal

of not only exhibiting the tensile properties noted above, but also accompanying double shear strength values to support a 110 ksi min. shear strength goal.

[012] In accordance with the invention, there is provided an alpha-beta, titanium-base alloy having a combination of high strength and ductility and exhibiting at least a 20% improvement in ductility at a given strength level compared to alloy Ti-17, as defined herein.

[013] More specifically, the alloy may exhibit a double shear strength of at least 110 ksi, as defined herein.

[014] The alloy may further exhibit a tensile strength of at least 195 ksi. More specifically, the tensile strength may be within the range of 195 to 215 ksi.

[015] The alpha-beta, titanium-base alloy in accordance with the invention comprises, in weight percent, 3.2 to 4.2 Al, 1.7 to 2.3 Sn, 2 to 2.6 Zr, 2.9 to 3.5 Cr, 2.3 to 2.9 Mo, 2 to 2.6 V, 0.25 to 0.75 Fe, 0.01 to 0.8 Si, 0.21 max. Oxygen and balance Ti and incidental impurities.

[016] More specifically in accordance with the invention, the alpha-beta, titanium-base alloy may comprise, in weight percent, about 3.7 Al, about 2 Sn, about 2.3 Zr, about 3.2 Cr, about 2.6 Mo, about 2.3 V, about 0.5 Fe, about 0.06 Si, about 0.18 max. Oxygen and balance Ti and incidental impurities.

[017] This alloy may exhibit a tensile strength of over 200 ksi and ductility in excess of 20% RA and double shear strength in excess of 110 ksi.

Description of the Preferred Embodiments and Specific Examples:

[018] All titanium alloys evaluated in this development effort were produced by double vacuum arc melting nominally 10-lb/4.5 inch diameter laboratory size ingots. All of these ingots were converted to bar product by the same process in order to minimize property scatter due to macrostructural and/or microstructural differences. The conversion practice employed was as follows:

[019] - Beta forge at 1800F to 1.75 inch square

[020] - Determine the beta transus

[021] - Alpha-beta roll from nominally 40F below each alloy's beta transus to 0.75 inch square bar.

[022] - Solution treat bar at a selected temperature in the range of nominally 80F to 150F below its beta transus followed by a fan air cool.

[023] - Age at various temperatures in order to produce a range of strength/ductility levels.

[024] - All material was determined to have a proper alpha-beta microstructure consisting of essentially equiaxed primary alpha in an aged beta matrix.

Table 2
First Iteration Heats - Chemistry and Beta Transus

Heat #	Al	Sn	Zr	Cr	Mo	V	Fe	Si	Oxygen	Beta Transus
V8226	5.05	1.93	2.09	4.04	4.00	0.00	0.22	0.014	0.110	1600
V8227	4.99	2.09	1.96	4.34	4.33	1.56	0.59	0.027	0.120	1570
V8228	3.79	1.90	2.32	3.30	2.61	2.43	0.48	0.032	0.164	1570
V8229	4.00	1.84	2.16	1.89	3.69	1.42	1.14	0.024	0.116	1600
V8230	3.85	1.93	2.17	2.50	3.96	1.50	1.20	0.025	0.181	1600
V8231	3.75	1.96	1.98	1.56	3.98	2.92	1.28	0.037	0.173	1570

* Chemistry in weight pct; beta transus in degrees F

[025] Table 2 provides a summary of the formulations that were produced in the first iteration of laboratory size heats. The baseline Ti-17 formulation is Heat V8226. Note that the Ti-17 baseline alloy has no vanadium addition; a low (less than 0.25%) iron addition; no intentional silicon addition (0.014 represents a typical "residual" level for titanium alloys for which no silicon is added); and an oxygen level in the range of 0.08-0.13, which conforms to common industry specifications concerning Ti-17.

[026] The remaining formulations cited in Table 2 are experimental alloys that incorporate additions/modifications relative to the Ti-17 baseline alloy. One of the primary additions is vanadium. This element is known to have significant solubility in the alpha phase (over 1%), thus it was added to specifically strengthen that phase of the resultant two-phase, alpha-beta alloy. This is an important addition since the other beta stabilizers in the Ti-17 alloy, Cr, Mo and Fe, have very limited solubility in the alpha phase. Other additions include iron and a higher oxygen level. Table 2 also shows the beta transus temperature of each formulation.

Table 3
First Iteration Tensile Results*

Heat	Age	YS (ksi)	UTS (ksi)	%EI	%RA
V8226	950/16	214	222	7	9
	"	212	220	5	12
	1000/12	209	237	6	13
		210	219	5	12
	1050/8	203	207	7	17
		198	205	6	15
	1100/8	191	197	10	29
		191	197	9	25
V8227	950/16	227	234	4	9
	"	230	239	5	15
	1000/12	222	222	6	15
		225	231	5	19
	1050/8	214	221	8	15
		213	220	6	12
	1100/8	205	211	9	21
		201	207	10	17
V8228	950/16	206	214	8	22
	"	207	213	9	23
	1000/12	197	205	10	26
		194	201	14	39
	1050/8	190	194	11	31
		189	192	13	44
	1100/8	180	182	13	40
		179	179	13	39
V8229	950/16	208	224	6	12
	"	209	218	7	11
	1000/12	205	209	8	17
		200	208	8	19
	1050/8	188	198	7	19
		187	199	11	26
	1100/8	176	188	11	41
		178	187	12	38
V8230	950/16	212	220	6	14
	"	212	219	9	20
	1000/12	204	211	11	26
		197	208	9	16
	1050/8	198	204	10	28
		195	202	9	23
	1100/8	182	191	10	25

Table 3
First Iteration Tensile Results*

Heat	Age	YS (ksi)	UTS (ksi)	%EI	%RA
V8231	950/16	187	194	12	38
	"	208	220	6	18
	"	208	220	8	15
	1000/12	200	207	9	23
	"	199	208	10	28
	1050/8	193	195	10	22
	"	191	199	11	33
	1100/8	184	189	11	36
	"	184	190	12	34

* All material solution treated 80 degrees F below beta transus and all aging treatments expressed in degrees F / hours

Table 4
Regression Analysis of First Iteration Tensile Results

Heat #	Equation	r-squared	Calculated %EI at 215 ksi UTS	Calculated %EI at 195 ksi UTS
V8226	%EI = 26.0 - 0.0897 UTS	0.46	6.7	8.5
V8227	%EI = 46.8 - 0.1802 UTS	0.84	8.1	11.1
V8228	%EI = 37.3 - 0.1313 UTS	0.60	9.1	11.7
V8229	%EI = 41.7 - 0.1635 UTS	0.64	6.5	9.2
V8230	%EI = 31.7 - 0.1078 UTS	0.42	8.5	10.7
V8231	%EI = 38.6 - 0.1425 UTS	0.81	8.0	10.8
Heat #	Equation	r-squared	Calculated %RA at 215 ksi UTS	Calculated %RA at 195 ksi UTS
V8226	%RA = 101.0 - 0.3966 UTS	0.62	15.7	23.7
V8227	%RA = 49.1 - 0.1513 UTS	0.20	16.5	19.6
V8228	%RA = 138.0 - 0.5315 UTS	0.66	23.7	34.6
V8229	%RA = 181.7 - 0.77089 UTS	0.85	13.5	29.8
V8230	%RA = 125.1 - 0.4915 UTS	0.48	19.4	28.6
V8231	%RA = 134.5 - 0.5325 UTS	0.71	20.0	30.7

[027] Table 3 summarizes the uniaxial tensile results obtained from the first iteration of experimental alloy formulations noted in Table 2 that were processed to bar and heat treated. Table 4 provides a regression analysis of the Table 3 data.

[028] The first item to note is a comparison of the tensile properties of the Ti-17 material cited in Table 3 (laboratory size Ti-17 heat) vs. those cited in Table 1 (production-sized Ti-17 heat). Note that the calculated %EI values of the lab-sized heat are 78% and 83% of those from the full sized heats at 195 ksi and 215 ksi respectively and the calculated %RA values are 67% and 62% at the same respective strengths. This data clearly confirms the significant drop-off of laboratory size heats vs. full-sized heats and reinforces the need to compare results from comparable sized heats.

[029] The results summarized in Table 4 show that Heat V8228 provided the best combination of ductilities at the strength levels of 195 ksi and 215 ksi, well above those of the Ti-17 baseline alloy. In fact, compared to the Ti-17 baseline alloy, Heat V8228's %EI values were 38% and 36% higher and the %RA values were 46% and 51% higher at the 195 and 215 ksi strength levels respectively, well above the goal of at least 20% improvement.

[030] Further examination of the Table 4 data show that in all but two cases the experimental alloys from Table 2 exhibited improved properties compared to the baseline Ti-17 alloy. Only the calculated %RA of Heat V8227 at 195 ksi and the %EI of V8229 at 215 ksi failed to show improvement over the Ti-17 baseline alloy. The following conclusions were drawn from these results:

[031] - Alloys with a vanadium addition fared better than the same alloy without vanadium. The benefit of the vanadium addition appeared to peak with an addition in the range of 2.4%.

[032] - Alloys with an elevated oxygen level performed better than those with a reduced oxygen level.

[033] - Iron additions beyond about 0.5% do not appear to offer any advantage

[034] - Lower aluminum levels - below about 4% - appear to be beneficial.

[035] - All of the experimental heats had a slightly higher silicon level compared to the baseline Ti-17 level (presumably because the vanadium master alloy carried along a minor silicon level). This slightly higher silicon level was not detrimental.

Table 5
First Iteration Heats - Chemistry and Beta Transus

Heat #	Al	Sn	Zr	Cr	Mo	V	Fe	Si	Oxygen	Beta Transus
V8247	3.65	1.96	2.39	3.23	2.55	2.37	0.50	0.035	0.167	1600
V8248	3.72	2.01	2.44	3.33	2.60	2.38	0.50	0.034	0.222	1610
V8249	3.62	1.94	2.31	3.16	2.50	2.36	0.53	0.069	0.208	1620
V8250	3.64	1.96	2.31	3.20	2.57	2.37	0.48	0.070	0.174	1590
V8251	3.13	1.97	2.48	3.17	2.52	2.35	0.48	0.035	0.164	1580
V8252	3.16	1.92	2.43	3.13	2.48	2.35	0.46	0.070	0.171	1580

* Chemistries in weight pct; beta transus in degrees F

[036] In light of the excellent properties obtained from the first iteration of heats, it was decided that an additional iteration would be desirable in order to refine the chemistry of the best alloy, i.e., Heat V8228. Table 5 summarizes this second iteration of experimental heats. The first Heat, V8247, is essentially a repeat of Heat H8228. This provides a measure of the repeatability of the results. The remaining second iteration heats provide the following modifications to the V8228/V8247 formulation:

[037] - Heat V8248 examines oxygen as high as 0.222 wt %, higher than any of the first iteration heats.

[038] - Heat V8249 evaluates higher oxygen (0.208%) in combination with higher silicon - double that of V8247.

[039] - Heat V8250 examines the higher silicon level alone, i.e., without the higher oxygen.

[040] - Heats V8251 and V8252 examine lower aluminum levels (about 0.5% less than V8547), in one case at the same silicon level (V8251) and another (V8252) at the higher silicon level.

Table 6
2nd Iteration Tensile Test Results*

Heat #	Age	YS (ksi)	UTS (ksi)	%EI	%RA
V8247	980/8	181	192	14	33
	"	185	196	12	28
	1040/8	174	182	16	39
	"	173	182	16	41
	1100/8	161	169	17	47
	"	161	169	19	43
	1160/8	152	162	18	50
	"	153	162	19	44
V8248	980/8	189	199	10	22
	"	189	200	12	30
	1040/8	179	188	13	38
	"	178	187	12	43
	1100/8	167	175	15	40
	"	165	173	14	38
	1160/8	155	163	16	43
	"	155	163	16	44
V8249	980/8	196	206	9	20
	"	202	211	8	23
	1040/8	186	195	12	34
	"	186	195	10	20
	1100/8	176	178	14	36
	"	174	182	12	27
	1160/8	161	170	15	31
	"	162	179	15	33
V8250	980/8	186	197	11	33
	"	185	196	13	36
	1040/8	180	189	13	31
	"	178	187	14	37
	1100/8	164	171	15	38
	"	165	173	15	37
	1160/8	155	163	16	40
	"	155	164	15	33
V8251	980/8	171	183	13	28
	"	173	184	14	33
	1040/8	170	179	14	37
	"	173	182	13	32
	1100/8	158	166	17	46
	"	158	167	14	41

Table 6
2nd Iteration Tensile Test Results*

Heat #	Age	YS (ksi)	UTS (ksi)	%EI	%RA
V8252	1160/8	149	158	18	47
	"	149	158	18	43
V8252	980/8	175	186	13	32
	"	176	190	10	27
V8252	1040/8	168	176	13	36
	"	165	174	13	35
V8252	1100/8	156	165	16	42
	"	152	160	17	39
V8252	1160/8	147	156	16	39
	"	147	157	18	40

* All material solution treated 80 degrees F below beta transus and all aging treatments expressed in degrees F./hours

Table 7
Regression Analysis of Second Iteration Tensile Results

Heat #	Equation	r-squared	Calculated %EI at 215 ksi UTS	Calculated %EI at 195 ksi UTS
V8247	%EI = 46.7 - 0.1719 UTS	0.88	9.7	13.2
V8248	%EI = 38.2 - 0.1364 UTS	0.88	8.9	11.6
V8249	%EI = 43.1 - 0.1659 UTS	0.94	7.4	10.7
V8250	%EI = 35.2 - 0.1170 UTS	0.89	10.0	12.4
V8251	%EI = 45.3 - 0.1755 UTS	0.81	7.6	11.1
V8252	%EI = 47.0 - 0.1906 UTS	0.87	6.0	9.8

Heat #	Equation	r-squared	Calculated %RA at 215 ksi UTS	Calculated %RA at 195 ksi UTS
V8247	%RA = 130.2 - 0.5047 UTS	0.87	21.1	31.3
V8248	%RA = 111.2 - 0.4084 UTS	0.62	23.4	31.5
V8249	%RA = 83.85 - 0.2952 UTS	0.68	20.4	26.3
V8250	%RA = 53.5 - 0.0993 UTS	0.21	32.1	34.1
V8251	%RA = 13639 - 0.5726 UTS	0.84	13.8	25.2
V8252	%RA = 93.7 - 0.3370 UTS	0.81	21.2	28.0

[041] The second iteration of laboratory size heats were processed as outlined earlier for the first iteration heats. Tensile tests were again performed and the results are summarized in Table 6. This data was analyzed by regression analysis and the results are provided in Table 7.

[042] Several conclusions can be drawn from Table 7. First, the correlation between the first iteration heat V8228 and its replicate V8247 is quite satisfactory. Secondly, it is also clear that the alloy can tolerate oxygen up to about 0.22% when the silicon level is low, but there is a minor drop-off at the higher silicon level when in combination with the higher oxygen level. The higher silicon level seems to offer no significant loss in properties as long as the oxygen level is in the intermediate range of about 0.17%. Finally, the lower aluminum levels (below about 3.2%) appear to be inferior to the higher levels suggesting that aluminum should be kept above the 3.2% level. They all have the intermediate aluminum level of 3.6%-3.7%, and all have silicon levels that are either low in combination with the highest oxygen or high or low in combination with the intermediate oxygen levels.

Table 8
Tensile and Double Shear Results from Selected Heats

Heat #	Solution Treat, F	Age F / hrs	YS (ksi)	UTS (ksi)	%EL	%RA	Double Shear (ksi)	Double Shear as % of UTS	Avg Double Shear as % of UTS
V8226	Beta - 110F	975/12	186	213	5	12	106	49.8%	53.4%
	"	"	193	202	9	17	107	53.0%	
	"	1050/18	188	196	10	24	106	54.1%	
	"	1050/8	182	189	12	33	107	56.6%	
V8228	Beta - 100F	975/12	197	207	9	19	112	54.1%	55.0%
	"	193	203	9	21	"	"	54.7%	
	"	1025/8	189	198	13	38	108	54.5%	
	"	"	189	198	9	35	112	56.6%	
V8247	Beta - 130F	975/12	191	202	12	31	110	54.5%	55.6%
	"	"	Invalid Test				"	56.1%	
	"	1025/8	189	198	13	38	"	56.1%	
	"	"	189	198	9	35	"	56.1%	
V8250	Beta - 150F	925/12	191	204	11	29	113	55.4%	55.9%
	"	"	191	204	12	32	116	56.9%	
	"	975/12	187	198	12	38	112	56.6%	
	"	"	188	199	11	37	109	54.8%	
V8250	Beta - 120F	975/12	203	213	8	16	112	52.6%	55.2%
	"	"	192	204	10	29	113	55.4%	
	"	1025/8	181	191	12	43	109	57.1%	
	"	"	183	192	13	40	107	55.7%	

Overall Avg: 55.0%

[043] As a final determination of the property capability of the alloys produced, four of the chemistries (the baseline Ti-17 heat V8226, the best of the first iteration, Heat V8228; the replicate of V8228, Heat V8247 and Heat V8250) were selected for double shear testing. Bars from each heat were solution treated at varying degrees below their respective beta transus values, fan air cooled, and then aged at various conditions aimed at producing strength levels in the targeted 195 ksi to 215 ksi range. These bars were then tested for routine uniaxial tension properties as well as double shear. The results are provided in Table 8.

[044] Several conclusions can be drawn from the data presented in Table 8. First, the double shear strength values of the laboratory size heats were in the range of 55% of their corresponding UTS values, with the Ti-17 baseline heat (V8226) exhibiting the lowest average at 53.4%. Since bar from the commercial Ti-17 heat

exhibited an average double shear strength of 59.8% of the UTS, we see an approximate 6.4 percentage point drop-off, slightly over 10% overall, associated with the laboratory vs. commercial heat. As noted earlier regarding ductility, this is not unexpected due to the lack of macrostructural refinement afforded by the small lab heats. It does however show that one could expect nominally 10% higher values from the laboratory size formulations if they were processed from larger commercial heats. Such an increase would put the laboratory heat data shown in Table 8 into the range of 117 ksi to 129 ksi double shear strength, sufficient to meet the 110 ksi minimum goal.

WHAT IS CLAIMED IS:

1. An alpha-beta, titanium-base alloy having a combination of high strength and ductility, said alloy exhibiting at least a 20% improvement in ductility at a given strength level compared to alloy Ti-17, as defined herein.
2. The alloy of claim 1 exhibiting a double shear strength of at least 110 ksi, as defined herein.
3. The alloy of claim 2, exhibiting a tensile strength of at least 195 ksi.
4. The alloy of claim 3, exhibiting a tensile strength of 195 to 215 ksi.
5. An alpha-beta, titanium-base alloy comprising, in weight percent, 3.2 to 4.2 Al, 1.7 to 2.3 Sn, 2 to 2.6 Zr, 2.9 to 3.5 Cr, 2.3 to 2.9 Mo, 2 to 2.6 V, 0.25 to 0.75 Fe, 0.01 to 0.8 Si, 0.21 max. Oxygen and balance Ti and incidental impurities.
6. The alloy of claim 5 exhibiting at least a 20% improvement in ductility at a given strength level compared to alloy Ti-17, as defined herein.
7. The alloy of claim 6 exhibiting a double shear strength of at least 110 ksi, as defined herein.
8. The alloy of claim 7 exhibiting a tensile strength of 195 to 215 ksi.
9. An alpha-beta, titanium-base alloy comprising, in weight percent, about 3.7 Al, about 2 Sn, about 2.3 Zr, about 3.2 Cr, about 2.6 Mo, about 2.3 V, about 0.5 Fe, about 0.06 Si, about 0.18 max. Oxygen and balance Ti and incidental impurities.
10. The alloy of claim 9 exhibiting tensile strength of over 200 ksi and ductility in excess of 20% RA and double shear strength in excess of 110 ksi.

INTERNATIONAL SEARCH REPORT

national Application No

PT/US2004/011260

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C22C14/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	M.J.DONACHIE JR: "Titanium A Technical Guide" 1988, ASM, METAL PARK, OHIO, US, XP002299937 page 449 - page 452 -----	1-5
A	SPIEKERMANN P: "LEGIERUNGEN - EIN BESONDERES PATENTRECHTLICHES PROBLEM? - LEGIERUNGSPRUEFUNG IM EUROPAEISCHEN PATENTAMT -" MITTEILUNGEN DER DEUTSCHEN PATENTANWAELTE, HEYMANN, KOLN, DE, 1993, pages 178-190, XP000961882 ISSN: 0026-6884 ----- -/-	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

8 October 2004

Date of mailing of the international search report

25/10/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, TX. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Gregg, N

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2004/011260

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	SPIEKERMANN P: "Alloys - a special problem of patent law" NONPUBLISHED ENGLISH TRANSLATION OF DOCUMENT ABOVE, 1993, pages 1-20, XP002184689 -----	