

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 June 2008 (12.06.2008)

PCT

(10) International Publication Number
WO 2008/069333 A1

(51) International Patent Classification:
C08G 59/40 (2006.01)

(21) International Application Number:
PCT/JP2007/073736

(22) International Filing Date:
3 December 2007 (03.12.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2006-327219 4 December 2006 (04.12.2006) JP

(71) Applicant (for all designated States except US): **DOW CORNING TORAY CO., LTD.** [JP/JP]; 1-3, Marunouchi 1-chome, Chiyoda-ku, Tokyo, 1000005 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MORITA, Yoshit-sugu** [JP/JP]; c/o Dow Corning Toray Co., Ltd., 2-2, Chigusaigaigan, Ichihara-shi, Chiba, 2990108 (JP). **UEKI, Hiroshi** [JP/JP]; c/o Dow Corning Toray Co., Ltd., 2-2, Chigusaigaigan, Ichihara-shi, Chiba, 2990108 (JP).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report



WO 2008/069333 A1

(54) Title: CURABLE EPOXY RESIN COMPOSITION, CURED BODY THEREOF, AND USE THEREOF

(57) Abstract: A curable epoxy resin composition comprising at least the following components: (I) an epoxy resin; (II) a curing agent for an epoxy resin; (III) a diorganosiloxane having on both molecular terminals siloxane residual radicals represented by the following average unit formula: $(XR_{1/2}SiO_{1/2})_a(SiO_{4/2})_b$ (where R_1 is a monovalent hydrocarbon group that is free of unsaturated aliphatic bond, and "X" is a single bond, a hydrogen atom, a group designated by R_1 , an epoxy-containing monovalent organic group, or an alkoxyalkyl group; however, at least one group designated by "X" in one molecule is a single bond, at least two groups designated by "X" are epoxy-containing alkyl groups; "a" is a positive number; "b" is a positive number; and "a/b" is a number ranging from 0.2 to 4); and (IV) an inorganic filler; is capable of producing a cured body of high strength in spite of having a low modulus of elasticity (low stress).

DESCRIPTIONCURABLE EPOXY RESIN COMPOSITION,
CURED BODY THEREOF, AND USE THEREOFTechnical Field

5 [0001] The present invention relates to a curable epoxy resin composition, as well as to a cured body of the composition and the use of the composition.

Background Art

[0002] It is known that curable epoxy resin compositions find application as agents for sealing and bonding electrical or electronic devices. However, since cured bodies obtained
10 by curing conventional curable epoxy resin compositions are characterized by a high modulus of elasticity and therefore by high rigidity, the use of such bodies in conjunction with electrical or electronic devices is associated with problems such as development of high stress that occurs under conditions of thermal expansion and shrinkage at curing. In order to reduce the modulus of elasticity in cured bodies of the aforementioned
15 compositions, it was suggested to combine the curable epoxy resin composition with a diorganopolysiloxane that contains epoxy groups. Such a diorganopolysiloxane, which is disclosed in Japanese Unexamined Patent Application Publication (hereinafter referred to as "Kokai") H06-56999, is one having siloxane residual radicals with epoxy groups on molecular terminals. Kokai H06-56999 does not give specific examples of the contents of
20 the aforementioned curable epoxy resin compositions. However, when the recommended diorganopolysiloxanes are added to the curable epoxy resin compositions, the decrease of modulus of elasticity provided by such an addition in cured bodies may be accompanied by decrease in strength.

[0003] On the other hand, it was proposed in Kokai 2006-257115 to replace the
25 curable epoxy resin composition with a curable silicone composition which comprises of a diorganopolysiloxane with silicone residual radicals having epoxy groups on both molecular terminals and a curing agent for an epoxy resins. Although such a curable silicone composition provided a cured body having excellent modulus of elasticity and adhesiveness, the use of this composition was still limited because the cured body was
30 insufficiently strong.

[0004] It is an object of the present invention to provide a curable epoxy resin composition that is characterized by excellent moldability, and that, when cured, forms a

cured body which, in spite of having a low modulus of elasticity (low stress), has high strength. Another object is to provide a curable epoxy resin composition that is suitable for use as a sealing agent for semiconductor devices. A still further object of the invention is to provide a cured body that combines low modulus of elasticity (low stress) with high strength.


Disclosure of Invention

[0005] The above problems are solved by the present invention that provides a curable epoxy resin composition comprising at least the following components:


(I) an epoxy resin;

(II) a curing agent for an epoxy resin;

(III) a diorganosiloxane that is used in an amount of 0.1 to 100 parts by weight per 100 parts by weight of the sum of components (I) and (II) and is represented by the following general formula:



{where R¹ designates the same or different unsubstituted or substituted monovalent hydrocarbon groups which are free of unsaturated aliphatic bonds; R² is a bivalent organic group; "A" is a siloxane residual radical represented by the following average unit formula:



(where R¹ is the same as defined above, and "X" is a single bond, a hydrogen atom, a group designated by R¹, an epoxy-containing monovalent organic group, or an alkoxysilylalkyl group; however, at least one group designated by "X" in one molecule is a single bond, at least two groups designated by "X" are epoxy-containing alkyl groups; "a" is a positive number; "b" is a positive number; and "a/b" is a number ranging from 0.2 to 4), and where "n" is an integer equal to or greater than 1}, and

(IV) an inorganic filler (contained in the composition in an amount of at least 20 wt.%).

[0006] The curable epoxy resin composition of the invention is characterized by being used as a sealing agent or an adhesive agent for a semiconductor device.

[0007] A cured body of the invention is obtained by curing the composition of the invention.

Effects of Invention

[0008] The curable epoxy resin composition of the invention is efficient in that it possesses excellent moldability, and, when cured, can form a cured body that has high strength in spite of having a low modulus of elasticity (low stress). Furthermore, a cured
5 body of the composition is characterized by high strength along with low modulus of elasticity (low stress).

Detailed Description of the Invention

[0009] The epoxy resin that constitutes component (I) is a main component of the composition. There are no special restrictions with regard to component (I), provided that
10 this component contains an epoxy group such as a glycidyl group or an alicyclic epoxy group. Component (I) may be exemplified by novolak-type epoxy resin, cresol-novolak type epoxy resin, triphenol-alkane type epoxy resin, aralkyl-type epoxy resin, aralkyl-type epoxy resin with a biphenyl backbone, biphenyl-type epoxy resin, dicyclopentadiene-type epoxy resin, heterocyclic-type epoxy resin, naphthalene-ring containing epoxy resin,
15 bisphenol-A type epoxy resin, bisphenol-F type epoxy resin, stilbene-type epoxy resin, trimethylolpropane-type epoxy resin, terpene-modified epoxy resin, linear aliphatic epoxy resin obtained by oxidizing the olefin bond with a peroxy acid, such as a peracetic acid, alicyclic epoxy resin, or sulfur-containing epoxy resin. Component (I) may be composed of one or more of the aforementioned epoxy resins. Most preferable for use as component (I)
20 are aralkyl-type epoxy resin with a biphenyl backbone, biphenyl-type epoxy resin, or a similar epoxy resin that contains a biphenyl group.

[0010] Component (I) is generally available. For example, the biphenyl-type epoxy resin is commercially produced by Japan Epoxy Resin Co., Ltd. under the name YX-4000; the bisphenol-F type epoxy resin is commercially produced by Nippon Steel Chemical Co.,
25 Ltd. under the name VSLV-80XY; the aralkyl-type epoxy resin with a biphenyl backbone is produced by Nippon Kayaku Co., Ltd. under the names NC-3000 and CER-3000L (a mixture with a phenyl-type epoxy resin); and the naphthol-aralkyl-type epoxy resin is produced by Nippon Steel Chemical Co., Ltd. under the name ESN-175.

[0011] When the composition of the invention is used as a sealing agent or an adhesive
30 agent for a semiconductor device, it is recommended that component (I) contain hydrolysable chlorine in an amount of not more than 1000 ppm, preferably not more than 500 ppm. The content of sodium and potassium in component (I) should not exceed 10 ppm of each. If the content of the hydrolysable chlorine exceeds the recommended upper


limit, or if the content of sodium and potassium exceed the respective recommended upper limits, this will impair moisture-resistant properties of semiconductor devices having parts sealed or bonded with the use of the composition of the invention when such devices operate under conditions of high temperature and high humidity.

5 **[0012]** Component (II) is a curing agent for an epoxy resin that reacts with the epoxy groups of component (I) and is used for curing the composition. It is recommended that component (II) be a compound that contains phenolic hydroxyl groups, such as phenol-novolak resin, phenol resin that contains a naphthalene ring, aralkyl-type phenol resin, triphenolalkane-type phenol resin, biphenyl-containing phenol resin, alicyclic phenol resin,
10 heterocyclic phenol resin, bisphenol-A, or bisphenol-F. Component (II) may be composed of two or more of the aforementioned compounds with phenolic hydroxyl groups. The use of component (II) in the form of the biphenyl-containing aralkyl-type phenol resin, or a similar biphenyl-containing phenol resin, is preferable.

[0013] Component (II) is readily available. For example, the aralkyl-type phenol resin
15 is commercially produced by Mitsui Chemical Co., Ltd. under the name Milex XLC-3L and by Meiwa Plastic Industries Co., Ltd. under the name MEH-781; the naphthalene-ring-containing phenol resin is produced by Nippon Steel Chemical Co., Ltd. under the names SN-475 and SN-170; the phenol-novolak resin is produced by Meiwa Plastic Industries Co., Ltd. under the name MEH-7500; and the biphenyl-containing phenol resin is produced
20 by Meiwa Plastic Industries Co., Ltd. under the name MEH 7851M.

[0014] There are no special restrictions with regard to the amount in which component (II) can be used, provided that this amount is sufficient for curing component (I). However, it is recommended that the epoxy-reactive functional groups of component (II) be in the range of 0.5 to 2.5 moles per 1 mole of the epoxy groups of component (I). For example,
25 when component (II) is a compound that contains phenolic hydroxyl groups, the content of the phenolic hydroxyl groups of component (II) should be in the range of 0.5 to 2.5 moles per 1 mole of the epoxy groups of component (I). If component (II) is contained in an amount less than the recommended lower limit, it will be difficult to provide complete curing of the composition, and, if, on the other hand, the content of component (II) exceeds
30 the recommended upper limit, this will reduce the strength of the cured body.


[0015] Component (III) is used in the composition for improving its moldability and for decreasing the modulus of elasticity in the cured body of the composition. Component (III) is a diorganosiloxane of the following general formula:



In the above formula, the groups designated by R^1 are same or different and constitute substituted or unsubstituted monovalent hydrocarbon groups without unsaturated aliphatic bonds. Specific examples of such groups are the following: methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, decyl, octadecyl, or a similar alkyl group; cyclopentyl, cyclohexyl, cycloheptyl, or a similar cycloalkyl group; phenyl, tolyl, xylyl, or a similar aryl groups; benzyl, phenethyl, phenylpropyl, or a similar aralkyl group; and 3-chloropropyl, 3,3,3-trifluoropropyl, or a similar halogenated alkyl group. Most preferable are alkyl groups, especially methyl groups. In the above formula, R^2 designates bivalent organic groups.

These groups can be specifically exemplified by ethylene, methylethylene, propylene, butylene, pentylene, hexylene, or a similar alkylene group; ethylenoxyethylene, ethylenoxypropylene, ethylenoxybutylene, propylenoxypropylene, or a similar alkyleneoxyalkylene group. Preferable are alkylene groups, in particular, ethylene groups. In the formula, "n" is an integer, which is equal to or greater than 1 and which represents the degree of polymerization of the diorganosiloxane contained in the main molecular chain. From the viewpoint of improved flexibility of a cured body of the composition, "n" should be equal to or greater than 10. There are no special restrictions with regard to the upper limit of the value of "n", but it is recommended that the value of "n" do not exceed 500.

[0016] In the above formula, "A" is a siloxane residual radical represented by the following average unit formula:



In this formula, R^1 designated the same or different substituted or unsubstituted monovalent hydrocarbon groups which are free of unsaturated aliphatic bonds. These groups may be exemplified by the same groups as given for them earlier, most preferable of which are alkyl groups and especially methyl groups. "X" designates a single bond, a hydrogen atom, a group designated by R^1 , an epoxy-containing monovalent organic group, or an alkoxyalkyl group. However, at least one group designated by "X" in one molecule is a single bond, which is used for bonding to R^2 in the aforementioned diorganopolysiloxane. Moreover, at least two groups designated by "X" are epoxy-containing alkyl groups.

[0017] Groups designated by R^1 may be exemplified by the same groups as mentioned above for R^1 . At least one group designated by "X" should be a monovalent hydrocarbon

group with 6 or more carbon atoms. In order to improve flowability of the composition, component (III) should be compatible with components (I) and (II). The monovalent hydrocarbon groups may be represented by hexyl, octyl, decyl, octadecyl, or similar alkyl groups; cyclohexyl, cycloheptyl, or similar cycloalkyl groups; and phenyl, tolyl, xylyl, or similar aryl groups; benzyl, phenethyl, phenylpropyl, or similar aralkyl groups, of which
5 alkyl groups are preferable.

[0018] The epoxy-containing alkyl groups can be exemplified by 2-glycidoxyethyl, 3-glycidoxypropyl, 4-glycidoxybutyl, or similar glycidoxyalkyl groups; 2-(3,4-epoxycyclohexyl) ethyl, 3-(3,4-epoxychlorohexyl) propyl, or similar 3,4-
10 epoxycyclohexylalkyl groups; and 4-oxiranylbutyl, 8-oxiranyloctyl, or similar oxiranylalkyl groups. Most preferable of these groups are glycidoxyalkyl, especially 3-glycidoxypropyl groups.

[0019] The alkoxyalkyl groups can be exemplified by trimethoxysilylethyl, trimethoxysilylpropyl, dimethoxymethylsilylpropyl, methoxydimethylsilylpropyl, triethoxysilylethyl, or tripropoxysilylpropyl groups. However, at least one group
15 designated by "X" in one molecule should be an alkoxyalkyl, and preferably a trimethoxysilylethyl group.

[0020] In the above formula, "a" is a positive number, "b" is a positive number, and "a/b" is a number in the range of 0.2 to 4.

[0021] There are no special restrictions with regard to weight-average molecular weight of component (III) but it may be recommended to have this value in the range of 500 to 1,000,000. Also, there are no special restrictions with regard to the form of component (III) at 25°C, but the liquid form is preferable. It is recommended that component (III) have a viscosity at 25°C in the range of 50 to 1,000,000 mPa·s. The
20 method of preparation of component (III) is described, e.g., in Kokai H06-56999.

[0022] In the composition of the invention, component (III) is used in an amount of 0.1 to 100 parts by weight, preferably 0.1 to 50 parts by weight, and most preferably 0.1 to 20 parts by weight per 100 parts by weight of the sum of components (I) and (II). If component (III) is used in an amount less than the recommended lower limit, this will
30 increase the modulus of elasticity of a cured body. If, on the other hand, the content of component (III) exceeds the recommended upper limit, this will reduce the strength of the cured body.

[0023] Component (IV) is an inorganic filler that is added for strengthening a cured body of the composition. When an inorganic filler is added to a curable epoxy resin composition, this normally improves strength of the body cured from the composition, but at the same time, flowability of the composition is noticeably impaired, and moldability of the composition worsens. Moreover, the modulus of elasticity of the cured body is significantly increased. In contrast to this, joint use of aforementioned components (III) and (IV) protects the composition from loss of flowability and moldability, and, in spite of decrease in modulus of elasticity (low stress), makes it possible to obtain a cured body of high strength.

10 [0024] There are no special restrictions with regard to the filler that constitutes component (IV), and inorganic fillers that are normally admixed with conventional curable epoxy resin compositions can be used for the purposes of the invention. Such fillers can be exemplified by glass fiber, asbestos, alumina fiber, ceramic fiber composed of alumina and silica, boron fiber, zirconia fiber, silicon carbide fiber, metallic fiber, or a similar fibrous
15 filler; amorphous silica, crystalline silica, precipitated silica, fumed silica, baked silica, zinc oxide, baked clay, carbon black, glass beads, talc, calcium carbonate, clay, aluminum hydroxide, magnesium hydroxide, barium sulfate, titanium dioxide, aluminum nitride, boron nitride, silicon carbide, aluminum oxide, magnesium oxide, titanium oxide, beryllium oxide, kaolin, mica, zirconia, or a similar powdery filler. Component (IV) may
20 be composed of two or more such fillers. There are no special restrictions with regard to the shape of the filler particles of component (IV). The powder particles may be spherical, needle-like, plate-like, ground (i.e., irregularly shaped), etc. From the viewpoint of moldability, the spherical shape is preferable. It is also preferable that component (IV) comprise spherical amorphous silica. There are no special restrictions with regard to the
25 average dimensions of the particles of component (IV), but from the viewpoint of improved moldability, the particles should be in the range of 0.1 to 50 μm . Two or more types of inorganic fillers having different average dimensions can be used in combination.

[0025] In order to improve affinity to component (I), component (IV) can be subjected to surface treatment with a silane coupling agent, a titanate coupling agent, or another
30 similar coupling agent. Such silane coupling agents can be represented by 3-glycidoxypropyl trimethoxysilane, 3-glycidoxypropyl methyldiethoxysilane, 2-(3,4-epoxycyclohexyl) ethyltrimethoxysilane, or a similar epoxy-containing alkoxysilane; N-(2-aminoethyl)-3-aminopropyl trimethoxysilane, 3-aminopropyl triethoxysilane, N-phenyl-3-

aminopropyl trimethoxysilane, or a similar amine-containing alkoxy silane; 3-mercaptopropyl trimethoxysilane or a similar mercapto-containing alkoxy silane; as well as 3-isocyanatepropyl triethoxysilane, or 3-ureidopropyl trimethoxysilane. And such titanate coupling agent can be represented by titanium tris(isostearate) i-propoxide. These coupling agents can be used in combination of two or more. There are no special restrictions with regard to the amounts in which the aforementioned coupling agents can be used. There are no restrictions also with regard to the methods of surface treatment.

[0026] Component (IV) should be used in the amount of at least 20 wt.%, preferably at least 30 wt.%, more preferably at least 50 wt.%, and most preferably at least 80 wt.% of the weight of the composition. If component (IV) is used in the amount less than the recommended lower limit, it will be difficult to impart sufficient strength to the cured body of the composition.

[0027] In the composition of the invention, component (IV) can be dispersed either in component (I) or in component (II). In order to improve affinity of component (IV) to component (I) or (II), a coupling agent, such as a silane coupling agent or a titanate coupling agent can be added to the mixture. These coupling agents can be exemplified by the same compounds as mentioned above.

[0028] The composition of the invention may additionally contain a curing accelerator (V). Such component (V) may be represented by triphenylphosphine, tributylphosphine, tri(p-methylphenyl) phosphine, tri(nonylphenyl) phosphine, triphenylphosphine-triphenylborate, tetraphenylphosphine-tetraphenylborate, or similar phosphorous compounds; triethylamine, benzyldimethylamine, α -methylbenzyldimethylamine, 1,8-diazobicyclo [5.4.0] undecene-7, or similar tertiary amine compounds; 2-methylimidazole, 2-phenylimidazole, 2-phenyl-4-methylimidazole, or similar imidazole compounds.

[0029] There are no special restrictions with regard to the amount in which component (V) can be added to the composition, but in general it can be recommended that this component be contained in the range of 0.001 to 20 parts by weight per 100 parts by weight of component (I). If the content of component (V) is below the recommended lower limit, it will be difficult to accelerate the reaction between components (I) and (II). If, on the other hand, the content of component (V) exceeds the recommended upper limit, this will impair strength of the cured body.

[0030] If necessary, the composition can be further combined with a stress-reducing agent, such as thermoplastic resin, thermoplastic elastomer, organic synthetic rubber,

silicone, etc.; wax such as carnauba wax, higher fatty acid, synthetic wax, etc.; a coloring agent such as carbon black; a halogen-trap agent, etc.

5 [0031] There are no restrictions for the method of preparation of the composition, and the composition can be prepared by merely uniformly mixing components (I) to (IV), if necessary, with an addition of the arbitrary components. Dispersion conditions of component (III) can be improved if component (III) is added to and mixed with a composition obtained by premixing components (I) and (II). Alternatively, components (II), (III), and arbitrary components can be added to and uniformly mixed with a premixture of components (I) and (IV). In this case, the process can be exemplified by a
10 so-called integral-blend method in which a coupling agent is added to components (I) and (IV), or by a method of premixing component (I) with component (IV) surface treated with a coupling agent. Mixing can be carried out by means of a single-shaft-type or a two-shaft-type continuous mixer, a two-roll mill, a Ross® mixer, a kneader mixer, a Henschel mixer, or the like.

15 [0032] Since the composition of the invention possesses excellent moldability prior to curing, it is suitable for use as a sealing agent, paint, coating agent, filler, adhesive, or a similar agent for electric or electronic devices and can be processed by transfer molding, injection molding, potting, casting, powder coating, immersion coating, drop-wise application, etc., for forming a cured body of low modulus of elasticity and high strength.

20 Examples

[0033] The curable epoxy resin composition of the invention will be further described in more detail with reference to Practical Examples. All values of viscosities used in the examples correspond to 25°C.

25 [0034] Characteristics of the curable epoxy resin compositions and cured bodies of the compositions were measured by the methods described below. The compositions were prepared by transfer press-curing for two minutes at 175°C under pressure of 70 kgf/cm² and then post-cured for 5 hours at 180°C.

[Moldability]

[0035]

30 - Spiral flow: measured at 175°C and 70 kgf/cm² by the method prescribed by the EMMI standard.

- Mold contamination: after continuously molding 5 disks with a diameter of 50 mm and a thickness of 2 mm in a row, the tarnishing of the chrome-plated surface of the mold was observed visually, designating cases in which there was no mold contamination as [○], case in which there was a thin tarnishing layer on the surface of the mold, as [△], and cases in which there was contamination on the surface of the mold, as [X].

[Mechanical Characteristics]


[0036]

- Flexural modulus of elasticity: measured as specified by JIS K 6911.


- Flexural strength: measured as specified by JIS K 6911.

10 [Practical Example 1]

[0037] A curable epoxy resin composition was prepared by melting and uniformly mixing the following components by means of a hot two-roll mill: 51 parts by weight of a biphenyl-aralkyl type epoxy resin (produced by Nippon Kayaku Co., Ltd. under the name NC-3000; epoxy equivalent = 275; softening point = 56°C); 39.0 parts by weight of a biphenyl-aralkyl type phenol resin (produced by Meiwa Plastic Industries Co., Ltd. under the name MEH7851M; phenolic hydroxyl group equivalent = 207; softening point = 80°C); 3.0 parts by weight of a dimethylpolysiloxane of the following formula:



{where "A" is represented by the following formula:




(where "X" is composed of single bonds and 3-glycidoxypropyl groups; at least one "X" in one molecule is a single bond, and the remaining part of "X" consists of 3-glycidoxypropyl groups); 510 parts by weight of spherical amorphous silica with an average particle size equal to 14 μm (the product of Denki Kagaku Kogyo Co., Ltd. known under the name of FB-48X); 1.0 part by weight of triphenylphosphine; and 1.0 part by weight of carnauba wax. Characteristics of the aforementioned curable epoxy resin compositions and of the cured bodies were measured. The results of measurement are shown in Table 1.


[Practical Example 2]

[0038] A curable epoxy resin composition was prepared by melting and uniformly mixing the following components by means of a hot two-roll mill: 51.1 parts by weight of a biphenyl-aralkyl type epoxy resin (produced by Nippon Kayaku Co., Ltd. under the name NC-3000; epoxy equivalent = 275; softening point = 56°C); 38.9 parts by weight of a

biphenyl-aralkyl type phenol resin (produced by Meiwa Plastic Industries Co., Ltd. under the name MEH7851M; phenolic hydroxyl group equivalent = 207; softening point = 80°C); 3.0 parts by weight of a dimethylpolysiloxane of the following formula:




5 {where "A" is represented by the following formula:




(where "X" is composed of single bonds, trimethoxysilylpropyl groups, and 3-glycidoxypropyl groups; at least one "X" in one molecule is a single bond, and the remaining part of "X" consists of trimethoxysilylpropyl groups and 3-glycidoxypropyl groups used in a mole ratio of 1 to 4)}; 510 parts by weight of spherical amorphous silica with an average particle size equal to 14 μm (the product of Denki Kagaku Kogyo Co., Ltd. known under the name of FB-48X); 1.0 part by weight of triphenylphosphine; and 1.0 part by weight of carnauba wax. Characteristics of the aforementioned curable epoxy resin compositions and of the cured bodies were measured. The results of measurement are shown in Table 1.

[Practical Example 3]

[0039] A curable epoxy resin composition was prepared by melting and uniformly mixing the following components by means of a hot two-roll mill: 51.2 parts by weight of a biphenyl-aralkyl type epoxy resin (produced by Nippon Kayaku Co., Ltd. under the name NC-3000; epoxy equivalent = 275; softening point = 56°C); 38.8 parts by weight of a biphenyl-aralkyl type phenol resin (produced by Meiwa Plastic Industries Co., Ltd. under the name MEH7851M; phenolic hydroxyl group equivalent = 207; softening point = 80°C); 3.0 parts by weight of a dimethylpolysiloxane of the following formula:



25 {where "A" is represented by the following formula:




(where "X" is composed of single bonds, trimethoxysilylpropyl groups, and 3-glycidoxypropyl groups; at least one "X" in one molecule is a single bond, and the remaining part of "X" consists of trimethoxysilylpropyl groups and 3-glycidoxypropyl groups used in a mole ratio of 1 to 4)}; 510 parts by weight of spherical amorphous silica with an average particle size equal to 14 μm (the product of Denki Kagaku Kogyo Co., Ltd. known under the name of FB-48X); 1.0 part by weight of triphenylphosphine; and 1.0 part by weight of carnauba wax. Characteristics of the aforementioned curable epoxy resin

compositions and of the cured bodies were measured. The results of measurement are shown in Table 1.

[Practical Example 4]

[0040] A curable epoxy resin composition was prepared by melting and uniformly mixing the following components by means of a hot two-roll mill: 50.3 parts by weight of a biphenyl-aralkyl type epoxy resin (produced by Nippon Kayaku Co., Ltd. under the name NC-3000; epoxy equivalent = 275; softening point = 56°C); 39.7 parts by weight of a biphenyl-aralkyl type phenol resin (produced by Meiwa Plastic Industries Co., Ltd. under the name MEH7851M; phenolic hydroxyl group equivalent = 207; softening point = 80°C); 3.0 parts by weight of a dimethylpolysiloxane of the following formula:



{where A is represented by the following formula:



(where X is composed of single bonds, octyl groups, and glycidoxypropyl groups; at least one X in one molecule is a single bond, and the remaining part of X consists of octyl groups and 3-glycidoxypropyl groups used in a mole ratio of 1 to 4); 510 parts by weight of spherical amorphous silica with an average particle size equal to 14 μm (the product of Denki Kagaku Kogyo Co., Ltd. known under the name of FB-48X); 1.0 part by weight of triphenylphosphine; and 1.0 part by weight of carnauba wax. Characteristics of the aforementioned curable epoxy resin compositions and of the cured bodies were measured. The results of measurement are shown in Table 1.

[Comparative Example 1]

[0041] A curable epoxy resin composition was prepared by melting and uniformly mixing the following components by means of a hot two-roll mill: 51.5 parts by weight of a biphenyl-aralkyl type epoxy resin (produced by Nippon Kayaku Co., Ltd. under the name NC-3000; epoxy equivalent = 275; softening point = 56°C); 38.5 parts by weight of a biphenyl-aralkyl type phenol resin (produced by Meiwa Plastic Industries Co., Ltd. under the name MEH7851M; phenolic hydroxyl group equivalent = 207; softening point = 80°C); 510 parts by weight of spherical amorphous silica with an average particle size equal to 14 μm (the product of Denki Kagaku Kogyo Co., Ltd. known under the name of FB-48X); 1.0 part by weight of triphenylphosphine; and 1.0 part by weight of carnauba wax.

Characteristics of the aforementioned curable epoxy resin compositions and of the cured bodies were measured. The results of measurement are shown in Table 1.

[Comparative Example 2]

[0042] A curable epoxy resin composition was prepared by melting and uniformly mixing the following components by means of a hot two-roll mill: 41.5 parts by weight of a biphenyl-aralkyl type epoxy resin (produced by Nippon Kayaku Co., Ltd. under the name NC-3000; epoxy equivalent = 275; softening point = 56°C); 38.5 parts by weight of a biphenyl-aralkyl type phenol resin (produced by Meiwa Plastic Industries Co., Ltd. under the name MEH7851M; phenolic hydroxyl group equivalent = 207; softening point = 80°C); 3.0 parts by weight of a diorganopolysiloxane of the following formula:

$$(CH_3)_3SiO[(CH_3)_2SiO]_{130}[Z(CH_3)SiO]_3[CH_3CO\{OCH(CH_3)CH_2\}_{24}(OCH_2CH_2)_{24}OCH_2CH_2CH_2(CH_3)SiO]_7Si(CH_3)_3$$

(where "Z" is a 3-glycidoxypropyl group); 510 parts by weight of spherical amorphous silica with an average particle size equal to 14 μm (the product of Denki Kagaku Kogyo Co., Ltd. known under the name of FB-48X); 1.0 part by weight of triphenylphosphine; and 1.0 part by weight of carnauba wax. Characteristics of the aforementioned curable epoxy resin compositions and of the cured bodies were measured. The results of measurement are shown in Table 1.

[0043]

[Table 1]


Characteristics	Examples	Practical Examples				Comp. Ex.	
		1	2	3	4	1	2
Spiral flow	(inch)	17	17	17	22	25	23
Mold contamination		○	○	○	○	○	x
Flexural modulus of elasticity	(kgf/mm ²)	2260	2160	2240	2180	2380	2320
Flexural strength	(kgf/mm ²)	13.1	13.0	13.0	13.0	11.9	10.7

Industrial Applicability


[0044] Since the curable epoxy resin composition is characterized by excellent moldability prior to curing, and, when cured, forms a cured body which, in spite of low modulus of elasticity (low stress), has high strength, it is suitable for use as a sealing agent for semiconductor devices.

CLAIMS

1. A curable epoxy resin composition comprising at least the following components:
(I) an epoxy resin;
(II) a curing agent for an epoxy resin;
5 (III) a diorganosiloxane that is used in an amount of 0.1 to 100 parts by weight per 100 parts by weight of the sum of components (I) and (II) and is represented by the following general formula:



{where R¹ designates the same or different unsubstituted or substituted monovalent hydrocarbon groups which are free of unsaturated aliphatic bonds; R² designates a bivalent organic group; "A" designates a siloxane residual radical represented by the following average unit formula:



(where R¹ is the same as defined above, and "X" is a single bond, a hydrogen atom, a group designated by R¹, an epoxy-containing monovalent organic group, or an alkoxysilylalkyl group; however, in one molecule at least one group designated by "X" is a single bond, at least two groups designated by "X" are epoxy-containing alkyl groups; "a" is a positive number; "b" is a positive number; and "a/b" is a number ranging from 0.2 to 4), and where "n" is an integer equal to or greater than 1}, and

(IV) an inorganic filler (contained in the composition in the amount of at least 20 wt.%).

2. The curable epoxy resin composition of Claim 1, wherein component (I) is an epoxy resin that contains biphenyl groups.

3. The curable epoxy resin composition of Claim 1, wherein component (II) is a compound that contains phenolic hydroxyl groups.

4. The curable epoxy resin composition of Claim 3, wherein the compound that contains phenolic hydroxyl groups is a biphenyl-containing phenol resin.

5. The curable epoxy resin composition of Claim 1, wherein component (II) is contained in such an amount that the content of epoxy reactive functional groups in component (II) is in the range of 0.5 to 2.5 moles per 1 mole of the epoxy groups of component (I).

6. The curable epoxy resin composition of Claim 1, wherein in component (III) at least one group designated by "X" is a monovalent hydrocarbon group having six or more carbon atoms.
7. The curable epoxy resin composition of Claim 1, wherein in component (III) at least one group designated by "X" is an alkoxysilylalkyl group.
8. The curable epoxy resin composition of Claim 1, wherein component (IV) is a spherical inorganic filler.
9. The curable epoxy resin composition of Claim 1, wherein component (IV) is a spherical amorphous silica.
10. The curable epoxy resin composition of Claim 1, further provided with (V) a curing accelerator for an epoxy resin.
11. The curable epoxy resin composition according to any claim from 1 to 10, wherein the curable epoxy resin composition is a sealing agent for a semiconductor device.
12. A cured body obtained by curing the curable epoxy resin composition according to any claim from 1 to 10.

INTERNATIONAL SEARCH REPORT

International application No

PCT/JP2007/073736

A: CLASSIFICATION OF SUBJECT MATTER
INV. C08G59/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 561 174 A (SAITO YOSHINORI [JP] ET AL) 1 October 1996 (1996-10-01) column 2, lines 32-36 table 1	1
A	WO 2006/098493 A (DOW CORNING TORAY CO LTD [JP]; MORITA YOSHITSUGU [JP]; ISSHIKI MINORU) 21 September 2006 (2006-09-21) claims 1-3	1-12
A	US 4 877 822 A (ITOH KUNIO [JP] ET AL) 31 October 1989 (1989-10-31) examples 1-8	1-12

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

13 March 2008

Date of mailing of the international search report

25/03/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Von Kuzenko, Michael

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/JP2007/073736

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
US 5561174	A	01-10-1996	JP 3147677 B2	19-03-2001
			JP 8100106 A	16-04-1996
WO 2006098493	A	21-09-2006	EP 1858983 A1	28-11-2007
			JP 2006257115 A	28-09-2006
			KR 20070117597 A	12-12-2007
US 4877822	A	31-10-1989	DE 3689022 D1	21-10-1993
			DE 3689022 T2	21-04-1994
			DE 4006450 A1	05-09-1991
			EP 0218228 A2	15-04-1987
			US 5053445 A	01-10-1991