

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08L 95/00, C08K 5/09	A1	(11) International Publication Number: WO 96/16128 (43) International Publication Date: 30 May 1996 (30.05.96)
(21) International Application Number: PCT/EP95/04604 (22) International Filing Date: 20 November 1995 (20.11.95) (30) Priority Data: 94402657.4 21 November 1994 (21.11.94) EP (34) Countries for which the regional or international application was filed: FR et al. (71) Applicant: SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V. [NL/NL]; Maatschappij B.V., Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL). (72) Inventors: DESAIX, Jean-Claude; Shell Recherche S.A., Centre de Recherche, Route de Caen, F-76530 Grand-Couronne (FR). MORIZUR, Marie-Françoise; Shell Recherche S.A., Centre de Recherche, Route de Caen, F-76530 Grand-Couronne (FR). RABIOT, Denis; Shell Recherche S.A., Centre de Recherche, Route de Caen, F-76530 Grand-Couronne (FR).		(81) Designated States: AU, HU, JP, NZ, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: BITUMEN COMPOSITIONS (57) Abstract The present invention provides bitumen compositions comprising bitumen and a succinic anhydride derivative contained in the bitumen, wherein the derivative comprises a mono-alkene on which has been grafted a succinic anhydride function; processes for their preparation and their use in bitumen emulsions for road applications, e.g. surface dressings.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

BITUMEN COMPOSITIONS

The present invention relates to bitumen compositions, their preparation, and their use in bitumen emulsions for road applications, e.g. surface dressings.

5 Bitumens used for these applications may have different origins. Venezuelan crude oils that naturally contain acidic molecules (naphthenic acids) are considered as having good qualities for manufacturing bitumen emulsions. Crude oils from other sources, e.g.
10 Middle East oils, do not contain these acids. However, it is known to add (and incorporate) naphthenic acids to non-naphthenic bitumens in order to try to attain the quality of naphthenic bitumens.

EP-A-0416682 discloses bitumen compositions
15 comprising bitumen and at least one polymerised fatty acid contained in the bitumen and their use in bitumen emulsions for surface dressing applications suitable for roads.

It has now been found that bitumen compositions
20 having surprisingly enhanced properties can be obtained by incorporating a particular succinic anhydride derivative into bitumens.

According to the present invention there is provided a bitumen composition comprising bitumen and a succinic
25 anhydride derivative incorporated in the bitumen, wherein the derivative comprises a mono-alkene on to which has been grafted a succinic anhydride function.

Preferred mono-alkenes are those having a chain
length of 12 to 40 carbon atoms, particularly 1-alkenes.
30 Particularly preferred are the 1-alkenes having a chain length of 14 to 19 carbon atoms.

-2-

Such succinic anhydride derivatives can be obtained by any suitable known method, for example, by the processes described in US-A-3412111 or US-A-4691030.

5 The succinic anhydride derivative is preferably present in an amount of at least 0.1% w/w of the bitumen, preferably an amount in the range of 0.1% to 1% w/w of the bitumen, more preferably an amount in the range of 0.1% to 0.5% of the bitumen. In accordance with the present invention the bitumen composition may
10 suitably comprise two or more different types of the succinic anhydride derivative.

The present invention also provides a process for preparing a bitumen composition of the present invention which process comprises incorporating the succinic
15 anhydride derivative into the bitumen, conveniently by mixing the succinic anhydride derivative directly into molten bitumen. The bitumen may be any bitumen, but the advantages of the present invention are most clearly attained when the bitumen is a non-naphthenic bitumen,
20 as will readily be appreciated by those skilled in the art.

Emulsions for road applications, e.g. surface dressings, may readily be prepared from bitumen compositions of the invention, in known manner.

25 The present invention thus further includes the use of bitumen compositions according to the present invention in a bitumen emulsion for surface dressings suitable for road applications.

The present invention will be further understood
30 from the following illustrative Examples, in which parts and percentages are by weight unless otherwise indicated.

EXAMPLES

Various doped bitumens were prepared based on two
35 200 penetration bitumens, that is, industrially produced

non-naphthenic bitumens (Bitumens A and B) which were each prepared from different crude oils.

The bitumens were doped by adding agents to the molten bitumens whilst stirring until homogeneous.

5 Emulsions containing about 65% bitumen were prepared in conventional manner from the above bitumens, by introducing bitumen (at 140°C) into a colloid mill together with an aqueous phase containing hydrochloric acid and emulsifier (N-alkyl (tallow) propylene diamine
10 - "DINORAM S" ex. CECA, France (DNS)).

Various properties of the bitumens (adhesivity) and of the emulsions (e.g. viscosity, breaking behaviour) were measured, and the results are given in Tables 1 to 3 following, in which:

15 R is a maleinated 1-alkene having a hydrocarbon chain length of 14 carbon atoms;

 S is a maleinated 1-alkene having a hydrocarbon chain length of 16 carbon atoms;

 T is a maleinated 1-alkene having a hydrocarbon chain length of 18 carbon atoms;

20 U is a blend of maleinated 1-alkenes having hydrocarbon chain lengths from 15 to 19 carbon atoms;

 V is a blend of maleinated 1-alkenes having hydrocarbon chain lengths from 15 to 19 carbon atoms;

25 W is a blend of maleinated 1-alkenes, 25% having a hydrocarbon chain length of 14 carbon atoms, 50% having a hydrocarbon chain length of 16 carbon atoms and 25% having a hydrocarbon chain length of
30 18 carbon atoms;

and

 C is a polymerised fatty acid ("PRIPOL 1017" ex. Unichema International, UK) used for purposes of
35 comparison

TABLE 1

BITUMEN 200	A							
DOPE	0%	C 0.5%	R 0.1%	S 0.1%	S 0.5	T 0.1%	U 0.1 %	U 0.5
penetration at 15°C	48	50	53	50	56	50	53	56
penetration at 25°C	187	191	167	182	190	167	180	187
Acid number	0	1.1	0.6	0.3	1.7		0.3	1.6
Adhesivity								
quartzite	0	25	0	50	25	0	50	25
flint	50	75	25	50	75	25	25	75
limestone	50	90	50	75	75	50	75	75
diorite	25	50	25	25	90	25	25	90
EMULSION	Emulsifier : 0.43%							
Water Phase	HCl => pH = 2.5							
bitumen content %	64.8	64.8	65.0	65.2	65.5	65.1	66. 2	65.0
pH	3.4	3.2	3.2	3.5	2.4	3,3	3.8	2.4
viscosity (mPa.s)	183	231	160	290		172	238	
breaking properties								
IREC	90	70	85	80	10	80	90	10
SMS 210m	2.5	13.3	9.4	7.5	52	11.0	9.9	break- ing
GBI	44	75	64	63	120	68	62	
seive residues								
630µm %	<0.1	<0.1	<0.1			<0.1	<0.1	
160µm %	<0.1	<0.1	<0.1			<0.1	<0.1	
63µm %	1.0	0.2	0.3			0.2	0.3	
38µm %	5.5	1.5	2.1			1.5	1.6	

- 5 -

TABLE 1 (continued)

storage stability								
decantation %		0.8	0.8			0.8		
sedimentation %	2.3	2.9	3.2			3.7		

TABLE 2

BITUMEN 200	B				
DOPE	0%	C 0.7%	V 0.25%	V 0.4%	V 0.5%
penetration at 15°C	51				
penetration at 25°C	184		183		178
Acid number		1.4	0.8	1.1	1.2
Adhesivity					
quartzite	0	75	25		25
flint	50	90	75		75
limestone	50	100	75		75
diorite	75	90	75		75
EMULSION	Emulsifier: 0.43%				
Water Phase	HCl =>pH = 2.5				
bitumen content %	65.00	64.70	65.00	65.10	65.50
pH	3.5	2.7	2.9	2.8	2.6
viscosity (mPa.s)	53	49	54	61	68
breaking properties					
IREC	120	100	85	75	45
SMS 210m	1.2	12.0	2.3	9.0	21.5
GBI	21	60	45	68	92

- 6 -

TABLE 2 (continued)

seive residues					
630µm %	<0.1	<0.1	<0.1	<0.1	<0.1
160µm %	<0.1		<0.1		<0.1
63µm %	0.6		1.0		0.6
38µm %	2.3		2.9		2.1
storage stability					
decantation %	1.5		2.0		0.8
sedimentation %	9.7		13.2		5.8

TABLE 3

BITUMEN 200	B				
DOPE	0%	C 0.7%	W 0.25%	W 0.4%	W 0.5%
penetration at 15°C	51				
penetration at 25°C	184		170		180
Acid number	-	1.4	0.8	1.1	1.2
Adhesivity					
quartzite	0	75			
flint	50	90			
limestone	50	100			
diorite	75	90			
EMULSION Water Phase	Emulsifier: 0.43% HCl =>pH = 2.5				
bitumen content %	65.0	64.7	65.1	65.1	65.1
pH	3.5	2.7	2.5	2.8	2.6
viscosity (mPa.s)	53	49	48	60	68
breaking properties					
IREC	120	100	90	60	55
SMS 210m	1.2	12.0	2.0	1.7	3.4
GBI	21	60	41	52	64
seive residues					
630µm %	<0.1	<0.1	<0.1	<0.1	<0.1

-7-

In the above Tables 1 to 3 viscosity was measured in known manner using a dynamic viscometer Bohling V88 (25°C; shear rate - 150 sec⁻¹; time - 30 min).

Adhesivity of the bitumen and breaking rates of the emulsions were tested as follows:

1. ADHESIVITY (LCPC Method)

The purpose of this test is to assess the adhesivity, in the presence of water, of a hydrocarbon binder coated on aggregate, and in it the displacement of bitumen by water on the surface of the aggregate is measured. In the test, bitumen-coated aggregate is plunged into water while hot, and the percentage of the surface covered by the binder after 16 hours' immersion at 60°C is evaluated. The test is carried out with four types of reference aggregate, as indicated.

2. IREC break index

Reference fines (siliceous fines in the case of cationic emulsions) are poured continuously through a funnel at a rate of 0.3 to 0.5 g/s into a beaker containing 100g of emulsion. The mixture is agitated constantly, and the addition of fines halted when the aggregate-emulsion system takes on the appearance of a block. The quantity of fines added to the 100g of bitumen emulsion is called the break index.

3. SMS 210m break index

10g of aggregate (Corbigny porphyry, 2 to 4mm) are placed in contact with an excess of emulsion (about 10g) for 1 hour in an environment saturated with water in order to prevent any evaporation. The unbroken emulsion is removed with distilled water. After drying, the quantity of bitumen deposited is determined by weighing, and the result expressed in relation to 10g of emulsion.

- 8 -

4. GBI (Global Breaking Index)

The results of the IREC and SMS 210 tests are combined to generate the global breaking index. This is defined by the relationship:

5
$$\text{GBI} = 72.5 - 0.45 \text{ IREC} + 30.2 \log(\text{SMS 210})$$

From the Tables, it is evident that the succinic acid derivatives significantly improved the breaking properties of the emulsions. In particular, it can be seen that the bitumen compositions of the present invention exhibit improved breaking properties when compared to the comparative compositions containing no dope (indicated in Tables 1 to 3 by "0%") and those containing "PRIPOL 1017" (indicated by "C" in Tables 1 to 3).

15

C L A I M S

1. A bitumen composition comprising bitumen and a succinic anhydride derivative incorporated in the bitumen, wherein the derivative comprises a mono-alkene on to which has been grafted a succinic anhydride
5 function.
2. A composition according to claim 1 wherein the mono-alkene has a chain length of 12 to 40 carbon atoms.
3. A composition according to claim 2 wherein the mono-alkene is a 1-alkene.
- 10 4. A composition according to claim 3, wherein the 1-alkene has a chain length of 14 to 19 carbon atoms.
5. A composition according to any one of claims 1 to 4 wherein the succinic anhydride derivative is present in an amount of at least 0.1% w/w of the bitumen.
- 15 6. A process for preparing a bitumen composition according to any one of Claims 1 to 5 which comprises incorporating the succinic anhydride derivative into the bitumen.
7. Use of a bitumen composition according to any one of
20 Claims 1 to 5 in a bitumen emulsion for surface dressings suitable for road applications.

INTERNATIONAL SEARCH REPORT

Inter: al Application No
PCT/EP 95/04604

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08L95/00 C08K5/09

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB,A,2 221 686 (SHOWA SHELL SEKIYU ;SHIMIZU CONSTRUCTION CO LTD (JP)) 14 February 1990 see page 7, paragraph 3 see claim 1	1
A	--- EP,A,0 496 457 (EURON SPA) 29 July 1992 see example 1 see claim 1	1,6,7
A	--- EP,A,0 561 472 (SHELL INT RESEARCH) 22 September 1993 see column 7, line 31 - line 47 see claim 1	1
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

16 February 1996

Date of mailing of the international search report

- 4. 03. 96

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

Inter nal Application No
PCT/EP 95/04604

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Derwent Publications Ltd., London, GB; AN 94-165757 & SU,A,1 801 974 (MINSK TEKHENERGOKHIMPROMSCI PRODN ASSOC) , 15 March 1993 see abstract -----	1

INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/EP 95/04604

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-2221686	14-02-90	JP-A- 2049063 US-A- 5324758	19-02-90 28-06-94
EP-A-0496457	29-07-92	IT-B- 1244685 DE-D- 69200069 DE-T- 69200069 HU-B- 211092 PL-B- 167978 US-A- 5225462	08-08-94 21-04-94 25-08-94 30-10-95 30-12-95 06-07-93
EP-A-0561472	22-09-93	US-A- 5212220 CN-A- 1092788 JP-A- 6041440	18-05-93 28-09-94 15-02-94