




(86) Date de dépôt PCT/PCT Filing Date: 2012/01/13
(87) Date publication PCT/PCT Publication Date: 2012/07/26
(45) Date de délivrance/Issue Date: 2018/12/18
(85) Entrée phase nationale/National Entry: 2013/07/18
(86) N° demande PCT/PCT Application No.: JP 2012/050573
(87) N° publication PCT/PCT Publication No.: 2012/099009
(30) Priorité/Priority: 2011/01/18 (JP2011-008293)

(51) Cl.Int./Int.Cl. *C22B 11/02* (2006.01),
B01J 23/42 (2006.01), *B01J 38/00* (2006.01),
B09B 3/00 (2006.01), *C22B 7/00* (2006.01),
C22B 9/10 (2006.01)
(72) Inventeurs/Inventors:
NAKAMURA YUZURU, JP;
KAWASAKI MINORU, JP;
YAMAGUCHI KATSUNORI, JP
(73) Propriétaire/Owner:
DOWA METALS & MINING CO., LTD., JP
(74) Agent: DENNISON ASSOCIATES

(54) Titre : PROCEDE PERMETTANT DE RECUPERER LES METAUX DU GROUPE DU PLATINE (PGM)
(54) Title: METHOD OF RECOVERING PGM



(57) Abrégé/Abstract:

A method of suppressing a distribution of PGM into a Cu₂O slag in an oxidation smelting of a method of recovering PGM, is provided, including: carrying out reduction smelting to a treatment target member containing PGM, Cu and/or Cu₂O, and flux, to thereby generate a molten slag and a Cu alloy containing PGM; and oxidizing and melting the Cu alloy containing the PGM, to thereby generate a Cu₂O slag containing PGM and the Cu alloy, with more concentrated PGM concentration than the Cu alloy containing the PGM, wherein when carrying out the oxidation smelting, acidic oxide or basic oxide is added.

ABSTRACT OF THE INVENTION

A method of suppressing a distribution of PGM into a Cu₂O slag in an oxidation smelting of a method of recovering PGM, is provided, including: carrying out reduction smelting to a treatment target member containing PGM, Cu and/or Cu₂O, and flux, to thereby generate a molten slag and a Cu alloy containing PGM; and oxidizing and melting the Cu alloy containing the PGM, to thereby generate a Cu₂O slag containing PGM and the Cu alloy, with more concentrated PGM concentration than the Cu alloy containing the PGM, wherein when carrying out the oxidation smelting, acidic oxide or basic oxide is added.

METHOD OF RECOVERING PGM

Technical Field

[0001]

The present invention relates to a method of recovering platinum group metals from each kind of member containing the platinum group metals, for example a catalyst for cleaning exhaust gas of a used car, used electronic substrates and lead frames, and used petrochemistry catalysts.

Description of Related Art

[0002]

For example, as a method of efficiently recovering platinum group metals from each kind of member containing the platinum group metals (described as "PGM" in the present invention in some cases), like the exhaust gas cleaning catalyst for the used car, inventors of the present invention disclose a dry-type recovering method of recovering PGM including heating and melting a treatment target member containing PGM together with a copper source material, and absorbing the PGM into a molten metal, and further disclose operability and a recovery ratio improving method (see patent document 1).

[0003]

Patent document 1 discloses a recovering method (described as "ROSE process" in the present invention in some

cases) of recovering PGM, wherein a treatment target member containing PGM and a copper source material containing copper oxide are charged into a sealed type electric furnace together with a flux component and a reducing agent, so as to be reduced and melted, then a molten metal essentially consisting of metal copper is settled under a molten slag layer essentially consisting of oxide, so that PGM is concentrated in the molten metal settled under the molten slag layer; and the molten metal in which the PGM is concentrated, is sorted from the molten slag and is shifted to another furnace in a molten state, and the molten metal is oxidized and melted in such another furnace, to thereby separate the layer into a slag layer essentially consisting of oxide and the molten metal layer in which the PGM is further concentrated, and in this dry-type recovering method of PGM, the molten slag layer with the content of copper reduced to $\leq 3.0\text{wt}\%$, is discharged from the electric furnace, and further by water-cooling the molten slag generated in such another furnace from a high temperature state, a granular copper source material containing the copper oxide with a diameter of 0.1 to 10 mm is obtained.

Prior Art Document

Patent document

[0004]

Japanese Patent Laid Open Publication No.2009-24263

Summary of the Invention

Problem to be solved by the Invention

[0005]

Inventors of the present invention make strenuous efforts and pursuit a further efficient recovering method of recovering PGM from a treatment target member, without satisfying with the above-mentioned outcome.

As a result, a distribution ratio of PGM (platinum, rhodium, palladium) in Cu_2O -molten copper when carrying out the above-mentioned oxidation smelting, indicates a large value of about 100 times the value of the distribution ratio in $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ -based slag-molten copper, when carrying out the reduction smelting. Therefore, it is found that a considerable amount of PGM is distributed into a Cu_2O slag in an oxidation furnace, which is generated in an oxidation smelting process of concentrating the PGM in copper. Then, since the considerable amount of PGM is distributed into the Cu_2O slag in the oxidation furnace, the recovery ratio of the PGM as Cu-PGM alloy is suppressed, with a result that the PGM distributed into the Cu_2O slag is circulated in a system of the ROSE process.

[0006]

From the above-mentioned knowledge, it is found by the inventors of the present invention, that if the distribution of the PGM into the Cu_2O slag can be suppressed in oxidation smelting, a PGM amount circulated in the system of the ROSE

process can be suppressed, then the recovery ratio of the PGM can be improved, and the time required for the recovery can be shortened.

Therefore, a subject to be solved by the present invention is to provide a method of suppressing the distribution of the PGM to the Cu_2O slag when carrying out the oxidation smelting in the PGM recovering method.

Means for solving the Problem

[0007]

As a result of further strenuous efforts by the inventors of the present invention, following breakthrough knowledge is obtained: namely, by adding Na_2O being basic oxide or SiO_2 being acidic oxide as oxide when carrying out the oxidation smelting, the distribution of the PGM to the Cu_2O slag can be suppressed. Thus, the present invention is completed.

[0008]

Namely, in order to solve the above-mentioned subject, a first invention provides a method of recovering PGM, including:

carrying out reduction smelting to a treatment target member containing PGM, Cu and/or Cu_2O , and flux, to thereby generate a molten slag and a Cu alloy containing PGM; and

oxidizing and melting the Cu alloy containing the PGM, to thereby generate the Cu_2O slag containing PGM and the Cu alloy, with more concentrated PGM concentration than the Cu

alloy containing the PGM,

wherein when carrying out the oxidation smelting, acidic oxide or basic oxide is added.

[0009]

A second invention provides the method of recovering PGM according to the first invention, wherein SiO_2 is used as the acidic oxide.

[0010]

A third invention provides the method of recovering PGM according to the second invention, wherein SiO_2 content in the Cu_2O slag containing the PGM, is set to 0.01 mass% or more and 10.0 mass% or less by adding the SiO_2 .

[0011]

A fourth invention provides the method of recovering PGM according to the first invention, wherein at least one kind selected from a group consisting of Na_2O , Na_2CO_3 , and NaHCO_3 , is used as the basic oxide.

[0012]

A fifth invention provides the method of recovering PGM according to claim 4, wherein Na_2O conversion content of the basic oxide in the Cu_2O slag containing the PGM, is set to 0.01 mass% or more and 20.0 mass% or less.

[0013]

A sixth invention provides the method of recovering PGM according to any one of the first to fifth inventions, wherein the Cu_2O slag containing PGM generated in the oxidation smelting

process, is charged to a reduction smelting process performed thereafter.

Advantage of the Invention

[0014]

According to the present invention, when carrying out the oxidation smelting, distribution of the PGM to the Cu_2O slag is suppressed, and a degree of the PGM concentration into the Cu alloy is increased, and therefore productivity of recovering PGM can be increased.

Brief description of the drawings

[0015]

FIG. 1 is a step flowchart of PGM recovery according to the present invention.

FIG. 2 is a step flowchart of the PGM recovery according to a conventional technique.

FIG. 3 is a graph showing a distribution ratio of Pt, Rh, and Pd in Cu_2O - SiO_2 based slag and molten copper.

FIG. 4 is a graph showing the distribution ratio of Pt, Rh, and Pd in Cu_2O - Na_2O based slag and molten copper.

FIG. 5 is a mass flowchart in a case of setting SiO_2 addition amount to 2 mass% as acidic oxide, and setting Cu amount to 100kg.

FIG. 6 is a mass flowchart in a case of setting SiO_2 addition amount to 5 mass% as acidic oxide, and setting Cu

amount to 100kg.

FIG. 7 is a mass flowchart in a case of setting the Cu amount to 100kg without adding SiO_2 as the acidic oxide.

FIG. 8 is a mass flowchart in a case of setting SiO_2 addition amount to 2 mass% as the acidic oxide, and setting the Cu amount to 50kg.

FIG. 9 is a mass flowchart in a case of setting the SiO_2 addition amount to 5 mass% as the acidic oxide, and setting the Cu amount to 50kg.

FIG. 10 is a mass flowchart in a case of setting the Cu amount to 50kg without adding SiO_2 as the acidic oxide.

Modes for carrying out the Invention

[0016]

First, a ROSE process of a conventional technique will be briefly described, with reference to the drawings.

FIG. 2 is a flowchart of a ROSE process according to a conventional technique.

A treatment target member containing PGM (for example, ceramics automobile catalyst (2)), Cu(3) being an extracting agent, flux (CaO , SiO_2 (1)), and a C-containing material (4) being a reducing agent, are charged into a reducing furnace, to thereby carry out reduction smelting (5). Then, a molten metal of the Cu alloy (6) is settled under a molten slag ($\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag (7)) layer essentially composed of oxide, and PGM is concentrated into the Cu alloy (6) settled thereunder.

Meanwhile, $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag in which Cu content is reduced to 3.0 mass% or less, is discharged from the electric furnace.

By shifting the Cu alloy (6), in which PGM is concentrated, to the oxidation furnace in a molten state, and applying the oxidation smelting (9) thereto, a layer is divided into a Cu_2O slag (11) layer mainly composed of oxide, and a molten metal (Cu-PGM alloy (10)) layer in which the PGM is further concentrated.

The Cu_2O slag (11) layer mainly composed of oxide generated on a surface of molten metal, is discharged to outside of the furnace, and oxidation treatment and discharge treatment of the oxide layer are repeated in the oxidation furnace, to thereby concentrate the PGM content in the molten metal (Cu-PGM alloy(10)) layer in which the PGM is further concentrated, until the concentration of the PGM is 10 to 75%.

[0017]

However, as described above, the distribution ratio of platinum, rhodium, and palladium in the Cu_2O slag(11)-Cu-PGM alloy(10) when carrying out the oxidation smelting, is a large value of about 100 times the distribution ratio in $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7)-Cu alloy(6) when carrying out the reduction smelting(5). Therefore, a considerable amount of PGM is distributed into the Cu_2O slag(11) generated in a process of concentrating the PGM in the Cu alloy. As a result, the considerable amount of PGM contained in the initial treatment target member (for example, ceramics automobile catalyst(2))

is distributed into the Cu_2O slag generated when carrying out the oxidation smelting(9). The Cu_2O slag (11) is returned to the reduction smelting(5), and therefore the recovering ratio of PGM as Cu-PGM alloy(10) is suppressed, and the PGM distributed into the Cu_2O slag is circulated in the system of the ROSE PROCESS.

[0018]

It is found by the inventors of the present invention, that the distribution of PGM to the generated Cu_2O slag can be reduced by adding oxide, when carrying out oxidation smelting(9).

Therefore, first, as a preliminary test, Na_2O being the basic oxide, or SiO_2 being the acidic oxide, is added to the Cu_2O slag as oxide, and the distribution of Pt, Rh, and Pd in Cu_2O melt-molten copper is measured at 1250°C .

[0019]

A measurement test method will be described.

<Preparation of a sample>

5g of metal Cu and 5g of Cu_2O regarded as slag, were weighed. Then, SiO_2 or Na_2CO_3 were weighed so that SiO_2 , Na_2O content were 0 mass%, 2 mass%, 5 mass%, and 7 mass%, with respect to the mass of Cu_2O regarded as the slag. Next, 100mg of Pt, Rh, and Pd, which was 1 mass%, were weighed, with respect to 5g of metal Cu and 5g of Cu_2O regarded as the slag, namely 10g of them in total.

Then, SiO_2 or Na_2CO_3 weighed as oxidizing agent, were

respectively added into a sample in which metal Cu and Cu_2O were mixed, and weighed Pt, Rh, and Pd were further added to each of the obtained samples.

[0020] <Melting of samples>

Final samples were respectively charged into magnesia crucible, and were melted and retained for 1 hour at 1250°C .

The sample obtained by being melted, retained, and cooled, was separated into a metal copper phase and a slag phase.

Regarding a composition analysis of the metal copper phase and the slag phase in the sample after being melted, Na_2O was quantitatively determined using atomic absorption spectrometry, and the other element was quantitatively analyzed by an ICP-AES method.

[0021] <Measurement result>

First, PGM distribution ratio in the Cu_2O -based slag and the Cu alloy was measured, in the case of not adding oxide at 1250°C .

Results thereof are shown in table 1.

[0022] [Table 1]

Pt	Rh	Pd
0.05	0.008	0.025

[0023]

Next, FIG. 3 shows the distribution ratio of Pt, Rh, Pd in the Cu_2O slag and the Cu alloy in the case of adding SiO_2 as oxide.

FIG. 3 is a graph in which $L^{s/Cu}_x$ logarithmic value is taken on the vertical axis, and the concentration of SiO_2 in the Cu_2O slag is taken on the horizontal axis by mass%, wherein Pt is plotted by $\bigcirc$ and connected by solid line, and Rh is plotted by $\triangle$ and connected by short broken line, and Pd is plotted by $\square$ and connected by long broken line.

Note that $L^{s/Cu}_x$ is the PGM distribution ratio in the Cu_2O -based slag and molten copper, and is defined by (formula 1).

$$L^{s/Cu}_x = (\text{mass\% of X in the slag phase}) / [\text{mass\% of X in the molten copper phase}] \dots (\text{Formula 1})$$

Wherein X indicates Pt, Rh, Pd, and () indicates a value related to the slag phase, and [] indicates a value related to the molten copper phase.

[0024]

From FIG. 3, it is found that the distribution ratio of Pt, Rh, Pd is reduced, with increase of SiO_2 addition concentration to an oxidation smelting process. The distribution ratio of Pt, Rh, Pd of the Cu_2O slag containing 3 to 4 mass% of SiO_2 , is a value of 1/3 to 1/2 of pure Cu_2O slag, and is stabilized from 5 mass% or more. Further, it is confirmed that the distribution ratio is reduced to 10 mass% level of SiO_2 .

Therefore, addition of SiO_2 with respect to the weight of the Cu_2O slag in the oxidation smelting process, may be adjusted in a range of 0.01 to 10.0 mass%, preferably 2.0 to

8.0 mass%, and more preferably 3.0 to 5.0 mass%. Thus, the PGM amount distributed to the Cu_2O slag is suppressed, and a recovering efficiency of PGM can be increased. Note that when the SiO_2 addition amount exceeds 10.0 mass%, an addition effect is easily saturated.

[0025]

Further, FIG. 4 shows the distribution ratio of Pt, Rh, Pd in the Cu_2O slag and the Cu alloy in the case of adding Na_2O as oxide.

Similarly to FIG. 3, FIG. 4 is a graph in which $L^{s/\text{Cu}}_x$ logarithmic value is taken on the vertical axis, and the concentration of SiO_2 in the Cu_2O slag is taken on the horizontal axis by mass%, wherein Pt is plotted by $\bigcirc$ and connected by solid line, and Rh is plotted by $\triangle$ and connected by short broken line, and Pd is plotted by $\square$ and connected by long broken line.

[0026]

From FIG. 4, it is found that the distribution ratio of Pt, Rh, Pd is reduced, with increase of Na_2O concentration in the slag before the oxidation smelting process. The distribution ratio of Pt, Rh, Pd of the Cu_2O slag containing 5 mass% of Na_2O , is a value of 4/5 to 1/3 of pure Cu_2O slag, and is stabilized from 9 mass% or more. Further, it is confirmed that the distribution ratio is reduced to 20 mass% level of Na_2O .

Therefore, in the oxidation smelting process, a basic

oxide content (Na_2O conversion content of the basic oxide) converted to Na_2O in the weight of the Cu_2O slag, may be adjusted in the range of 0.01 to 20.0 mass%, preferably 5.0 to 20.0 mass%, and more preferably 9.0 to 10.0 mass%. Thus, the PGM amount distributed to the Cu_2O slag is suppressed, and the recovering efficiency of PGM can be increased. Note that when the Na_2O conversion content of the basic oxide exceeds 20.0 mass%, an addition effect is easily saturated.

[0027]

From the above-mentioned test result, it is found that by adding SiO_2 being the acidic oxide or Na_2O being the basic oxide as oxide when carrying out oxidation smelting, the distribution ratio of PGM in the Cu_2O slag and the Cu alloy is small compared with a case that the oxide is not added, and the PGM concentration in the Cu_2O slag can be reduced.

[0028]

Here, brief explanation is given for a consideration why the distribution ratio of PGM in the Cu_2O slag and the molten copper is reduced in the Cu_2O slag to which oxide is added.

The distribution ratio of PGM in Al_2O_3 - CaO - SiO_2 based slag and the Cu alloy, becomes small, with reduction of an oxygen partial pressure. It seems that this is because the oxide of PGM is hardly generated due to the reduction of the oxygen partial pressure and a copper dissolution degree in the slag becomes small. The degree of the dissolution into the molten Cu_2O slag of PGM is large, compared with the Al_2O_3 - CaO - SiO_2 slag.

Therefore, it can be considered that an attractive force works between the PGM and the Cu_2O slag, although this is an abstract expression.

[0029]

Meanwhile, it is known that N_2O is the basic oxide, SiO_2 is the acidic oxide, and Cu_2O is neutral oxide (amphoteric oxide). It can be considered that a property of the Cu_2O slag is changed by adding strongly basic Na_2O or strongly acid SiO_2 into Cu_2O which is the amphoteric oxide, and a bonding force by neutralization occurs between the Cu_2O , and Na_2O or SiO_2 , and therefore an attractive force between the Cu_2O and the PGM is relatively weakened. Thus, it can be considered that the attractive force between the Cu_2O and the PGM is weakened, and therefore the PGM is hardly distributed to the Cu_2O slag.

[0030]

Here, brief explanation is given for the ROSE process of the present invention, with reference to the drawings.

FIG. 1 is a flowchart of the ROSE process of the present invention.

The treatment target member containing PGM (for example, ceramics automobile catalyst (2)), Cu (3) being an extracting agent, flux (CaO , SiO_2 (1)), and a C-containing material (4) being a reducing agent, are charged into a reducing furnace, to thereby carry out reduction smelting (5). Then, a molten metal of the Cu alloy (6) is settled under a molten slag ($\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag (7)) layer essentially composed of oxide,

and platinum group metals are concentrated in the Cu alloy (6) settled thereunder. Meanwhile, the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag (7) in which Cu content is reduced to 3.0 mass% or less, is discharged from the electric furnace, similarly to the ROSE process of the conventional technique.

[0031]

When the Cu alloy (6) in which PGM is concentrated, is shifted to the oxidation furnace in the molten state and the oxidation smelting (9) is applied thereto, SiO_2 or Na_2O is added as the above-mentioned oxide (8), to thereby separate the layer into the Cu_2O slag (11) layer mainly composed of oxide, and the molten metal (Cu-PGM alloy (10)) layer in which the PGM is further concentrated. Then, the Cu_2O slag (11) is returned to the reduction smelting (5).

Here, the distribution ratio of PGM in the Cu_2O slag (11) and the Cu-PGM alloy (10) becomes small by adding oxide (8), compared with a case that the oxide (8) is not added, and therefore the PGM concentration in the Cu_2O slag (11) can be reduced. As a result, the PGM amount circulated in the ROSE process can also be reduced.

Examples

[0032]

Based on the above-mentioned test result, a distribution behavior of Pt in the ROSE process of the present invention is examined.

[0033] [Example 1]

In example 1, an Al_2O_3 automobile catalyst (ceramics automobile catalyst) as the treatment target member was pulverized, and a quantitative analysis was performed by the ICP-AES method after reduction. As a result, it was found that 0.5 mass% of Pt was contained.

[0034]

An operation condition for example 1 will be described.

<1> 853kg, and 995kg of CaO, SiO_2 (1) were prepared respectively as flux.

<2> 1000kg of the Al_2O_3 automobile catalyst (2) was used as the treatment target member.

<3> 100kg of Cu (3) was used as the extracting agent.

<4> SiO_2 (8) was used as oxide contained in the Cu_2O slag.

Mass% of (SiO_2) was adjusted to three levels of 2 mass%, 5 mass%, and 0 mass%.

<5> Cokes (4) was added as the reducing agent, by an amount described later according to the amount of the oxide.

[0035] <Case of 2 mass% of SiO_2 >

The distribution behavior of Pt in the ROSE process of the present invention will be described, with reference to FIG. 5.

[0036]

853kg, 995kg of CaO and SiO_2 (1) as flux (prepared so that a slag composition was CaO:30 mass%, and SiO_2 :35 mass%), and 1000kg of Al_2O_3 automobile catalyst (2) as the treatment target

member, 100kg of Cu(3) as the extracting agent, and 15.5kg of cokes(4) as the reducing agent, were prepared when carrying out a first reduction smelting (5).

They were charged into an electric furnace, and retained under reducing atmosphere, at 1450°C, for 6 hours, in a sealed state, to thereby carry out the first reduction smelting (5). As a result, the molten metal of the Cu alloy (6) was settled under the CaO-SiO₂-Al₂O₃ slag (7). The Pt amount in the CaO-SiO₂-Al₂O₃ was 0.04030kg, and the Pt amount in the Cu alloy (6) was 4.9597kg. By using these values, 0.0003 of the distribution ratio of Pt was obtained in the reduction smelting (5) calculated by the above-mentioned formula (1).

[0037]

The molten metal of the Cu alloy (6) was shifted to the oxidation furnace, and 2.26kg of SiO₂(8) was added thereto so that the content of the SiO₂(8) was 2 mass% with respect to the Cu₂O slag, on the premise that a mass ratio of the Cu alloy(6) and the Cu₂O slag(11) was around 1:17, and was retained for 6 hours at 1300°C under oxidation atmosphere condition in which 40% oxygen was flowed therein at 30L/h.

Meanwhile, the CaO-SiO₂-Al₂O₃ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu₂O slag(11) layer. The Pt amount in the Cu₂O slag(11) was 1.693kg. The Pt amount in the Cu-PGM alloy(10) was 3.267kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting (9) calculated using the

above-mentioned values, was 0.03.

[0038]

The obtained Cu₂O slag(11), CaO and SiO₂(1) as flux (wherein CaO:30 mass% and SiO₂:35 mass% were prepared as slug compositions), 1000kg of Al₂O₃ automobile catalyst(2) as the treatment target member, additional Cu(3) as the extracting agent, and cokes (4) as the reducing agent, were prepared.

Here, 96.73kg of Cu and 2.26kg of SiO₂ were contained in the Cu₂O slag(11). Therefore, 853kg, 993kg of CaO and SiO₂(1) were prepared as flux, and 3.27kg of Cu(3) was prepared as the extracting agent, and 24.7kg of cokes(4) was prepared as the reducing agent.

[0039]

They were charged into the electric furnace, and a second reduction smelting(5) was carried out under the same condition as the first time, excluding a point that 24.7kg of cokes(4) was used as the reducing agent. As a result, the molten metal of the Cu alloy(6) was settled under the CaO-SiO₂-Al₂O₃ slag(7) layer. The Pt amount in the CaO-SiO₂-Al₂O₃ slag(7) layer was 0.05301kg, and the Pt amount in the Cu alloy(6) was 6.637kg. The distribution ratio of Pt in the reduction smelting(5) calculated using these values, was 0.0003.

[0040]

The molten metal of the Cu alloy(6) was shifted to the oxidation furnace, and 2.22kg of SiO₂(8) was added, so that the content of the SiO₂(8) was 2 mass% with respect to the Cu₂O

slag, on the premise that the mass ratio of the Cu alloy(6) and the Cu₂O slag(11) was around 1:11, and a second oxidation smelting(9) was carried out under the same condition as the first time. Meanwhile, the CaO-SiO₂-Al₂O₃ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu₂O slag(11) layer.

The Pt amount in the Cu₂O slag(11) was 1.663kg. The Pt amount in the Cu-PGM alloy(10) was 4.974kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using the above-mentioned values, was 0.03.

[0041]

The obtained Cu₂O slag(11), CaO and SiO₂(1) as flux (wherein CaO:30 mass% and SiO₂:35 mass% were prepared as slug compositions), 1000kg of Al₂O₃ automobile catalyst(2) as the treatment target member, and additional Cu(3) as the extracting agent, were prepared.

Here, 95.03kg of Cu and 2.22kg of SiO₂ were contained in the Cu₂O slag(11). Therefore, 853kg, 993kg of CaO and SiO₂(1) were prepared as flux, and 4.97kg of Cu(3) was prepared as the extracting agent.

[0042]

They were charged into the electric furnace, and a reduction smelting(5) was carried out three times under the same condition as the first time, excluding a point that 24.2kg

of cokes(4) was used as the reducing agent. As a result, the molten metal of the Cu alloy(6) was settled under the CaO-SiO₂-Al₂O₃ slag(7) layer. The Pt amount in the CaO-SiO₂-Al₂O₃ slag(7) layer was 0.05279kg, and the Pt amount in the Cu alloy(6) was 6.607kg. The distribution ratio of Pt in the reduction smelting(5) calculated using these values, was 0.0003.

[0043]

The molten metal of the Cu alloy(6) was shifted to the oxidation furnace, and further 2.22kg of SiO₂(8) was added thereto, so that the content of the SiO₂(8) was 2 mass% with respect to the Cu₂O slag, on the premise that the mass ratio of the Cu alloy(6) and the Cu₂O slag(11) was around 1:11, and a third oxidation smelting(9) was carried out under the same condition as the first time. Meanwhile, the CaO-SiO₂-Al₂O₃ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu₂O slag(11) layer. The Pt amount in the Cu₂O slag(11) was 1.664kg. The Pt amount in the Cu-PGM alloy(10) was 4.943kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using these values, was 0.03.

[0044]

As described above, 3000kg (Pt:15kg) of the Al₂O₃ automobile catalyst(2) was treated by reduction smelting(5) and oxidation smelting(9) three times, to thereby obtain

13.184kg of Pt in the Cu-PGM alloy(10) in total (first 3.267kg + second 4.974kg + third 4.943kg), as Pt in the Cu-PGM alloy(10). Meanwhile, Pt in the ROSE process was 1.664kg.

[0045] <A case of 5 mass% of SiO₂>

Next, with reference to FIG. 6, explanation is given for the distribution behavior of Pt in the ROSE process of the present invention in a case that the SiO₂(8) content is set to 5 mass%, which is the oxide in the Cu₂O slag(11) containing PGM.

Note that FIG. 6 is a view showing a mass flow when the addition amount of SiO₂(8) as oxide, is set to 5 mass%, which is the above-mentioned operation condition.

[0046]

Similarly to the above-mentioned <the case of 2 mass% of SiO₂>, 853kg, 995kg of CaO and SiO₂(1) as the flux (prepared so that the slag composition was CaO:30 mass%, and SiO₂:35 mass%)., 1000kg of Al₂O₃ automobile catalyst(2) as the treatment target member, 100kg of Cu(3) as the extracting agent, and 15.4kg of cokes as the reducing agent, were prepared when carrying out a first reduction smelting (5).

They were charged into the electric furnace, to thereby carry out the first reduction smelting (5) similarly to <the case of 2 mass% of SiO₂>. As a result, the molten metal of the Cu alloy (6) was settled under the CaO-SiO₂-Al₂O₃ slag (7). The Pt amount in the CaO-SiO₂-Al₂O₃ was 0.04030kg, and the Pt amount in the Cu alloy (6) was 4.9597kg. By using these values, 0.0003

of the distribution ratio of Pt was calculated in the reduction smelting (5).

[0047]

The molten metal of the Cu alloy (6) was shifted to the oxidation furnace, and 5.76kg of SiO_2 (8) was added so as to be 5 mass% with respect to the Cu_2O slag, on the premise that the mass ratio of the Cu alloy(6) and the Cu_2O slag(11) was around 1:15, to thereby carrying out the first oxidation smelting(9) similarly to <the case of 2 mass% of SiO_2 >. Meanwhile, the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu_2O slag(11) layer. The Pt amount in the Cu_2O slag(11) was 1.152kg. The Pt amount in the Cu-PGM alloy(10) was 3.808kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using the above-mentioned values, was 0.02.

[0048]

The obtained Cu_2O slag(11), CaO and SiO_2 (1) as flux, 1000kg of Al_2O_3 automobile catalyst(2) as the treatment target member, and additional Cu(3) as the extracting agent, were prepared.

Here, 96.19kg of Cu and 5.76kg of SiO_2 were contained in the Cu_2O slag(11). Therefore, 853kg, 989kg of CaO and SiO_2 (1) were prepared as flux, and 3.81kg of Cu was prepared as the extracting agent.

[0049]

They were charged into the electric furnace, and the second reduction smelting(5) was carried out under the same condition as the first time, excluding a point that 24.5kg of cokes(4) was used as the reducing agent. As a result, the molten metal of the Cu alloy(6) was settled under the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) layer. The Pt amount in the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) layer was 0.04892kg, and the Pt amount in the Cu alloy(6) was 6.101kg. The distribution ratio of Pt in the reduction smelting(5) calculated using these values, was 0.0003.

[0050]

The molten metal of the Cu alloy(6) was shifted to the oxidation furnace, and 5.69kg of SiO_2 (8) was added so as to be 5 mass% with respect to the Cu_2O slag, on the premise that the mass ratio of the Cu alloy(6) and the Cu_2O slag(11) was around 1:11, to thereby carry out the second oxidation smelting(9) under the same condition as the first time. Meanwhile, the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) containing 50% Pt was settled under the Cu_2O slag(11) layer. The Pt amount in the Cu_2O slag(11) was 1.138kg. The Pt amount in the Cu-PGM alloy(10) was 4.963kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using the above-mentioned values, was 0.02.

[0051]

The obtained Cu₂O slag(11), CaO and SiO₂(1) as flux, 1000kg of Al₂O₃ automobile catalyst(2) as the treatment target member, and additional Cu(3) as the extracting agent, were prepared.

Here, 95.04kg of Cu and 5.69kg of SiO₂ were contained in the Cu₂O slag(11). Therefore, 853kg, 989kg of CaO and SiO₂(1) were prepared as flux, and 4.96kg of Cu was prepared as the extracting agent.

[0052]

They were charged into the electric furnace, and the reduction smelting(5) was carried out three times under the same condition as the first time, excluding the point that 24.2kg of cokes(4) was used as the reducing agent. As a result, the molten metal of the Cu alloy(6) was settled under the CaO-SiO₂-Al₂O₃ slag(7) layer. The Pt amount in the CaO-SiO₂-Al₂O₃ slag(7) layer was 0.04885kg, and the Pt amount in the Cu alloy(6) was 6.091kg. The distribution ratio of Pt in the reduction smelting(5) calculated using these values, was 0.0003.

[0053]

The molten metal of the Cu alloy(6) was shifted to the oxidation furnace, and 5.69kg of SiO₂(8) was added so as to be 5 mass% with respect to the Cu₂O slag, on the premise that the mass ratio of the Cu alloy(6) and the Cu₂O slag(11) was around 1:11, to thereby carry out the third oxidation

smelting(9) under the same condition as the first time. Meanwhile, the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu_2O slag(11) layer. The Pt amount in the Cu_2O slag(11) was 1.138kg. The Pt amount in the Cu-PGM alloy(10) was 4.953kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using the above-mentioned values, was 0.02.

[0054]

As described above, 3000kg (Pt:15kg) of the Al_2O_3 automobile catalyst(2) was treated by the reduction smelting(5) and oxidation smelting(9) three times, to thereby obtain 13.724kg of Pt in the Cu-PGM alloy(10) in total (first 3.808kg + second 4.963kg + third 4.953kg) as Pt in the Cu-PGM alloy(10). Meanwhile, Pt in the ROSE process was 1.138kg.

[0055] <The case of 0 mass% of SiO_2 >

Next, with reference to FIG. 7, explanation is given for the distribution behavior of Pt in the ROSE process of the present invention in the case that the SiO_2 (8) content is not added as oxide.

Note that FIG. 7 is a view showing a mass flow when the SiO_2 (8) is not added as oxide, which is the above-mentioned operation condition.

[0056]

Similarly to the above-mentioned <the case of 2 mass%

of SiO_2 >, 853kg, 995kg of CaO and SiO_2 (1) as flux (prepared so that the slag composition was CaO:35 mass%, and SiO_2 :30 mass%).), and 1000kg of Al_2O_3 automobile catalyst(2) as the treatment target member, 100kg of Cu(3) as the extracting agent, and 15.7kg of cokes as the extracting agent, were prepared when carrying out the first reduction smelting (5).

They were charged into the electric furnace, to thereby carry out the first reduction smelting (5) similarly to <the case of 2 mass% of SiO_2 >. As a result, the molten metal of the Cu alloy (6) was settled under the CaO- SiO_2 - Al_2O_3 slag (7). The Pt amount in the CaO- SiO_2 - Al_2O_3 was 0.04030kg, and the Pt amount in the Cu alloy (6) was 4.9597kg. By using these values, 0.0003 of the distribution ratio of Pt was obtained in the reduction smelting (5) calculated by the above-mentioned values.

[0057]

The molten metal of the Cu alloy (6) was shifted to the oxidation furnace, and similarly to <the case of 2 mass% of SiO_2 >, the first oxidation smelting(9) was carried out without adding SiO_2 (8) as oxide. Meanwhile, the CaO- SiO_2 - Al_2O_3 slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu_2O slag(11) layer. Since the distribution ratio of Pt in this oxidation smelting(9) was 0.05, the Pt amount in the Cu_2O slag(11) was 2.825kg, and the Pt amount in the Cu-PGM alloy(10) was 2.135KG, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9)

calculated using the above-mentioned values, was 0.05.

[0058]

The obtained Cu_2O slag(11), CaO and $\text{SiO}_2(1)$ as flux, 1000kg of the Al_2O_3 automobile catalyst (2) as the treatment target member, and additional $\text{Cu}(3)$ as the extracting agent, were prepared.

Here, 97.87kg of Cu was contained in the Cu_2O slag(11). Therefore, 853kg, 995kg of CaO and $\text{SiO}_2(1)$ were prepared as flux, and 2.13kg of $\text{Cu}(3)$ was prepared as the extracting agent.

[0059]

They were charged into the electric furnace, and the second reduction smelting(5) was carried out under the same condition as the first time, excluding the point that 24.9kg of cokes(4) was used as the reducing agent. As a result, the molten metal of the Cu alloy(6) was settled under the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) layer. The Pt amount in the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) layer was 0.06142kg, and the Pt amount in the Cu alloy(6) was 7.769kg. The distribution ratio of Pt in the reduction smelting(5) calculated using these values, was 0.0003.

[0060]

The molten metal of the Cu alloy(6) was shifted to the oxidation furnace, and the second oxidation smelting(9) was carried out under the same condition as the first time, without adding $\text{SiO}_2(8)$ as oxide. Meanwhile, the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu₂O slag(11) layer. The Pt amount in the Cu₂O slag(11) was 2.742kg. The Pt amount in the Cu-PGM alloy(10) was 5.027kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using these values, was 0.05.

[0061]

The obtained Cu₂O slag(11), CaO and SiO₂(1) as flux, 1000kg of Al₂O₃ automobile catalyst(2) as the treatment target member, and additional Cu(3) as the extracting agent, were prepared.

Here, 94.97kg of Cu was contained in the Cu₂O slag(11). Therefore, 853kg, 995kg of CaO and SiO₂(1) were prepared as flux, and 5.03kg of Cu(3) was prepared as the extracting agent.

[0062]

They were charged into the electric furnace, and the reduction smelting(5) was carried out three times under the same condition as the first time, excluding the point that 24.2kg of cokes(4) was used as the reducing agent. As a result, the molten metal of the Cu alloy(6) was settled under the CaO-SiO₂-Al₂O₃ slag(7) layer. The Pt amount in the CaO-SiO₂-Al₂O₃ slag(7) layer was 0.06077kg, and the Pt amount in the Cu alloy(6) was 7.679kg. The distribution ratio of Pt in the reduction smelting(5) calculated using these values, was 0.0003.

[0063]

The molten metal of the Cu alloy(6) was shifted to the oxidation furnace, to thereby carry out the third oxidation smelting(9) under the same condition as the first time, without adding SiO_2 (8) as oxide. Meanwhile, the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag(7) was discarded.

As a result, the Cu-PGM alloy(10) was settled under the Cu_2O slag(11) layer. The Pt amount in the Cu_2O slag(11) was 2.744kg. The Pt amount in the Cu-PGM alloy(10) was 4.935kg, and 50% Pt was contained therein. The distribution ratio of Pt in this oxidation smelting(9) calculated using the above-mentioned values, was 0.05.

[0064]

As described above, 3000kg (Pt:15kg) of the Al_2O_3 automobile catalyst(2) was treated by the reduction smelting(5) and oxidation smelting(9) three times, to thereby obtain 12.097kg of Pt in the Cu-PGM alloy(10) in total (first 2.135kg + second 5.027kg + third 4.935kg), as Pt in the Cu-PGM alloy(10). Meanwhile, Pt in the ROSE process was 2.744kg.

[0065] [Example 2]

The Al_2O_3 automobile catalyst(2) being the treatment target member, was treated under a similar operation condition as example 1, excluding a point that 50kg of Cu(3) as the extracting agent, was prepared.

[0066] <The case of 2 mass% of SiO_2 >

FIG. 8 shows the distribution behavior of Pt in the ROSE

process of the present invention, when SiO_2 (8) being the oxide in the Cu_2O slag(11) containing PGM is set to 2 mass%, on the premise that the mass ratio of the Cu alloy(6) and the Cu_2O slag(11) is around 1:6 (first to third times). In this figure, the same description method as example 1 is used.

[0067]

3000kg (Pt:15kg) of the Al_2O_3 automobile catalyst(2) was treated by the reduction smelting(5) and oxidation smelting(9) three times, to thereby obtain 13.956kg of Pt in the Cu-PGM alloy(10) in total (first 4.120kg + second 4.923kg + third 4.913kg), as Pt in the Cu-PGM alloy(10). Meanwhile, Pt in the ROSE process was 0.789kg.

[0068] <The case of 5 mass% of SiO_2 >

FIG.9 shows the distribution behavior of Pt in the ROSE process of the present invention, when SiO_2 (8) being the oxide in the Cu_2O slag(11) containing PGM is set to 5 mass%, on the premise that the mass ratio of the Cu alloy(6) and the Cu_2O slag(11) is around 1:6 (first to third times). In this figure, the same description method as example 1 is used.

[0069]

3000kg (Pt:15kg) of the Al_2O_3 automobile catalyst(2) was treated by the reduction smelting(5) and oxidation smelting(9) three times, to thereby obtain 14.219kg of Pt in the Cu-PGM alloy(10) in total (first 4.377kg + second 4.926kg + third 4.916kg), as Pt in the Cu-PGM alloy(10). Meanwhile, Pt in the ROSE process was 0.540kg.

[0070] <The case of 0 mass% of SiO₂>

Next, FIG. 10 shows the distribution behavior of Pt in the ROSE process of the present invention in the case of not adding SiO₂(8) as oxide. The description method in this figure is the same as example 1.

[0071]

3000kg (Pt:15kg) of the Al₂O₃ automobile catalyst(2) was treated by the reduction smelting(5) and oxidation smelting(9) three times, to thereby obtain 13.43kg of Pt in the Cu-PGM alloy(10) in total (first 3.583kg + second 4.944kg + third 4.903kg), as Pt in the Cu-PGM alloy(10). Meanwhile, Pt in the ROSE process was 1.302kg.

[0072] [Conclusion]

As described above, regarding the distribution behavior of Pt in the ROSE process of the present invention shown in FIG. 5 to FIG. 10 in examples 1 and 2, results were totaled, from a viewpoint of the Pt mass (three times in total) in the Cu-PGM alloy, the Pt mass (third time) in the Cu₂O slag, and the Pt mass (three times in total) in the CaO-SiO₂-Al₂O₃ slag, and the results are shown in table 2.

[0073]

From table 2, it is found that the Pt amount circulated in the ROSE process can be remarkably reduced in both of the examples 1 and 2, by adding SiO₂ when carrying out the oxidation smelting. Meanwhile, the Pt mass (three times in total) in the Cu-PGM alloy was increased. On the other hand, the Pt mass

in the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag is also reduced, with remarkable reduction of the Pt amount circulated in the ROSE process.

As described above, by adding the acidic oxide or the basic oxide like SiO_2 in the process of the oxidation smelting of the ROLSE process, a preferable result of improving productivity can be obtained from the viewpoint of each of the Pt mass in the Cu-PGM alloy, the Pt mass in the Cu_2O slag, and the Pt mass in the $\text{CaO-SiO}_2\text{-Al}_2\text{O}_3$ slag.

[0074]

Further, it can be considered that the above-mentioned effects of examples 1 and 2 can be exhibited in PGM, from a behavior comparison between Pt, and Rh, Pd described in the "Modes for carrying out the invention". Also, it can be considered that the effects of the examples 1 and 2 can be exhibited even when the basic oxide is added into the Cu_2O slag, from the behavior comparison between SiO_2 added into the Cu_2O slag, and at least one kind selected from a group consisting of SiO_2 , Na_2O , Na_2CO_3 and NaHCO_3 , similarly as described in the "Mode for carrying out the invention".

[0075] [Table 2]

Cu charging amount for every time	SiO ₂ addition amount for every time	Pt weight (three times in total) in Cu-PGM alloy	Pt weight (third time) in CuO ₂ slag	Pt weight (three times in total) in CaO-SiO ₂ -Al ₂ O ₃ slag
(Kg)	(mass %)	(Kg)	(Kg)	(Kg)
100	2	13. 184	1. 664	0. 14686
	5	13. 724	1. 138	0. 13889
	—	12. 097	2. 744	0. 1627
50	2	13. 956	0. 789	0. 25228
	5	14. 219	0. 54	0. 24544
	—	13. 43	1. 302	0. 27012

Claims

1. A method of recovering Platinum Group Metals (PGM), comprising:

carrying out reduction smelting to a treatment target member containing PGM, Cu and/or Cu_2O , and flux, to thereby generate a molten slag and a Cu alloy containing PGM; and

oxidizing and melting the Cu alloy containing the PGM, to thereby generate a Cu_2O slag containing PGM and the Cu alloy, with more concentrated PGM concentration than the Cu alloy containing the PGM,

wherein when carrying out the oxidation smelting, SiO_2 used as acidic oxide or at least one kind selected from a group consisting of Na_2O , Na_2CO_3 , and NaHCO_3 used as basic oxide is added.

2. The method of recovering PGM according to claim 1, wherein SiO_2 content in the Cu_2O slag containing the PGM, is set to 0.01 mass% or more and 10.0 mass% or less by adding the SiO_2 .

3. The method of recovering PGM according to claim 1, wherein Na₂O conversion content of the basic oxide in the Cu_2O slag containing the PGM, is set to 0.01 mass% or more and 20.0 mass% or less.

4. The method of recovering PGM according to any one of claims 1 to 3, wherein the Cu_2O slag containing PGM generated in the oxidation smelting process, is charged to a reduction smelting process performed thereafter.

FIG.1




FIG.2 - PRIOR ART




FIG. 3




FIG.4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG.10

