

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 April 2007 (05.04.2007)

PCT

(10) International Publication Number
WO 2007/038220 A2

- (51) International Patent Classification: Not classified
- (21) International Application Number: PCT/US2006/036881
- (22) International Filing Date: 21 September 2006 (21.09.2006)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 11/235,743 27 September 2005 (27.09.2005) US
- (71) Applicant (for all designated States except US): **BOSTON SCIENTIFIC SCIMED, INC** [US/US]; One Scimed Place, Maple Grove, Minnesota 55311 (US).
- (72) Inventors: **ZOROMSKI, Michele**; 3316 Pillsbury Avenue, Minneapolis, Minnesota 54408 (US). **ATANA-SOSKA, Liliana**; 5209 Windsor Avenue, Edina, Minnesota 55436 (US). **SCHEWE, Scott**; 6300 Duck Lane Rd, Eden Prairie, Minnesota 55346 (US). **WOLTERS, Mark**; 672 Arlington Avenue East, St. Paul, Minnesota 55106 (US). **WARNER, Robert**; 1665 Lamplight Dr., Woodbury, Minnesota 55125 (US).
- (74) Agent: **STEINKRAUS, Walter**; 6109 Blue Circle Drive Suite 2000, Minnetonka, Minnesota 55343 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2007/038220 A2

(54) Title: ORGANIC-INORGANIC HYBRID PARTICLE MATERIAL AND POLYMER COMPOSITIONS CONTAINING SAME

(57) Abstract: Particulate materials useful as fillers, reinforcing agents, radioopacifiers, or impact modifiers. The particulate material has an average particle size range of about 10,000 nm or less and comprises an organic-inorganic hybrid material that has a ceramic material network having organic polymer segments distributed throughout the ceramic network. The ceramic network may be prepared by a sol-gel technique. The particulate material may be compounded in thermoplastic polymer compositions useful in a variety of applications such as preparation of medical device components.

TITLE

**ORGANIC-INORGANIC HYBRID PARTICLE MATERIAL
AND POLYMER COMPOSITIONS CONTAINING SAME**

5

BACKGROUND OF THE INVENTION

Ceramic sol-gel compositions that have sites that will crosslink into a polymer
10 network are known. Such compositions may be formulated with cureable monomers to
produce radiation curing compositions, for instance.

Compositions of thermoplastic polymers and particulate ceramic and metal nano-
particles particles are known. For instance, fumed and colloidal silicas have wide uses in
polymer compositions as fillers and reinforcing agents. Nanocomposite thermoplastic
15 materials are typically made by mechanically mixing nanoparticles with the
thermoplastic resin in a compounding process. However dispersion is often difficult,
particularly in viscous melt or rubbery compositions of thermoplastic high polymers.
The particulate materials will often agglomerate or clump when processed or blended
into the base material. Furthermore, often it is difficult to achieve desired physical
20 properties without sacrificing other desired properties. Using such particles to increase
tensile properties of the polymer composition often produces an undesirable loss of
flexibility, for instance. Additionally, many of these compositions are susceptible to a
loss of desired properties upon aging.

There exists a need therefore for improved particulate materials useful in
25 thermoplastic high polymer compositions that provide a wider range of physical property
improvement benefits than are currently available.

US Patent Application No. 11/094638, filed March 30, 2005, incorporated herein
by reference in its entirety, describes polymeric/ceramic composite materials for use in
medical devices polymer and sol-gel derived ceramic. The polymer and sol-gel ceramic
30 may form a bi-continuous nanophase or separate polymeric and sol-gel derived ceramic
phases.

SUMMARY OF THE INVENTION

The present application pertains to novel particulate form materials useful as
35 fillers, reinforcing agents, radioopacifiers, impact modifiers, or the like, in compositions

of thermoplastic high polymers and to thermoplastic polymer compositions comprising such particulate materials.

The novel particulate materials may have improved dispersion characteristics relative to currently available materials and/or may prevent the agglomeration of the
5 desired nano-particle in thermal processing. These benefits may be obtained by functionalizing a ceramic particle material comprising an inorganic ceramic network with organic polymer segments that interpenetrate the ceramic network. Optionally the polymer segments may also be covalently linked into the ceramic network. The materials may be made by known organic-inorganic sol-gel processing techniques,
10 following which the materials are processed into particles of suitable size for compounding.

When compounded with thermoplastic high polymer materials the presence of the interpenetrating polymer segments in the particulate material modifies the particle/thermoplastic interface, which suitably compatibilizes the particle and polymer
15 materials and can reduce the tendency to agglomerate during thermal processing of the composition.

In one aspect the invention is directed to a particulate material having an average particle size range of about 1 nm to about 10,000 nm that comprises a ceramic/polymer material, the ceramic/polymer material comprising a ceramic material network, the
20 ceramic material network having a organic polymer segments distributed throughout the ceramic network.

In another aspect the invention is directed to a composition comprising a thermoplastic polymer and a particulate material as described herein.

The polymer/particulate compositions may be utilized to prepare medical
25 components to alter physical properties such as, burst, distension, tensile, flexibility, abrasion resistance, fatigue resistance and/or toughness properties of the component. Therefore, in further aspects, the invention is directed to components prepared from the compositions disclosed herein.

These and other aspects of the invention will be apparent to the skilled person
30 from the disclosure herein.

DETAILED DESCRIPTION OF THE INVENTION

All published documents, including all US patent documents, mentioned anywhere in this application are hereby expressly incorporated herein by reference in their entirety. Any copending patent applications, mentioned anywhere in this
5 application are also hereby expressly incorporated herein by reference in their entirety.

The particulate material of the invention is an organic-inorganic hybrid material. The organic part may be a polymer provided to the composition in solution with a solvent compatible with the ceramic sol, generated in-situ during the sol-gel processing or generated by a separate polymerization reaction run after the ceramic has been
10 produced by the sol-gel reaction. If some of the components used to formulate the ceramic are functionalized with polymerizable groups, or if the organic polymers are functionalized with groups co-condensable with the ceramic in the sol-gel processing, the interpenetrate polymer may also crosslink the inorganic ceramic network.

Ceramic materials typically are networks of metal or semi-metal oxides or mixed
15 oxide compounds. Examples of suitable metals and semi-metals include silicon, iron, vanadium, barium, zirconium, titanium, aluminum, tin, hafnium, rubidium, bismuth, strontium, tantalum, molybdenum, tungsten, rhenium, ruthenium, and/or iridium oxides, among others. In general, metal/semi-metal atoms (designated generally herein as M) within the ceramic phases are linked to one another via covalent linkages, such as M—
20 O—M linkages, although other interactions are also commonly present including, for example, hydrogen bonding due to the presence of hydroxyl groups such as residual M—OH groups within the ceramic phases. Most typically the ceramic material will be based primarily on silicon oxide. Appropriate selection of additional or alternative components of the ceramic material, however, may be used to provide the particles of the invention
25 with radiopacity, magneto-opacity, selective gas or liquid permeability, specific density or other desirable properties. In some cases the ceramic network includes linkages to organic groups, typically via a carbon or oxygen atom linkage.

The ceramic employed in the present invention is beneficially formed using a sol-gel technique. In sol-gel techniques, the precursor materials used are typically inorganic
30 metallic and semi-metallic salts, metallic and semi-metallic complexes/chelates (e.g., metal acetylacetonate complexes), metallic and semi-metallic hydroxides, or organometallic and organo-semi-metallic compounds (e.g., metal alkoxides and silicon alkoxides and acyloxides). Silicon alkoxides and acyloxides are beneficial due to the

variety of formulation options, including co-condensation with related compounds having strong stable C-Si bonds and which can form a strong link between the polymeric and ceramic networks.

In some embodiments the organic-inorganic material is prepared by
5 compounding a sol-gel ceramic precursor, optionally functionalized with an organic linking group, with a polymer component at elevated temperature, and subsequently processing the composition in a sol-gel technique to condense the ceramic network. If the ceramic precursor is functionalized with an organic linking group, such as isocyanate epoxy, a carbon-linked amino group or an ethylenically unsaturated group, a linking
10 reaction to the organic polymer component may be run during the elevated temperature compounding step. Other functionalized sol-gel ceramic precursors that can form covalent linkages to the polymer during the elevated temperature compounding step may be alkoxysilanes having an ethylenically unsaturated group, for instance (meth)acryloxyethyltrimethoxysilane, (meth)acryloxypropyltriethoxysilane and 4-
15 trimethoxysilylstyrene. Such functionalized sol-gel ceramic precursor can also be an alkoxysilane having a carbon-linked amino group, for instance 3-aminopropyltriethoxysilane. A SiH functionalized alkoxy silane such as triethoxysilane may be employed to form covalent linkages by hydrosilation.

In other alternatives the functionalized sol-gel ceramic precursor may have
20 hydrolyzable groups other than alkoxide, for instance acyloxy.

In an alternative preparation the functionalized sol-gel ceramic precursor can be an active hydrogen reactive compound, for instance an isocyanate functional alkoxysilane, such as 3-isocyanatopropyltriethoxysilane or
2-isocyanatoethyltriethoxysilane. Epoxy functional ceramic precursors are also suitable,
25 for example glycidoxypropyltrimethoxysilane. Such compounds may be reacted with polymers that have active hydrogen groups, e.g. hydroxyl, thiol, primary amine, or secondary amine groups, to provide a covalent bond between the polymer and the functionalized alkoxide. The resulting polymer, now functionalized with alkoxysilane or other hydrolyzable silane groups, may then be incorporated into a ceramic network by
30 hydrolysis/condensation of the alkoxysilane groups, suitably together with other sol-gel ceramic precursor compounds such as tetraethoxysilane, tetramethoxysilane, and/or monophenyltriethoxysilane, to produce the organic-inorganic hybrid material from which the inventive particulate materials are prepared. Further examples of preparation of such

organic-inorganic hybrids are found in Honma, et al, Solid State Ionics, Vol 118, p 29-36, (1999); Honma, et al, Solid State Ionics, Vol 120, p. 255-264, (1999); Honma, et al, Journal of Membrane Science, Vol 185, p. 83-94, (2001); Huang, Wilkes, Polymer, Vol 30, p 2001-2012, (1989); Young, et al, Polymer, Vol 43, p 6101-6114, (2002); de Zea Bermudez, et al, Chem. Mater., Vol 11, p.569-580, (1999); Yano, S., et al, Mater Sci Engng, Vol C6, p. 75-90, (1998); and Correia, et al, Solid State Ionics, Vol 156, p. 85-93, (2003).

Alternatively, the organic-inorganic hybrid can be made without covalent bonding therebetween, believed to be through weak hydrogen or Van der Waals bonding, by addition of polymer in an aqueous phase to a sol-gel process, for instance as described in Yano, S., et al, Mater Sci Engng, Vol C6, p. 75-90, (1998).

The polymer incorporated into the organic-inorganic hybrid material may be for instance polyethers such as poly(ethylene oxide), poly(propylene oxide) poly(tetramethyleneoxide), ethylene oxide/propylene oxide copolymers, including block copolymers, and the like; polyesters such as poly(caprylactone); polyamides such as polycaprylactam, block copolymers of polyethers and polyamides, or polyurethanes. In some embodiments the polymer of the organic-inorganic hybrid material is an oligomer or low molecular weight polymer, for instance having a number average molecular weight of about 250 to about 10,000, or about 400 to about 4,000. Suitably the polymer incorporated into the hybrid material will be one that has good compatibility with the thermoplastic polymer with which the hybrid material particles of the invention will be compounded. In some embodiments the polymer is a linear polyether oligomer having terminal amine or hydroxyl groups and that is covalently reacted with ceramic precursor that is functionalized with an organic linking group such as isocyanatopropyltriethoxysilane and then hydrolyzed and condensed with another sol-gel ceramic precursor such as tetraethoxysilane.

The functionalized nanocomposite hybrid can be tailored to include many different types of organic and inorganic species, organic to inorganic ratios as well as specialized physical properties such as electrical conductivity, gas and/or liquid permeability and the like. This can be accomplished by customizing the chemical composition and concentration of the hybrid material precursors.

US 6,825,260 describes a technique for preparing organic-inorganic hybrid materials usable in some embodiments of the present invention.

US Patent Application No. 11/094638, filed March 30, 2005, describes various ways in which sol-gel derived organic-inorganic hybrid materials may be prepared. Such materials may be employed in some embodiments of the invention.

In accordance with the present invention, the condensed hybrid material is a
5 ceramic network that includes polymer interpenetrated therethrough, the polymer optionally also being covalently bound thereto. This hybrid material is dried and granulated into particles of suitable size. Granulating may be by any known process, for instance by grinding, crushing, milling, pounding, or the like. Cryogrinding may be particularly useful for hybrid materials having relatively high organic polymer content,
10 for instance about 25% or more by weight polymer, such as 40-90%.

Suitably the inventive particles are sized to have an average size of less than 10,000 nm, suitably in the range of range of from about 1 to about 1000 nm, for instance from about 3 to about 300 nm or about 10 to about 100 nm. Sieving or other known techniques can be used to classify and fractionate the particles. In addition to sizing the
15 particles to a desirable range, the ratios of components, pH conditions, timing and other techniques of the sol-gel processing may be modified to influence the surface area of the particles obtained.

The particles of the invention may be compounded in compositions with thermoplastic polymers and the compositions processed by standard thermoplastic
20 polymer processing techniques such as extrusion, injection molding, blow molding, rotomolding, stretch-blow molding and the like into formed articles or intermediate products such as tubes or sheets. Intermediate products may be further processed into formed articles. The particles will contribute to the physical properties of the formed articles in accordance with the combined effects of the particle size, the particle surface area, the
25 hybrid material properties and the interaction between the polymer of the hybrid material and the polymer with which it is compounded, as well as the relative ratio of polymer to particle that is employed. The skilled person therefore has the ability to vary properties of such compositions over a very wide range and to more selectively modify physical properties of products formed of the compositions than is presently available from less
30 complex particles such as particles such as fumed or precipitated silicas and the various treated versions thereof currently available commercially.

In addition to thermoplastic polymer compositions, the inventive particles may also be usefully compounded in other types of compositions, such as curable adhesive and/or sealant compositions, paints, coatings and the like.

In some embodiments the polymers for use in compositions with the inventive
5 particles may be one or more of the following: polyester; polyester block copolymers;
polycarboxylic acid polymers and copolymers including polyacrylic acids; acetal
polymers and copolymers; acrylate and methacrylate polymers and copolymers;
cellulosic polymers and copolymers; polyoxymethylene polymers and copolymers;
polyimide polymers and copolymers such as polyether block imides, polyamidimides,
10 polyesterimides, and polyetherimides; polysulfone polymers and copolymers including
polyarylsulfones and polyethersulfones; polyamide polymers; polyamide block
copolymers; polycaprolactams and polyacrylamides; resins including alkyd resins,
phenolic resins, urea resins, melamine resins, epoxy resins, allyl resins and epoxide
resins; polycarbonates; polyacrylonitriles; polyvinylpyrrolidones; polymers and
15 copolymers of vinyl monomers including polyvinyl alcohols, polyvinyl halides such as
polyvinyl chlorides, ethylene-vinyl acetate copolymers (EVA), polyvinylidene chlorides,
polyvinyl ethers such as polyvinyl methyl ethers, polystyrenes, styrene-maleic anhydride
copolymers, vinyl-aromatic-olefin copolymers, including styrene-butadiene copolymers,
styrene-ethylene-butylene copolymers (e.g., a polystyrene-polyethylene/butylene-
20 polystyrene (SEBS) copolymer, available as Kraton® G series polymers), styrene-
isoprene copolymers (e.g., polystyrene-polyisoprene-polystyrene), acrylonitrile-styrene
copolymers, acrylonitrile-butadiene-styrene copolymers, styrene-butadiene copolymers
and styrene-isobutylene copolymers (e.g., polyisobutylene-polystyrene and polystyrene-
polyisobutylene-polystyrene block copolymers such as those disclosed in U.S. Patent No.
25 6,545,097), polyvinyl ketones, polyvinylcarbazoles, and polyvinyl esters such as
polyvinyl acetates; polybenzimidazoles; ethylene-methacrylic acid copolymers and
ethylene-acrylic acid copolymers, where some of the acid groups can be neutralized with
either zinc or sodium ions (commonly known as ionomers); polyalkylene oxide polymers
and copolymers including polyethylene oxides (PEO); polyesters including polyethylene
30 terephthalates and aliphatic polyesters such as polymers and copolymers of lactide
(which includes lactic acid as well as d-,l- and meso lactide), epsilon-caprolactone,
glycolide (including glycolic acid), hydroxybutyrate, hydroxyvalerate, para-dioxanone,
trimethylene carbonate (and its alkyl derivatives), 1,4-dioxepan-2-one, 1,5-dioxepan-2-

one, and 6,6-dimethyl-1,4-dioxan-2-one (a copolymer of poly(lactic acid) and poly(caprolactone) is one specific example); polyether polymers and copolymers including polyarylethers such as polyphenylene ethers, polyether ketones, polyether ether ketones; polyphenylene sulfides; polyisocyanates; polyolefin polymers and copolymers, 5 including polyalkylenes such as polypropylenes, polyethylenes (low and high density, low and high molecular weight), polybutylenes (such as polybut-1-ene and polyisobutylene), polyolefin elastomers, ethylene propylene diene monomer (EPDM) rubbers, poly-4-methyl-pen-1-enes, ethylene-alpha-olefin copolymers, ethylene-methyl methacrylate copolymers and ethylene-vinyl acetate copolymers; fluorinated polymers 10 and copolymers, including polytetrafluoroethylenes (PTFE), poly(tetrafluoroethylene-co-hexafluoropropene) (FEP), modified ethylene-tetrafluoroethylene copolymers (ETFE), and polyvinylidene fluorides (PVDF); silicone polymers and copolymers; thermoplastic polyurethanes (TPU); elastomers such as elastomeric polyurethanes and polyurethane copolymers (including block and random copolymers that are polyether based, polyester 15 based, polycarbonate based, aliphatic based, aromatic based and mixtures thereof; examples of commercially available polyurethane copolymers include Bionate®, Carbothane®, Tecoflex®, Tecothane®, Tecophilic®, Tecoplast®, Pellethane®, Chronothane® and Chronoflex®); p-xylylene polymers; polyiminocarbonates; copoly(ether-esters) such as polyethylene oxide-poly(lactic acid) copolymers; 20 polyphosphazines; polyalkylene oxalates; polyoxaamides and polyoxaesters (including those containing amines and/or amido groups); polyorthoesters; biopolymers, such as polypeptides, proteins, polysaccharides and fatty acids (and esters thereof), including fibrin, fibrinogen, collagen, elastin, chitosan, gelatin, starch, glycosaminoglycans such as hyaluronic acid; as well as further copolymers of the above.

25 In some embodiments the inventive particles are compounded with a thermoplastic polyester, for instance poly(ethylene terephthalate), a thermoplastic polyester copolymer for instance Hytrel® or Arnitel® polymers, a thermoplastic polyamide such as nylon 6, nylon 6/6, nylon 9/10, nylon 10, nylon 6/10, nylon 11, or nylon 12, or a polyamide block copolymer such a Pebax® polymer, for instance Pebax® 30 polymers having Shore D durometer grades of about 25 to about 75, or a fluoropolymer.

Without being limited thereto, it is thought that particularly advantageous polymer-polymer interactions will be facilitated when the polymer of the hybrid particle material and the thermoplastic polymer with which the particles are compounded have

multiple sites at which interpolymer hydrogen bonding can occur. These interactions can facilitate easier incorporation of the particles into the thermoplastic polymer, better light transparency, toughness and flexibility, thermal formability or the like. Such interactions may occur, for instance, with various combinations of ether, hydroxyl, amide, urethane, 5 urea, and/or carboxyl groups between these polymer moieties. Of course other weak interactions, for instance van der Waals bonding, may also be important to obtaining such benefits from the invention.

Compositions of the invention may be used to form objects of many types. Medical devices of various types are exemplary. Medical devices in which the inventive 10 compositions may be employed include a wide variety of implantable or insertable medical devices, which are implanted or inserted either for procedural uses or as implants. Examples include balloons, catheters (e.g., renal or vascular catheters such as balloon catheters), guide wires, filters (e.g., vena cava filters), stents (including coronary artery stents, peripheral vascular stents such as cerebral stents, urethral stents, ureteral 15 stents, biliary stents, tracheal stents, gastrointestinal stents and esophageal stents), stent grafts, vascular grafts, vascular access ports, embolization devices including cerebral aneurysm filler coils (including Guglielmi detachable coils and metal coils), myocardial plugs, pacemaker leads, left ventricular assist hearts and pumps, total artificial hearts, heart valves, vascular valves, tissue bulking devices, sutures, suture anchors, anastomosis 20 clips and rings, tissue staples and ligating clips at surgical sites, cannulae, metal wire ligatures, orthopedic prosthesis, joint prostheses, as well as various other medical devices that are adapted for implantation or insertion into the body. Such medical devices include implantable and insertable medical devices that are used for diagnosis, for systemic treatment, or for the localized treatment of any tissue or organ. Non-limiting 25 examples are tumors; organs including the heart, coronary and peripheral vascular system (referred to overall as "the vasculature"), the urogenital system, including kidneys, bladder, urethra, ureters, prostate, vagina, uterus and ovaries, eyes, lungs, trachea, esophagus, intestines, stomach, brain, liver and pancreas, skeletal muscle, smooth muscle, breast, dermal tissue, cartilage, tooth and bone. As used herein, 30 "treatment" refers to the prevention of a disease or condition, the reduction or elimination of symptoms associated with a disease or condition, or the substantial or complete elimination of a disease or condition. Typical subjects are vertebrate subjects, more typically mammalian subjects and even more typically human subjects.

In some embodiments of the invention, the particles are used in formulations used to produce catheter balloons for dilatation and/or stent delivery to improve the robustness of the balloon during deployment and use.

The invention is illustrated by the following non-limiting example.

5

Example of Functionalized Hybrid

Materials: Terathane® 650 hydroxyl terminated polytetramethylene ether, number average molecular weight about 650; 3-(triethoxysilyl)propyl isocyanate; hydrochloric acid (HCl) 0.15M, ethanol, tetrahydrofuran (THF), and water.

- 10 20.24 g (0.0311 mol) of Terathane® 650 was dissolved in 20 ml anhydrous THF. 13.6331 g (0.0551 mol) of 3-(triethoxysilyl)propyl isocyanate was combined with the Terathane® solution. The mixture was refluxed for 24 hrs. NMR and IR were used to determine that the isocyanate fully reacted. Subsequently 3.1795 g of 0.15M HCL and 20 ml of ethanol were added to the solution. The mixture was stirred for one minute.
- 15 The mixture was cast into Teflon® beakers and let to air dry. The resultant material had a degradation temperature of about 394 °C as determined by TGA. The DSC results concluded that the material did not melt within a 250 °C sweep. The typical melting point of Terathane 650 is 11-19 °C.

- 20 When cryo-ground to a suitable particle size as described above, this material may be compounded with a thermoplastic polymer which may then be extruded into components such as catheter tubing or tubing for forming a catheter balloon.

- The above examples and disclosure are intended to be illustrative and not exhaustive. These examples and description will suggest many variations and
- 25 alternatives to one of ordinary skill in this art. All these alternatives and variations are intended to be included within the scope of the claims, where the term "comprising" means "including, but not limited to." Those familiar with the art may recognize other equivalents to the specific embodiments described herein which equivalents are also intended to be encompassed by the claims. Further, the particular features presented in
- 30 the dependent claims can be combined with each other in other manners within the scope of the invention such that the invention should be recognized as also specifically directed to other embodiments having any other possible combination of the features of the dependent claims. For instance, for purposes of claim publication, any dependent claim

which follows should be taken as alternatively written in a multiple dependent form from all claims which possess all antecedents referenced in such dependent claim, regardless of claim sequence, if such multiple dependent format is an accepted format within the jurisdiction. In jurisdictions where multiple dependent claim formats are restricted, the
5 following dependent claims should each be also taken as alternatively written in each singly dependent claim format which creates a dependency from an antecedent-possessing claim other than the specific claim listed in such dependent claim.

CLAIMS

1. A particulate material having an average particle size range of about 10,000 nm or less and comprising a organic-inorganic hybrid material comprising a ceramic material network having organic polymer segments distributed throughout the ceramic network.
2. A particulate material as in claim 1 wherein the ceramic material network comprises an oxide of silicon, iron, vanadium, barium, zirconium, titanium, aluminum, tin, hafnium, rubidium, bismuth, strontium, tantalum, molybdenum, tungsten, rhenium, ruthenium or iridium oxides, or a mixture thereof.
3. A particulate material as in claim 1 wherein the organic polymer segments are polymer segments having a number average molecular weight of about 250 to about 10,000.
4. A particulate material as in claim 1 wherein the organic polymer segments are covalently bonded to the ceramic material network.
5. A particulate material as in claim 1 wherein the average particle size range is from about 1 to about 1000 nm.
6. A particulate material as in claim 1 wherein the organic-inorganic material is prepared by compounding a sol-gel ceramic precursor with a polymer component and subsequently processing the composition in a sol-gel technique to condense the ceramic network.
7. A particulate material as in claim 6 wherein the polymer component is a organic polymer endcapped with a silyl group having one or more hydrolyzable groups attached to the silicon atom thereof.
8. A particulate material as in claim 7 wherein the organic polymer is a polyether polymer.

9. A particulate material as in claim 7 wherein the linear organic polymer is a polyether, polyester, polyamide, block copolymer of polyethers and polyamides, or polyurethane oligomer having a molecular weight of from about 400 to about 4,000, and
5 terminal amine or hydroxyl groups that has been covalently reacted with a ceramic precursor compound that is functionalized with an organic linking group.
10. A particulate material as in claim 9 wherein the organic linking group comprises an isocyanate group, an ethylenically unsaturated group, a carbon-linked amino group or
10 an epoxy group.
11. A composition comprising a thermoplastic polymer and a particulate material as in claim 1.
- 15 12. A composition as in claim 11 wherein the thermoplastic polymer comprises a polyester, polyester block copolymer, a polyamide, a polyamide block copolymer, a fluoropolymer, or a mixture of two or more thereof.
13. A thermoformed article prepared from a composition as in claim 11.
20
14. A medical device having a component formed from a composition as in claim 11.
15. A medical device as in claim 14 wherein the medical device is a balloon, a guide wire, a vena cava filter, a stent, a stent graft, a vascular graft, a cerebral aneurysm filler
25 coil, a myocardial plug, a heart valve, a vascular valve or a tissue engineering scaffold.
16. A medical device formed of a composition as in claim 7.
17. A medical device as in claim 17 wherein the medical device is a balloon, a guide
30 wire, a vena cava filter, a stent, a stent graft, a vascular graft, a cerebral aneurysm filler coil, a myocardial plug, a heart valve, a vascular valve or a tissue engineering scaffold.

18. An adhesive, sealant, paint, or coating composition comprising a particulate material as in claim 1.
19. A composition formed by mixing a thermoplastic polymer in melt phase with a
5 particulate material as in claim 1, said thermoplastic polymer and the polymer segments of the particulate material comprising groups that can form hydrogen bonds during said melt phase mixing.
20. A composition as in claim 19 wherein the groups that can form hydrogen bonds
10 during said melt phase mixing include at least one member selected from ether, hydroxyl, amide, urethane, urea, and/or carboxyl groups.
21. A method comprising
preparing an organic-inorganic hybrid material comprising a ceramic material
15 network having organic polymer segments distributed throughout the ceramic network,
granulating the organic-inorganic hybrid material,
isolating a particle fraction of the granulated organic-inorganic material having an average particle size range of about 10,000 nm or less.
- 20 22. A method as in claim 19 wherein the ceramic material network is prepared by a sol-gel technique.
23. A method comprising
providing a particulate material having an average particle size range of about
25 10,000 nm or less and comprising a organic-inorganic hybrid material comprising a ceramic material network having organic polymer segments distributed throughout the ceramic network,
providing a melted thermoplastic polymer, and
mixing the a particulate material and the melted thermoplastic polymer to form a
30 composition.

24. A method as in claim 23 wherein thermoplastic polymer and the polymer segments of the particulate material each comprise groups that can form hydrogen bonds during said mixing step.
- 5 25. A method as in claim 24 wherein the groups that can form hydrogen bonds during said mixing step include at least one member selected from ether, hydroxyl, amide, urethane, urea, and/or carboxyl groups.