

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 November 2007 (22.11.2007)

PCT

(10) International Publication Number
WO 2007/133973 A2

- (51) International Patent Classification: Not classified
- (21) International Application Number: PCT/US2007/068261
- (22) International Filing Date: 4 May 2007 (04.05.2007)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/798,781 8 May 2006 (08.05.2006) US
- (71) Applicant (for all designated States except US): **BP CORPORATION NORTH AMERICA INC.** [US/US]; 4101 Winfield Road, Warrenville, IL 60555 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **GONG, William, H.** [US/US]; 900 Fairfield Avenue, Elmhurst, IL 60126 (US). **ADAMIAN, Victor** [US/US]; 2937 Bunker Circle, Naperville, IL 60563 (US). **BRUGGE, Stephen, P.** [US/US]; 1209 Jane Avenue, Naperville, IL 60540 (US). **METELSKI, Peter, D.** [CA/US]; 651 Red Barn Trail, Bolingbrook, IL 60490 (US). **NUBEL, Phillip, O.** [US/US]; 619 Tulip Lane, Naperville, IL 60540 (US). **SCHAMMEL, Wayne, P.** [US/US]; 22818 Elder Court, Plainfield, IL 60544 (US). **ZHOU, Chengxiang** [CN/US]; 2529 Old Tavern Road, Apt. 13, Lisie, IL 60532 (US).
- (74) Agent: **HENSLEY, Stephen, L.**; BP America Inc., 4101 Winfield Road, Mail Code 5 East, Warrenville, IL 60555 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Declaration under Rule 4.17:**
— of inventorship (Rule 4.17(iv))
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: PROCESS AND CATALYST FOR OXIDIZING AROMATIC COMPOUNDS

(57) Abstract: Catalytic compositions for conversion of substituted aromatic feed materials to oxidized products comprising aromatic carboxylic acid derivatives of the substituted aromatic feed materials comprise at least two metal or metalloid elements, at least one of which is palladium, platinum, vanadium or titanium, and at least one of which is a Group 5, 6, 14 or 15 metal or metalloid. A process for oxidizing substituted aromatic feed materials comprises contacting the feed material with oxygen in the presence of such a catalytic composition in a liquid reaction mixture.



WO 2007/133973 A2

PROCESS AND CATALYST FOR OXIDIZING AROMATIC COMPOUNDS

This application claims the benefit of U.S. Provisional Application No. 60/798,781 filed May 8, 2006, the disclosure of which is incorporated herein by reference.

5 Field of the Invention

10 This invention relates to a process for converting substituted aromatic compounds to oxidized products comprising aromatic carboxylic acids and a catalyst composition useful for such a process. More particularly, the invention relates to catalytic oxidation of feedstock materials comprising substituted aromatic compounds with at least one oxidizable alpha carbon to product comprising aromatic carboxylic acid in a liquid reaction mixture using a catalyst composition that is active for such oxidation in the absence of bromine sources commonly used to promote catalytic oxidation of substituted aromatic compounds to aromatic carboxylic acids and comprises a palladium, platinum, 15 vanadium or titanium component and a Group 5, 6, 14, or 15 metal or metalloid component wherein the components do not both consist of a vanadium component.

Background of the Invention

20 Terephthalic acid and other aromatic carboxylic acids are widely used in the manufacture of polyesters, commonly by reaction with one or more glycols, and particularly ethylene glycol and combinations thereof with one or more higher homologues of alkylene glycols, for conversion to fiber, film, containers, bottles and other packaging materials, and molded articles.

25 In commercial practice, aromatic carboxylic acids are commonly made by liquid phase oxidation in an aqueous acetic acid solvent of methyl-substituted benzene and naphthalene feedstocks, in which the positions of the methyl substituents correspond to the positions of carboxyl groups in the desired aromatic carboxylic acid product. Oxidation is conducted by contacting the feedstock with air or another source of oxygen, which is normally gaseous, in the

presence of a catalyst comprising cobalt and manganese promoted with a source of reactive bromine as described in US 2,833,816. The oxidation is exothermic and yields the aromatic carboxylic acid together with by-products, including partial and intermediate oxidation products of the aromatic feedstock as well as
5 oxidation and other reaction products of the acetic acid solvent such as methanol, methyl acetate, methyl bromide, carbon monoxide and carbon dioxide. Water is also generated as a by-product. The aromatic carboxylic acid oxidation product, by-products and intermediate oxidation products of the feedstock are commonly formed dissolved or as solids suspended in the liquid phase reaction
10 mixture and are commonly recovered by crystallization and solid-liquid separation techniques.

Pure forms of aromatic carboxylic acids are often favored for manufacture of polyesters for important applications, such as fibers, bottles, and other containers and packaging materials, because impurities, such as by-products
15 generated from aromatic feedstocks in oxidation processes such as those described above and, more generally, various carbonyl-substituted aromatic species, are known to cause or correlate with color formation in polyesters made from the carboxylic acids and, in turn, off-color in polyester converted products. Aromatic carboxylic acids with reduced levels of impurities can be made by
20 further oxidizing crude products from liquid phase oxidation as described above, for example at one or more progressively lower temperatures and/or oxygen levels or during crystallization steps commonly used to recover products of the oxidation, for conversion of feedstock partial oxidation products to the desired acid product, as known from U.S. 4,877,900, 4,772,748 and 4,286,101.
25 Preferred pure forms of terephthalic acid and other aromatic carboxylic acids with lower impurities contents, such as purified terephthalic acid or "PTA", are made by catalytically hydrogenating less pure forms of the acids, such as crude product comprising aromatic carboxylic acid and by-products generated by liquid phase oxidation of aromatic feedstock, so-called medium purity products or other
30 impure forms of the acids, in solution at elevated temperature and pressure using a noble metal catalyst. In some commercial operations, liquid phase oxidation of alkyl aromatic feed materials to crude aromatic carboxylic acid and purification of

the crude product are often conducted in continuous integrated processes in which crude product from liquid phase oxidation is used as starting material for purification.

5 A difficulty in manufacture of aromatic carboxylic acids by such processes results from use of bromine-promoted oxidation catalysts. Bromine sources used with the catalyst and reaction products thereof formed during oxidation are corrosive. To limit corrosion, process equipment, including major equipment items such as oxidation reactors and off-gas treatment equipment, is normally constructed using titanium or other expensive, corrosion-resistant metals or
10 alloys. Treatment of process off-gases to avoid atmospheric emissions of volatile bromine compounds formed in the process, such as by thermal or catalytic oxidations to oxidize organic bromine compounds to carbon oxides and molecular bromine and reduction of the latter to anionic bromine using sodium formate, also are commonly used, adding complexity and cost to manufacturing
15 processes.

Eliminating bromine from conventional cobalt-manganese oxidation catalysts is not practical for commercial scale aromatic carboxylic acid manufacture because yields of desired products are unacceptably low. In addition, oxidation of acetic acid solvent for the liquid phase reaction tends to
20 increase in cobalt and manganese-catalyzed oxidations without bromine. Sacrificial promoters, such as methyl ethyl ketone and acetaldehyde, have been proposed as alternatives to bromine, as known from US 3,361,803, but their use in practical applications is disfavored because they are consumed in oxidation, not only adding costs for replacing the consumed promoter but also diverting
25 oxygen from desired reactions. These sacrificial promoters can also negatively affect product quality in higher temperature oxidations. N-hydroxyphthalamide has been reported in Y. Ishii, *J. Mol. Catal. A.: Chem*, 1997, 117 (1-3, *Proceedings of the 6th International Symposium on the Activation of Dioxygen and Homogeneous Catalytic Oxidation*, 1996), 123, as a bromine-free alternative
30 promoter for cobalt - catalyzed reactions but its utility in manufacture of aromatic carboxylic acids is limited by its low solubility in acetic acid oxidation reaction

solvent, and its consumption, and conversion to undesirable by-products during oxidation due to multiple competing decomposition reactions.

5 German Patent No. 2804158 describes a process for manufacture of terephthalic acid by solvent-free co-oxidation of p-xylene and/or p-tolualdehyde plus methyl p-toluate to dimethyl terephthalate using a bromine-free catalyst composed of cobalt or manganese salts or a combination of manganese with cobalt or with zinc salts at a temperature in the range of 140 - 240°C according to the so-called Witten-Hercules process, followed by catalytic hydrogenation of the total reactor effluent from the co-oxidation in the presence of a palladium, platinum, nickel or cobalt catalyst. The process also includes a heat treatment step for transesterification of terephthalate and p-toluate mono- and diesters from either the co-oxidation or hydrogenation step, which is conducted at 180 – 350°C after removal of hydrogen and volatiles. Heat treating is conducted under a nitrogen atmosphere, preferably with addition of water and methanol and, for reducing treatment time, optionally in the presence of Mo, W, Ti, Mg, Ca, Sr, Ba, Mn, Fe, Ni, Zn, Y, K, Y, La, Ce, Nd, Sm, Re, In, Sb, Bi, Se, Te, Sn, P or combinations thereof as catalyst. Absence of bromine from the oxidation catalyst and of monocarboxylic acid reaction solvent in the oxidation are said to permit use of less corrosion-resistant metals for construction of equipment for the co-oxidation and lessen solvent burning.

25 US Patent 3,865,870 describes a process for oxidizing methylated benzenes to carboxylic acids in which streams of water, methylated benzene feedstock and oxygen-containing gas are fed concurrently over a catalyst metal in a reactor pressurized to 300 - 1200 psi and at temperatures of 170-300°C. The catalyst metal is silver, palladium, ruthenium, platinum, rhodium, iridium or osmium and is supported on alumina, silica, titania, zirconia, silicon carbide or carbon. Para-xylene oxidations with the patent's preferred metals, ruthenium, palladium or silver, resulted in low yields of oxidized para-xylene derivatives, low aromatic carboxylic acid selectivities (e.g., 3-5% with palladium) and often with significant generation of carbon oxides due to burning of para-xylene feedstock according to the patent's examples.

US Patent No. 6,160,170 of Codignola discloses oxidation of aromatic feed materials to aromatic carboxylic acids with gaseous oxygen in the absence of bromine in a liquid phase reaction mixture including an aqueous organic solvent using a homogeneous catalytic complex characterized generally as consisting of (A) at least one Group VIIIA metal with a valence greater than 2; and/or at least one Group VIIA metal and/or cerium; and (B) and at least one Group IVA metal which is preferably zirconium or hafnium. (Groups VIIIA, VIIA and IVA referred to in the patent correspond, respectively, to Groups VIII, VIIB and IVB of more recent versions of the Periodic Table according to US Patent Application No. 2002/0188155 A1 of Codignola et al.) Catalyst compositions described in the patent consist of cerium acetate and zirconium acetate, and of ruthenium oxide and zirconium acetate. Practical effectiveness of the catalysts for manufacture of aromatic carboxylic acids is limited because water in amounts commonly present in product recovery or other process steps can rapidly convert zirconium (IV) acetate to zirconium (IV) oxide, which, due to its insolubility in water, can be difficult to separate from aromatic carboxylic acid products recovered in solid form, cause plugging of equipment and catalysts in downstream processing and diminish quality of purified aromatic carboxylic acids products. Precipitated zirconium (IV) oxide also represents a loss of catalyst metal. US Patent Application No. 2002/0188155, noting instability of the catalysts according to International Application WO 98/2938, to which US 6,160,170 corresponds, and reduced activity and selectivity due to their degradation, proposes low temperature (90 - 150°) oxidation using bromine-free catalytic complexes as in the patent preferably containing a Group VIII metal or cerium and zirconium or hafnium and preferably a mixture of cobalt or cerium and zirconium salts, with filtration of the oxidation product and return of mother liquor from filtration to oxidation, all under substantially the same temperature and pressure conditions. In addition to added complexity of the process, catalysts according to this citation show strong activity for oxidation of acetic acid reaction solvent to carbon oxides unless reaction temperatures are maintained below about 120 - 140°.

US 5,877,330 describes catalysts prepared from polyvanadic acid sols and other metal compounds for use in gas phase hydrocarbon conversions, reporting 99.5% conversion in high temperature gas-phase oxidation of o-xylene with air at 320°C with 73.6% selectivity to phthalic anhydride using a calcined combination of polyvanadic acid sol and titanium dioxide and 16.1% conversion of toluene with selectivities of 22.9% to benzaldehyde and 30.1 % to benzoic acid using a combination prepared from polyvanadic acid sol and boehmite.

Oxidation of selected aromatic substrates to alcohols and their esterification reactions using catalysts free of bromine are known from the following patents and publications but oxidation to aromatic carboxylic acid products are not described.

Combinations of palladium and antimony are reported useful for production of benzyl mono- and bis-acetates by oxidation of toluene with oxygen gas in an acetic acid solvent to benzyl alcohol and esterification thereof by reaction with the acetic acid according to JP 10265437 A2, and by esterification of mono- or bis-hydroxy products resulting from oxidation of para-xylene in acetic acid according to JP 2004137234 A2. Oxidations did not progress beyond the benzylic alcohols in either case. US 5,183,931 and 5,280,001 state generally that alkyl aromatics having a benzylic hydrogen can be oxidized to corresponding oxidized products selected from acids, aldehydes, alcohols and esters by contact in the presence of an oxygen containing fluid in a reaction medium with a catalyst composed of a palladium salt, a lithium, sodium, potassium, magnesium or calcium persulfate, an alkali or alkaline earth metal salt and a tin salt. As demonstrated in the patents' examples, all oxidations were conducted in alkaline reaction media of acetic acid with added potassium acetate and the only reactions exemplified are conversions of p-t-butyl toluene to p-t-butyl benzyl acetate. As in the Japanese publications, oxidations did not proceed beyond formation of the benzylic alcohol, which underwent esterification with acetic acid from the reaction medium.

Tanielyan, S. K. and Augustine, R. L., "Acetoxylation of Toluene Catalyzed by Supported Pd-Sn Catalyst", *J. Mol. Cat.* **1994**, 87, 311, reports oxygen uptake

in stages corresponding to color changes and residue formation during reaction of toluene with oxygen in acetic acid solvent in the presence of palladium(II) acetate, tin(II) acetate and potassium acetate and proposes a reaction mechanism in which an homogeneous Pd/Sn complex forms and Sn(II) is oxidized to Sn(IV) by oxygen in a first stage, the Pd/Sn(II) complex absorbs oxygen and generates Pd/Sn(III) or Pd/Sn(IV) intermediates which undergo oxidation and reduction reactions to generate Pd(0)/Sn(IV) in a second stage, and the resulting Pd(0)/Sn(IV) catalyzes acetoxylation of the benzylic carbon atom in the third stage.

Other catalytic oxidations of substituted aromatic compounds using catalysts containing or prepared from palladium components and particular other metal components or combinations are reported in US 6,245,936, US 4,804,777 US 6,476,258 and US 2004/0158068. The oxidations according to those patents are conducted in alkaline reaction media and/or for preparation of aryloxyacetic acids from aryloxyethanol starting materials by oxidation of the alcohol of the ring-bonded oxyethanol group but without oxidation of the carbon atoms of ring-bonded carbon-containing substituent groups that may be present in the starting materials.

Antimony (III) is known as a polycondensation catalyst for the manufacture of polyethylene terephthalate from terephthalic acid and glycols. It is considered to have sufficient Lewis acidity to catalyze the polycondensation and not to undergo oxidation, although Leuz, A-K.; Johnson, C. A., *Geochemica et Cosmochimica Acta* **2000**, 69(5), 1165, reports that oxidation of trivalent antimony to pentavalent antimony can occur in the presence of oxygen at a pH greater than 9.8 but not at a pH range of 3.6 - 9.8, or in the presence of hydrogen peroxide at a pH range of 8.1 to 11.7 but not at pH below 8.1.

Summary of the Invention

This invention provides a process and catalyst composition for conversion of feed materials comprising substituted aromatic compounds, at least one substituent of which comprises an oxidizable alpha carbon atom, to an oxidized

aromatic product with selectivity to aromatic carboxylic acids. As used herein, the expression "alpha carbon atom" means a carbon atom linked directly to an aromatic ring; an "oxidizable alpha carbon" is an alpha carbon atom having at least one hydrogen bonded directly to it. Unlike conventional commercial
5 catalysts and processes for making aromatic carboxylic acids such as terephthalic and isophthalic acids, the invented process and catalyst are effective in the substantial or complete absence of bromine sources. While the process and catalyst are tolerant of bromine in some amounts, the presence of bromine in proportions commonly used in conventional commercial processes adversely
10 affects the invented process and catalysts, either reducing conversion to oxidized product or shifting selectivity away from aromatic carboxylic acid products toward aromatic species with less fully oxidized substituent groups. Surprisingly, aromatic carboxylic acid yields according to the invention exceed those achieved with known bromine-free catalyst systems and oxidations proceed beyond the
15 benzylic alcohols and without esterification thereof. In some embodiments, the invention also provides surprising process benefits, including good yields and selectivities when using water as a liquid medium for the reaction and insubstantial generation of carbon oxide by-products due to burning of aromatic feedstock and monocarboxylic acid reaction solvents, such as acetic acid, when
20 used. In some embodiments, water generated as a by-product in the invented process can serve as a liquid reaction medium for the process, with desirable conversion and selectivities, but insubstantial carbon oxide by-product formation even without addition of water or reaction solvents to the process.

In one of its aspects the invention is a process for conversion of feed
25 materials comprising substituted aromatic compounds to oxidized aromatic products with selectivity to aromatic carboxylic acids. According to embodiments of this aspect of the invention, a process for conversion of an aromatic feedstock comprising a substituted aromatic compound, at least one substituent group of which comprises an oxidizable alpha carbon atom, to an oxidized aromatic
30 product comprising at least one aromatic carboxylic acid, at least one carboxylic acid group of which comprises an alpha carbon atom, comprises contacting the aromatic feedstock with oxygen in a liquid reaction mixture in the presence of a

catalytic composition that comprises at least one of platinum, palladium, titanium or vanadium, and at least one metal or metalloid of Group 5, 6, 14 or 15 of the Periodic Table of the Elements provided that the composition does not consist only of vanadium. Preferably, the catalyst composition is free of bromine and is
5 contacted with the aromatic feedstock in the absence of bromine.

In another embodiment, a process for manufacture of aromatic carboxylic acid comprises contacting a feed material comprising at least one dialkyl arene, partially oxidized alkylarene derivative or combination thereof, with oxygen in a liquid phase reaction mixture at temperature and pressure effective to maintain a
10 liquid phase in the presence of a catalyst composition as described above.

Another aspect of the invention is a catalytic composition having activity for conversion of a substituted aromatic compound, at least one substituent group of which comprises an oxidizable alpha carbon, in contact with oxygen in a liquid reaction mixture to oxidized aromatic product comprising an aromatic
15 carboxylic acid in which at least one carboxylic acid group comprises an alpha carbon. The composition comprises at least one metal selected from palladium, platinum, titanium and vanadium, and at least one metal or metalloid of Group 5, 6, 14 or 15 of the Periodic Table of the Elements wherein the metal and the metal or metalloid do not both consist only of vanadium.

As used herein, "conversion of substituted aromatic compound" refers to
20 conversion of the compound to its oxidized aromatic derivatives and accordingly, for purposes hereof, expressions such as "oxidized aromatic derivatives" and "oxidized aromatic product" do not include carbon monoxide or carbon dioxide generated due to burning of aromatic starting materials or oxidation products.
25 "Selectivity to aromatic carboxylic acid" refers to the weight of oxidized aromatic derivative or derivatives substituted with at least one carboxylic acid group expressed as a percentage of the total weight of oxidized aromatic derivatives. In reciting that the components of the catalyst compositions according to the invention do not consist of only vanadium, it will be understood that the
30 vanadium-containing catalyst compositions according to the invention and used in the invented process include at least one of platinum, palladium, titanium or a

Group 6, 14 or 15 metal or metalloid or a Group 5 metal other than vanadium, but do not include compositions in which vanadium is present without at least one other such metal or metalloid. Except as otherwise stated, Groups of the Periodic Table of the Elements referred to herein correspond to "New Notation" designations according to the Periodic Table of the Elements as found, for example, in the Handbook of Chemistry and Physics, 78th Edition, CRC Press, 1997. The terms "Group" and "Groups" in reference to elements, metals and metalloids will be understood to refer to Groups of such a Periodic Table of the Elements.

The invention also provides aromatic carboxylic acid compositions, and especially terephthalic acid, isophthalic acid and naphthalene dicarboxylic acid compositions prepared according to processes of the invention or using catalyst compositions according to the invention. A terephthalic acid composition according to a preferred embodiment of the invention comprises terephthalic acid and, by weight thereof, about 0.1 to about 500 ppmw of at least one of palladium, platinum, titanium or vanadium, calculated as the element, and about 0.1 to about 500 ppmw of at least one other metal or metalloid which is a Group 5, 6, 14 or 15 metal or metalloid, calculated as the element, or combinations thereof. In another embodiment, a terephthalic acid composition suitable for direct conversion by reaction with at least one glycol to polyester suitable for manufacture of fiber comprises terephthalic acid and, by weight of the terephthalic acid, about 0.01 to about 100 ppmw palladium, platinum, vanadium or titanium, calculated as the element, and about 0.01 to about 100 ppmw of at least one other metal or metalloid which is a Group 5, 6, 14 or 15 metal or metalloid, calculated as the element, or a combination thereof.

Detailed Description of the Invention

Catalyst compositions according to aspects and embodiments of the invention comprise a metal component in which the metal is at least one of palladium, platinum, titanium or vanadium, and at least metal or metalloid component in which the metal or metalloid is at least one Group 5, 6, 14 or 15 metal or metalloid, provided that the compositions do not consist only of vanadium. The expression "metal or metalloid" is used herein to refer collectively

to metallic elements as well as semi-metallic and other elements not considered metals in a strict sense but having metal-like properties. In referring to metals and metalloids and such components of the catalyst composition, it will be understood that the terms are used in a broad sense to include the metals and metalloids as such as well as their compounds, complexes, alloys and combinations in other forms. Among the Group 5, 6, 14 and 15 elements included in catalyst compositions according to aspects of the invention, arsenic, antimony, and bismuth of Group 15 and tellurium and polonium of Group 16 are or may be considered metalloids. Other elements that may be considered metalloids include boron, aluminum, silicon and germanium. Significance of distinctions between metals and metalloids is not apparent for purposes of the invention.

Preferred catalysts according to more particular embodiments of the invention comprise at least one of platinum, vanadium and titanium and at least one Group 5, 6, 14 or 15 metal or metalloid. According to other embodiments, preferred catalyst compositions for use in the invented process, and particularly for oxidation of dialkylarene feedstocks and partially oxidized dialkylarene derivatives to aromatic carboxylic acids, comprises palladium or a combination thereof with titanium or vanadium and at least one Group 14 metal or metalloid or combination thereof with at least one Group 5, 6 or 14 metal or metalloid.

Specific examples of metals or metalloids that are present in the invented catalyst compositions, in addition to at least one of palladium, platinum, vanadium and titanium, include Group 5 metals such as vanadium, niobium and tantalum, Group 6 metals such as molybdenum, chromium and tungsten, Group 14 metals or metalloids such as germanium, tin and lead, and Group 15 metalloids such as antimony and bismuth. Preferred Group 5, 6, 14 and 15 metals and metalloids include tin, antimony, bismuth, vanadium, chromium, niobium, molybdenum, lead and combinations thereof. Preferred metal and metalloid components and combinations can vary somewhat depending on other components of the invented compositions. Combinations of antimony or bismuth and tin, vanadium, molybdenum, chromium, niobium or combinations thereof often provide desirable results in oxidations according to the invention.

According to embodiments of the invention, catalyst compositions containing palladium or palladium and titanium and a combination of antimony or bismuth and one or more of tin, vanadium, molybdenum and chromium provide surprising conversions of aromatic substrates to oxidized products and aromatic carboxylic acid selectivities. In another embodiment, combinations of bismuth and niobium provide beneficial results in compositions containing palladium. In embodiments of the invention in which the catalyst compositions contain a platinum component or a combination thereof with a titanium component, combinations that include vanadium can be advantageous.

The specific form and chemical identity of the catalytically active specie or species of the invented catalytic compositions is not known. Accordingly, the description herein of the invented catalytic compositions in terms of their constituent elements, metals, metalloids or components is intended to include the form or forms and composition or compositions in which the components are catalytically active, whether that be as mixtures or combinations of discrete metals or metalloids or compounds thereof or as complexes, reaction products or other combinations thereof. Water- and organic acid-soluble and insoluble forms of the catalytic compositions have been observed to exhibit activity for oxidation of oxidizable alpha carbon-containing substituents of substituted aromatic compounds and selectivity to aromatic carboxylic acid oxidation products. Accordingly, in oxidation processes conducted in the presence of water, aqueous monocarboxylic acid reaction solvents and other liquid reaction media, the invention includes use of homogeneous and heterogeneous forms of catalyst composition, as well as hybrid forms in which the catalyst composition is made up of components in both homogeneous and heterogeneous forms, as where one or more heterogeneous components comprises an unsupported or supported metal, metalloid or combination thereof that is insoluble in the liquid reaction mixture and one or more components soluble in the liquid reaction medium is present as a homogeneous component.

In some embodiments, a form of the invented catalytic compositions is a solution comprising a palladium, platinum, vanadium or titanium component or combination thereof and a Group 5, 6, 14 or 15 metal or metalloid component or

combination thereof in a suitable solvent such as water or an organic acid or aqueous organic acid. Such a solution is suitably prepared by combining soluble metal or metal and metalloid compounds. Preferred organic solvents are C₁₋₈ monocarboxylic acids and aqueous solutions thereof and especially acetic acid or aqueous acetic acid. Water is also a preferred solvent for preparation of catalyst composition or component solutions and especially for preparing solutions for use in liquid phase oxidations according to the invention in which a liquid reaction medium for the oxidation reaction mixture is wholly or largely water. Suitable metal or metalloid compounds are at least partially soluble in the water or acidic preparation solvent or form at least partially soluble species on combination with salts or compounds of the other metals or metalloids used in preparing the compositions. Carboxylate salts of the metals and metalloids, such as acrylates, acetates, propionates, butyrates, hexanoates, cyclohexanoates, oxalates, and benzoates, and preferably those with 2 to about 10 carbon atoms, are generally preferred owing to their solubility in common organic solvents and availability. For a given metal or metalloid, other suitable compounds can include oxides, hydroxides, carbonates, chlorides, nitrates, sulfates, sulfites, methanesulfonates, trifluoromethanesulfonates, tetrafluoroborates, oxides, acetylacetonates, methoxides, ethoxides, propoxides, butoxides, and other alkoxides, hydrides, phosphates and combinations thereof. Bromine-free salts and compounds of the metals and metalloids used for preparing the catalytic compositions are preferred because presence of reactive bromine at high enough concentrations in oxidation reaction mixtures using the invented catalyst compositions has been seen to correlate with decreases in activity and selectivity of the catalyst compositions and undesired precipitation of soluble metal or metalloid components from the reaction mixtures. Preferred metal and metalloid salts also are free of halogens other than bromine although such other halogens may be present provided they do not cause undesirable corrosion in use of the catalytic compositions or adversely affect activity or selectivity of the compositions.

Another preferred form of the invented catalytic compositions comprises a water and/or monocarboxylic acid-insoluble composition formed from a

palladium, platinum, vanadium or titanium composition or combination thereof and one or more Group 5, 6, 14 or 15 metal or metalloid compounds or combinations thereof. Such insoluble compositions are conveniently prepared by contacting solutions of individual or combined metal and metalloid compositions such as described in the previous paragraph, with the metal and metal or metalloid compositions, contacting conditions or additional preparative steps selected to yield a wholly or partially solid product. In one embodiment, a solid catalyst composition is conveniently prepared by contacting a solution of metal and metal or metalloid compounds with air or another oxygen source at above-ambient temperatures such as about 80°C or greater and preferably at about 90°C to about 150°C. In some embodiments, the insoluble reaction product is a catalytically active composition while in other embodiments, the insoluble portion exhibits activity in combination with a soluble portion remaining after reaction to form the insoluble product. By way of example, combining acetic acid solutions of palladium(II), antimony(III) and tin(II) acetates under an inert atmosphere in amounts providing approximately equimolar palladium, antimony and tin tends to yield a solid precipitate which is active for oxidation of substituted aromatic compounds. When an acetic acid solution of molybdenum(II) dimer providing approximately equimolar molybdenum is also included in the solution, solid precipitate comprising substantially all of the palladium, antimony and tin but only a portion of the molybdenum forms with another portion of the molybdenum remaining in solution, with both the solid portion and its combination with the insoluble portion showing activity. When the solutions are contacted in the presence of oxygen, solid comprising essentially all of the palladium, antimony, tin and molybdenum is obtained and is active.

Another suitable form of the invented catalyst compositions comprises at least one of the platinum, palladium, vanadium or titanium metal components or Group 5, 6, 14 or 15 metal or metalloid components carried on a solid support material in the form of a supported catalyst composition or component. Preferred supported catalyst compositions comprise platinum, palladium, titanium or vanadium components and Group 5, 6, 14 or 15 metal or metalloid components carried on a support material.

Metal and metalloid components used to prepare catalyst solutions or insoluble catalyst compositions or components can be in any valence state that provides a composition having activity and selectivity under conditions of use for oxidation of substituted aromatic compounds in which substituent groups comprise an oxidizable alpha carbon to oxidized product comprising aromatic carboxylic acid derivatives of the substituted aromatic compound.

Specific examples of suitable palladium compounds for preparing catalytic compositions include Pd(II) acetate, Pd(II) acetylacetonate, Pd(II) propionate, Pd(II) nitrate, Pd(II) cyanide, Pd(II) hydroxide, Pd(II) oxide, Pd(II) sulfate and Pd(II) sulfide. Halide salts can be used in preparation of solid or supported catalyst compositions or components in which halogen derived from the starting salts is not, or is only negligibly, present in the final supported composition. For preparation of catalyst compositions or palladium components thereof in the form of solutions in water or aqueous organic acids, however, use of halide salts and especially bromides, is preferably avoided. For preparation of supported catalyst compositions in which palladium, either alone or with other metals or metalloids of the compositions, is carried on a support, palladium supported on a suitable support material such as described below and palladium(0) alloys also are useful.

Specific examples of suitable platinum compounds for preparation of catalyst compositions include Pt(II) acetylacetonate, Pt(II) cyanide, Pt(IV) oxide, Pt(IV) oxide hydrate, Pt(IV) oxide monohydrate, Pt octaethylporphyrin and Pt(IV) sulfide. As with the palladium salts, platinum halides such as Pt(II) chloride, Pt(II) diamine dichloride and Pt(II) iodide are suitable for preparation of supported catalyst compositions or components that are free of halogen but are best avoided in preparing catalyst compositions and components for use in homogeneous form in oxidation processes. For preparation of solid or supported catalysts, platinum(0) supported on a suitable support, as described more fully below and platinum(0) alloys also can be utilized.

Specific examples of suitable vanadium compounds useful for preparing catalyst compositions include V(III) acetylacetonate, V(IV) carbide, V(III) oxide, V(IV) oxide, V(V) oxide, V(IV) oxide sulfate, V(V) oxytriethoxide, V(V)

oxytriisopropoxide, V(V) oxytripropoxide, V oxide acetylacetonate and V oxide 2,3-naphthalocyanine.

5 Examples of titanium compounds that are suitable for catalyst composition preparation include Ti(IV) butoxide, Ti(IV) carbide, Ti(IV) carbonitride, Ti(IV) diisopropoxide bis(acetylacetonate), Ti(IV) ethoxide, Ti(II) hydride, Ti(IV) isopropoxide, Ti(IV) methoxide, Ti(IV) chloride, Ti(IV) nitrate, Ti(IV) nitride, Ti(II) oxide acetylacetonate, Ti(IV) oxysulfate, Ti(IV) propoxide, Ti(III) sulfate and Ti(IV) sulfide.

10 Examples of useful Group 5 metal compounds include the vanadium compounds exemplified above, Nb(IV) carbide, Nb(V) chloride, Nb(IV) chloride, Nb(III) chloride, Nb(V) ethoxide, Nb(V) fluoride, Nb(V) iodide, Nb nitride, Nb(II) oxide, Nb(IV) oxide and Nb(V) oxide.

15 Examples of useful Group 6 compounds include Mo(II) acetate, Mo(II) carbide, Mo(0) hexacarbonyl, Mo(IV) oxide, Mo(VI) oxide, Mo(IV) sulfide, molybdic acid and various molybdates (MoO_4^-); chromium salts such as Cr(III) acetate, Cr(III) acetylacetonate, Cr(III) carbide, Cr hexacarbonyl, Cr(III) nitrate, Cr(III) nitride, Cr(III) oxide, Cr(VI) oxide, Cr(III) phosphate, Cr(III) sulfate, and various chromates (CrO_4^-) and dichromates (Cr_2O_7^-)

20 Examples of useful Group 14 metal or metalloid compound include germanium compounds such as Ge(II) acetate, Ge(IV) chloride, Ge(IV) ethoxide, Ge(IV) fluoride, Ge(IV) isopropoxide, Ge(IV) methoxide, Ge(III) nitride, Ge(IV) oxide and Ge(II) sulfide; tin compounds such as Sn(II) acetate, Sn(IV) acetate, Sn(2) oleate, Sn(IV) t-butoxide, Sn(II) 2-ethylhexanoate, Sn(II) hydride, Sn(II) iodide, Sn(II) methanesulfonate, Sn(II) 2,3-naphthalocyanine, Sn(II) oxalate, Sn(II) phthalocyanine, Sn(II) pyrophosphate, Sn(II) sulfate and Sn(II) sulfide; and lead compounds such as Pb(II) acetate, Pb(IV) acetate, Pb(II) acetylacetonate, Pb(II) carbonate, Pb(II) chloride, Pb(II) iodate, Pb(II) chromate, Pb(II) metavanadate, Pb(II) methanesulfonate, Pb(II) molybdate, Pb(II) niobate, Pb(II) nitrate, Pb(II) oxide, Pb(IV) oxide, Pb(II) phthalocyanine, Pb(II) salicylate, Pb(II) sulfate, Pb(II) sulfide, Pb(II) thiocyanate, Pb(II) titanate, Pb(II) tungstate and Pb(II) zirconate.

25

30

Examples of useful Group 15 metal or metalloid compounds include antimony compounds such as Sb(III) acetate, Sb(III) butoxide, Sb(III) ethoxide, Sb(III) isopropoxide, Sb(III) methoxide, Sb(III) oxide, Sb(IV) oxide, Sb(V) oxide, Sb(III) propoxide, Sb(III) sulfide, Sb(V) sulfide, antimony tin oxide; bismuth salts including Bi(III) acetate, Bi(III) carbonate, Bi(III) chloride, Bi(III) citrate, Bi(III) fluoride, Bi(V) fluoride, Bi(III) iodide, Bi(III) molybdate, Bi neodecanoate, Bi(III) nitrate, Bi(III) oxide, Bi(III) oxychloride, Bi(III) perchlorate, Bi(III) phosphate, Bi(III) salicylate, Bi(III) sulfide, Bi(III) titanate, Bi(III) triflate and Bi(III) zirconate.

Halides of the metals and metalloids included above are suitable used in preparing supported or other solid catalyst compositions and components from which halogen from starting materials is absent or present in only traces, but not in preparing soluble forms of the invented catalyst or their components for process use. As with palladium and platinum, supported and other insoluble forms of the titanium, vanadium and Group 5, 6, 14 and 15 metals and metalloids, including their alloys also are useful in preparing solid and supported catalysts and components.

Additional metals and metalloids, e.g., aluminum, gold, calcium, cadmium, cerium, copper, iron, gallium, hafnium, indium, iridium, potassium, lithium, sodium, rhodium, ruthenium, selenium, zinc and combinations thereof may be included in the compositions although their effects can vary depending on other components of the compositions and amounts in which they are used. Compounds of other metals and metalloids that may be used for preparation of catalyst compositions include acetates, oxalates, benzoates and other carboxylates, hydroxides, nitrates, sulfates, sulfites, oxides, hydrides, carbonates, phosphates, perchlorates, methanesulfonates, trifluoromethanesulfonates, tetrafluoroborates, acetylacetonates, methoxides, ethoxides, propoxides, butoxides and other alkoxides as well as solid and supported forms and alloys thereof. Selection of such additional metals or metalloids and combinations varies with choices and combinations of platinum, palladium, vanadium and titanium and of Group 5, 6, 14 and 15 metal or metalloid of the composition. In a specific embodiment of the invention, catalyst compositions containing palladium and bismuth are enhanced by inclusion of

gold, which can conveniently be used in catalyst or component preparations in the form of gold(I) sulfide gold(I) cyanide, gold(III) hydroxide, gold(III) oxide, and gold(III) sulfide; chlorides and iodides such as gold(I) chloride or iodide and gold(III) chloride may also be used but are less preferred for preparing compositions and components to be used in soluble form due to potential corrosion from chlorides and iodides. Cobalt, nickel, zirconium and silver tend to diminish performance of catalyst compositions containing platinum when used in approximately equal amounts, as do combinations of cerium and hafnium.

Organic acid solutions of the palladium, platinum, vanadium or titanium and Group 5, 6, 14 or 15 metals or metalloids of the catalyst compositions and optional additional metal and/or metalloid components are preferred forms of the invented compositions not only due to ease of preparation and availability of common metal and metalloid compounds useful for their preparation but also because they are in a form compatible with use of the catalytic compositions in oxidation of substituted aromatic feed materials in liquid phase reaction systems. It may also be desirable in some embodiments that the catalytic composition be formed by separate or sequential addition of metal and/or metalloid compounds or components or combinations thereof such that a final catalytic composition is formed on addition to the liquid reaction mixture used for oxidation of substituted aromatic feed materials. While a preferred form of the compositions comprises a solution of metal and/or metalloid components in a carboxylic acid or aqueous carboxylic acid solvent, it also is to be understood that the invention includes other forms of the catalytic composition or its constituent metals, metalloids or combinations thereof.

In another preferred embodiment of the invention, catalytic compositions or components thereof are formulated with support materials. The catalytic composition or components can be deposited or otherwise combined with the support material by any suitable technique, such as by contacting a support material, for example in the form of pellets, granules, extrudate or other particulate or solid form suited to process use, with a solution of catalyst metal compounds in water or another solvent that is inert to the support and easily removed, after which the solvent is removed, such as by drying at ambient or

elevated temperature. For such preparations, a single solution of all catalyst metal or metalloid salts or compounds can be employed as can concurrent or sequential impregnations with solutions of individual catalyst metals or metalloids or combinations. Support materials pre-impregnated with one or more metals or metalloids, for example supported platinum or palladium components, can be contacted with a solution or solutions of other catalyst metal or metalloid. So-called "incipient wetness techniques," in which a support is contacted with a solution of the catalyst metal compound in an amount that just wets the support and then the resulting wetted support is dried, are known and well suited to manufacture of the catalysts. In another suitable technique, sometimes referred to as the "excess solution method," the support is contacted with a greater volume of one or more impregnation solutions than required to wet the support, after which solvent is removed by drying, for example by evaporation under ambient conditions or with moderate heating. Excess solution techniques are sometimes preferred over incipient wetness methods when using low surface area supports. Other techniques, such as spraying a solution of catalyst metal compound or compounds onto a support material also are suitable. Post-treatments, such as heating and high temperature calcinations in the presence of air or nitrogen, and reduction with hydrogen also may be yield catalyst compositions or components with advantages or characteristics of interest.

For use in the invented process, any carrier for the catalyst composition or components thereof that is stable in the environment and under conditions of process use is suitable. Preferred support materials are solids that are stable in the sense of maintaining physical integrity and metal or metal and metalloid loadings suitable to process operation over prolonged exposures to process conditions and use. Substantial insolubility of the support and resistance to significant loss of catalyst metal or metalloid loadings in water or aqueous acetic acid solutions at temperatures of at least about 100°C for a period on the order of several days, for example at least 7 days, are indicative of suitable support materials. Preferred supports for use in the invented process include carbons and non-zeolitic metal oxides such as alpha alumina, silicas and titania, including rutile and anatase forms thereof and mixed forms in which both anatase and

rutile phases are present. Non-zeolitic supports are preferred because zeolites tend to lack adequate stability for use in oxidations. Other supports which may be suitable include high strength, acid stable silicon carbides, zirconia, gamma alumina and zinc oxide. Common examples of suitable commercially available carbon supports tend to have BET surface areas ranging from about one or even a fractional square meter per gram up to about 1500 m²/g. Metal oxide surface areas tend to run from about 1 m²/g in the case of rutile titanias up to about 500 m²/g for silicas. Support materials can be used in any suitable form, examples of which include powders, particulates, pellets, extrudate, tablets, granules, spheres and microspheres. Catalyst metal loadings of supported compositions are not critical though loadings in the range of about 0.1, and preferably 0.5 to about 20 and preferably 15 percent by weight of the supported composition are preferred for high catalyst performance and activity.

Proportions of the palladium, platinum, vanadium or titanium metal and the Group 5, 6, 14 or 15 metal or metalloid components of the invented catalytic compositions can vary widely. Preferably, palladium, platinum, vanadium, titanium or a combination thereof and Group 5, 6, 14 or 15 metal or metalloid or combination thereof are present in amounts such that the atom ratio of palladium, platinum, vanadium or titanium or a combination thereof to the Group 5, 6, 14, or 15 metal or metalloid or combination is about 1 : 1000 to about 1000 : 1, and more preferably about 1 : 100 to about 100 : 1. Proportions of palladium, platinum, vanadium, titanium or a combination thereof and of one or more Group 5, 6, 14 and 15 metal or metalloid elements in various combinations can be determined and optimized for particular combinations and usages by persons skilled in catalytic oxidations for manufacture of benzene and naphthalene dicarboxylic acids guided by the description and examples herein.

In more particular embodiments of the invention, a catalyst composition comprises palladium and at least one Group 5, 6, 14 or 15 metal or metalloid. Such compositions are useful in the invented process in unsupported or supported form or with a combination of supported and unsupported palladium and Group 5, 6, 14 or 15 metal(s) or metalloid(s). Preferred catalysts according

to this embodiment are those in which at least one Group 14 or 15 metal or metalloid or combination thereof with at least one Group 4 or 5 metal is present.

5 A preferred catalytic composition according to embodiments of the invention comprises at least one palladium component and at least one antimony or bismuth component. More preferably, such a composition also contains titanium or at least one additional Group 5, 6 or 14 metal or metalloid. Preferred compositions are those in which the additional metal or metalloid component comprises tin, titanium, molybdenum, vanadium, chromium, niobium or a combination thereof. Especially preferred compositions comprise a palladium component, an antimony component and at least one component of tin, titanium, 10 vanadium or molybdenum. Another particularly preferred composition comprises a palladium component, a bismuth component and at least one tin, titanium, niobium, molybdenum or vanadium component. Metals such as gold, gallium, calcium and zinc can also be beneficial when included in the catalysts.

15 Such compositions can exhibit desirable activities for oxidation of substituted aromatic substrates according to the invention with good selectivity to aromatic carboxylic acid derivatives and, in some embodiments, relatively low burning of aromatic substrates and organic acid reaction solvents to carbon oxides. As described above, atom ratios of the palladium and other metal or metalloid in such compositions can vary widely and can be optimized or tailored to applications by routine experimentation guided by the disclosure herein. Palladium and other metal or metalloid component or components are preferably present in amounts such that the atom ratio of palladium to each other metal or metalloid is about 1 : 100 to about 100 : 1. More preferably, in compositions 20 comprising palladium and antimony or bismuth, the atomic ratio of antimony and/or bismuth to each such other metal or metalloid also is about 1 : 10 to about 10 : 1. Preferably, the compositions are free or at least substantially free of reactive bromine. In some embodiments, compositions according to invention in which the atom ratio of palladium to one or more of antimony, bismuth or tin is about 1 : 1 and more preferably about 1.5 : 1 to about 10 : 1 and more preferably about 5 : 1, and in which the atom ratio of palladium to one or more additional metals or metalloids such as molybdenum, titanium or vanadium is about 0.3 : 1, 25 30

and preferably about 1 : 1 to about 5 : 1 and more preferably about 3 : 1, are highly effective for oxidations with high conversions and selectivities. A specific example of such a catalyst that is particularly effective composition for oxidation of disubstituted aromatic compounds with high conversion and selectivity to corresponding aromatic dicarboxylic acids includes a palladium component, at least one antimony or tin component, and a vanadium or molybdenum component or a combination thereof or of either with another metal or metalloid component such as chromium or titanium, in amounts such that the atom ratio of palladium to antimony or tin (or a combination thereof) to molybdenum, vanadium or combination thereof with each other or such other metals or metalloids is about 1 : 1 : 0.5.

Another catalytic composition according to more specific embodiments of the invention comprises at least one palladium component and at least one Group 14 metal or metalloid component. Tin is a preferred Group 14 metalloid with respect to conversion and selectivity of the compositions in oxidation of substituted aromatic substrates. More preferably, such compositions also comprise at least one other metal or metalloid component because such compositions tend to show good conversions and selectivities with less loss of aromatic substrate to carbon oxides than if the additional metal or metalloid were not present. Preferred compositions comprising palladium, tin, at least one of antimony or bismuth, and one or more optional additional metals or metalloids are described above. Other preferred compositions comprise palladium, tin and one or more of titanium, molybdenum, vanadium, chromium. Especially preferred compositions comprise a palladium component, a tin component and at least one component comprising antimony, molybdenum, vanadium, chromium or a combination thereof. Such compositions are effective in the absence of reactive bromine for oxidation of substituted aromatic substrates with oxidizable alpha-carbon-containing substituents with good yields of oxidized product selectivity to aromatic carboxylic acid derivatives and often with low carbon oxide generation. Atom ratios of palladium, tin and other metal or metalloid in such compositions can vary and preferred proportions can be determined or optimized by experimentation, as described above. Preferably, palladium, tin and, if

present, other metal or metalloid components, are present in amounts such that the atom ratio of palladium to tin is about 1 : 10 to about 10 : 1 and the atom ratio of palladium to each other metal or metalloid is about 1 : 10 to about 10 : 1. More preferably, the atom ratio of tin to any such other metal or metalloid is about 1 : 1 to about 10 : 1.

Another preferred catalytic composition according to specific embodiments of the invention comprises platinum and at least one Group 5, 6, 14 or 15 metal or metalloid component. Preferred among such platinum-containing compositions are those in which a Group 5 or 6 metal or combination thereof or of one or both with titanium is also present. In such combinations, vanadium and niobium are preferred Group 5 metals. Molybdenum and chromium are preferred Group 6 metals. An especially preferred composition according to this embodiment of the invention comprises platinum, titanium and vanadium. Such compositions exhibit desirable activities for oxidation of substituted aromatic substrates according to the invention with good selectivity to aromatic carboxylic acid derivatives. Liquid phase oxidation of alkyl aromatic substrates with oxygen gas according to embodiments of the invention using such a catalyst in aqueous acetic acid solvent for the oxidation and in the absence of reactive bromine sources yielded high conversions of substrates to oxidized aromatic product as compared to oxidations using the individual metals or metalloids, other things being equal, and with surprising selectivity to aromatic carboxylic acids. Atom ratios of platinum and other metal or metalloid components in compositions according to this embodiment of the invention can vary and, as described above, optimized proportions can be determined by routine experimentation guided by the disclosure herein. Preferably, platinum, Group 5, 6, 14 or 15 metal or metalloid and titanium if present are in amounts such that the atom ratio of palladium to Group 5, 6, 14 or 15 metal or metalloid about 1 : 10 to about 10 : 1. In compositions that include titanium in addition to the platinum and Group 5, 6, 14 or 15 metal or metalloid components, the platinum to titanium atom ratio is preferably about 1 : 100 to about 100 : 1 and more preferably about 10 : 1 to about 1 : 10.

Another preferred catalytic composition according to specific embodiments of the invention comprises vanadium and at least one Group 5, 6, 14 or 15 metal or metalloid component, it being understood that such embodiments do not include compositions consisting of vanadium alone. Preferred vanadium-
5 containing compositions are those in which a Group 15 metal or metalloid, and especially antimony or bismuth. Compositions comprising vanadium and platinum or palladium, optionally with Group 5, 6, 14 or 15 components and especially molybdenum, chromium, tin, antimony, bismuth or combinations thereof are described above. Atom ratios of vanadium and other metal or
10 metalloid components in compositions according to this embodiment of the invention can vary and, as described above, relative proportions can be determined and optimized by routine experimentation guided by the disclosure herein. Preferably, vanadium and other metal and metalloid components are present in amounts such that the atom ratio of vanadium to Group 5, 6, 14 or 15
15 metal or metalloid is about 1 : 10 to about 10 : 1.

In other embodiments of the invention, a preferred catalytic composition comprises titanium and at least one Group 5, 6, 14 or 15 metal or metalloid component. A preferred titanium-containing compositions comprises at least one Group 5 metal, and especially vanadium, in addition to the titanium. Preferred
20 platinum- and palladium-containing compositions in which titanium is also present are described above. Titanium-containing compositions in which molybdenum is also present also are preferred. Atom ratios of titanium and other metal or metalloid components in compositions according to this embodiment of the invention can vary widely. As described above, relative proportions can be
25 determined and optimized by routine experimentation guided by the disclosure herein. Preferably, titanium and other metal and metalloid components are present in amounts such that the atom ratio of titanium to Group 5, 6, 14 or 15 metal or metalloid is about 1 : 10 to about 10 : 1.

The mechanism or mechanisms by which the invented compositions
30 catalyze reaction of oxidizable alpha carbon substituent-bearing aromatic compounds with oxygen to oxidized products with selectivity to aromatic carboxylic acids in which the aromatic ring is linked to carbon atoms of one or

more carboxylic acid groups is not understood. The compositions exhibit activity for oxidation of alkyl-substituted aromatics as well as partially oxidized derivatives thereof, such as toluic acids, hydroxymethyl benzoic acids, aromatic aldehydes and carboxybenzaldehydes, to more completely oxidized carboxylic acid derivatives.

As seen from the Examples herein, certain of the individual metals and metalloids of the invented compositions exhibit some activity for conversion of para-xylene to oxidized aromatic derivatives thereof; however, conversions are accompanied by highly varying selectivities to oxidized derivatives of the para-xylene and often by comparable or even greater burning of the para-xylene to carbon oxides. However, compositions in which platinum, palladium, vanadium or titanium is present in combinations including a Group 5, 6, 14 or 15 metal or metalloid showed increased and often unexpected conversions to oxidized aromatic derivatives, selectivities, reduced carbon oxide generation or combinations of those improvements and, in some cases, potential for further improvement by addition of combinations of Group 5, 6, 14 or 15 metals or metalloids.

Activity and selectivity of the invented compositions have been demonstrated in liquid reaction media, including essentially neutral systems such as water as well as mildly and strongly acidic media. The invented compositions show surprising differences in sensitivity to water as compared to known, bromine-promoted catalysts for oxidation of alkyl aromatics. Known bromine-promoted catalysts used in commercial manufacture of terephthalic acid by oxidation of para-xylene or of isophthalic acid by oxidation of meta-xylene tend to fall off in conversion activity in aqueous acetic acid reaction media with increases in water content of as little as 1 wt%. In contrast, with catalytic compositions according to embodiments of the invention, oxidations continued to progress actively even as water concentrations in liquid reaction media increased to almost 50%. In para-xylene oxidations with the invented compositions, selectivity to fully oxidized terephthalic acid product was virtually unchanged at water levels ranging from about 5 to about 40 wt%, and selectivities to partially oxidized intermediates capable of being oxidized further to terephthalic acid

tended to decrease in minor amounts, which is an indication of increased catalytic activity. Even with 100 wt% water as liquid reaction medium, oxidation ranged from modest to vigorous while selectivity to aromatic carboxylic acids was generally greater than 50% and as high as 80% or more.

5 Compositions according to embodiments of the invention exhibit activity and selectivity for converting oxidizable alpha carbon-substituted aromatic compounds to carboxylic acid derivatives, with relatively low levels of burning of the substrate compounds or of organic acids used as reaction solvents. Generation of carbon oxides tends to increase with increasing temperature, other
10 things being equal, and conversion to carbon dioxide appears to be favored over carbon monoxide.

The compositions are active for oxidation of substituted aromatic substrates and show selectivity to aromatic carboxylic acids in the absence of reactive bromine. In oxidation trials conducted with added aqueous hydrogen
15 bromide as a source of reactive bromine, neither conversions to oxidized aromatic derivatives nor selectivities to carboxylic acid derivatives were improved. The invented catalyst compositions appear to be tolerant of small amounts of reactive bromine in oxidation of substituted aromatic substrates, although amounts of less than 5% by weight of total catalyst metal and
20 metalloid have been observed to deactivate the compositions in the sense that selectivity to carboxylic acid derivatives is more favorable to less fully oxidized products such as aldehydes and, in conversions of di-substituted aromatics, to derivatives with a single carboxylic acid group and one or more unconverted or only partially oxidized group such as an hydroxymethyl or aldehyde group. With
25 still larger amounts of bromine, e.g., 400 - 500 ppmw, at least some of the compositions according to the invention show loss of conversion, to the point that little or no oxidized product is obtained. Preferably, reactive bromine is present at levels less than about 2 wt% based on catalyst metal and metalloid weight.

The invented compositions also appear to deactivate with increasing
30 levels of methyl ethyl ketone, which is a known sacrificial, organic promoter for cobalt-based catalysts used for oxidation of alkyl aromatics. At low levels,

activity and selectivity appear relatively unaffected but at greater levels, conversion drops and selectivity shifts away from aromatic carboxylic acids toward less fully oxidized derivatives.

5 Although catalytic mechanisms and reaction pathways of the invented catalytic compositions are not understood, the compositions are effective for oxidation of substituted aromatic substrates, exhibiting activity for substantial conversion of substituent groups comprising alpha carbon atoms to more fully oxidized derivatives substituted with aldehyde groups, carboxylic acid groups or combinations thereof with selectivity to carboxylic acid groups, and without need
10 for use of bromine to promote the oxidation. Activity and selectivity of the compositions in the absence of reactive bromine afford a number of benefits and opportunities for advantage over conventional processes for oxidizing aromatic substrates using bromine-promoted catalysts, as well as alternative proposals that rely on catalysts with low activities and selectivities, alkaline reaction media
15 or catalysts prone to conversion to insoluble precipitates that can cause plugging in other process steps. In the manufacture of aromatic carboxylic acids from aromatic feed materials, and particularly alkyl aromatic hydrocarbons such as toluene, xylenes and methyl naphthalenes, the invention can provide opportunities for process simplification and costs savings by allowing bromine to
20 be eliminated from oxidation process and catalyst systems. Such opportunities include potential not only for eliminating or reducing requirements for treatment of process effluents, such as by thermal or catalytic oxidation and scrubbing, to eliminate unwanted brominated by-products of the process, but also for downgrading metallurgy of reaction vessels, agitators and associated reaction
25 off-gas treatment equipment, such as condensers, distillation columns and the like, from expensive titanium metal and nickel alloy steel solid and clad constructions commonly required for conventional bromine-promoted catalytic oxidations to less corrosion resistant constructions such as stainless or mild steels or with reduced cladding. Furthermore, high temperature oxidations, for
30 example at temperatures of about 170°C and greater, can be conducted without substantial burning of aromatic substrates or carboxylic acid solvents to carbon oxides. Oxidations in water or dilute aqueous organic acid liquid reaction media

or solvents also provide opportunities for reduced organic solvent usage, reduced corrosivity of reaction mixtures, process streams, effluents and off-gases and potential for process simplification and downgrading materials of construction of process equipment.

5 Briefly, the invented process provides for conversion of an aromatic feedstock comprising a substituted aromatic compound, at least one substituent group of which comprises an alpha carbon atom, to oxidized aromatic product comprising at least one aromatic carboxylic acid derivative of the substituted aromatic compound, i.e., a derivative of the substituted aromatic starting material
10 in which at least one carboxylic acid group comprises an alpha carbon atom, by contacting the aromatic feedstock with oxygen in a liquid reaction mixture in the presence of a catalytic composition according to the invention. Oxidation of substituted aromatic feed materials is selective to aromatic carboxylic acid derivatives in which at least one substituent group is a carboxylic acid group
15 having an alpha carbon atom but the oxidation product can also include derivatives with less fully oxidized substituents or in which one but not all of the substituent groups of the starting material is oxidized to a carboxylic acid group while other groups are less fully oxidized or remain unconverted. Other things being equal, conversions and selectivities with the invented catalytic
20 compositions exceed those using individual metals or metalloids of the compositions. Conversion to oxidized aromatic derivatives of aromatic starting materials preferably is at least about 25 mole % and, in some embodiments of the invention, approaches 100 mole %. Selectivity to aromatic carboxylic acid derivatives, taking into account all carboxylic acid-substituted oxidation products
25 of the aromatic feed material, is preferably at least about 40 % and can approach 100 %. According to some embodiments of the invention, conversions of at least about 80 mole % with at least 80%, and more preferably 90% or greater, selectivity to a single aromatic acid derivative are achieved such that the invention provides processes for manufacture of such derivatives in which
30 recovery techniques and recycle of intermediate oxidation products can be minimized or simplified. Preferred aromatic carboxylic acids for which embodiments of the invented process is suited are those manufactured in a liquid

phase reaction system and include mono- and polycarboxylated species having one or more aromatic rings in which at least one, and preferably all, of the carboxylic acid groups comprise a carbon atom linked directly to the aromatic ring, i.e., an alpha carbon atom. Examples of such aromatic carboxylic acids include terephthalic acid, trimesic acid, trimellitic acid, phthalic acid, isophthalic acid, benzoic acid and naphthalene dicarboxylic acids.

Liquid phase oxidation according to embodiments of the invented process is conducted at elevated temperature and pressure, and preferably under pressure effective to maintain a liquid phase reaction mixture. Oxidation of the aromatic feed material in the liquid phase oxidation step produces oxidized product comprising aromatic carboxylic acid as well as reaction by-products such as partial or intermediate oxidation products of the aromatic feed material. The liquid-phase oxidation and associated process steps, such as product recoveries, separations, purifications and off-gas and liquid effluent treatments, can be conducted as a batch process, a continuous process, or a semi-continuous process.

Suitable aromatic feed materials for the oxidation generally comprise an aromatic hydrocarbon substituted at one or more positions, normally corresponding to the positions of the carboxylic acid groups of the aromatic carboxylic acid being prepared, with at least one group that includes an alpha carbon atom that is oxidizable to a carboxylic acid group. The oxidizable substituent or substituents can be alkyl groups, such as a methyl, ethyl or isopropyl groups, or groups already containing oxygen, such as a hydroxyalkyl, formyl or acyl group. The substituents can be the same or different. The aromatic portion of feedstock compounds can be a benzene nucleus or it can be bi- or polycyclic, such as a naphthalene nucleus. The number of oxidizable substituents on the aromatic portion of the feedstock compound can be equal to the number of sites available on the aromatic ring, but is generally fewer than all such sites and preferably 1 or 2 and most preferably 2. Examples of useful feed compounds, which can be used alone or in combinations, include toluene, ethylbenzene and other alkyl-substituted benzenes, o-xylene, p-xylene, m-xylene, tolualdehydes, toluic acids, alkyl benzyl alcohols, 1-formyl-4-

methylbenzene, 1-hydroxymethyl-4-methylbenzene, methyl-acetophenone, 1,2,4-trimethylbenzene, 1-formyl-2,4-dimethylbenzene, 1,2,4,5-tetra-methylbenzene, alkyl-, formyl-, acyl-, and hydroxymethyl-substituted naphthalenes, such as 2,6-dimethylnaphthalene, 2,6-diethylnaphthalene, 2,7-dimethylnaphthalene, 2,7-diethylnaphthalene, 2-formyl-6-methylnaphthalene, 2-acyl-6-methylnaphthalene, 2-methyl-6-ethylnaphthalene and partially oxidized derivatives of the foregoing.

For manufacture of aromatic carboxylic acids by oxidation of their correspondingly substituted aromatic hydrocarbon pre-cursors, e.g., manufacture of benzoic acid from mono-substituted benzenes, terephthalic acid from para-disubstituted benzenes, phthalic acid from ortho-disubstituted benzenes, and 2,6- or 2,7-naphthalenedicarboxylic acids from, respectively, 2,6- and 2,7-disubstituted naphthalenes, it is preferred to use relatively pure feed materials, and more preferably, feed materials in which content of the precursor corresponding to the desired acid is at least about 95 wt.%, and more preferably at least 98 wt.% or even higher. Preferred precursors include alkyl aromatic compounds as well as their partially oxidized derivatives. By way of example, in the case of para-xylene, examples of partially oxidized derivatives that also can be converted to more fully oxidized product comprising aromatic carboxylic acid include derivatives such as p-methylacetophenone, p-toluic acid, p-hydroxymethyl benzoic acid, tolualdehyde and 4-carboxybenzaldehyde. A preferred aromatic hydrocarbon feed for use to make terephthalic acid comprises para-xylene. A preferred feed material for benzoic acid comprises toluene.

Oxidation of aromatic feed materials according to the invented process is conducted in a liquid reaction mixture. Acidic reaction media are preferred. Water can be used as the reaction medium with surprisingly good conversions and selectivities. Water generated as by-product in oxidations of aromatic feed materials according to the invention can serve as liquid medium for the reaction, thereby eliminating or reducing the need for addition of water to the process from external sources or by recycle of water from other process steps and also eliminating use or presence of different liquids and process and equipment complexities that may be needed for their separation and recycle or re-use. In one embodiment, a preferred liquid medium for the reaction mixture comprises

water and not more than about 10% C₁-C₈ monocarboxylic acid. Preferred solvents for aromatic feed materials in the liquid phase reaction comprise low molecular weight monocarboxylic acids and preferably a C₁-C₈ monocarboxylic acid, for example acetic acid, propionic acid, butyric acid, valeric acid and benzoic acid. Acetic acid is a preferred among such monocarboxylic acids. Solvents in the form of aqueous solutions thereof, for example about 40 to about 95 wt.% solutions of the acid can be used with good results. Ethanol and other co-solvent materials that oxidize to monocarboxylic acids under the liquid phase oxidation reaction conditions also can be used as is or in combination with monocarboxylic acids. While water is a preferred liquid medium for the process and monocarboxylic acid solvents for the liquid reaction medium are preferred, other suitable solvents or liquid media can be used. According to preferred embodiments of the invention in which the process is conducted in a non-alkaline reaction mixture, examples of liquid media that can be used with or as alternatives to water and C₁-C₈ monocarboxylic acids, include oxalic acid, malonic acid, methyl malonic acid, dimethyl malonic acid, succinic acid, methyl succinic acid, glutaric acid and cyanoalkanes or cyanoarenes, for example, acetonitrile or benzonitrile, respectively, and including aqueous forms thereof and combinations of two or more thereof may be suitable. Catalysts used for liquid phase oxidations according to the invention comprise at least one palladium, platinum, vanadium or titanium component and at least one Group 5, 6, 14 or 15 metal or metalloid components as described above. Preferred catalysts in some embodiments of the invention are soluble in the liquid phase reaction mixture used for oxidation because soluble catalysts can promote contact among catalyst, oxygen and liquid feed materials; however, in other preferred embodiments, catalysts in heterogeneous form or having one or more heterogeneous components used. Catalysts compositions or components thereof that are used in heterogeneous form can be supported or unsupported.

In preferred embodiments, liquid phase oxidation according to the invention is carried out in the absence or substantial absence of active bromine. Although minor amounts of bromine do not appear to hinder catalyst performance, the invented catalysts are active and selective without bromine

and, in at least some embodiments, tend to become less active or selectivities shift from more to less fully oxidized aromatic carboxylic acid derivatives with increasing bromine levels. In preferred processes according to the invention, reactive bromine content of the liquid reaction mixture is no more than about 50 ppm by weight of the reaction medium. Minor amounts of reactive bromine that do not have substantial adverse effects on catalyst performance may be tolerated but the reaction system most preferably is free of reactive bromine due to its and its by-products' corrosivity.

Reactants for the liquid phase reaction of the oxidation step also include a source of molecular oxygen. Gaseous oxygen sources are preferred, with air conveniently used as such a source. Oxygen-enriched air, pure oxygen and other gaseous mixtures comprising molecular oxygen also are useful.

Proportions of aromatic feed material, catalyst, oxygen and liquid reaction medium or solvent are not critical and can be varied widely based on factors that include choice of reactants, liquid medium or solvent and catalyst compositions and intended oxidized and aromatic carboxylic acid products, details of process design and operating factors. Solvent or liquid reaction medium to aromatic feedstock weight ratios ranging from about 1:1 to about 30:1 are preferred, with about 2:1 to about 5:1 being more preferred although higher and lower ratios, even in the range of hundreds to one also can be used. Oxygen typically is used in at least a stoichiometric amount based on aromatic feed material but, in the case of gaseous oxygen, not so great, taking into account reactant and solvent compositions, reaction conditions and rates, that off-gases generated as a result of the liquid phase oxidation form a flammable mixture. Oxygen, most commonly supplied in the form of air, is preferably supplied at a rate effective to provide at least about 3 to about 5.6 moles molecular oxygen per mole of aromatic hydrocarbon feed material. Catalyst is used in amounts effective for conversion of aromatic feed material to oxidized product and can vary widely. Other things being equal, reaction rates and consumption of oxygen gas in oxidations using the invented catalytic compositions increase with increased concentrations of the catalytic composition in the oxidation reaction mixture. In batch and continuous slurry processes, the invented catalytic compositions preferably are used in

amounts such that concentrations of total catalyst metals and metalloids, based on weight of liquid medium or solvent used in oxidation are at least about 100 ppmw, and more preferably at least about 500 ppmw, up to about 10,000 ppmw, more preferably up to about 6,000 ppmw, and still more preferably up to about 3,000 ppmw. In continuous flow processes such as fixed, fluid and ebullated bed processes, weight hourly space velocities of substituted aromatic hydrocarbon feed per weight of catalyst composition can be determined by routine experimentation based on catalyst performance reported the in batch and semi-continuous oxidations guided by the Examples appearing herein.

Liquid phase reactions for oxidation of aromatic feed material to oxidized products comprising one or more carboxylic acid-substituted aromatic derivatives are conducted in a suitable oxidation reaction zone, which normally comprises one or more reaction vessels. Suitable reaction vessels are configured and constructed to withstand the high temperature and pressure conditions and generally acidic liquid phase reaction mixture present in the reaction zone and to provide for addition and mixing of catalyst, liquid and gaseous reactants and reaction media or solvent and removal of oxidized product or a liquid effluent comprising such product for recovery thereof. Oxidations according to the invention in some of its embodiments tend to be exothermic and, in such cases, heat of reaction can conveniently be controlled by evaporating a reaction off-gas from the liquid reaction mixture and removing the off-gas from the reaction zone. In such cases, the reaction vessel also should be configured for venting of off-gas. Reactor types which can be used include slurry reactors, continuous stirred tank reactors, bubble column reactors, tubular reactors, ebulating bed, fixed or packed bed and trickle bed reactors. Stirred tank reactors in the form of a columnar vessel, normally with a central axis which extends vertically when the vessel is positioned for use, having one or more mixing features for mixing reactants, including distributing gaseous reactants or reactant sources, if used, within the liquid phase boiling reaction mixture. Typically, the mixing feature comprises one or more impellers mounted on a rotatable or otherwise movable shaft. For example, impellers may extend from a rotatable central vertical shaft. Reactors may be constructed of materials designed to withstand the particular

temperatures, pressures and reaction compounds used. For use of the invented catalytic compositions in heterogeneous form, fixed, fluidized and ebullated bed reactors and slurry reactors are useful. Stainless or duplex steels are preferred materials of construction for oxidations conducted without sources of reactive bromine although more corrosion-resistant metals or alloys, such as titanium or high nickel steel alloys can be used if desired.

A reaction mixture for the liquid phase oxidation is formed by combining components comprising aromatic feed material, liquid reaction medium or solvent and the catalytic composition according to the invention or components thereof and adding a suitable oxygen source to the mixture. In continuous or semi-continuous processes, components can be combined in one or more mixing vessels before being introduced to the oxidation zone; however, the reaction mixture can also be formed in the oxidation zone. As noted above, in oxidations using water as liquid medium for the reaction mixture, water generated as by-product of the oxidation can serve as the liquid media such that addition thereof from external sources is eliminated or reduced.

Contacting aromatic feed material with oxygen in the presence of catalytic composition according to the invention is conducted under reaction conditions effective for conversion of substituted aromatic compounds having oxidizable alpha carbon atoms to oxidized product comprising aromatic carboxylic acid derivatives of the substituted aromatic feed materials. Preferred reaction conditions include temperatures and pressures effective for such conversion while maintaining a liquid phase reaction mixture. Temperatures of about 100 to about 300° are preferred. Preferred temperatures are about 140°C, and more preferably about 160°C, to about 230°C, and more preferably about 200°C. Pressure of the liquid phase reaction mixture can be used to control the temperature at which the liquid phase reaction mixture boils and is preferably selected to maintain a substantial liquid phase reaction mixture. Pressures of about 5 to about 40 kg/cm² gauge are preferred, with preferred pressures for particular processes varying with feed and solvent or liquid reaction media compositions, temperatures and other factors and more preferably ranging between about 10 to about 30 kg/cm². Residence times in the reaction vessel

can be varied as appropriate for given throughputs and conditions, with about 20 to about 150 minutes being generally suited to a range of processes. As will be appreciated by persons skilled in the manufacture of aromatic carboxylic acids, preferred conditions and operating parameters vary with different products and processes and can vary within or even beyond the ranges specified above.

Products obtained by oxidation of aromatic feed materials according to the invention include aromatic carboxylic acid derivatives of the aromatic feed material as well as less fully oxidized derivatives. By way of example, in the oxidation of para-xylene in aqueous acetic acid reaction solvent or water according to the invention, an oxidized product typically includes one or more para-xylene derivatives having at least one carboxylic acid substituent group having an alpha carbon atom, such as terephthalic acid, 4-carboxybenzaldehyde, p-toluic acid and p-hydroxymethylbenzoic acid, as well as one or more other oxidation products such as p-tolualdehyde, trimellitic acid, benzoic acid and 2, 4', 5-tricarboxybiphenyl. In embodiments of the invention in which a vapor phase is evaporated from the liquid reaction mixture for control of reaction temperature, major components of the vapor phase typically include water, which is generated as by-product of oxidation of the substituted aromatic feed material and may also be present as liquid medium for the reaction or a component thereof. The vapor phase will also include organic acid reaction solvent and oxidation by-products thereof if an organic acid solvent is used in the process. The vapor phase also typically contains lesser amounts of carbon monoxide and carbon dioxide, which can result from burning of aromatic feed material and, if present, organic acid reaction solvent. Aggregate carbon oxide (CO and CO₂) content of the vapor phase generally is less than about 0.5 mole carbon oxides per mole of oxygen consumed in oxidation and in embodiments using preferred catalyst compositions can be less than about 0.1 mole carbon oxides per mole of consumed oxygen. The vapor phase may also contain minor amounts of unreacted aromatic feed material and oxidation products thereof and unreacted oxygen from gaseous oxygen sources together with inert gas components that may be included in such sources. In preferred embodiments of the invention, aromatic feed material is converted to an oxidation product comprising one or

more aromatic carboxylic acid derivatives of the feed material without substantial generation of carbon oxides. More preferably, carbon oxide levels in vent gases from the oxidation, including carbon oxides from burned aromatic feedstock as well as burned organic acid reaction solvent if used, are less than about one mole per mole of substituted aromatic feed material and still more preferably less than about 0.5 or less than 0.25 mole of carbon monoxide plus carbon dioxide per mole of the substituted aromatic feed material.

Oxidized product resulting from the invented process commonly is formed dissolved or as suspended solids in the liquid phase reaction mixture. Recovery of oxidized product or components thereof can be accomplished by any suitable technique. Solid product can be recovered from the liquid reaction medium by filtration techniques. Oxidized products present in the reaction medium both in solution and as suspended solids can conveniently be recovered by crystallization techniques. Aromatic carboxylic acid derivatives of the feed material are preferably recovered in solid form by crystallization from the reaction medium, which can be accomplished conveniently by cooling and releasing pressure on the liquid reaction mixture in the reaction zone or after removal therefrom. Solid product slurried in the liquid and/or solids crystallized from reaction liquid or from crystallization solvents are conveniently separated from the liquids by centrifuging, filtration or combinations thereof. Solid products recovered from the reaction liquid by such techniques comprise aromatic carboxylic acid derivatives of the aromatic feed material and other components of the oxidation product. If needed or desired, further separation of product species can be conducted by any suitable technique, such as extraction with suitable solvents, distillation or sublimation.

In some of its embodiments, features of the invented catalytic compositions and process, such as high conversions and carboxylic acid-selectivities, low carbon oxide generation, and performance even using water as a liquid reaction medium or solvents with relatively high water contents and in the complete or substantial absence of bromine, are especially suited to oxidation of aromatic feed materials comprising at least one dialkyl benzene, intermediate oxidation product thereof or combination thereof to aromatic carboxylic acids in

high yields and at high selectivities to benzenedicarboxylic acids. Preferred processes according to such aspects of the invention comprise oxidation of aromatic feed materials comprising para-xylene or one or more intermediate oxidation products thereof or combinations thereof, to an oxidation product comprising terephthalic acid and oxidation of meta-xylene or one or more intermediate oxidation products thereof or combinations thereof to an oxidation products comprising isophthalic acid.

In such embodiments, the oxidation preferably comprises contacting the aromatic feed material with oxygen gas in a liquid phase reaction mixture which comprises water or water and acetic acid and has dissolved or slurried therein, or is otherwise contacted, such as in a fixed bed of supported or unsupported catalyst or catalyst component particles, with a catalytic composition according to the invention at elevated temperature and pressure effective to maintain a liquid phase reaction mixture and preferably at a temperature of at least about 150 to about 230°C. Catalytic compositions according to the invention that are preferred for such processes exhibit conversions to oxidized product of at least about 90 mole % with selectivities to benzenedicarboxylic acid derivatives of the aromatic feed material of at least about 90 %.

A particularly preferred catalytic composition according to the invention for such a process with good conversion and selectivity but low generation of carbon oxides from the aromatic feed material comprises at least one palladium component, optionally in combination with a vanadium or titanium component, and at least one Group 15 metal or metalloid component, and especially an antimony component, and optionally also including a Group 5 metal, a Group 6 metal or Group 14 metal or metalloid or a combination thereof. A specific example of such a preferred composition comprises at least one palladium component, at least one antimony component and at least one titanium component. Another example comprises at least one palladium component, at least one antimony component and at least one molybdenum component. Another example comprises at least one palladium component, at least one antimony component, at least one tin component and at least one molybdenum component. Particularly preferred homogeneous catalytic compositions are

those comprising components as described above in the form of a solution in water, acetic acid or aqueous acetic acid. Particularly preferred heterogeneous forms of the catalysts for such processes comprise at least a palladium component, and preferably one or more additional metal and/or metalloid components, and most preferably the palladium and other such components in solid form or deposited on a support. Conversion to oxidized aromatic derivatives of the feed material, selectivity to aromatic carboxylic acid derivatives and minimal loss of aromatic feed to carbon oxides are achieved using such catalysts in the absence of reactive bromine sources and accordingly the compositions and their components and the oxidation reaction mixture in which they are used are most preferably free of reactive bromine.

Oxidation products of the liquid phase reaction in processes according to this embodiment of the invention comprise terephthalic acid or isophthalic acid in good yield and with intermediate oxidation products and catalyst residues comprising palladium, platinum, vanadium or titanium and at least one Group 5, 6, 14 or 15 metal or metalloid present in sufficiently low levels that the oxidation product is useful for conversion to pure forms of terephthalic acid or isophthalic acid if not for conversion directly to polyester suitable for melt spinning into fiber. A preferred terephthalic acid composition according to the invention comprises terephthalic acid and, by weight thereof, about 0.1 to about 500 ppmw palladium, platinum, vanadium or titanium calculated as the element, and about 0.1 to about 500 ppmw Group 5, 6, 14 or 15 metal or metalloid, calculated as the element, or a combination thereof. A terephthalic acid composition according to a preferred embodiment of the invention comprises terephthalic acid and, by weight thereof, about 0.1 to about 100 ppmw palladium, platinum, vanadium or titanium calculated as the element, and about 0.1 to about 100 ppmw molybdenum, tin, antimony or bismuth, calculated as the element, or a combination thereof. In another embodiment, a terephthalic acid composition suitable for direct conversion by reaction with at least one glycol to polyester suitable for manufacture of fiber comprises terephthalic acid and, by weight of the terephthalic acid, about 0.01 to about 100 ppmw palladium, platinum, vanadium or titanium calculated as the element, and about 0.01 to about 100 ppmw Group

5, 6, 14 or 15 metal or metalloid, and especially molybdenum, tin, antimony or bismuth, calculated as the element, or a combination thereof.

Pure forms of aromatic carboxylic acids produced according to the invention can be obtained, if purification is desired, by subjecting the oxidation product, either before or after recovery from the liquid phase reaction mixture, to lower temperature oxidation in one or more stages, such as described in as known from U.S. 4,877,900, 4,772,748 and 4,286,101. Preferred pure forms of terephthalic acid or isophthalic acid with lower impurities contents, such as purified terephthalic acid or "PTA", can be made by catalytic hydrogenation of aqueous solutions of the oxidation product in the presence of a noble metal catalyst as described in US 3,584,039. A preferred terephthalic acid composition according to the invention that is suitable for direct conversion by reaction with at least one glycol to polyester suitable for manufacture of fiber comprises terephthalic acid and, by weight thereof, less than about 100 ppmw 4-carboxybenzaldehyde and about 0.01 to about 100 ppmw palladium, platinum, vanadium or titanium, calculated as the element, and about 0.01 to about 100 ppmw Group 5, 6, 14 or 15 metal or metalloid calculated as the element, or a combination thereof.

The invention is described further in the following examples which are presented for purposes of non-limiting illustration and explanation.

Examples 1 - 4

Weighed amounts of palladium(II) acetate, antimony(III) acetate and tin(II) acetate salts or stock solutions in various combinations were measured into a 10 mL Teflon reaction tube together with amounts of para-xylene, acetic acid and water (95 % acetic acid and 5 % water by weight of the combination thereof) providing a total liquid volume of 7.5 mL. A Teflon stir bar was inserted into the reaction tube and the reaction tube was placed into a thermostatted reactor block. The reactor block was closed, sealing the reaction tube. Headspace in the reaction tube was purged with nitrogen under pressure of 14 bars. The reactor block was used to heat the reaction tube to 170°C, after which air flow into the reaction tube at 1.8 L/min and mixing at 1000 rpm were begun. After 60

minutes, stirring and air flow were stopped and the reactor block and reaction tube were allowed to cool to room temperature. Contents of the reaction tube were removed and dissolved in dimethyl sulfoxide. Samples were analyzed for major product intermediates and impurities by high pressure liquid chromatography (HPLC).

Conditions and results of the oxidations are reported in TABLE 1. Amounts of metals and metalloids used in the oxidations are expressed in parts per million by weight of the acetic acid and water used in the oxidations. Para-xylene ("PX") conversions reported in the table are expressed as moles of converted para-xylene per mole of para-xylene starting material reduced by para-xylene contents of condensed overhead vapors from the oxidations, which typically ranged up to 5% of the initial charge. Selectivities shown in the table are percentages, by weight, of terephthalic acid ("TA"), 4-carboxybenzaldehyde ("4CBA") and p-toluic acid ("PTOL"), respectively, of the converted products weight.

TABLE 1

Run No.	Example 1	Example 2	Control 1	Example 3	Example 4
Composition	Pd / Sb	Pd / Sn	Sb / Sn	Pd/Sb/Sn	Pd/Sb/Sn
Pd (ppmw)	504.7	510.9	-----	483.0	510.6
Sb (ppmw)	513.2	-----	485.5	503.7	494.5
Sn (ppmw)	-----	503.6	496.5	493.9	489.2
Temperature (°C)	167	169	168	168	147
PX Conversion (mole %)	8.20	10.88	0.04	94.67	78.98

Selectivity (% converted product)					
TA	0.00	6.13	0.00	2.70	4.04
4CBA	0.47	6.24	0.00	3.67	4.25
PTOL	76.75	65.60	0.00	77.58	72.04

As seen from the table, conversions of para-xylene to carboxylic acid derivatives using binary combinations of palladium with tin or antimony without bromine in Examples 1 and 2 were far greater than that with tin and antimony in Control 1. Conversions in Examples 1 and 2 were also significantly greater than those in trials using each of palladium, antimony and tin alone in Controls 11-13 reported below. Surprisingly, the catalytic compositions used in Examples 4 and 5, which contained palladium, antimony and tin, showed still greater conversion of the para-xylene feed to carboxylic acid derivatives, including nearly quantitative conversion in Example 3, in combination with low levels of carbon oxides.

Example 5

Weighed amounts of palladium(II) acetate, antimony(III) acetate and tin(II) acetate were added to a solvent composed of 95 wt.% acetic acid and 5 wt.% water and the resulting mixture was batch loaded into a stirred 100 mL titanium reactor. The reactor was sealed, pressurized to 22 bara with compressed nitrogen and heated to about 190-195°C and, while maintaining those conditions, a gaseous mixture of 8 vol.% oxygen with nitrogen was added continuously at a rate of 1.0 gram/minute and greater than 99 wt% pure para-xylene was added continuously at a rate of 0.133 gram/minute. After one hour, addition of para-xylene feed was stopped. Addition of the gaseous mixture was continued for an additional thirty minutes and then stopped. Vent gas removed from the reactor was sampled at intervals beginning after thirty minutes of para-xylene addition. The reactor contents were then cooled and a sample of product slurry resulting from the reaction was removed and analyzed by HPLC. TABLE 2 reports metals

concentrations, yields of products determined by HPLC and carbon oxide production calculated from vent gas samples.

TABLE 2

<u>Catalyst Metals or Metalloids</u>	<u>Concentration (ppmw)</u>
Palladium	8000
Antimony	7999
Tin	5337
<u>Products</u>	<u>Yield (mole/mole para-xylene fed X 100%)</u>
TA	50.3
4CBA	6.4
PTOL	6.2
p-Tolualdehyde ("PTAL")	7.2
Carbon Oxides	19

5 From Example 5 and TABLE 2 it is evident that the palladium-antimony-tin composition of the example was active in the absence of bromine for conversion of para-xylene to derivatives with oxidized substituent groups at a yield of about 70 mole % based on moles of para-xylene feed. Selectivity to carboxyl-substituted derivatives of the p-xylene feed was high, as seen not only from the 62.9 % combined yields of TA, 4CBA and PTOL, each of which includes at least one carboxyl-substituent, but also from the 50.3 % yield of TA. The 50.3 % TA yield based on para-xylene feed corresponds to about 72% based on moles of para-xylene feed converted to oxidized alkyl aromatic derivatives. TA selectivity of the catalytic composition of Example 5 at the reaction temperature of the example was unexpected. Also as seen from the example and the table, good oxidized alkyl aromatic yield and carboxyl selectivity with the palladium-antimony-

10

15

tin catalyst were achieved with carbon oxides generated in an amount corresponding to only 19 % of the molar amount of p-xylene added.

Controls 2 - 10

5 For purposes of comparison a bromine-promoted cobalt-manganese catalyst representative of catalysts used in commercial manufacture of terephthalic acid by oxidation of para-xylene was tested in Control 2. Bromine-free catalysts containing various amounts of cobalt and zirconium as in US Patent Application No. 2002/0188155 were used in Controls 3 - 10.

10 For Control 2, cobalt(II) acetate tetrahydrate, manganese(II) acetate tetrahydrate and a solution of 48 wt% hydrobromic acid in water were added to a solvent containing 95 wt% acetic acid and 5 wt% water in amounts providing 615 parts per million by weight ("ppmw") cobalt, 616 ppmw manganese and 1120 ppmw bromine. The solution was loaded into a stirred 100 mL titanium reactor. The reactor was sealed, pressurized to 22 bara with compressed nitrogen and
15 heated to maintain a constant reactor temperature of 190°C and, while maintaining those conditions, a gaseous mixture of 8 vol.% oxygen and 92 vol% nitrogen was added continuously at a rate of 2.0 grams/minute and para-xylene (>99% pure) was added continuously at a rate of 0.133 gram/minute. After one hour, addition of para-xylene feed was stopped. Addition of the gaseous mixture
20 was continued for an additional thirty minutes and then stopped. The reactor contents were then cooled and a sample of the total reactor product slurry was removed and analyzed by HPLC. Production of carbon oxides during the reaction was calculated based on concentrations in gas samples removed from the reactor during the last 30 minutes of para-xylene addition.

25 For controls 3 - 10, cobalt(II) acetate tetrahydrate and a solution of 16.2 wt% zirconyl(IV) acetate in water were added to an acetic acid and water solvent as in Control 2 in amounts providing varying levels of cobalt and zirconium. The resulting catalysts were loaded into a reactor as used in Control 2 and, while maintaining the reactor at a constant temperature of 195°C and pressure of 22
30 bara, a nitrogen and oxygen mixture and para-xylene feed, both as in Control 2 , were added continuously over a period of one hour at rates of 2.0 g/min. of the

5 gas mixture and 0.133 g/min. of the para-xylene. Addition of para-xylene feed was discontinued after one hour and addition of the oxygen and nitrogen gas mixture was discontinued after another one-half hour. Reactor contents were then cooled and total product was analyzed as in Control 2. Carbon oxide production was calculated from vent gas samples taken during the last 30 minutes of p-xylene addition.

Results of the oxidations with Controls 2 - 10 are reported in TABLE 3, in which numbers of the Controls are shown in the "#" column.

TABLE 3

#	Catalyst Metals and Br Proportions (ppmw)	Yields (mole / mole p-xylene fed x 100%)				
		TA	4CBA	PTOL	PTAL	COx
2	Co / Mn / Br 615 / 615 / 1120	98.1	0.4	0.4	0.2	35
3	Co / Zr 500 / 50	9.2	4.9	49.5	3.9	131
4	Co / Zr 5000 / 4975	4.9	2.1	39.2	7.8	189
5	Co / Zr 500 / 4975	6.8	2.1	45.6	4.3	119
6	Co / Zr 5000 / 4975	5.6	2.1	39.0	6.1	193
7	Co / Zr 5000 / 50	4.9	1.9	36.9	4.8	172
8	Co / Zr 500 / 50	9.9	2.0	48.0	3.0	103
9	Co / Zr 500 / 498	9.7	2.4	48.6	3.8	146

10	Co / Zr 5000 / 498	5.3	2.1	37.8	7.8	204
----	-----------------------	-----	-----	------	-----	-----

From TABLE 3, it can be seen that the conventional, bromine-promoted cobalt and manganese catalyst of Control 2 was highly selective to TA with only minor production of less fully oxidized intermediates. PTOL, which is an intermediate oxidation product in oxidation of para-xylene to terephthalic acid, was the primary oxidation product produced in the bromine-free cobalt-zirconium catalyzed trials in Controls 3 - 10. It also can be seen that carbon oxide generation with the cobalt-zirconium-catalyzed controls was very high.

Controls 11 - 15

Weighed amounts of each of palladium(II) acetate, antimony(III) acetate and tin(II) acetate, bismuth (III) acetate and molybdenum(II) dimer were added to a solvent composed of 95 wt.% acetic acid and 5 wt.% water and the resulting mixtures were batch loaded individually and in various combinations into a stirred, vented 300 mL titanium reactor. The reactor was sealed, pressurized to 390 psig with nitrogen and agitation was begun. The reactor contents were heated to 182°C, after which the nitrogen flow was replaced by a mixture of 8 vol. % oxygen in nitrogen flowing at 15 standard cubic feet per hour ("SCFH"), and para-xylene feedstock and supplemental solvent were added. The feedstock and supplemental solvent were added for 60 minutes at 0.567 mL/min and 0.633 mL/min, respectively. Thirty seconds after the reactor contents had reached 182°C, the temperature set-point was increased to 194°C and after another 20 minutes the set-point temperature was increased to 195°C. After 60 minutes, feedstock and solvent additions were terminated. For 30 minutes thereafter the 8% oxygen in nitrogen gas mixture was added at 15 SCFH. At the end of the 30 minutes, the flow of 8% oxygen in nitrogen was replaced by a flow of only nitrogen gas. The vent gas from the reactor was monitored continuously by a bank of on-line analyzers for carbon monoxide, carbon dioxide, and oxygen throughout span of the oxidation. The heating mantel was then removed and the reactor was cooled, depressurized, and unsealed. A representative sample of the reactor effluent was removed for analysis by HPLC. Results of the oxidations

are reported in TABLE 4. Conversions reported in the table are expressed as moles of converted para-xylene per mole of para-xylene starting material. Selectivities shown in the table are percentages, by weight, of terephthalic acid ("TA"), 4-carboxybenzaldehyde ("4CBA"), p-toluic acid ("PTOL") and p-tolualdehyde ("PTAL") respectively, of the converted products weight. Acid Selectivity reported in the Table is the sum of TA, 4CBA and PTOL selectivities. Carbon oxides production was calculated from vent gas samples.

TABLE 4

Control #	11	12	13	14	15
Metal	Pd	Sb	Sn	Bi	Mo
Conc (ppmw)	4000	4570	4460	3600	7845
<u>Selectivity (%)</u>					
TA	2.06	8.69	3.21	6.03	4.03
4-CBA	3.92	1.75	2.54	2.00	2.15
PTOL	5.04	20.90	48.32	40.14	29.88
PTAL	52.27	67.42	44.61	50.08	61.95
Burned pX (%)	6.7	1.23	1.33	1.75	1.99
pX Conversion (%)	4.67	1.18	2.09	1.05	2.10
Acid Selectivity (%)	11.02	31.34	54.07	48.17	36.16
COx (moles)	0.015	0.001	0.001	0.001	0.002
O ₂ Consumed (moles)	0.129	0.083	0.0098	0.089	0.100
COx/pX (mol/mol)	0.056	0.002	0.005	0.003	0.007
COx/O ₂ * 100	11.61	0.792	1.280	0.938	1.902

10

Comparing TABLES 3 and 4, it is evident that none of the metals of Controls 11 - 15 approached the performance of the bromine-promoted cobalt and manganese catalyst of Control 1. Conversion of para-xylene in these trials was

greatest with palladium in Control 11 but less than half that in Examples 1 and 2 with combinations of palladium and antimony and palladium and tin, respectively, and far below that in Examples 3-5 using palladium antimony and tin. Among Controls 11 - 15, only antimony and bismuth, in Controls 12 and 14, showed comparable selectivity to TA as the cobalt-zirconium compositions of Controls 3 - 10. However, as seen in TABLE 4, conversions in Controls 12 and 14 were only about 1%.

Examples 6 - 9 and Controls 16 - 17

Combinations of salt solutions used in Controls 11 - 15 were used in para-xylene oxidations and reactor liquid product and vent gas samples were analyzed following the procedures of Controls 11-15. Results are reported in TABLE 3.

TABLE 5

Run	Example 6	Control 16	Example 7	Example 8	Example 9	Control 17
Catalyst	Pd/Sn	Sb/Sn	Pd/Sb	Pd/Bi	Pd/Mo	Sb/Mo
Conc (ppmw)	4000/ 2000	2000/ 2000	4000/ 2000	4000/ 3400	4000/ 5000	2000/ 2000
<u>Products Sel (%)</u>						
TA	4.51	66.80	12.90	5.64	10.60	23.83
4-CBA	3.05	2.25	19.07	1.28	4.82	3.37
PTOL	32.68	14.87	42.23	28.97	37.97	24.60
PTAL	45.41	16.08	25.33	61.87	30.16	40.98
Burned pX	14.35	<0.001	0.47	2.23	16.46	7.23
% pX Conversion	6.49	3.08	19.92	9.13	6.29	0.53
Acid Selectivity (%)	40.24	83.92	74.20	35.89	53.39	51.80
CO _x (moles)	0.049	<0.001	0.010	0.009	0.055	0.002
O ₂ Consumed	0.189	0.081	0.477	0.128	0.215	0.085

(moles)						
CO _x /pX (mol/mol)	0.180	<0.001	0.036	0.035	0.205	0.007
CO _x /O ₂ * 100	25.599	0.001	2.271	7.057	25.617	2.145

As with Examples 1 and 2, improved conversions in oxidations with the binary metal or metal and metalloid combinations in Examples 6 - 9 over results with the individual metals or metalloids in Controls 11 - 15 can be seen from TABLE 5 and comparison thereof with TABLE 4. Although metals concentration in Control 16, using a combination of antimony and tin, was about 4 times that in Control 1, also using antimony and tin, conversion was still low.

Controls 18 - 21 and Examples 10 - 12

Oxidations were conducted as in Controls 11-15 using weighed amounts of platinum(II) acetate, vanadium(III) acetylacetonate and titanium(IV) oxide acetylacetonate in aqueous 95 wt.% acetic acid. Results appear in TABLE 6.

TABLE 6

Control No.	Control 18	Control 19	Control 20
Metal	Pt	V	Ti
Conc (ppmw)	7327	2000	2000
<u>Selectivity (%)</u>			
TA	7.11	8.82	3.28
4-CBA	0.48	0.54	0.31
PTOL	20.90	18.20	24.30
PTAL	43.73	54.04	56.54
Acid Selectivity (%)	28.49	27.56	27.89
Burned pX (%)	27.77	18.40	15.57
pX Conversion (%)	4.09	4.12	3.67
CO _x (moles)			
O ₂ Consumed	0.072	0.043	0.031

(moles)	0.187	0.164	0.131
COx/pX (mol/mol)	0.261	0.153	0.112
COx/O ₂ * 100	38.57	25.91	23.84

Oxidations were conducted by the same procedures using combinations of the platinum, vanadium and titanium metal solutions. Results are reported in TABLE 7.

TABLE 7

Run	Control 21	Example 10	Example 11	Example 12
Metals	Pt / Ti	V / Ti	Pt / V	Pt / V / Ti
Conc (ppmw)	7327/2000	2000/2000	7327/2000	7327/2000/2000
<u>Selectivity (%)</u>				
TA	1.59	23.30	5.14	6.17
4-CBA	0.08	0.57	0.98	1.35
PTOL	9.91	13.42	31.95	34.86
PTAL	1.93	46.17	12.10	16.36
<u>Acid Selectivity (%)</u>	12.48	37.29	38.07	42.38
pX Conversion (%)	2.87	7.56	4.67	8.09
Burned pX (%)	86.49	16.54	49.82	41.25
COx (moles)	0.846	0.069	0.212	0.260
O ₂ Consumed (moles)	1.071	0.210	0.384	0.459
COx/pX (mol/mol)	3.055	0.247	0.766	0.939
COx/O ₂ * 100	79.01	32.69	55.24	56.65

5 As seen from TABLES 6 and 7, oxidations with combinations of vanadium and titanium in Example 10, platinum and vanadium in Example 11 and platinum, titanium and vanadium in Example 12 resulted in higher conversions than when the individual metals were used in Controls 18 - 20. Conversion in Control 21 using platinum and titanium but lacking a Group 5, 6, 14 or 15 metal or metalloid

was less than in Controls 18 and 20 in which platinum and titanium were used individually.

Examples 13 - 20

5 In these examples palladium-antimony-tin compositions according to the invention were used for semi-continuous oxidations of various feed materials using a 300 mL titanium Parr reactor outfitted with a Magnadrive impeller agitator, reflux condensers, a back pressure regulator, a mass flow controller, on-line vent gas analyzers (CO, O₂, and CO₂), one pump for adding liquid feedstock and another pump for adding supplemental solvent.

10 The reactor bottom was preloaded with weighed amounts of palladium(II) acetate (1.208 g), antimony(III) acetate (1.407 g), and tin(II) acetate (1.143 g), and 95% aqueous acetic acid (72.6 g). The reactor was sealed, pressurized to 390 psig with nitrogen and agitation was begun. The reactor contents were heated to 182°C. At initiation, the nitrogen flow was replaced by a mixture of 8% oxygen in nitrogen flowing at 15 standard cubic feet per hour ("SCFH"), and the feedstock and supplemental solvent were added. The feedstock and the aqueous, 95 wt% acetic acid as supplemental solvent were added for 60 minutes at 0.567 mL/min and 0.633 mL/min, respectively. Thirty seconds after initiation, the temperature set-point was increased to 194°C. Twenty minutes after initiation, the set-point temperature was increased again to 195°C. After 60 minutes, feedstock and solvent additions were terminated and, in each of Examples 13 - 15, a 30 minute tailout period was begun. During that period, the 8% oxygen in nitrogen gas mixture was added at 15 SCFH. At the end of the tailout period, the flow of 8% oxygen in nitrogen was replaced by a flow of only nitrogen gas. Example 16 was carried out as in Examples 13 - 15 except the tailout step was omitted. In all examples, the reactor was sequentially removed from the heat source, cooled, depressurized, and unsealed. Representative samples of the total reactor product slurries were collected and analyzed by HPLC and Karl Fisher (water) analyses.

Results of semi-continuous oxidations using para-xylene feed in Examples 13 - 16 are reported in TABLE 8.

TABLE 8

Example:	13	14	15	Ave. 13-15	16
Feed:	Para-Xylene (PX)				
<u>Products Sel (%)</u>					
TA	80.37	83.25	81.48	81.70	78.57
4CBA	11.04	9.21	10.65	10.30	14.24
PTOL	4.14	3.48	3.63	3.75	4.16
PTAL	0.83	0.71	0.76	0.77	3.01
Burned pX	3.63	3.35	3.48	3.49	0.02
pX Conversion (mol%)	50.78	57.78	54.98	54.52	28.07
Trimellitic Acid (TMLA) (wt%)	0.2045	0.2070	0.2228	0.2114	0.0066
Benzoic Acid (BA) (wt%)	0.1816	0.1890	0.1972	0.1893	0.1321
2,4',5-tricarb-oxybiphenyl (wt%)	0.051	0.048	0.058	0.052	0.410
Main Oxidation COx ^a (mol)	0.085	0.092	0.091	0.089	0.088
Tailout COx ^b (mol)	0.196	0.198	0.189	0.195	---
COx/Feedstock (mol/mol) ^a	0.317	0.332	0.329	0.326	0.318
COx/O ₂ (mol*100/mol) ^a	10.18	10.84	10.87	10.63	10.61

^a Data collected only over the first 60 minute period of the oxidation.

^b Data collected during the tailout period.

The oxidations in Examples 13 - 15 produced TA in an average selectivity of almost 82 %. The average total selectivities of less fully oxidized carboxylic acid derivatives (4CBA + PTOL) in the oxidations using para-xylene feed was 14.05 mole%. Results of semi-continuous oxidations using alternate feed materials in Examples 16 - 19 are reported in TABLE 9.

TABLE 9

Example:	16	17	18	19
Feed:	p-Tolualdehyde		p-Methylacetophenone	
<u>Product Sel. (%)</u>				
TA	32.72	34.50	11.64	11.69
4CBA	7.43	7.70	2.65	1.97
PTOL	54.38	52.49	43.66	46.07
PTAL	2.57	2.54	1.32	0.65
Feedstock Converted (mol%)	63.74	67.65	13.03	12.80
Burned Feed (mol%)	2.90	2.77	40.74	39.60
TMLA (wt%)	0.0708	0.0638	0.1427	0.1562
BA (wt%)	0.1926	0.2041	0.0305	0.0884
2,4',5-tricarboxybiphenyl (wt%)	0.1898	0.1544	0.4375	0.2474
Main Oxidation COx (mol%) ^a	0.091	0.090	0.367	0.345
Tailout Oxidation COx ^b	0.058	0.055	0.206	0.198
COx/Feedstock (mol/mol) ^a	0.317	0.321	0.639	1.396
COx/O ₂ (mol*100/mol) ^a	21.135	20.696	57.479	53.900

^a Data collected only over the first 60 minute period of the oxidation.

^b Data collected during the tailout period.

TABLE 9 displays oxidation results using liquid feedstocks, p-tolualdehyde and p-methylacetophenone. The duplicate p-tolualdehyde oxidations in Examples 16 and 17 generated very similar results, demonstrating good reproducibility of the oxidations. The p-tolualdehyde feed was converted to TA, although at lower efficiency and with greater levels of partial carboxylic acid derivatives as compared to the para-xylene feed in Examples 13 - 15. However, the total COx generated was much lower than in the para-xylene oxidations. The p-methylacetophenone oxidations in Examples 18 and 19 had similar results, including low TA yields. The total COx generated in those examples was higher than the amount made in the p-tolualdehyde oxidations, consistent with a higher activity of the catalyst for oxidation of the p-methylacetophenone feed material to carbon oxides than the p-tolualdehyde and p-xylene feeds.

Examples 20 - 23

In these examples palladium-antimony-tin compositions according to the invention were used in batch oxidations of various feed materials in solid form at ambient temperature using the 300 mL reactor used in Examples 13 - 20. Batch oxidations were conducted by loading the reactor with palladium(II) acetate (1.208 g), antimony(III) acetate (1.407 g), and tin(II) acetate (1.143 g), weighed amounts of solid feed materials and 95% aqueous acetic acid (114.5 g). In Examples 20 and 21, the feed was 42.4 g *p*-toluic acid and in Examples 22 and 23 the feed was 41.7 g terephthaldehyde. The reactor was sealed, pressurized to 390 psig by addition of nitrogen gas and agitation was started. The reactor contents were heated to 182°C and the nitrogen flow was replaced by flow of a mixture of oxygen and nitrogen containing 8% oxygen at 15 SCFH. Thirty seconds after initiation, the temperature set-point was increased to 194°C. Twenty minutes after initiation, the temperature set-point was increased to 195°C. After 90 minutes, the 8% oxygen in nitrogen flow was replaced by a flow of only nitrogen. The reactor was removed from the heat source, cooled, depressurized, and unsealed. Representative samples of the total reactor product slurries from each run were collected and analyzed by HPLC and Karl Fisher analyses. Results are reported in TABLE 10.

TABLE 10

Example:	20	21	22	23
Feed:	<i>p</i> -Toluic Acid		Terephthaldehyde	
<u>Product Sel (%)</u>				
TA	11.60	0.27	55.72	58.07
4CBA	6.73	0.62	32.54	29.92
PTOL	81.26	99.06	----	----
Burned Feedstock (mol%)	0.41	0.05	11.69	11.92
Feedstock Converted (mol%)	46.10	<1.00	50.88	51.24
TMLA (wt%)	0.0236	0.0000	0.4905	0.4891
BA (wt%)	0.2224	0.0484	2.1662	2.0064

2,4',5-tricarboxybiphenyl (wt%)	0.0478	0.0043	1.2386	0.9192
Total Oxidation COx (mol)	0.056	0.002	0.291	0.301
COx/Feedstock (mol/mol)	0.211	0.009	1.116	1.149
COx/O ₂ (mol*100/mol)	24.878	2.826	52.270	52.361

Inconsistent results in Examples 20 and 21 appear to have resulted from the presence of a contaminant(s) carried over from a previous oxidation experiment. When the *p*-toluic acid feed was oxidized a second time as in Example 21, there was very little measured activity. Therefore, Example 21 is believed to represent the more accurate results of *p*-toluic acid oxidation. Examples 22 and 23 produced reproducible results in oxidation of a terephthaldehyde feed. TA product selectivity averaged about 57 % with 4-CBA as the only intermediate carboxylic acid derivative at about 31 %. Total COx generated in these examples was high.

Examples 24 - 25

A palladium, antimony, tin composition according to the invention was used for semi-continuous oxidations according to the procedure of Examples 13 - 15 except that meta-xylene was used as feed material. Results are reported in TABLE 11. The averages of the results of Examples 13, 14 and 15 as reported in TABLE 8 are also repeated in TABLE 11 for comparison of results with the meta- and para-xylene feeds.

TABLE 11

Example:	24	25	Ave. 13 - 15	
Feed:	Meta-Xylene (MX)		Para-Xylene (PX)	
<u>Product Sel (%)</u>			<u>Products Sel (%)</u>	
Isophthalic Acid (IA)	56.45	55.26	TA	81.70
3CBA	11.44	11.56	4-CBA	10.30
MTOL	26.36	27.22	PTOL	3.75
MTAL	2.35	2.67	PTAL	0.77
Burned MX (mol%)	3.39	3.29	Burned PX (mol%)	3.49
MX Conversion	56.77	56.40	PX Conversion	54.52

(mol%)			(mol%)	
TMLA (wt%)	0.2837	0.4905	TMLA (wt%)	0.2114
BA (wt%)	0.5662	0.5618	BA (wt%)	0.1893
2,3',4-tricarboxy-biphenyl (wt%)	0.0142	0.0130	2,4',5-tricarboxy-biphenyl (wt%)	0.410
Main Oxidation COx ^a	0.089	0.086	Main Oxidation COx ^a	0.089
Tailout COx ^b	0.231	0.226	Tailout COx ^b	0.195
COx/MX (mol/mol) ^a	0.331	0.319	COx/PX (mol/mol) ^a	0.326
COx/O ₂ (mol*100/mol) ^a	11.44	11.09	COx/O ₂ (mol*100/mol) ^a	10.63

^a Data collected over the first 60 minute period of the oxidation.

^b Data collected in the tailout period.

5 The meta-xylene oxidations of Examples 24 and 25 again demonstrated good reproducibility. There was a lower yield of IA than there was of TA in the para-xylene oxidations of Examples 13 - 15. The lower IA yields were also consistent with the lower conversions of meta-xylene oxidation intermediates such as m-toluic acid. Overall, meta-xylene oxidations in Examples 24 and 25 produced slightly more COx than the para-xylene oxidations of Examples 13 - 15.

Examples 26 - 29

10 Batch oxidations of PX feed were conducted as in Examples 20 - 23 except that batch initiation temperatures were varied. Pressure was fixed at 390 psig. Results are reported in TABLE 12 with the average of the results from the semi-continuous oxidations in Examples 13 - 15 also reproduced for reference.

TABLE 12

Example	26	27	28	29	Ave. 13 - 15
Initiation Temperature (°C)	100	120	140	182	182
<u>Product Sel (%)</u>					
TA	14.56	6.08	6.70	32.16	81.70
4-CBA	7.74	5.80	10.47	24.08	10.30

PTOL	51.37	55.53	68.27	29.84	3.75
PTAL	26.33	30.12	13.11	8.33	0.77
PX Burned	0.00	2.46	1.45	5.59	3.49
TMLA (wt%)	<0.0001	<0.0001	0.0021	0.0911	0.2114
BA (wt%)	<0.0001	<0.0001	0.0414	0.3896	0.1893
2,4',5- Tricarboxybiphenyl (wt%)	0.0339	0.0702	0.2181	0.7432	0.052
Main Oxidation COx (mol) ^a	0.001	0.004	0.021	0.092	0.089
Tailout Oxidation COx (mol) ^b	---	---	---	---	0.195
COx/Feedstock (mol/mol) ^a	0.005	0.013	0.074	0.329	0.326
COx/O ₂ (mol*100/mol) ^a	3.08	5.28	4.451	13.11	10.63

^a Data collected during the first 60 minute period of oxidation.

^b Data collected during the tailout period.

^c Batch oxidation time was limited to 55 minutes.

5 Oxidation activities were low until a temperature of 140°C was employed in Example 28. Unexpectedly, at 140°C there was very little burning of solvent to carbon oxides for the degree of PX conversion that was achieved. When the oxidation was repeated, but at a temperature of 182°C in Example 29, TA yield nearly doubled. At the higher temperature in Example 29, however, total carbon oxides formation was higher.

10 Controls 22 - 23

15 Semi-continuous oxidations without tailouts were conducted as in Example 16 but with addition of 48 wt% aqueous hydrobromic acid, which is a common bromine source used as a promoter in commercial manufacture of terephthalic acid by oxidation of para-xylene using cobalt-manganese catalysts. Results are reported in TABLE 13. Results from Example 16 are included for reference.

TABLE 13

Run:	Example 16	Control 22	Control 23
HBr (g 48 wt % aqueous)	0.000	0.0777	0.1540
<u>Product Sel (%)</u>			
TA	78.57	8.66	2.36
4CBA	14.24	3.74	0.26
PTOL	4.16	77.09	62.28
PTAL	3.01	9.28	34.54
Burned pX (mol%)	0.02	1.24	0.56
PX Conversion (mol%)	28.07	39.40	7.25
TMLA (wt%)	0.0066	0.0050	<0.0001
Benzoic Acid (BA) (wt%)	0.1321	0.1083	<0.0001
2,4',5-Tricarboxybiphenyl (wt%)	0.4103	0.1409	<0.0018
Total Oxidation COx (mol)	0.088	0.023	0.002
COx/Feedstock (mol/mol)	0.318	0.082	0.007
COx/O ₂ (mol*100/mol)	10.61	5.176	1.517

In contrast to Example 16 in which no bromine was added, under otherwise identical conditions the oxidations in Controls 22 and 23 were impeded by the presence of the aqueous hydrogen bromide. The TA product selectivity fell by an order of magnitude and the main product was PTOL in Control 22. In Control 23, in which the bromine concentration was double the amount used in Control 22, only a trace of TA was made.

Examples 30 - 33

A catalyst composition of palladium, tin, antimony and molybdenum was used in a series of semi-continuous para-xylene oxidations conducted substantially as in Examples 6 - 9 except that in Examples 48 - 50 the reaction temperatures ranged from 193 to 199°C. Catalyst compositions were prepared by charging weighed amounts of palladium(II) acetate, antimony(III) acetate, tin(II) acetate, molybdenum(II) acetate dimer and 95% aqueous acetic acid to the

reactor in amounts providing 4000 ppmw palladium, 2000 ppmw antimony, 2000 ppmw tin and 5000 ppmw molybdenum, calculated as metals and based on weight of aqueous acetic acid. Contents of the reactor were removed after each oxidation run and were analyzed as in Examples 6 - 9 to assess products and selectivities. Results of Examples 48 - 50, together with selectivities averaged over the three experiments, are reported in Table 14. Reactor contents from each run also included darkly colored solid particles.

Table 14

Example	30	31	32	Ave. Ex. 30 - 32
<u>Products Sel (%)</u>				
TA	95.52	94.93	95.06	95.17
4CBA	2.60	3.07	3.08	2.92
PTOL	0.52	0.63	0.58	0.58
PTAL	0.29	0.38	0.37	0.35
Burned Feed (mol%)	1.07	0.99	0.91	0.99
PX Conversion (mol%)	92.34	85.03	85.67	87.68
BA	0.0034	0.0038	0.0030	0.0034
2,4,'5-tricarboxybiphenyl	0.0100	0.0109	0.0074	0.0094
TMLA	0.1727	0.1660	0.1634	0.1674
COx (moles)	0.043	0.039	0.036	0.039
O ₂ Consumed (moles)	0.930	0.893	0.891	0.905
COx/pX (mol/mol)	0.166	0.140	0.130	0.145
COx/O ₂ * 100 (mol/mol)	4.671	4.353	4.037	4.354

As seen from these examples and the table, terephthalic acid selectivity of the palladium, tin, antimony and molybdenum containing catalytic composition was exceptionally high and results of the three runs were highly reproducible.

In Example 33, the procedure of Examples 30 - 32 was followed except that the temperature was increased to 203-209°C. The oxidation proceeded vigorously with even greater selectivity to terephthalic acid (97%) than in Examples 30 - 32, 1.2% 4CBA and 0.1% each of PTOL and PTAL. Feedstock

burning and generation of carbon oxides at the higher temperature were about 1.5 - 2 times the average of Examples 30 - 32

Examples 34 - 37

5 A series of oxidations experiments was conducted substantially as in Examples 30 - 32 except that concentrations of palladium, antimony, tin and molybdenum salts charged to the reactor were varied and the 95 wt% aqueous acetic acid solution charged to the reactor with the catalyst metal salts and as supplemental solvent was diluted or replaced with water. Water contents in weight percent based on total solvent charged and results of analyses of the reactor contents in each of these experiments, including metals concentrations in the supernatant liquid from each run determined by inductive coupled plasma analyses ("ICP") are reported in Table 15.

TABLE 15

Example	Ave. Ex. 30-32	34	35	36	37
Water Conc (wt%)	5	10	20	40	100
<u>Product Sel (%)</u>	95.17	95.08	95.04	94.93	6.43
TA	2.92	2.58	2.12	2.70	13.88
4CBA	0.58	0.57	0.92	0.57	40.74
PTOL	0.35	0.23	0.02	0.08	36.53
PTAL	0.99	1.53	1.90	1.72	2.42
Burned pX	87.68	90.85	81.52	98.20	8.73
pX Conversion (mol%)					
BA (wt%)	0.0034	0.0022	0.0023	0.0025	0.0012
2,4,5-tricarboxybiphenyl (wt%)	0.0094	0.0059	0.0051	0.0052	0.3204
TMLA (wt%)	0.1674	0.1998	0.2271	0.2199	0.0045
COx (moles)	0.039	0.175	0.203	0.222	0.013
O ₂ Consumed (moles)	0.905	1.103	1.104	1.036	0.349

COx/pX (mol/mol)	0.145	0.649	0.753	0.827	0.047
COx/O ₂ * 100 (mol/mol)	4.354	15.835	18.370	21.467	3.718
<u>Supernatant Metals</u>					
Palladium (ppmw)		1138	1166	1710	141
Antimony (ppmw)		725	774	1441	1157
Tin (ppmw)		567	676	1300	1110
Molybdenum (ppmw)		1090	1102	2640	2793

These examples and the table illustrate effectiveness of the catalyst composition in oxidations with increasing water contents from 5 to 100 wt%. Of course, at 100%, the solvent is only water. In oxidations using bromine-promoted cobalt - manganese catalyst compositions conventionally used in commercial manufacture of terephthalic acid, and also those using bromine free catalysts as in US Patent Application No. 2002/0188155, even small increases in water content of the liquid phase reaction mixtures can adversely affect both conversions and selectivity to desired terephthalic acid products. Surprisingly, however, Examples 34 - 36 and Table 15 illustrate that oxidations progressed actively, and with high selectivities to terephthalic acid, at water contents as high as 40 wt%. It also was surprising that selectivities to intermediate oxidation products such as 4CBA, PTAL and PTOL decreased slightly with increases in water concentration to 40 wt%. The decreases in selectivities for these intermediates are indicative of higher catalyst activity in the conversion of the intermediates to terephthalic acid. At 100 wt% water as liquid medium for the oxidation in Example 37, conversion was lower than expected due to ineffective mixing of para-xylene and water in the apparatus used, but even with that difficulty, selectivity to carboxylic acid derivatives of the para-xylene feed was greater than 50% and selectivity to terephthalic acid was 6%. Oxidations in water with significantly higher conversions to oxidized para-xylene derivatives and selectivities to terephthalic acid are illustrated in the Examples 38 - 41 below.

Examples 38 - 41

Semi-continuous para-xylene oxidations were conducted in water using supported and unsupported catalysts in 300 mL titanium Parr reactors linked to

two liquid feed systems and outfitted with a Magnadrive stirrer and two parallel water-cooled titanium condensers for receiving overhead gas vented from the reactor. Gas feed to the reactor was controlled by a mass flow controller, the pressure was regulated by a back pressure regulator and vent gases were continuously analyzed for carbon monoxide, carbon dioxide and oxygen by a bank of three analyzers. The reactor was heated using a heating mantel with control over the heating profile managed by a Parr controller.

The catalyst composition used in Examples 40 and 41 were supported catalyst compositions composed of palladium, antimony and molybdenum loaded at levels reported in TABLE 16 on titania and were prepared by calcining in air at 650°C a mixed anatase and rutile phase titania powder identified as P25 having average primary particle size of 21 nm and BET surface area of 50 m²/g obtained from Degussa, cooling the titania, and wet impregnating it by excess liquid impregnation at room temperature using an aqueous solution containing palladium nitrate, antimony acetate, and ammonium heptamolybdate which was prepared by mixing individual stock solutions of the salts in relative proportions corresponding to the loading levels of the final supported catalyst compositions. The palladium nitrate stock solution was an aqueous 35 wt% solution of palladium nitrate. The antimony acetate stock solution was prepared by mixing 5 grams antimony acetate with 10 grams citric acid monohydrate and 30 grams water at 60°C for 1 hour and then cooling to room temperature. The ammonium heptamolybdate stock solution consisted of 10 grams ammonium heptamolybdate that had been mixed in 20 grams citric acid monohydrate and 60 grams water at 60°C for 1 hour and then allowed to cool to room temperature. After addition of the impregnating solution to the titania, the slurry was homogenized by shaking briefly. The slurry was then dried at 50°C for 60 hours, heated to 120°C at a rate of 2 °C per minute, and held at 120°C for 2 hours. The dried solid was then calcined under flowing air (100 mL/min) by heating slowly (0.4°C/min) to 400°C and holding at 400°C for 2 hours under air flow. The calcined solid was ground to a free-flowing powder and transferred to a crucible. The calcined solid was then reduced with hydrogen by exposure to a flow of dilute hydrogen (7 vol% H₂ in nitrogen) for 1 hour at room temperature and

heating in an oven to 250°C with increases in oven temperature at a rate of 0.4°C/min, after which the temperature was held at 250°C for 5 hours under dilute hydrogen flow.

5 The carbon-supported palladium used in combination with antimony and molybdenum acetate salt solutions in Examples 38 and 39 was a commercially available carbon-supported palladium in powder form containing 5 wt% palladium and was obtained from Aldrich Corporation.

10 Oxidations were begun by charging the reactor bottom with weighed amounts of catalyst or catalyst components and of distilled and deionized water ("D&D Water") as liquid medium for the reaction. In each of the examples, 2.0 g of p-toluic acid were also added to the reaction mixture. After affixing the reactor bottom to the reactor head the reactor was filled and pressurized to 450 psig using high pressure bottled nitrogen. The reactor contents then were stirred and heating to a target initiation temperature, reported in TABLE 16, was begun.
15 Once the reactor contents reached the target initiation temperature, reactions were begun by discontinuing the nitrogen flow and beginning a flow of a mixture of 8 vol% oxygen and 92 vol% nitrogen. Feed of liquid para-xylene at rates shown in TABLE 16 was then started. Semi-continuous oxidations were conducted for pre-determined periods of time, also reported in the table, and then
20 the liquid feed addition was stopped while continuing the 8% oxygen and 92% nitrogen flow and heating for an additional period of time as reported in the table.

25 After the oxidation periods ended, the 8% oxygen plus 92% nitrogen flow was stopped and nitrogen flow was resumed at 15 SCFH. The heating mantel was shut off and the reactor and its contents were allowed to cool to room temperature. At that point, the reactor was depressurized, the reactor bottom was detached and a sample of the total reactor effluent was collected for analysis by HPLC. Reaction conditions and results are shown in TABLE 16. Feedstock conversions in the table do not take into account unreacted feedstock that entered the vapor phase in the reactor such that it was unavailable for
30 conversion to oxidized aromatic products. Unreacted feedstock in the vapor phase was estimated to be no more than about 5% by weight of feed material.

TABLE 16

Example No.	38	39	40	41
<u>Reactor Charge</u>				
5% Pd / 2.5% Sb / 5% Mo / Titania (g)	---	---	4.5051	---
5% Pd / 5% Sb / 2.5% Mo / Titania (g)	---	---	---	7.5
5% Pd/Carbon (g)	5.8503	5.8514	---	---
Pd(II) acetate (g)	---	---	---	---
Sb(III) acetate (g)	0.5209	0.5230	---	---
Sn(II) acetate (g)	---	---	---	---
Mo(II) acetate dimer (g)	0.6510	0.6258	---	---
D&D water (g)	139.4	135.2	134.1	150.7
pX added (g)	20.14	22.36	22.36	21.70
p-Toluic Acid added (g)	2.0	2.0	2.0	2.0
Feedstock Conversion (mol%)	90.3	100	100	98.3
<u>Oxidation Conditions</u>				
Initiation Temp.(°C)	200	210	210	210
Oxidation Temp. (°C)	205	210	210	210
Oxidation Time (min)	90	90	90	90
Tailout Time (min)	15	15	15	15
8% Oxygen Flow (SCFH)	9	9	9	9
Reactor Pressure (psig)	455	455	455	390
<u>Product Selectivity (%)</u>				
TA	94.30	90.85	85.37	92.43
4CBA	0.92	0.60	6.69	1.11
PTOL	1.65	0.64	3.88	2.23
PTAL	0.14	0.26	<0.01	0.18
Burned pX	2.99	5.20	4.01	1.18
<u>By-products (wt% of Total Product)</u>				

BA	0.2236	2.44	0.046	2.89
TMA	<0.0001	N/A	N/A	NA
CO ₂ /CO (mol/mol)	>50	>50	>50	>50

Example 43

Following the procedure of Examples 1 - 4, a series of para-xylene oxidation trials in aqueous acetic acid solvent was conducted using compositions prepared from various combinations of one or more acetic acid soluble salts of palladium, platinum, vanadium, titanium, molybdenum, chromium, tin, antimony and, in some cases, acetic acid-soluble salts of one or more of additional metal or metalloid or standardized solutions thereof in aqueous acetic acid in amounts providing the metals or metalloids in about equal parts by weight corresponding to about 500 ppmw based on weight of acetic acid solvent used in the oxidations. Metal and metalloid combinations, temperatures and oxidation results are reported in TABLE 14; results of Examples 1-4 are also included for reference.

TABLE 14

Example or Trial #	Composition	Temp. (°C)	Conversion (mole %)	Selectivity (%)		
				TA	4CBA	PTOL
Ex. 3	Pd / Sb / Sn	168	94.67	2.70	3.67	77.58
43-1	Pd / Sn / Sb / Mo	170	90.89	0.74	3.14	66.97
43-2	Pd / Sb / Ti	170	89.41	1.03	2.45	84.23
Ex. 4	Pd / Sb / Sn	147	78.98	4.04	4.25	72.04
43-3	Pd / Sb / Ti	166	78.11	2.93	3.68	89.83
43-4	Pd / Sn / Sb / Cr	170	63.18	1.13	2.77	80.08
43-5	Pd / Sb / Mo / V	175	57.71	0.44	2.43	58.22
43-6	Pd / Sn / Sb / V	170	59.56	1.80	3.01	73.79
43-7	Pd / Sb / Mo / Ca	173	55.46	0.79	2.18	81.72
43-8	Pd / Sb / V / Ni	171	49.15	0.86	2.58	66.05

43-9	Pd / Sb / Cr / V	171	46.16	0.99	2.42	71.79
43-10	Pd / Sn / Mo / Cr	172	25.30	13.90	5.35	65.83
43-11	Pd / Sb / Ce / Hf	171	23.87	0.00	0.61	83.78
43-12	Pt / V / Mo	---	12.91	0.31	0.26	9.58
Ex. 2	Pd / Sn	169	10.88	6.13	6.24	65.60
43-13	Pd / Sb / Ce / Hf	174	9.81	0.00	0.55	83.50
Ex. 1	Pd / Sb	167	8.20	0.00	0.47	76.75
43-14	Pt / Ti / V	---	8.06	0.07	0.04	4.32
43-15	Pt / Sb / V	---	6.87	0.04	0.04	2.66
43-16	Pt / V / Nb	---	6.75	0.05	0.04	3.34
43-17	Pd / Sb / V / Hf	167	6.42	0.00	0.00	18.27
43-18	Pd / Sb / V / Ca	175	6.40	0.00	0.30	35.50
43-19	Pt / V / Ga	---	6.32	0.02	0.03	2.43
43-20	Pd / Pt / Mo	---	6.23	0.12	0.09	3.01
43-21	Pt / V / Ag	---	5.17	0.00	0.00	0.77
43-22	Pt / V	---	5.09	0.04	0.10	2.12
43-23	Pt / Mo	---	3.36	0.05	0.00	2.39
43-24	Pd / Pt / Ti	---	2.84	0.05	0.01	0.95
43-25	Pd / Sb / Ca / Ni	166	0.49	0.00	0.00	0.00
43-26	Pd / Sb / Mo / Ni	171	0.38	0.00	0.00	0.00
43-27	Pd / Sb / Ca / Ce	174	0.22	0.00	0.00	0.00
43-28	Pd / Sb / Cr / Ce	173	0.17	0.00	0.00	0.00
43-29	Pd / Sb / Ni / Hf	172	0.13	0.00	0.00	0.00
43-30	Pd / Sb / Mo / Ce	171	0.13	0.00	0.00	0.00
43-31	Pd / Sb / Hf	165	0.11	0.00	0.00	0.00

We claim:

1. A process for conversion of an aromatic feedstock comprising a substituted aromatic compound, at least one substituent group of which comprises an alpha carbon atom, to an oxidized aromatic product comprising at least one aromatic carboxylic acid, at least one carboxylic acid group of which comprises an alpha carbon atom, comprising contacting the aromatic feedstock with oxygen in a liquid reaction mixture in the presence of a catalyst composition having activity for such conversion in the absence of bromine comprising (A) at least one of platinum, palladium, titanium or vanadium, and (B) at least one Group 5, 6, 14 or 15 metal or metalloid, provided that (A) and (B) do not each consist only of vanadium.
2. The process of claim 1 wherein the liquid reaction mixture comprises at least one C₁₋₈ monocarboxylic acid solvent for the aromatic feedstock.
3. The process of claim 1 wherein the liquid reaction mixture comprises water and no more than about 10 wt.% C₁₋₈ monocarboxylic acid.
4. The process of claim 1 wherein at least a portion of the catalyst composition is soluble in the liquid reaction mixture.
5. The process of claim 1 wherein at least a portion of the catalyst composition is insoluble in the liquid reaction mixture.
6. The process of claim 1 wherein the substituted aromatic compound is a dialkylarene or a partially oxidized dialkylarene derivative or a combination thereof.
7. The process of claim 1 wherein the substituted aromatic compound is para-xylene or a partially oxidized para-xylene derivative or a combination thereof.
8. The process of claim 7 wherein the oxidized aromatic product comprises terephthalic acid, p-toluic acid, 4-carboxybenzaldehyde, hydroxymethyl benzoic acid or a combination thereof.

9. The process of claim 1 wherein carbon monoxide and carbon dioxide are generated in the process in an amount less than about 0.5 mole per mole of oxygen consumed.
- 5 10. The process of claim 1 wherein the catalyst composition is present in the liquid reaction mixture in an amount such that about 500 to about 10000 parts per million by weight of metal and metalloid of the catalyst composition are present based on weight of liquid medium or solvent in the liquid reaction mixture.
- 10 11. The process of any of claims 1-10 wherein the catalyst composition comprises platinum.
12. The process of any of claims 1-10 wherein the catalyst composition comprises vanadium.
13. The process of any of claims 1-10 wherein the catalyst composition comprises titanium.
- 15 14. The process of any of claims 1-10 wherein the catalyst composition comprises palladium.
15. The process of claim 14 wherein the catalyst composition comprises antimony or bismuth.
- 20 16. The process of claim 15 wherein the catalyst composition comprises at least one of vanadium, molybdenum and tin.
17. The process of any of claims 1-10 wherein the catalyst composition comprises palladium or a combination thereof with at least one of vanadium or titanium, and antimony or a combination thereof with at least one Group 5, 6 or 14 metal or metalloid.
- 25 18. A process for manufacture of aromatic carboxylic acid comprising contacting a feed material comprising at least one dialkylarene, partially oxidized dialkylarene derivative or a combination thereof with oxygen in a liquid reaction mixture at temperature and pressure effective to maintain a liquid reaction mixture in the presence of a catalyst composition
- 30 comprising (A) at least one of palladium, platinum, vanadium and titanium,

and (B) at least one Group 5, 6, 14, or 15 metal or metalloid wherein (A) and (B) do not both consist only of vanadium.

19. The process of claim 18 wherein the liquid reaction mixture is free of reactive bromine.

5 20. The process of claim 18 wherein the liquid reaction mixture comprises at least one C₁₋₈ monocarboxylic acid solvent for the aromatic feedstock.

21. The process of claim 18 wherein the liquid reaction mixture comprises water and not more than 10 wt.% C₁₋₈ monocarboxylic acid.

10 22. The process of claim 18 wherein at least a portion of the catalyst composition is soluble in the liquid reaction mixture.

23. The process of claim 18 wherein at least a portion of the catalyst composition is insoluble in the liquid reaction mixture.

24. The process of claim 18 wherein the dialkylarene is para-xylene and the oxidized aromatic product comprises terephthalic acid.

15 25. The process of claim 18 wherein the dialkylarene is meta-xylene and the oxidized aromatic product comprises isophthalic acid.

20 26. The process of claim 18 wherein the dialkylarene is 2,6-dimethyl or -diethyl naphthalene, 2,7-dimethyl or -diethyl naphthalene and the oxidized aromatic product comprises, correspondingly, 2,6-naphthalene dicarboxylic acid or 2,7-naphthalene dicarboxylic acid.

27. The process of claim 18 wherein carbon monoxide and carbon dioxide are generated in the process in an amount less than about 0.5 mole per mole of oxygen consumed.

25 28. The process of claim 18 wherein the catalyst composition is present in the liquid reaction medium in an amount such that about 500 to about 10000 parts per million by weight of metal and metalloid of the catalyst composition are present based on weight of liquid medium or solvent in the liquid reaction mixture.

29. The process of claim 18 wherein the temperature is about 100 to about 300°C.
30. Terephthalic acid made by a process according to any of claims 18-24 or 27-29.
- 5 31. Isophthalic acid made by a process according to any of claims 18-23, 25 or 27-29.
32. 2,6-naphthalene dicarboxylic acid or 2,7-naphthalene dicarboxylic acid made by a process according to any of claims 18-23 or 26-29.
- 10 33. The process of any of claims 18-29 wherein the catalyst composition comprises palladium or a combination thereof with at least one of vanadium or titanium, and antimony or a combination thereof with at least one Group 5, 6 or 14 metal or metalloid.
34. The process of claim 33 wherein the catalyst composition wholly or partially supported on a solid support.
- 15 35. The process of claim 33 wherein the catalyst composition comprises palladium, antimony and at least one of vanadium, molybdenum and tin.
36. Terephthalic acid made by the process of any of claims 33-36.
- 20 37. A catalyst composition having activity for conversion of a substituted aromatic compound, at least one substituent group of which comprises an oxidizable alpha carbon atom, in contact with oxygen in liquid reaction mixture substantially free of reactive bromine to an oxidized aromatic product comprising at least one aromatic carboxylic acid in which at least one carboxylic acid group comprises an alpha carbon atom, wherein the catalytic composition comprises (A) at least one of palladium, platinum, vanadium or titanium, and (B) at least one Group 5, 6, 14 or 15 metal or metalloid, provided that (A) and (B) do not both consist only of vanadium
- 25 38. The catalyst composition of claim 37 comprising palladium.
39. The catalyst composition of claim 37 comprising platinum.

40. The catalyst composition of claim 37 comprising vanadium.
41. The catalyst composition of claim 37 comprising titanium.
42. The catalyst composition of claim 37 comprising platinum and titanium.
43. The catalyst composition of claim 37 comprising vanadium and titanium.
- 5 44. The catalyst composition of claim 37 comprising a Group 5 metal.
45. The catalyst composition of claim 44 wherein the Group 5 metal is vanadium or niobium.
46. The catalyst composition of claim 37 comprising a Group 6 metal.
47. The catalyst composition of claim 46 wherein the Group 6 metal is
10 chromium or molybdenum.
48. The catalyst composition of claim 37 comprising a Group 14 metal or metalloid.
49. The catalyst composition of claim 48 wherein the Group 14 metal or metalloid is tin.
- 15 50. The catalyst composition of claim 37 comprising a Group 15 metal or metalloid.
51. The catalyst composition of claim 50 wherein the Group 15 metal or metalloid is antimony or bismuth.
52. The catalyst composition of claim 37 comprising palladium or a
20 combination thereof with at least one of vanadium or titanium and antimony or a combination thereof with at least one Group 5, 6 or 14 metal or metalloid.
53. The catalyst composition of any of claims 37-52 wherein palladium, platinum, vanadium or titanium and Group 5, 6, 14, or 15 metal or
25 metalloid are present such that the atom ratio thereof, calculated as elements, is about 1 : 1000 to about 1000 : 1.
54. A catalyst solution comprising aqueous monocarboxylic acid having dissolved therein the catalyst composition according to any of claims 37-52.

55. A catalyst solution comprising water having dissolved therein the catalyst composition according to any of claims 37-52.
56. The catalyst composition according to any of claims 37-52 in the form of a water and aqueous organic acid insoluble solid.
- 5 57. A catalyst composition according to any of claims 37-52 comprising at least one of the palladium, platinum, vanadium or titanium and Group 5, 6, 14, or 15 metal or metalloid thereof carried on a solid support material.
58. A catalyst composition according to any of claims 37-52 in which gold is present.
- 10 59. A terephthalic acid composition comprising terephthalic acid and, by weight of the terephthalic acid, about 0.1 to about 500 ppmw palladium, platinum, vanadium or titanium calculated as the element, and about 0.1 to about 500 ppmw Group 5, 6, 14 or 15 metal or metalloid, calculated as the element, or a combination thereof.
- 15 60. A terephthalic acid composition suitable for direct conversion by reaction with at least one glycol to polyester suitable for manufacture of fiber comprising terephthalic acid and, by weight of the terephthalic acid, about 0.01 to about 100 ppmw palladium, platinum, vanadium or titanium, calculated as the element, and about 0.01 to about 100 ppmw Group 5, 6,
20 14 or 15 metal or metalloid, calculated as the element, or a combination thereof.