

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 March 2002 (14.03.2002)

PCT

(10) International Publication Number
WO 02/20649 A1

- (51) **International Patent Classification⁷:** C08J 5/18, A61K 9/48, C08L 5/00, C12P 19/04
- (21) **International Application Number:** PCT/EP01/09593
- (22) **International Filing Date:** 21 August 2001 (21.08.2001)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
00402437.8 5 September 2000 (05.09.2000) EP
- (71) **Applicant** (*for all designated States except US*):
WARNER-LAMBERT COMPANY [US/US]; 201 Tabor Road, Morris Plains, NJ 07950 (US).
- (72) **Inventors; and**
- (75) **Inventors/Applicants** (*for US only*): **SCOTT, Robert** [GB/BE]; Königin Elisabethplein 26, bus 4, B-9100 Sint Niklaas (BE). **CADE, Dominique** [FR/FR]; 11, rue des Américains, F-68000 Colmar (FR). **HE, Xiongwei** [CN/FR]; 3, rue du Jura, F-68280 Andolsheim (FR).
- (74) **Agents:** **MANSMANN, Ivo** et al.; Gödecke GmbH, Patents, Mooswaldallee 1, 79090 Freiburg (DE).
- (81) **Designated States** (*national*): AE, AG, AL, AU, BA, BB, BG, BR, BZ, CA, CN, CO, CR, CU, CZ, DM, DZ, EC, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MA, MG, MK, MN, MX, NO, NZ, PH, PL, RO, SG, SI, SK, TT, UA, US, UZ, VN, YU, ZA.
- (84) **Designated States** (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Declaration under Rule 4.17:**
— *of inventorship (Rule 4.17(iv)) for US only*
- Published:**
— *with international search report*
— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 02/20649 A1

(54) **Title:** COMPOSITION FOR SOLUBLE FILMS WITH A NEW HYDROLYZED POLYSACCHARIDE

(57) **Abstract:** The invention is concerned with film-forming compositions containing hydrolysates of the exopolysaccharide YAS34 for the use in pharmaceutical, veterinary, food, cosmetic or other products like films for wrapping food, aspics or jellies, preferably for predosed formulations like soft or hard capsules.

YAS34 has a thermal reversible gelling ability and excellent properties for forming films with sufficient mechanical characteristics for the manufacturing of capsules, especially hard capsules. A disadvantage of the YAS34-films however is the poor water solubility at 37°C. It takes 50 minutes to dissolve a film of 100 µm thickness
5 whereas a conventional gelatin film will be dissolved in only 2 minutes. A further disadvantage of YAS34 is its very high viscosity resulting from the very high molecular weight of the polysaccharide. But high viscosity and gelling ability result in the impossibility of forming films by casting or dip moulding, especially for hard capsules from solutions having an EPS concentration above 10 %. Especially for the
10 production of hard capsules high solid contents of the film forming aqueous solution are required. Low solid content will result in non-uniform film forming, long drying time and low productivity.

Surprisingly we have found that the disadvantages can be overcome by hydrolysis of YAS34, which reduces efficiently the molecular weight and the viscosity of the
15 aqueous solution viscosity. Furthermore the solubility of the polysaccharide film is significantly improved. Though some alterations of the mechanical properties have been observed, they remain at an acceptable level for the requirements of hard capsules.

The original polysaccharide YAS34 has a molecular weight of 1,400,000. An aqueous
20 solution of 5 % by weight gelatinizes at 60°C and the the working temperature has to be above 60°C for capsule manufacturing. If the concentration is increased to 10%, the working temperature has to be increased above 80°C. Such conditions are quite inconvenient and energy consuming for an industrial manufacturing process.

The hydrolysis of YAS34 under acid conditions is very efficient as demonstrated in
25 experiments. Under the conditions given in example 1, within one hour, the molecular weight of the polysaccharide is reduced below 200,000 which can be used for the preparation of film-forming aqueous solutions with a content above 20 %. Such solutions have acceptable viscosity even at room temperature. For this reason the molecular weight of the hydrolyzed YAS34 is preferably between 500,000 and 10,000

which allows the preparation of film-forming solutions in the range from 10 to 50% by weight.

Within the preferred Mw range the mechanical properties of the film remain quite acceptable even for hard capsule production.

5 Conventional hard capsules are produced from gelatin by a dip moulding process. This process is based on the setting ability of hot gelatin solution by cooling. On a totally automatic industrial hard gelatin capsule machine, mould pins are dipped into hot gelatin solution, the pins are removed from the solution, inverted, the gelatin solution (gel) remaining on the pins dried, stripped off the capsule shells and finally
10 cap and body of the capsules cut and pre-joined. The immediate setting of the gelatin solution on the mould pins after dipping is the key step in the process. Otherwise, the gelatin solution would flow down to form capsules with non-uniform wall thickness and unacceptable properties.

However the aqueous solution of the hydrolyzed polysaccharide YAS34 does not
15 gelatinize at room temperature and does not have the necessary setting ability for hard capsule manufacturing by the described conventional dip moulding process. Surprisingly we have found that the addition of an additional setting agent to the aqueous solution or to the film-forming composition allows the adjustment and optimization of the setting ability of the solution to achieve uniform shell thickness of
20 hard capsules.

Preferred setting agents for the inventive film-forming compositions or the aqueous solutions thereof are carrageenan, gellan gum, pectin, agarose, gelatin, xanthan with locust bean gum, xanthan with konjac, or unhydrolyzed YAS34. The preferred content of the setting agent in the solid film composition is 0.5 % to 15 % by weight.
25 In the aqueous solution the setting agent is in the range of 0.05 % to 5 % by weight. Optionally the gelling agents are combined with mono or divalent cations like Calcium Ca^{++} or Mg^{++} , e.g. water-soluble salts thereof, preferably in the aqueous

solution in an amount of 0.01 to 3 % or in the solid film composition in an amount of 0.1 to 5% by weight.

Aqueous solutions of the inventive film-forming composition containing hydrolyzed YAS34 and a setting agent and the films derived therefrom have following
5 advantages:

- High solid content which improves significantly the feasibility of different manufacturing processes.
- Sufficient setting ability for hard capsule production by conventional dip moulding process.
- 10 • High solubility of the films, suitable for predosed formulations such as hard capsules, soft capsules, tablet coating and ingredient packaging.
- Acceptable mechanical properties of the films for hard capsules allowing filling and blistering operations.

The inventive composition may contain in a further aspect additional plasticizer,
15 especially for soft film formulations such as soft capsules.

The inventive composition may contain in a further aspect additional coloring agents or flavoring agents.

The hard capsules of the invention may be used as containers for providing unit dosage forms, e.g. for agrochemicals, seeds, herbs, foodstuffs, dyestuffs,
20 pharmaceuticals, flavouring agents and the like.

Example 1

Hydrolysis of the native polysaccharide YAS34

15 g of YAS34 are dissolved in distilled water at 52°C to form a solution containing 1.5 % by weight to which 1000 ml 2M HCl are added under stirring. The mixture is
25 incubated at 52°C for A 1 hour and in a second batch B for 1.5 hours. After the given

incubation time the solution is cooled to room temperature and neutralized to pH 7. The hydrolysates are precipitated with a water/ethanol (50/50 v/v) and washed 4 times with ethanol.

Molecular weights and viscosity of YAS34 and hydrolysates are shown in Table 1:

5

Table 1

	Mw average	Viscosity (cps)
YAS34	1,400,000	5% at 50°C gelatinized 5% at 60°C gelatinized
Hydrolysate A	123,000	20% at 50°C 650
Hydrolysate B	45,000	27% at 50°C 300

The results in Table 1 demonstrate that hydrolysis under mild conditions efficiently reduces molecular weight and viscosity and the hydrolysates are well suitable for the preparation of aqueous solutions with acceptable viscosity and solid content for the manufacturing of hard or soft capsules.

10 Example 2

Polysaccharide films

- 15 a) 50 g YAS34 are dissolved in distilled water at 90°C to form a solution of 10 % by weight. After debubbling the solution was stabilized at 80°C. Films with a thickness about 100 µm were prepared by casting the solution on glass plates and drying at 22°C / 50 % RH over night.
- b) 50 g hydrolysate B (Mw ≈ 45,000) are dissolved in distilled water at 60°C to form a solution of 27 %. After debubbling, the solution was stabilized at 50°C. Films with a thickness about 100 µm were prepared by casting the solution on glass plates and drying at 22°C / 50 % RH over night.

20 The dissolution times of the films shown in Table 2 are determined according to UPS XXII dissolution test method conditions (at 37°C, in demineralized water).

Table 2

	YAS34	Hydrolysate B	Gelatin
Dissolution (min)	51	1.2	2.2

The mechanical properties of the films shown in Table 3 are determined by tensile tests with an Instron machine with films equilibrated by 50 % RH at 22°C before test.

Table 3

	YAS34	Hydrolysate B
Young's modulus (MPa)	2400	2880
Strength (MPa)	59	55
Elongation at break (%)	19	9

- 5 The result of the tests demonstrate that hydrolysate B has a significantly higher dissolution rate than YAS34. The dissolution is even better than gelatin. The tensile strenght of the hydrolysate is reduced when compared with YAS34 but the mechanical properties remain very acceptable not only for soft but even for hard capsule manufacturing.

10 **Example 3**

Hard capsules from hydrolysate B

54 g hydrolysate B and 4 g of YAS34 are dissolved in distilled water at 70°C to 200 g of a solution containing 27 % hydrolysate B and 2 % YAS34 by weight. After debubbling the solution was stabilized at 60°C.

- 15 The solution thus prepared was then poured into a dipping dish of a single pin pilot machine of conventional hard gelatin capsule production equipment. Hard capsules of size 1 were produced under similar conditions to hard gelatin capsule production. The produced hard capsules have similar dimensions to the conventional gelatin hard capsules.

The produced hard capsules were evaluated by disintegration tests according to USPXXIII at 37°C in demineralized water:

First leak: 1.4 minute

Total disintegration: 9.5 minutes

Claims

1. Film-forming composition containing hydrolyzed exopolysaccharide YAS34.
2. Film-forming composition according to claim 1, wherein the EPS YAS34 is hydrolyzed to an average molecular weight range from 500,000 to 10,000.
- 5 3. Film composition according to claim 2, wherein the hydrolyzed YAS34 has an average molecular weight of 45,000.
4. Film composition, according to claims 1 to 3 containing an additional setting agent for processing purpose.
5. Film composition according to claim 4, wherein the setting agent is selected from
10 carrageenan, gellan gum, pectin, agorose, gelatin, xanthan with locust bean gum, xanthan with konjac, or native EPS YAS34.
6. Film composition according to claims 4 or 5, wherein the setting agent is contained in an amount of 0.5 to 15 % by weight.
7. Film composition according to claims 4 to 6, wherein the setting agent is
15 combined with salts of mono or divalent cations.
8. Film composition according to claim 7, wherein the cation salt is contained in an amount of 0.01 to 5 % by weight of the whole composition.
9. Film composition according to claims 1 to 8 containing additionally coloring agents, flavoring agents and/or plasticizers.
- 20 10. Container produced from the film-forming composition according to claims 1 to 9 for unit dosage forms of agrochemicals, seeds, herbs, foodstuffs, pharmaceuticals or flavoring agents.

11. An aqueous solution of the film-forming composition according to claims 1 to 9 for the manufacturing of soft and hard capsules.
12. The aqueous solution according to claim 11 containing hydrolyzed EPS YAS34 in an amount of 10 to 50%, preferably 15 to 40% by weight of the aqueous solution.
- 5 13. The aqueous solution according to claims 11 and 12 containing an additional setting agent in an amount of 0.01 to 5%, preferably 0.03 to 3% by weight of the aqueous solution.
14. The aqueous solution according to claims 11 to 13 containing additionally salts of mono or divalent cations in an amount of 0.01 to 3%, preferably 0.01 to 1% by
10 weight of the aqueous solution.
15. Use of the aqueous solution according to claims 11 and 14 for the manufacturing of hard capsules in a dip moulding process.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/09593

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08J5/18 A61K9/48 C08L5/00 C12P19/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08J A61K C08L C12P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	AGNÈS VILLAIN-SIMONNET ET AL.: "A new bacterial polysaccharide (YAS34)." INT. J. BIOL. MACROMOL., vol. 27, no. 1, 2000, pages 65-75, XP002159348 Amsterdam page 69; table 2	1, 2, 11, 12
X	AGNÈS VILLAIN-SIMONNET ET AL.: "A new bacterial exopolysaccharide (YAS34)" INTERNATIONAL JOURNAL OF BIOLOGICAL MACROMOLECULES, vol. 27, no. 1, 2000, pages 77-87, XP002159349 Amsterdam page 85 -page 86	1-14



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

11 January 2002

Date of mailing of the international search report

24/01/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lensen, H

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/09593

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 306 059 A (KOJI YOKOBAYASHI ET AL.) 15 December 1981 (1981-12-15) examples 1-3,13 -----	1-14
Y	GB 2 223 503 A (AGRICULTURAL & FOOD RESEARCH COUNCIL) 11 April 1990 (1990-04-11) page 7, paragraph 2 -----	1-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/09593

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4306059	A	15-12-1981	JP 1337448 C	29-09-1986
			JP 54052793 A	25-04-1979
			JP 60054322 B	29-11-1985
			DE 2842855 A1	12-04-1979
			FR 2404655 A1	27-04-1979
			GB 2007245 A ,B	16-05-1979
<hr/>				
GB 2223503	A	11-04-1990	NONE	
<hr/>				