



(51) International Patent Classification:

B60C 1/00 (2006.01) C08K 5/00 (2006.01)

C08C 19/00 (2006.01) C08L 9/00 (2006.01)

C08C 19/06 (2006.01) C08L 9/06 (2006.01)

C08C 19/22 (2006.01)

EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(21) International Application Number:

PCT/US2016/040254

Declarations under Rule 4.17:

— of inventorship (Rule 4.17(iv))

(22) International Filing Date:

30 June 2016 (30.06.2016)

Published:

— with international search report (Art. 21(3))

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: COMPAGNIE GENERALE DES
ETABLISSEMENTS MICHELIN [FR/FR]; 12 Cours
Sablon, 63000 Clermont-Ferrand (FR).

(72) Inventors; and

(71) Applicants (for US only): MCDOWELL, Jessica
[US/US]; c/o Michelin North America, Inc., Intellectual
Property Dept, 515 Michelin Road, Greenville, SC 29605
(US). SAINTIGNY, Xavier [FR/US]; c/o Michelin North
America, Inc., Intellectual Property Dept, 515 Michelin
Road, Greenville, SC 29605 (US).

(74) Agent: CAMPIGOTTO, Frank, J.; Michelin North
America, Inc., Intellectual Property Dept., 515 Michelin
Road, Greenville, SC 29605 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ,
EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR,
HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA,
LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN,
MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE,
PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE,
SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ,
UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,

(54) Title: FUNCTIONALIZED RUBBER COMPOSITION WITH SBR/BR RUBBER

(57) Abstract: Rubber compositions, rubber articles and methods for making such rubber articles that include a rubber composition having, per 100 parts by weight of rubber (phr), a modified rubber component such as an epoxidized rubber component selected from an epoxidized polybutadiene rubber (eBR), an epoxidized styrene-butadiene rubber (eSBR), or combinations thereof having a Tg of between -80 °C and -110 °C as well as a second rubber component selected from the group consisting of a polybutadiene rubber (BR), a styrene-butadiene rubber (SBR) and combinations thereof. Also between 30 phr and 130 phr of an efficient plasticizing resin may be included. An efficient plasticizing resin is one that when included in a mixture of the modified rubber component and 67 phr of the efficient plasticizing resin, causes a Tg of the mixture to be at least 14 °C higher than the Tg of the modified rubber component itself.



FUNCTIONALIZED RUBBER COMPOSITION WITH SBR/BR RUBBERBACKGROUND OF THE INVENTIONField of the Invention

[0001] This invention relates generally to rubber compositions and more particularly, to rubber compositions useful for making tires or semi-finished products for tires.

Description of the Related Art

[0002] Tire designers must often deal with conflicting requirements when they design a new tread for a tire. Tire consumers want to have tires that grip well in the snow as well as on dry and wet roads, they want low rolling resistance tires that require tires be designed with low hysteresis and they want tires with good wear properties so they can run the tires for many miles without wearing them out.

[0003] Improving grip and wear at the same time remains a constant challenge to the tire designer. It is well known in the industry that tire designers often compromise on certain tire performance characteristics since often each improvement to one characteristic is offset by a decline in another tire performance characteristic. Such is the case for tire wear and wet traction. There is a compromise that tire designers must reach since when they try to achieve an improvement in the wear properties of the tire there is often a decrease in the braking performance of the tire. For example it is known that adding a polybutadiene to a rubber composition will result in improved wear but it is known that it also results in a decrease in traction. Therefore, tire designers are looking for improvements to their designs that allow them to break this compromise, *i.e.*, achieve an improvement in wear without a corresponding decrease in another tire property such as braking.

[0004] New materials are useful for breaking compromises and tire designers are developing new materials that can be successfully integrated into rubber compositions that are used to build tires.

SUMMARY OF THE DISCLOSURE

[0005] Particular embodiments of the disclosure provide rubber compositions, rubber articles including tire treads and methods for making such rubber articles. An embodiment includes a rubber composition that is based up a cross-linkable elastomer composition, the cross-linkable elastomer composition having, per 100 parts by weight of rubber (phr), a modified rubber component selected from a modified polybutadiene rubber, a modified styrene-butadiene rubber, or combinations thereof as well as a second rubber component selected from the group consisting of a polybutadiene rubber (BR), a styrene-butadiene rubber (SBR) and combinations thereof. The modified rubber component has been modified with a functional group having a heteroatom selected from oxygen, nitrogen, silicon or combinations thereof. The modified rubber component has a Tg of between -80 °C and -110 °C. In particular embodiments the modified rubber component is selected from an epoxidized polybutadiene rubber (eBR), an epoxidized styrene-butadiene rubber (eSBR), or combinations thereof.

[0006] In particular embodiments, the rubber composition may provide that the functional group of the modified rubber component be characterized in that it can have a hydrogen bonding interaction with the efficient plasticizing resin.

[0007] Particular embodiments of the rubber compositions disclosed herein further include between 30 phr and 130 phr of an efficient plasticizing resin, wherein the efficient plasticizing resin is, when included in a mixture consisting of the modified rubber component and 67 phr of the efficient plasticizing resin, causes a glass transition temperature (Tg) of the mixture to be at least 14 °C higher than the Tg of the modified rubber component. Such rubber compositions further include a reinforcement filler and a curing system.

[0008] In particular embodiments of the disclosed rubber composition the modified rubber component may have an epoxide content of between 1 mol% and 25 mol%. Furthermore particular embodiments may have the epoxidized rubber component in an amount of between 10 phr and 95 phr and the second rubber component in an amount of between 5 phr and 90 phr.

[0009] The foregoing and other objects, features and advantages of the invention will be apparent from the following more detailed descriptions of particular embodiments of the invention.

DETAILED DESCRIPTION OF PARTICULAR EMBODIMENTS

[0010] Particular embodiments of the present invention include treads and tires having such treads that have improved wear characteristics while maintaining or even improving their traction, *i.e.*, improved braking performance, especially wet traction. This improvement in wear and traction has been achieved by forming unique tire treads from a rubber composition that includes blending a rubber component having a low glass transition temperature (T_g) with an efficient resin that results in a rubber composition having a T_g within a range suitable for all-weather tires, summer tires and/or winter tires. Such tires are particularly suitable for use on passenger cars and/or light trucks and while certain embodiments are limited to such uses, other embodiments are broader and may include tires useful for other vehicles including heavy trucks, aircraft and so forth.

[0011] In other embodiments of the rubber compositions disclosed herein, an improvement in traction of a tread can be achieved without sacrificing the improvement in wear. It has been found that by combining a low-T_g modified rubber component that is selected from a modified styrene-butadiene rubber (SBR), a modified polybutadiene rubber (BR) or combinations thereof with a second rubber component selected from BR and/or SBR and with an efficient plasticizing resin that wet traction is improved without a compromise in the wear property. Surprisingly it has been discovered that adding the second rubber component SBR/BR to the rubber composition does not decrease the glass transition temperature (T_g) of the resulting rubber composition but actually increases it even though, for example, BR has a very low T_g, *e.g.*, less than -90 ° C. In particular embodiments the modified rubber composition is functionalized with an epoxide so that the modified rubber component is selected from the group consisting of an epoxidized polybutadiene rubber (eBR), an epoxidized styrene-butadiene rubber (eSBR), or combinations thereof.

[0012] As used herein, “phr” is “parts per hundred parts of rubber by weight” and is a common measurement in the art wherein components of a rubber composition are measured relative to the total weight of rubber in the composition, *i.e.*, parts by weight of the component per 100 parts by weight of the total rubber(s) in the composition.

[0013] As used herein, elastomer and rubber are synonymous terms.

[0014] As used herein, “based upon” is a term recognizing that embodiments of the present invention are made of vulcanized or cured rubber compositions that were, at the time of their assembly, uncured. The cured rubber composition is therefore “based upon” the uncured rubber composition. In other words, the cross-linked rubber composition is based upon or comprises the constituents of the cross-linkable rubber composition.

[0015] As is generally known, a tire tread includes the road-contacting portion of a vehicle tire that extends circumferentially about the tire. It is designed to provide the handling characteristics required by the vehicle; *e.g.*, traction, dry braking, wet braking, cornering and so forth – all preferably being provided with a minimum amount of generated noise and at low rolling resistance.

[0016] Treads of the type disclosed herein include tread elements, the structural features of the tread that contact the ground. Such structural features may be of any type or shape, examples of which include tread blocks and tread ribs. Tread blocks have a perimeter defined by one or more grooves that create an isolated structure in the tread while a rib runs substantially in the longitudinal (circumferential) direction and is not interrupted by grooves that run in the substantially lateral (axial) direction or any other grooves that are oblique thereto. The radial (depth) direction is perpendicular to the lateral direction.

[0017] It is recognized that treads may be formed from only one rubber composition or in two or more layers of differing rubber compositions, *e.g.*, a cap and base construction. In a cap and base construction, the cap portion of the tread is made of one rubber composition that is designed for contact with the road. The cap is supported on the base portion of the tread, the base portion made of different rubber composition. In particular embodiments of the present invention the entire tread may be made from the rubber compositions disclosed herein while in other embodiments only the cap portions of the tread may be made from such rubber compositions.

[0018] In other embodiments it is recognized that the contact surface of the tread elements, *i.e.*, that portion of the tread element that contacts the road, may be formed totally and/or only partially from the rubber compositions disclosed herein. In particular embodiments the tread block, for example, may be formed as a composite of laterally layered rubber compositions such that at least one lateral layer of a tread block is of the rubber compositions

disclosed herein and another lateral layer of a tread block is of an alternative rubber composition. In particular embodiments of tread constructions, at least 80 % of the total contact surface area of the tread is formed solely from the rubber compositions disclosed herein. The total contact surface area of the tread is the total surface area of all the radially outermost faces of the tread elements that are adapted for making contact with the road.

[0019] Particular embodiments of the rubber compositions that are disclosed herein and that are useful for treads include a modified polybutadiene rubber (BR), a modified styrene-butadiene rubber (SBR) or combinations thereof that have been modified with a functional group that contains a heteroatom selected from oxygen, nitrogen and/or silicon. Such useful rubbers may be characterized as having a low glass transition temperature (T_g), *i.e.*, a T_g of between -80 °C and -110 °C or alternatively between -80 °C and -105 °C, between -85 °C and -105 °C or between -90 °C and -100 °C. The glass transition temperatures of such elastomers may be measured by differential scanning calorimetry (DSC) in accordance with ASTM D3418.

[0020] Without limiting the invention, it is thought that the modification of the elastomer with such a heteroatom may provide an opportunity for the elastomer to form a hydrogen bonding relationship with a properly selected resin. As will be further disclosed below, such properly selected resins are efficient plasticizing resins – those resins that when mixed in an amount of 67 phr with just the low T_g modified rubber component, results in a mixture having a T_g that is at least 14 °C higher than the T_g of the modified rubber component.

[0021] As is known in the art, a proton donor/acceptor relationship provides hydrogen bonding which may be illustrated as D-H- -A, where D is the proton donor and A is the proton acceptor. While often the donor will interact with just one acceptor, it is also possible for the donor to interact with multiple acceptors simultaneously. Such systems are often referred to as bifurcated or trifurcated arrangements.

[0022] In particular embodiments of the systems described herein, the proton donor may be provided by the elastomer or alternatively it may be provided by the resin. For example if the resin has readily available OH groups, as is the case of terpene phenolic resins, then the resin would act as the proton donor and the elastomer would be functionalized to act as the proton acceptor, having been modified, for example, with an epoxide moiety or with a nitrile moiety. As another example, if the resin has epoxide groups, as in the case of epoxide resins,

then the resin would act as the proton acceptor and the elastomer would be functionalized to act as the proton donor, having been modified, for example with a silanol moiety. Such elastomers and resins are well known in the art.

[0023] Particular embodiments of the modified rubber compositions that are disclosed herein and that are useful for treads include those that have been modified by functionalizing the backbone or the branches of the elastomers. As noted, such modifications of elastomers are well known and may include, for example, modifying the elastomers with silanol or polysiloxane as may be described, for example, in US Patent 6,013,718. Other examples include those having alkoxy silane groups as described in US Patent 5,977,238, carboxylic groups as described in US 6,815,473 or polyether groups as described in US 6,503,973, all of these cited patents being fully incorporated herein by reference.

[0024] While much of the remaining disclosure is concentrated on epoxidized SBR and BR, it should be understood by those skilled in the art that such disclosure is relevant to the entire disclosure that includes any SBR and BR rubbers as disclosed above that have been modified with a functional group having a heteroatom selected from O, N and/or Si and having a glass transition temperature of between -80 °C and -110 °C. However, particular embodiments of the rubber compositions disclosed herein are limited to those having only the epoxidized SBR and epoxidized BR, either singly or combination with each other, as the low Tg modified rubber component.

[0025] Particular embodiments of the rubber compositions that are disclosed herein and that are useful for treads include an epoxidized rubber component that is selected from an epoxidized polybutadiene rubber (eBR), an epoxidized styrene-butadiene rubber (eSBR) or combinations thereof. These useful rubbers may be further characterized as having a low glass transition temperature (Tg), *i.e.*, a Tg of between -80 °C and -110 °C or alternatively between -80 °C and -105 °C, between -85 °C and -105 °C or between -90 °C and -100 °C. The glass transition temperatures of epoxidized elastomers may be measured by differential scanning calorimetry (DSC) in accordance with ASTM D3418.

[0026] Epoxidized rubbers such as eBR and eSBR are well known and may be obtained, as is known to those skilled in the art, by processes based on chlorohydrin or

bromohydrin or processes based on hydrogen peroxides, alkyl hydroperoxides or peracids (such as peracetic acid or performic acid).

[0027] To obtain the targeted technical effect, the epoxidized rubber includes between 1 mol% and 25 mol% of the epoxy functionality or alternatively between 2 mol% and 25 mol%, between 2 mol% and 18 mol%, between 3 mol% and 18 mol%, between 5 mol% and 25 mol%, between 5 mol% and 18 mol%, between 8 mol% and 15 mol% or between 8 mol% and 20 mol%. Since the Tg of the rubber increases with increasing epoxy functionality, greater than 25 mol% impacts the desired wear properties of the treads disclosed herein and less than the 1 mol% impacts the resin selection and content of the resulting rubber composition. The epoxy functionality by mole percent can be determined in known way through NMR analysis.

[0028] eSBR is a copolymer of styrene and butadiene that has been functionalized with an epoxy functional group as explained above. The SBR may be manufactured by any of the known processes including the emulsion process producing E-SBR and the solution process producing S-SBR.

[0029] The microstructure of the eSBR is typically described in terms of the amount of bound styrene and the form of the butadiene portion of the polymer. Looking first at the amount of bound styrene, since the Tg of the eSBR increases as the bound styrene content increases it is necessary to limit the amount of bound styrene to an amount that still provides the required low Tg of the elastomer. Particular embodiments of the present invention may utilize an SBR having a bound styrene content, for example, of between 3 wt% and 30 wt% or alternatively between 3 wt% and 25 wt% or between 5 wt% and 20 wt% bound styrene.

[0030] Considering the butadiene portion of the copolymer, the butadiene portion is made up of three forms because of the double bond present in that butadiene portion. The three forms are the *cis*-1,4, *trans*-1, 4 and *vinyl*-1,2 forms. Higher levels of the *cis*-form may typically provide a lower Tg while increasing levels of the *vinyl*-form may typically increase the Tg. SBR materials suitable for use as the low Tg SBR may be described, for example, as having a vinyl-1,2-bond content of between 4 mol% and 30 mol% or alternatively, between 4 mol% and 25 mol% or between 4 mol% and 20 mol%.

[0031] Of course it is a balancing of the styrene content and the microstructure of the butadiene portion of the eSBR that provides the physical properties desired of the material,

including the low T_g. While the microstructure and styrene content of the eSBR can be adjusted to provide improvements to the properties of the elastomer, the invention requires that the low T_g eSBR elastomers that are included in the suitable rubber compositions disclosed herein fall within the claimed glass transition range.

[0032] eBR is a homopolymer of butadiene units that have polymerized and that has then been functionalized with an epoxy functional group as explained above. As in the case of the butadiene portion of the eSBR, the eBR T_g decreases with increased levels of the *cis*-form microstructure and increases with increased levels of the *vinyl*-form. In particular embodiments, for example, the *cis*-form content of the eBR is in excess of 50 mol%. While the microstructure of the eBR can be adjusted to provide improvements to the properties of the elastomer, the invention requires that the low T_g eBR elastomers that are included in the suitable rubber compositions disclosed herein fall within the claimed glass transition range.

[0033] Particular embodiments of the suitable rubber compositions useful for tire treads disclosed herein include between 70 phr and 100 phr of the low T_g epoxidized rubber component. Alternatively the rubber compositions may include between 80 phr and 100 phr of the low T_g epoxidized rubber component, between 85 phr and 100 phr, between 90 phr and 100 phr or greater than 90 phr of the rubber component. Particular embodiments may include less than 100 phr of the low T_g epoxidized rubber component such as between 80 phr and 95 phr, between 85 phr and 95 phr or between 90 phr and 95 phr. Particular embodiments include 100 phr of the low T_g epoxidized rubber component.

[0034] Alternatively, in those particular embodiments wherein the rubber composition includes a second rubber component of a polybutadiene (BR) and/or styrene-butadiene rubber (SBR) rubber in addition to the modified rubber component and the efficient plasticizing resin, then the most basic requirement of such embodiments merely requires that some amount of both the low T_g modified rubber component and the BR and/or SBR component be included in the rubber composition. Alternatively the rubber composition may include between 10 phr and 95 phr of the modified rubber component, or between 50 phr and 95 phr, between 25 phr and 95 phr, between 10 phr and 90 phr, between 50 phr and 90 phr, between 25 phr and 90 phr, between 10 phr and less than 70 phr, between 25 phr and less than 70 phr or between 50 phr and less than 70 phr of the modified rubber component. Likewise such rubber compositions may alternatively

include between 5 phr and 90 phr of the second rubber component of BR and/or SBR or between 5 phr and 50 phr, between 5 phr and 75 phr, between 10 phr and 90 phr, between 10 phr and 50 phr, between 10 phr and 75 phr, between greater than 30 phr and 90 phr, between greater than 30 phr and 75 phr or between greater than 30 phr and 50 phr of the BR and/or SBR rubber second rubber component.

[0035] Particular embodiments of those that include both the modified rubber component and the second rubber component of SBR and/or BR rubber, the SBR/BR second rubber component may include only BR, only SBR or combinations of both BR and SBR in any ratio. In particular embodiments of the rubber compositions that include the SBR/BR second rubber component, optionally there can be no natural rubber (NR) as an additional rubber component included in the rubber compositions or alternatively no more than 5 phr of NR. In other embodiments there optionally can be no isoprene/styrene copolymers (SIR) and isoprene/butadiene/styrene copolymers (SBIR) as additional rubber components, either separately or in combination with one another or alternatively no more than 5 phr of any one of them or combination thereof. The presence of such additional rubber components may interfere with or marginalize the desired properties being sought in particular embodiments. Optionally, in particular embodiments, there can be no other additional rubber component other than the epoxidized rubber component and the SBR and/or BR second rubber component.

[0036] Of course as indicated above, particular embodiments of the rubber compositions disclosed herein may be limited to having only the eBR and/or eSBR as the low Tg modified rubber component.

[0037] Particular embodiments of the suitable rubber compositions disclosed herein may include as the low Tg epoxidized rubber component only eBR, only eSBR or combinations of both eBR and SBR in any ratio. In those embodiments that include both eBR and eSBR, some embodiments may be limited to including eBR in a majority amount or alternatively in amount greater than 60 % of the total phr of the eBR and the SBR in the rubber composition or at least 75 % or at least 90 % of such total phr.

[0038] In addition to the low Tg epoxidized eBR and/or eSBR, particular embodiments of the rubber compositions disclosed herein may include one or more additional diene rubber components. Such diene elastomers are understood to be those elastomers resulting at least in

part, *i.e.*, a homopolymer or a copolymer, from diene monomers, *i.e.*, monomers having two double carbon-carbon bonds, whether conjugated or not.

[0039] While particular embodiments of the rubber compositions disclosed herein include only the low Tg epoxidized rubber components discussed above, others may additionally include such diene elastomers capped at an amount of no more than 30 phr or alternatively, no more than 25 phr, no more than 20 phr, no more than 10 phr or no more than 5 phr of such additional diene elastomers. Particular embodiments of such rubber compositions may include a lower limit for each of these caps of 0 phr and others may include a lower limit of 5 phr of such additional diene elastomers.

[0040] These additional diene elastomers may be classified as either “essentially unsaturated” diene elastomers or “essentially saturated” diene elastomers. As used herein, essentially unsaturated diene elastomers are diene elastomers resulting at least in part from conjugated diene monomers, the essentially unsaturated diene elastomers having a content of such members or units of diene origin (conjugated dienes) that is at least 15 mol. %. Within the category of essentially unsaturated diene elastomers are highly unsaturated diene elastomers, which are diene elastomers having a content of units of diene origin (conjugated diene) that is greater than 50 mol. %.

[0041] Those diene elastomers that do not fall into the definition of being essentially unsaturated are, therefore, the essentially saturated diene elastomers. Such elastomers include, for example, butyl rubbers and copolymers of dienes and of alpha-olefins of the EPDM type. These diene elastomers have low or very low content of units of diene origin (conjugated dienes), such content being less than 15 mol. %. Particular embodiments of the present invention exclude any additional diene elastomers that are essentially saturated.

[0042] Suitable elastomers that may be included as additional elastomers in the rubber compositions disclosed herein in addition to the eBR and eSBR include, for example, one or more highly unsaturated elastomers such as polybutadienes (BR), polyisoprenes (IR), natural rubber (NR), butadiene copolymers, isoprene copolymers and mixtures of these elastomers. Such copolymers include, for example, butadiene/styrene copolymers (SBR), isoprene/butadiene copolymers (BIR), isoprene/styrene copolymers (SIR) and isoprene/butadiene/styrene

copolymers (SBIR). Particular embodiments of the present invention are limited only to highly unsaturated diene elastomers as useful additional elastomers.

[0043] In addition to the elastomers described above, particular embodiments of the present invention include an efficient plasticizing resin. An efficient plasticizing resin is one that when mixed in an amount of 67 phr with just the low Tg epoxidized rubber component, results in a mixture having a Tg that is at least 14 °C higher than the Tg of the epoxidized rubber component. Such plasticizing resins are typically compatible with the rubber composition; that is, they are miscible with the rubber composition. If the plasticizing resin is not compatible, then a determination of the Tg using DSC in accordance with ASTM D3418 will have Tg peaks representing the rubber blend as well as the resin itself. If the resin is compatible, then there will be but one peak for the rubber composition.

[0044] Table 1 demonstrates how some plasticizing resins are efficient plasticizing resins for some levels of epoxy functionality but not at others. Some are not efficient plasticizing resins with BR having no epoxy functionality but become efficient with at least some of the epoxy functionality levels.

Table 1 – Change in Tg of BR at Various Epoxy Functionality Levels

Plasticizer			Change in Tg of BR Mixture with 67 phr of Plasticizer, °C			
Name	Type	Tg, °C	0 mol% X	5 mol% X	12.5 mol% X	20 mol % X
BPH	antioxidant	16			18	21
C30	Coumarone-Indene	-16			19	
Colophane	Pine rosin	52		12	19	
Dertophene 1510	Terpene Phenolic	108		23	31	
Dertophene H150	Terpene Phenolic	74	4	16	38	34
Dertophene T115	Terpene Phenolic	74		16	18	
Dertophene T135	Terpene Phenolic	85			23	
Escorez 5690	Cycloaliphatic	38	14			
Oppera	Hydrocarbon Resin	44	12		14	3
Resin- OPFT	Octylphenol formaldehyde	52		9	17	
Sylvares 600	AMS phenolic	47			20	
Sylvares TP2019	Terpene Phenolic	74	12	19	17	
Sylvares TP2040	Terpene Phenolic	74	4	15	36	36
Sylvares TP300	Terpene Phenolic	68			35	32
Sylvatac RE40	Terpene Phenolic	-5		10	15	
Uni-Rez TP115	polyamide	64		14	20	

[0045] For example, as may be seen in Table 1, the Oppera plasticizer (modified aliphatic hydrocarbon resin available from ExxonMobil) is demonstrated as an efficient resin

only when mixed with the BR having 12.5 mol% epoxy functionality and not with the non-functionalized BR nor with the 20 mol% functionalization. BPH is the well-known antioxidant 2,2'-methylene-bis(4-methyl-6-tert-butyl)-phenol and is a useful efficient plasticizing resin at least for the BR having the 12.5 mol% epoxy functionality.

[0046] Other useful efficient plasticizing resins include the SYLVARES 600 resin (M_n 850 g/mol; I_p 1.4; T_g 47° C.; HN of 31 mg KOH/g) that is an octyl phenol-modified copolymer of styrene and alpha methyl styrene as well as the coumarone-indene resins.

[0047] As may be noted, the terpene phenolic resins are especially useful as a class for providing efficient plasticizing resins. Terpene phenolic resins are well known and are produced by the copolymerization of terpene monomers and phenol. As is known, terpene monomers include alpha-pinene, beta-pinene and limonene monomers, with the limonene monomers existing in three possible isomers: L-limonene (laevorotatory enantiomer), D limonene (dextrorotatory enantiomer) or else dipentene, the racemate of the dextrorotatory and laevorotatory enantiomers. Useful terpene phenolic resins may be those that include the copolymerization of the monomers selected from alpha-pinene, beta-pinene, limonene monomers or combinations thereof with phenol. These types of resins are sometimes known as phenol modified terpene resins.

[0048] The degree of polarity of the terpene phenolic resins is determined by the number of hydroxyl groups contained within the resin. The higher the hydroxyl content, the greater the polarity of the terpene phenolic resin. The hydroxyl number of the resin is the amount, in milligrams, of potassium hydroxide equivalent to the hydroxyl groups in a 1 g sample of the resin and is, therefore, a measure of the concentration of hydroxyl groups in the resin. It is determined in known manner in accordance with ASTM E222. Particular embodiments have resins having a hydroxyl number that is at least 30 mg KOH/g or alternatively at least 50 mg KOH/g.

[0049] Terpene phenolic resins are available on the market from, for example, Arizona Chemical having offices in Savannah, GA. Arizona Chemical markets a range of terpene phenolic resins under the name SYLVARES with varying softening points (SP), glass transition temperatures (T_g) hydroxyl numbers (HN), number-average molecular masses (M_n) and polydispersity indices (I_p), examples of which include: SYLVARES TP105 (SP: 105 °C; T_g :

55 °C; HN: 40; Mn: 540; Ip:1.5); SYLVARES TP115 (SP: 115 °C; Tg: 55 °C; HN: 50; Mn: 530; Ip:1.3); and SYLVARES TP2040 (SP: 125 °C; Tg: 80 °C; HN: 135-150; Mn: 600; Ip:1.3).

[0050] Particular embodiments of the useful rubber compositions disclosed herein may include between 30 phr and 150 phr or 40 phr and 150 phr of the efficient plasticizing resin or alternatively between 50 phr and 150 phr or between 60 phr and 100 phr of the resin. In particular embodiments the amount of efficient plasticizing resin that is added is an amount that adjusts the glass transition temperature of the final rubber composition to between -35 °C and 0 °C as may be desired for the a tread designed for a particular season. For example the efficient resin may be added in an amount sufficient to adjust the Tg of the rubber compositions around the broad range mentioned above to provide a Tg of between -35 °C and -25 °C for winter tires, between -30 °C and -17 °C for all-season tires and between -17 °C and 0 °C for summer tires.

[0051] It is recognized that in some rubber compositions that include the eBR and/or the eSBR, the amount of the efficient resin added to the rubber composition may result in the Tg of the rubber composition being higher than the target for the particular use. Therefore, in particular embodiments, an additional plasticizer, such as a low Tg resin other than an efficient plasticizing resin may be used to lower the Tg to the target or to adjust another performance characteristic for the tread to be formed from the rubber composition. Such plasticizers may include other resins or may include a plasticizing oil as are well known to those having ordinary skill in the art. Such additional plasticizer may be added in an amount of between 0 phr and 60 phr or alternatively between 0 and 40 phr, between 1 phr and 30 phr or between 5 phr and 15 phr or 0 phr.

[0052] In addition to the elastomers, the efficient plasticizing resins and other plasticizers disclosed above, particular embodiments of the rubber compositions that are useful for treads disclosed herein may further include a reinforcing filler. Reinforcing fillers are added to rubber compositions to, *inter alia*, improve their tensile strength and wear resistance. Any suitable reinforcing filler may be suitable for use in compositions disclosed herein including, for example, carbon blacks and/or inorganic reinforcing fillers such as silica, with which a coupling agent is typically associated.

[0053] It should be noted that particular embodiments of the rubber compositions disclosed herein may include no carbon black or alternatively, very little carbon black such as,

for example, between 0.5 phr and 15 phr of carbon black or between 0.5 phr and 10 phr of carbon black. For those embodiments that contain carbon black, suitable carbon blacks include, for example, those of the type HAF, ISAF and SAF, conventionally used in tires. Reinforcing blacks of ASTM grade series 100, 200 and/or 300 are suitable such as, for example, the blacks N115, N134, N234, N330, N339, N347, N375 or alternatively, depending on the intended application, blacks of higher ASTM grade series such as N660, N683 and N772.

[0054] Inorganic reinforcing fillers include any inorganic or mineral fillers, whatever its color or origin (natural or synthetic), that are capable without any other means, other than an intermediate coupling agent, of reinforcing a rubber composition intended for the manufacture of tires. Such inorganic reinforcing fillers can replace conventional tire-grade carbon blacks, in whole or in part, in a rubber composition intended for the manufacture of tires. Typically such fillers may be characterized as having the presence of hydroxyl (-OH) groups on its surface.

[0055] Inorganic reinforcing fillers may take many useful forms including, for example, as powder, microbeads, granules, balls and/or any other suitable form as well as mixtures thereof. Examples of suitable inorganic reinforcing fillers include mineral fillers of the siliceous type, such as silica (SiO_2), of the aluminous type, such as alumina (AlO_3) or combinations thereof.

[0056] Useful silica reinforcing fillers known in the art include fumed, precipitated and/or highly dispersible silica (known as "HD" silica). Examples of highly dispersible silicas include Ultrasil 7000 and Ultrasil 7005 from Degussa, the silicas Zeosil 1165MP, 1135MP and 1115MP from Rhodia, the silica Hi-Sil EZ150G from PPG and the silicas Zeopol 8715, 8745 and 8755 from Huber. In particular embodiments, the silica may have a BET surface area, for example, of between $60 \text{ m}^2/\text{g}$ and $400 \text{ m}^2/\text{g}$ or alternatively between $80 \text{ m}^2/\text{g}$ and $300 \text{ m}^2/\text{g}$.

[0057] For coupling the inorganic reinforcing filler to the diene elastomer, a coupling agent that is at least bifunctional provides a sufficient chemical and/or physical connection between the inorganic reinforcement filler and the diene elastomer. Examples of such coupling agents include bifunctional organosilanes or polyorganosiloxanes. Such coupling agents and their use are well known in the art. The coupling agent may optionally be grafted beforehand onto the diene elastomer or onto the inorganic reinforcing filler as is known. Otherwise it may be mixed into the rubber composition in its free or non-grafted state. One useful coupling agent

is X50-S, a 50-50 blend by weight of Si69 (the active ingredient, bis-(triethoxysilylpropyl) tetrasulfide, abbreviated to TESPT) and N330 carbon black, available from Evonik. Another useful example of silane polysulfides useful as coupling agents include bis-(triethoxysilylpropyl) disulfide, abbreviated to TESPd.

[0058] In the rubber compositions according to the invention, the coupling agent may be included at any suitable amount for the given application, examples of which are between 2 phr and 20 phr or alternatively, between 2 phr and 15 phr or between 4 phr and 12 phr. It is generally desirable to minimize its use. In particular embodiments, the amount of coupling agent may represent between 0.5 and 15 wt. % relative to the total weight of the silica filler. In the case for example of tire treads for passenger vehicles, the coupling agent may be less than 12 wt. % or even less than 8 wt. % relative to the total weight of the silica filler.

[0059] In particular embodiments, the amount of total reinforcing filler (carbon black (if used) and/or reinforcing inorganic filler) may include any suitable amount for the given application, examples of which are between 40 phr and 180 phr or alternatively between 50 phr and 150 phr, between 50 phr and 130 phr, between 50 phr and 110 phr or between 60 phr and 120 phr of reinforcing filler.

[0060] The rubber compositions disclosed herein may be cured with any suitable curing system including a peroxide curing system or a sulfur curing system. Particular embodiments are cured with a sulfur curing system that includes free sulfur and may further include, for example, one or more of accelerators, stearic acid and zinc oxide. Suitable free sulfur includes, for example, pulverized sulfur, rubber maker's sulfur, commercial sulfur, and insoluble sulfur. The amount of free sulfur included in the rubber composition is not limited and may range, for example, between 0.4 phr and 10 phr or alternatively between 0.4 phr and 5 phr or between 0.5 phr and 2 phr. Particular embodiments may include no free sulfur added in the curing system but instead include sulfur donors.

[0061] Accelerators are used to control the time and/or temperature required for vulcanization and to improve the properties of the cured rubber composition. Particular embodiments of the present invention include one or more accelerators. One example of a suitable primary accelerator useful in the present invention is a sulfenamide. Examples of suitable sulfenamide accelerators include n-cyclohexyl -2-benzothiazole sulfenamide (CBS), N-

tert-butyl-2-benzothiazole Sulfenamide (TBBS), N-Oxydiethyl-2-benzthiazolsulfenamid (MBS) and N'-dicyclohexyl-2-benzothiazolesulfenamide (DCBS). Combinations of accelerators are often useful to improve the properties of the cured rubber composition and the particular embodiments include the addition of secondary accelerators.

[0062] Particular embodiments may include as a secondary accelerant the use of a moderately fast accelerator such as, for example, diphenylguanidine (DPG), triphenyl guanidine (TPG), diorthotolyl guanidine (DOTG), o-tolylbigaunide (OTBG) or hexamethylene tetramine (HMTA).

[0063] Without limiting the invention, such accelerators may be added in an amount of up to 10 phr, between 0.5 and 5 phr, between 0.5 and 2.5 phr or between 1 and 4.5 phr. Particular embodiments may exclude the use of fast accelerators and/or ultra-fast accelerators such as, for example, the fast accelerators: disulfides and benzothiazoles; and the ultra-accelerators: thiurams, xanthates, dithiocarbamates and dithiophosphates.

[0064] Other additives can be added to the rubber compositions disclosed herein as known in the art. Such additives may include, for example, some or all of the following: antidegradants, antioxidants, fatty acids, waxes, stearic acid and zinc oxide. Examples of antidegradants and antioxidants include 6PPD, 77PD, IPPD and TMQ and may be added to rubber compositions in an amount, for example, of from 0.5 phr and 5 phr. Zinc oxide may be added in an amount, for example, of between 1 phr and 6 phr or alternatively, of between 1.5 phr and 4 phr. Waxes may be added in an amount, for example, of between 0.5 phr and 5 phr.

[0065] The rubber compositions that are embodiments of the present invention may be produced in suitable mixers, in a manner known to those having ordinary skill in the art, typically using two successive preparation phases, a first phase of thermo-mechanical working at high temperature, followed by a second phase of mechanical working at lower temperature.

[0066] The first phase of thermo-mechanical working (sometimes referred to as "non-productive" phase) is intended to mix thoroughly, by kneading, the various ingredients of the composition, with the exception of the vulcanization system. It is carried out in a suitable kneading device, such as an internal mixer or an extruder, until, under the action of the mechanical working and the high shearing imposed on the mixture, a maximum temperature generally between 110° C and 190° C, more narrowly between 130° C and 170° C, is reached.

[0067] After cooling of the mixture, a second phase of mechanical working is implemented at a lower temperature. Sometimes referred to as "productive" phase, this finishing phase consists of incorporating by mixing the vulcanization (or cross-linking) system (sulfur or other vulcanizing agent and accelerator(s)), in a suitable device, for example an open mill. It is performed for an appropriate time (typically between 1 and 30 minutes, for example between 2 and 15 minutes) and at a sufficiently low temperature lower than the vulcanization temperature of the mixture, so as to protect against premature vulcanization.

[0068] The rubber composition can be formed into useful articles, including treads for use on vehicle tires. Articles may be formed, for example, by extrusion or by placing the rubber in a mold and molding the rubber article. Tire treads may, for example, be formed by extrusion as tread bands or may be cured in a mold and then later made a part of a tire. Alternatively they be formed directly onto a tire carcass by, for example, extrusion and then cured in a mold.

[0069] The invention is further illustrated by the following examples, which are to be regarded only as illustrations and not delimitative of the invention in any way. The properties of the compositions disclosed in the examples were evaluated as described below and these utilized methods are suitable for measurement of the claimed properties of the claimed invention.

[0070] Modulus of elongation (MPa) was measured at 10% (MA10) at a temperature of 23 °C based on ASTM Standard D412 on dumb bell test pieces. The measurements were taken in the second elongation; *i.e.*, after an accommodation cycle. These measurements are secant moduli in MPa, based on the original cross section of the test piece.

[0071] Mooney viscosity (ML 1+4) was measured in accordance with ASTM Standard D1646-04. In general, the composition in an uncured state is molded in a cylindrical enclosure and heated to 100 °C. After 1 minute of preheating, the rotor turns within the test sample at 2 rpm, and the torque used for maintaining this movement is measured after 4 minutes of rotation. The Mooney viscosity is expressed in "Mooney units" (MU, with 1 MU=0.83 Newton-meter).

[0072] Hysteresis losses (HL) were measured in percent by rebound at 60 °C at the sixth impact in accordance with the following equation:

$$HL(\%)=100(W_0-W_1)/W_1,$$

where W_0 is the energy supplied and W_1 is the energy restored.

[0073] Dynamic properties (T_g and G^*) for the rubber compositions were measured on a Metravib Model VA400 ViscoAnalyzer Test System in accordance with ASTM D5992-96. The response of a sample of vulcanized material (double shear geometry with each of the two 10 mm diameter cylindrical samples being 2 mm thick) was recorded as it was being subjected to an alternating single sinusoidal shearing stress of a constant 0.7 MPa and at a frequency of 10 Hz over a temperature sweep from -80° C to 100° C with the temperature increasing at a rate of 1.5° C/min. The shear modulus G^* was captured at 60° C and the temperature at which the max tan delta occurred was record as the glass transition temperature, T_g . The tan delta at 0° C was also recorded as a useful predictor of wet traction with a higher tan delta at 0° C measurement indicating an improved performance in traction performance.

[0074] The mole percent of the epoxide functional group was determined by NMR characterization. First a 25 mg sample of the epoxidized elastomer is dissolved in 1 mL of deuterated chloroform ($CDCl_3$). The NMR analyses were performed on a 500MHz Bruker Spectrometer equipped with a 5mm Broad Band Cryoprobe. The sequence used was a quantitative 30 degrees 1H simple impulsion with a recycle delay of 5 seconds. The spectral width was 12 ppm and the number of scans was 64. Calibration was carried out at 7.20 ppm on the $CHCl_3$ signal. Acquisition parameters were adjusted to obtain a full spectrum without FID truncation.

[0075] The 1H NMR Spectrum shows the characteristic signal of the $CH=CH$ of BR1-4 ($\delta=5.32$ ppm) and the $CH-CH$ of epoxidized BR1-4 ($\delta=2.86$ ppm). A small signal at 2.63 ppm is also attributed to epoxidized BR. These attributions were confirmed by 2D NMR 1H - ^{13}C HSQC and HMBC.

[0076] The 1H NMR spectrum makes it possible to quantify the functional group by integration of the signal characteristic of the protons of the epoxidized group situated in the vicinity of $\delta=2.86$ ppm. The 1H NMR technique was used to determine the microstructure of the elastomers obtained.

[0077] The molar ratio was estimated with the ratio of each pattern on the total according to the following calculation:

$$\%Epoxy = \frac{1H(Epoxy)}{1H(BR1-4)+1H(Epoxy)}.$$

[0078] The macrostructure of the epoxidized BR was determined by Size Exclusion Chromatography (SEC) characterization. The polymer was solubilized in THF at a concentration of 1 g/l. A volume of 100 μ l was injected after filtration over 0.45 μ m filters, through a set of SEC columns (« STYRAGEL HMW7 », « STYRAGEL HMW6E » and 2 « STYRAGEL HT6E » columns, apparatus « WATERS alliance »). The mobile phase flow was 0.7 ml/min. The columns were thermostated in an oven at 35° C. The detection is made by a thermostated refractometer at 35° C. The stationary phase is constituted of a copolymer of polystyrene/divinylbenzene at a controlled porosity. The Moore calibration curve is previously made with polystyrene standards.

[0079] Tire wear was measured by running the tires on a predetermined circuit over a varying public road surfaces in the Greenville SC area. The tread depth was measured at the start and was measured again after the same number of miles for the tires being compared, typically between 5000 miles and 8000 miles. The difference between the tread depths was the measurement of the wear.

Example 1

[0080] Rubber compositions were prepared using the components shown in Table 2. The amount of each component making up the rubber compositions shown in Table 2 are provided in parts per hundred parts of rubber by weight (phr). The percent epoxidation of the rubber component is also shown in Table 2 as either 5 mol% or 12.5 mol%.

[0081] The silica was Sil160 from Rhodia. The C30 was NOVARES C30 (coumarone-indene resin; softening point: 20 to 30° C.) from Rutgers Chemicals. Dertophene H150 was a terpene phenolic resin from DRT having a softening point of 118 °C and hydroxyl value of between 156-170 and an Mn of 579 and an Ip of 1.18. The SYLVARES TP2040 was a terpene phenolic resin with a softening point of 125 °C, a Tg of 74 °C, a hydroxyl value of between 141-160, an Mn of 608 and an Ip of 1.3. The SYLVARES TP2019 was a terpene phenolic resin with a softening point of 125 °C, a Tg of 73 °C, a hydroxyl value of between 70 and 80, an Mn of 657 g/mol and an Ip of 1.34.

[0082] The HTO was the sunflower oil AGRI-PURE 80 having a high oleic acid content of between 70 wt% and 80 wt%, available from Cargill.

[0083] The rubber formulations were prepared by mixing the components given in Table 2, except for the accelerators and sulfur, in a Banbury mixer until a temperature of between 110 °C and 190 °C was reached. The accelerators and sulfur were added in the second phase on a mill. Vulcanization was effected at 150 °C for 40 minutes. The formulations were then tested to measure their properties, the results of which are shown in Table 2.

Table 2 – Formulations and Properties

Formulations	F1	F2	F3	F4	F5
eBR 5 mol%	100			100	
eBR 12.5 mol%		100	100		100
N234	6.56	8.56	8.56	97	97
Sil160	104	100	100		
Si69 coupling agent	8.32	8	8		
C30	22			4	16
TP2040	51		63		
Dertophene H150		73			
TP2019				64	67
HTO			10		
6PPD	2	1.9	1.9	2	2
Wax	1.5	1.5	1.5	1.5	1.5
DPG	1.7	1.7	1.7		
SAD	2	2	2	2	2
ZnO	1.5	1.5	1.5	1.5	1.5
CBS	3.86	3.86	3.86	1.5	1.5
S	0.83	0.83	0.83	1.5	1.5
Physical Properties					
T _g , °C	-19	-8	-22	-25	-21
G* at 60 °C	1.1	1.8	2.3	1.1	1.4

Example 2

[0084] This example provides a procedure for making epoxidized BR. A solution of BR at 5wt% in toluene was prepared by dissolving 8.4 kg of BR in 175.3L of toluene. 809.8 g of formic acid (purity>98%) was added in the reactor under a sustained stirring. The reactor was then heated up to 50° C. After the temperature was reached, 2.12 L of H₂O₂ solution (solution at 35wt% in water) was added to the reaction mixture. The temperature was kept at 50° C during 4 hours at a stirring of 200 RPM.

[0085] At the end of the reaction, the temperature was decreased to 30° C. Then, formic acid was neutralized with a NaOH solution at 2.5M (1.01eq) to obtain a pH of around 10. The contact time for the neutralization was at least 30 minutes.

[0086] Antioxidants (4,4'-methylene-bis-2,6-tert-butylphénol / N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine: 1/1) are added to the epoxidized BR solution at a rate of 0.5g for 100g of elastomer. The contact time was at least 15 minutes. After, the epoxidized BR solution was stripped and dried.

[0087] The epoxide quantity, as obtained by NMR as described above, is 12.5 mol% +/- 0.5 mol%. The yield of the chemical modification is 95 wt%. The macrostructure of the epoxidized BR is the following: Mn=232940 g/mol; Mw=533348 g/mol and Ip=2.29 as determined by SEC as described above.

Example 3

[0088] This example provides a demonstration of the improved wear that may be obtained in an example of the rubber compositions disclosed herein. Rubber compositions were prepared using the components shown in Table 3. The amount of each component making up the rubber compositions shown in Table 3 are provided in parts per hundred parts of rubber by weight (phr). The eBR was had a epoxide content of 12.5 mol%.

[0089] The silica was a 50-50 mix of Solvay ZEOSIL 1165, a micoperle silica having a BET of 160 m²/g and a CTAB of 157 m²/g and Evonik ULTRASIL 7000, a granuele silica having a BET of 175 m²/g and a CTAB of 160 m²/g. The low Tg resin was NOVARES C30 (coumarone-indene resin; softening point: 20 to 30° C; Tg: -16° C) from Rutgers Chemicals.

[0090] The high Tg resin used in the F6 formulation was SYLVARES TP115, a terpene phenolic resin with a softening point of 115 °C, a Tg of 60 °C, a hydroxyl value of between 25 and 35, an Mn of 575 g/mol and an Ip of 1.3. The high Tg resin used in the W1 formulation was ESCOREZ 5600, a aromatic modified, cycloaliphatic hydrocarbon resin with a softening point of 103 ° C, a Tg of 55 ° C and an Mn of 500 g/mol.

[0091] The HTO was the sunflower oil AGRI-PURE 80 having a high oleic acid content of between 70 wt% and 80 wt%, available from Cargill. The cure and antidegradant packages contained the typical components such as sulfur, accelerators, zinc oxide, stearic acid, 6ppd and so forth. The silol coupling agent was bis(3-hydroxydimethylsilyl)propyl tetrasulfide that is known and its various forms and methods of making are fully disclosed in US Patent 6,774,255.

[0092] The rubber formulations were prepared by mixing the components given in Table 2, except for the accelerators and sulfur, in a Banbury mixer until a temperature of between 110 °C and 190 °C was reached. The accelerators and sulfur were added in the second phase on a mill. Vulcanization was effected at 150 °C for 40 minutes. The formulations were then tested to measure their properties, the results of which are shown in Table 2.

Table 3

Formulations	W1	F6
SBR	100	
eBR 12.5 mol%		100
Carbon Black N234	4	4
Sil160/165	110	110
Si69 coupling agent	11	
Silol coupling agent		7.4
High Tg Resin	60	76
Low Tg Resin		3
HTO	12	0
Antidegradants Pkg	8	8
Cure Pkg	9.5	11
Physical Properties		
Tg, °C	-15	-13
G* at 60 °C	1.0	0.9
G* 10%	2.0	1.9
Tire Results		
Wear	100	119

[0093] As can be seen in tire results, the wear improved significantly between the tires having treads with the W1 rubber composition and the inventive F6 rubber composition.

Example 4

[0094] Rubber compositions were prepared using the components shown in Tables 4. The amount of each component making up the rubber compositions shown in Tables 4 are provided in parts per hundred parts of rubber by weight (phr). The percent epoxidation of the rubber component is also shown in Table 4 as either 5 mol% or 12.5 mol%.

[0095] The silica was Sil160 from Rhodia. The resins included C30, Oppera and TP2019. The C30 was a low-Tg resin NOVARES C30 (coumarone-indene resin; softening point: 20 to 30° C; Tg: -16° C.) from Rutgers Chemicals. The SYLVARES TP2019 was a terpene phenolic resin with a softening point of 125 °C, a Tg of 73 °C, a hydroxyl value of between 70 and 80, an Mn of 657 g/mol and an Ip of 1.34. The Oppera from ExxonMobil was a

dicyclopentadiene based resin with a softening point of 103 ° C, a Tg of 45 ° C a hydroxyl value of 0 and an Mn of 480 g/mole. High Tg resins are typically considered those that have a Tg of at least 25° C. The HTO was the sunflower oil AGRI-PURE 80 having a high oleic acid content of between 70 wt% and 80 wt%, available from Cargill.

[0096] The rubber formulations were prepared by mixing the components given in Table 3, except for the accelerators and sulfur, in a Banbury mixer until a temperature of between 110 °C and 190 °C was reached. The accelerators and sulfur were added in the second phase on a mill. Vulcanization was effected at 150 °C for 40 minutes. The formulations were then tested to measure their properties, the results of which are shown in Table 3.

[0097] Tires were also manufactured using the formulations below and tested for wear. The wear properties of the tires are shown in Table 3.

Table 4 – Formulations and Properties

Formulations	W2	F7	F8A	F8B
BR	43		30	
SBR	57			30
eBR 5 mol%		100	70	70
Carbon Black N234	7	7	7	7
Sil160	104	104	104	104
Si69 coupling agent	8	8	8	8
High Tg Resin	41	68	64	33
Low Tg Resin		10	15	42
HTO	16	0	0	0
Antidegradants Pkg	5	3.5	3.5	3.5
Cure Pkg	8.5	10	10	10
Physical Properties				
Tg, °C	-22	-22	-20	-24
G* at 60 °C	1.1	1.0	1.1	2
G* 10%	2.3	2.1	2.2	1
Tire Properties				
Wear	100	107	109	107

[0098] As may be seen in the results, the wear of tires made with both F7 and F8A, B improved significantly over the witness tire that had no epoxidized rubber component and, when BR was added in F8A, there was a slight improvement in wear and even more surprisingly, when the SBR was added in F8B, there was no significant decrease in wear which would have been expected.

Example 5

[0099] This example illustrates the surprising effect of adding BR to a rubber composition having epoxidized BR or epoxidized SBR included. Rubber compositions were prepared using the components shown in Table 5. The amount of each component making up the rubber compositions shown in Table 5 are provided in parts per hundred parts of rubber by weight (phr).

[00100] Table 6 and Table 7 provide the makeup of the rubber compositions expressed as 100 phr in Table 5. The rubber compositions were prepared similarly to those in the examples above and then tested to measure their properties, the results of which are shown in Table 6 and in Table 7. The SBR used in the rubber compositions of Table 6 was an SBR functionalized at the chain end with a silanol functional unit with 27 % styrene and a Tg of -48 °C.

[00101] The SYLVARES TP115 was a terpene phenolic resin with a softening point of 115 °C, a Tg of 60 °C, a hydroxyl value of between 25 and 35, an Mn of 575 g/mol and an Ip of 1.3. The SYLVARES TP2019 was a terpene phenolic resin with a softening point of 125 °C, a Tg of 73 °C, a hydroxyl value of between 70 and 80, an Mn of 657 g/mol and an Ip of 1.34.

Table 5 – Base Rubber Composition

Formulations	Base
Rubber*	100
Carbon Black	7
Sil160	104
Si69 coupling agent	8.3
Resin*	73 / 80
Antidegradants Pkg	3.5
Cure Pkg	16

*See Table 5

Table 6 – Rubber Formulations Properties 5% eBR

Formulations	F9	F10	F11	F12	F13	F14	F15	F16
eBR 5 mol%	100	67	50	33	100	67	50	33
BR	0	33	50	67	0	0	0	0
SBR	0	0	0	0	0	33	50	67
TP Resin TP2019	73	73	73	73	73	73	73	73
Physical Properties								
Tg, °C	-17	-4	2	5	-30	-5	4	10
Tan Delta at 0 °C	0.57	0.68	0.73	0.71	0.38	0.76	0.83	0.76

Table 7 – Rubber Formulations Properties 12.5% eBR

Formulations	F17	F18	F19	F20	F21	F22	F23
eBR 12.5 mol%	100	67	50	33	25	15	7
BR	0	33	50	67	75	85	93
TP Resin TP115	80	80	80	80	80	80	80
Physical Properties							
Tg, °C	-18	-10	-4	2	8	10	0
Tan Delta at 0 °C	0.52	0.72	0.78	0.72	0.67	0.6	0.6

[00102] As may be seen from the results from Table 6, the addition of either BR or SBR to the rubber composition that included the epoxidized BR and the efficient plasticizing resin surprisingly provided a higher Tg of the rubber composition and provided a higher tan delta at 0° C, which indicates an improved wet traction performance. Note that in the results shown in both Table 6 and Table 7 that the tan delta at 0 ° C reached a maximum somewhere around 50 phr of BR or SBR being added to the rubber composition.

[00103] The terms “comprising,” “including,” and “having,” as used in the claims and specification herein, shall be considered as indicating an open group that may include other elements not specified. The term “consisting essentially of,” as used in the claims and specification herein, shall be considered as indicating a partially open group that may include other elements not specified, so long as those other elements do not materially alter the basic and novel characteristics of the claimed invention. The terms “a,” “an,” and the singular forms of words shall be taken to include the plural form of the same words, such that the terms mean that one or more of something is provided. The terms “at least one” and “one or more” are used interchangeably. The term “one” or “single” shall be used to indicate that one and only one of something is intended. Similarly, other specific integer values, such as “two,” are used when a specific number of things is intended. The terms “preferably,” “preferred,” “prefer,” “optionally,” “may,” and similar terms are used to indicate that an item, condition or step being referred to is an optional (not required) feature of the invention. Ranges that are described as being “between a and b” are inclusive of the values for “a” and “b.”

[00104] It should be understood from the foregoing description that various modifications and changes may be made to the embodiments of the present invention without departing from its true spirit. The foregoing description is provided for the purpose of illustration only and should not be construed in a limiting sense. Only the language of the following claims should limit the scope of this invention.

CLAIMS

What is claimed is:

1. A rubber composition that is based upon a cross-linkable elastomer composition, the cross-linkable elastomer composition comprising, per 100 parts by weight of rubber (phr):

a modified rubber component selected from a modified polybutadiene rubber, a modified styrene-butadiene rubber or combinations thereof, wherein the modified rubber component has been modified with a functional group having a heteroatom selected from oxygen, nitrogen, silicon or combinations thereof and wherein the modified rubber component has a Tg of between -80 °C and -110 °C;

a second rubber component selected from the group consisting of a polybutadiene rubber (BR), a styrene-butadiene rubber (SBR) and combinations thereof;

between 30 phr and 130 phr of an efficient plasticizing resin, wherein the efficient plasticizing resin is, when included in a mixture consisting of the modified rubber component and 67 phr of the efficient plasticizing resin, causes a Tg of the mixture to be at least 14° C higher than the Tg of the modified rubber component;

a reinforcement filler; and

a curing system.

2. The rubber composition of claim 1, wherein the functional group and the efficient plasticizing resin have a hydrogen bonding interaction and wherein a hydrogen bond acceptor atom is included in the functional group.

3. The rubber composition of claim 1 or claim 2, wherein the modified rubber component is epoxidized with the functional group being an epoxide and wherein the epoxidized rubber component is selected from epoxidized polybutadiene rubber (eBR), epoxidized styrene-butadiene rubber (eSBR) or combinations thereof.

4. The rubber composition of claim 3, wherein the epoxide content of the epoxidized rubber component is between 1 mol% and 25 mol%.

5. The rubber composition of claim 4, wherein the epoxide content of the epoxidized rubber component is between 3 mol% and 15 mol%.
6. The rubber composition of any of claims 3 through 4, wherein the epoxidized rubber component is the eBR.
7. The rubber composition of any of claims 3 through 4, wherein the epoxidized rubber component is the eSBR.
8. The rubber composition any of the preceding claims, wherein the modified rubber component is in an amount of between 10 phr and 95 phr.
9. The rubber composition of any of the preceding claims, wherein the modified rubber component is in an amount of between 25 phr and less than 90 phr.
10. The rubber composition of any of the preceding claims, wherein the second rubber component is in an amount of between 5 phr and 90 phr.
11. The rubber composition of claim 10, wherein the second rubber component is in an amount of between 10 phr and 75 phr.
12. The rubber composition of claim 10, wherein the second rubber component is in an amount of between greater than 30 phr and 90 phr.
13. The rubber composition of any of the preceding claims, wherein the second rubber component is BR.
14. The rubber composition of any of claims 1 through 12, wherein the second rubber component is SBR.
15. The rubber composition of any of the preceding claims, wherein a T_g of the rubber composition is between -35 °C and 0 °C.

16. The rubber composition of any of the preceding claims, wherein the rubber composition includes no other rubber components.
17. The rubber composition of any of the preceding claims, comprising between 40 phr and 130 phr of the efficient plasticizing resin.
18. The rubber composition of any of the preceding claims, wherein the efficient plasticizing resin is a terpene phenolic resin.
19. The rubber composition of any of claims 1 through 17, wherein the efficient plasticizing resin is a coumarone-indene resin.
20. The rubber composition of any of claims 1 through 17, wherein the efficient plasticizing resin is a polyamide resin.
21. The rubber composition of any of the preceding claims, wherein the reinforcement filler is silica.
22. A tire tread, comprising at least in part the rubber composition of any of claims 1 - 21.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2016/040254

A. CLASSIFICATION OF SUBJECT MATTER

INV. B60C1/00 C08C19/00 C08C19/06 C08C19/22 C08K5/00
C08L9/00 C08L9/06

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B60C C08C C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 2016/106408 A1 (MICHELIN & CIE [FR]; MICHELIN RECH TECH [CH]; MCDOWELL JESSICA [US]; S) 30 June 2016 (2016-06-30) claims 1-16 paragraph [0038] paragraph [0021] table 2	1-22
X	----- EP 2 853 558 A1 (CONTINENTAL REIFEN DEUTSCHLAND [DE]) 1 April 2015 (2015-04-01) paragraph [0001] - paragraph [0002] paragraph [0058] example E4; table 2 paragraph [0012] ----- -/-	1-22



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

31 January 2017

Date of mailing of the international search report

10/02/2017

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Laïb, Samia

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2016/040254

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2013/331498 A1 (MIYAZAKI TATSUYA [JP]) 12 December 2013 (2013-12-12) paragraph [0001] paragraph [0009] example 1; table 1 paragraph [0147] paragraph [0114] paragraph [0113] paragraph [0104] paragraph [0115] -----	1-22
A	US 2011/144236 A1 (MIHARA SATOSHI [JP]) 16 June 2011 (2011-06-16) paragraph [0003] paragraph [0007] paragraph [0009] paragraph [0042] paragraph [0053] example 3; table 1 -----	1-22
A	US 2014/187711 A1 (LUO STEVEN [US] ET AL) 3 July 2014 (2014-07-03) example 9; table 3 paragraph [0167] table 2 -----	1-22
A	JP 2014 205842 A (BRIDGESTONE CORP) 30 October 2014 (2014-10-30) example 11; table 1 paragraph [0091] paragraph [0001] -----	1-22
A	US 2013/324638 A1 (NAKA AYUMI [JP] ET AL) 5 December 2013 (2013-12-05) example comparative 4; table 2 paragraph [0117] paragraph [0087] - paragraph [0090] paragraph [0001] -----	1-22

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2016/040254

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2016106408 A1	30-06-2016	US 2016312015 A1 US 2016312016 A1 WO 2016106408 A1 WO 2016106409 A1	27-10-2016 27-10-2016 30-06-2016 30-06-2016
EP 2853558 A1	01-04-2015	CN 105579507 A EP 2853558 A1 US 2016194485 A1 WO 2015043902 A1	11-05-2016 01-04-2015 07-07-2016 02-04-2015
US 2013331498 A1	12-12-2013	CN 103483636 A JP 5650690 B2 JP 2013256585 A US 2013331498 A1	01-01-2014 07-01-2015 26-12-2013 12-12-2013
US 2011144236 A1	16-06-2011	CN 102093606 A DE 102010062557 A1 JP 4883172 B2 JP 2011122057 A US 2011144236 A1	15-06-2011 01-09-2011 22-02-2012 23-06-2011 16-06-2011
US 2014187711 A1	03-07-2014	NONE	
JP 2014205842 A	30-10-2014	JP 5914572 B2 JP 2014205842 A	11-05-2016 30-10-2014
US 2013324638 A1	05-12-2013	CN 103237842 A DE 112011104011 T5 JP 5240409 B2 US 2013324638 A1 WO 2012073838 A1	07-08-2013 29-08-2013 17-07-2013 05-12-2013 07-06-2012