

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2014239197 B2**

(54) Title
Color stable red-emitting phosphors

(51) International Patent Classification(s)
C09K 11/61 (2006.01)

(21) Application No: **2014239197** (22) Date of Filing: **2014.03.14**

(87) WIPO No: **WO14/152787**

(30) Priority Data

(31) Number	(32) Date	(33) Country
61/791,511	2013.03.15	US
14/208,592	2014.03.13	US

(43) Publication Date: **2014.09.25**

(44) Accepted Journal Date: **2017.02.02**

(71) Applicant(s)
General Electric Company

(72) Inventor(s)
Murphy, James Edward;Nammalwar, Prasanth Kumar;Karkada, Nagaveni;Lyons, Robert Joseph;Chowdhury, Ashfaqu Islam;Setlur, Anant Achyut;Garcia, Florencio;Beers, William Winder;Du, Fangming

(74) Agent / Attorney
Phillips Ormonde Fitzpatrick, PO Box 323, Collins Street West, VIC, 8007

(56) Related Art
US 2006/0169998 A1
US 8057706 B1
US 2010/0013373 A1



(43) International Publication Date
25 September 2014 (25.09.2014)

- (51) International Patent Classification:
C09K 11/61 (2006.01)
- (21) International Application Number:
PCT/US2014/027733
- (22) International Filing Date:
14 March 2014 (14.03.2014)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/791,511 15 March 2013 (15.03.2013) US
14/208,592 13 March 2014 (13.03.2014) US
- (71) Applicant: **GENERAL ELECTRIC COMPANY**
[US/US]; 1 River Road, Schenectady, NY 12345 (US).
- (72) Inventors: **MURPHY, James, Edward**; One Research Circle, Niskayuna, NY 12309-1027 (US). **NAMMALWAR, Prasanth, Kumar**; MRL, 122, Ph2, JFWTC, EPIP, Whitefield Road, Bangalor, Karnataka 560037 (IN). **KARKADA, Nagaveni**; JFWTC, Plot#122, EPIP, Phase 2, Whitefield Road, Bangalore, Karnataka 560066 (IN). **LYONS, Robert, Joseph**; MET 179, 1 Research Circle, Niskayuna, NY 12309 (US). **CHOWDHURY, Ashfaqul, Islam**; GE Consumer And Industrial - Lighting, 1975 Noble Road, Cleveland, OH 44112 (US). **SETLUR, Anant,**

Achyut; 1 Research Circle, K1-4A41, Niskayuna, NY 12309 (US). **GARCIA, Florencio**; 1 Research Circle, Niskayuna, NY 12309-1027 (US). **BEERS, William, Winder**; 1975 Noble Rd, Nela Park, Cleveland, OH 44112 (US). **DU, Fangming**; 1975 Noble Road, Cleveland, OH 44112 (US).

(74) Agents: **DIMAURO, Peter T.** et al.; General Electric Company, Global Patent Operation, 2 Corporate Drive, Suite 648, Shelton, CT 06484 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,

[Continued on next page]

(54) Title: COLOR STABLE RED-EMITTING PHOSPHORS




Fig. 1

(57) Abstract: A process for synthesizing a color stable Mn⁴⁺ doped phosphor includes contacting a precursor of formula I, in gaseous form at an elevated temperature with a fluorine-containing oxidizing agent to form the color stable Mn⁴⁺ doped phosphor A_x [MF_y]_z:Mn⁴⁺ (I), wherein A is Li, Na, K, Rb, Cs, NR₄ or a combination thereof; M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof; R is H, lower alkyl, or a combination thereof; x is the absolute value of the charge of the [MF_y]_z ion; and y is 5, 6 or 7.

WO 2014/152787 A1

TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

- *with international search report (Art. 21(3))*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

COLOR STABLE RED-EMITTING PHOSPHORS


BACKGROUND

[0001] Red-emitting phosphors based on complex fluoride materials activated by Mn^{4+} , such as those described in US 7,358,542, US 7,497,973, and US 7,648,649, can be utilized in combination with yellow/green emitting phosphors such as YAG:Ce or other garnet compositions to achieve warm white light (CCTs < 5000 K on the blackbody locus, color rendering index (CRI) > 80) from a blue LED, equivalent to that produced by current fluorescent, incandescent and halogen lamps. These materials absorb blue light strongly and efficiently emit between about 610-635 nm with little deep red/NIR emission. Therefore, luminous efficacy is maximized compared to red phosphors that have significant emission in the deeper red where eye sensitivity is poor. Quantum efficiency can exceed 85% under blue (440-460 nm) excitation.

[0002] While the efficacy and CRI of lighting systems using Mn^{4+} doped fluoride hosts can be quite high, one potential limitation is their susceptibility to degradation under high temperature and humidity (HTHH) conditions. It is possible to reduce this degradation using post-synthesis processing steps, as described in US 8,252,613. However, further improvement in stability of the materials is desirable.

BRIEF DESCRIPTION

[0003] Briefly, in accordance with a first aspect, the present invention relates to a process for synthesizing a color stable Mn^{4+} doped phosphor, the process comprising contacting a precursor of formula I,



at an elevated temperature with a fluorine-containing oxidizing agent in gaseous form to form the color stable Mn^{4+} doped phosphor;

wherein

A is Li, Na, K, Rb, Cs, NR_4 or a combination thereof;

M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof;

R is H, lower alkyl, or a combination thereof;

x is the absolute value of the charge of the $[MF_y]$ ion; and

y is 5, 6 or 7.

[0004] In accordance with a second aspect, the present invention relates to a lighting apparatus comprising a semiconductor light source; and a color stable Mn^{4+} doped phosphor prepared by a process according to the first aspect.

[0004a] In accordance with a third aspect, the present invention relates to a process for synthesizing a color stable Mn^{4+} doped phosphor the process comprising contacting a precursor at an elevated temperature with a fluorine-containing oxidizing agent in gaseous form to form the color stable Mn^{4+} doped phosphor, wherein the precursor is selected from the group consisting of

- (A) $A_2[MF_5]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Al, Ga, In, and combinations thereof;
- (B) $A_3[MF_6]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Al, Ga, In, and combinations thereof;
- (C) $Zn_2[MF_7]:Mn^{4+}$, where M is selected from Al, Ga, In, and combinations thereof;
- (D) $A[In_2F_7]:Mn^{4+}$ where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof;
- (E) $A_2[MF_6]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Ge, Si, Sn, Ti, Zr, and combinations thereof;
- (F) $E[MF_6]:Mn^{4+}$, where E is selected from Mg, Ca, Sr, Ba, Zn, and combinations thereof; and where M is selected from Ge, Si, Sn, Ti, Zr, and combinations thereof;
- (G) $Ba_{0.65}Zr_{0.35}F_{2.70}:Mn^{4+}$; and
- (H) $A_3[ZrF_7]:Mn^{4+}$ where A is selected from Li, Na, K, Rb, Cs, NH_4 ; and
- (I) combinations thereof.

[0004b] In accordance with a fourth aspect, the present invention relates to a lighting apparatus comprising a semiconductor light source; and a color stable Mn^{4+} doped phosphor prepared by a process according to the third aspect.

DRAWINGS

[0005] These and other features, aspects, and advantages of the present invention will become better understood when the following detailed description is read with reference to the accompanying drawings in which like characters represent like parts throughout the drawings, wherein:

[0006] FIG. 1 is a schematic cross-sectional view of a lighting apparatus in accordance with one embodiment of the invention;

[0007] FIG. 2 is a schematic cross-sectional view of a lighting apparatus in accordance with another embodiment of the invention;

[0008] FIG. 3 is a schematic cross-sectional view of a lighting apparatus in accordance with yet another embodiment of the invention;

[0009] FIG. 4 is a cutaway side perspective view of a lighting apparatus in accordance with one embodiment of the invention;

[0010] FIG. 5 is a schematic perspective view of a surface-mounted device (SMD) backlight LED.

DETAILED DESCRIPTION

[0011] In the processes according to the present invention, a non-color stable precursor to a color stable phosphor is annealed, or subjected to an elevated temperature, while in contact with an atmosphere containing a fluorine-containing oxidizing agent. The precursor is a complex fluoride material activated by Mn^{4+} of formula I. In the context of the present invention, the term "complex fluoride material or phosphor", means a coordination compound, containing at least one coordination center, surrounded by fluoride ions acting as ligands, and charge-compensated by counter ions as necessary. In one example, $K_2SiF_6:Mn^{4+}$, the coordination center is Si and the counterion is K. Complex fluorides are occasionally written down as a combination of simple, binary fluorides but such a representation does not indicate the coordination number for the ligands around the coordination center. The square brackets (occasionally omitted for simplicity) indicate that the complex ion they encompass is a new chemical species, different from the simple fluoride ion. The activator ion (Mn^{4+}) also acts as a coordination center, substituting part of the centers of the host lattice, for example, Si. The host lattice (including the counter ions) may further modify the excitation and emission properties of the activator ion.

[0012] The non-color stable precursor has a nominal composition similar to the color stable phosphor but lacks the color stability of the final product. The amount of manganese in the Mn^{4+} doped precursors of formula I and in the color stable phosphors ranges from about 0.3 weight% to about 1.5 weight%, based on total weight of the precursor or color stable phosphor. $K_2SiF_6:Mn^{4+}$ containing about 0.5 wt% Mn, before and after annealing, is typically more color stable under high light flux conditions than $K_2SiF_6:Mn^{4+}$ containing about 0.68 wt% Mn, before and after annealing. For $K_2SiF_6:Mn^{4+}$,

the amount of Mn ranges from about 0.50 wt% to about 0.85 wt%, more particularly from about 0.65 wt% to about 0.75 wt%.

[0013] In particular embodiments, the coordination center of the precursor, that is, M in formula I, is Si, Ge, Sn, Ti, Zr, or a combination thereof. More particularly, the coordination center is Si, Ge, Ti, or a combination thereof, and the counterion, or A in formula I, is Na, K, Rb, Cs, or a combination thereof, and y is 6. Examples of precursors of formula I include $K_2[SiF_6]:Mn^{4+}$, $K_2[TiF_6]:Mn^{4+}$, $K_2[SnF_6]:Mn^{4+}$, $Cs_2[TiF_6]$, $Rb_2[TiF_6]$, $Cs_2[SiF_6]$, $Rb_2[SiF_6]$, $Na_2[TiF_6]:Mn^{4+}$, $Na_2[ZrF_6]:Mn^{4+}$, $K_3[ZrF_7]:Mn^{4+}$, $K_3[BiF_6]:Mn^{4+}$, $K_3[YF_6]:Mn^{4+}$, $K_3[LaF_6]:Mn^{4+}$, $K_3[GdF_6]:Mn^{4+}$, $K_3[NbF_7]:Mn^{4+}$, $K_3[TaF_7]:Mn^{4+}$. In particular embodiments, the precursor of formula I is $K_2SiF_6:Mn^{4+}$.

[0014] Although the inventors do not wish to be held to any particular theory to explain the improvement in color stability that can result from subjecting the precursor to a process according to the present invention, it is postulated that the precursor may contain defects such as dislocations, F^- vacancies, cation vacancies, Mn^{3+} ions, Mn^{2+} ions, OH^- replacement of F^- , or surface or interstitial H^+/OH^- groups that provide non-radiative recombination pathways, and these are healed or removed by exposure to the oxidizing agent at elevated temperature.

[0015] The temperature at which the precursor is contacted with the fluorine-containing oxidizing agent may range from about 200°C to about 700°C, particularly from about 350°C to about 600°C during contact, and in some embodiments from about 200°C to about 700°C. In various embodiments of the present invention, the temperature is at least 100°C, particularly at least 225°C, and more particularly at least 350°C. The phosphor precursor is contacted with the oxidizing agent for a period of time sufficient to convert it to a color stable phosphor. Time and temperature are interrelated, and may be adjusted together, for example, increasing time while reducing temperature, or increasing temperature while reducing time. In particular embodiments, the time is at least one hour, particularly for at least four hours, more particularly

at least six hours, and most particularly at least eight hours. In a specific embodiment, the precursor is contacted with the oxidizing agent for a period of at least eight hours and a temperature of at least 250°C, for example, at about 250°C for about four hours and then at a temperature of about 350°C for about four hours.

[0016] The fluorine-containing oxidizing agent may be F₂, HF, SF₆, BrF₅, NH₄HF₂, NH₄F, KF, AlF₃, SbF₅, ClF₃, BrF₃, KrF, XeF₂, XeF₄, NF₃, SiF₄, PbF₂, ZnF₂, SnF₂, CdF₂ or a combination thereof. In particular embodiments, the fluorine-containing oxidizing agent is F₂. The amount of oxidizing agent in the atmosphere may be varied to obtain the color stable phosphor, particularly in conjunction with variation of time and temperature. Where the fluorine-containing oxidizing agent is F₂, the atmosphere may include at least 0.5% F₂, although a lower concentration may be effective in some embodiments. In particular the atmosphere may include at least 5% F₂ and more particularly at least 20% F₂. The atmosphere may additionally include nitrogen, helium, neon, argon, krypton, xenon, in any combination with the fluorine-containing oxidizing agent. In particular embodiments, the atmosphere is composed of about 20% F₂ and about 80% nitrogen.

[0017] The manner of contacting the precursor with the fluorine-containing oxidizing agent is not critical and may be accomplished in any way sufficient to convert the precursor to a color stable phosphor having the desired properties. In some embodiments, the chamber containing the precursor may be dosed and then sealed such that an overpressure develops as the chamber is heated, and in others, the fluorine and nitrogen mixture is flowed throughout the anneal process ensuring a more uniform pressure. In some embodiments, an additional dose of the fluorine-containing oxidizing agent may be introduced after a period of time.

[0018] In another aspect, the present invention relates to a process for synthesizing a color stable Mn⁴⁺ doped phosphor, the process comprising contacting a precursor at an elevated temperature with a fluorine-containing oxidizing agent in gaseous form to form the color stable Mn⁴⁺ doped phosphor, wherein the precursor is selected from the group consisting of

- (A) A₂[MF₅]:Mn⁴⁺, where A is selected from Li, Na, K, Rb, Cs, NH₄, and combinations thereof; and where M is selected from Al, Ga, In, and combinations thereof;
- (B) A₃[MF₆]:Mn⁴⁺, where A is selected from Li, Na, K, Rb, Cs, NH₄, and combinations thereof; and where M is selected from Al, Ga, In, and combinations thereof;
- (C) Zn₂[MF₇]:Mn⁴⁺, where M is selected from Al, Ga, In, and combinations thereof;
- (D) A[In₂F₇]:Mn⁴⁺ where A is selected from Li, Na, K, Rb, Cs, NH₄, and combinations thereof;

- (E) $A_2[MF_6]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Ge, Si, Sn, Ti, Zr, and combinations thereof;
- (F) $E[MF_6]:Mn^{4+}$, where E is selected from Mg, Ca, Sr, Ba, Zn, and combinations thereof; and where M is selected from Ge, Si, Sn, Ti, Zr, and combinations thereof;
- (G) $Ba_{0.65}Zr_{0.35}F_{2.70}:Mn^{4+}$; and
- (H) $A_3[ZrF_7]:Mn^{4+}$ where A is selected from Li, Na, K, Rb, Cs, NH_4 ; and
- (I) combinations thereof.

Time, temperature and fluorine-containing oxidizing agents for the process are described above.

[0019] Color stability and quantum efficiency of phosphors annealed in a process according to the present invention may be enhanced by treating the phosphor in particulate form with a saturated solution of a composition of formula II



II

in aqueous hydrofluoric acid, as described in US 8,252,613. The temperature at which the phosphor is contacted with the solution ranges from about 20°C to about 50°C. The period of time required to produce the color stable phosphor ranges from about one minute to about five hours, particularly from about five minutes to about one hour. Concentration of hydrofluoric acid in the aqueous HF solutions ranges from about 20% w/w to about 70% w/w, particularly about 40% w/w to about 70% w/w. Less concentrated solutions may result in lower yields of the phosphor.

[0020] A lighting apparatus or light emitting assembly or lamp 10 according to one embodiment of the present invention is shown in FIG. 1. Lighting apparatus 10 includes a semiconductor radiation source, shown as light emitting diode (LED) chip 12, and leads 14 electrically attached to the LED chip. The leads 14 may be thin wires supported by a thicker lead frame(s) 16 or the leads may be self supported electrodes and the lead frame may be omitted. The leads 14 provide current to LED chip 12 and thus cause it to emit radiation.

[0021] The lamp may include any semiconductor blue or UV light source that is capable of producing white light when its emitted radiation is directed onto the phosphor. In one embodiment, the semiconductor light source is a blue emitting LED doped with various impurities. Thus, the LED may comprise a semiconductor diode based on any suitable III-V, II-VI or IV-IV semiconductor layers and having an emission wavelength of about 250 to 550 nm. In particular, the LED may contain at least one semiconductor layer comprising GaN, ZnSe or SiC. For example, the LED may comprise a nitride compound semiconductor represented by

the formula $\text{In}_i\text{Ga}_j\text{Al}_k\text{N}$ (where $0 \leq i$; $0 \leq j$; $0 \leq k$ and $i + j + k = 1$) having an emission wavelength greater than about 250 nm and less than about 550 nm. In particular embodiments, the chip is a near-uv or blue emitting LED having a peak emission wavelength from about 400 to about 500 nm. Such LED semiconductors are known in the art. The radiation source is described herein as an LED for convenience. However, as used herein, the term is meant to encompass all semiconductor radiation sources including, e.g., semiconductor laser diodes. Further, although the general discussion of the exemplary structures of the invention discussed herein is directed toward inorganic LED based light sources, it should be understood that the LED chip may be replaced by another radiation source unless otherwise noted and that any reference to semiconductor, semiconductor LED, or LED chip is merely representative of any appropriate radiation source, including, but not limited to, organic light emitting diodes.

[0022] In lighting apparatus 10, phosphor composition 22 is radiationally coupled to the LED chip 12. Radiationally coupled means that the elements are associated with each other so radiation from one is transmitted to the other. Phosphor composition 22 is deposited on the LED 12 by any appropriate method. For example, a water based suspension of the phosphor(s) can be formed, and applied as a phosphor layer to the LED surface. In one such method, a silicone slurry in which the phosphor particles are randomly suspended is placed around the LED. This method is merely exemplary of possible positions of phosphor composition 22 and LED 12. Thus, phosphor composition 22 may be coated over or directly on the light emitting surface of the LED chip 12 by coating and drying the phosphor suspension over the LED chip 12. In the case of a silicone-based suspension, the suspension is cured at an appropriate temperature. Both the shell 18 and the encapsulant 20 should be transparent to allow white light 24 to be transmitted through those elements. Although not intended to be limiting, in some embodiments, the median particle size of the phosphor composition ranges from about 1 to about 50 microns, particularly from about 15 to about 35 microns.

[0023] In other embodiments, phosphor composition 22 is interspersed within the encapsulant material 20, instead of being formed directly on the LED chip 12. The phosphor (in the form of a powder) may be interspersed within a single region of the encapsulant material 20 or throughout the entire volume of the encapsulant material. Blue light emitted by the LED chip 12 mixes with the light emitted by phosphor composition 22, and the mixed light appears as white light. If the phosphor is to be interspersed within the material of encapsulant 20, then a phosphor powder may be added to a polymer or silicone precursor, loaded around the LED chip 12, and then the polymer precursor may be cured to solidify the polymer or silicone material. Other known phosphor interspersions methods may also be used, such as transfer loading.

[0024] In some embodiments, the encapsulant material 20 is a silicone matrix having an index of refraction R , and, in addition to phosphor composition 22, contains a diluent material having less than about 5% absorbance and index of refraction of $R \pm 0.1$. The diluent material has an index of refraction of ≤ 1.7 , particularly ≤ 1.6 , and more particularly ≤ 1.5 . In particular embodiments, the diluent material is of formula II, and has an index of refraction of about 1.4. Adding an optically inactive material to the phosphor/silicone mixture may produce a more gradual distribution of light flux through the phosphor/encapsulant mixture and can result in less damage to the phosphor. Suitable materials for the diluent include fluoride compounds such as LiF, MgF₂, CaF₂, SrF₂, AlF₃, K₂NaAlF₆, KMgF₃, CaLiAlF₆, K₂LiAlF₆, and K₂SiF₆, which have index of refraction ranging from about 1.38 (AlF₃ and K₂NaAlF₆) to about 1.43 (CaF₂), and polymers having index of refraction ranging from about 1.254 to about 1.7. Non-limiting examples of polymers suitable for use as a diluent include polycarbonates, polyesters, nylons, polyetherimides, polyetherketones, and polymers derived from styrene, acrylate, methacrylate, vinyl, vinyl acetate, ethylene, propylene oxide, and ethylene oxide monomers, and copolymers thereof, including halogenated and unhalogenated derivatives. These polymer powders can be directly incorporated into silicone encapsulants before silicone curing.

[0025] In yet another embodiment, phosphor composition 22 is coated onto a surface of the shell 18, instead of being formed over the LED chip 12. The phosphor composition is preferably coated on the inside surface of the shell 18, although the phosphor may be coated on the outside surface of the shell, if desired. Phosphor composition 22 may be coated on the entire surface of the shell or only a top portion of the surface of the shell. The UV/blue light emitted by the LED chip 12 mixes with the light emitted by phosphor composition 22, and the mixed light appears as white light. Of course, the phosphor may be located in any two or all three locations or in any other suitable location, such as separately from the shell or integrated into the LED.

[0026] FIG. 2 illustrates a second structure of the system according to the present invention. Corresponding numbers from FIGS. 1-4 (e.g. 12 in FIG. 1 and 112 in FIG. 2) relate to corresponding structures in each of the figures, unless otherwise stated. The structure of the embodiment of FIG. 2 is similar to that of FIG. 1, except that the phosphor composition 122 is interspersed within the encapsulant material 120, instead of being formed directly on the LED chip 112. The phosphor (in the form of a powder) may be interspersed within a single region of the encapsulant material or throughout the entire volume of the encapsulant material. Radiation (indicated by arrow 126) emitted by the LED chip 112 mixes with the light emitted by the phosphor 122, and the mixed light appears as white light 124. If the phosphor is to be interspersed within the encapsulant material 120, then a phosphor powder may be added to a

polymer precursor, and loaded around the LED chip 112. The polymer or silicone precursor may then be cured to solidify the polymer or silicone. Other known phosphor interspersion methods may also be used, such as transfer molding.

[0027] FIG. 3 illustrates a third possible structure of the system according to the present invention. The structure of the embodiment shown in FIG. 3 is similar to that of FIG. 1, except that the phosphor composition 222 is coated onto a surface of the envelope 218, instead of being formed over the LED chip 212. The phosphor composition 222 is preferably coated on the inside surface of the envelope 218, although the phosphor may be coated on the outside surface of the envelope, if desired. The phosphor composition 222 may be coated on the entire surface of the envelope, or only a top portion of the surface of the envelope. The radiation 226 emitted by the LED chip 212 mixes with the light emitted by the phosphor composition 222, and the mixed light appears as white light 224. Of course, the structures of FIGS. 1-3 may be combined, and the phosphor may be located in any two or all three locations, or in any other suitable location, such as separately from the envelope, or integrated into the LED.

[0028] In any of the above structures, the lamp may also include a plurality of scattering particles (not shown), which are embedded in the encapsulant material. The scattering particles may comprise, for example, alumina or titania. The scattering particles effectively scatter the directional light emitted from the LED chip, preferably with a negligible amount of absorption.

[0029] As shown in a fourth structure in FIG. 4, the LED chip 412 may be mounted in a reflective cup 430. The cup 430 may be made from or coated with a dielectric material, such as alumina, titania, or other dielectric powders known in the art, or be coated by a reflective metal, such as aluminum or silver. The remainder of the structure of the embodiment of FIG. 4 is the same as those of any of the previous figures, and can include two leads 416, a conducting wire 432, and an encapsulant material 420. The reflective cup 430 is supported by the first lead 416 and the conducting wire 432 is used to electrically connect the LED chip 412 with the second lead 416.

[0030] Another structure (particularly for backlight applications) is a surface mounted device ("SMD") type light emitting diode 550, e.g. as illustrated in FIG. 5. This SMD is a "side-emitting type" and has a light-emitting window 552 on a protruding portion of a light guiding member 554. An SMD package may comprise an LED chip as defined above, and a phosphor material that is excited by the light emitted from the LED chip. Other backlight devices include, but are not limited to, TVs, computers, smartphones, tablet computers and other handheld devices that

have a display including a semiconductor light source; and a color stable Mn⁴⁺ doped phosphor according to the present invention.

[0031] When used with an LED emitting at from 350 to 550 nm and one or more other appropriate phosphors, the resulting lighting system will produce a light having a white color. Lamp 10 may also include scattering particles (not shown), which are embedded in the encapsulant material. The scattering particles may comprise, for example, alumina or titania. The scattering particles effectively scatter the directional light emitted from the LED chip, preferably with a negligible amount of absorption.

[0032] In addition to the color stable Mn⁴⁺ doped phosphor, phosphor composition 22 may include one or more other phosphors. When used in a lighting apparatus in combination with a blue or near UV LED emitting radiation in the range of about 250 to 550 nm, the resultant light emitted by the assembly will be a white light. Other phosphors such as green, blue, yellow, red, orange, or other color phosphors may be used in the blend to customize the white color of the resulting light and produce specific spectral power distributions. Other materials suitable for use in phosphor composition 22 include electroluminescent polymers such as polyfluorenes, preferably poly(9,9-dioctyl fluorene) and copolymers thereof, such as poly(9,9'-dioctylfluorene-co-bis-N,N'-(4-butylphenyl)diphenylamine) (F8-TFB); poly(vinylcarbazole) and polyphenylenevinylene and their derivatives. In addition, the light emitting layer may include a blue, yellow, orange, green or red phosphorescent dye or metal complex, or a combination thereof. Materials suitable for use as the phosphorescent dye include, but are not limited to, tris(1-phenylisoquinoline) iridium (III) (red dye), tris(2-phenylpyridine) iridium (green dye) and Iridium (III) bis(2-(4,6-difluorephenyl)pyridinato-N,C2) (blue dye). Commercially available fluorescent and phosphorescent metal complexes from ADS (American Dyes Source, Inc.) may also be used. ADS green dyes include ADS060GE, ADS061GE, ADS063GE, and ADS066GE, ADS078GE, and ADS090GE. ADS blue dyes include ADS064BE, ADS065BE, and ADS070BE. ADS red dyes include ADS067RE, ADS068RE, ADS069RE, ADS075RE, ADS076RE, ADS067RE, and ADS077RE.

[0033] Suitable phosphors for use in phosphor composition 22 include, but are not limited to:

$((\text{Sr}_{1-z}(\text{Ca}, \text{Ba}, \text{Mg}, \text{Zn})_z)_{1-(x+w)}(\text{Li}, \text{Na}, \text{K}, \text{Rb})_w\text{Ce}_x)_3(\text{Al}_{1-y}\text{Si}_y)\text{O}_{4+y+3(x-w)}\text{F}_{1-y-3(x-w)}$, $0 < x \leq 0.10$, $0 \leq y \leq 0.5$, $0 \leq z \leq 0.5$, $0 \leq w \leq x$;

$(\text{Ca}, \text{Ce})_3\text{Sc}_2\text{Si}_3\text{O}_{12}(\text{CaSiG})$;

$(\text{Sr}, \text{Ca}, \text{Ba})_3\text{Al}_{1-x}\text{Si}_x\text{O}_{4+x}\text{F}_{1-x}:\text{Ce}^{3+}$ (SASOF));

$(\text{Ba}, \text{Sr}, \text{Ca})_5(\text{PO}_4)_3(\text{Cl}, \text{F}, \text{Br}, \text{OH}):\text{Eu}^{2+}, \text{Mn}^{2+}$; $(\text{Ba}, \text{Sr}, \text{Ca})\text{BPO}_5:\text{Eu}^{2+}, \text{Mn}^{2+}$;

$(\text{Sr}, \text{Ca})_{10}(\text{PO}_4)_6^*v\text{B}_2\text{O}_3:\text{Eu}^{2+}$ (wherein $0 < v \leq 1$); $\text{Sr}_2\text{Si}_3\text{O}_8^*2\text{SrCl}_2:\text{Eu}^{2+}$;

$(\text{Ca}, \text{Sr}, \text{Ba})_3\text{MgSi}_2\text{O}_8:\text{Eu}^{2+}, \text{Mn}^{2+}$; $\text{BaAl}_8\text{O}_{13}:\text{Eu}^{2+}$; $2\text{SrO} \cdot 0.84\text{P}_2\text{O}_5 \cdot 0.16\text{B}_2\text{O}_3:\text{Eu}^{2+}$;
 $(\text{Ba}, \text{Sr}, \text{Ca})\text{MgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}, \text{Mn}^{2+}$; $(\text{Ba}, \text{Sr}, \text{Ca})\text{Al}_2\text{O}_4:\text{Eu}^{2+}$; $(\text{Y}, \text{Gd}, \text{Lu}, \text{Sc}, \text{La})\text{BO}_3:\text{Ce}^{3+}, \text{Tb}^{3+}$;
 $\text{ZnS}:\text{Cu}^+, \text{Cl}^-$; $\text{ZnS}:\text{Cu}^+, \text{Al}^{3+}$; $\text{ZnS}:\text{Ag}^+, \text{Cl}^-$; $\text{ZnS}:\text{Ag}^+, \text{Al}^{3+}$; $(\text{Ba}, \text{Sr}, \text{Ca})_2\text{Si}_{1-\xi}\text{O}_{4-2\xi}:\text{Eu}^{2+}$ (wherein
 $0 \leq \xi \leq 0.2$); $(\text{Ba}, \text{Sr}, \text{Ca})_2(\text{Mg}, \text{Zn})\text{Si}_2\text{O}_7:\text{Eu}^{2+}$; $(\text{Sr}, \text{Ca}, \text{Ba})(\text{Al}, \text{Ga}, \text{In})_2\text{S}_4:\text{Eu}^{2+}$;
 $(\text{Y}, \text{Gd}, \text{Tb}, \text{La}, \text{Sm}, \text{Pr}, \text{Lu})_3(\text{Al}, \text{Ga})_{5-\alpha}\text{O}_{12-3/2\alpha}:\text{Ce}^{3+}$ (wherein $0 \leq \alpha \leq 0.5$);
 $(\text{Ca}, \text{Sr})_8(\text{Mg}, \text{Zn})(\text{SiO}_4)_4\text{Cl}_2:\text{Eu}^{2+}, \text{Mn}^{2+}$; $\text{Na}_2\text{Gd}_2\text{B}_2\text{O}_7:\text{Ce}^{3+}, \text{Tb}^{3+}$; $(\text{Sr}, \text{Ca}, \text{Ba}, \text{Mg}, \text{Zn})_2\text{P}_2\text{O}_7:\text{Eu}^{2+}, \text{Mn}^{2+}$;
 $(\text{Gd}, \text{Y}, \text{Lu}, \text{La})_2\text{O}_3:\text{Eu}^{3+}, \text{Bi}^{3+}$; $(\text{Gd}, \text{Y}, \text{Lu}, \text{La})_2\text{O}_2\text{S}:\text{Eu}^{3+}, \text{Bi}^{3+}$; $(\text{Gd}, \text{Y}, \text{Lu}, \text{La})\text{VO}_4:\text{Eu}^{3+}, \text{Bi}^{3+}$;
 $(\text{Ca}, \text{Sr})\text{S}:\text{Eu}^{2+}, \text{Ce}^{3+}$; $\text{SrY}_2\text{S}_4:\text{Eu}^{2+}$; $\text{CaLa}_2\text{S}_4:\text{Ce}^{3+}$; $(\text{Ba}, \text{Sr}, \text{Ca})\text{MgP}_2\text{O}_7:\text{Eu}^{2+}, \text{Mn}^{2+}$;
 $(\text{Y}, \text{Lu})_2\text{WO}_6:\text{Eu}^{3+}, \text{Mo}^{6+}$; $(\text{Ba}, \text{Sr}, \text{Ca})_\beta\text{Si}_\gamma\text{N}_\mu:\text{Eu}^{2+}$ (wherein $2\beta + 4\gamma = 3\mu$); $\text{Ca}_3(\text{SiO}_4)\text{Cl}_2:\text{Eu}^{2+}$;
 $(\text{Lu}, \text{Sc}, \text{Y}, \text{Tb})_{2-u-v}\text{Ce}_v\text{Ca}_{1+u}\text{Li}_w\text{Mg}_{2-w}\text{P}_w(\text{Si}, \text{Ge})_{3-w}\text{O}_{12-u/2}$ (where $-0.5 \leq u \leq 1$, $0 < v \leq 0.1$, and $0 \leq w \leq 0.2$);
 $(\text{Y}, \text{Lu}, \text{Gd})_{2-\phi}\text{Ca}_\phi\text{Si}_4\text{N}_{6+\phi}\text{C}_{1-\phi}:\text{Ce}^{3+}$, (wherein $0 \leq \phi \leq 0.5$); $(\text{Lu}, \text{Ca}, \text{Li}, \text{Mg}, \text{Y})$, α -SiAlON doped with Eu^{2+}
and/or Ce^{3+} ; $(\text{Ca}, \text{Sr}, \text{Ba})\text{SiO}_2\text{N}_2:\text{Eu}^{2+}, \text{Ce}^{3+}$; β -SiAlON: Eu^{2+} , $3.5\text{MgO} \cdot 0.5\text{MgF}_2 \cdot \text{GeO}_2:\text{Mn}^{4+}$; Ca_{1-c} -
 $\text{rCe}_c\text{Eu}_r\text{Al}_{1+c}\text{Si}_{1-c}\text{N}_3$, (where $0 \leq c \leq 0.2$, $0 \leq f \leq 0.2$); $\text{Ca}_{1-h-r}\text{Ce}_h\text{Eu}_r\text{Al}_{1-h}(\text{Mg}, \text{Zn})_h\text{SiN}_3$, (where $0 \leq h \leq 0.2$,
 $0 \leq r \leq 0.2$); $\text{Ca}_{1-2s-t}\text{Ce}_s(\text{Li}, \text{Na})_s\text{Eu}_t\text{AlSiN}_3$, (where $0 \leq s \leq 0.2$, $0 \leq f \leq 0.2$, $s+t > 0$); and $\text{Ca}_{1-\sigma-\chi}$ -
 $\phi\text{Ce}_\sigma(\text{Li}, \text{Na})_\chi\text{Eu}_\phi\text{Al}_{1+\sigma-\chi}\text{Si}_{1-\sigma+\chi}\text{N}_3$, (where $0 \leq \sigma \leq 0.2$, $0 \leq \chi \leq 0.4$, $0 \leq \phi \leq 0.2$).

[0034] The ratio of each of the individual phosphors in the phosphor blend may vary depending on the characteristics of the desired light output. The relative proportions of the individual phosphors in the various embodiment phosphor blends may be adjusted such that when their emissions are blended and employed in an LED lighting device, there is produced visible light of predetermined x and y values on the CIE chromaticity diagram. As stated, a white light is preferably produced. This white light may, for instance, may possess an x value in the range of about 0.20 to about 0.55, and a y value in the range of about 0.20 to about 0.55. As stated, however, the exact identity and amounts of each phosphor in the phosphor composition can be varied according to the needs of the end user. For example, the material can be used for LEDs intended for liquid crystal display (LCD) backlighting. In this application, the LED color point would be appropriately tuned based upon the desired white, red, green, and blue colors after passing through an LCD/color filter combination.

[0035] LED devices incorporating the color stable phosphors and used for backlighting or general illumination lighting may have a color shift of <1.5 MacAdam ellipses over 2,000 hours of device operation, and, in particular embodiments, <1 MacAdam ellipse over 2,000 hours, where the phosphor/polymer composite is in direct contact with the LED chip surface, LED wall plug efficiency greater than 40%, and LED current densities are greater than 2 A/cm². In accelerated testing, where the phosphor/polymer composite is in direct contact with the LED chip surface, LED wall plug efficiency greater than 18%, and LED current densities are greater than 70 A/cm², LED devices may have color shift of <1.5 MacAdam ellipse over 30 minutes.

[0036] The color stable Mn⁴⁺ doped phosphors of the present invention may be used in applications other than those described above. For example, the material may be used as a phosphor in a fluorescent lamp, in a cathode ray tube, in a plasma display device or in a liquid crystal display (LCD). The material may also be used as a scintillator in an electromagnetic calorimeter, in a gamma ray camera, in a computed tomography scanner or in a laser. These uses are merely exemplary and not limiting.

EXAMPLES

General Procedures

Silicone Tape Sample Preparation

[0037] Samples were prepared by mixing 500 mg of the material to be tested with 1.50 g silicone (Sylgard 184). The mixture was degassed in a vacuum chamber for about 15 minutes. The mixture (0.70 g) was poured into a disc-shaped template (28.7mm diameter and 0.79 mm thick) and baked for 30 minutes at 90°C. The sample was cut into squares of size approximately 5 mm x 5 mm for testing.

Stability Testing

High Light Flux Conditions

[0038] A laser diode emitting at 446 nm was coupled to an optical fiber with a collimator at its other end. The power output was 310 mW and the beam diameter at the sample was 700 microns. This is equivalent to a flux of 80 W/cm² on the sample surface. The spectral power distribution (SPD) spectrum that is a combination of the scattered radiation from the laser and the emission from the excited phosphor is collected with a 1 meter (diameter) integrating sphere and the data processed with the spectrometer software (Specwin). At intervals of two minutes, the integrated power from the laser and the phosphor emission were recorded over a period of about 21 hours by integrating the SPD from 400nm to 500nm and 550 nm to 700 nm respectively. The first 90 minutes of the measurement are discarded to avoid effects due to the thermal stabilization of the laser. The percentage of intensity loss due to laser damage is calculated as follows:

$$\text{Intensity loss (\%)} = 100 \frac{(\text{Power} - \text{Initial power})}{\text{Initial power}}$$

While only the emitter power from the phosphor is plotted, the integrated power from the laser emission as well as its peak position was monitored to ensure that the laser remained stable (variations of less than 1%) during the experiment.

High Temperature High Humidity (HHTH) Treatment

[0039] Samples for high temperature, high humidity (HTHH) treatment were made by mixing phosphor powders into a two-part methyl silicone binder (RTV-615, Momentive Performance Materials) in a ratio of 0.9 g phosphor to 0.825 g silicone (parts A+B). The phosphor/silicone mixture is then poured into aluminum sample holders and cured at 90°C for 20 minutes. Control samples were stored under nitrogen, and samples for exposure to HTHH conditions were placed into a 85°C/85% RH controlled atmosphere chamber. These HTHH samples are periodically removed and their luminescence intensity under 450 nm excitation compared to that of the control samples.

EXAMPLES 1-12 ANNEALING UNDER FLUORINE ATMOSPHERE

Procedure

[0040] A Mn-doped potassium fluorosilicate (PFS:Mn) precursor, $K_2SiF_6:Mn$, containing 0.68 wt% Mn, based on total weight of the precursor material was placed in a furnace chamber. The furnace chamber was evacuated and was filled with an atmosphere containing fluorine gas and nitrogen gas. The chamber was then heated to the desired anneal temperature. After holding for the desired amount of time, the chamber was cooled to room temperature. The fluorine nitrogen mixture was evacuated, the chamber was filled and purged several times with nitrogen to ensure the complete removal of fluorine gas before opening the chamber.

[0041] For Examples 1-5, the atmosphere in the chamber was composed of 20% fluorine gas and 80% nitrogen gas. For Example 6, the atmosphere was composed of 5% fluorine gas and 95% nitrogen gas. Furnace setpoint temperature and time for a first annealing period (T_1 and t_1) and furnace setpoint temperature and time for a second annealing period, if any, (T_2 and t_2) are indicated in Table 1. Due to the furnace setup and how the sample is placed relative to the control thermocouples in the furnace actual sample temperatures in the furnace were 25-75°C higher than the furnace setpoint.

The stability of precursor PFS:Mn having wt% Mn ranging from 0.68-0.73 wt% and the product phosphor (Comparative Example 1) was tested under conditions of high light flux, and results are shown in Table 1. The annealed materials experienced significantly less damage than the materials that were not heat treated.

TABLE 1

Example No.	T1 (°C)	t1 (hr.)	T2 (°C)	t2 (hr.)	Laser Damage	Comments
Comp. Ex. 1	--	--	--	--	6%-9%	No heat treatment
1	225	4	--	--	3.8%	Post-treatment
2	225	4	350	4	1.8%	
3	300	4	425	4	0.8%	
4	350	4	--	--	2.7%	
5	425	4	--	--	1.1%	
6	225	4	350	4	2.5%	

EXAMPLE 2 Post-Treatment of Annealed Phosphor

[0042] The annealed PFS phosphor powder from Example 2 was treated with a saturated solution of K₂SiF₆ by placing the powder (~10 g) in a Teflon beaker containing 100 mL of a saturated solution of K₂SiF₆ (initially made by adding ~17 g of K₂SiF₆ in 40% HF at room temperature, stirring, and filtering the solution). The suspension was stirred slowly, and the residue is filtered and dried under vacuum. Further removal of HF from the dried filtrate was done by washing in acetone 3-5 times and heating the filtrate to 100°C for 10 min. Stability of the post-treated phosphor along with a sample of PFS that was not annealed but was post treated was evaluated under HHTH conditions, at 85°C/85%RH for 620 hours. The post-treated sample experienced less degradation under the high temperature/humidity conditions, maintaining about 94% emission intensity, while the non-annealed sample maintained about 86% emission intensity.

COMPARATIVE EXAMPLES 2-7

[0043] Samples of unannealed and untreated PFS precursors having Mn content ranging from 0.5-0.85 wt% were tested under conditions of high light flux as shown in Table 2.

EXAMPLES 7-12

[0044] Samples of the PFS precursors were annealed at furnace setpoint temperatures ranging from 425-550°C for times ranging from 4-8 hours as shown in Table 2. After annealing, all samples were treated in saturated K₂SiF₆ solutions in 48%HF as in Example 2. The annealed phosphors were tested under conditions of high light flux, and results are shown in Table 2.

Table 2

Table 2				
Example no.	Mn level (wt%)	Furnace setpoint T, °C	Time	Laser damage/%intensity loss
Comp. Ex. 2	0.74%	N/A		6.9%
7		500	8 hours	1.5%
Comp. Ex. 3	0.84%	N/A		10.9%
8		500	8 hours	2.3%
Comp. Ex. 4	0.68%	N/A		7.1%
9		475	8 hours	1.0%
Comp. Ex. 5	0.73%	N/A		8.4%
10		500	8 hours	1.25%
Comp. Ex. 6	0.71%	N/A		9.9%
11		475	8 hours	1.1%
Comp. Ex. 7	0.53%	N/A		3.3%
12		425	4 hours	0.6%

EXAMPLE 13 Diluted PFS Silicone tape

[0045] Unannealed $K_2SiF_6:Mn$ (0.68 wt% Mn) was mixed with a silicone precursor and formed into a solid tape composed of 87.8 volume% silicone and 12.2 volume% PFS. A control contained a 1:1 mixture of $K_2SiF_6:Mn$ (0.68 wt% Mn) (doped PFS) and K_2SiF_6 (0 wt% Mn) (undoped PFS), having a final composition of 75.6 vol% silicone, 12.2% undoped PFS and 12.2 vol% doped PFS.

[0046] The tape was subjected to stability testing under high light flux conditions. Power intensity loss for the diluted PFS sample was about 2.5% after 24 hours, and was significantly lower than that of the control.

EXAMPLE 14 Reduced Mn Level

[0047] A Mn-doped potassium fluorosilicate (PFS:Mn) precursor, $K_2SiF_6:Mn$, containing 0.53 wt% Mn, based on total weight of the precursor material was tested under conditions of high light flux, and results are shown in Table 3. The material containing the lower Mn level experienced significantly less damage than the control that was not heat treated (Comparative Example 8).

TABLE 3

Example	Laser Damage	%Mn	Comments
Comp. Ex. 8	6%-9%	0.68- 0.73	Not annealed
14	3.4%	0.53	Mn ⁴⁺ reduced by 25%

Example 15 Higher annealing temperatures in an alternate furnace

[0048] A Mn-doped potassium fluorosilicate (PFS:Mn) precursor, K₂SiF₆:Mn, containing 0.84 wt% Mn, based on total weight of the precursor material was annealed under the conditions shown in Table 4 in a different furnace whose setpoint temperatures were closer to the maximum temperature in the furnace. After the annealing step, the materials were processed using the post-treatment process in Example 2. The phosphor and an annealed, untreated sample (Comparative Example 9) were tested under conditions of high light flux. Results are shown in Table 4. The annealed and post-treated material experienced significantly less damage than the control that was not heat treated. In addition, the phosphor quantum efficiency under blue LED excitation was higher by ~7.5% versus the initial control sample.

TABLE 4

Example	Laser Damage	Relative quantum efficiency	%Mn	Conditions
Comp. Ex. 9	10.9%	100	0.84%	Not annealed
15	1.5%	107.5	0.82%	540°C in 10 psia of 20%F ₂ /80%N ₂ for 8 hours

EXAMPLES 16 AND 17 LED packaging and testing procedure

[0049] LED packages were made using K₂SiF₆:Mn⁴⁺ phosphors that were annealed using the conditions in examples 2 (Example 16) and 5 (Example 17) as well as unannealed K₂SiF₆:Mn⁴⁺ phosphors (Comparative Examples 10 and 11). These phosphors were blended with Ce³⁺-doped garnets and a silicone binder and deposited within a package similar to typical 3030 LED package with two blue emitting LED chips for a color temperature of ~4000K. The packages were then attached to a printed circuit board. The LED dimensions in these packages were approximately 0.65mm x 0.65mm; taking this LED area, the LED current density is defined as:

LED current density=Drive current/[(LED area)*(number of LEDs in package)]

The devices of Comparative Example 10 and Example 16 were operated at 30mA, at ambient temperature ($T_{ambient}$) of 47°C for 4000 hours . The devices of Comparative Example 11 and Example 17 were operated at 700 mA drive current at a board temperature (T_{board}) of 60°C for 30 minutes. Using the above formula, a 30 mA drive current gives a LED current density of approximately 3.6 A/cm², and a 700 mA drive current gives a LED current density of approximately 83 A/cm². Similar LED packages without phosphors give a wall-plug efficiency (defined by emitted optical power divided by input electrical power) of 54% at 100mA drive current and board temperature of 60°C and 22% at 700 mA drive current and board temperature of 60°C. The device color point was obtained by measuring the spectral power distribution of the LED device using a calibrated integrating sphere spectrometer at different times after LED operation under different drive current and ambient/board temperature conditions.. Results are shown in Tables 5 and 6.

Table 5				
Example no.	MacAdam steps after 4000 hours	Dx after 4000 hours	Dy after 4000 hours	D[intensity@631nm] after 4000 hours
Comp. Ex. 10	1.82	0.0023	0.0010	91.7%
16	0.91	0.0004	0.0000	93.5%

Table 6				
Example no.	MacAdam steps after 30 min	Dx after 30 min	Dy after 30 min	D[(631 nm)/(455nm)] after 30 min
Comp. Ex. 11	4.0	-0.0058	-0.0012	-10.5%
17	0.5	-0.0011	-0.0009	-1.3%

[0050] While only certain features of the invention have been illustrated and described herein, many modifications and changes will occur to those skilled in the art. It is, therefore, to be


understood that the appended claims are intended to cover all such modifications and changes as fall within the true spirit of the invention.

[0051] The discussion of documents, acts, materials, devices, articles and the like is included in this specification solely for the purpose of providing a context for the present invention. It is not suggested or represented that any or all of these matters formed part of the prior art base or were common general knowledge in the field relevant to the present invention as it existed before the priority date of each claim of this application.

[0052] Throughout the description and claims of this specification, the word "comprise" and variations of the word, such as "comprising" and "comprises", is not intended to exclude other additives, components, integers or steps.

The claims defining the invention are as follows:

1. A process for synthesizing a color stable Mn^{4+} doped phosphor, the process comprising contacting a precursor of formula I,



at an elevated temperature with a fluorine-containing oxidizing agent in gaseous form to form the color stable Mn^{4+} doped phosphor;

wherein

A is Li, Na, K, Rb, Cs, NR_4 or a combination thereof;

M is Si, Ge, Sn, Ti, Zr, Al, Ga, In, Sc, Hf, Y, La, Nb, Ta, Bi, Gd, or a combination thereof;

R is H, lower alkyl, or a combination thereof;

x is the absolute value of the charge of the $[MF_y]$ ion; and

y is 5, 6 or 7.

2. A process according to claim 1, wherein the fluorine-containing oxidizing agent is F_2 , anhydrous HF, BrF_5 , NH_4HF_2 , NH_4F , AlF_3 , SF_6 , SbF_5 , ClF_3 , BrF_3 , KrF, XeF_2 , XeF_4 , NF_3 , PbF_2 , ZnF_2 , SiF_4 , SnF_2 , CdF_2 or a combination thereof.
3. A process according to claim 1, wherein the fluorine-containing oxidizing agent is F_2 .
4. A process according to any one of claims 1 to 3, wherein the temperature is at least 100°C.
5. A process according to any one of claims 1 to 3, wherein the temperature is at least 350°C.
6. A process according to any one of claims 1 to 3, wherein the temperature is at least 225°C.
7. A process according to any one of claims 1 to 3, wherein the temperature ranges from about 200°C to about 700°C.
8. A process according to any one of claims 1 to 3, wherein the temperature ranges from about 350°C to about 600°C.
9. A process according to any one of claims 1 to 8, wherein the phosphor precursor is contacted with the reactant for a period of at least one hours.

10. A process according to any one of claims 1 to 8, wherein the phosphor precursor is contacted with the reactant for a period of at least four hours.
11. A process according to any one of claims 1 to 8, wherein the phosphor precursor is contacted with the reactant for a period of least about six hours.
12. A process according to any one of claims 1 to 8, wherein the phosphor precursor is contacted with the reactant for a period of about eight hours.
13. A process according to any one of claims 1 to 8, wherein the phosphor precursor is contacted with the reactant for a period of at least eight hours and a temperature of at least 250°C.
14. A process according to any one of claims 1 to 8, wherein the temperature is initially about 250°C for about four hours and then about 350 °C for about four hours.
15. A process according to any one of claims 1 to 14, wherein the atmosphere comprises at least 0.5% fluorine.
16. A process according to any one of claims 1 to 14, wherein the atmosphere comprises at least 5% fluorine.
17. A process according to any one of claims 1 to 14, wherein the atmosphere comprises at least 20% fluorine.
18. A process according to any one of claims 1 to 17, wherein the atmosphere additionally comprises nitrogen, helium, neon, argon, krypton, xenon, or a combination thereof.
19. A process according to any one of claims 1 to 14, wherein the atmosphere comprises about 20% fluorine and about 80% nitrogen.
20. A process according to any one of claims 1 to 19, wherein M is Si, Ge, Sn, Ti, Zr, or a combination thereof.
21. A process according to any one of claims 1 to 19, wherein
 - A is Na, K, Rb, Cs, or a combination thereof;
 - M is Si, Ge, Ti, or a combination thereof; and
 - Y is 6.

22. A process according to any one of claims 1 to 19, wherein the phosphor precursor is $K_2SiF_6:Mn^{4+}$.

23. A process according to any one of claims 1 to 22, additionally comprising contacting the color stable Mn^{4+} doped phosphor in particulate form with a saturated solution of a composition of formula II in aqueous hydrofluoric acid.



II

24. A color stable Mn^{4+} doped phosphor prepared by a process according to any one of claims 1 to 23.

25. A lighting apparatus comprising

a semiconductor light source; and a color stable Mn^{4+} doped phosphor prepared by a process according to any one of claims 1 to 23.

26. A process for synthesizing a color stable Mn^{4+} doped phosphor, the process comprising contacting a precursor at an elevated temperature with a fluorine-containing oxidizing agent in gaseous form to form the color stable Mn^{4+} doped phosphor, wherein the precursor is selected from the group consisting of

(A) $A_2[MF_5]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Al, Ga, In, and combinations thereof;

(B) $A_3[MF_6]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Al, Ga, In, and combinations thereof;

(C) $Zn_2[MF_7]:Mn^{4+}$, where M is selected from Al, Ga, In, and combinations thereof;

(D) $A[In_2F_7]:Mn^{4+}$ where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof;

(E) $A_2[MF_8]:Mn^{4+}$, where A is selected from Li, Na, K, Rb, Cs, NH_4 , and combinations thereof; and where M is selected from Ge, Si, Sn, Ti, Zr, and combinations thereof;

(F) $E[MF_6]:Mn^{4+}$, where E is selected from Mg, Ca, Sr, Ba, Zn, and combinations thereof; and where M is selected from Ge, Si, Sn, Ti, Zr, and combinations thereof;

(G) $Ba_{0.65}Zr_{0.35}F_{2.70}:Mn^{4+}$; and

(H) $A_3[ZrF_7]:Mn^{4+}$ where A is selected from Li, Na, K, Rb, Cs, NH_4 ; and

(l) combinations thereof.

27. A process according to claim 26, wherein the temperature ranges from about 500°C to about 600°C.
28. A lighting apparatus comprising a semiconductor light source; and a color stable Mn^{4+} doped phosphor prepared by a process according to claim 26.




Fig. 1




Fig. 2

2/3




Fig. 3




Fig. 4




Fig. 5