



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B41M 5/00	A1	(11) International Publication Number: WO 94/02324 (43) International Publication Date: 3 February 1994 (03.02.94)
(21) International Application Number: PCT/GB93/01437 (22) International Filing Date: 9 July 1993 (09.07.93) (30) Priority data: 9215167.9 16 July 1992 (16.07.92) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventor; and (75) Inventor/Applicant (for US only) : EDWARDS, Paul, Andrew [GB/GB]; 3 Chase Lane, Dovercourt, Harwich, Essex CO12 4NB (GB). (74) Agents: MILLROSS, Christopher, Robert et al.; ICI Group Patents Services Dept., P.O. Box 6, Shire Park, Bessemer Road, Welwyn Garden City, Hertfordshire AL7 1HD (GB).		(81) Designated States: JP, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: THERMAL TRANSFER PRINTING RECEIVER SHEET		
(57) Abstract <p>A thermal transfer printing receiver sheet which comprises a substrate having a dye-receiving surface on one side and a backcoat on the other side wherein the backcoat comprises a sulphonated polyester and preferably a cellulosic polymer and an electrically conductive particulate material. The receiver is suitable for use in applications in which writability and adhesion of for example aqueous based gums to the backcoat are desired.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

Thermal Transfer Printing Receiver Sheet

This invention relates to a thermal transfer printing (TTP) receiver sheet and especially to a TTP receiver sheet having a backcoat which possesses improved properties.

5 Thermal transfer printing is a printing process in which a dye is caused, by thermal stimuli, to transfer from a dye sheet to a receiver sheet. In such processes, the dye sheet and receiver sheet are placed in intimate contact, the thermal stimuli are applied to the dye sheet and the dye sheet and receiver sheet are then separated. By applying
10 the thermal stimuli to pre-determined areas in the dye-sheet, the dye is selectively transferred to the receiver to form the desired image.

Receiver sheets conventionally comprise a substrate with a dye-receiving polar surface on one side, into which a dye is thermally transferable and retainable. Where the substrate is itself polar and
15 capable of receiving a dye, the dye may be transferred directly to a surface of the substrate. However receiver sheets typically comprise a substrate supporting a receiver layer specifically tailored to receive the dye.

Receiver sheets may also comprise a backcoat on the opposite
20 surface to the dye-receiving surface which is typically employed to impart desirable characteristics to the sheet to improve both processing of the sheet during application of the TTP image and the end use properties of the sheet depending on the particular application of the sheet.

25 In many applications, for example for use as post cards and greetings cards, it is a requirement that the backcoat be capable of receiving drafting marks from for example pencils and inks, both aqueous and solvent based. Other characteristics which the backcoat should desirably possess when employed in such applications include a
30 good resistance to smudging of the applied drafting marks and an ability to accept aqueous based adhesives, for example to allow adherence of a postage stamp to the sheet.

Hitherto, receiver sheets for use in such applications have been
35 deficient in certain respects due to the combination of properties which it is desired that such a receiver sheet should possess.

However, we have now devised a receiver sheet which has a backcoat having an improved combination of characteristics which make the sheet particularly suitable for use in applications in which drafting marks are to be applied to the backcoat and/or adhesive, especially aqueous based adhesive is to be accepted by the backcoat.

According to a first aspect of the invention there is provided a thermal transfer printing receiver sheet which comprises a substrate having a dye-receiving surface on one side and a backcoat on the other side wherein the backcoat comprises a sulphonated polyester.

The backcoat of receiver sheets according to the first aspect of the invention are compatible with both aqueous based and non aqueous based materials and thus provide good adhesion to both non aqueous and aqueous based adhesives which may be employed to adhere labels, stamps and the like to the receiver backcoat. Furthermore, this compatibility improves the capability to receive non-aqueous and aqueous based inks and provides an improved writability for the receiver backcoat.

Suitably, the sulphonated polyester in the backcoat is a salt of a sulphonated polyester, for example an alkali metal salt and preferably an ammonium salt. Particularly preferred sulphonated polyesters include Eastman Size WD30, AQ29, AQ38 and AQ55 (solid or dispersion) available from Eastman Kodak and Toyobo MD1400 sulphonated polyesters.

The sulphonated polyester is suitably present in the backcoat in an amount of at least 30% by weight of the back coat to maintain the mechanical integrity of the coating and to avoid an undesirable decrease in the adhesion of the backcoat to the substrate. Preferably the sulphonated polyester is present in an amount of up to 80% by weight of the backcoat and especially 40 to 70% by weight.

Suitably, the sulphonated polyester has an average molecular weight of up to about 30000 and preferably in the range 10000 to 20000. The sulphonated polyester may be of any viscosity which allows application to the substrate but desirably has a melt viscosity at 200°C of up to about 50000 poise as measured using the Sieglaff/McKelvey capillary rheometer at 100 sec⁻¹ shear rate.

Desirably the sulphonated polyester has a glass transition temperature (T_g) of up to about 100°C.

The sulphonated polyester is suitably hydrophilic and is desirably soluble or dispersible in water as this provides improved compatibility with aqueous based adhesives.

We have also found that writability may be improved by the incorporation of a cellulosic polymer into the backcoat of a receiver sheet. Accordingly, a second aspect of the invention provides a thermal transfer printing receiver sheet which comprises a substrate having a dye-receiving surface on one side and a backcoat on the other side wherein the backcoat comprises a sulphonated polyester and a cellulosic polymer.

The cellulosic polymer is desirably polar or a salt as this aids water retention thus providing improved writability for aqueous based inks and also improved compatibility for aqueous based adhesives. Suitably the cellulosic polymers include a hydroxyalkylcellulose, for example hydroxypropylcellulose and METHOCEL E50 LV, a hydroxypropylmethylcellulose, and especially a salt of carboxyalkylcellulose, for example COURLOSE F20G, a sodium carboxymethylcellulose available from Courtaulds.

Suitably, the cellulosic polymer is present in the backcoat in sufficient amount to improve the writability of the backcoat, preferably at least 2% and more preferably at least 4% by weight of the backcoat. Desirably the cellulosic polymer is present in an amount not exceeding 15% and preferably not exceeding 10% by weight of the backcoat as too high a level of the cellulosic polymer may give rise to undesirable characteristics including humid blocking.

A receiver according to the invention preferably comprises an electrically conductive material, for example a conductive particulate material or a conductive polymer, in the backcoat to improve the antistatic performance of the receiver.

A further aspect of the invention provides a thermal transfer printing receiver sheet which comprises a substrate having a dye-receiving surface on one side and a backcoat on the other side wherein the backcoat comprises a sulphonated polyester and has a surface resistivity in the range 1×10^8 to 1×10^{13} Ohms per square.

If the sulphonated polyester does not itself provide a backcoat having the desired surface resistivity, the backcoat may further comprise an electrically conducting material to provide a backcoat having the desired resistivity.

5 If the backcoat resistivity is too low, problems due to dipolar charge formation may occur wherein there is a small charge on the dye-receiving surface of the receiver and effectively no charge on the backcoat. This charge imbalance may cause receivers to stick together when stacked. Further, if the resistivity is too high, there may be
10 an undesirable build up of static charge on the printer.

Preferably, the backcoat has a surface resistivity of 1×10^9 to 1×10^{12} Ohms per square. A receiver which has a small charge of the same polarity on both the backcoat and the dye-receiving surface may provide optimum feed and stacking performance.

15 By employing a conductive particulate material, desirably as a particle having a conductive coating, we have found that excellent antistatic properties may be secured in addition to the improved adhesion and writability.

Accordingly, a further aspect of the invention provides a thermal
20 transfer printing receiver sheet which comprises a substrate having a dye-receiving surface on one side and a backcoat on the other side wherein the backcoat comprises a sulphonated polyester and a conductive particulate material, preferably comprising a particle having an electrically conductive coating.

25 The improved antistatic properties reduce handling problems and the tendency for adjacent sheets to stick to each other whilst in a stack. Desirably, the conductive material conducts electronically rather than ionically. This provides the advantage that the conductance of the backcoat is independent of the moisture content of
30 the environment and the antistatic performance hence does not vary with humidity. Suitably the conductive particulate material is sufficiently soft to reduce the possibility that the backcoat may score the dye-receiving surface of an adjacent receiver when receivers are arranged in a stack.

35 The conductive particulate material may comprise particles of a conductive material but preferably comprises a particulate material

for example alumina and silica, which is covered with a conductive coating for example a metal oxide doped with a metal. An especially preferred particulate material comprises particles of barium sulphate which are coated with tin oxide doped with antimony which is available from Sachtleben Chemie under the trade name SACON P401.

The conductive material is suitably present in the backcoat in a sufficient quantity to provide improved antistatic performance, preferably at least 15% by weight of the backcoat. Suitably the amount of the conductive material does not exceed 70% by weight as this may render the backcoat unacceptably fragile. Furthermore, as consumers conventionally require white receiver sheet for many applications, the conductive material, if not white in colour, may impart an undesirable colour to the receiver sheet if present in the backcoat in large quantities. Desirably the conductive material is present in the backcoat in an amount of 20 to 50% by weight of the back coat.

Suitably the backcoat has a coat weight in the range 0.5 to 10 gm⁻² and preferably 1.5 to 4gm⁻². The surface resistivity of the backcoat is dependent upon its coat weight and composition and it will be appreciated that, for a given backcoat composition, the coat weight will be selected to provide a surface resistivity within the range 1x10⁸ to 1x10 Ohms per square.

The backcoat may comprise other components as desired for a particular application. The backcoat suitably comprises a filler to reduce image retransfer and blocking. Suitable fillers include micronised polymers which are preferably cross-linkable, for example melamine and urea formaldehyde, available under the trade name PERGOPAK M3, or insoluble in conventional coating solvents for example water, methanol, methyl ethyl ketone and acetone, including for example polyethylene and polytetrafluoroethylene.

The filler, excluding the conductive particulate material if present, is suitably present in an amount of up to 20% by weight and preferably in an amount of 2 to 10% by weight of the backcoat.

Desirably the backcoat also comprises an aqueous dispersing agent to reduce problems of particulate aggregation, suitable agents including surfactants for example SYNPERONIC T/908 available from ICI.

The dispersing agent is suitably present in an amount of up to 10% and preferably in an amount of 0.2 to 2% by weight of the backcoat.

Receiver sheets according to the present invention suitably comprise a substrate having a dye-receiving surface on one side.

5 Substrates which are themselves dye-receiving materials, for example polyvinyl chloride may be adapted by the provision of a smooth surface texture. In most cases, however, receiver sheets comprise a substrate having a receiver layer on one side of the substrate, which layer comprises a dye-receptive composition into which thermally
10 transferable dyes can readily pass in a TTP process.

Receiver sheet substrates known in the art may be employed in the present invention including cellulose fibre paper desirably with a polymer coating, thermoplastic films for example polyethylene terephthalate (desirably biaxially orientated), filled and/or voided
15 thermoplastic films for example pearl film, and laminates of two or more substrate materials.

The receiver layer preferably comprises at least one dye-receptive polymer which is an amorphous polyester, polyvinyl chloride. The polymer may comprise other polymers for example
20 polyvinyl alcohol/polyvinyl chloride copolymer as desired.

Commercially available examples of suitable amorphous polyesters include VITEL PE200 (Goodyear) and VYLON polyesters (Toyobo) especially grades 103, 200 and 290. Different grades of polyester may be mixed to provide a suitable composition as desired.

25 If desired, the receiver layer may also comprise a release agent. A preferred release agent is the thermoset reaction product of at least one silicone having a plurality of hydroxyl groups per molecule and at least one organic polyfunctional N-(alkoxymethyl) amine resin which is reactive with the hydroxyl groups under acid catalysed
30 conditions.

If desired the backcoat and/or the receiver layer may be applied be separated from the substrate by a conventional primer layer known in the art which may be employed for example to improve adhesion of the the backcoat and/or receiver layer to the substrate.

35 The coatings applied to the substrate may be applied by conventional coating techniques for example gravure coating, reverse

gravure coating and using a Meyer bar. The coating may be deposited as a solution or a dispersion as desired from any suitable solvent for example water, acetone, methyl ethyl ketone and methanol which is then suitably removed by drying. Suitable drying conditions include, heating in air at a temperature of 60 to 110°C for a period of 30 seconds to 2 minutes according to the coating solvent employed.

The invention is illustrated by the following non-limiting examples.

Example 1

A receiver according to the present invention was produced by coating onto a sample of Melinex D969 polyester film available from ICI with a Meyer bar, a dispersion containing 8% by weight of solids, in a solvent system comprising water:methanol:methyl ethyl ketone in a 50:25:25 volume ratio, of the following composition

	<u>Composition (Parts by Weight)</u>			
	<u>1A</u>	<u>1B</u>	<u>1C</u>	<u>1D</u>
EASTMAN SIZE WD30 (sulphonated polyester)	51	50	68	48
SACON P401 (conductive particles)	43	43	25	45
COURLOSE F20G (sodium carboxymethylcellulose)	6	-	5	-
METHOCEL E50 LG (Hydroxypropylmethylcellulose)	-	7	-	7
SYNPERONIC T/908 (surfactant)	0.4	0.5	0.5	0.5
PERGOPAK M3 (filler)	3	6	6	6

The backcoat was dried at between 60 and 110°C for between 30 seconds to 2 minutes to produce a backcoat having a weight of 1.3, 2.5, 2.0 and 2.5gm⁻² for receiver sheets 1A to 1D respectively.

Example 2

A receiver sheets produced according to Examples 1A to 1D were tested (according to the tests below) to assess various characteristics thereof. A

commercially available receiver sheet having a writable backcoat comprising a styrene/maleic anhydride copolymer was also tested for comparative purposes.

Writability:

5 Marks were applied to the receiver backcoat using a variety of pencils
of different hardnesses and variety of pens having different inks
including, aqueous based and mixed solvent non-aqueous based inks. The
marks were then visually observed for their line density and uniformity.

Smudge Test:

10 Ink and pencil marks were applied to the backcoat as in the writability
test. The marks were left for a set period and then rubbed with a
finger to assess the degree to which the marks smudged.

Stamp Adhesion:

15 A stamp having an aqueous-based adhesive gum was wetted, applied to the
backcoat and left for 2 minutes after which time, it was attempted to
peel the stamp from the backcoat.

Resistivity:

20 The receiver sheet was stored for a period of 1 hour at a temperature of
25°C in a relative humidity of 60%, after which time, the resistivity of
the backcoat was measured using a Model TI500 Surface Resistivity meter
from Static Control Services.

Static Charge:

The static charge on the backcoat was measured after the receiver sheet
had been passed through a Hitachi VY200 printer.

Stacking:

25 100 receiver sheets produced in accordance with Example 1 were passed
through a Hitachi VY200 printer and the stacking of the sheets was
observed.

30

Results

<u>Test</u>	<u>Examples 1A, 1B, 1C, 1D</u>	<u>Prior Art</u>
Writability: Pencils	Good line uniformity and density	Good line uniformity and density
5 Writability: Solvent based ink pens	Good line uniformity and density	Good line uniformity and density
10 Writability: Biro pens	Good line uniformity and density	Good line uniformity and density
Writability: Aqueous based ink pens	Good line uniformity and density without any ink retraction	Ink retraction occurs
15 Smudge Resistance: Aqueous based ink pens Pencils	Good resistance Slight smudge	Smudge easily Smudge easily
Stamp Adhesion	Stamp damaged when attempting removal	Remove easily without damage to stamp
20 Surface Resistivity	1×10^{10}	1×10^{14}
Post Printing Static	6kV	20+kV
25 Post Printing Stacking	Good	Levitation of sheet in outfeed and printer jamming due to back feed to back feeding

30 The receiver sheets produced in Example 1 exhibited excellent writeability and compared with the prior art sheet have improved writability with aqueous-based inks, improved smudge properties with all of the pencils and different inks tested, improved adhesion to an aqueous based adhesive and

superior stacking properties due to the lower surface resistivity and post printing static.

Claims

1. A thermal transfer printing receiver sheet which comprises a substrate having a dye-receiving surface on one side and a backcoat on the other side wherein the backcoat comprises a sulphonated polyester.
2. A receiver sheet according to claim 1 in which the sulphonated polyester comprises a salt, preferably an ammonium salt, of a sulphonated polyester.
3. A receiver sheet according to claim 1 or claim 2 in which the sulphonated polyester is present in the backcoat in an amount in the range 30% to 80% by weight of the back coat.
4. A receiver sheet according to any preceding claim in which the sulphonated polyester has an average molecular weight of up to about 30000.
5. A receiver sheet according to any preceding claim in which the backcoat has a surface resistivity in the range 1×10^8 to 1×10^{13} Ohms per square.
6. A receiver sheet according to any preceding claim in which the backcoat further comprises a conductive particulate material.
7. A receiver sheet according to claim 6 in which the conductive material is present in the backcoat in an amount of 15% to 70% by weight of the backcoat.
8. A receiver sheet according to any preceding claim in which the backcoat further comprises a cellulosic polymer.
9. A receiver sheet according to claim 8 in which the cellulosic polymer comprises a hydroxyalkylcellulose and/or a salt of carboxyalkylcellulose.
10. A receiver sheet according to claim 8 or claim 9 in which the cellulosic polymer is present in the backcoat in an amount not exceeding 15% by weight of the backcoat.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 93/01437

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 B41M5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 5 B41M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 10, no. 151 (M-483)(2208) 31 May 1986 & JP,A,61 003 796 (MITSUBISHI SEISHI KK) see abstract ---	1-10
A	EP,A,0 272 400 (EASTMAN KODAK) 29 June 1988 see claims 1-11 ---	1-10
A	PATENT ABSTRACTS OF JAPAN vol. 11, no. 183 (M-598)(2630) 12 June 1987 & JP,A,62 011 680 (TOMOEGAWA PAPER) see abstract ---	1-10
	-/--	

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 November 1993

Date of mailing of the international search report

23. 11. 93

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

FOUQUIER, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 93/01437

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 11, no. 191 (M-600)(2638) 19 June 1987 & JP,A,62 016 185 (TOMOEGAWA PAPER) see abstract -----	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 93/01437

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0272400	29-06-88	US-A- 4727057	23-02-88
		CA-A- 1283539	30-04-91
		JP-A- 63115791	20-05-88
