United States Patent [19]

Chia et al.

[11] **3,830,635**

[45]***Aug. 20, 1974**

[54] **ALUMINUM NICKEL ALLOY ELECTRICAL CONDUCTOR AND METHOD FOR MAKING SAME**

[75] Inventors: **Enrique C. Chia; Roger J. Schoerner,** both of Carrollton, Ga.

[73] Assignee: **Southwire Company,** Carrollton, Ga.

[*] Notice: The portion of the term of this patent subsequent to Apr. 30, 1991, has been disclaimed.

[22] Filed: **July 9, 1971**

[21] Appl. No.: **161,324**

Related U.S. Application Data

[63] Continuation-in-part of Ser. No. 147,196, May 26, 1971, abandoned.

[52] **U.S. Cl.** ..... **29/193,** 29/527.7, 75/138, 75/143, 75/147, 148/2, 148/11.5 A, 148/32, 164/76

[51] **Int. Cl.** **B21c 1/00,** C22f 1/04

[58] **Field of Search** ..... 75/138, 139, 148, 147, 75/146, 140, 141, 142, 143, 144; 164/76; 148/32, 32.5, 2, 11.5 A; 29/193, 527.7

[56] **References Cited**

UNITED STATES PATENTS

1,579,481	4/1926	Hybinette	75/138
1,916,087	6/1933	Titus	75/147
1,945,297	1/1934	Sterner-Rainer	75/147
2,245,166	6/1941	Stroup	75/147
3,697,260	10/1972	Hunsicker	75/139

Primary Examiner—R. Dean
Attorney, Agent, or Firm—Van C. Wilks; Herbert M. Hanegan

[57] **ABSTRACT**

Aluminum alloy electrical conductors are produced from aluminum base alloys containing from about 0.20 percent to about 1.60 percent by weight nickel, from about 0.30 percent to about 1.30 percent by weight cobalt, optionally up to about 2.00 percent by weight of additional alloying elements, and from about 97.00 percent to about 99.50 percent by weight aluminum. The alloy conductors have an electrical conductivity of at least 57 percent, based on the International Annealed Copper Standard (IACS), and improved properties of increased thermal stability, tensile strength, percent ultimate elongation, ductility, fatigue resistance and yield strength as compared to conventional aluminum alloys of similar electrical properties.

25 Claims, No Drawings

ALUMINUM NICKEL ALLOY ELECTRICAL CONDUCTOR AND METHOD FOR MAKING SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application is a continuation-in-part of our co-pending application Ser. No. 147,196, filed May 26, 1971, now abandoned.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention concerns an aluminum base alloy especially suited for producing high strength light weight electrical conductors including wire, rod and other such articles of manufacture. The present alloy is particularly well suited for use as a wire, rod, cable, bus bar, tube connector, termination, receptacle plug, or electrical contact device for conducting electricity.

Aluminum base alloys are finding wider acceptance in the marketplace of today because of their light weight and low cost. One area where aluminum alloys have found increasing acceptance is in the replacement of copper in the manufacture of electrically conductive wire. Conventional electrically conductive aluminum alloy wire (referred to as EC) contains a substantial amount of pure aluminum and trace amounts of impurities such as silicon, vanadium, iron, copper, manganese, magnesium, zinc, boron and titanium.

Even though desirable in terms of weight and cost, aluminum alloys have received far less than complete acceptance in the electrical conductor marketplace. One of the chief reasons for the lack of complete acceptance is the range of physical properties available with conventional EC aluminum alloy conductors. If the physical properties, such as thermal stability, tensile strength, percent elongation, ductility and yield strength, could be improved significantly without substantially lessening the electrical conductivity of the finished product, a very desirable improvement would be achieved. It is accepted, however, that addition of alloying elements, as in other aluminum alloys, reduces conductivity while improving the physical properties. Consequently, only those additions of elements which improve physical properties without substantially lessening conductivity will yield an acceptable and useful product.

It is an object of the present invention, therefore, to provide a new aluminum alloy electrical conductor which combines improved physical properties with acceptable electrical conductivity. These and other objects, features and advantages of the present invention will be apparent from a consideration of the following detailed description of an embodiment of the invention.

In accordance with the invention, the present aluminum base alloy is prepared by mixing nickel, cobalt and optionally other alloying elements with aluminum in a furnace to obtain a melt having requisite percentages of elements. It has been found that suitable results are obtained with nickel present in a weight percentage of from about 0.20 percent to about 1.60 percent. Superior results are achieved when nickel is present in a weight percentage of from about 0.50 percent to about 1.00 percent and particularly superior and preferred results are obtained when nickel is present in a percentage by weight of from about 0.60 percent to about 0.80 percent.

Suitable results are obtained with cobalt present in a weight percentage of from about 0.30 percent to about 1.30 percent. Superior results are achieved when cobalt is present in a weight percentage of from about 0.40 percent to about 0.80 percent and particularly superior and preferred results are obtained when cobalt is present in a percentage by weight of from about 0.45 percent to about 0.65 percent.

The aluminum content of the present alloy may vary from about 97.00 percent to about 99.50 percent by weight with superior results being obtained when the aluminum content varies between about 97.80 percent and about 99.20 percent by weight. Since the percentages for maximum and minimum aluminum do not correspond with the maximums and minimums for alloying elements, it should be apparent that suitable results are not obtained if the maximum percentages for all alloying elements are employed. If commercial aluminum is employed in preparing the present melt, it is preferred that the aluminum, prior to adding to the melt in the furnace, contain no more than about 0.10 percent total of trace impurities.

Optionally the present alloy may contain an additional alloying element of group or alloying elements. The total concentration of the optional alloying elements may be up to about 2.00 percent by weight; preferably from about 0.10 percent to about 1.50 percent by weight is employed. Particularly superior and preferred results are obtained when from about 0.10 percent to about 1.00 percent by weight of total additional alloying elements is employed.

Additional alloying elements include the following:

ADDITIONAL ALLOYING ELEMENTS

Magnesium	Scandium	Terbium
Iron	Thorium	Erbium
Copper	Tin	Neodymium
Silicon	Molybdenum	Indium
Zirconium	Zinc	Boron
Cerium	Tungsten	Thallium
Niobium	Chromium	Rubidium
Hafnium	Bismuth	Titanium
Lanthanum	Antimony	Carbon
Tantalum	Vanadium	Cesium
Rhenium	Yttrium	Dysprosium

Superior results are obtained with the following additional alloying elements in the percentages, by weight, as shown:

PREFERRED ADDITIONAL ALLOYING ELEMENTS

Magnesium	0.001 to 1.00%
Iron	0.001 to 1.00%
Copper	0.05 to 1.00%
Silicon	0.05 to 1.00%
Zirconium	0.01 to 1.00%
Niobium	0.01 to 2.00%
Tantalum	0.01 to 2.00%
Yttrium	0.01 to 1.00%
Scandium	0.01 to 1.00%
Thorium	0.01 to 1.00%
Rare Earth Metals	0.01 to 2.00%
Carbon	0.01 to 1.00%

Particularly superior and preferred results are obtained with the use of iron or magnesium as the additional alloying element. Suitable results are obtained with magnesium or iron in a percentage range of from

about 0.001 to about 1.00 percent by weight with superior results being obtained when from about 0.025 percent to about 0.50 percent by weight is used. Particularly superior and preferred results are obtained when from about 0.03 to about 0.10 percent by weight of magnesium or iron is employed.

The rare earth metals may be present either individually within the percentage range stated or as a partial or total group, the total percentage of the group being within the percentage range stated previously.

It should be understood that the additional alloying elements may be present either individually or as a group of two or more of the elements. It should be understood, however, that if two or more of the additional alloying elements are employed, the total concentration of additional alloying elements should not exceed about 2.00 percent by weight.

After preparing the melt, the aluminum alloy is preferably continuously cast into a continuous bar by a continuous casting machine and then, substantially immediately thereafter, hot-worked in a rolling mill to yield a continuous aluminum alloy rod.

One example of a continuous casting and rolling operation capable of producing continuous rod as specified in this application is contained in the following paragraphs. It should be understood that other methods of preparation may be employed to obtain suitable results but that preferable results are obtained with continuous processing. Such other methods include conventional extrusion and hydrostatic extrusion to obtain rod or wire directly, sintering an aluminum alloy powder to obtain rod or wire directly, casting rod or wire directly from a molten aluminum alloy, and conventional casting of aluminum alloy billets which are subsequently hot-worked to rod and drawn with intermediate anneals into wire.

CONTINUOUS CASTING AND ROLLING OPERATION

A continuous casting machine serves as a means for solidifying the molten aluminum alloy metal to provide a cast bar that is conveyed in substantially the condition in which it solidifed from the continuous casting machine to the rolling mill, which serves as a means for hot-forming the cast bar into rod or another hot-formed product in a manner which imparts substantial movement to the cast bar along a plurality of angularly disposed axes.

The continuous casting machine is of conventional casting wheel type having a casting wheel with a casting groove in its periphery which is partially closed by an endless belt supported by the casting wheel and an idler pulley. The casting wheel and the endless belt cooperate to provide a mold into one end of which molten metal is poured to solidify and from the other end of which the cast bar is emitted in substantially that condition in which it solidified.

The rolling mill is of conventional type having a plurality of roll stands arranged to hot-form the cast bar by a series of deformations. The continuous casting machine and the rolling mill are positioned relative to each other so that the cast bar enters the rolling mill substantially immediately after solidification and in substantially that condition in which it solidified. In this condition, the cast bar is at a hot-forming temperature within the range of temperatures for hot-forming the cast bar at the initiation of hot-forming without heating between the casting machine and the rolling mill. In the event that it is desired to closely control the hot-forming temperature of the cast bar within the conventional range of hot-forming temperatures, means for adjusting the temperature of the cast bar may be placed between the continuous casting machine and the rolling mill without departing from the inventive concept disclosed herein.

The roll stands each include a plurality of rolls which engage the cast bar. The rolls of each roll stand may be two or more in number and arranged diametrically opposite from one another or arranged at equally spaced positions about the axis of movement of the cast bar through the rolling mill. The rolls of each roll stand of the rolling mill are rotated at a predetermined speed by a power means such as one or more electric motors and the casting wheel is rotated at a speed generally determined by its operating characteristics. The rolling mill serves to hot-form the cast bar into a rod of a cross-sectional area substantially less than that of the cast bar as it enters the rolling mill.

The peripheral surfaces of the rolls of adjacent roll stands in the rolling mill change in configuration; that is, the cast bar is engaged by the rolls of successive roll stands with surfaces of varying configuration, and from different directions. This varying surface engagement of the cast bar in the roll stands functions to knead or shape the metal in the cast bar in such a manner that it is worked at each roll stand and also to simultaneously reduce and change the cross-sectional area of the cast bar into that of the rod.

As each roll stand engages the cast bar, it is desirable that the cast bar be received with sufficient volume per unit of time at the roll stand for the cast bar to generally fill the space defined by the rolls of the roll stand so that the rolls will be effective to work the metal in the cast bar. However, it is also desirable that the space defined by the rolls of each roll stand not be overfilled so that the cast bar will not be forced into the gaps between the rolls. Thus, it is desirable that the rod be fed toward each roll stand at a volume per unit of time which is sufficient to fill, but not overfill, the space defined by the rolls of the roll stand.

As the cast bar is received from the continuous casting machine, it usually has one large flat surface corresponding to the surface of the endless band and inwardly tapered side surfaces corresponding to the shape of the groove in the casting wheel. As the cast bar is compressed by the rolls of the roll stands, the cast bar is deformed so that it generally takes the cross-sectional shape defined by the adjacent peripheries of the rolls of each roll stand.

Thus, it will be understood that with this apparatus, cast aluminum alloy rod of an infinite number of different lengths is prepared by simultaneous casting of the molten aluminum alloy and hot-forming or rolling the cast aluminum bar. The continuous rod has a minimum electrical conductivity of 57 IACS and may be used in conducting electricity or it may be drawn to wire of a smaller cross-sectional diameter.

To produce wire of various gauges, the continuous rod produced by the casting and rolling operation is processed in a reduction operation. The unannealed rod (i.e., as rolled to *f* temper) is cold-drawn through a series of progressively constricted dies, without intermediate anneals, to form a continuous wire of desired diameter. It has been found that the elimination of in-

termediate anneals is preferable during the processing of the rod and improves the physical properties of the wire. Processing with intermediate anneals is acceptable when the requirements for physical properties of the wire permit reduced values. The conductivity of the hard-drawn wire is at least 58 percent IACS. If greater conductivity or increased elongation is desired, the wire may be annealed or partially annealed after the desired wire size is obtained and cooled. Fully annealed wire has a conductivity of at least 59 IACS. At the conclusion of the drawing operation and optional annealing operation, it is found that the alloy wire has the properties of improved tensile strength and yield strength together with improved thermal stability, percent ultimate elongation and increased ductility and fatigue resistance as specified previously in this application. The annealing operation may be continuous as in resistance annealing, induction annealing, convection annealing by continuous furnaces or radiation annealing by continuous furnaces, or, preferably, may be batch annealed in a batch furnace. When continuously annealing, temperatures of about 450°F to about 1,200°F may be employed with annealing times of about 5 minutes to about 1/10,000 of a minute. Generally, however, continuous annealing temperatures and times may be adjusted to meet the requirements of the particular overall processing operation so long as the desired physical properties are achieved. In a batch annealing operation, a temperature of approximately 400°F to about 750°F is employed with residence times of about 30 minutes to about 24 hours. As mentioned with respect to continuous annealing, in batch annealing the times and temperatures may be varied to suit the overall process so long as the desired physical properties are obtained.

It has been found that the properties of a Number 10 gauge (American wire gauge) fully annealed soft wire of the present alloy vary between the following figures:

Conductivity	Tensile Strength, psi.	% Elongation	Yield Strength, psi.
58%-63+%	12,000-24,000	12%-30%	8,000-18,000

A more complete understanding of the invention will be obtained from the following examples:

EXAMPLE 1

Various melts were prepared by adding the required amount of alloying elements to 1,816 grams of molten aluminum, containing less than 0.10 percent trace element impurities, to achieve a percentage concentration of elements as shown in the accompanying table; the remainder being aluminum. Graphite crucibles were used except in those cases where the alloying elements were known carbide formers, in which cases aluminum oxide crucibles were used. The melts were held for sufficient times and at sufficient temperatures to allow complete solubility of the alloying elements with the base aluminum. An argon atmosphere was provided over the melt to prevent oxidation. Each melt was continuously cast on a continuous casting machine and immediately hot-rolled through a rolling mill to ⅜ inch continuous rod. Wire was then drawn and annealed from the rod (soft [annealed] wire from hard [as rolled] rod). The final wire diameter obtained was 0.1019 inches, 10 gauge AWG.

The types of alloys employed and the results of the tests performed thereon are as follows:

Ni	Fe	Mg	Co	UTS	%Elong	%IACS
0.80		0.08	0.80	18,900	25.6	60.06
0.30		0.10	0.90	19,040	22.0	59.75
0.40	0.80	0.10	0.40	19,400	23.3	60.65

%Elong. = Percent ultimate elongation
UTS = Ultimate Tensile Strength
%IACS = Conductivity in Percentage IACS

EXAMPLE 2

An additional alloy melt was prepared according to Example 1 having a composition as follows in weight percent:

Nickel	—	0.60%
Cobalt	—	0.60%
Magnesium	—	0.07%
Aluminum	—	Remainder

The melt was processed to a No. 10 gauge soft wire. The physical properties of the wire were as follows:

Ultimate Tensile Strength	—	18,800 psi
Percent Ultimate Elongation	—	21%
Conductivity	—	59.05% IACS

EXAMPLE 3

An additional alloy melt was prepared according to Example 1 having a composition as follows in weight percent:

Nickel	—	0.80%
Cobalt	—	0.50%
Misch Metal	—	1.0%
Aluminum	—	Remainder

Misch metal is a commercial designation for a blend of rare earth metals and Thorium obtained during the processing of Thorium metal.

The melt was processed to a No. 10 gauge soft wire. The physical properties of the wire were as follows:

Ultimate Tensile Strength	—	18,500 psi
Percent Ultimate Elongation	—	19%
Conductivity	—	59.2% IACS

EXAMPLE 4

An additional alloy melt was prepared according to Example 1 having a composition as follows in weight percent:

Nickel	—	0.80%
Cobalt	—	0.40%
Niobium	—	0.20%
Tantalum	—	0.20%
Aluminum	—	Remainder

The melt was processed to a No. 10 gauge soft wire. The physical properties of the wire were as follows:

Ultimate Tensile Strength	—	19,880 psi
Percent Ultimate Elongation	—	19.6%
Conductivity	—	59.3% IACS

EXAMPLE 5

An additional alloy melt was prepared according to Example 1 having a composition as follows in weight percent:

Nickel	—	0.60%
Cobalt	—	0.35%
Copper	—	0.20%
Silicon	—	0.18%
Aluminum	—	Remainder

The melt was processed to a No. 10 gauge soft wire. The physical properties of the wire were as follows:

Ultimate Tensile Strength	—	18,000 psi
Percent Ultimate Elongation	—	19.3%
Conductivity	—	59.5% IACS

EXAMPLE 6

An additional alloy melt was prepared according to Example 1 having a composition as follows in weight percent:

Nickel	—	0.80%
Cobalt	—	0.45%
Zirconium	—	0.30%
Aluminum	—	Remainder

The melt was processed to a No. 10 gauge soft wire. The physical properties of the wire were as follows:

Ultimate Tensile Strength	—	18,900 psi
Percent Ultimate Elongation	—	18.8%
Conductivity	—	59.9% IACS

EXAMPLE 7

Various melts were prepared by adding the required amount of alloying elements to 1,816 grams of molten aluminum, containing less than 0.10 percent trace element impurities, to achieve a percentage concentration of elements as shown in the accompanying table; the remainder being aluminum. Graphite crucibles were used except in those cases where the alloying elements were known carbide formers, in which cases aluminum oxide crucibles were used. The melts were held for sufficient times and at sufficient temperatures to allow complete solubility of the alloying elements with the base aluminum. An argon atmosphere was provided over the melt to prevent oxidation. Each melt was continuously cast on a continuous casting machine and immediately hot-rolled through a rolling mill to ⅜ inch continuous rod. Wire was then drawn and annealed from the rod which had been annealed for five hours at 650°F (soft [annealed] wire from soft [annealed] rod). The final wire diameter obtained was 0.1019 inches, 10 gauge AWG.

The types of alloys employed and the results of the tests performed thereon are as follows:

TABLE I

Ni	Fe	Mg	Co	UTS	%Elong.	%IACS
0.80		0.08	0.80	16,500	26.2	61.10
0.30		0.10	0.90	16,850	24.3	60.40
0.40	0.80	0.10	0.40	17,100	25.0	60.90

ADDITIONAL EXAMPLES

Additional alloy melts were prepared according to Example 1. The composition and the physical properties of No. 10 gauge soft wire of the alloy melts were as follows:

TABLE 2

Example	Ni	Co	Mg	UTS in psi	% Elongation	% IACS Conductivity
8	0.2	0.6		18,900	26.9	60.55
9	0.2	0.8		18,600	22.8	61.23
10	0.8	0.6	0.1	17,800	23.0	60.50

Through testing and analysis of an alloy containing 0.80 weight percent nickel, 0.30 weight percent cobalt, and the remainder aluminum, it has been found that the present aluminum base alloy after cold working includes an intermetallic compound precipitate. The compound is identified as nickel aluminate ($NiAl_3$). The nickel intermetallic compound is found to be very stable and expecially so at high temperatures. The compound also has a low tendency to coalesce during annealing of products formed from the alloy and the compound is generally incoherent with the aluminum matrix. The mechanism of strengthening for this alloy is in part due to the dispersion of the nickel intermetallic compound as a precipitate throughout the aluminum matrix. The precipitate tends to pin dislocation sites which are created during cold working of the wire formed from the alloy. Upon examination of the nickel intermetallic compound precipitate in a cold drawn wire, it is found that the precipitates are oriented in the direction of drawing. In addition, it is found that the precipitates can be spherical, rod-like or plate-like in configuration and a majority are less than 2 microns in length and less than one-half micron in width.

Other intermetallic compounds may also be formed depending upon the constituents of the melt and the relative concentrations of the alloying elements. Those intermetallic compounds include the following: Ni_2Al_3, MgCoAl, Co_2Al_9, Co_4Al_{13}, Fe_2Al_5, $FeAl_3$, $CeAl_4$, $CeAl_2$, VAl_{11}, VAl_7, VAl_6, VAl_3, VAl_{12}, Zr_3Al, $LaAl_4$, $LaAl_2$, $FeNiAl_{10}$, Co_2Al_5, $FeNiAl_9$, Zr_2Al.

A characteristic of high conductivity aluminum alloy wires which is not indicated by the historical tests for tensile strength, percent elongation and electrical conductivity is the possible change in properties as a result of increases, decreases or fluctuations of the temperature of the strands. It is apparent that the maximum operating temperature of a strand or series of strands will be affected by this temperature characteristic. The

characteristic is also quite significant from a manufacturing viewpoint since many insulation processes require high temperature thermal cures. In tests which determine the decrease in tensile and yield strength in response to aging at established temperatures and times the aluminum alloy wire of the present invention has been found to have the characteristic of high thermal stability.

A significant aspect shown by the results of these tests is the lack of thermal stability obtainable with several aluminum alloys. The test sample wire identified as No. 2 and 3 show a significant decrease in thermal stability in the yield and tensile strength tests and alloy No. 2 has almost completely softened after a 550 hour soak period at 190°–200°C. On the other hand, the wire fabricated from the present alloy demonstrates a high degree of thermal stability by exhibiting zero decreases in yield and tensile strength.

For the purpose of clarity, the following terminology used in this application is explained as follows:

Aluminum alloy rod — A solid product that is long in relation to its cross-section. Rod normally has a cross-section of between 3 inches and 0.375 inches.

Aluminum alloy wire — A solid wrought product that is long in relation to its cross-section, which is square or rectangular with sharp or rounded corners or edges, or is round, a regular hexagon or a regular octagon, and whose diameter or greatest perpendicular distance between parallel faces is between 0.374 inches and 0.0031 inches.

While this invention has been described in detail with particular reference to preferred embodiments thereof, it will be understood that variations and modifications can be effected within the spirit and scope of the invention as described hereinbefore and as defined in the appended claims.

What is claimed is:

1. An aluminum alloy electrical conductor having a minimum conductivity of 57 percent IACS consisting essentially of from about 0.20 weight percent to about 1.60 weight percent nickel, from about 0.30 weight percent to about 1.30 weight percent cobalt, the remainder being aluminum with associated trace elements.

2. The aluminum alloy electrical conductor of claim **1**, further including an additional alloying element selected from the group consisting of magnesium and iron, in an amount ranging from 0.001 weight percent to 1.0 weight percent.

3. The aluminum alloy electrical conductor of claim **1**, further including iron as an additional alloying element in an amount ranging from about 0.1 percent to about 0.5 percent.

4. The aluminum alloy electrical conductor of claim **1**, further including magnesium as an additional alloying element in an amount ranging from about 0.1 percent to about 0.5 percent.

5. The aluminum alloy electrical conductor according to claim **1** wherein the weight percentages of the constituents are as follows:

Nickel	—	0.60% to 0.80%
Cobalt	—	0.45% to 0.65%
Magnesium	—	0.03% to 0.10%
Aluminum	—	97.80% to 99.20%.

6. The aluminum alloy conductor according to claim **1** wherein the weight percentages of the constituents are as follows:

Nickel	—	0.60% to 0.80%
Cobalt	—	0.45% to 0.65%
Iron	—	0.03% to 0.10%
Aluminum	—	97.80% to 99.20%.

7. The aluminum alloy electrical conductor according to claim **1**, wherein the weight percentages of the constituents are as follows:

Nickel	—	0.80%
Cobalt	—	0.50%
Misch Metal	—	1.0%
Aluminum	—	remainder.

8. The aluminum alloy electrical conductor according to claim **1** wherein the weight percentages of the constituents are as follows:

Nickel	—	0.80%
Cobalt	—	0.40%
Niobium	—	0.20%
Tantalum	—	0.20%
Aluminum	—	remainder.

9. The aluminum alloy electrical conductor according to claim **1** wherein the weight percentages of the constituents are as follows:

Nickel	—	0.60%
Cobalt	—	0.35%
Copper	—	0.20%
Silicon	—	0.18%
Aluminum	—	remainder.

10. The aluminum alloy electrical conductor according to claim **1** wherein the weight percentages of the constituents are as follows:

Nickel	—	0.80%
Cobalt	—	0.45%
Zirconium	—	0.30%
Aluminum	—	remainder.

11. The aluminum alloy electrical conductor of claim **1** wherein said conductor is in the form of a rod.

12. The aluminum alloy electrical conductor according to claim **1** wherein said conductor is in the form of a wire.

13. An aluminum alloy electrical conductor having a minimum conductivity of 57 percent IACS consisting essentially of from about 0.20 weight percent to about 1.60 weight percent nickel, from about 0.30 weight percent to about 1.30 weight percent cobalt, the remainder being aluminum with associated trace elements, said aluminum alloy electrical conductor having the following properties when measured as a No. 10 A.W.G. fully annealed wire:

Tensile strength:	12,000 – 24,000 psi
Elongation:	12 – 30%
Yield strength:	8,000 – 18,000 psi

14. The method of preparing an aluminum alloy conductor having a minimum conductivity of at least 57% IACS comprising the steps of:

A. alloying from about 0.20 weight percent to about 1.60 weight percent nickel, from about 0.30 to about 1.30 weight percent cobalt, the remainder being aluminum with associated trace elements;

B. casting the alloy in a moving mold formed between a groove in the periphery of a rotating casting wheel and a metal belt lying adjacent said groove for a portion of its length;

C. hot rolling the cast alloy substantially immediately after casting while the cast alloy is in substantially that condition as cast to form a continuous rod;

said aluminum alloy conductor having the following properties when measured as a fully annealed wire:

Tensile strength: at least 12,000 psi

Yield strength: at least 8,000 psi.

15. The method according to claim **14** including the further step of drawing said conductor through wire-drawing dies, without annealing the conductor between drawing dies, to form wire.

16. The method according to claim **14** wherein the alloying step also includes the addition of alloying elements taken from the group consisting of iron and magnesium, in an amount ranging from 0.001 to 1.0 percent, by weight.

17. The method according to claim **14** wherein the alloying step includes the addition of iron as an alloying element in an amount ranging from about 0.1 percent to about 0.5 percent, by weight.

18. The method according to claim **14** wherein the alloying step includes the addition of magnesium as an alloying element in an amount ranging from about 0.1 percent to about 0.5 percent, by weight.

19. The method according to claim **14** wherein the alloying step includes the addition of magnesium in an amount sufficient to yield an alloy having the following weight percentages:

Nickel	—	0.60% to 0.80%
Cobalt	—	0.45% to 0.65%
Magnesium	—	0.03% to 0.10%
Aluminum	—	97.80% to 99.20%.

20. The method according to claim **14** wherein the alloying step includes the addition of iron in an amount sufficient to yield an alloy having the following weight percentages:

Nickel	—	0.60% to 0.80%
Cobalt	—	0.45% to 0.65%
Iron	—	0.03% to 0.10%
Aluminum	—	97.80% to 99.20%.

21. The method according to claim **14** wherein the alloying step includes the addition of misch metal in an amount sufficient to yield an alloy having the following weight percentages:

Nickel	—	0.80%
Cobalt	—	0.50%
Misch metal	—	1.0%
Aluminum	—	remainder.

22. The method according to claim **14** wherein the alloying step includes the addition of niobium and tantalum in an amount sufficient to yield an alloy having the following weight percentages:

Nickel	—	0.80%
Cobalt	—	0.40%
Niobium	—	0.20%
Tantalum	—	0.20%
Aluminum	—	remainder.

23. The method according to claim **14** wherein the alloying step includes the addition of copper and silicon in an amount sufficient to yield an alloy having the following weight percentages:

Nickel	—	0.60%
Cobalt	—	0.35%
Copper	—	0.20%
Silicon	—	0.18%
Aluminum	—	remainder.

24. The method according to claim **14** wherein the alloying step includes the addition of zirconium in an amount sufficient to yield an alloy having the following weight percentages:

Nickel	—	0.80%
Cobalt	—	0.45%
Zirconium	—	0.30%
Aluminum	—	remainder.

25. The method according to claim **14** including the further step of:

D. drawing the rod through wire-drawing dies, without annealing the rod between drawing dies, to form wire; said wire having the following properties when measured as a No. 10 A.W.G. fully annealed wire:

Tensile strength:	12,000 – 24,000 psi
Elongation:	12 – 30%
Yield strength:	8,000 – 18,000 psi.

* * * * *