

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
16 May 2019 (16.05.2019)



(10) International Publication Number
WO 2019/092467 A1

(51) International Patent Classification:

C23C 2/02 (2006.01)	C22C 38/48 (2006.01)
C23C 2/06 (2006.01)	C22C 38/50 (2006.01)
C23C 2/28 (2006.01)	C22C 38/54 (2006.01)
C21D 9/46 (2006.01)	C22C 38/58 (2006.01)
C22C 38/00 (2006.01)	C21D 9/56 (2006.01)
C22C 38/02 (2006.01)	C21D 9/573 (2006.01)
C22C 38/06 (2006.01)	C21D 1/74 (2006.01)
C22C 38/38 (2006.01)	C21D 1/76 (2006.01)
C22C 38/46 (2006.01)	

(21) International Application Number:

PCT/IB2017/001343

(22) International Filing Date:

08 November 2017 (08.11.2017)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: **ARCELORMITTAL** [LU/LU]; 24-26, Boulevard d'Avranches, 1160 Luxembourg (LU).

(72) Inventors: **ZAPICO ALVAREZ, David**; 4 rue Vigne Saint-Avold, 57000 Metz (FR). **BERTRAND, Florence**; 82 Voie de la Liberté, 57160 Scy-Chazelles (FR). **GIROUX, Joris**; 37 Avenue Foch, 57000 Metz (FR).

(74) Agent: **PLAISANT, Sophie**; ArceloMittal France, R&D Intellectual Property, 6, rue André Campra, Immeuble le Cézanne, 93212 La Plaine Saint-Denis (FR).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: A GALVANNEALED STEEL SHEET

(57) Abstract: The present invention relates to a method for the manufacture of a galvanized steel sheet and a galvanized steel sheet.



A galvanized steel sheet

The present invention relates to a method for the manufacture of a galvanized steel sheet and a galvanized steel sheet. The invention is particularly well suited for the automotive industry.

With a view of saving the weight of vehicles, it is known to use high strength steels for the manufacture of automobile vehicle. For example for the manufacture of structural parts, mechanical properties of such steels have to be improved. It is known to add alloying elements to improve the mechanical properties of the steel. Thus, high strength steels or ultra-high strength steels having high mechanical properties including TRIP (Transformation-Induced Plasticity) steel, DP (Dual Phase) steels, HSLA (High-Strength Low Alloyed), TRIPLEX, DUPLEX are produced and used.

Usually, DP steels have a ferritic–martensitic microstructure. This results in a microstructure consisting of a soft ferrite matrix containing islands of martensite as the secondary phase (martensite increases the tensile strength). The overall behavior of DP steels is governed by among others the phases' volume fraction and morphology (grain size, aspect, ratio, etc.), in addition to the steel chemical composition. DP steels have high ultimate tensile strength (UTS, enabled by the martensite) combined with low initial yield stress (provided by the ferrite phase) and high early-stage strain hardening. These features render DP steels ideal materials for automotive-related sheet forming operations.

Their advantages are: low yield strength, low yield to tensile strength ratio, high initial strain hardening rates, good uniform elongation, a high strain rate sensitivity and good fatigue resistance.

Usually, these steels are coated with a metallic coating improving properties such that: corrosion resistance, phosphatability, etc. The metallic coatings can be deposited by hot-dip galvanizing after the annealing of the steel sheets. Sometimes, it is followed by an alloying treatment so that the iron of the steel sheet diffuses towards the zinc coating in order to obtain a zinc-iron alloy on the steel

sheet, called a galvanized steel sheet. This galvanized steel sheet has a good welding behavior.

However, in particular for DP steels, during the annealing performed in a continuous annealing line, the alloying elements having higher affinity towards oxygen (compared to iron) such as Manganese (Mn), Aluminum (Al), Silicon (Si) or Chromium (Cr) oxidize and lead to the formation of oxides at the surface. These oxides being for example manganese oxide (MnO) or silicon oxide (SiO₂) can be present in a form of a continuous or non-continuous film on the surface of the steel sheet. They prevent the proper adherence of the metallic coating to be applied and can result in zones in which there is no coating on the final product or problems related to the delamination of the coating.

Galvanizing the DP steels is a challenging task because the oxides formed during annealing on the steel sheet can interfere with the Fe-Zn formation. Indeed, the oxides formed can delay the galvanizing since the iron diffusion is bothered. The galvanizing depends on among others the distribution of the oxides at the steel sheet surface, in the steel sheet, the oxides morphology and sometimes the nature of the oxides formed.

The patent application EP2415896 discloses a method for manufacturing a high-strength galvanized steel sheet including a zinc plating layer, having a mass per unit area of 20 g/m² to 120 g/m², disposed on a steel sheet containing 0.01% to 0.18% C, 0.02% to 2.0% Si, 1.0% to 3.0% Mn, 0.001% to 1.0% Al, 0.005% to 0.060% P, and 0.01% or less S on a mass basis, the remainder being Fe and unavoidable impurities, includes annealing and galvanizing the steel sheet in a continuous galvanizing line. A temperature region with a furnace temperature of A°C to B°C is performed at an atmosphere dew-point temperature of - 5°C or higher in a heating process, where $600 \leq A \leq 780$ and $800 \leq B \leq 900$. The dew-point temperature of the atmosphere in the annealing furnace other than a region from A°C to B°C is not particularly limited and is preferably within a range from - 50°C to -10°C. It also discloses a method that further comprises alloying the steel sheet by heating the steel sheet to a temperature of 450 to 600°C after galvanizing such that the content Fe in the zinc plating layer is within a range from 7 to 15% by weight.

A galvanized steel sheet obtained by the above method has a texture or microstructure in which an oxide of at least one or more selected from the group consisting of Fe, Si, Mn, Al, P, B, Nb, Ti, Cr, Mo, Cu, and Ni is formed in a surface portion of a steel sheet that lies directly under a plating layer and that is within 100
5 μm from a surface of a base steel sheet at 0.010 g/m^2 to 0.50 g/m^2 per unit area and a crystalline Si oxide, a crystalline Mn oxide, or a crystalline Si-Mn complex oxide is precipitated in base metal grains that are present in a region within $10 \mu\text{m}$ down from the plating layer and that are within $1 \mu\text{m}$ from grain boundaries.

However, by using the above method, there is a risk that an important layer
10 of external oxide such as FeO is formed at the steel sheet surface. In this case, it is difficult to reduce all the external oxide leading to a bad wettability and a bad coating adhesion of the zinc on the steel surface and during the alloying treatment, there is a risk that the diffusion of iron into the zinc coating is considerably delayed. Thus, in this case, there is no interest to perform an alloying treatment to
15 obtain a galvanized steel sheet.

The patent application JP2008156734 discloses a method for manufacturing a high-strength hot-dip galvanized steel sheet comprising:

- subjecting a steel composed of the components described in claim 1 or 2 to hot rolling, pickling and cold rolling, and subjecting the resultant steel sheet to hot-dip
20 galvanizing treatment to manufacture the hot-dip galvanized steel sheet, wherein
- in the hot rolling, a slab heating temperature is set at 1150 to 1300°C , a finish rolling temperature is set at 850 to 950°C , and a winding temperature is set at 400 to 600°C ;
- in the pickling, a bath temperature is set at 10°C or higher and lower than 100°C ,
25 and a concentration of hydrochloric acid is set at 1 to 20% ; and
- in the hot-dip galvanizing treatment, a hydrogen concentration in an atmosphere in a heat treatment furnace from a temperature-rising process to 600°C or higher to a cooling process to 450°C via an annealing temperature is set at 2 to 20% and a dew point of the atmosphere is set at -60 to -10°C , and the cold-rolled steel
30 sheet is kept at the annealing temperature of 760 to 860°C for 10 to 500 seconds, and then cooled at an average cooling rate of 1 to $30^\circ\text{C}/\text{sec}$. The method can also

comprise an alloying treatment in a temperature range of 450 to 600°C for 10 to 120 seconds in order to obtain a galvanized steel sheet.

It is mentioned that in the inside of the steel sheet, Si-based and Mn-based oxides are formed in the crystal grain boundaries and the grains.

5 However, in Examples, the alloying treatment time is not mentioned. And, since the oxides are close to the steel sheet surface, there is a risk that the presence of such oxides forms a discontinuous oxides film in the steel sheet inhibiting the diffusion of iron into the zinc coating. Therefore, there is a risk to delay the alloying treatment.

10 The patent application JP2000212648 discloses an one stage method for producing a high-strength hot-dip galvanized steel sheet with excellent workability and plating adhesiveness, the method comprising the steps of:

- subjecting a steel slab comprising 0.10 wt% or less of P to hot rolling followed by pickling, or otherwise subjecting the steel slab to cold rolling;

15 - heating in an atmosphere where a heating temperature T is 750°C or more and 1000°C or less and satisfies the following formula (2), a dew point t of an atmosphere gas satisfies the following formula (3) and a hydrogen concentration of an atmosphere gas is 1 to 100 vol%; and then subjecting to hot-dip galvanization:

20 $0.85 \leq \{[P(\text{wt}\%)+(2/3)]*1150\}/\{T(^{\circ}\text{C})\} \leq 1.15$ (2);

$0.35 \leq \{[P(\text{wt}\%)+(2/3)]*(-30)\}/\{t(^{\circ}\text{C})\} \leq 1.8$ (3).

The method also discloses a further alloying treatment in order to obtain a galvanized steel sheet.

25 All the examples of JP2000212648 wherein the one stage heat treatment method is performed (Examples 18-26) include a heat reduction treatment where a heating temperature T is between 810 and 850°C with a dew point very dry ($\leq -35^{\circ}\text{C}$) or very humid ($\geq 35^{\circ}\text{C}$) allowing the coating adhesion. The heat reduction treatment between 750 and 1000°C is followed by an alloying treatment.

30 The only comparative example of the one stage method of JP2000212648 (Comparative Example 10) is performed with a steel sheet having very low amounts of Si and Cr. In this case, the one stage heat treatment method includes a heat reduction treatment where a heating temperature T is 820°C with a dew

point of 0°C. It was followed by an alloying treatment performed at 480°C. However, P-based oxides were not reduced leading to a bad coating adhesion and a bad appearance after alloying.

The patent application JP2011117040 discloses an alloyed hot-dip
5 galvanized steel sheet comprising a steel sheet base material having a chemical composition comprising, by mass%, 0.01 to 0.25% of C, 0.3 to 2.0% of Si, 0.030 to 3.0% of Mn, 0.050% or less of P, 0.010% or less of S, 0.0060% or less of N, and 0.5% or less of sol. Al, with a balance being Fe and impurities, and a plated layer containing, by mass%, 8.0 to 15% of Fe and 0.15 to 0.50% of Al, on the surface of
10 the steel sheet base material, wherein the steel sheet further comprising a single oxide of Si, Mn or Al, an oxide comprising two or more of these, or a composite oxide comprising two or more of these and Fe, wherein the single oxide, the oxide or the composite oxide is present in the steel sheet base material within a depth of 2 µm from the interface between the plated layer and the steel sheet base
15 material, and the single oxide, the oxide or the composite oxide having a maximum grain diameter of 0.10 µm or less.

It also discloses a method for manufacturing an alloyed hot-dip galvanized steel sheet comprising:

- a hot rolling step of hot rolling a steel slab having a chemical composition
20 comprising, by mass%, 0.01 to 0.25% of C, 0.3 to 2.0% of Si, 0.030 to 3.0% of Mn, 0.050% or less of P, 0.010% or less of S, 0.0060% or less of N, and 0.5% or less of sol. Al, and coiling the obtained hot rolled steel sheet at a coiling temperature of 650°C or lower;
- a pickling step of pickling the hot rolled steel sheet;
- 25 - a cold rolling step of cold rolling the hot rolled steel sheet pickled in the pickling step, at a reduction in thickness of 50% or more; and
- a hot-dip galvanizing step of successively subjecting the cold rolled steel sheet after the cold rolling step to: annealing in a reduction annealing furnace in a continuous hot-dip galvanizing line for reduction of the steel sheet surface at a
30 temperature range of 700°C or higher, under a nitrogen-hydrogen atmosphere with a hydrogen concentration of 1 to 30 vol.% and a dew point of -30°C to 10°C; hot-dip galvanization; and

- an alloying treatment.

Nevertheless, a large number of oxides having a completely different nature can be formed during the annealing including: a single oxide of Si, Mn or Al, an oxide comprising two or more of these, or a composite oxide comprising two or more of these and Fe. The oxides nature, especially oxides including Al and a composite oxide comprising two or more of these and Fe, can be formed in a form of a continuous layer reducing thus the coating adhesion and delaying the galvannealing.

Thus, in addition to the recrystallization annealing method, the chemical composition and the steel microstructure, the oxides nature and the oxides repartition which are formed during the recrystallization annealing are also important characteristics to take into account to improve the galvannealing kinetics of DP steels.

Consequently, there is a need to find a way to improve the wetting and the coating adhesion of high strength steels and ultra-high strength steels, in particular to DP steels comprising a certain amount of alloying elements.

The object of the invention is therefore to provide a galvannealed steel sheet having a chemical composition including alloying elements, wherein the alloying treatment time is reduced allowing an industrial implementation. Another object is to obtain a galvannealed steel sheet having a high quality, i.e. the diffusion of the iron into the steel was well performed. Finally, the object is to provide an easy to implement method for the manufacture of said galvannealed steel sheet.

This object is achieved by providing a method according to claim 1. The method can also comprise any characteristics of claims 2 to 12.

Another object is achieved by providing a galvannealed steel sheet according to claim 13. The galvannealed steel sheet can also comprise any characteristic of claims 14 to 16.

Finally, the object is achieved by providing the use of a galvannealed steel sheet according to claim 17.

Other characteristics and advantages of the invention will become apparent from the following detailed description of the invention.

The following terms will be defined:

- "vol.%" means the percentage by volume,
- "wt.%" means the percentage by weight.

5 The invention relates to a method for the manufacture of a galvanized steel sheet comprising:

A. The provision of a steel sheet having the following chemical composition in weight percent:

$$0.05 \leq C \leq 0.20\%,$$

$$1.5 \leq Mn \leq 3.0\%,$$

10 $0.10 \leq Si \leq 0.45\%,$

$$0.10 \leq Cr \leq 0.60\%,$$

$$Al \leq 0.20\%,$$

$$V < 0.005\%$$

and on a purely optional basis, one or more elements such as

15 $P < 0.04\%,$

$$Nb \leq 0.05 \%,$$

$$B \leq 0.003\%,$$

$$Mo \leq 0.20\%,$$

$$Ni \leq 0.1\%,$$

20 $Ti \leq 0.06\%,$

$$S \leq 0.01\%$$

$$Cu \leq 0.1\%,$$

$$Co \leq 0.1\%,$$

$$N \leq 0.01\%,$$

25 the remainder of the composition being made of iron and inevitable impurities resulting from the elaboration,

B. The recrystallization annealing of said steel sheet in a full radiant tube furnace comprising a heating section, a soaking section, a cooling section, an equalizing section comprising the sub-following steps:

30

- i. the heating of said steel sheet from ambient temperature to a temperature T1 between 700 and 900°C in the heating section

having an atmosphere A1 comprising from 0.1 to 15% by volume of H₂ and an inert gas whose a dew point DP1 is between -18°C and +8°C,

5 ii. the soaking of the steel sheet from T1 to a temperature T2 between 700 and 900°C in the soaking section having an atmosphere A2 identical to A1 with a dew point DP2 equal to DP1,

10 iii. the cooling of the steel sheet from T2 to T3 between 400 and 700°C in the cooling section having an atmosphere A3 comprising from 1 to 30%H₂ by volume and an inert gas whose a dew point DP3 is below or equal to -30°C,

15 iv. optionally, the equalizing of the steel sheet from a temperature T3 to a temperature T4 between 400 and 700°C in the equalizing section having an atmosphere A4 comprising from 1 to 30%H₂ by volume and an inert gas whose a dew point DP4 is below or equal to -30°C,

C. The hot-dip galvanizing of the annealed steel sheet in a zinc bath and

20 D. An alloying treatment performed at a temperature T5 between 460 and 600°C during a time t5 between 1 and 45 seconds.

Without willing to be bound by any theory, it seems that the method according to the present invention allows for a high improvement of the wettability and the coating adhesion of the steel sheet having a specific chemical composition. Additionally, with the method according to the present invention, it is possible to perform the alloying treatment in a reduced time. Indeed, the inventors have found that the recrystallization annealing according to the present invention performed in a full Radiant Tube Furnace (RTF) wherein the heating and soaking section have the same atmosphere with DP being -18°C and +8°C, such atmosphere comprising from 0.1 to 15% by volume of H₂ allows for the production of a galvanized steel sheet having a specific oxides repartition allowing a high wettability and having a high quality. In particular, the oxides including MnO, FeO and Mn₂SiO₄ are formed during the recrystallization annealing at the steel sheet

surface and internally allowing a high wettability and coating adhesion. Preferably, these external oxides are present in form of nodules at the sheet surface. Thus, during the alloying treatment, the iron of the steel can easily diffuse towards the coating in a reduced time.

5 If the recrystallization annealing of the above specific steel sheet is not performed according to the present invention, in particular if the heating and soaking sections do not have the same atmosphere and if the dew point is below -18°C, there is a risk to form oxides such as MnO, FeO and Mn₂SiO₄, such oxides being mainly or only external. Moreover, there is a risk that these oxides form a
10 thick continuous layer at the steel sheet surface decreasing significantly the wettability. In this case, there is no interest to perform the alloying treatment in order to obtain a galvanized steel sheet.

Moreover, if the heating and soaking sections do not have the same atmosphere and if the dew point is above 8°C, there is a risk to form external
15 oxides such as MnO and FeO and internal oxide such as Mn₂SiO₄. Especially, there is a risk that MnO and mainly FeO are formed in a form of a continuous layer at the steel sheet surface decreasing the wettability. In this case, there is no interest to perform the alloying treatment in order to obtain a galvanized steel sheet.

20 Regarding the chemical composition of the steel, the carbon amount is between 0.05 and 0.20% by weight. If the carbon content is below 0.050%, there is a risk that the tensile strength is insufficient. Furthermore, if the steel microstructure contains retained austenite, its stability which is necessary for achieving sufficient elongation, can be not obtained. In a preferred embodiment,
25 the carbon content is in the range between 0.05 and 0.15%.

Manganese is a solid solution hardening element which contributes to obtain high tensile strength. Such effect is obtained when Mn content is at least 1.5% in weight. However, above 3.0%, Mn addition can contribute to the formation of a structure with excessively marked segregated zones which can adversely
30 affect the welds mechanical properties. Preferably, the manganese content is in the range between 1.5 and 2.9% to achieve these effects. This makes it possible to obtain satisfactory mechanical strength without increasing the difficulty of

industrial fabrication of the steel and without increasing the hardenability in the welds.

Silicon must be comprised between 0.1 and 0.45%, preferably between 0.1 to 0.30% and more preferably between 0.1 to 0.25% by weight of Si to achieve the requested combination of mechanical properties and weldability: silicon reduces the carbides precipitation during the annealing after cold rolling of the sheet, due to its low solubility in cementite and due to the fact that this element increases the activity of carbon in austenite.

Aluminum must be below or equal to 0.20%, preferably below 0.18 by weight. With respect to the stabilization of retained austenite, aluminum has an influence that is relatively similar to the one of the silicon. However, aluminum content higher than 0.20% in weight would increase the Ac3 temperature, i.e. the temperature of complete transformation into austenite in the steel during the annealing step and would therefore make the industrial process more expensive.

Chromium makes it possible to delay the formation of pro-eutectoid ferrite during the cooling step after holding at the maximal temperature during the annealing cycle, making it possible to achieve higher strength level. Thus, the chromium content is between 0.10 and 0.60%, preferably between 0.10 and 0.50% by weight for reasons of cost and for preventing excessive hardening.

Vanadium also plays an important role within the context of the invention. According to the present invention, the amount of V is below 0.005% and preferably $0.0001 \leq V \leq 0.005\%$. Preferably, V forms precipitates achieving hardening and strengthening.

The steels may optionally contain elements such as P, Nb, B, Mo, Ni, Ti, S, Cu, Co, N achieving precipitation hardening.

P and S are considered as a residual element resulting from the steelmaking. P can be present in an amount $< 0.04\%$ by weight. S can present in an amount below or equal to 0.01% by weight.

Titanium and Niobium are also elements that may optionally be used to achieve hardening and strengthening by forming precipitates. However, when the Nb amount is above 0.05% and/or Ti content is greater than 0.06%, there is a risk

that an excessive precipitation may cause a reduction in toughness, which has to be avoided.

The steels may also optionally contain boron in quantity comprised below or equal to 0.003%. By segregating at the grain boundary, B decreases the grain boundary energy and is thus beneficial for increasing the resistance to liquid metal embrittlement.

Molybdenum in quantity below or equal to 0.2% is efficient for increasing the hardenability and stabilizing the retained austenite since this element delays the decomposition of austenite.

The steel may optionally contain nickel, in quantity below or equal to 0.1% so to improve the toughness.

Copper can be present with a content below or equal to 0.1% for hardening the steel by precipitation of copper metal.

Preferably, in steps B.i) and B.ii), A1 comprises between 1 and 10% by volume of H2 and more preferably, A1 comprises between 2 and 8% by volume of H2, A2 being identical to A1.

Advantageously, in steps B.i) and B.ii), DP1 is between -15°C and +5°C, and more preferably, DP1 is between -10 and +5°C, DP2 being equal to DP1.

In a preferred embodiment, in step B.i), the steel sheet is heated from ambient temperature to T1 with a heating rate above 1°C per second and for example between 2 and 5°C per second.

Preferably, in step B.i), the heating is performed during a time t1 between 1 and 500 seconds and advantageously between 1 and 300s.

Advantageously, in step B.ii), the soaking is performed during a time t2 between 1 and 500 seconds and advantageously between 1 and 300s.

Preferably, in step B.ii), T2 is equal to T1. In this case, in steps B.i) and B.ii), T1 and T2 are between 750 and 850°C, T2 being equal to T1. In another embodiment, it is possible that T2 is below or above T1 depending on the steel sheet chemical composition and microstructure. In this case, in steps B.i) and B.ii), T1 and T2 are between 750 and 850°C independently from each other.

Preferably, in step B.iii), A3 comprises from 1 to 20% by weight of H2 and more preferably, from 1 to 10% by weight of H2.

Preferably, in step B.iii), DP3 is below or equal to -35°C .

In a preferred embodiment, in step B.iii), the cooling is performed during a time t_3 between 1 and 50 seconds.

Advantageously, in step B.iii), the cooling rate is above 10°C per second and preferably between 15 and 40°C per second.

Advantageously, in step B.iv), A4 comprises from 1 to 20% and more preferably, from 1 to 10% by weight of H₂.

Preferably, in step B.iv), DP4 is below or equal to -35°C .

In a preferred embodiment, in step B.iv), the equalizing is performed during a time t_4 between 1 and 100 seconds and for example between 20 and 60 seconds.

Advantageously, in steps B.iii) and B.iv), A3 is identical to A4, DP4 being equal to DP3.

Preferably, in step B.iv), T4 is equal to T3. In this case, in steps B.iii) and B.iv), T3 and T4 are between 400 and 550°C or between 550 and 700°C , T4 being equal to T3. In another embodiment, it is possible that T4 is below or above T3 depending on the steel sheet chemical composition and microstructure. In this case, in steps B.iii) and B.iv), T3 and T4 are between 400 and 550°C or between 550 and 700°C independently from each other.

Preferably, in steps B.i) to B.iv), the inert gas is chosen from: N₂, Ar, He and Xe.

Preferably in step C), the zinc-based coating comprises between 0.01 and 0.4% by weight of Al, the balance being Zn.

Advantageously, in step D), T5 is between 470 and 570°C , more preferably between 470 and 530°C .

Preferably, in step D), t_5 is between 1 and 35 seconds and for example between 1 and 20s.

In a preferred embodiment, the alloying treatment is performed in atmosphere A5 comprising air.

The invention also relates to a galvanized steel sheet wherein the zinc coating is alloyed through diffusion of the iron from the steel sheet such that the zinc coating comprises from 5 to 15% by weight of Fe, oxides including FeO,

Mn₂SiO₄ and MnO, the balance being zinc, the steel sheet comprising internal oxides including FeO, Mn₂SiO₄ and MnO in the steel sheet. Preferably, the oxides comprising FeO, Mn₂SiO₄ and MnO present in the zinc or aluminum coating are in a form of nodules.

5 Preferably, the thickness of the coating is between 1 and 15µm.

Preferably, the steel microstructure comprises bainite, martensite, ferrite and optionally austenite. In one preferred embodiment, the steel microstructure comprises from 1 to 45% of martensite, from 1 to 60% of bainite, the balance being austenite. In another preferred embodiment, the steel microstructure
10 comprises from 1 to 25% of fresh martensite, from 1 to 10% of ferrite, from 35 to 95% of martensite and lower bainite and less than 10% of austenite.

In a preferred embodiment, the surface of steel sheet is decarburized. Preferably, the depth of the decarburization is up to 100µm, preferably up to 80µm, from the surface steel sheet. In this case, without willing to be bound by any
15 theory, it is believed that the steel sheet has a better resistance to LME due to the reduction of carbon amount into the steel sheet. Indeed, it seems that carbon is an element highly sensitive to liquid metal embrittlement LME. Additionally, better bendability and better crash behavior.

Finally, the invention relates to the use of the galvanized steel sheet for
20 the manufacture of a part of an automotive vehicle.

The invention will now be explained in trials carried out for information only. They are not limiting.

Examples

In this example, DP steels having the following composition in weight
25 percentage were used:

C	Mn	Si	Cr	Al	Mo	Ti	P	S	Cu	Ni	Nb	V	B	N
0.072	2.52	0.255	0.30	0.15	0.1	0.017	0.013	0.001	0.015	0.021	0.025	0.004	0.0020	0.006

All Trials being DP steels were annealed from ambient temperature in a full
RTF furnace according to the conditions of Table 1.

30 Then, all Trials were hot-dip coated in a zinc bath containing 0.117% of Aluminum.

After the coating deposition, the trials were analyzed by naked eyes, scanning electron microscope and Auger spectroscopy. For the wettability, 0 means that the coating is continuously deposited and 1 means that the coating is not continuously deposited. When the wettability was of 0, i.e. really good, the
5 Trials were alloyed in order to obtain a galvanized steel sheet. When the wettability was of 1, i.e. very bad, there was no need to alloy since the quality of the coating was very bad due to the presence of a lot of unwanted oxides are present at the steel sheet surface.

Results are shown in the Table 1 below.

Trials	Heating section (A1)			Soaking section (A2)				Cooling section (A3)				Equalizing (A4)				Wetability	Alloying treatment		Presence of FeO, Mn ₂ SiO ₄ , MnO Oxides in the coating	In the steel	Coating thickness (μm)
	DP1 (°C)	T1 (°C)	%H2	t1 (s)	DP2 (°C)	T2 (°C)	%H2	t2(s)	DP3 (°C)	T3 (°C)	%H2	t3 (s)	DP4 (°C)	T4 (°C)	%H2		t4 (s)	T5 (°C)			
1	+18	780	5	209	+18	780	5	72	-40	460	5	10	-40	460	5	35	ND	ND	-	-	-
2	+15	780	5	209	+15	780	5	72	-40	460	5	10	-40	460	5	35	ND	ND	-	-	-
3	+10	780	5	209	+10	780	5	72	-40	460	5	10	-40	460	5	35	ND	ND	-	-	-
4*	+5	780	5	209	+5	780	5	72	-40	460	5	10	-40	460	5	35	470	20	yes	yes	9.4
5*	0	780	5	209	0	780	5	72	-40	460	5	10	-40	460	5	35	470	28	yes	yes	9.0
6*	-10	780	5	209	-10	780	5	72	-40	460	5	10	-40	460	5	35	470	40	yes	yes	9.7
7*	-15	780	5	209	-15	780	5	72	-40	460	5	10	-40	460	5	35	470	40	yes	yes	9.5
8	-20	780	5	209	-20	780	5	72	-40	460	5	10	-40	460	5	35	ND	ND	-	-	-
9	-30	780	5	209	-30	780	5	72	-40	460	5	10	-40	460	5	35	ND	ND	-	-	-
10	-40	780	5	209	-40	780	5	72	-40	460	5	10	-40	460	5	35	ND	ND	-	-	-
11	-50	780	5	209	-50	780	5	72	-50	460	5	10	-50	460	5	35	470	76	no	no	10.7
12	-60	780	5	209	-60	780	5	72	-60	460	5	10	-60	460	5	35	470	72	no	no	10.8

* Examples according to the present invention. ND: not done.

Trials 4 to 7 according to the present invention and Examples 11 and 12 show a good wettability. Nevertheless, for Trials 4 to 7, the alloying time was significantly reduced compared to Trials 11 and 12. Moreover, the surface aspect
5 of the coating was significantly good for the Examples according to the present invention.

10

15

20

Claims

- 5 1. Method for the manufacture of a galvanized steel sheet comprising:
- A. The provision of a steel sheet having the following chemical composition in weight percent:
- 10 $0.05 \leq C \leq 0.20\%$,
 $1.5 \leq Mn \leq 3.0\%$,
 $0.10 \leq Si \leq 0.45\%$,
 $0.10 \leq Cr \leq 0.60\%$,
 $Al \leq 0.20\%$,
 $V < 0.005\%$
- and on a purely optional basis, one or more elements such as
- 15 $P < 0.04\%$,
 $Nb \leq 0.05 \%$,
 $B \leq 0.003\%$,
 $Mo \leq 0.20\%$,
 $Ni \leq 0.1\%$,
20 $Ti \leq 0.06\%$,
 $S \leq 0.01\%$,
 $Cu \leq 0.1\%$,
 $Co \leq 0.1\%$,
 $N \leq 0.01\%$,
- 25 the remainder of the composition being made of iron and inevitable impurities resulting from the elaboration,
- B. The recrystallization annealing of said steel sheet in a full radiant tube furnace comprising a heating section, a soaking section, a cooling section, an equalizing section comprising the sub-following
- 30 steps:
- i. the heating of said steel sheet from ambient temperature to a temperature T1 between 700 and 900°C in the heating section having an atmosphere A1 comprising from 0.1 to 15% by

volume of H₂ and an inert gas whose a dew point DP₁ is between -18°C and +8°C,

5 ii. the soaking of the steel sheet from T₁ to a temperature T₂ between 700 and 900°C in the soaking section having an atmosphere A₂ identical to A₁ with a dew point DP₂ equal to DP₁,

10 iii. the cooling of the steel sheet from T₂ to T₃ between 400 and 700°C in the cooling section having an atmosphere A₃ comprising from 1 to 30% H₂ by volume and an inert gas whose a dew point DP₃ is below or equal to -30°C,

15 iv. optionally, the equalizing of the steel sheet from a temperature T₃ to a temperature T₄ between 400 and 700°C in the equalizing section having an atmosphere A₄ comprising from 1 to 30% H₂ by volume and an inert gas whose a dew point DP₄ is below or equal to -30°C,

C. The hot-dip galvanizing of the annealed steel sheet in a zinc bath and

D. An alloying treatment performed at a temperature T₅ between 460 and 600°C during a time t₅ between 1 and 45 seconds.

20 2. A method according to claim 1, wherein in step A), the steel sheet comprises less than 0.30% by weight of Si.

25 3. A method according to claim 1 or 2, wherein in step A), the steel sheet comprises above 0.0001% by weight of V.

4. A method according to anyone of claims 1 to 3, wherein in steps B.i) and B.ii), A₁ comprises between 1 and 10% by volume of H₂, A₂ being identical to A₁.

30 5. A method according to anyone of claims 1 to 4, wherein in steps B.i) and B.ii), DP₁ is between -15°C and +5°C, DP₂ being equal to DP₁.

6. A method according to anyone of claims 1 to 5, wherein in step B.ii), T₂ is equal to T₁.

7. A method according to anyone of claims 1 to 6, wherein in steps B.i) and B.ii), T1 and T2 are between 750 and 850°C.
- 5 8. A method according to anyone of claims 1 to 7, wherein in steps B.iii) and B.iv), A3 is identical to A4, DP4 being equal to DP3.
9. A method according to anyone of claims 1 to 8, wherein in steps B.i) to B.iv), the inert gas is chosen from: N2, Ar, He and Xe.
- 10
10. A method according to anyone of claims 1 to 9, wherein the zinc-based coating comprises between 0.01 and 0.4% by weight of Al, the balance being Zn.
- 15
11. A method according to anyone of claims 1 to 10, wherein in step D), T5 is between 470 and 570°C.
12. A method according to anyone of claims 1 to 11, wherein in step D), t5 is
- 20 between 1 and 35 seconds.
13. A galvanized steel sheet obtainable from the method according to anyone of claims 1 to 12, wherein the zinc coating is alloyed through diffusion of the iron from the steel sheet such that the zinc coating comprises from 5 to 15%
- 25 by weight of Fe, oxides including FeO, Mn₂SiO₄ and MnO, the balance being zinc, the steel sheet comprising internal oxides including FeO, Mn₂SiO₄ and MnO in the steel sheet.
14. A galvanized steel sheet according to claim 13, wherein the oxides present
- 30 in the zinc or aluminum coating are in a form of nodules.
15. A galvanized steel sheet according to claim 14, wherein the steel microstructure comprises bainite, martensite, ferrite and optionally austenite.

16. A galvanized steel sheet according to anyone of claims 13 to 15, wherein the surface of steel sheet is decarburized.
17. Use of a galvanized steel sheet according to anyone of claims 13 to 16 or
5 obtainable from the method according to anyone of claims 1 to 12, for the manufacture of a part of an automotive vehicle.

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2017/001343

A. CLASSIFICATION OF SUBJECT MATTER					
INV.	C23C2/02	C23C2/06	C23C2/28	C21D9/46	C22C38/00
	C22C38/02	C22C38/06	C22C38/38	C22C38/46	C22C38/48
	C22C38/50	C22C38/54	C22C38/58	C21D9/56	C21D9/573

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols) C23C C21D C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EPO-Internal, WPI Data
--

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 2011 153367 A (SUMITOMO METAL IND) 11 August 2011 (2011-08-11)	1,2,4-7, 9-17
Y	paragraph [0001] paragraph [0068] paragraph [0089] - paragraph [0090] example C19; tables 4,5 figure 1	3,8
Y	----- EP 3 017 073 A1 (ARCELORMITTAL INVESTIGACION Y DESARROLLO SL [ES]) 11 May 2016 (2016-05-11)	8
A	paragraph [0001] - paragraph [0004] paragraph [0025] paragraph [0079] paragraph [0088]; examples C,C1; tables 1-5 ----- -/--	1-7,9-17

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search 23 March 2018	Date of mailing of the international search report 04/04/2018
--	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Neibecker, Pascal
--	---

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2017/001343

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	JP 2017 048412 A (NIPPON STEEL & SUMITOMO METAL CORP) 9 March 2017 (2017-03-09)	3
A	paragraph [0001] paragraph [0030] example J; table 1	1,2,4-17
A	----- EP 2 415 896 A1 (JFE STEEL CORP [JP]) 8 February 2012 (2012-02-08) cited in the application paragraph [0002] paragraph [0050] example J; table 1 example 30; table 2 example AJ; table 3 example 77; table 4	1-17
A	----- JP 5 434537 B2 (SUMITOMO METAL IND) 5 March 2014 (2014-03-05) example D; table 1 paragraph [0053]; example 24; table 2 paragraph [0001] - paragraph [0002] -----	1-17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/IB2017/001343

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2011153367 A	11-08-2011	JP 5392116 B2 JP 2011153367 A	22-01-2014 11-08-2011
EP 3017073 A1	11-05-2016	CA 2915776 A1 CN 105358719 A EP 3017073 A1 ES 2641853 T3 JP 2016529392 A KR 20160027105 A MA 38660 A1 PL 3017073 T3 RU 2016103568 A US 2016194739 A1 WO 2015001367 A1 WO 2015001414 A1 ZA 201508970 B	08-01-2015 24-02-2016 11-05-2016 14-11-2017 23-09-2016 09-03-2016 31-10-2016 28-02-2018 10-08-2017 07-07-2016 08-01-2015 08-01-2015 25-01-2017
JP 2017048412 A	09-03-2017	NONE	
EP 2415896 A1	08-02-2012	CA 2751593 A1 CN 102369305 A EP 2415896 A1 KR 20110117220 A KR 20140128458 A TW 201042079 A US 2012018060 A1 WO 2010114142 A1	07-10-2010 07-03-2012 08-02-2012 26-10-2011 05-11-2014 01-12-2010 26-01-2012 07-10-2010
JP 5434537 B2	05-03-2014	JP 5434537 B2 JP 2011117041 A	05-03-2014 16-06-2011