

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number
WO 2013/101693 A1

(43) International Publication Date
4 July 2013 (04.07.20 13)

W I P O | P C T

(51) International Patent Classification:

C08F 283/10 (2006.01) *C08K 3/36* (2006.01)
C09J 4/06 (2006.01) *C08K 5/00* (2006.01)
C09J 7/02 (2006.01)

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:

PCT/US20 12/071123

(22) International Filing Date:

21 December 2012 (21.12.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

201 110444884.6 27 December 2011 (27.12.2011) CN

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

Published:

— with international search report (Art. 21(3))

(72) Inventor; and

(71) Applicant : WU, Qing [CN/CN]; 8 Xing Yi Road, Maxdo Centre, 38/F, Shanghai, 200336 (CN).

(74) Agents: **EHRICH, Dena M.**, et al; 3M Center Office of Intellectual Property Counsel Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).



WO 2013/101693 A1

(54) Title: ADHESIVE TAPE COMPOSITION AND ADHESIVE TAPE PREPARED FROM SAME

(57) Abstract: The present invention provides an adhesive tape composition and an adhesive tape prepared from same. Based on the total weight of the adhesive tape composition, the adhesive tape composition comprises: 25-75 wt.% of an acrylate monomer; 20-70 wt.% of an epoxy resin; 0.001-3 wt.% of a free radical photoinitiator; 0-10 wt.% of a fumed silica; and 0.02-5 wt.% of a cationic thermal initiator. According to the present invention, an adhesive tape having a room temperature retention time as long as 6 months that can be cured at low temperature such as 80 degree C can be produced from the adhesive tape composition.

ADHESIVE TAPE COMPOSITION AND ADHESIVE TAPE PREPARED FROM SAME

5

TECHNICAL FIELD OF THE INVENTION

The present invention relates to an adhesive tape composition and an adhesive tape prepared from same. In particular, the present invention relates to a low temperature thermosetting structural adhesive composition and an adhesive tape prepared from same.

10

TECHNICAL BACKGROUND OF THE INVENTION

Current electronic products such as laptops, products for vehicles, portable mobile terminals are designed to be of small size, light weight, thin thickness and high efficiency in production. This trend requires that more and more plastic materials are used for such products. As for bonding techniques, extremely high adhesive strength would thus be required to achieve the bonding of small areas.

15

Typically, one-component or two-component structural glues may satisfy the bonding requirements of these products; however, such structural glues exhibit numerous flaws, for example, irremovable, not reworkable, uncontrollable bonding area which would result in an inaesthetic bonding surface. Some structural glues comprise a huge amount of solvent and thus it takes extremely long time (low efficiency), or require a high temperature (not adapted to plastic materials which can not withstand high temperature) for the glues to cure. All these flaws have limited extensive use of the structural glues in the aforesaid products.

25

Another typical widely used adhesive tape material is pressure-sensitive adhesive tape. Pressure-sensitive adhesive tape is very easy to use as the bonding can be achieved by exerting thereon only a very small force and thus a long period or high temperature cure becomes unnecessary. Pressure-sensitive adhesive tapes may be used directly upon shaped by die-cutting and achieve continuous production, and thus exhibit extremely high bonding efficiency. Nevertheless, pressure-sensitive adhesive tape has a flaw, i.e. the bonding strength being weak, generally smaller than IMPa, and thus it is not adapted to small area bonding.

Structural adhesive tape has both the advantages of structural glue and pressure-sensitive adhesive tape, i.e. structural adhesive tape can be used very easily like a pressure-sensitive adhesive tape, and can also be imparted the same strength of a structural glue or a semi-structural glue upon activation by a certain 5 energy, such as UV light or heat).

WO 9957216 (Al) (Karim Naimul, et al) employed a thermoplastic material, such as EVA, to hybridize with epoxy resin, and the cure of epoxy resin was initiated using a cationic photoinitiator to effect the bonding at room temperature; however, this method requires irradiation by UV light prior to bonding.

10

Furthermore, with respect to the currently developed structural adhesive tape, the room temperature retention time is relatively short (typically less than one month) and the retention and transportation needs to be done under freeze (lower than 5 degree C) conditions. Additionally, the curing temperature is relatively high, which is typically up to 100 degree C.

15

Therefore, it is of significance to provide a structural adhesive tape which can be cured at a relatively low temperature and has a long retention time at room temperature.

SUMMARY OF THE INVENTION

20

The present invention relates to a structural adhesive tape composition which is cured at low temperature, in particular, to a low temperature curable structural adhesive tape comprising a hybrid system of acrylate/epoxy resin where the cure of epoxy resin is initiated by a cationic thermal initiator. The initiation temperature of the cationic thermal initiator can be as low as 80 degree C and such a 25 pressure-sensitive structural adhesive tape has a room temperature retention time as long as 6 months. As a result, the present invention can be used to bond plastic materials which can not endure a high temperature, such as acrylonitrile butadiene styrene (ABS), polycarbonate (PC), and polymethylmethacrylate (PMMA).

30 According to one aspect of the present invention, an adhesive tape composition is provided. The adhesive tape composition comprises:

25-75 wt.% of an acrylate monomer;
20-70 wt.% of an epoxy resin;
0.001-3 wt.% of a free radical photoinitiator;
5 0-10 wt.% of a fumed silica; and
0.02-5 wt.% of a cationic thermal initiator,
based upon the total weight of the adhesive tape composition.

According to another aspect of the present invention, an adhesive tape is provided. The adhesive tape is
10 produced by a method comprising: coating the adhesive tape composition as described above in a liquid
form onto a release material and curing the composition by UV irradiation.

Compared with prior art, a low temperature curable structural adhesive tape can be produced from the
composition of the present invention. The structural adhesive tape can be cured by heating at low
15 temperature, for example, 80 degree C. Another benefit of the present invention is that the adhesive tape
can be preserved for a relatively long period of time at room temperature (as long as 6 months at room
temperature), while currently available structural adhesive tapes all require low temperature freeze
preservation (lower than 5 degree C). As a result, the transportation and preservation costs can be
significantly decreased.

20

DETAILED DESCRIPTION OF THE INVENTION

Unless otherwise provided in the invention, "room temperature" used herein refers to a temperature
between 20 degree C and 25 degree C.

25

A low temperature curable structural adhesive tape can be produced using the composition of the present
invention. By "low temperature curable structural adhesive tape", it is meant that the structural adhesive
tape exhibits the behavior of a typical pressure-sensitive adhesive tape at the initial stage of bonding
(initial adhesion by which the articles can be bonded by exerting only a minor force; formable by die
30 cutting); after cure by low temperature heating (for example, 80 degree C), it can be transformed to an

adhesive tape with a strength of from semi-structural strength to structural strength and thus the adhesive tape can be used to bond plastic articles which can not endure a high temperature, such as PC, PMMA, ABS and the like.

5 In the present invention, an adhesive tape composition is provided. The adhesive tape composition comprises:

25-75 wt.% of an acrylate monomer;

20-70 wt.% of an epoxy resin;

10 0.001-3 wt.% of a free radical photoinitiator;

0-10 wt.% of a fumed silica; and

0.02-5 wt.% of a cationic thermal initiator,

based upon the total weight of the adhesive tape composition.

15 In the adhesive tape composition according to the present invention, an acrylate monomer is used to provide the subsequently formed structural adhesive tape with initial adhesion to effect the initial adhesion of the materials to be bonded (for example, electronic devices). For the purpose of ensuring that the acrylate monomer is compatible well with other components contained in the composition, it is required to make selection as to the compatibility of the acrylate monomer. In the present invention, the 20 solubility parameter of the acrylate monomer is between 9.3 and 13.5 (cal/cm³)^{0.5} (see, Journal of Applied Polymer Science, vol. 116, pages 1-9 (2010)). Examples of acrylate monomer useful in the present invention include one or more substance selected from the group consisting of tert-butyl acrylate (tBA, solubility parameter: 9.36), phenoxy ethyl acrylate (PEA, solubility parameter: 10.9), isobornyl acrylate (IBoA, solubility parameter: 9.71), Propenoic acid, 2-hydroxy-3-phenoxypropyl ester (HPPA, solubility 25 parameter: 12.94), N-vinylpyrrolidone (NVP, solubility parameter: 13.38), and n-vinyl-epsilon-caprolactam (NVC, solubility parameter: 12.1), and the like.

30 The amount of the acrylate monomer as described above present in the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention is typically between 25 wt.% and 75 wt.%, more preferably between 40 wt.% and 60 wt.%. As such, the acrylate monomer can be

compatible well with the epoxy resin and bring very good toughening effect to the cured epoxy resin.

Epoxy resin is used in the adhesive tape composition of the present invention. By cure of the epoxy resin via heating at low temperature (about 80 degree C), a complete cure of the adhesive tape produced from the adhesive tape composition may be provided, and thus impart the adhesive tape a desired strength. According to some preferred embodiments of the present invention, the epoxy resin used herein may contain at least two epoxy groups in the molecule and the epoxy equivalent may be in the range of between 150 and 600. In particular, widely known epoxy resins such as ring ester epoxy resins and epoxidation polyolefins such as glycidyl ethers derived from the reactions of epichlorohydrin with polyphenols such as bisphenol A, bisphenol F, bisphenol S, hexahydrobisphenol A, tetramethylbisphenol A, diaryl bisphenol A, and tetramethylbisphenol F. Examples of commercially available epoxy resins include YD128 having an epoxy equivalent of about 187, and KD212 having an epoxy equivalent of 535 (Kudko Chemical, Kunshan, Jiangsu, China).

15 The amount of the epoxy resins as described above present in the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention is typically between 20 wt.% and 70 wt.%, more preferably between 30 wt.% and 60 wt.%. As such, a sufficient strength of the structural adhesive tape can be ensured after cure.

20 A free radical photoinitiator is used in the adhesive tape composition of the present invention to polymerize the acrylate monomers under irradiation of light (for example, UV light) to provide an initial adhesion. A free radical photoinitiator is a compound which a photochemical reaction may occur to generate free radicals upon being irradiated by light. The free radicals generated by the free radical photoinitiator can initiate free radical polymerization of the system which would result in cure of the same. Photoinitiators of different structures may have different absorption spectrum and free radical activity. Examples of free radical photoinitiators include: acetophenones such as 2,2-dimethoxy-2-phenylacetophenone (BDK), 1-hydroxycyclohexyl phenyl ketone (184), 2-hydroxy-2-methyl-phenyl-propene-1-one (1173), thioxanthones such as 2-isopropyl thioxanthone or 4-isopropyl thioxanthone (ITX), acryl phosphine oxides such as 2,4,6-trimethylbenzoyldiphenyl phosphine oxide (TPO) and 2,4,6-trimethylbenzoyldiphenyl phosphine oxide (819), and the like.

The amount of the free radical photoinitiators as described above present in the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention is typically between 0.001 wt.% and 3.0 wt.%, more preferably between 0.25 wt.% and 2.2 wt%. If the amount of the free radical photoinitiators is too low, the curing speed of the low temperature cure pressure-sensitive structural glue may be too slow upon UV light irradiation and thus the coating speed may be slow. If the amount of the free radical photoinitiators is too high, the curing speed of the low temperature cure pressure-sensitive structural glue may be too quick upon UV light irradiation and thus the molecular weight of the resulting acrylate copolymer may be too low, which may not be able to toughen the epoxy resins effectively.

According to some preferred embodiments of the present invention, a fumed silica may be added to the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention to adjust the viscosity of the composition such that a viscosity required for the coating of the composition can be achieved. The fumed silica would not be limited so long as it can be used to adjust the viscosity of the glue. Commercially available fumed silica includes R974, which is produced by EVONIK Indusrries.

The amount of fumed silica as described above present in the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention is typically between 0 wt.% and 10 wt.%, more preferably between 3 wt.% and 5 wt.%. By using the fumed silica in an amount in the range as provided above would result in an optimal coordination between tensile strength and elongation. When the amount of fumed silica is zero, the resulting adhesive tape composition would be relatively thin, while when the amount of the fumed silica is 10, the resulting adhesive tape composition would be very thick; however, the both as described above can achieve the purpose of the present invention, i.e. to provide a structural adhesive tape which can be cured at relatively low temperature and preserved for a long period of time at room temperature. Even so, when the amount of the fumed silica is greater than 10 wt. %, the resulting adhesive tape may be too rigid.

A cationic thermal initiator is used in the adhesive tape composition of the present invention to facilitate a

complete cure of the adhesive tape composition at low temperature (80 degree C) heating such that the adhesive tape is provided with an ultimate strength. The amount of the cationic thermal initiator used in the acrylate/epoxy resin hybrid system based structural adhesive tape composition is very small; however, it would exhibit a significant effect on the curing speed and preservation stability of the acrylate/epoxy resin hybrid system based structural adhesive tape composition.

5 The cationic thermal initiator is selected from one or more substance selected from the group consisting of a hexafluoroantimonate, trifluoromethanesulfonic acid, and the like. Examples of commercially available cationic thermal initiator include: ICAM8409 (a hexafluoroantimonate cationic thermal initiator) 10 produced by Shenzhen Chuchuang Applied Materials Co., Ltd, CXC-1612 (a hexafluoroantimonate cationic thermal initiator) produced by Jinshi Co., Ltd and CXC-1614 (a trifluoromethanesulfonic acid cationic thermal initiator) also produced by Jinshi Co., Ltd.

15 The amount of the cationic thermal initiator as described above present in the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention is typically between 0.02 wt.% and 5 wt.%, more preferably between 0.5 wt.% and 2.5 wt.%. If the amount of the cationic thermal initiator in the composition is too low, the required curing temperature would be high, the curing speed would be slow but the preservation stability at room temperature would be good. In contrast, if the amount of the cationic thermal initiator in the composition is too high, the required curing temperature 20 would be low, the curing speed would be high but the preservation stability at room temperature would be decreased.

25 The viscosity of the acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention should be in the range of between 500 cPs and 23,000 cPs, more preferably in the range of between 1,500 cPs and 16,000 cPs prior to the cure upon irradiation by UV light. Neither extremely high viscosity nor extremely low viscosity would facilitate the coating of the acrylate/epoxy resin hybrid system based structural adhesive tape composition.

30 According to another aspect of the present invention, an adhesive tape is provided. The adhesive tape is produced according to the following method comprising: coating the adhesive tape composition as

described above in a liquid form onto a release material and curing the composition by UV irradiation.

The acrylate/epoxy resin hybrid system based structural adhesive tape composition of the present invention may be coated in a liquid form onto a double sided release paper or a release film of a certain thickness using a conventional coating method, and dried and cured by UV irradiation to form a glue film having a certain thickness.

Useful coating methods include roller blade coating, comma roll coating, drag blade coating, reverse roll coating, Mayer coating, gravure roll coating, slot die coating, and the like. More preferable coating methods are comma roll coating and slot die coating.

Settings of light intensity and residence time for the UV oven which is used to partially cure the composition of the present invention by UV irradiation may be the following: area 1: 2.2 mw/cm², residence time: 50s; area 2: 9.1 mw/cm², residence time: 60s; area 3: 18 mw/cm², residence time: 9s.

15

The low temperature curable adhesive tape obtained from the present invention has a thickness (dry glue thickness) of from 8 μ m to 250 μ m, preferably from 25 μ m to 150 μ m, more preferably from 50 μ m to 125 μ m. Too thick or too thin are not good for coating and use.

20

Testing Methods

The samples obtained from the examples and the comparative examples were tested according to the testing methods below.

25

90° Peel Test

90° peel test was conducted on the samples according to the method described in FINAL FTM 2 (the 8th edition, FINAT TECHNICAL MANUAL FOR TESTING METHODS) (Published by the FINAT Technical Committee in July, 2009) to obtain the release force, peel strength and shear strength.

30

Room Temperature Retention Test

Release force changes were measured with respect to the samples at room temperature, upon a certain period of storage, according to the 90° peel test method as described above to assess the room temperature retention performance, that is, the adhesive tape just produced according to the present invention was first tested to determine the 90° release force P_o , and after a period of storage at room temperature, the adhesive tape sample was then tested using the same method to determine the 90° release force P_i . If the 90° release force P_i of the adhesive sample can be up to 80% of the 90° release force P_o after a period of storage, the period of storage can be deemed as the longest retention period of the adhesive tape.

10

Low Temperature Cure Test

The release paper for the low temperature thermosetting structural adhesive tape was removed and the glue surface of the tape was attached to a standard test steel plate and then the standard test steel plate attached with the adhesive tape was placed into an 80 degree C oven for 3 hours. Next, the standard test steel plate attached with the adhesive tape was placed in an environment of 25 degree C and 50% constant humidity prior to being tested for cure performance. In the cure performance test, the release paper on the other side of the adhesive tape after storage was removed and the exposed tape may be pressed by a finger. If the tape was not tacky, it can be deemed that the adhesive has been cured completely.

20

Examples

Examples will be provided to further describe the present invention. It should be understood that the scope of the present invention would be defined by the appended claims rather than be limited to the examples.

Unless otherwise provided, the percentage used herein refers to weight percentage.

Materials:

Product Name	Description	Supplier
--------------	-------------	----------

PEA	phenoxy ethyl acrylate (PEA, solubility parameter: 10.9)	San Ester Company
t-BA	tert-butyl acrylate (tBA, solubility parameter: 9.36)	BASF
IBoA	isobornyl acrylate (IBoA, solubility parameter: 9.71)	San Ester Company
YD128	epoxy resin, epoxy equivalent: 197, in liquid form at room temperature under atmosphere	Kudko Chemical (Kunshan) Co., Ltd
KD212	epoxy resin (glycidyl ether of bisphenol A, CAS No. 25036-25-3); epoxy equivalent: 535	Kudko Chemical (Kunshan) Co., Ltd
R974	hydrophobic fumed silica	EVONIK Industries
Irgacure65 1	Free radical photoinitiator, 2, 2-dimethoxy-2-phenylacetophenone	Ciba
ICAM 8409	a hexafluoroantimonate cationic thermal initiator, initiation temperature: 80 degree C	Shenzhen Chuchuang Applied Materials Co., Ltd
CXC-1612	a closed type hexafluoroantimonate cationic thermal initiator, initiation temperature: 80 degree C	Jinshi Co., Ltd
CXC-1614	a trifluoromethanesulfonic acid cationic thermal initiator, initiation temperature: 100 degree C	Jinshi Co., Ltd

Example 1

Components	Percentage (%)
------------	----------------

PEA	24.88
tBA	25.38
YD 128	33.93
KD212	11.31
R974	3.52
Irgacure65 1	0.15
ICAM 8409	0.83

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 62.20 g of PEA, 63.45 g of tBA, 84.83 g of YD128, 28.28 g of KD212, 0.38 g of Irgacure651 and 2.08 g of ICAM8409 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity being 155 cPs. Next, 8.80 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity of up to 6500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with the adhesive tape composition to obtain an adhesive tape.

15

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 9 months; the adhesive tape was cured completely upon heating at 80 degree C for 0.5 hours; the 90 degree peel strength of the adhesive tape with respect to the stainless steel plate was up to 2.344 N/mm; the shear strength was up to 20 5.45 MPa.

Example 2

Components	Percentage (%)
PEA	24.88
tBA	25.38
YD 128	34.49
KD212	11.31
R974	3.52
Irgacure65 1	0.15
ICAM8409	0.27

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 62.20 g of PEA, 63.45 g of tBA, 86.23 g of YD128, 28.28 g of KD212, 0.38 g of Irgacure651 and 0.68 g of ICAM8409 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of 155 cPs. Next, 8.80 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity being up to 6500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with the adhesive tape composition to obtain an adhesive tape.

15

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 1 year; the adhesive tape was cured completely upon heating at 80 degree C for 3 hours; the 90 degree peel strength of the adhesive tape with respect to the stainless steel plate was up to 1.24 N/mm; the shear strength was up to 20 3.64 MPa.

Compared with example 1, the amount of the cationic thermal initiator used in example 2 was decreased,

and thereby the room temperature retention time was extended but the strength was somewhat decreased.

Example 3

Components	Percentage (%)
PEA	24.88
tBA	25.38
YD128	32.53
KD212	11.31
R974	3.52
Irgacure651	0.15
ICAM8409	2.23

5

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 62.20 g of PEA, 63.45 g of tBA, 81.33 g of YD128, 28.28 g of KD212, 0.38 g of Irgacure651 and 5.58 g of ICAM8409 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of 155 cPs. Next, 8.80 g of R974 was added to the system above and subjected to 10 high speed dispersion for 20 minutes to make the system have a viscosity of up to 6500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon release agent (Dow Corning, DC-292) to obtain a PET release film coated with the 15 adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with the adhesive tape composition to obtain an adhesive tape.

20 The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 1 month; the adhesive tape was cured completely upon heating at 80 degree C for 5 minutes; the 90 degree peel strength of the

adhesive tape with respect to the stainless steel plate was up to 0.87 N/mm; the shear strength was up to 2.64 MPa.

Compared with examples 1 and 2, the amount of the cationic thermal initiator in example 3 was too high 5 and thus the room temperature retention time of the resultant adhesive tape was too short, and the strength was decreased due to excess reaction after the low temperature cure.

Example 4

10

Components	Percentage (%)
PEA	22.6
IBoA	29.95
YD128	45.46
R974	1.68
Irgacure651	0.15
CXC-1612	0.16

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 56.50 g of PEA, 74.88 g of IBoA, 113.65 g of YD128, 0.38 g of Irgacure651 and 0.4 g of CXC-1612 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of 75 15 cPs. Next, 4.20 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity of up to 1,500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon 20 release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with

the adhesive tape composition to obtain an adhesive tape.

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 1 year; the adhesive 5 tape was cured completely upon heating at 80 degree C for 3 hours; the 90 degree peel strength of the adhesive tape with respect to the stainless steel plate was up to 1.07 N/mm; the shear strength was up to 4.48 MPa.

Compared with examples 1 and 2, the cationic thermal initiator used in example 4 was a closed type 10 cationic thermal initiator and the amount of the same was much lower. As a result, the room temperature retention time of the adhesive tape was up to more than 1 year, but the strength was somewhat decreased.

Example 5

15

Components	Percentage (%)
PEA	22.6
IBoA	29.95
YD128	43.24
R974	3.52
Irgacure651	0.15
CXC-1612	0.54

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 56.50 g of PEA, 74.88 g of IBoA, 108.10 g of YD128, 0.38 g of Irgacure651 and 20 1.35 g of CXC-1612 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of 75 cPs. Next, 8.80 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity being up to 1,500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi

polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was 5 covered on the adhesive tape composition coating layer of the PET release film which was coated with the adhesive tape composition to obtain an adhesive tape.

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 9 months; the adhesive 10 tape was cured completely upon heating at 80 degree C for 30 minutes; the 90 degree C peel strength of the adhesive tape with respect to the stainless steel plate was up to 1.77 N/mm; the shear strength was up to 7.48 MPa.

Compared with example 4, the cationic thermal initiator used in example 5 was a closed type cationic 15 thermal initiator and the amount of the same was increased. As a result, the room temperature retention time of the adhesive tape was shortened, but the strength was somewhat increased.

Example 6

Components	Percentage (%)
PEA	22.6
IBoA	29.95
YD128	39.62
R974	6.32
Irgacure651	0.15
CXC-1612	1.36

20

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 56.50 g of PEA, 74.88 g of IBoA, 99.05 g of YD128, 0.38 g of Irgacure65 1 and 3.40 g of CXC-1612 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of

75 cPs. Next, 15.80 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity being up to 15,500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film 5 (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with 10 the adhesive tape composition to obtain an adhesive tape.

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 3 months; the adhesive tape was cured completely upon heating at 80 degree C for 5 minutes; the 90 degree peel strength of the 15 adhesive tape with respect to the stainless steel plate was up to 1.32 N/mm; the shear strength was up to 2.50 MPa.

Compared with examples 4 and 5, the cationic thermal initiator used in example 6 was a closed type cationic thermal initiator and the amount of the same was increased. As a result, the room temperature 20 retention time of the adhesive tape was shortened, and the strength was somewhat decreased due to excess reaction after cure.

Example 7

Components	Percentage (%)
PEA	24.88
tBA	25.38
YD128	33.93
KD212	11.31
R974	3.52

Irgacure651	0.15
CXC-1614	0.83

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 62.20 g of PEA, 63.45 g tBA, 84.83 g of YD128, 0.38 g of Irgacure651 and 2.08 g of CXC-1614 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of 155 cPs. Next, 8.80 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity of up to 6500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with the adhesive tape composition to obtain an adhesive tape.

15

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 1.5 years; the adhesive tape was cured completely upon heating at 105 degree C for 5 minutes; the 90 degree peel strength of the adhesive tape with respect to the stainless steel plate was up to 2.87 N/mm; the shear strength was up to 20 8.64 MPa.

Compared with example 1, the initiation temperature of the cationic thermal initiator used in example 7 was increased (100 degree C). As a result, the room temperature retention time of the adhesive tape was up to 1.5 years, and both the peel strength and the shear strength were somewhat increased after the high 25 temperature cure (105 degree C).

Example 8

5

Components	Percentage (%)
PEA	52.55
YD128	43.24
R974	3.52
Irgacure651	0.15
CXC-1612	0.54

At room temperature, an air agitator (ZD-J-1, available from Shanghai Zuoda Coating Equipments Co., Ltd) was used to mix 131.38 g of PEA, 108.10 g of YD128, 0.38 g of Irgacure651 and 1.35 g of CXC-1612 for 30 minutes to obtain an acrylate/epoxy resin hybrid solution having a viscosity of 75 cPs.

10 Next, 8.80 g of R974 was added to the system above and subjected to high speed dispersion for 20 minutes to make the system have a viscosity of up to 1,500 cPs. The resultant mixture was left to stand for 20 minutes to remove air bubbles. A comma roll coater (YS-T300, available from Changzhou Yongsheng Packing Co. Ltd) was used to coat the resultant mixture onto a PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) which was coated on both sides with silicon 15 release agent (Dow Corning, DC-292) to obtain a PET release film coated with the adhesive tape composition having a coating thickness being controlled to 50 microns (dry glue thickness). Then, another layer of PET release film (Mitsubishi polyester film, Hostaphan 2SAB/SAC, 0.05 mm thick) was covered on the adhesive tape composition coating layer of the PET release film which was coated with the adhesive tape composition to obtain an adhesive tape.

20

The adhesive tape so obtained was tested according to the testing methods as described above and the results indicated that the room temperature retention time of the adhesive tape was 9 months; the adhesive tape was cured completely upon heating at 80 degree C for 25 minutes; the 90 degree peel strength of the adhesive tape with respect to the stainless steel plate was up to 1.43 N/mm; the shear strength was up to

6.73 MPa.

Compared with other examples, only an acrylate monomer and an epoxy resin were used in example 8. As a result, the room temperature retention time of the adhesive tape was kept substantially unchanged, 5 and both the peel strength and the shear strength were not high; however, example 8 could also achieve the purpose of the present invention.

Although examples have been provided to further describe the present invention, it should be understood that the scope of the present invention would rather be defined by the appended claims than be limited to 10 the examples. The person of ordinary skill in the art will understand that various modifications and alterations may be made without departing the spirit of the present invention, and such modifications and alterations would rather be covered by the scope of the present invention which is defined by the appended claims.

What is Claimed is:

1. A bonding tape composition, based on the total weight of the bonding tape composition, comprising:

25-75 percent by weight of an acrylate monomer;

5 20-70 percent by weight of an epoxy resin;

0.001-3 percent by weight of a radical photo-initiator;

0-10 percent by weight of a fumed silica; and

0.02-5 percent by weight of a cationic thermal initiator.

10 2. The bonding tape composition according to claim 1, wherein the acrylate monomer has a solubility parameter in a range of 9.3 to 13.5.

15 3. The bonding tape composition according to claim 1 or 2, wherein the acrylate monomer is one or more selected from the group consisting of tert-butyl acrylate, phenoxyethyl acrylate, isobornyl acrylate, 2-hydroxyl-3-phenoxypropyl acrylate, N-vinyl-2- pyrrolidone, and N-vinylcaprolactam.

20 4. The bonding tape composition according to claim 1 or 2, wherein the acrylate has an epoxy equivalent in a range of 150 to 600.

25 5. The bonding tape composition according to claim 1 or 2, wherein the radical photo-initiator is one or more selected from the group consisting of 2, 2-dimethoxy-2-phenyl acetophenone, 1-hydroxylcyclohexylphenylmethanone, 2-hydroxyl-2-methyl- 1-phenylpropane- 1-one, 2-isopropylthioxanthone, 4-isopropylthioxanthone, 2, 4, 6-trimethylbenzoyldiphenylphosphine oxide, and bis(2, 4, 6-trimethylbenzoyl)-phenylphosphine oxide.

25 6. The bonding tape composition according to claim 1 or 2, wherein the bonding tape composition comprises 3-5 percent by weight of the fumed silica.

30 7. The bonding tape composition according to claim 1 or 2, wherein the cationic thermal initiator is one or more selected from the group consisting of hexafluoroantimonates and trifluoromethanesulfonic acid.

8. The bonding tape composition according to claim 1 or 2, wherein the bonding tape composition has a viscosity in a range of 500 to 23000 cPs.

5 9. A bonding tape prepared by coating a bonding tape composition according to any one of claims 1-8 in liquid form onto a releasing material and curing the bonding tape composition by irradiating ultraviolet light.

10 10. The bonding tape according to claim 9, wherein the releasing material is releasing paper or releasing film.

11. The bonding tape according to claim 9, wherein the bonding tape has a thickness of 8-250 μm .

15

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2012/071123

A. CLASSIFICATION OF SUBJECT MATTER	INV. C08F283/10	C09J4/06	C09J7/02	C08K3/36	C08K5/00
ADD.					

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09J C08F C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 10 2008 028638 A1 (HENKEL AG & CO KGAA [DE]) 24 December 2009 (2009-12-24) paragraph [0010] - paragraph [0017] paragraph [0026] - paragraph [0027] paragraph [0039] ; cl aims ; examples -----	1-11
X	WO 94/29399 A1 (MINNESOTA MINING & MFG [US]) 22 December 1994 (1994-12-22) cl aims ; examples 3, Comparative 3 -----	1-11
A	WO 03/040250 A1 (3M INNOVATIVE PROPERTIES CO [US]) 15 May 2003 (2003-05-15) the whole document -----	1-11
A	WO 00/71632 A1 (3M INNOVATIVE PROPERTIES CO [US] ; KITANO SHUICHI [JP] ; IMAI KOJI [JP]) 30 November 2000 (2000-11-30) the whole document -----	1-11



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
25 March 2013	03/04/2013

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Iraegui Retolaza, E
--	---

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2012/071123

Patent document cited in search report	Publication date	Patent family member(s)	
		Publication date	
DE 102008028638 AI	24-12-2009	DE 102008028638 AI	24-12-2009
		W0 2009153274 AI	23-12-2009
<hr style="border-top: 1px dashed black;"/>			
W0 9429399 AI	22-12-1994	CA 2163108 AI	22-12-1994
		CN 1125460 A	26-06-1996
		DE 69404147 D1	14-08-1997
		DE 69404147 T2	26-02-1998
		EP 0703952 A1	03-04-1996
		JP 3834594 B2	18-10-2006
		JP H08511569 A	03-12-1996
		MY 130102 A	29-06-2007
		US 5453450 A	26-09-1995
		US 5599622 A	04-02-1997
		W0 9429399 AI	22-12-1994
<hr style="border-top: 1px dashed black;"/>			
W0 03040250 AI	15-05-2003	AT 549386 T	15-03-2012
		CN 1585807 A	23-02-2005
		CN 1864995 A	22-11-2006
		EP 1448746 A1	25-08-2004
		JP 4447910 B2	07-04-2010
		JP 2005508435 A	31-03-2005
		US 2003192638 A1	16-10-2003
		US 2005276916 A1	15-12-2005
		WO 03040250 A1	15-05-2003
<hr style="border-top: 1px dashed black;"/>			
W0 0071632 AI	30-11-2000	AT 282075 T	15-11-2004
		AU 5025500 A	12-12-2000
		DE 60015754 D1	16-12-2004
		DE 60015754 T2	01-12-2005
		EP 1187888 A1	20-03-2002
		JP 4573373 B2	04-11-2010
		JP 2000328009 A	28-11-2000
		W0 0071632 A1	30-11-2000
<hr style="border-top: 1px dashed black;"/>			