



(86) Date de dépôt PCT/PCT Filing Date: 2000/07/13
(87) Date publication PCT/PCT Publication Date: 2001/01/18
(45) Date de délivrance/Issue Date: 2012/09/04
(85) Entrée phase nationale/National Entry: 2002/01/09
(86) N° demande PCT/PCT Application No.: US 2000/019127
(87) N° publication PCT/PCT Publication No.: 2001/004638
(30) Priorité/Priority: 1999/07/13 (US09/352,025)

(51) Cl.Int./Int.Cl. *C23F 1/00* (2006.01),
B81B 3/00 (2006.01), *B81C 1/00* (2006.01),
C23F 1/02 (2006.01), *G01P 15/135* (2006.01),
G02B 26/00 (2006.01), *G02B 26/08* (2006.01),
G03F 7/26 (2006.01)

(72) Inventeurs/Inventors:
YU, LIANZHONG, US;
RIED, ROBERT P., US;
GOLDBERG, HOWARD D., US;
YU, DULI, US

(73) Propriétaire/Owner:
ION GEOPHYSICAL CORPORATION, US

(74) Agent: CASSAN MACLEAN

(54) Titre : PROCEDE DE MICRO-USINAGE A MASQUE FUSIONNE
(54) Title: MERGED-MASK MICRO-MACHINING PROCESS

(57) **Abrégé/Abstract:**

The present invention provides merged-mask processes for fabricating micro-machined devices in general and mirrored assemblies for use in optical scanning devices in particular. The process includes (a) providing a substrate having a predetermined thickness; (b) applying a first masking layer on a first portion of the substrate and a second masking layer on a second portion of the substrate, said second masking layer being at least as thick as the first masking layer; (c) etching a portion of the second masking layer to provide a first exposed portion of the substrate; (d) etching the first exposed portion of the substrate to a first depth; (e) etching the second masking layer to provide a second exposed portion of the substrate; and (f) etching simultaneously the first exposed portion of the substrate to a second depth and the second exposed portion of the substrate to a first depth. The process further comprises patterning the first masking layer before applying the second masking layer to provide the second portion of the substrate for etching and etching the first masking layer to expose the second portion of the substrate. The first and second masking layers are applied prior to etching the substrate.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 January 2001 (18.01.2001)

PCT

(10) International Publication Number
WO 01/04638 A1

- (51) International Patent Classification⁷: **G01P 9/04**, 15/135, G02B 26/00, C23F 1/00, G03F 7/26
- (74) Agent: **MADAN, Paul, S.**; Madan, Mossman & Sriram, P.C., Suite 700, 2603 Augusta, Houston, TX 77057 (US).
- (21) International Application Number: PCT/US00/19127
- (81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 13 July 2000 (13.07.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/352,025 13 July 1999 (13.07.1999) US
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant: **INPUT OUTPUT, INC.** [US/US]; 12300 Charles E. Selecman Drive, Stafford, TX 77477 (US).
- (72) Inventors: **YU, Lianzhong**; 13906 NE 9th PL, Apt. No. A-2, Bellevue, WA 98005 (US). **RIED, Robert, P.**; 5010 Grove West Boulevard, No. 1602, Stafford, TX 77477-2622 (US). **GOLDBERG, Howard, D.**; 3007 Colony Crossing Drive, Sugar Land, TX 77479 (US). **YU, Duli**; 15700 Lexington Boulevard, No. 301, Sugar Land, TX 77478 (US).
- Published:**
— *With international search report.*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 01/04638 A1

(54) Title: MERGED-MASK MICRO-MACHINING PROCESS

(57) Abstract: The present invention provides merged-mask processes for fabricating micro-machined devices in general and mirrored assemblies for use in optical scanning devices in particular. The process includes (a) providing a substrate having a predetermined thickness; (b) applying a first masking layer on a first portion of the substrate and a second masking layer on a second portion of the substrate, said second masking layer being at least as thick as the first masking layer; (c) etching a portion of the second masking layer to provide a first exposed portion of the substrate; (d) etching the first exposed portion of the substrate to a first depth; (e) etching the second masking layer to provide a second exposed portion of the substrate; and (f) etching simultaneously the first exposed portion of the substrate to a second depth and the second exposed portion of the substrate to a first depth. The process further comprises patterning the first masking layer before applying the second masking layer to provide the second portion of the substrate for etching and etching the first masking layer to expose the second portion of the substrate. The first and second masking layers are applied prior to etching the substrate.

APPLICATION FOR PATENT

Title: **MERGED-MASK MICRO-MACHINING PROCESS**

Inventors: **Lianzhong Yu, Robert P. Ried, Howard D. Goldberg,
and Duli Yu**

Background of the Invention

This invention relates generally to micro-machined three dimensional structures, and in particular to micro-machined movable structures.

5 Conventional bar code scanners are used to scan a surface with a laser beam. Conventional bar code scanners further typically utilize mirrors that are oscillated to permit the laser beam to scan. Conventional mirrors for bar code scanners are relatively large and imprecise.

10 In order to manufacture smaller and more precise bar code mirrors, micromachining processes are commonly used in which a silicon substrate is micromachined to produce a mirror. However, conventional micromachining processes suffer from a number of limitations.

For example, in micromachining an initially planar substrate using repeated iterations of photolithographic patterning and etching, it is typically desirable to etch the substrate to achieve etch depth variations that are greater
15 than those appropriate for conventional photolithographic patterning methods used in manufacturing integrated circuits. In some cases, the etch depth variation of the substrate may exceed the depth of focus of the optical lithography equipment. The variation in etch depth may also be sufficiently large to preclude the application of a thin, uniform layer of photoresist using the
20 conventional technique of pouring photoresist onto the substrate and then rapidly spinning the substrate to distribute the photoresist. If photoresist is spun onto a surface having significant topography, then the resulting thickness of the photoresist may vary by more than 1000%. As a result, lithography of fine
25 features in uneven photoresist is difficult because of the overexposure of the thinner photoresist regions. However, in typical micromachining applications, it is typically desirable to subsequently pattern such a substrate having significant topography.

5 An additional complication arises during micromachining if relatively deep recesses are formed on one side of a substrate and then the other side of the substrate is micromachined. Typical vacuum chucks of conventional automatic wafer handling equipment may not be able to hold such wafers due to the uneven micromachined surface.

10 In order to overcome some of the difficulties of micromachining, a number of so-called merged-mask micromachining processes have been developed. The typical processing steps in a merged-mask micromachining process include forming all of the etching masks onto the substrate, and then micromachining the substrate. In this manner, the etching masks are formed on a substantially planar surface resulting in relatively consistent and even film thicknesses. However, the conventional merged-mask micromachining processes still suffer from a number of limitations.

15 The present invention is directed to overcoming one or more of the limitations of the existing micromachining processes.

Summary of the Invention

20 According to one aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes (1) providing a substrate; (2) applying a layer of a first masking material onto the substrate; (3) patterning the layer of the first masking material; (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material; (5) patterning the layer of the second masking material; (6) etching the exposed portions of the substrate; (7) etching the exposed portions of the layer of the second masking material; and (8) etching the exposed portions of the substrate.

25 According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; patterning the layer of the first masking material; applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking

30

material; patterning the layer of the second masking material; etching the exposed portions of the substrate; etching the exposed portions of the layer of the second masking material; and etching the exposed portions of the substrate.

5 According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; patterning the layer of the first masking material; then etching the exposed portions of the substrate; applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is
10 at least as thick as the layer of the first masking material; patterning the layer of the second masking material; etching the exposed portions of the substrate; etching the exposed portions of the layer of the second masking material; and etching the exposed portions of the substrate.

15 According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; applying a layer of a second masking material onto the layer of the first masking material; patterning the layer of the second masking material; applying a layer of a third masking material onto the portions not covered by the patterned layer
20 of the second masking material, the layer of the third masking material is at least as thick as the combined thickness of the layers of the first and second masking materials; patterning the layers of the first and third masking materials; etching the exposed portions of the substrate; etching the exposed portions of the layers of the first and third masking materials; and etching the exposed portions of the
25 substrate.

30 According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; applying a layer of a second masking material onto the layer of the first masking material; patterning the layer of the second masking material; patterning the layer of the first masking material; applying a layer of a third masking material onto the portions not covered by the patterned layer of the second masking

material, the layer of the third masking material is at least as thick as the combined thickness of the layers of the first and second masking materials; patterning the layers of the first and third masking materials; etching the exposed portions of the substrate; etching the exposed portions of the layers of the first and third masking materials; and etching the exposed portions of the substrate.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; applying a layer of a second masking material onto the layer of the first masking material; patterning the layer of the second masking material; patterning the layer of the first masking material; thin etching the exposed portions of the substrate; applying a layer of a third masking material onto the portions not covered by the patterned layer of the second masking material, the layer of the third masking material is at least as thick as the combined thickness of the layers of the first and second masking materials; patterning the layers of the first and third masking materials; etching the exposed portions of the substrate; etching the exposed portions of the layers of the first and third masking materials; and etching the exposed portions of the substrate.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; patterning the layer of the first masking material; applying a layer of a second masking material onto the patterned layer of the first masking material; patterning the layer of the second masking material; dry etching the exposed portions of the substrate; etching the exposed portions of the patterned layer of the first masking material; and dry etching the exposed portions of the substrate.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes (1) providing a substrate; (2) applying a layer of a first masking material onto the substrate; (3) patterning the layer of the first masking material; (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first

masking material; (5) patterning a fraction of the thickness of the layer of the second masking material a plurality of times; (6) etching the exposed portions of the substrate; (7) etching a fraction of the thickness of the exposed portions of the layer of the second masking material; (8) etching the exposed portions of the substrate; and (9) repeating steps (7) and (8) a plurality of times.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes (1) providing a substrate; (2) applying a layer of a first masking material onto the substrate; (3) patterning the layer of the first masking material; (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material; (5) patterning the layer of the second masking material; (6) applying a layer of a third masking material onto substrate; (7) patterning the layer of the third masking material; (8) etching the layer of the third masking material; (9) etching the exposed portions of the substrate; (10) etching the exposed portions of the layer of the second masking material; and (11) etching the exposed portions of the substrate.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes (1) providing a substrate; (2) applying a layer of a first masking material onto the substrate; (3) patterning the layer of the first masking material; (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material; (5) patterning a fraction of the thickness of the layer of the second masking material a plurality of times; (6) applying a layer of a third masking material onto substrate; (7) patterning the layer of the third masking material; (8) etching the layer of the third masking material; (9) etching the exposed portions of the substrate; (10) etching a fraction of the thickness of the exposed portions of the layer of the second masking material; (11) etching the exposed portions of the substrate; and (12) repeat steps (10) and (11) a plurality of times.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes (1) providing a substrate; (2) applying a layer of a first masking material onto the substrate; (3) patterning a fraction of the thickness of the layer of the first masking material a plurality of times; (4) applying a layer of a second masking material onto substrate; (5) patterning the layer of the second masking material; (6) etching the layer of the second masking material; (7) etching the exposed portions of the substrate; (8) etching a fraction of the thickness of the exposed portions of the layer of the first masking material; (9) etching the exposed portions of the substrate; and (10) repeat steps (8) and (9) a plurality of times.

According to another aspect of the present invention, a method of fabricating a three-dimensional structure is provided that includes providing a substrate; applying a layer of a first masking material onto the substrate; patterning the layer of the first masking material; applying a layer of a second masking material onto the patterned first layer of masking material; patterning the layer of the second masking material; dry etching a first group of exposed portions of the substrate for a first time period; etching the exposed portions of the layer of the first masking material; and dry etching a second group of exposed portions of the substrate for a second time period; wherein the first time period and the second time period are a function of the size of the exposed portions of the substrate.

According to another aspect of the present invention, a method of micro-machining a substrate is provided that includes wet etching the substrate using a merged-mask micro-machining process and dry etching the substrate using a merged-mask micro-machining process.

According to another aspect of the present invention, a method of creating multiple masking layers for use in micro-machining a substrate is provided that includes applying a layer of an etch resistant material onto the substrate and eroding different areas of the layer at different rates to form a multiple thickness layer.

According to another aspect of the present invention, a method of micromachining a substrate is provided that includes using a combination of different etchants having different anisotropic properties.

5 According to another aspect of the present invention, a method of micromachining a substrate is provided that includes decoupling a first etching process from a second etching process.

10 According to another aspect of the present invention, a mirror assembly is provided that includes a mirror, a top cap and a bottom cap. The mirror includes a mirror support structure, a pair of T-shaped hinges coupled to the mirror support structure and a mirrored plate coupled to the T-shaped hinges. The mirrored plate includes one or more travel stops for limiting movement of the mirrored plate. The top cap is coupled to one side of the mirror. The top cap includes a top cap support structure including an opening for permitting light to reflect off of the mirrored plate and one or more travel stops coupled to the top cap support structure for limiting movement of the mirrored plate. The bottom cap is coupled to another side of the mirror. The bottom cap includes a bottom cap support structure including an opening and one or more travel stops coupled to the bottom cap support structure for limiting movement of the mirrored plate. The mirror is fabricated using a process comprising a merged-mask micro-machining process.

20 According to another aspect of the present invention, a mirror assembly is provided that includes a support structure, a pair of T-shaped hinges coupled to the support structure and a mirrored plate coupled to the T-shaped hinges. The mirrored plate includes one or more travel stops for limiting movement of the mirrored plate. The mirror is fabricated using a process comprising a merged-mask micro-machining process.

25 According to another aspect of the present invention, an apparatus is provided that includes one or more T-shaped springs and a mass coupled to the T-shaped springs. The apparatus is fabricated using a merged-mask micro-machining process.

30

Brief Description of the Drawings

FIG. 1 is a schematic illustration of a mirror assembly and laser for use in a bar code scanner.

5 **FIG. 2** is a schematic side view of a preferred embodiment of the mirror assembly of **FIG. 1**.

FIG. 3 is a top view of the top cap of the mirror assembly of **FIG. 2**.

FIG. 4 is a cross-sectional view of the top cap of **FIG. 3**.

FIG. 5 is a cross-sectional view of the top cap of **FIG. 3**.

FIG. 6 is a top view of the mirror of the mirror assembly of **FIG. 2**.

10 **FIG. 6a** is a top view of an alternative embodiment of the hinge of the mirror assembly of **FIG. 2**.

FIG. 6b is a top view of an alternative embodiment of the hinge of the mirror assembly of **FIG. 2**.

15 **FIG. 6c** is a top view of an alternative embodiment of the hinge of the mirror assembly of **FIG. 2**.

FIG. 6d is a top view of an alternative embodiment of the mirror of the mirror assembly of **FIG. 2**.

FIG. 7 is a cross-sectional view of the mirror of **FIG. 6**.

FIG. 8 is a cross-sectional view of the mirror of **FIG. 6**.

20 **FIG. 9** is a bottom view of the mirror of **FIG. 6**.

FIG. 10 is a top view of the bottom cap of the mirror assembly of **FIG. 2**.

FIG. 11 is a cross-sectional view of the bottom cap of **FIG. 10**.

FIG. 12 is a cross-sectional view of the bottom cap of **FIG. 10**.

25 **FIG. 13** is a top view of the base member of the mirror assembly of **FIG. 2**.

FIG. 14 is a cross-sectional view of the base member of **FIG. 13**.

FIG. 15 is a cross-sectional view of the base member of **FIG. 13**.

FIG. 16 is a top view of the top cap and mirror of the mirror assembly of **FIG. 2**.

30 **FIG. 17** is a top view of the bottom cap and base member of the mirror assembly of **FIG. 2**.

FIG. 18 is a cross-sectional view of the mirror assembly of **FIG. 16** illustrating the oscillation of the mirror collection plate.

FIG. 19 is a view of the mirror assembly of **FIG. 18** illustrating the use of tapered surfaces to minimize clipping of the laser light.

5 **FIG. 20** is a flow chart illustrating the fabrication of the mirror assembly of **FIG. 2**.

FIG. 21a is a flow chart illustrating the fabrication of the mirror of the mirror assembly of **FIG. 2**.

10 **FIG 21b** is a flow chart illustrating the fabrication of the mirror of the mirror assembly of **FIG. 2**.

FIG. 22 is a cross-sectional illustration of a silicon wafer having layers of silicon dioxide and silicon nitride applied to its front and back sides.

FIG. 23 is an illustration of the nitride photolithography and etching of the backside of the silicon wafer.

15 **FIG. 23a** is an illustration of the etching of the exposed areas of the pad layer of silicon dioxide.

FIG. 23b is an illustration of the growth of a field oxide layer onto the exposed areas of silicon of the silicon wafer of **FIG. 23a**.

20 **FIG. 24** is a composite illustration of the silicon nitride and silicon dioxide photolithography and etching of the backside of the silicon wafer.

FIG. 25 is an illustration of the KOH etching of the backside of the silicon wafer of **FIG. 24**.

FIG. 26 is a cross-sectional illustration of the silicon wafer of **FIG. 25**.

25 **FIG. 27** is an illustration of the etching of the exposed layer of silicon dioxide on the backside of the silicon wafer, KOH etching of the exposed silicon on the backside of the silicon wafer, and stripping of both silicon nitride layers off of the silicon wafer of **FIG. 25**.

FIG. 28 is a cross-sectional view of the silicon wafer of **FIG. 27**.

30 **FIG. 29a** is an illustration of the patterning of the layer of silicon dioxide on the front side of the silicon wafer of **FIG. 27**.

FIG. 29b is a cross-sectional illustration of the silicon wafer of **FIG. 29a**.

FIG. 30a is an illustration of the gold depositing, gold lithography and gold etching of the front side of the silicon wafer of **FIG. 29a**.

FIG. 30b is a cross-sectional illustration of the silicon wafer of **FIG. 30a**.

5 **FIG. 30c** is an illustration of the application and patterning of a layer of photoresist onto the front side of the silicon wafer of **FIG. 30a**.

FIG. 30d is a cross-sectional illustration of the silicon wafer of **FIG. 30c**.

FIG. 31 is an illustration of deep reactive ion etching of exposed silicon, etching exposed silicon dioxide, deep reactive ion etching of exposed silicon, and removal of the photoresist on the front side of the silicon wafer of **FIG. 30c**.

10 **FIG. 32** is a cross-sectional illustration of the silicon wafer of **FIG. 31**.

FIG. 33 is a flow chart illustrating the fabrication of the top and bottom caps of the mirror assembly of **FIG. 2**.

FIG. 34 is a cross-sectional illustration of a silicon wafer with pad layers of silicon dioxide and layers of silicon nitride on its front and backsides.

15 **FIG. 35a** is an illustration of the photolithography and etching of the layers of silicon nitride and pad layers of silicon dioxide on the frontside of the silicon wafer of **FIG. 34**.

FIG. 35b is an illustration of the growth of a field layer of silicon dioxide onto the exposed areas of silicon of the silicon wafer of **FIG. 35a**.

20 **FIG. 36** is an illustration of the photolithography and etching of the field layer of silicon dioxide on the frontside of the silicon wafer of **FIG. 35b**.

FIG. 37 is an illustration of the photolithography and etching of the layer of silicon nitride on the backside of the silicon wafer of **FIG. 36**.

25 **FIG. 38** is an illustration of the photolithography and etching of the pad layer of silicon dioxide on the backside of the silicon wafer of **FIG. 37**.

FIG. 39 is an illustration of the KOH etching to a depth of 150 microns of the exposed areas of silicon on the front and back sides of the silicon wafer of **FIG. 38**.

FIG. 39a is a cross-sectional illustration of the silicon wafer of **FIG. 39**.

30 **FIG. 39b** is a cross-sectional illustration of the silicon wafer of **FIG. 39**.

FIG. 39c is a cross-sectional illustration of the silicon wafer of **FIG. 39**.

FIG. 40 is an illustration of the etching of the exposed portions of the field layer of silicon dioxide on the front side of the silicon wafer of **FIG. 39**.

FIG. 41 is an illustration of the etching of the exposed portions of the layer of silicon dioxide on the back side of the silicon wafer of **FIG. 40**.

5 **FIG. 42** is an illustration of the KOH etching of the exposed areas of silicon to a depth of 50 microns of the front and back sides of the silicon wafer of **FIG. 41**.

FIG. 42a is a cross-sectional illustration of the silicon wafer of **FIG. 42**.

FIG. 42b is a cross-sectional illustration of the silicon wafer of **FIG. 42**.

10 **FIG. 42c** is a cross-sectional illustration of the silicon wafer of **FIG. 42**.

FIG. 43 is an illustration of the application of a layer of gold to both sides of the silicon wafer of **FIG. 42**.

FIG. 43a is a cross-sectional illustration of the silicon wafer of **FIG. 43**.

FIG. 43b is a cross-sectional illustration of the silicon wafer of **FIG. 43**.

15 **FIG. 43c** is a cross-sectional illustration of the silicon wafer of **FIG. 43**.

FIG. 43d is a flow chart illustrating an embodiment of a process for bonding the top/bottom caps to the mirror.

FIG. 44 is an illustration of a flow chart for various alternative embodiments of LOCOS merged-mask micro-machining processes.

20 **FIG. 45a** is a cross-sectional illustration of a silicon wafer.

FIG. 45b is a cross-sectional illustration of the silicon wafer of **FIG. 45a** including a layer of silicon nitride.

FIG. 45c is a cross-sectional illustration of a silicon wafer of **FIG. 45b** after patterning the layer of silicon nitride.

25 **FIG. 45d** is a cross-sectional illustration of the silicon wafer of **FIG. 45c** after growing a layer of silicon dioxide on the exposed portions of the silicon wafer.

FIG. 45e is a cross-sectional illustration of the silicon wafer of **FIG. 45d** after patterning the layer of silicon dioxide.

30 **FIG. 45f** is a cross-sectional illustration of the silicon wafer of **FIG. 45e** after etching the exposed portions of the silicon wafer.

FIG. 45g is a cross-sectional illustration of the silicon wafer of **FIG. 45f** after removing the exposed portions of the layer of silicon dioxide.

FIG. 45h is a cross-sectional illustration of the silicon wafer of **FIG. 45g** after etching the exposed portions of the silicon wafer.

5 **FIG. 45i** is a cross-sectional illustration of the silicon wafer of **FIG. 45h** after removing the layer of silicon nitride.

FIG. 46a is a cross-sectional illustration of a silicon wafer.

FIG. 46b is a cross-sectional illustration of the silicon wafer of **FIG. 46a** including a layer of silicon nitride.

10 **FIG. 46c** is a cross-sectional illustration of a silicon wafer of **FIG. 46b** after patterning the layer of silicon nitride.

FIG. 46d is a cross-sectional illustration of the silicon wafer of **FIG. 46c** after a thin etch of the exposed portions of the silicon wafer.

15 **FIG. 46e** is a cross-sectional illustration of the silicon wafer of **FIG. 46d** after growing a layer of silicon dioxide on the exposed portions of the silicon wafer.

FIG. 46f is a cross-sectional illustration of the silicon wafer of **FIG. 46e** after patterning the layer of silicon dioxide.

20 **FIG. 46g** is a cross-sectional illustration of the silicon wafer of **FIG. 46f** after etching the exposed portions of the silicon wafer.

FIG. 46h is a cross-sectional illustration of the silicon wafer of **FIG. 46g** after removing the exposed portions of the layer of silicon dioxide.

FIG. 46i is a cross-sectional illustration of the silicon wafer of **FIG. 46h** after etching the exposed portions of the silicon wafer.

25 **FIG. 46j** is a cross-sectional illustration of the silicon wafer of **FIG. 46i** after removing the layer of silicon nitride.

FIG. 47a is a cross-sectional illustration of a silicon wafer.

FIG. 47b is a cross-sectional illustration of the silicon wafer of **FIG. 47a** including a buffer layer of silicon dioxide.

30 **FIG. 47c** is a cross-sectional illustration of the silicon wafer of **FIG. 47b** including a layer of silicon nitride on the buffer layer of silicon dioxide.

FIG. 47d is a cross-sectional illustration of a silicon wafer of **FIG. 47c** after patterning the layer of silicon nitride.

5 **FIG. 47e** is a cross-sectional illustration of the silicon wafer of **FIG. 47d** after growing a layer of silicon dioxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 47f is a cross-sectional illustration of the silicon wafer of **FIG. 47e** after patterning the layer of silicon dioxide.

FIG. 47g is a cross-sectional illustration of the silicon wafer of **FIG. 47f** after etching the exposed portions of the silicon wafer.

10 **FIG. 47h** is a cross-sectional illustration of the silicon wafer of **FIG. 47g** after removing the exposed portions of the layers of silicon dioxide.

FIG. 47i is a cross-sectional illustration of the silicon wafer of **FIG. 47h** after etching the exposed portions of the silicon wafer.

15 **FIG. 47j** is a cross-sectional illustration of the silicon wafer of **FIG. 46i** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 48a is a cross-sectional illustration of a silicon wafer.

FIG. 48b is a cross-sectional illustration of the silicon wafer of **FIG. 48a** including a buffer layer of silicon dioxide.

20 **FIG. 48c** is a cross-sectional illustration of the silicon wafer of **FIG. 48b** including a layer of silicon nitride on the buffer layer of silicon dioxide.

FIG. 48d is a cross-sectional illustration of a silicon wafer of **FIG. 48c** after patterning the layer of silicon nitride.

25 **FIG. 48e** is a cross-sectional illustration of the silicon wafer of **FIG. 48d** after patterning the exposed portions of the buffer layer of silicon dioxide.

FIG. 48f is a cross-sectional illustration of the silicon wafer of **FIG. 48e** after growing a layer of silicon dioxide on the portions not covered by the patterned layer of silicon nitride.

30 **FIG. 48g** is a cross-sectional illustration of the silicon wafer of **FIG. 48f** after patterning the layer of silicon dioxide.

FIG. 48h is a cross-sectional illustration of the silicon wafer of **FIG. 48g** after etching the exposed portions of the silicon wafer.

FIG. 48i is a cross-sectional illustration of the silicon wafer of **FIG. 48h** after removing the exposed portions of the layers of silicon dioxide.

5 **FIG. 48j** is a cross-sectional illustration of the silicon wafer of **FIG. 48i** after etching the exposed portions of the silicon wafer.

FIG. 48k is a cross-sectional illustration of the silicon wafer of **FIG. 48j** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

10 **FIG. 49a** is a cross-sectional illustration of a silicon wafer.

FIG. 49b is a cross-sectional illustration of the silicon wafer of **FIG. 49a** including a buffer layer of silicon dioxide.

FIG. 49c is a cross-sectional illustration of the silicon wafer of **FIG. 49b** including a layer of silicon nitride on the buffer layer of silicon dioxide.

15 **FIG. 49d** is a cross-sectional illustration of a silicon wafer of **FIG. 49c** after patterning the layer of silicon nitride.

FIG. 49e is a cross-sectional illustration of the silicon wafer of **FIG. 49d** after patterning the exposed portions of the buffer layer of silicon dioxide.

20 **FIG. 49f** is a cross-sectional illustration of the silicon wafer of **FIG. 49e** after thin etching the exposed portions of the silicon wafer.

FIG. 49g is a cross-sectional illustration of the silicon wafer of **FIG. 49f** after growing a layer of silicon dioxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 49h** is a cross-sectional illustration of the silicon wafer of **FIG. 49g** after patterning the layer of silicon dioxide.

FIG. 49i is a cross-sectional illustration of the silicon wafer of **FIG. 49h** after etching the exposed portions of the silicon wafer.

FIG. 49j is a cross-sectional illustration of the silicon wafer of **FIG. 49i** after removing the exposed portions of the layers of silicon dioxide.

30 **FIG. 49k** is a cross-sectional illustration of the silicon wafer of **FIG. 49j** after etching the exposed portions of the silicon wafer.

FIG. 49l is a cross-sectional illustration of the silicon wafer of **FIG. 49k** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

5 **FIG. 50** is a flow chart illustrating several embodiments of LOCOS merged-mask micromachining processes including multiple etch depths.

FIG. 51a is a cross-sectional view of a silicon wafer.

FIG. 51b is a cross-sectional view of the silicon wafer of **FIG. 51a** including a layer of silicon nitride.

10 **FIG. 51c** is a cross-sectional view of the silicon wafer of **FIG. 51b** after patterning the layer of silicon nitride.

FIG. 51d is a cross-sectional view of the silicon wafer of **FIG. 51c** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 51e is a cross-sectional view of the silicon wafer of **FIG. 51d** after multiple patterning operations performed on the field layer of oxide.

15 **FIG. 51f** is a cross-sectional view of the silicon wafer of **FIG. 51e** after etching the exposed portions of silicon.

FIG. 51g is a cross-sectional view of the silicon wafer of **FIG. 51f** after etching portions of the exposed portions of the field layer of silicon dioxide.

20 **FIG. 51h** is a cross-sectional view of the silicon wafer of **FIG. 51g** after etching the exposed portions of silicon.

FIG. 51i is a cross-sectional view of the silicon wafer of **FIG. 51h** after etching portions of the exposed portions of the field layer of silicon dioxide.

FIG. 51j is a cross-sectional view of the silicon wafer of **FIG. 51i** after etching the exposed portions of silicon.

25 **FIG. 51k** is a cross-sectional view of the silicon wafer of **FIG. 51j** after etching the exposed portions of the layer of silicon nitride.

FIG. 52a is a cross-sectional view of a silicon wafer.

FIG. 52b is a cross-sectional view of the silicon wafer of **FIG. 52a** including a layer of silicon nitride.

30 **FIG. 52c** is a cross-sectional view of the silicon wafer of **FIG. 52b** after patterning the layer of silicon nitride.

FIG. 52d is a cross-sectional view of the silicon wafer of **FIG. 52c** after a thin etch of the exposed portions of silicon.

FIG. 52e is a cross-sectional view of the silicon wafer of **FIG. 52d** after growing a field layer of oxide on the exposed portions of silicon.

5 **FIG. 52f** is a cross-sectional view of the silicon wafer of **FIG. 52e** after multiple patterning operations performed on the field layer of oxide.

FIG. 52g is a cross-sectional view of the silicon wafer of **FIG. 52f** after etching the exposed portions of silicon.

10 **FIG. 52h** is a cross-sectional view of the silicon wafer of **FIG. 52g** after etching portions of the exposed portions of the field layer of silicon dioxide.

FIG. 52i is a cross-sectional view of the silicon wafer of **FIG. 52h** after etching the exposed portions of silicon.

FIG. 52j is a cross-sectional view of the silicon wafer of **FIG. 52i** after etching portions of the exposed portions of the field layer of silicon dioxide.

15 **FIG. 52k** is a cross-sectional view of the silicon wafer of **FIG. 52j** after etching the exposed portions of silicon.

FIG. 52l is a cross-sectional view of the silicon wafer of **FIG. 52k** after etching the exposed portions of the layer of silicon nitride.

FIG. 53a is a cross-sectional view of a silicon wafer.

20 **FIG. 53b** is a cross-sectional view of the silicon wafer of **FIG. 53a** including a pad layer of silicon dioxide.

FIG. 53c is a cross-sectional view of the silicon wafer of **FIG. 53b** including a layer of silicon nitride.

25 **FIG. 53d** is a cross-sectional view of the silicon wafer of **FIG. 53c** after patterning the layer of silicon nitride.

FIG. 53e is a cross-sectional view of the silicon wafer of **FIG. 53d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

30 **FIG. 53f** is a cross-sectional view of the silicon wafer of **FIG. 53e** after multiple patterning operations performed on the layers of silicon dioxide.

FIG. 53g is a cross-sectional view of the silicon wafer of **FIG. 53f** after etching the exposed portions of silicon.

FIG. 53h is a cross-sectional view of the silicon wafer of **FIG. 53g** after etching portions of the exposed portions of the layers of silicon dioxide.

5 **FIG. 53i** is a cross-sectional view of the silicon wafer of **FIG. 53h** after etching the exposed portions of silicon.

FIG. 53j is a cross-sectional view of the silicon wafer of **FIG. 53i** after etching portions of the exposed portions of the layers of silicon dioxide.

10 **FIG. 53k** is a cross-sectional view of the silicon wafer of **FIG. 53j** after etching the exposed portions of silicon.

FIG. 53l is a cross-sectional view of the silicon wafer of **FIG. 53k** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 54a is a cross-sectional view of a silicon wafer.

15 **FIG. 54b** is a cross-sectional view of the silicon wafer of **FIG. 54a** including a pad layer of silicon dioxide.

FIG. 54c is a cross-sectional view of the silicon wafer of **FIG. 54b** including a layer of silicon nitride.

20 **FIG. 54d** is a cross-sectional view of the silicon wafer of **FIG. 54c** after patterning the layer of silicon nitride.

FIG. 54e is a cross-sectional view of the silicon wafer of **FIG. 54d** after patterning the pad layer of silicon dioxide.

25 **FIG. 54f** is a cross-sectional view of the silicon wafer of **FIG. 54e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 54g is a cross-sectional view of the silicon wafer of **FIG. 54f** after multiple patterning operations performed on the layers of silicon dioxide.

FIG. 54h is a cross-sectional view of the silicon wafer of **FIG. 54g** after etching the exposed portions of silicon.

30 **FIG. 54i** is a cross-sectional view of the silicon wafer of **FIG. 54h** after etching portions of the exposed portions of the layers of silicon dioxide.

FIG. 54j is a cross-sectional view of the silicon wafer of **FIG. 54i** after etching the exposed portions of silicon.

FIG. 54k is a cross-sectional view of the silicon wafer of **FIG. 54j** after etching portions of the exposed portions of the layers of silicon dioxide.

5 **FIG. 54l** is a cross-sectional view of the silicon wafer of **FIG. 54k** after etching the exposed portions of silicon.

FIG. 54m is a cross-sectional view of the silicon wafer of **FIG. 54l** after etching the exposed portions of the layers of silicon dioxide and silicon nitride.

FIG. 55a is a cross-sectional view of a silicon wafer.

10 **FIG. 55b** is a cross-sectional view of the silicon wafer of **FIG. 55a** including a pad layer of silicon dioxide.

FIG. 55c is a cross-sectional view of the silicon wafer of **FIG. 55b** including a layer of silicon nitride.

15 **FIG. 55d** is a cross-sectional view of the silicon wafer of **FIG. 55c** after patterning the layer of silicon nitride.

FIG. 55e is a cross-sectional view of the silicon wafer of **FIG. 55d** after patterning the pad layer of silicon dioxide.

FIG. 55f is a cross-sectional view of the silicon wafer of **FIG. 55e** after a thin etch of the exposed areas of silicon.

20 **FIG. 55g** is a cross-sectional view of the silicon wafer of **FIG. 55f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 55h is a cross-sectional view of the silicon wafer of **FIG. 55g** after multiple patterning operations performed on the layers of silicon dioxide.

25 **FIG. 55i** is a cross-sectional view of the silicon wafer of **FIG. 55h** after etching the exposed portions of silicon.

FIG. 55j is a cross-sectional view of the silicon wafer of **FIG. 55i** after etching portions of the exposed portions of the layers of silicon dioxide.

30 **FIG. 55k** is a cross-sectional view of the silicon wafer of **FIG. 55j** after etching the exposed portions of silicon.

FIG. 55l is a cross-sectional view of the silicon wafer of **FIG. 55k** after etching portions of the exposed portions of the layers of silicon dioxide.

FIG. 55m is a cross-sectional view of the silicon wafer of **FIG. 55l** after etching the exposed portions of silicon.

5 **FIG. 55n** is a cross-sectional view of the silicon wafer of **FIG. 55m** after etching the exposed portions of the layers of silicon dioxide and silicon nitride.

FIGS. 56a and **56b** are a flow chart illustrating several embodiments of LOCOS merged-mask micromachining processes including using photoresist as a mask for deep reactive ion etching of silicon.

10 **FIG. 57a** is a cross-sectional view of a silicon wafer.

FIG. 57b is a cross-sectional view of the silicon wafer of **FIG. 57a** including a layer of silicon nitride.

FIG. 57c is a cross-sectional view of the silicon wafer of **FIG. 57b** after patterning the layer of silicon nitride.

15 **FIG. 57d** is a cross-sectional view of the silicon wafer of **FIG. 57c** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 57e is a cross-sectional view of the silicon wafer of **FIG. 57d** after patterning the field layer of oxide.

20 **FIG. 57f** is a cross-sectional view of the silicon wafer of **FIG. 57e** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 57g is a cross-sectional view of the silicon wafer of **FIG. 57f** after etching the exposed portions of silicon.

FIG. 57h is a cross-sectional view of the silicon wafer of **FIG. 57g** after removing the photoresist.

25 **FIG. 57i** is a cross-sectional view of the silicon wafer of **FIG. 57h** after etching the exposed portions of silicon.

FIG. 57j is a cross-sectional view of the silicon wafer of **FIG. 57i** after etching the exposed portions of the field layer of silicon dioxide.

30 **FIG. 57k** is a cross-sectional view of the silicon wafer of **FIG. 57j** after etching the exposed portions of silicon.

FIG. 57l is a cross-sectional view of the silicon wafer of **FIG. 57k** after etching the exposed portions of the layer of silicon nitride.

FIG. 58a is a cross-sectional view of a silicon wafer.

5 **FIG. 58b** is a cross-sectional view of the silicon wafer of **FIG. 58a** including a layer of silicon nitride.

FIG. 58c is a cross-sectional view of the silicon wafer of **FIG. 58b** after patterning the layer of silicon nitride.

FIG. 58d is a cross-sectional view of the silicon wafer of **FIG. 58c** after growing a field layer of oxide on the exposed portions of silicon.

10 **FIG. 58e** is a cross-sectional view of the silicon wafer of **FIG. 58d** after patterning the field layer of oxide.

FIG. 58f is a cross-sectional view of the silicon wafer of **FIG. 58e** after applying and patterning a layer of photoresist onto the silicon wafer.

15 **FIG. 58g** is a cross-sectional view of the silicon wafer of **FIG. 58f** after etching the exposed portions of silicon.

FIG. 58h is a cross-sectional view of the silicon wafer of **FIG. 58g** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 58i is a cross-sectional view of the silicon wafer of **FIG. 58h** after removing the photoresist.

20 **FIG. 58j** is a cross-sectional view of the silicon wafer of **FIG. 58i** after etching the exposed portions of silicon.

FIG. 58k is a cross-sectional view of the silicon wafer of **FIG. 58j** after etching the exposed portions of the field layer of silicon dioxide.

25 **FIG. 58l** is a cross-sectional view of the silicon wafer of **FIG. 58k** after etching the exposed portions of silicon.

FIG. 58m is a cross-sectional view of the silicon wafer of **FIG. 58l** after etching the exposed portions of the layer of silicon nitride.

FIG. 59a is a cross-sectional view of a silicon wafer.

30 **FIG. 59b** is a cross-sectional view of the silicon wafer of **FIG. 59a** including a layer of silicon nitride.

FIG. 59c is a cross-sectional view of the silicon wafer of **FIG. 59b** after patterning the layer of silicon nitride.

FIG. 59d is a cross-sectional view of the silicon wafer of **FIG. 59c** after growing a field layer of oxide on the exposed portions of silicon.

5 **FIG. 59e** is a cross-sectional view of the silicon wafer of **FIG. 59d** after patterning the field layer of oxide.

FIG. 59f is a cross-sectional view of the silicon wafer of **FIG. 59e** after applying and patterning a layer of photoresist onto the silicon wafer.

10 **FIG. 59g** is a cross-sectional view of the silicon wafer of **FIG. 59f** after etching the exposed portions of silicon.

FIG. 59h is a cross-sectional view of the silicon wafer of **FIG. 59g** after etching the exposed portions of silicon.

FIG. 59i is a cross-sectional view of the silicon wafer of **FIG. 59h** after removing the photoresist.

15 **FIG. 59j** is a cross-sectional view of the silicon wafer of **FIG. 59i** after etching the exposed portions of silicon.

FIG. 59k is a cross-sectional view of the silicon wafer of **FIG. 59j** after etching the exposed portions of the field layer of silicon dioxide.

20 **FIG. 59l** is a cross-sectional view of the silicon wafer of **FIG. 59k** after etching the exposed portions of silicon.

FIG. 59m is a cross-sectional view of the silicon wafer of **FIG. 59l** after etching the exposed portions of the layer of silicon nitride.

FIG. 60a is a cross-sectional view of a silicon wafer.

25 **FIG. 60b** is a cross-sectional view of the silicon wafer of **FIG. 60a** including a layer of silicon nitride.

FIG. 60c is a cross-sectional view of the silicon wafer of **FIG. 60b** after patterning the layer of silicon nitride.

FIG. 60d is a cross-sectional view of the silicon wafer of **FIG. 60c** after growing a field layer of oxide on the exposed portions of silicon.

30 **FIG. 60e** is a cross-sectional view of the silicon wafer of **FIG. 60d** after patterning the field layer of oxide.

FIG. 60f is a cross-sectional view of the silicon wafer of **FIG. 60e** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 60g is a cross-sectional view of the silicon wafer of **FIG. 60f** after etching the exposed portions of silicon.

5 **FIG. 60h** is a cross-sectional view of the silicon wafer of **FIG. 60g** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 60i is a cross-sectional view of the silicon wafer of **FIG. 60h** after etching the exposed portions of silicon.

10 **FIG. 60j** is a cross-sectional view of the silicon wafer of **FIG. 60i** after removing the photoresist.

FIG. 60k is a cross-sectional view of the silicon wafer of **FIG. 60j** after etching the exposed portions of silicon.

FIG. 60l is a cross-sectional view of the silicon wafer of **FIG. 60k** after etching the exposed portions of the field layer of silicon dioxide.

15 **FIG. 60m** is a cross-sectional view of the silicon wafer of **FIG. 60l** after etching the exposed portions of silicon.

FIG. 60n is a cross-sectional view of the silicon wafer of **FIG. 60m** after etching the exposed portions of the layer of silicon nitride.

FIG. 61a is a cross-sectional view of a silicon wafer.

20 **FIG. 61b** is a cross-sectional view of the silicon wafer of **FIG. 61a** including a layer of silicon nitride.

FIG. 61c is a cross-sectional view of the silicon wafer of **FIG. 61b** after patterning the layer of silicon nitride.

25 **FIG. 61d** is a cross-sectional view of the silicon wafer of **FIG. 61c** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 61e is a cross-sectional view of the silicon wafer of **FIG. 61d** after patterning the field layer of oxide.

FIG. 61f is a cross-sectional view of the silicon wafer of **FIG. 61e** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 61g** is a cross-sectional view of the silicon wafer of **FIG. 61f** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 61h is a cross-sectional view of the silicon wafer of **FIG. 61g** after removing the photoresist.

FIG. 61i is a cross-sectional view of the silicon wafer of **FIG. 61h** after etching the exposed portions of silicon.

5 **FIG. 61j** is a cross-sectional view of the silicon wafer of **FIG. 61i** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 61k is a cross-sectional view of the silicon wafer of **FIG. 61j** after etching the exposed portions of silicon.

10 **FIG. 61l** is a cross-sectional view of the silicon wafer of **FIG. 61k** after etching the exposed portions of the layer of silicon nitride.

FIG. 62a is a cross-sectional view of a silicon wafer.

FIG. 62b is a cross-sectional view of the silicon wafer of **FIG. 62a** including a layer of silicon nitride.

15 **FIG. 62c** is a cross-sectional view of the silicon wafer of **FIG. 62b** after patterning the layer of silicon nitride.

FIG. 62d is a cross-sectional view of the silicon wafer of **FIG. 62c** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 62e is a cross-sectional view of the silicon wafer of **FIG. 62d** after patterning the field layer of oxide.

20 **FIG. 62f** is a cross-sectional view of the silicon wafer of **FIG. 62e** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 62g is a cross-sectional view of the silicon wafer of **FIG. 62f** after etching the exposed portions of the field layer of silicon dioxide.

25 **FIG. 62h** is a cross-sectional view of the silicon wafer of **FIG. 62g** after etching the exposed portions of silicon.

FIG. 62i is a cross-sectional view of the silicon wafer of **FIG. 62h** after removing the photoresist.

FIG. 62j is a cross-sectional view of the silicon wafer of **FIG. 62i** after etching the exposed portions of silicon.

30 **FIG. 62k** is a cross-sectional view of the silicon wafer of **FIG. 62j** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 62l is a cross-sectional view of the silicon wafer of **FIG. 62k** after etching the exposed portions of silicon.

FIG. 62m is a cross-sectional view of the silicon wafer of **FIG. 62l** after etching the exposed portions of the layer of silicon nitride.

5 **FIG. 63a** is a cross-sectional view of a silicon wafer.

FIG. 63b is a cross-sectional view of the silicon wafer of **FIG. 63a** including a layer of silicon nitride.

FIG. 63c is a cross-sectional view of the silicon wafer of **FIG. 63b** after patterning the layer of silicon nitride.

10 **FIG. 63d** is a cross-sectional view of the silicon wafer of **FIG. 63c** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 63e is a cross-sectional view of the silicon wafer of **FIG. 63d** after patterning the field layer of oxide.

15 **FIG. 63f** is a cross-sectional view of the silicon wafer of **FIG. 63e** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 63g is a cross-sectional view of the silicon wafer of **FIG. 63f** after etching the exposed portions of silicon.

FIG. 63h is a cross-sectional view of the silicon wafer of **FIG. 63g** after removing the photoresist.

20 **FIG. 63i** is a cross-sectional view of the silicon wafer of **FIG. 63h** after etching the exposed portions of silicon.

FIG. 63j is a cross-sectional view of the silicon wafer of **FIG. 63i** after etching the exposed portions of the field layer of silicon dioxide.

25 **FIG. 63k** is a cross-sectional view of the silicon wafer of **FIG. 63j** after etching the exposed portions of silicon.

FIG. 63l is a cross-sectional view of the silicon wafer of **FIG. 63k** after etching the exposed portions of the layer of silicon nitride.

FIG. 64a is a cross-sectional view of a silicon wafer.

30 **FIG. 64b** is a cross-sectional view of the silicon wafer of **FIG. 64a** including a layer of silicon nitride.

FIG. 64c is a cross-sectional view of the silicon wafer of **FIG. 64b** after patterning the layer of silicon nitride.

FIG. 64d is a cross-sectional view of the silicon wafer of **FIG. 64c** after a thin etch of the exposed portions of silicon.

5 **FIG. 64e** is a cross-sectional view of the silicon wafer of **FIG. 64d** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 64f is a cross-sectional view of the silicon wafer of **FIG. 64e** after patterning the field layer of oxide.

10 **FIG. 64g** is a cross-sectional view of the silicon wafer of **FIG. 64f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 64h is a cross-sectional view of the silicon wafer of **FIG. 64g** after etching the exposed portions of silicon.

FIG. 64i is a cross-sectional view of the silicon wafer of **FIG. 64h** after removing the layer of photoresist.

15 **FIG. 64j** is a cross-sectional view of the silicon wafer of **FIG. 64i** after etching the exposed portions of silicon.

FIG. 64k is a cross-sectional view of the silicon wafer of **FIG. 64j** after etching the exposed portions of the field layer of silicon dioxide.

20 **FIG. 64l** is a cross-sectional view of the silicon wafer of **FIG. 64k** after etching the exposed portions of silicon.

FIG. 64m is a cross-sectional view of the silicon wafer of **FIG. 64l** after etching the exposed portions of the layer of silicon nitride.

FIG. 65a is a cross-sectional view of a silicon wafer.

25 **FIG. 65b** is a cross-sectional view of the silicon wafer of **FIG. 65a** including a layer of silicon nitride.

FIG. 65c is a cross-sectional view of the silicon wafer of **FIG. 65b** after patterning the layer of silicon nitride.

FIG. 65d is a cross-sectional view of the silicon wafer of **FIG. 65c** after a thin etch of the exposed portions of silicon.

30 **FIG. 65e** is a cross-sectional view of the silicon wafer of **FIG. 65d** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 65f is a cross-sectional view of the silicon wafer of **FIG. 65e** after patterning the field layer of oxide.

FIG. 65g is a cross-sectional view of the silicon wafer of **FIG. 65f** after applying and patterning a layer of photoresist onto the silicon wafer.

5 **FIG. 65h** is a cross-sectional view of the silicon wafer of **FIG. 65g** after etching the exposed portions of silicon.

FIG. 65i is a cross-sectional view of the silicon wafer of **FIG. 65h** after etching the exposed portions of the field layer of silicon dioxide.

10 **FIG. 65j** is a cross-sectional view of the silicon wafer of **FIG. 65i** after removing the layer of photoresist.

FIG. 65k is a cross-sectional view of the silicon wafer of **FIG. 65j** after etching the exposed portions of silicon.

FIG. 65l is a cross-sectional view of the silicon wafer of **FIG. 65k** after etching the exposed portions of the field layer of silicon dioxide.

15 **FIG. 65m** is a cross-sectional view of the silicon wafer of **FIG. 65l** after etching the exposed portions of silicon.

FIG. 65n is a cross-sectional view of the silicon wafer of **FIG. 65m** after etching the exposed portions of the layer of silicon nitride.

FIG. 66a is a cross-sectional view of a silicon wafer.

20 **FIG. 66b** is a cross-sectional view of the silicon wafer of **FIG. 66a** including a layer of silicon nitride.

FIG. 66c is a cross-sectional view of the silicon wafer of **FIG. 66b** after patterning the layer of silicon nitride.

25 **FIG. 66d** is a cross-sectional view of the silicon wafer of **FIG. 66c** after a thin etch of the exposed portions of silicon.

FIG. 66e is a cross-sectional view of the silicon wafer of **FIG. 66d** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 66f is a cross-sectional view of the silicon wafer of **FIG. 66e** after patterning the field layer of oxide.

30 **FIG. 66g** is a cross-sectional view of the silicon wafer of **FIG. 66f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 66h is a cross-sectional view of the silicon wafer of **FIG. 66g** after etching the exposed portions of silicon.

FIG. 66i is a cross-sectional view of the silicon wafer of **FIG. 66h** after etching the exposed portions of silicon.

5 **FIG. 66j** is a cross-sectional view of the silicon wafer of **FIG. 66i** after removing the layer of photoresist.

FIG. 66k is a cross-sectional view of the silicon wafer of **FIG. 66j** after etching the exposed portions of silicon.

10 **FIG. 66l** is a cross-sectional view of the silicon wafer of **FIG. 66k** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 66m is a cross-sectional view of the silicon wafer of **FIG. 66l** after etching the exposed portions of silicon.

FIG. 66n is a cross-sectional view of the silicon wafer of **FIG. 66m** after etching the exposed portions of the layer of silicon nitride.

15 **FIG. 67a** is a cross-sectional view of a silicon wafer.

FIG. 67b is a cross-sectional view of the silicon wafer of **FIG. 67a** including a layer of silicon nitride.

FIG. 67c is a cross-sectional view of the silicon wafer of **FIG. 67b** after patterning the layer of silicon nitride.

20 **FIG. 67d** is a cross-sectional view of the silicon wafer of **FIG. 67c** after a thin etch of the exposed portions of silicon.

FIG. 67e is a cross-sectional view of the silicon wafer of **FIG. 67d** after growing a field layer of oxide on the exposed portions of silicon.

25 **FIG. 67f** is a cross-sectional view of the silicon wafer of **FIG. 67e** after patterning the field layer of oxide.

FIG. 67g is a cross-sectional view of the silicon wafer of **FIG. 67f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 67h is a cross-sectional view of the silicon wafer of **FIG. 67g** after etching the exposed portions of silicon.

30 **FIG. 67i** is a cross-sectional view of the silicon wafer of **FIG. 67h** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 67j is a cross-sectional view of the silicon wafer of **FIG. 67i** after etching the exposed portions of silicon.

FIG. 67k is a cross-sectional view of the silicon wafer of **FIG. 67j** after removing the layer of photoresist.

5 **FIG. 67l** is a cross-sectional view of the silicon wafer of **FIG. 67k** after etching the exposed portions of silicon.

FIG. 67m is a cross-sectional view of the silicon wafer of **FIG. 67l** after etching the exposed portions of the field layer of silicon dioxide.

10 **FIG. 67n** is a cross-sectional view of the silicon wafer of **FIG. 67m** after etching the exposed portions of silicon.

FIG. 67o is a cross-sectional view of the silicon wafer of **FIG. 67n** after etching the exposed portions of the layer of silicon nitride.

FIG. 68a is a cross-sectional view of a silicon wafer.

15 **FIG. 68b** is a cross-sectional view of the silicon wafer of **FIG. 68a** including a layer of silicon nitride.

FIG. 68c is a cross-sectional view of the silicon wafer of **FIG. 68b** after patterning the layer of silicon nitride.

FIG. 68d is a cross-sectional view of the silicon wafer of **FIG. 68c** after a thin etch of the exposed portions of silicon.

20 **FIG. 68e** is a cross-sectional view of the silicon wafer of **FIG. 68d** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 68f is a cross-sectional view of the silicon wafer of **FIG. 68e** after patterning the field layer of oxide.

25 **FIG. 68g** is a cross-sectional view of the silicon wafer of **FIG. 68f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 68h is a cross-sectional view of the silicon wafer of **FIG. 68g** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 68i is a cross-sectional view of the silicon wafer of **FIG. 68h** after removing the layer of photoresist.

30 **FIG. 68j** is a cross-sectional view of the silicon wafer of **FIG. 68i** after etching the exposed portions of silicon.

FIG. 68k is a cross-sectional view of the silicon wafer of **FIG. 68j** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 68l is a cross-sectional view of the silicon wafer of **FIG. 68k** after etching the exposed portions of silicon.

FIG. 68m is a cross-sectional view of the silicon wafer of **FIG. 68l** after etching the exposed portions of the layer of silicon nitride.

FIG. 69a is a cross-sectional view of a silicon wafer.

FIG. 69b is a cross-sectional view of the silicon wafer of **FIG. 69a** including a layer of silicon nitride.

FIG. 69c is a cross-sectional view of the silicon wafer of **FIG. 69b** after patterning the layer of silicon nitride.

FIG. 69d is a cross-sectional view of the silicon wafer of **FIG. 69c** after a thin etch of the exposed portions of silicon.

FIG. 69e is a cross-sectional view of the silicon wafer of **FIG. 69d** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 69f is a cross-sectional view of the silicon wafer of **FIG. 69e** after patterning the field layer of oxide.

FIG. 69g is a cross-sectional view of the silicon wafer of **FIG. 69f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 69h is a cross-sectional view of the silicon wafer of **FIG. 69g** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 69i is a cross-sectional view of the silicon wafer of **FIG. 69h** after etching the exposed portions of silicon.

FIG. 69j is a cross-sectional view of the silicon wafer of **FIG. 69i** after removing the layer of photoresist.

FIG. 69k is a cross-sectional view of the silicon wafer of **FIG. 69j** after etching the exposed portions of silicon.

FIG. 69l is a cross-sectional view of the silicon wafer of **FIG. 69k** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 69m is a cross-sectional view of the silicon wafer of **FIG. 69l** after etching the exposed portions of silicon.

FIG. 69n is a cross-sectional view of the silicon wafer of **FIG. 69m** after etching the exposed portions of the layer of silicon nitride.

FIG. 70a is a cross-sectional view of a silicon wafer.

5 **FIG. 70b** is a cross-sectional view of the silicon wafer of **FIG. 70a** including a layer of silicon nitride.

FIG. 70c is a cross-sectional view of the silicon wafer of **FIG. 70b** after patterning the layer of silicon nitride.

FIG. 70d is a cross-sectional view of the silicon wafer of **FIG. 70c** after a thin etch of the exposed portions of silicon.

10 **FIG. 70e** is a cross-sectional view of the silicon wafer of **FIG. 70d** after growing a field layer of oxide on the exposed portions of silicon.

FIG. 70f is a cross-sectional view of the silicon wafer of **FIG. 70e** after patterning the field layer of oxide.

15 **FIG. 70g** is a cross-sectional view of the silicon wafer of **FIG. 70f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 70h is a cross-sectional view of the silicon wafer of **FIG. 70g** after etching the exposed portions of silicon.

FIG. 70i is a cross-sectional view of the silicon wafer of **FIG. 70h** after removing the layer of photoresist.

20 **FIG. 70j** is a cross-sectional view of the silicon wafer of **FIG. 70i** after etching the exposed portions of silicon.

FIG. 70k is a cross-sectional view of the silicon wafer of **FIG. 70j** after etching the exposed portions of the field layer of silicon dioxide.

25 **FIG. 70l** is a cross-sectional view of the silicon wafer of **FIG. 70k** after etching the exposed portions of silicon.

FIG. 70m is a cross-sectional view of the silicon wafer of **FIG. 70l** after etching the exposed portions of the layer of silicon nitride.

FIG. 71a is a cross-sectional view of a silicon wafer.

30 **FIG. 71b** is a cross-sectional view of the silicon wafer of **FIG. 71a** including a pad layer of silicon dioxide.

FIG. 71c is a cross-sectional view of the silicon wafer of **FIG. 71b** including a layer of silicon nitride.

FIG. 71d is a cross-sectional view of the silicon wafer of **FIG. 71c** after patterning the layer of silicon nitride.

5 **FIG. 71e** is a cross-sectional view of the silicon wafer of **FIG. 71d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 71f is a cross-sectional view of the silicon wafer of **FIG. 71e** after patterning the layers of silicon dioxide.

10 **FIG. 71g** is a cross-sectional view of the silicon wafer of **FIG. 71f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 71h is a cross-sectional view of the silicon wafer of **FIG. 71g** after etching the exposed portions of silicon.

15 **FIG. 71i** is a cross-sectional view of the silicon wafer of **FIG. 71h** after removing the layer of photoresist.

FIG. 71j is a cross-sectional view of the silicon wafer of **FIG. 71i** after etching the exposed portions of silicon.

FIG. 71k is a cross-sectional view of the silicon wafer of **FIG. 71j** after etching the exposed portions of the layers of silicon dioxide.

20 **FIG. 71l** is a cross-sectional view of the silicon wafer of **FIG. 71k** after etching the exposed portions of silicon.

FIG. 71m is a cross-sectional view of the silicon wafer of **FIG. 71l** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

25 **FIG. 72a** is a cross-sectional view of a silicon wafer.

FIG. 72b is a cross-sectional view of the silicon wafer of **FIG. 72a** including a pad layer of silicon dioxide.

FIG. 72c is a cross-sectional view of the silicon wafer of **FIG. 72b** including a layer of silicon nitride.

30 **FIG. 72d** is a cross-sectional view of the silicon wafer of **FIG. 72c** after patterning the layer of silicon nitride.

FIG. 72e is a cross-sectional view of the silicon wafer of **FIG. 72d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

5 **FIG. 72f** is a cross-sectional view of the silicon wafer of **FIG. 72e** after patterning the layers of silicon dioxide.

FIG. 72g is a cross-sectional view of the silicon wafer of **FIG. 72f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 72h is a cross-sectional view of the silicon wafer of **FIG. 72g** after etching the exposed portions of silicon.

10 **FIG. 72i** is a cross-sectional view of the silicon wafer of **FIG. 72h** after etching the exposed portions of the field layer of silicon dioxide.

FIG. 72j is a cross-sectional view of the silicon wafer of **FIG. 72i** after removing the layer of photoresist.

15 **FIG. 72k** is a cross-sectional view of the silicon wafer of **FIG. 72j** after etching the exposed portions of silicon.

FIG. 72l is a cross-sectional view of the silicon wafer of **FIG. 72k** after etching the exposed portions of the layers of silicon dioxide.

FIG. 72m is a cross-sectional view of the silicon wafer of **FIG. 72l** after etching the exposed portions of silicon.

20 **FIG. 72n** is a cross-sectional view of the silicon wafer of **FIG. 72m** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 73a is a cross-sectional view of a silicon wafer.

25 **FIG. 73b** is a cross-sectional view of the silicon wafer of **FIG. 73a** including a pad layer of silicon dioxide.

FIG. 73c is a cross-sectional view of the silicon wafer of **FIG. 73b** including a layer of silicon nitride.

FIG. 73d is a cross-sectional view of the silicon wafer of **FIG. 73c** after patterning the layer of silicon nitride.

FIG. 73e is a cross-sectional view of the silicon wafer of **FIG. 73d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

5 **FIG. 73f** is a cross-sectional view of the silicon wafer of **FIG. 73e** after patterning the layers of silicon dioxide.

FIG. 73g is a cross-sectional view of the silicon wafer of **FIG. 73f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 73h is a cross-sectional view of the silicon wafer of **FIG. 73g** after etching the exposed portions of silicon.

10 **FIG. 73i** is a cross-sectional view of the silicon wafer of **FIG. 73h** after etching the exposed portions of silicon.

FIG. 73j is a cross-sectional view of the silicon wafer of **FIG. 73i** after removing the layer of photoresist.

15 **FIG. 73k** is a cross-sectional view of the silicon wafer of **FIG. 73j** after etching the exposed portions of silicon.

FIG. 73l is a cross-sectional view of the silicon wafer of **FIG. 73k** after etching the exposed portions of the layers of silicon dioxide.

FIG. 73m is a cross-sectional view of the silicon wafer of **FIG. 73l** after etching the exposed portions of silicon.

20 **FIG. 73n** is a cross-sectional view of the silicon wafer of **FIG. 73m** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 74a is a cross-sectional view of a silicon wafer.

25 **FIG. 74b** is a cross-sectional view of the silicon wafer of **FIG. 74a** including a pad layer of silicon dioxide.

FIG. 74c is a cross-sectional view of the silicon wafer of **FIG. 74b** including a layer of silicon nitride.

FIG. 74d is a cross-sectional view of the silicon wafer of **FIG. 74c** after patterning the layer of silicon nitride.

FIG. 74e is a cross-sectional view of the silicon wafer of **FIG. 74d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

5 **FIG. 74f** is a cross-sectional view of the silicon wafer of **FIG. 74e** after patterning the layers of silicon dioxide.

FIG. 74g is a cross-sectional view of the silicon wafer of **FIG. 74f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 74h is a cross-sectional view of the silicon wafer of **FIG. 74g** after etching the exposed portions of silicon.

10 **FIG. 74i** is a cross-sectional view of the silicon wafer of **FIG. 74h** after etching the exposed portions of the layers of silicon dioxide.

FIG. 74j is a cross-sectional view of the silicon wafer of **FIG. 74i** after etching the exposed portions of silicon.

15 **FIG. 74k** is a cross-sectional view of the silicon wafer of **FIG. 74j** after removing the layer of photoresist.

FIG. 74l is a cross-sectional view of the silicon wafer of **FIG. 74k** after etching the exposed portions of silicon.

FIG. 74m is a cross-sectional view of the silicon wafer of **FIG. 74l** after etching the exposed portions of the layers of silicon dioxide.

20 **FIG. 74n** is a cross-sectional view of the silicon wafer of **FIG. 74m** after etching the exposed portions of silicon.

FIG. 74o is a cross-sectional view of the silicon wafer of **FIG. 74n** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

25 **FIG. 75a** is a cross-sectional view of a silicon wafer.

FIG. 75b is a cross-sectional view of the silicon wafer of **FIG. 75a** including a pad layer of silicon dioxide.

FIG. 75c is a cross-sectional view of the silicon wafer of **FIG. 75b** including a layer of silicon nitride.

30 **FIG. 75d** is a cross-sectional view of the silicon wafer of **FIG. 75c** after patterning the layer of silicon nitride.

FIG. 75e is a cross-sectional view of the silicon wafer of **FIG. 75d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

5 **FIG. 75f** is a cross-sectional view of the silicon wafer of **FIG. 75e** after patterning the layers of silicon dioxide.

FIG. 75g is a cross-sectional view of the silicon wafer of **FIG. 75f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 75h is a cross-sectional view of the silicon wafer of **FIG. 75g** after etching the exposed portions of the layers of silicon dioxide.

10 **FIG. 75i** is a cross-sectional view of the silicon wafer of **FIG. 75h** after removing the layer of photoresist.

FIG. 75j is a cross-sectional view of the silicon wafer of **FIG. 75i** after etching the exposed portions of silicon.

15 **FIG. 75k** is a cross-sectional view of the silicon wafer of **FIG. 75j** after etching the exposed portions of the layers of silicon dioxide.

FIG. 75l is a cross-sectional view of the silicon wafer of **FIG. 75k** after etching the exposed portions of silicon.

20 **FIG. 75m** is a cross-sectional view of the silicon wafer of **FIG. 75l** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 76a is a cross-sectional view of a silicon wafer.

FIG. 76b is a cross-sectional view of the silicon wafer of **FIG. 76a** including a pad layer of silicon dioxide.

25 **FIG. 76c** is a cross-sectional view of the silicon wafer of **FIG. 76b** including a layer of silicon nitride.

FIG. 76d is a cross-sectional view of the silicon wafer of **FIG. 76c** after patterning the layer of silicon nitride.

30 **FIG. 76e** is a cross-sectional view of the silicon wafer of **FIG. 76d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 76f is a cross-sectional view of the silicon wafer of **FIG. 76e** after patterning the layers of silicon dioxide.

FIG. 76g is a cross-sectional view of the silicon wafer of **FIG. 76f** after applying and patterning a layer of photoresist onto the silicon wafer.

5 **FIG. 76h** is a cross-sectional view of the silicon wafer of **FIG. 76g** after etching the exposed portions of the layers of silicon dioxide.

FIG. 76i is a cross-sectional view of the silicon wafer of **FIG. 76h** after etching the exposed portions of silicon.

10 **FIG. 76j** is a cross-sectional view of the silicon wafer of **FIG. 76i** after removing the layer of photoresist.

FIG. 76k is a cross-sectional view of the silicon wafer of **FIG. 76j** after etching the exposed portions of silicon.

FIG. 76l is a cross-sectional view of the silicon wafer of **FIG. 76k** after etching the exposed portions of the layers of silicon dioxide.

15 **FIG. 76m** is a cross-sectional view of the silicon wafer of **FIG. 76l** after etching the exposed portions of silicon.

FIG. 76n is a cross-sectional view of the silicon wafer of **FIG. 76m** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

20 **FIG. 77a** is a cross-sectional view of a silicon wafer.

FIG. 77b is a cross-sectional view of the silicon wafer of **FIG. 77a** including a pad layer of silicon dioxide.

FIG. 77c is a cross-sectional view of the silicon wafer of **FIG. 77b** including a layer of silicon nitride.

25 **FIG. 77d** is a cross-sectional view of the silicon wafer of **FIG. 77c** after patterning the layer of silicon nitride.

FIG. 77e is a cross-sectional view of the silicon wafer of **FIG. 77d** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

30 **FIG. 77f** is a cross-sectional view of the silicon wafer of **FIG. 77e** after patterning the layers of silicon dioxide.

FIG. 77g is a cross-sectional view of the silicon wafer of **FIG. 77f** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 77h is a cross-sectional view of the silicon wafer of **FIG. 77g** after etching the exposed portions of silicon.

5 **FIG. 77i** is a cross-sectional view of the silicon wafer of **FIG. 77h** after removing the layer of photoresist.

FIG. 77j is a cross-sectional view of the silicon wafer of **FIG. 77i** after etching the exposed portions of silicon.

10 **FIG. 77k** is a cross-sectional view of the silicon wafer of **FIG. 77j** after etching the exposed portions of the layers of silicon dioxide.

FIG. 77l is a cross-sectional view of the silicon wafer of **FIG. 77k** after etching the exposed portions of silicon.

15 **FIG. 77m** is a cross-sectional view of the silicon wafer of **FIG. 77l** after removing the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 78a is a cross-sectional view of a silicon wafer.

FIG. 78b is a cross-sectional view of the silicon wafer of **FIG. 78a** including a pad layer of silicon dioxide.

20 **FIG. 78c** is a cross-sectional view of the silicon wafer of **FIG. 78b** including a layer of silicon nitride.

FIG. 78d is a cross-sectional view of the silicon wafer of **FIG. 78c** after patterning the layer of silicon nitride.

FIG. 78e is a cross-sectional view of the silicon wafer of **FIG. 78d** after patterning the pad layer of silicon dioxide.

25 **FIG. 78f** is a cross-sectional view of the silicon wafer of **FIG. 78e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 78g is a cross-sectional view of the silicon wafer of **FIG. 78f** after patterning the layers of silicon dioxide.

30 **FIG. 78h** is a cross-sectional view of the silicon wafer of **FIG. 78g** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 78i is a cross-sectional view of the silicon wafer of **FIG. 78h** after etching the exposed portions of silicon.

FIG. 78j is a cross-sectional view of the silicon wafer of **FIG. 78i** after removing the layer of photoresist.

5 **FIG. 78k** is a cross-sectional view of the silicon wafer of **FIG. 78j** after etching the exposed portions of silicon.

FIG. 78l is a cross-sectional view of the silicon wafer of **FIG. 78k** after etching portions of the exposed portions of the layers of silicon dioxide.

10 **FIG. 78m** is a cross-sectional view of the silicon wafer of **FIG. 78l** after etching the exposed portions of silicon.

FIG. 78n is a cross-sectional view of the silicon wafer of **FIG. 78m** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 79a is a cross-sectional view of a silicon wafer.

15 **FIG. 79b** is a cross-sectional view of the silicon wafer of **FIG. 79a** including a pad layer of silicon dioxide.

FIG. 79c is a cross-sectional view of the silicon wafer of **FIG. 79b** including a layer of silicon nitride.

FIG. 79d is a cross-sectional view of the silicon wafer of **FIG. 79c** after patterning the layer of silicon nitride.

20 **FIG. 79e** is a cross-sectional view of the silicon wafer of **FIG. 79d** after patterning the pad layer of silicon dioxide.

FIG. 79f is a cross-sectional view of the silicon wafer of **FIG. 79e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 79g** is a cross-sectional view of the silicon wafer of **FIG. 79f** after patterning the layers of silicon dioxide.

FIG. 79h is a cross-sectional view of the silicon wafer of **FIG. 79g** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 79i** is a cross-sectional view of the silicon wafer of **FIG. 79h** after etching the exposed portions of silicon.

FIG. 79j is a cross-sectional view of the silicon wafer of **FIG. 79i** after etching the exposed portions of the layers of silicon dioxide.

FIG. 79k is a cross-sectional view of the silicon wafer of **FIG. 79j** after removing the layer of photoresist.

5 **FIG. 79l** is a cross-sectional view of the silicon wafer of **FIG. 79k** after etching the exposed portions of silicon.

FIG. 79m is a cross-sectional view of the silicon wafer of **FIG. 79l** after etching portions of the exposed portions of the layers of silicon dioxide.

10 **FIG. 79n** is a cross-sectional view of the silicon wafer of **FIG. 79m** after etching the exposed portions of silicon.

FIG. 79o is a cross-sectional view of the silicon wafer of **FIG. 79n** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 80a is a cross-sectional view of a silicon wafer.

15 **FIG. 80b** is a cross-sectional view of the silicon wafer of **FIG. 80a** including a pad layer of silicon dioxide.

FIG. 80c is a cross-sectional view of the silicon wafer of **FIG. 80b** including a layer of silicon nitride.

FIG. 80d is a cross-sectional view of the silicon wafer of **FIG. 80c** after patterning the layer of silicon nitride.

20 **FIG. 80e** is a cross-sectional view of the silicon wafer of **FIG. 80d** after patterning the pad layer of silicon dioxide.

FIG. 80f is a cross-sectional view of the silicon wafer of **FIG. 80e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 80g** is a cross-sectional view of the silicon wafer of **FIG. 80f** after patterning the layers of silicon dioxide.

FIG. 80h is a cross-sectional view of the silicon wafer of **FIG. 80g** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 80i** is a cross-sectional view of the silicon wafer of **FIG. 80h** after etching the exposed portions of silicon.

FIG. 80j is a cross-sectional view of the silicon wafer of **FIG. 80i** after etching the exposed portions of silicon.

FIG. 80k is a cross-sectional view of the silicon wafer of **FIG. 80j** after removing the layer of photoresist.

5 **FIG. 80l** is a cross-sectional view of the silicon wafer of **FIG. 80k** after etching the exposed portions of silicon.

FIG. 80m is a cross-sectional view of the silicon wafer of **FIG. 80l** after etching portions of the exposed portions of the layers of silicon dioxide.

10 **FIG. 80n** is a cross-sectional view of the silicon wafer of **FIG. 80m** after etching the exposed portions of silicon.

FIG. 80o is a cross-sectional view of the silicon wafer of **FIG. 80n** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 81a is a cross-sectional view of a silicon wafer.

15 **FIG. 81b** is a cross-sectional view of the silicon wafer of **FIG. 81a** including a pad layer of silicon dioxide.

FIG. 81c is a cross-sectional view of the silicon wafer of **FIG. 81b** including a layer of silicon nitride.

FIG. 81d is a cross-sectional view of the silicon wafer of **FIG. 81c** after patterning the layer of silicon nitride.

20 **FIG. 81e** is a cross-sectional view of the silicon wafer of **FIG. 81d** after patterning the pad layer of silicon dioxide.

FIG. 81f is a cross-sectional view of the silicon wafer of **FIG. 81e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 81g** is a cross-sectional view of the silicon wafer of **FIG. 81f** after patterning the layers of silicon dioxide.

FIG. 81h is a cross-sectional view of the silicon wafer of **FIG. 81g** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 81i** is a cross-sectional view of the silicon wafer of **FIG. 81h** after etching the exposed portions of silicon.

FIG. 81j is a cross-sectional view of the silicon wafer of **FIG. 81i** after etching the exposed portions of the layers of silicon dioxide.

FIG. 81k is a cross-sectional view of the silicon wafer of **FIG. 81j** after etching the exposed portions of silicon.

5 **FIG. 81l** is a cross-sectional view of the silicon wafer of **FIG. 81k** after removing the layer of photoresist.

FIG. 81m is a cross-sectional view of the silicon wafer of **FIG. 81l** after etching the exposed portions of silicon.

10 **FIG. 81n** is a cross-sectional view of the silicon wafer of **FIG. 81m** after etching portions of the exposed portions of the layers of silicon dioxide.

FIG. 81o is a cross-sectional view of the silicon wafer of **FIG. 81n** after etching the exposed portions of silicon.

FIG. 81p is a cross-sectional view of the silicon wafer of **FIG. 81o** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

15 **FIG. 82a** is a cross-sectional view of a silicon wafer.

FIG. 82b is a cross-sectional view of the silicon wafer of **FIG. 82a** including a pad layer of silicon dioxide.

FIG. 82c is a cross-sectional view of the silicon wafer of **FIG. 82b** including a layer of silicon nitride.

20 **FIG. 82d** is a cross-sectional view of the silicon wafer of **FIG. 82c** after patterning the layer of silicon nitride.

FIG. 82e is a cross-sectional view of the silicon wafer of **FIG. 82d** after patterning the pad layer of silicon dioxide.

25 **FIG. 82f** is a cross-sectional view of the silicon wafer of **FIG. 82e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 82g is a cross-sectional view of the silicon wafer of **FIG. 82f** after patterning the layers of silicon dioxide.

30 **FIG. 82h** is a cross-sectional view of the silicon wafer of **FIG. 82g** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 82i is a cross-sectional view of the silicon wafer of **FIG. 82h** after etching the exposed portions of the layers of silicon dioxide.

FIG. 82j is a cross-sectional view of the silicon wafer of **FIG. 82i** after removing the layer of photoresist.

5 **FIG. 82k** is a cross-sectional view of the silicon wafer of **FIG. 82j** after etching the exposed portions of silicon.

FIG. 82l is a cross-sectional view of the silicon wafer of **FIG. 82k** after etching portions of the exposed portions of the layers of silicon dioxide.

10 **FIG. 82m** is a cross-sectional view of the silicon wafer of **FIG. 82l** after etching the exposed portions of silicon.

FIG. 82n is a cross-sectional view of the silicon wafer of **FIG. 82m** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 83a is a cross-sectional view of a silicon wafer.

15 **FIG. 83b** is a cross-sectional view of the silicon wafer of **FIG. 83a** including a pad layer of silicon dioxide.

FIG. 83c is a cross-sectional view of the silicon wafer of **FIG. 83b** including a layer of silicon nitride.

FIG. 83d is a cross-sectional view of the silicon wafer of **FIG. 83c** after patterning the layer of silicon nitride.

20 **FIG. 83e** is a cross-sectional view of the silicon wafer of **FIG. 83d** after patterning the pad layer of silicon dioxide.

FIG. 83f is a cross-sectional view of the silicon wafer of **FIG. 83e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 83g** is a cross-sectional view of the silicon wafer of **FIG. 83f** after patterning the layers of silicon dioxide.

FIG. 83h is a cross-sectional view of the silicon wafer of **FIG. 83g** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 83i** is a cross-sectional view of the silicon wafer of **FIG. 83h** after etching the exposed portions of the layers of silicon dioxide.

FIG. 83j is a cross-sectional view of the silicon wafer of **FIG. 83i** after etching the exposed portions of silicon.

FIG. 83k is a cross-sectional view of the silicon wafer of **FIG. 83j** after removing the layer of photoresist.

5 **FIG. 83l** is a cross-sectional view of the silicon wafer of **FIG. 83k** after etching the exposed portions of silicon.

FIG. 83m is a cross-sectional view of the silicon wafer of **FIG. 83l** after etching portions of the exposed portions of the layers of silicon dioxide.

10 **FIG. 83n** is a cross-sectional view of the silicon wafer of **FIG. 83m** after etching the exposed portions of silicon.

FIG. 83o is a cross-sectional view of the silicon wafer of **FIG. 83n** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 84a is a cross-sectional view of a silicon wafer.

15 **FIG. 84b** is a cross-sectional view of the silicon wafer of **FIG. 84a** including a pad layer of silicon dioxide.

FIG. 84c is a cross-sectional view of the silicon wafer of **FIG. 84b** including a layer of silicon nitride.

FIG. 84d is a cross-sectional view of the silicon wafer of **FIG. 84c** after patterning the layer of silicon nitride.

20 **FIG. 84e** is a cross-sectional view of the silicon wafer of **FIG. 84d** after patterning the pad layer of silicon dioxide.

FIG. 84f is a cross-sectional view of the silicon wafer of **FIG. 84e** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 84g** is a cross-sectional view of the silicon wafer of **FIG. 84f** after patterning the layers of silicon dioxide.

FIG. 84h is a cross-sectional view of the silicon wafer of **FIG. 84g** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 84i** is a cross-sectional view of the silicon wafer of **FIG. 84h** after etching the exposed portions of silicon.

FIG. 84j is a cross-sectional view of the silicon wafer of **FIG. 84i** removing the layer of photoresist.

FIG. 84k is a cross-sectional view of the silicon wafer of **FIG. 84j** after etching the exposed portions of silicon.

5 **FIG. 84l** is a cross-sectional view of the silicon wafer of **FIG. 84k** after etching portions of the exposed portions of the layers of silicon dioxide.

FIG. 84m is a cross-sectional view of the silicon wafer of **FIG. 84l** after etching the exposed portions of silicon.

10 **FIG. 84n** is a cross-sectional view of the silicon wafer of **FIG. 84m** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 85a is a cross-sectional view of a silicon wafer.

FIG. 85b is a cross-sectional view of the silicon wafer of **FIG. 85a** including a pad layer of silicon dioxide.

15 **FIG. 85c** is a cross-sectional view of the silicon wafer of **FIG. 85b** including a layer of silicon nitride.

FIG. 85d is a cross-sectional view of the silicon wafer of **FIG. 85c** after patterning the layer of silicon nitride.

FIG. 85e is a cross-sectional view of the silicon wafer of **FIG. 85d** after patterning the pad layer of silicon dioxide.

20 **FIG. 85f** is a cross-sectional view of the silicon wafer of **FIG. 85e** after a thin etch of the exposed areas of silicon.

FIG. 85g is a cross-sectional view of the silicon wafer of **FIG. 85f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 85h** is a cross-sectional view of the silicon wafer of **FIG. 85g** after patterning the layers of silicon dioxide.

FIG. 85i is a cross-sectional view of the silicon wafer of **FIG. 85h** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 85j** is a cross-sectional view of the silicon wafer of **FIG. 85i** after etching the exposed portions of silicon.

FIG. 85k is a cross-sectional view of the silicon wafer of **FIG. 85j** after removing the layer of photoresist.

FIG. 85l is a cross-sectional view of the silicon wafer of **FIG. 85k** after etching the exposed portions of silicon.

5 **FIG. 85m** is a cross-sectional view of the silicon wafer of **FIG. 85l** after etching the exposed portions of the layers of silicon dioxide.

FIG. 85n is a cross-sectional view of the silicon wafer of **FIG. 85m** after etching the exposed portions of silicon.

10 **FIG. 85o** is a cross-sectional view of the silicon wafer of **FIG. 85n** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 86a is a cross-sectional view of a silicon wafer.

FIG. 86b is a cross-sectional view of the silicon wafer of **FIG. 86a** including a pad layer of silicon dioxide.

15 **FIG. 86c** is a cross-sectional view of the silicon wafer of **FIG. 86b** including a layer of silicon nitride.

FIG. 86d is a cross-sectional view of the silicon wafer of **FIG. 86c** after patterning the layer of silicon nitride.

FIG. 86e is a cross-sectional view of the silicon wafer of **FIG. 86d** after patterning the pad layer of silicon dioxide.

20 **FIG. 86f** is a cross-sectional view of the silicon wafer of **FIG. 86e** after a thin etch of the exposed areas of silicon.

FIG. 86g is a cross-sectional view of the silicon wafer of **FIG. 86f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

25 **FIG. 86h** is a cross-sectional view of the silicon wafer of **FIG. 86g** after patterning the layers of silicon dioxide.

FIG. 86i is a cross-sectional view of the silicon wafer of **FIG. 86h** after applying and patterning a layer of photoresist onto the silicon wafer.

30 **FIG. 86j** is a cross-sectional view of the silicon wafer of **FIG. 86i** after etching the exposed portions of silicon.

FIG. 86k is a cross-sectional view of the silicon wafer of **FIG. 86j** after etching the exposed portions of the layers of silicon dioxide.

FIG. 86l is a cross-sectional view of the silicon wafer of **FIG. 86k** after removing the layer of photoresist.

5 **FIG. 86m** is a cross-sectional view of the silicon wafer of **FIG. 86l** after etching the exposed portions of silicon.

FIG. 86n is a cross-sectional view of the silicon wafer of **FIG. 86m** after etching the exposed portions of the layers of silicon dioxide.

10 **FIG. 86o** is a cross-sectional view of the silicon wafer of **FIG. 86n** after etching the exposed portions of silicon.

FIG. 86p is a cross-sectional view of the silicon wafer of **FIG. 86o** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 87a is a cross-sectional view of a silicon wafer.

15 **FIG. 87b** is a cross-sectional view of the silicon wafer of **FIG. 87a** including a pad layer of silicon dioxide.

FIG. 87c is a cross-sectional view of the silicon wafer of **FIG. 87b** including a layer of silicon nitride.

FIG. 87d is a cross-sectional view of the silicon wafer of **FIG. 87c** after patterning the layer of silicon nitride.

20 **FIG. 87e** is a cross-sectional view of the silicon wafer of **FIG. 87d** after patterning the pad layer of silicon dioxide.

FIG. 87f is a cross-sectional view of the silicon wafer of **FIG. 87e** after a thin etch of the exposed areas of silicon.

25 **FIG. 87g** is a cross-sectional view of the silicon wafer of **FIG. 87f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 87h is a cross-sectional view of the silicon wafer of **FIG. 87g** after patterning the layers of silicon dioxide.

30 **FIG. 87i** is a cross-sectional view of the silicon wafer of **FIG. 87h** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 87j is a cross-sectional view of the silicon wafer of **FIG. 87i** after etching the exposed portions of silicon.

FIG. 87k is a cross-sectional view of the silicon wafer of **FIG. 87j** after etching the exposed portions of silicon.

5 **FIG. 87l** is a cross-sectional view of the silicon wafer of **FIG. 87k** after removing the layer of photoresist.

FIG. 87m is a cross-sectional view of the silicon wafer of **FIG. 87l** after etching the exposed portions of silicon.

10 **FIG. 87n** is a cross-sectional view of the silicon wafer of **FIG. 87m** after etching the exposed portions of the layers of silicon dioxide.

FIG. 87o is a cross-sectional view of the silicon wafer of **FIG. 87n** after etching the exposed portions of silicon.

FIG. 87p is a cross-sectional view of the silicon wafer of **FIG. 87o** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

15 **FIG. 88a** is a cross-sectional view of a silicon wafer.

FIG. 88b is a cross-sectional view of the silicon wafer of **FIG. 88a** including a pad layer of silicon dioxide.

FIG. 88c is a cross-sectional view of the silicon wafer of **FIG. 88b** including a layer of silicon nitride.

20 **FIG. 88d** is a cross-sectional view of the silicon wafer of **FIG. 88c** after patterning the layer of silicon nitride.

FIG. 88e is a cross-sectional view of the silicon wafer of **FIG. 88d** after patterning the pad layer of silicon dioxide.

25 **FIG. 88f** is a cross-sectional view of the silicon wafer of **FIG. 88e** after a thin etch of the exposed areas of silicon.

FIG. 88g is a cross-sectional view of the silicon wafer of **FIG. 88f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

30 **FIG. 88h** is a cross-sectional view of the silicon wafer of **FIG. 88g** after patterning the layers of silicon dioxide.

FIG. 88i is a cross-sectional view of the silicon wafer of **FIG. 88h** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 88j is a cross-sectional view of the silicon wafer of **FIG. 88i** after etching the exposed portions of silicon.

5 **FIG. 88k** is a cross-sectional view of the silicon wafer of **FIG. 88j** after etching the exposed portions of the layers of silicon dioxide.

FIG. 88l is a cross-sectional view of the silicon wafer of **FIG. 88k** after etching the exposed portions of silicon.

10 **FIG. 88m** is a cross-sectional view of the silicon wafer of **FIG. 88l** after removing the layer of photoresist.

FIG. 88n is a cross-sectional view of the silicon wafer of **FIG. 88m** after etching the exposed portions of silicon.

FIG. 88o is a cross-sectional view of the silicon wafer of **FIG. 88n** after etching the exposed portions of the layers of silicon dioxide.

15 **FIG. 88p** is a cross-sectional view of the silicon wafer of **FIG. 88o** after etching the exposed portions of silicon.

FIG. 88q is a cross-sectional view of the silicon wafer of **FIG. 88p** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 89a is a cross-sectional view of a silicon wafer.

20 **FIG. 89b** is a cross-sectional view of the silicon wafer of **FIG. 89a** including a pad layer of silicon dioxide.

FIG. 89c is a cross-sectional view of the silicon wafer of **FIG. 89b** including a layer of silicon nitride.

25 **FIG. 89d** is a cross-sectional view of the silicon wafer of **FIG. 89c** after patterning the layer of silicon nitride.

FIG. 89e is a cross-sectional view of the silicon wafer of **FIG. 89d** after patterning the pad layer of silicon dioxide.

FIG. 89f is a cross-sectional view of the silicon wafer of **FIG. 89e** after a thin etch of the exposed areas of silicon.

FIG. 89g is a cross-sectional view of the silicon wafer of **FIG. 89f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

5 **FIG. 89h** is a cross-sectional view of the silicon wafer of **FIG. 89g** after patterning the layers of silicon dioxide.

FIG. 89i is a cross-sectional view of the silicon wafer of **FIG. 89h** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 89j is a cross-sectional view of the silicon wafer of **FIG. 89i** after etching the exposed portions of the layers of silicon dioxide.

10 **FIG. 89k** is a cross-sectional view of the silicon wafer of **FIG. 89j** after removing the layer of photoresist.

FIG. 89l is a cross-sectional view of the silicon wafer of **FIG. 89k** after etching the exposed portions of silicon.

15 **FIG. 89m** is a cross-sectional view of the silicon wafer of **FIG. 89l** after etching the exposed portions of the layers of silicon dioxide.

FIG. 89n is a cross-sectional view of the silicon wafer of **FIG. 89m** after etching the exposed portions of silicon.

FIG. 89o is a cross-sectional view of the silicon wafer of **FIG. 89n** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

20 **FIG. 90a** is a cross-sectional view of a silicon wafer.

FIG. 90b is a cross-sectional view of the silicon wafer of **FIG. 90a** including a pad layer of silicon dioxide.

FIG. 90c is a cross-sectional view of the silicon wafer of **FIG. 90b** including a layer of silicon nitride.

25 **FIG. 90d** is a cross-sectional view of the silicon wafer of **FIG. 90c** after patterning the layer of silicon nitride.

FIG. 90e is a cross-sectional view of the silicon wafer of **FIG. 90d** after patterning the pad layer of silicon dioxide.

30 **FIG. 90f** is a cross-sectional view of the silicon wafer of **FIG. 90e** after a thin etch of the exposed areas of silicon.

FIG. 90g is a cross-sectional view of the silicon wafer of **FIG. 90f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

5 **FIG. 90h** is a cross-sectional view of the silicon wafer of **FIG. 90g** after patterning the layers of silicon dioxide.

FIG. 90i is a cross-sectional view of the silicon wafer of **FIG. 90h** after applying and patterning a layer of photoresist onto the silicon wafer.

FIG. 90j is a cross-sectional view of the silicon wafer of **FIG. 90i** after etching the exposed portions of the layers of silicon dioxide.

10 **FIG. 90k** is a cross-sectional view of the silicon wafer of **FIG. 90j** after etching the exposed portions of silicon.

FIG. 90l is a cross-sectional view of the silicon wafer of **FIG. 90k** after removing the layer of photoresist.

15 **FIG. 90m** is a cross-sectional view of the silicon wafer of **FIG. 90l** after etching the exposed portions of silicon.

FIG. 90n is a cross-sectional view of the silicon wafer of **FIG. 90m** after etching the exposed portions of the layers of silicon dioxide.

FIG. 90o is a cross-sectional view of the silicon wafer of **FIG. 90n** after etching the exposed portions of silicon.

20 **FIG. 90p** is a cross-sectional view of the silicon wafer of **FIG. 90o** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIG. 91a is a cross-sectional view of a silicon wafer.

FIG. 91b is a cross-sectional view of the silicon wafer of **FIG. 91a** including a pad layer of silicon dioxide.

25 **FIG. 91c** is a cross-sectional view of the silicon wafer of **FIG. 91b** including a layer of silicon nitride.

FIG. 91d is a cross-sectional view of the silicon wafer of **FIG. 91c** after patterning the layer of silicon nitride.

30 **FIG. 91e** is a cross-sectional view of the silicon wafer of **FIG. 91d** after patterning the pad layer of silicon dioxide.

FIG. 91f is a cross-sectional view of the silicon wafer of **FIG. 91e** after a thin etch of the exposed areas of silicon.

5 **FIG. 91g** is a cross-sectional view of the silicon wafer of **FIG. 91f** after growing a field layer of oxide on the portions not covered by the patterned layer of silicon nitride.

FIG. 91h is a cross-sectional view of the silicon wafer of **FIG. 91g** after patterning the layers of silicon dioxide.

FIG. 91i is a cross-sectional view of the silicon wafer of **FIG. 91h** after applying and patterning a layer of photoresist onto the silicon wafer.

10 **FIG. 91j** is a cross-sectional view of the silicon wafer of **FIG. 91i** after etching the exposed portions of silicon.

FIG. 91k is a cross-sectional view of the silicon wafer of **FIG. 91j** after removing the layer of photoresist.

15 **FIG. 91l** is a cross-sectional view of the silicon wafer of **FIG. 91k** after etching the exposed portions of silicon.

FIG. 91m is a cross-sectional view of the silicon wafer of **FIG. 91l** after etching the exposed portions of the layers of silicon dioxide.

FIG. 91n is a cross-sectional view of the silicon wafer of **FIG. 91m** after etching the exposed portions of silicon.

20 **FIG. 91o** is a cross-sectional view of the silicon wafer of **FIG. 91n** after etching the remaining portions of the layers of silicon dioxide and silicon nitride.

FIGS. 92a and **92b** are a flow chart illustrating several embodiments of LOCOS merged-mask micromachining processes including multiple etch depths and using photoresist as a mask for deep reactive ion etching of silicon.

25 **FIGS. 93a** and **93b** are a flow chart illustrating several embodiments of merged-mask micromachining processes including multiple etch depths and using photoresist as a mask for deep reactive ion etching of silicon.

FIG. 94 is a flow chart illustrating an embodiment of a merged-mask micromachining process for etching multiple etch depths.

30 **FIG. 95a** is a cross-sectional illustration of a silicon wafer.

FIG. 95b is a cross-sectional illustration of the silicon wafer of **FIG. 95a** including a layer of a first masking material.

FIG. 95c is a cross-sectional illustration of the silicon wafer of **FIG. 95b** after patterning the layer of the first masking material.

5 **FIG. 95d** is a cross-sectional illustration of the silicon wafer of **FIG. 95c** including a layer of a second masking material.

FIG. 95e is a cross-sectional illustration of the silicon wafer of **FIG. 95d** after patterning the layer of the second masking material.

10 **FIG. 95f** is a cross-sectional illustration of the silicon wafer of **FIG. 95e** after etching the exposed portions of the silicon wafer.

FIG. 95g is a cross-sectional illustration of the silicon wafer of **FIG. 95f** after etching the exposed portions of the layer of the first masking material.

FIG. 95h is a cross-sectional illustration of the silicon wafer of **FIG. 95g** after etching the exposed portions of the silicon wafer.

15 **FIG. 96** is a flow chart illustrating an embodiment of a merged-mask micromachining process for etching different sized exposed areas to the same etch depth.

FIG. 97a is a cross-sectional illustration of a silicon wafer.

20 **FIG. 97b** is a cross-sectional illustration of the silicon wafer of **FIG. 97a** including a layer of a first masking material.

FIG. 97c is a cross-sectional illustration of the silicon wafer of **FIG. 97b** after patterning the layer of the first masking material.

FIG. 97d is a cross-sectional illustration of the silicon wafer of **FIG. 97c** including a layer of a second masking material.

25 **FIG. 97e** is a cross-sectional illustration of the silicon wafer of **FIG. 97d** after patterning the layer of the second masking material.

FIG. 97f is a cross-sectional illustration of the silicon wafer of **FIG. 97e** after etching the exposed portions of the silicon wafer.

30 **FIG. 97g** is a cross-sectional illustration of the silicon wafer of **FIG. 97f** after etching the exposed portions of the layer of the first masking material.

FIG. 97h is a cross-sectional illustration of the silicon wafer of **FIG. 97g** after etching the exposed portions of the silicon wafer.

Detailed Description of the Preferred Embodiments

5 A merged-mask micro-machining process for forming a micro-machined structure is provided. The merged-mask micro-machining process is preferably used to fabricate a mirror assembly for use in a bar code reader. The mirror assembly preferably includes a micro-machined three dimensional mirror having a "T" shaped hinge. The mirror assembly further preferably includes one or more travel stops for limiting the movement of the mirror. The mirror assembly
10 further preferably includes one or more tapered edge surfaces and cut-outs for minimizing clipping of incident and reflected laser beams.

FIG. 1 is a cross section view of a laser scanning device such as a bar code scanner **100** having a light beam **115** that emanates from the device to strike a target **120**. The light beam is reflected or scattered by the target **120**.
15 The bar code scanner **100** includes a laser beam source **105** and a mirror assembly **110**. During the operation of the bar code scanner **100**, the optically reflective portion **111** of the mirror assembly **110** is preferably oscillated to permit the laser beam **115** to scan a surface, such as a bar code symbol **120**, by reflecting the laser beam **115** off of the optically reflective portion **111** of the
20 mirror assembly **110**. The reflected light **125** enters the bar code scanner **100** through a window **165** and is detected by a light detector **160**. The laser beam source **105** may comprise any number of conventional commercially available devices to generate the laser beam **115**.

The bar code scanner **100** may include additional features for user
25 interface, control and data processing. These features may comprise a processor **130** and memory device **135** as part of a central processing unit **140**, a controller **145** for generating voltage used to oscillate the mirror **110**, a data entry device such as a keypad **150** and a data display device such as a liquid crystal display **155**. The mirror assembly **110** made according to the present
30 invention is described below in reference to **FIGS. 2-19**.

Referring to **FIG. 2**, in a preferred embodiment, the mirror assembly **110** includes a top cap **205**, a mirror **210**, a bottom cap **215**, and a base member **220**. The top cap **205** includes an opening that permits the laser beam **115** to reflect off of the mirror **210**. In this manner, the mirror **210** is surrounded and
5 protected by the top cap **205** and the bottom cap **215**. The sub-assembly that includes the top cap **205**, mirror **210** and bottom cap **215** is formed and then mounted onto the base member **220**.

The top cap **205** and bottom cap **215** may be fabricated from any number of conventional commercially available materials such as, for example, silicon
10 glass, ceramic or plastic. In a preferred embodiment, the top cap **205** is fabricated by micro-machining a silicon wafer.

FIGS. 3-5 show various views of a preferred embodiment of the top cap **205** which has a frame **301** that includes a top, bottom, left and right support members **305**, **315**, **325** and **335**. Top and bottom travel stop members **310** and
15 **320** are coupled respectively to the top and bottom support members **305** and **315**. The left and right support members **325** and **335** include corresponding left and right rim cutouts **330** and **340** for minimizing clipping of the incident light.

The top cap frame **301** provides an overall support structure for the top cap **205**. The thickness of the frame **301** may range, for example, from about
20 400 to 600 microns with a preferred thickness ranging from about 390 to 400 microns in order to provide a compact structure having a low mass.

The top travel stop **310** preferably limits the motion of the reflective portion of the mirror **210** in the direction normal to the plane of the reflective portion of the mirror **210** (the Z-direction). The top travel stop **310** preferably
25 extends in substantially orthogonal direction from the top support member **305**. In a preferred embodiment, the top travel stop **310** is positioned within the plane of the top support member **305**. The thickness of the top travel stop **310** may range, for example, from about 340 to 580 microns. In a preferred embodiment, the thickness of the top travel stop **310** ranges from about 350 to 380 microns
30 in order to provide optimum shock protection, freedom of motion, and a compact structure having a low mass.

Referring to **FIG. 4**, in a particularly preferred embodiment, the bottom surface **310b** of the top travel stop **310** is recessed below the level of the bottom surface **305b** of the top support member **305**. In this manner, the bottom surface **310b** of the top travel stop **310** is preferably positioned above the level of the reflective surface of the mirror **210**. The length of the top travel stop member **310** may range, for example, from about 800 to 2800 microns. In a preferred embodiment, the length of the top travel stop member **310** ranges from about 2000 to 2500 microns. In a particularly preferred embodiment, the length of the top travel stop member **310** is selected to overlap with the mirror collection plate **610** of the mirror by about 300 microns.

The bottom travel stop **320** extends in a substantially orthogonal direction from the bottom support member **315** and is substantially identical to the top travel stop **310**. An opening **345** permits light to reflect off of the reflective surface of the mirror **210**. The opening **345** preferably includes a left rim cut out **330** and a right rim cut out **340**. The left and right rim cut outs, **330** and **340**, are preferably positioned on opposite sides in surrounding relation to the reflective surface of the mirror **210**. In this manner, the left and right rim cut-outs, **330** and **340**, provide optical access to the reflective surface of the mirror **210**.

In a preferred embodiment, the top cap frame **301**, travel stops **310** and **320**, rim cut outs **330** and **340**, and the opening **345** all include tapered edges, **350A** and **350B**, to facilitate optical access to the reflective surface of the mirror **210** (**FIG. 5**). The taper angle of the tapered edges, **350A** and **350B**, preferably ranges from about 50 to 60 degrees in order to optimally facilitate the reflection of laser light transmitted at an angle towards the edge portions of the reflective surface of the mirror **210**.

FIG. 6 shows a top view of a mirror or mirror assembly **210** made in according to one embodiment of the present invention. The mirror **210** includes a frame or mirror support structure **600** having support members **602**, **604**, **606** and **608**. The mirror **210** further comprises a mirror collection plate **610** with a reflective surface **628**, a top T-shaped hinge **612**, a bottom T-shaped hinge **614**, a top left travel stop finger **616**, a top right travel stop finger **618**, a bottom left

travel stop finger **620**, a bottom right travel stop finger **622**, an opening **624**, a conductive layer **626**, and a reflective surface **628**.

5 The mirror frame **600** provides the overall support structure for the mirror **210**. The thickness of the frame **600** may range, for example, from about 400 to 600 microns with a preferred thickness ranging from about 400 to 450 microns in order to provide a compact structure having a low mass. In a preferred embodiment, the support members **602**, **604**, **606**, and **608** provide effective beam lengths ranging from about 500-2500 microns and cross sections of about 8,000 microns² to 160,000 microns² in order to optimally absorb shock loads of about 2000g/0.5 mS half sine wave input.

10 The mirror collection plate **610** is coupled to the top T-shaped hinge **612** and the bottom T-shaped hinge **614**. In this manner, the mirror collection plate **610** rotates about the axis **630** i.e. has torsional movement about such axis. In a preferred embodiment, the axis **630** is positioned substantially along the centerline of the mirror collection plate **610** and is coincident with the center of the T-shaped hinges, **612** and **614**, thereby providing a common axis of rotation for the springs. The reflective surface **628** is coupled to the top **632** of the mirror collection plate **610**. In this manner, rotation of the mirror collection plate **610** about the axis **630** causes laser light from a stationary laser to reflect off of the reflective surface **628** in a plurality of directions.

20 The thickness of the mirror collection plate **610** may range, for example, from about 100 to 600 microns with a preferred thickness ranging from about 100 to 250 microns to provide a low mass and maximize the effective natural frequency of the mirror **210**.

25 The reflective surface **628** may be comprised of any number of conventional commercially available optically reflective surfaces such as, for example, gold, silver or aluminum. In a preferred embodiment, the reflective surface **628** comprises gold in order to optimize the amount of optical energy that is reflected. In a preferred embodiment, the surface roughness of the reflective surface **628** is less than about 0.1 wavelengths of the reflected light in order to optimize the amount of optical energy that is reflected.

30

The **FIGS. 7 and 8** show cross-sectional views of the mirror of **FIG. 6** and **FIG. 9** shows a bottom view of the mirror of **FIG. 6**. As illustrated in **FIGS. 7-9**, in a preferred embodiment, the bottom **634** of the mirror collection plate **610** includes a top travel stop **710**, a bottom travel stop **715**, and a cavity **720**. The top travel stop **710** extends from the bottom **634** of the mirror collection plate **610**. The top travel stop **710** preferably limits movement of the mirror collection plate **610** in the z-direction. The top travel stop **710** preferably extends from the bottom **634** of the mirror collection plate **610** in a substantially orthogonal direction. The top travel stop **710** may extend from the bottom **634** of the mirror collection plate **610** for a distance ranging, for example, from about 200 to 400 microns with a preferred distance ranging from about 200 to 250 microns to optimally limit movement of the mirror collection plate **610**. In a preferred embodiment, the top travel stop **710** is centered about the axis **630** and is positioned adjacent to and on one side of the cavity **720**. The bottom travel stop **715** is preferably identical to the top travel stop **710** described above.

The cavity **720** extends into the bottom of the mirror collection plate **610**, which reduces the mass of the mirror collection plate **610**. In this manner, the droop of the mirror **210** is reduced. In a preferred embodiment, the depth and volume of the cavity **720** ranges from about 200 to 500 microns and 8×10^6 to 1×10^9 microns.³ In a preferred embodiment, the cavity **720** is centrally positioned along the axis **630** and within the back side **634** of the mirror collection plate **610**.

For typical bar code scanner applications, the rotational accuracy of the laser beam may be required to be within 1.3 when the mirror collection plate **610** is subjected to an across-the-hinge self-induced gravity torque. Where torque $T = mg \cdot h/2$, with mg = mirror collection plate weight and h = mirror collection plate thickness. The mirror accuracy is a function of the pointing accuracy and mirror droop. The torsional spring constant K_r of the T-shaped hinges, **612** and **614**, is determined by the resonant frequency F of the mirror collection plate **610** and the size and mass of the mirror collection plate **610**. The mirror tilt angle θ due to a gravity torque is determined by the relation,

$\theta=T/K_r$. Consequently, the thickness and mass of the mirror collection plate **610**, are preferably selected to provide a mirror tilt angle less than 1.3° . In a preferred embodiment, the thickness and mass of the mirror collection plate **610** are reduced by reducing the thickness of the mirror collection plate **610** and by providing one or more cavities in the mirror collection plate **610**.

The top T-shaped hinge **612** is coupled to the left support member **606**, the right support member **608**, and the top portion of the mirror collection plate **610**. The top T-shaped hinge **612** preferably includes a vertical support member **644** (beam or leg) and a second or horizontal support member **646** (T-member). The horizontal support member **646** preferably is supported at opposite ends by the left support member **606** and the right support member **608**. In a preferred embodiment, the horizontal support member **646** is substantially orthogonal to both the left support member **606** and the right support member **608**. The vertical support member **644** is coupled to the horizontal support member **646**. In a preferred embodiment, the vertical support member **644** is substantially orthogonal to the horizontal support member **646**. The vertical support member **644** is coupled to the mid-point of the horizontal support member **646**. The vertical support member **644** is positioned along the axis **630**. The length, width and thickness of the vertical support member **644** may range, for example, from about 100 to 2500 microns, 2 to 100 microns and 2 to 100 microns, respectively. In a preferred embodiment, the length, width and thickness of the vertical support member **644** range from about 800 to 1000 microns, 8 to 15 microns and 8 to 15 microns, respectively. The torsional spring constant of the vertical support member **644** may range, for example, from about 2×10^{-9} to 10×10^{-7} lbf-ft/radian. In a preferred embodiment, the torsional spring constant of the vertical support member **644** ranges from about 2×10^{-8} to 10×10^{-8} lbf-ft/radian. The length, width and thickness of the horizontal support member **646** may range, for example, from about 500 to 4500 microns, 6 to 100 microns and 6 to 100 microns, respectively. In a preferred embodiment, the length, width and thickness of the

horizontal support member **646** range from about 2200 to 2500 microns, 15 to 25 microns and 15 to 25 microns, respectively.

5 The bottom T-shaped hinge **614** is coupled to the left support member **606**, the right support member **608**, and the bottom portion of the mirror collection plate **610**. The bottom T-shaped hinge **614** has the same structure as the top T-shaped hinge **612**.

10 Other embodiments of a T-shaped hinge according to the present invention, as illustrated in **FIGS. 6A-6C**, provide enhanced sensitivity for sensing acceleration loading conditions. In **FIG. 6A**, a T-shaped hinge **612A** includes a vertical support member **644A** having a serpentine shape and a horizontal support member **646A** having a substantially linear shape. In **FIG. 6B**, an alternative embodiment of a T-shaped hinge **612B** includes a vertical support member **644B** coupled to a horizontal support member **646B** at location that is off-center. In **FIG. 6C**, one or both of the T-shaped hinges **612** and **614**
15 are modified to include a T-shaped hinge **612C** having a vertical support member **644C** that intersects a horizontal support member **646C** at an acute angle and is also coupled to the horizontal support member **646C** at location that is off-center.

20 The top left travel stop **616** extends from and is coupled to the top left portion of the mirror collection plate **610**. The top left travel stop **616** preferably limits the motion of the mirror collection plate **610** in the x-direction. The top left travel stop **616** preferably is positioned in the plane of the mirror collection plate **610**. In a preferred embodiment, the top left travel stop **616** extends from the mirror collection plate **610** in a substantially orthogonal direction. The thickness
25 of the top left travel stop **616** may range, for example, from about 200 to 600 microns. In a preferred embodiment, the thickness of the top left travel stop **616** ranges from about 250 to 350 microns in order to optimally provide shock protection, and a resilient compact structure having a low mass. The length of the top left travel stop **616** may range, for example, from about 500 to 2000
30 microns. In a preferred embodiment, the length of the top left travel stop **616** ranges from about 900 to 1100 microns. In a particularly preferred

embodiment, the top surface of the top left travel stop **616** is planar with the top surface of the mirror collection plate **610**. In a particularly preferred embodiment, the bottom surface of the top left travel stop **616** is planar with the bottom surface of the mirror collection plate **610**.

5 The top right and bottom left and right travel stops **618**, **620** and **622** are substantially identical to the top left travel stop **616**. These travel stops are positioned in corresponding locations about the mirror collection plate **610**.

10 The travel stops, **616**, **618**, **620** and **622**, preferably provide overswing and x-axis shock protection for the mirror collection plate **610** during manufacturing and operation. In a preferred embodiment, the travel stops **616**, **618**, **620**, and **622** are formed as integral parts of the mirror collection plate **610**. In a preferred embodiment, the travel stops **616**, **618**, **620**, and **622** provide effective beam lengths greater than about 500 microns and cross sections of about 40,000 microns² to 240,000 microns² in order to optimally absorb shock loads of about 2000g/0.5 mS half sine wave input.

15 The opening **624** preferably permits the mirror collection plate **610** to rotate about the axis **630**. The walls **636** of the opening **624** preferably limit movement of the mirror collection plate **610** in the x-direction and the y-directions. The opening **624** preferably includes a top section **638**, a middle section **640**, and a bottom section **642**. The top section **638** of the opening **624** preferably contains the top T-shaped hinge **612** and the top left and right travel stops, **616** and **618**. The middle section **640** of the opening **624** preferably contains the mirror collection plate **610**. The bottom section **642** of the opening **624** preferably contains the bottom T-shaped hinge **614** and the bottom left and right travel stops, **620** and **622**.

20 The walls of the middle section **640** of the opening **624** may be spaced apart from the opposing edges of the mirror collection plate **610** by a distance ranging, for example, from about 30 to 150 microns. In a preferred embodiment, the walls of the middle section **640** of the opening **624** are spaced apart from the opposing edges of the mirror collection plate **610** by a distance ranging from about 60 to 100 microns in order to optimally minimize movement

30

of the mirror collection plate **610** in the x and y directions. In a preferred embodiment, the gap in the x-direction is different from the gap in the y-direction in order to optimally protect the mirror collection plate **610** from shocks. In a preferred embodiment, the gap between the mirror collection plate **610** and the middle section **640** of the opening **624** provides a spacing in the y-direction ranging from about 15 to 45 microns and a spacing in the x-direction ranging from about 50 to 180 microns in order to optimally limit shock loads on the mirror collection plate **610**.

The conductive layer **626** is preferably coupled to the outer periphery of the top surface of the mirror **210**. The conductive surface **626** preferably provides a conductive electrical path. The conductive layer **626** may be fabricated from any number of conventional commercially available materials such as, for example, gold, aluminum, or silver. In a preferred embodiment, the conductive layer **626** is fabricated from gold. In a preferred embodiment, the conductive layer **626** is bonded to the underlying substrate by an intermediate layer of titanium.

The mirror **210** may be fabricated from any number of conventional commercially available materials such as, for example, silicon, plated metal or plastic. In a preferred embodiment, the mirror **210** is fabricated by micro-machining a silicon wafer using any one, or combination, of the embodiments for micro-machining disclosed in the present disclosure.

In a preferred embodiment, the released and free-standing mirror collection plate **610** is connected to the surrounding support frame, **600** by the T-shaped hinges, **612** and **614**. In a preferred embodiment, the travel stop fingers, **616**, **618**, **620** and **622**, provide overswing protection for the mirror collection plate **610**. In a preferred embodiment, a 200-micron deep anisotropic deep reactive ion etching (DRIE) process is used to form very precise, narrow gaps for X-axis shock protection and Y-axis shock protection, where the mirror collection plate **610** is preferably completely confined within the frame, **602**, **604**, **606** and **608**, for X-axis and Y-axis translational or planar motion i.e. in the planes of the mirrored surface. Persons having ordinary skill in the art and the

benefit of the present disclosure will recognize that the term DRIE refers to deep reactive ion etching of a substrate. In a preferred implementation, the DRIE process is provided substantially as disclosed in United States Patent Nos. 5,498,312 and 5,501,893.

5 The T-shaped hinges, **612** and **614**, preferably provide the collection plate **610** with optimal translational motion in X-axis and Y-axis directions, in which the mirror collection plate **610** is shock-stopped by the frame, **602**, **604**, **606** and **608**, while also simultaneously maintaining low stress levels within the T-shaped hinges, **612** and **614**, to avoid fracture. In a preferred embodiment, the T-shape
10 hinges, **612** and **614**, are relatively compliant in the X-axis and Y-axis directions, while they are sufficiently rigid for rotational motion about the axis **630** for establishing the resonant frequency of the mirror collection plate **610**.

Thus, in a preferred embodiment of the present invention, the mirror collection plate **610** is supported and suspended by a pair of hinges **612** and
15 **614**. These hinges permit torsional movement or rotation of the mirror collection plate **610** about the common hinge axis **630** and movement of the mirror collection in each of the x, y and z direction. The gap or space **647** between the hinge member **646** and the frame **601** permits movement of the mirror collection plate **610** in the y-direction while the spacing **611** between the
20 stops **616**, **618**, **620** and **621** and the frame **601** permit movement in the x-direction. The movements in the x and y directions are sometimes referred to the planar or translational movements and the hinges as springs. The beams **644** and **628** also permit the mirror collection plate **610** to move in the z-direction. The T-hinges provide the necessary compliance to the mirror
25 collection plate motion in the y-direction, which improves the shock tolerance of the hinge to y-axis shock loads generated by the mirror collection plate **610**. Prior art typically utilizes a straight-beam hinge, i.e. a beam connected to the frame without a T-member, such as the member **646**. Such straight-beam hinges tend to buckle and fracture due to y-axis shock loads. Also, the beams
30 or legs **644** and **648** of the T-hinges **612** and **614** move up in the z-direction due to shock loads. The members **646** and **650** can torsionally rotate, which

reduces the stress induced in the **644 and 648** members of the hinges, which stress has been found to be less than the stress induced in the straight-beam hinges. The amount of stress reduction is a function of the "aspect ratio" of the hinges **612 and 614**, which is a ratio of the width/thickness.

5 As illustrated in **FIGS. 7-9**, the mirror **210** preferably includes portions, **602, 604, 606 and 608**, that are full-wafer thickness (e.g., 400 microns), and portions, **610**, that are half-wafer thickness (e.g., 200 microns). The cavity **720** in the center of the mirror collection plate **610** is preferably etched 150-microns down from the bottom surface **634** of the mirror collection plate **610**, and the T-
10 shape hinges, **612 and 614**, are preferably about 8-15 microns thick. The half-thickness mirror collection plate **610** reduces the amount of deep reactive ion etching (DRIE) and also improves the position accuracy of the mirror collection plate **610**. The cavity **720**, preferably etched in the center of the mirror collection plate **610**, is preferably primarily used to improve the position
15 accuracy of the mirror collection plate **610** and reduce the mass of the mirror collection plate **610** without substantially altering the resonant frequency.

The backside of the mirror collection plate **610** preferably includes the Z travel-stops, **710 and 715**, that preferably are full-wafer thickness (e.g., 400-microns). Since the mirror collection plate **610**, is preferably 200-microns thick,
20 the thicker travel-stops, **710 and 715**, optimally maintain the 50-micron gap with the travel-stop fingers, **1010 and 1020**, of the bottom cap **215** and, therefore, help provide shock protection in the Z-direction. A mirror collection plate **610** having minimum x-y plane dimensions of about 3-mm x 3-mm is preferred.

In an alternative embodiment, as illustrated in **FIG. 6D**, the left and right
25 support members, **606 and 608**, of the mirror **210** further include cut-outs, **660A and 660B**, positioned on opposite sides of the mirror collection plate **610**. In this manner, the amount of viscous damping due to the resistance to the passage of air between the mirror collection plate **610** and the left and right support members, **606 and 608**, is reduced. In this manner, the frequency
30 response characteristics of the mirror **210** are enhanced.

As illustrated in **FIGS. 10-12**, the bottom cap **215** includes a bottom cap frame **1000** to provide support for the bottom cap. The frame **1000** and includes support members and top and bottom travel stop members as described above for the top cap and shown in **FIG. 3**. The bottom cap further
5 comprises an upper left beam **1035**, an upper right beam **1040**, a lower left beam **1045**, a lower right beam **1050**, a top conductive surface **1055**, a bottom conductive surface **1060**, and an opening **1065**.

The thickness of the bottom cap frame **1000** may range, for example, from about 400 to 600 microns with preferred thickness ranging from about 400
10 to 450 microns to provide a compact structure having a low mass.

The top travel stop member **1010** preferably limits the motion of the reflective portion of the mirror **210** in the z-direction. The top travel stop member **1010** preferably extends in a substantially orthogonal direction from the top support member **1005**. In a preferred embodiment, the top travel stop
15 member **1010** is positioned within the plane of the top support member **1005**. The thickness of the top travel stop member **1010** may range, for example, from about 350 to 550 microns. In a preferred embodiment, the thickness of the top travel stop **1010** ranges from about 350 to 380 microns in order to provide a compact structure having a low mass. In a particularly preferred embodiment,
20 the top surface **1010A** of the top travel stop member **1010** is recessed below the level of the top surface **1005A** of the top support member **1005**. In this manner, the top surface **1010A** of the top travel stop **1010** is preferably positioned below the level of the mirror collection plate **610** of the mirror **210**. The length of the top travel stop member **1010** may range, for example, from
25 about 1200 to 2800 microns. In a preferred embodiment, the length of the top travel stop member **1010** ranges from about 2000 to 2500 microns. In a particularly preferred embodiment, the length of the top travel stop member **1010** is selected to overlap with the mirror collection plate **610** of the mirror by about 300 microns.

30 The bottom travel stop member **1020** preferably extends in a substantially orthogonal direction from the bottom support member **1015**. The

bottom travel stop member **1020** is otherwise substantially identical to the above-described top travel stop member **1010**.

The upper left beam **1035** preferably provides support and limits the motion of the mirror collection plate **610** of the mirror **210** in the z-direction during the manufacturing process. In this manner, defective mirrors **210** are protected from shock, catastrophic failure and from falling into the process equipment during the manufacturing process. The upper left beam **1035** preferably extends in a substantially orthogonal direction from the left support member **1025**. In a preferred embodiment, the upper left beam **1035** is positioned within the plane of the left support member **1025**. The thickness of the upper left beam **1035** may range, for example, from about 150 to 250 microns. In a preferred embodiment, the thickness of the upper left beam **1035** ranges from about 200 to 220 microns in order to optimally provide a compact structure having a low mass. In a particularly preferred embodiment, the top surface of the upper left beam **1035** is recessed below the level of the top surface **1025A** of the left support member **1025**. In this manner, the top surface of the upper left beam **1035** is preferably positioned below the level of the top left travel stop member **616** of the mirror **210**. The length of the upper left beam **1035** may range, for example, from about 1500 to 2200 microns. In a preferred embodiment, the length of the upper left beam **1035** is about 1800 microns.

The upper right and lower left and right beams **1040**, **1045** and **1050** are substantially identical to the upper left beam **1035**. These beams are positioned within the plane of corresponding support members.

The top conductive surface **1055** is preferably coupled to the outer periphery of the top surface of the bottom cap **215**. The top conductive surface **1055** preferably provides a conductive electrical path. The top conductive surface **1055** further preferably provides a bonding ring for subsequent compression bonding of the bottom cap **215** to the mirror **210**. The top conductive surface **1055** may be fabricated from any number of conventional commercially available materials such as, for example, gold, aluminum, or silver. In a preferred embodiment, the top conductive surface **1055** is fabricated

from gold. In a preferred embodiment, the top conductive surface **1055** is bonded to the bottom cap **215** using an intermediate layer of titanium. The bottom conductive surface **1060** is preferably coupled to the outer periphery of the bottom surface of the bottom cap **215** and is otherwise substantially identical to the top conductive surface **1055**.

In a preferred embodiment, the conductive surfaces **1055** and **1060** conformally coat all of the exposed surfaces of the bottom cap **215**.

The opening **1065** preferably permits the drive pad electrodes, **1310** and **1315**, of the base member **220** to electrostatically drive and capacitatively sense the position of the mirror collection plate **610** of the mirror **210**. The opening **1065** preferably comprises a substantially rectangular opening of greater size than the mirror collection plate **610** of the mirror **210**.

As illustrated in **FIGS. 13-15**, in a preferred embodiment, the base member **220** includes a bottom plate **1305**, a left drive pad electrode **1310**, a right drive pad electrode **1315**, a frame **1300**, a conductive layer **1340**, and conductive paths **1345**, **1350** and **1355**.

The bottom plate **1305**, and frame **1300** together provide structural support for the base member **220**. The base member **220** preferably supports the bottom cap **215**, mirror **210** and the top cap **205**.

The bottom plate **1305** preferably comprises a solid member fabricated from any number of conventional commercially available materials such as, for example, ceramic, silicon or glass. In a preferred embodiment, the thickness of the bottom plate **1305** ranges from about 200 to 400 microns.

The left drive pad electrode **1310** is coupled to the bottom plate **1305**. The left drive pad electrode **1310** preferably permits the mirror collection plate **610** of the mirror **210** to be driven using electrostatic force and/or the position of the mirror collection plate **610** of the mirror **210** to be capacitively sensed. In this manner, the mirror collection plate **610** of the mirror **210** oscillates about the axis **630**. In a preferred embodiment, the left drive pad electrode **1310** includes a conductive layer **1310A** that is coupled to the conductive path **1350**. In this manner, an electrical connection can be provided to the conductive layer

1310A. The conductive layer **1310A** may be fabricated from any number of conventional commercially available materials such as, for example, metal, polysilicon or conductive epoxy. In a preferred embodiment, the conductive layer **1310A** is fabricated from metal.

5 The left drive pad electrode **1310** may have a top surface area ranging, for example, from about 3×10^6 to 10×10^6 microns.² In a preferred embodiment, the top surface area of the left drive pad electrode **1310** is about 4.5×10^6 microns² in order to optimally drive the mirror collection plate **610** of the mirror **210**. The left drive pad electrode **1310** preferably extends from the bottom plate **1305** in a substantially orthogonal direction. The left drive pad electrode **1310** may extend from the bottom plate **1305** for a distance ranging, for example, from about 50 to 200 microns. In a preferred embodiment, the left drive pad electrode **1310** extends from the bottom plate **1305** for a distance ranging from about 50 to 100 microns. In a particularly preferred embodiment, gap between the top of the left drive pad electrode **1310** and the bottom of the mirror collection plate **610** of the mirror **210** ranges from about 300 to 400 microns.

15 The right drive pad electrode **1315** is substantially identical to the left pad electrode **1310**. In a preferred embodiment, the left and right drive pad electrodes, **1310** and **1315**, are positioned substantially equidistant from the axis **630**.

20 The top support member **1320** is coupled to the bottom plate **1305**, the left support member **1330**, the right support member **1335** and the conductive layer **1340**. The top support member **1320** may have a length, width and height ranging, for example, from about 4000 to 6000 microns, 400 to 600 microns, and 400 to 600 microns. In a preferred embodiment, the top support member **1320** length, width and height are about 4900 microns, 375 microns, and 400 microns.

25 The left support member **1330** is coupled to the bottom plate **1305**, the top support member **1320**, the bottom support member **1325** and the conductive layer **1340**. The left support member **1330** may have a length, width and height ranging, for example, from about 6000 to 9000 microns, 400 to 600

30

microns, and 400 to 600 microns. In a preferred embodiment, the left support member **1330** length, width and height are about 6800 microns, 375 microns, and 400 microns.

5 The bottom support member **1325** is substantially identical to the top support member **1320** and the right support member **1335** is substantially identical to the left support member **1330**.

In a preferred embodiment, the bottom plate **1305**, the top support member **1320**, the bottom support member **1325**, the left support member **1330**, and the right support member **1335** are integrally formed.

10 The conductive layer **1340** preferably extends around the periphery of the top surface of the base member **220**. The conductive layer **1340** preferably provides a conductive electric path for use in actuating the mirror collection plate **610** of the mirror **210**. The conductive layer **220** may be fabricated from any number of conventional commercially available materials such as, for
15 example, metal, polysilicon or conductive epoxy. In a preferred embodiment, the conductive layer **1340** is fabricated from gold. The conductive layer **1340** may be coupled to the conductive path **1345** using conventional methods.

The base member **220** may be fabricated from any number of conventional commercially available materials such as, for example, ceramic,
20 silicon or glass using any number of conventional fabrication processes. In a preferred embodiment, the base member **220** is fabricated by micro-machining and/or thick film printing a ceramic substrate using any one, or combination, of the embodiments for micro-machining disclosed in the present disclosure.

The base **220** preferably provides electrode access to the mirror
25 collection plate **610** for electrostatic actuation and capacitive position sensing using drive pad electrodes, **1310** and **1315**. The design and operation of the electrostatic actuation and capacitive position sensing are well known in the art.

30 The metal ring **1340** around the perimeter of the base member **220**, in combination with conductive-epoxy bonding of the base member **220** to the bottom cap **215**, preferably provides electrical contact between the base

member **220** and the bottom cap **215**. In a preferred embodiment, the wafer bonding process preferably allows the bottom cap **215** to be in direct electrical contact with the mirror collection plate **610**. Consequently, the mirror collection plate **610** preferably can be electrically accessed, controlled, and monitored using the base member **220**. The electrode drive pad and mirror contact metallization, **1310A**, **1315A**, and **1340**, on the base member **220** are preferably connected to electrical contact pads on the backside of the base member **220**, utilizing conventional thick-film through-hole via technology, which effectively makes the mirror assembly **110** a surface-mount component.

Referring now to **FIG. 16**, a sub-assembly including the top cap **205** and the mirror **210** is illustrated. As illustrated in **FIG. 16**, the travel stops, **310** and **320**, of the top cap **205** protect the mirror collection plate **610** from z-axis shock while also minimizing the shadowing/overlapping of the reflective surface **628** of the mirror collection plate **610**. Furthermore, the side rim cut-outs, **330** and **340**, of the top cap **205** maximize the optical path to the reflective surface **628** of the mirror collection plate **610**.

Referring now to **FIG. 17**, a sub-assembly including the bottom cap **215** and the base member **220** is illustrated. As illustrated in **FIG. 17**, the travel stop fingers, **1010** and **1020**, protect the mirror collection plate **610** from z-axis shock while also maximizing the drive area of the drive pad electrodes, **1310** and **1315**.

Referring now to **FIG. 18**, additional shock protection features of the mirror assembly **110** will be described. As illustrated in **FIG. 18**, preferably all of the interior walls of the top cap **205** and bottom cap **215** include tapered walls. In a preferred embodiment, the mirror collection plate **610** may be rotated out of plane by about 14° in both directions. In a preferred embodiment, the clearance between the mirror collection plate **610** and the interior walls of the top cap **205**, bottom cap **215**, and the support structure of the mirror **210** is about 60 ± 10 microns for rotation ranging from -14° to $+14^\circ$. As also illustrated in **FIG. 18**, the travel stops, **320** and **1020**, protect the mirror collection plate **610** from z-axis shocks. In a preferred embodiment, the clearance between the

mirror collection plate **610** and the travel stops, **320** and **1020**, is about 20-60 microns.

As illustrated in **FIG. 18**, the travel-stop fingers, **310** and **320**, of the top cap **205** protect the mirror **210** from Z-axis shock while minimizing the shadowing/overlap of the mirror collection plate **610**, thus providing the external laser optical access to the micromirror. The travel-stop fingers, **310** and **320**, are preferably recessed about 20-60 microns from the surfaces of the top cap **205**, which preferably sets the gap between the mirror collection plate **610** and the travel-stop fingers, **310** and **320**, to be about 20-60 microns in the Z-direction. The tapered walls around the inside perimeter of the top cap **205** are preferably for capturing the mirror collection plate **610** during an input shock while the mirror collection plate **610** is rotated out-of-plane. The left and right rim cut-outs, **330** and **340**, in the top cap **205** preferably provide clipping reduction. The travel-stop fingers, **1010** and **1020**, of the bottom cap **215** preferably protect the mirror collection plate **610** from Z-axis shock while maximizing the area of the drive pad electrodes, **1310** and **1315**. The travel-stop finger arrangement of the top and bottom caps, **205** and **215**, preferably constrain the mirror collection plate **610** from Z-axis translational motion, while promoting torsional rotation of the mirror collection plate **610** about the axis **630**. The bottom cap **215** also preferably includes the beams, **1025**, **1040**, **1045**, and **1050**, for facilitating the handling of defective mirrors during the fabrication process.

As illustrated in **FIGS. 6, 6A, 6B and 6C**, the design of the T-shaped hinges **612** and **614**, decouples the rotational spring constants from the translational spring constants. In this manner, the mirror collection plate **610** is optimally protected from vibration and shock loads.

Referring now to **FIG. 19**, additional features of the mirror assembly **110** for optimizing the reflection of incident laser beams will be described. In an exemplary application of the sensor assembly **110**, an incident laser beam A is directed to the mirror collection plate **610** at an angle of 45° and results in the reflected beam B. For a scanning range of $\pm 10^\circ$, the reflected laser beams are

bound by the rays B' and B . In order to avoid laser beam clipping, the tapered walls and rim cut-outs, **330** and **340**, of the top cap **205** minimize clipping of the incident and reflected laser beams. These features are particularly advantageous in the situation where the incident laser beam is displaced
5 resulting in the incident laser beam A' or the reflected laser beam B .

As illustrated in **FIGS. 18 and 19**, the tapered walls of the bottom cap **215** provide optimal shock protection to the mirror collection plate **610**, and the tapered walls of the top cap **205** minimize clipping of the incident and reflected laser beams. The rim cut-outs, **330** and **340**, of the top cap **205** further
10 minimize shadowing and clipping of the incident and reflected laser beams.

A mirror assembly has been described that includes a mirror, a top cap and a bottom cap. The mirror includes a mirror support structure, a pair of T-shaped hinges coupled to the mirror support structure and a mirrored plate coupled to the T-shaped hinges. The mirrored plate includes one or more travel
15 stops for limiting movement of the mirrored plate. The top cap is coupled to one side of the mirror. The top cap includes a top cap support structure including an opening for permitting light to reflect off of the mirrored plate and one or more travel stops coupled to the top cap support structure for limiting movement of the mirrored plate. The bottom cap is coupled to another side of the mirror.
20 The bottom cap includes a bottom cap support structure including an opening and one or more travel stops coupled to the bottom cap support structure for limiting movement of the mirrored plate. In a preferred embodiment, the mirror support structure includes a top support member, a bottom support member, a right side support member and a left side support member. In a preferred
25 embodiment, the mirror support structure includes an opening. In a preferred embodiment, the support structure opening includes a pair of oppositely positioned cut-outs. In a preferred embodiment, the support structure opening is complementary shaped with respect to the mirrored plate. In a preferred embodiment, the spacing between the edges of the support structure opening and the mirrored plate ranges from about 15 to 180 microns. In a preferred
30 embodiment, the pair of T-shaped hinges include a top T-shaped hinge and a

bottom T-shaped hinge positioned in opposing relation to the top T-shaped hinge. In a preferred embodiment, the mirrored plate includes a plate member including a first side and a second side, a reflective surface coupled to the first side of the plate member, a cavity formed in the second side of the plate member and a pair of travel stops coupled to the second side of the plate member. In a preferred embodiment, the plate member cavity includes a V-shaped cross section. In a preferred embodiment, the mirrored plate includes a plate member and one or more travel stops extending from the plate member. In a preferred embodiment, the travel stops are positioned in the plane of the plate member. In a preferred embodiment, the plate member travel stops that are positioned in the plane of the plate member have a length and thickness ranging from about 500 to 2000 microns and 200 to 600 microns. In a preferred embodiment, the plate member extend from the plane of the plate member. In a preferred embodiment, the plate member travel stops that extend from the plane of the plate member have a length ranging from about 200 to 250 microns. In a preferred embodiment, the mirrored plate includes a plate member and a plurality of travel stops extending from the plate member. In a preferred embodiment, at least one of the plate member travel stops is positioned in the plane of the plate member and at least one of the travel stops extends from the plane of the plate member. In a preferred embodiment, each T-shaped hinge includes a first member and a second member coupled to the first member. In a preferred embodiment, the first and second members are substantially orthogonal. In a preferred embodiment, the length, width and thickness of the first hinge member ranges from about 500 to 4500 microns, 10 to 100 microns and 10 to 100 microns. In a preferred embodiment, the length, width and thickness of the second hinge member ranges from about 400 to 1800 microns, 2 to 35 micron and 2 to 35 microns. In a preferred embodiment, each T-shaped hinge provides a torsional spring. In a preferred embodiment, the spring constant ranges from about 2×10^{-9} to 10×10^{-7} lbf-ft/radian. In a preferred embodiment, the top cap travel stops are positioned in the plane of the top cap support structure. In a preferred embodiment, the thickness of the top cap travel stops are less than the thickness of the top cap support structure.

In a preferred embodiment, the opening in the top cap support structure includes a pair of oppositely positioned cut-outs. In a preferred embodiment, the cut-outs include tapered walls. In a preferred embodiment, the taper angle of the tapered walls ranges from about 55 to 60 degrees. In a preferred embodiment, the top cap opening includes tapered walls. In a preferred embodiment, the taper angle of the tapered walls ranges from about 55 to 60 degrees. In a preferred embodiment, the bottom cap travel stops are positioned in the plane of the bottom cap support structure. In a preferred embodiment, the thickness of the bottom cap travel stops are less than the thickness of the bottom cap support structure. In a preferred embodiment, the bottom cap opening includes tapered walls. In a preferred embodiment, the taper angle of the tapered walls ranges from about 55 to 60 degrees. In a preferred embodiment, the mirror assembly further includes a base member coupled to the bottom cap. In a preferred embodiment, the base member includes one or more drive pads for actuating the mirrored plate. In a preferred embodiment, the base member includes one or more sensing members for sensing the position of the mirrored plate. In a preferred embodiment, the bottom cap further includes one or more support members for supporting the mirrored plate during the manufacturing process. In a preferred embodiment, the length and thickness of the top cap travel stops range from about 800 to 2800 microns and 340 to 580 microns. In a preferred embodiment, the length and thickness of the bottom cap travel stops range from about 800 to 2800 microns and 340 to 580 microns. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member is perpendicular to the first member. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member is serpentine. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member is offset from the center of the first member. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first

member, wherein the second member intersects the first member at an acute angle. In a preferred embodiment, each T-shaped hinge includes a translational spring constant and a rotational spring constant that are decoupled from one another.

5 A mirror assembly has also been described that includes a support structure, a pair of T-shaped hinges coupled to the support structure and a mirrored plate coupled to the T-shaped hinges. The mirrored plate includes one or more travel stops for limiting movement of the mirrored plate. In a preferred embodiment, each T-shaped hinge includes a rotational spring constant and a
10 translational spring constant that are decoupled. In a preferred embodiment, the support structure includes a top support member, a bottom support member, a right side support member and a left side support member. In a preferred embodiment, the support structure includes an opening. In a preferred embodiment, the opening includes a pair of oppositely positioned cut-
15 outs. In a preferred embodiment, the opening is complementary shaped with respect to the mirrored plate. In a preferred embodiment, the spacing between the edges of the opening and the mirrored plate ranges from about 15 to 180 microns. In a preferred embodiment, the pair of T-shaped hinges include a top T-shaped hinge and a bottom T-shaped hinge positioned in opposing relation
20 to the top T-shaped hinge. In a preferred embodiment, the mirrored plate includes a plate member including a first side and a second side, a reflective surface coupled to the first side of the plate member, a cavity formed in the second side of the plate member and a pair of travel stops coupled to the second side of the plate member. In a preferred embodiment, the cavity
25 includes a V-shaped cross section. In a preferred embodiment, the mirrored plate includes a plate member and one or more travel stops extending from the plate member. In a preferred embodiment, the travel stops are positioned in the plane of the plate member. In a preferred embodiment, the travel stops that are positioned in the plane of the plate member have a length and thickness that
30 range from about 500 to 2000 microns and 200 to 600 microns. In a preferred embodiment, the travel stops extend from the plane of the plate member. In a preferred embodiment, the travel stops that extend from the plane of the plate

member have a length that extends from about 200 to 250 microns. In a preferred embodiment, the mirrored plate includes a plate member and a plurality of travel stops extending from the plate member. In a preferred embodiment, at least one of the travel stops is positioned in the plane of the plate member and at least one of the travel stops extends from the plane of the plate member. In a preferred embodiment, each T-shaped hinge includes a first member and a second member coupled to the first member. In a preferred embodiment, the first and second members are substantially orthogonal. In a preferred embodiment, the length, width and thickness of the first member ranges from about 500 to 4500 microns, 10 to 100 microns and 10 to 100 microns. In a preferred embodiment, the length, width and thickness of the second member ranges from about 400 to 1800 microns, 20 to 35 microns and 2 to 35 microns. In a preferred embodiment, each T-shaped hinge provides a torsional spring. In a preferred embodiment, the spring constant ranges from about 2×10^{-9} to 10×10^{-7} lbf-ft/radian. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member is perpendicular to the first member. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member is serpentine. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member is offset from the center of the first member. In a preferred embodiment, one or more of the T-shaped hinges include a first member and a second member coupled to the first member, wherein the second member intersects the first member at an acute angle. In a preferred embodiment, the mirror assembly is fabricated using one or more of the merged-mask micro-machining processes disclosed in the present disclosure.

An apparatus has also been described that includes one or more T-shaped springs and a mass coupled to the T-shaped springs. In a preferred embodiment, the mass includes a reflective surface. In a preferred embodiment, the mass includes one or more travel stops for limiting movement

of the mass. In a preferred embodiment, the apparatus further includes a top cap coupled to the top of the mass, wherein the top cap includes one or more travel stops for limiting movement of the mass. In a preferred embodiment, the apparatus further includes a bottom cap coupled to bottom of the mass, wherein
5 the bottom cap includes one or more travel stops for limiting movement of the mass. In a preferred embodiment, the apparatus further includes a top cap coupled to the top of the mass and a bottom cap coupled to the bottom of the mass, wherein the top and bottom caps each include one or more travel stops for limiting movement of the mass. In a preferred embodiment, the apparatus
10 is fabricated using one or more of the merged-mask micro-machining processes disclosed in the present disclosure. In a preferred embodiment, each T-shaped hinge includes a rotational spring constant and a translational spring constant that are decoupled. In a preferred embodiment, the apparatus comprises an accelerometer. In a preferred embodiment, the apparatus comprises a
15 gyroscope.

An apparatus also has been described that includes a housing, a mass, and one or more springs for coupling the mass to the housing. Each spring includes a rotational spring constant and a translational spring constant. The rotational spring constant is decoupled from the translational spring constant.
20 In a preferred embodiment, the springs are fabricated by a process including micromachining a substrate. In a preferred embodiment, the housing, mass and springs are fabricated by a process including micromachining a substrate. In a preferred embodiment, each spring comprises a plurality of springs. In a preferred embodiment, each spring is T-shaped. In a preferred embodiment,
25 the apparatus further includes a top cap coupled to the top of the housing including a top cap cutout and a bottom cap coupled to the bottom of the housing including a bottom cap cutout. The top and bottom cap cutouts limit movement of the mass when the mass is rotated away from its rest position. In a preferred embodiment, each cutout includes tapered side walls. In a
30 preferred embodiment, the tapered side walls are rotated from the vertical direction at an angle ranging from about 15 to 45 degrees.

A method of resiliently supporting a mass in a housing also has been described that includes coupling the mass to the housing using one or more springs having translational spring constants and rotational spring constants and decoupling the translational spring constants from the rotational spring constants. In a preferred embodiment, the springs are fabricated by a process including micromachining a substrate. In a preferred embodiment, the housing, mass and springs are fabricated by a process including micromachining a substrate. In a preferred embodiment, each spring comprises a plurality of springs. In a preferred embodiment, each spring is T-shaped. In a preferred embodiment, method further includes limiting movement of the mass when it is rotated from a rest position. In a preferred embodiment, limiting movement of the mass when it is rotated from a rest position includes limiting translation of the mass when it is rotated from the rest position.

A method of resiliently supporting a mass in a housing also has been described that includes limiting translational movement of the mass in the X, Y and Z directions and limiting rotational movement of the mass. In a preferred embodiment, the housing and mass are fabricated by a process including micromachining a substrate. In a preferred embodiment, the method further includes limiting movement of the mass when it is rotated from a rest position. In a preferred embodiment, limiting movement of the mass when it is rotated from a rest position includes limiting translation of the mass when it is rotated from the rest position.

An apparatus also has been described that includes a housing and a mass resiliently coupled to the housing, the mass including one or more travel stops for limiting rotational and translational movement of the mass. In a preferred embodiment, the housing includes an opening for receiving the mass that limits the translational movement of the mass. In a preferred embodiment, the apparatus further includes a top cap coupled to the top of the housing and a bottom cap coupled to the bottom of the housing. The top and bottom caps limit movement of the mass when it is rotated out of its rest position within the housing. In a preferred embodiment, the top and bottom caps includes cutouts. In a preferred embodiment, each cutout includes tapered side walls. In a

preferred embodiment, the tapered side walls are rotated from the vertical direction at an angle ranging from about 15 to 45 degrees.

An apparatus also has been described that includes a housing including an opening, the opening including one or more cutouts and a reflective surface resiliently coupled to the housing. In a preferred embodiment, each cutout includes tapered side walls. In a preferred embodiment, the tapered side walls are rotated from the vertical direction at an angle ranging from about 15 to 45 degrees. In a preferred embodiment, the housing and reflective surface are fabricated by a process including micromachining a substrate.

A method of reflecting rays of light also has been described that includes providing a reflective surface and providing an optical pathway for accessing the reflective surface including one or more cutouts for minimizing clipping of the incident and reflected light rays. In a preferred embodiment, the optical pathway includes sidewalls that are rotated from the vertical direction at an angle ranging from about 15 to 45 degrees. In a preferred embodiment, the optical pathway and reflective surface are fabricated by a process including micromachining a substrate.

Referring now to **FIG. 20**, in a preferred embodiment, the fabrication of the mirror assembly **110** includes the steps of: (1) the mirror wafer process **2005**, (2) the ceramic base wafer process **2010**, (3) the top/bottom cap wafer processes **2015**, (4) gold bonding of the cap wafers to the mirror wafer to form a mirror wafer stack **2020**, (5) conductive epoxy bonding of the ceramic base wafer to the mirror wafer stack to form a packaged mirror wafer stack **2025**, (6) dicing of the packaged mirror wafer stack **2030**, and (7) testing of the packaged mirror die **2035**.

The mirror wafer process **2005** preferably provides the mirror **210**. In a preferred embodiment, as illustrated in **FIGS. 21a** and **21b**, the mirror wafer process **2005** preferably includes the steps of: (1) providing a silicon wafer in step **2105**, (2) growing pad layers of silicon dioxide on both sides of the silicon wafer in step **2110**, (3) applying layers of silicon nitride to both sides of the silicon wafer in step **2115**, (4) patterning the silicon nitride layer on the backside

of the silicon wafer in step **2120**, (5) etching the exposed areas of silicon dioxide on the backside of the silicon wafer in step **2125**, (6) thin etching of the exposed areas of silicon on the backside of the silicon wafer in step **2130**, (7) growing a field layer of silicon dioxide on the areas of the backside of the wafer not covered by the layer of silicon nitride in step **2135**, (8) patterning the field layer of silicon dioxide on the backside of the silicon wafer in step **2140**, (9) KOH etching of the exposed portions of silicon on the backside of the silicon wafer in step **2150**, (10) etching of the exposed portions of the field layer of silicon dioxide on the backside of the silicon wafer in step **2155**, (11) KOH etching of the exposed portions of silicon on the backside of the silicon wafer and stripping of the silicon nitride layers on both sides of the silicon wafer in step **2160**, (12) photolithography of the exposed portions of the silicon dioxide layer on the front side of silicon wafer in step **2165**, (13) etching the silicon dioxide layers on both sides of the silicon wafer in step **2170**, (14) depositing gold on the frontside of the silicon wafer in step **2175**, (15) photolithography and etching of the gold layer on the front side of the silicon wafer in step **2180**, (16) applying a photo resist layer to the front side of silicon wafer in step **2185**, (17) photolithography and etching of the photo resist layer on the front side of the silicon wafer in step **2190**, (18) deep reactive ion etching (DRIE) of the exposed portions of silicon on the frontside of the silicon wafer in step **2192**, (19) etching the exposed portions of the silicon dioxide layer on the frontside of silicon wafer in step **2194**, (20) deep reactive ion etching (DRIE) of the exposed portions of silicon on the front side of the silicon wafer in step **2196**, and (21) plasma stripping of the photo resist layer on the front side of the silicon wafer in step **2198**.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

In a preferred implementation, the DRIE process is provided substantially as disclosed in United States Patent Nos. 5,498,312 and 5,501,893.

5 As illustrated in FIG. 22, in process step 2105, a silicon wafer 2205 is provided having a frontside 2205a and a backside 2205b. In a preferred embodiment, the silicon wafer 2205 comprises a 400 micron thick wafer of silicon. In a preferred embodiment, the silicon wafer 2205 receives a doping of boron-doped epi on the frontside of the silicon wafer 2205. Heavily-doped boron silicon layers form an etch stop for KOH. In a preferred embodiment, the
10 doping of boron-doped epi on the frontside of the silicon wafer 2205 is provided for a depth of about 7 microns.

In a preferred embodiment, the starting material specifications for the top/bottom cap and mirror wafers are double-side polish, thickness control of 400 ± 7.5 microns, and a doping concentration of 10^{18} cm^{-3} of boron. For the
15 mirror wafers, the starting wafers preferably are deposited with 7-microns of heavily boron-doped epi on the frontside and the wafers are then polished back to approximately the 400-micron starting thickness. In a preferred embodiment, the electrical connection from the released mirror collection plate 610 to the ceramic base member 220 is through the thickness of the mirror wafer and the
20 bottom cap wafer. The high doping concentration of these wafers optimally provides a good, ohmic electrical contact between the mirror/bottom cap and bottom cap/base member metallization. In an alternative embodiment, double-side implanting of the bottom cap 220 and backside implanting of the mirror 210 are provided.

25 In process step 2110, pad layers, 2210a and 2210b, of silicon dioxide are then grown on both sides of the silicon wafer 2205. The layers, 2210a and 2210b, of silicon dioxide may be grown using any number of conventional commercially available processes. In a preferred embodiment, the layers, 2210a and 2210b, of silicon dioxide are grown by the process of thermal
30 oxidation. The layers, 2210a and 2210b, of silicon dioxide may be grown to depths ranging, for example, from 300 to 10000 Angstroms. In a preferred

embodiment, the layers, **2210a** and **2210b**, of silicon dioxide are grown to depths ranging from about 3000 to 6000 Angstroms. The pad layers, **2210a** and **2210b**, provide a buffer layer of silicon dioxide between the layers, **2215a** and **2215b**, of silicon nitride and the surface of the silicon wafer **2205**.

5 In process step **2115**, layers, **2215a** and **2215b**, of silicon nitride are then applied onto the layers, **2210a** and **2210b**, of silicon dioxide. The layers, **2215a** and **2215b**, of silicon nitride may be deposited using any number of conventional commercially available processes. In a preferred embodiment, the layers, **2215a** and **2215b**, of silicon nitride are deposited by the process of
10 chemical vapor deposition. The layers, **2215a** and **2215b**, of silicon nitride may be applied to depths ranging, for example, from about 1000 to 20000 Angstroms. In a preferred embodiment, the layers, **2215a** and **2215b**, of silicon nitride are applied to depths ranging from about 1200 to 1500 Angstroms.

As illustrated in **FIG. 23**, in process step **2120**, the layer **2215b** of silicon
15 nitride is then etched to expose portions of the pad layer **2210b** of silicon dioxide. The unetched portions of the layer **2215b** of silicon nitride provide protection for the regions of the backside **2205b** of the silicon wafer **2205** that are going to remain unetched which preferably includes the support structure for the mirror **210** and the travel stops, **710** and **715**, of the mirror collection
20 plate **610**.

As illustrated in **FIG. 23a**, in process step **2125**, the exposed portions of the pad layer of **2210b** silicon dioxide are then etched to expose portions of the backside **2205b** of the silicon wafer.

As illustrated in **FIG. 23b**, in process steps **2130** and **2135**, the exposed
25 portions of the backside **2205** of the silicon wafer are thin etched, and then a field layer **2210c** of silicon dioxide is then grown on the areas of the backside **2205** of the silicon wafer not covered by the layer **2215b** of silicon nitride. In a preferred embodiment, the depth of the thin etch of the backside **2205** of the silicon wafer ranges from about 0.5 to 1.5 microns in order to optimally facilitate
30 the growth of the layer **2210c** of field oxide. In a preferred embodiment, the thickness of the field layer **2210c** of silicon dioxide is greater than or equal to

the combined thicknesses of the pad layer **2210a** of the silicon dioxide and the layer **2210b** of silicon nitride.

As illustrated in **FIG. 24**, in process step **2140**, the exposed portions of the field layer **2210c** of silicon dioxide are then etched to expose portions of the backside **2205b** of the silicon wafer **2205**. These exposed portions of the backside **2205b** of the silicon wafer **2205** are preferably then etched down to the 7-micron thick epi layer in subsequent processing steps. In a preferred embodiment, the 7-micron thick epi layer provides a chemical etch stop.

The etched layers, **2210c** and **2215b**, of silicon dioxide and silicon nitride preferably provide etching masks for a plurality of etching depths. In a preferred embodiment, the exposed portions of the silicon wafer **2205** are first etched to a first depth through openings in the etched field layer **2210c** of silicon dioxide. In a preferred embodiment, the exposed portions of the etched field layer **2210c** of silicon dioxide are then removed. In a preferred embodiment, the exposed portions of the silicon wafer are then etched to a second depth through openings in the etched layer **2215b** of silicon nitride. In this manner, process steps **2110** to **2160** preferably provide a localized oxidation of silicon (LOCOS) merged-mask micro-machining process. As will be recognized by persons having ordinary skill in the art and the benefit of the present disclosure, LOCOS refers to the localized growth of silicon dioxide onto a substrate. In an alternative embodiment, additional masking layers are provided to permit micro-machining to additional etch depths. In an alternative embodiment, the masking layers comprise alternating layers of silicon dioxide and silicon nitride.

As illustrated in **FIGS. 25** and **26**, in process step **2150**, the backside **2205b** of the silicon wafer is then etched using KOH. In a preferred embodiment, the backside **2205b** of the silicon wafer is then etched using KOH to a depth of 190 microns. The KOH etching process preferably defines the hinges, **612** and **614**, the mirror collection plate **610**, and the cavity **720** of the mirror collection plate **610**.

As illustrated in **FIGS. 27** and **28**, in process steps **2155** and **2160**, the exposed portions of the field layer **2210c** of silicon dioxide on the backside

2205b of the silicon wafer **2205** are removed. The exposed portions of the backside **2205b** of the silicon wafer **2205** are then etched using KOH to a depth of 200 microns. The KOH etching process preferably further defines the hinges, **612** and **614**, the mirror collection plate **610**, and the cavity **720** of the mirror collection plate **610**. Finally, the remaining portions of the layers, **2215a** and **2215b**, of silicon nitride are then removed from both sides of the silicon wafer **2205**. The heavily boron-doped epi layer provided in the silicon wafer **2205** provides a chemical etch stop for the KOH process. In this manner, the cavity **720** in the mirror collection plate **610** and the T-shape hinge regions, **612** and **614**, are formed.

In an alternative embodiment, the cavity **720** in the mirror collection plate **610** is defined by the openings provided in the masking layers used to form the cavity **720**. In an alternative embodiment, the cavity **720** in the mirror collection plate **610** has a V-shaped cross section.

As illustrated in **FIG. 21a**, process steps **2110-2160** provide a localized oxidation of silicon (LOCOS) merged-mask KOH micro-machining process in which the masks required for etching to several different etch depths of the silicon wafer **2205** are provided by applying a plurality of etch-resistant layers and etching those etch-resistant layers to provide a plurality of masking layers. As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, LOCOS refers to the localized oxidation of a substrate or layer containing silicon to produce an overlying layer of silicon dioxide. This allows regions with different topologies to be defined with only one lithography and multiple etch cycles.

As illustrated in **FIGS. 29a** and **29b**, in process steps **2165** and **2170**, the pad layer **2210a** of silicon dioxide on the frontside **2205a** of the silicon wafer **2205** is then masked and etched to define a portion of the etching mask for the mirror collection plate **610** on the frontside **2205a** of the silicon wafer **2205**. The remaining exposed portions of the pad layer **2210b** of silicon dioxide on the backside **2205b** of the silicon wafer are also etched.

As illustrated in **FIGS. 30a** and **30b**, in process step **2175**, a layer **3005** of gold is then applied to the frontside **2205a** of the silicon wafer **2205**. The layer **3005** of gold is then patterned in process step **2180** to provide the reflective surface **628** of the mirror collection plate **610** and the outer perimeter
5 conductive layer **626** for compression bonding the mirror to the top cap. In a preferred embodiment, the layer **3005** of gold is bonded to the frontside **2205a** of the silicon wafer **2205** using an intermediate layer of titanium.

As illustrated in **FIGS. 30c** and **30d**, in process steps **2185** and **2190**, a layer **3010** of photoresist is applied and patterned on the frontside **2205a** of the
10 silicon wafer **2205**. The patterned layer **3010** of photoresist is then used as an etch mask for etching and defining the T-shaped hinges, **612** and **614**, and the mirror collection plate **610**.

As illustrated in **FIGS. 31** and **32**, in process steps **2192**, **2194**, **2196** and **2198**, the exposed portions of the frontside **2205a** of the silicon wafer are then
15 etched using a deep reactive ion etch (DRIE) of the exposed silicon on the frontside **2205a** of the silicon wafer to a depth of 190 microns to define the mirror collection plate **610**. The exposed portions of the layer **2210a** of silicon dioxide are then etched. The frontside **2205a** of the silicon wafer **2205** is then
20 etched using a deep reactive ion etch (DRIE) to a depth of 10 microns to form the T-shaped hinges. Finally, the photo resist layer is removed from the frontside **2205a** of the silicon wafer **2205**. In a preferred embodiment, the DRIE performed in steps **2192** and **2196** provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

The etched layers of silicon dioxide and photoresist on the frontside
25 **2205a** of the silicon substrate **2205** preferably provide etching masks for a plurality of etching depths. In a preferred embodiment, the exposed portions of the silicon wafer **2205** are first etched to a first depth through openings in the etched pad layer **2210a** of silicon dioxide. In a preferred embodiment, the exposed portions of the etched layer **2210a** of silicon dioxide are then removed.
30 In a preferred embodiment, the exposed portions of the silicon wafer **2205** are then etched to a second depth through openings in the etched layer of

photoresist. In this manner, process steps **2155** to **2185** provide a merged-mask micro-machining process that utilizes a photoresist layer as an etching mask.

As illustrated in **FIGS. 21a** and **21b**, process steps **2110** to **2160** also provide a wet KOH merged-mask micro-machining process, while process steps **2165** to **2198** provide a dry DRIE merged-mask micro-machining process. More generally, process steps **2110** to **2160** provide a merged-mask micro-machining process including the steps of: (1) providing a silicon substrate; (2) applying a buffer layer of silicon dioxide onto the silicon substrate; (3) applying a masking layer onto the buffer layer; (4) patterning the buffer and masking layer; (5) thin etching the exposed portions of the silicon substrate; (6) growing a field layer of silicon dioxide onto the exposed portions of the silicon substrate; (7) patterning the field layer of silicon dioxide; (8) etching the exposed portions of the silicon substrate using the field oxide as an etch mask; (9) removing the exposed portions of the field layer of silicon dioxide; and (10) etching the exposed portions of the silicon substrate using the silicon nitride as an etch mask. More generally, process steps **2165** to **2198** provide a merged-mask micro-machining process including the steps of: (1) providing a silicon substrate; (2) applying a first masking layer onto the silicon substrate; (3) patterning the first layer of masking material; (4) applying a second masking layer onto the patterned first layer of masking material; (5) etching the exposed portions of the silicon substrate; (6) removing the exposed portions of the first layer of masking material; (7) etching the exposed portions of the silicon substrate; and (8) removing the exposed portions of the second layer of masking material.

As illustrated in **FIGS. 21a-32**, in a preferred embodiment, the mirror fabrication process begins by providing a 400 micron silicon wafer **2205** with 7-microns of heavily boron-doped epi deposited on the frontside. The silicon wafer **2205** then has silicon dioxide, **2210**, and silicon nitride, **2215**, films deposited on both sides of the silicon wafer **2205** to form an etch-mask for the wet KOH etching. On the backside of the wafer **2205** the silicon nitride layer **2215b** is patterned to protect the regions that are going to remain unetched

(i.e., the mirror frame region and Z travel stop features. The underlying, exposed pad oxide layer **2210b** is then etched to expose the backside **2205b** of the silicon wafer **2205**. The exposed portions of the backside **2205b** of the silicon wafer **2205** are then thin etched to a depth of about 1 micron. A layer **2210c** of field oxide is then grown on the backside **2205b** of the silicon wafer **2205**. The field oxide layer **2210c** is then patterned to expose the regions that are going to be etched down to the epi layer. The silicon wafer **2205** is then placed in wet KOH etchant, which etches the exposed silicon regions and does not etch the regions protected with either silicon dioxide or silicon nitride. The exposed silicon is then etched to a depth of 190 microns. The exposed silicon dioxide field layer **2210c** is then etched away, leaving the silicon nitride protected regions as the etch mask. The silicon wafer **2205** is then placed back into the wet KOH etchant and etched for another 200 microns. The regions that were previously etched in the first round of KOH etching stop etching when the heavily boron-doped epi layer is reached, and these regions form the cavity **720** and T-shape hinge regions. Heavily-doped boron silicon layers form a chemical etch-stop for KOH. Therefore, the newly exposed silicon regions are etched to a depth of 200 microns during this second round of KOH etching and form the half-thickness mirror collection plate **610**. This merged-mask KOH process allows regions with different etch topologies to be defined with only one lithography and etch cycle. This manufacturing process avoids the significant yield issues associated with conventional deep-cavity lithography.

As illustrated in **FIGS. 21a, 31 and 32**, a deep reactive ion etching (DRIE) dry etching micro-machining process is preferably used to define the T-shaped hinges, **612** and **614**, and release the mirror collection plate **610** from the frame, **602, 604, 606** and **608**. In a preferred embodiment, the DRIE dry etching process provides minimal lateral undercutting and provides near-vertical sidewall profiles. In this manner, the DRIE dry etching process optimally provides X-gaps and Y-gaps, between the mirror collection plate **610** and the frame, **602, 604, 606**, and **608**, that optimally function as shock travel stops for the mirror collection plate **610**. In a preferred embodiment, the X-gap and Y-gap sidewall

profiles of the mirror collection plate **610** and support frame, **602**, **604**, **606**, and **608**, are substantially vertical. In a preferred embodiment, the X-gap and Y-gap between the mirror collection plate **610** and the support structure, **602**, **604**, **606** and **608**, is maintained for all rotational orientations of the mirror collection plate **610**. In this manner, the mirror collection plate **610** is shock stopped by the frame, **602**, **604**, **606** and **608**. Excessive taper of the mirror collection plate **610** or the sidewalls of the frame, **602**, **604**, **606**, and **608**, makes the X-gaps or Y-gaps effectively larger for a given rotation angle, and therefore will not provide as much shock protection for the T-shaped hinges, **612** and **614**. In a preferred embodiment, the degree of taper of the mirror collection plate **610** or the sidewalls of the frame, **602**, **604**, **606**, and **608** is about 54.7E.

In a preferred embodiment, the release etching process for the mirror collection plate **610** and the etch for the T-shaped hinges, **612** and **614**, are decoupled. In an exemplary embodiment, the T-shaped hinge etch is only 10-microns deep and the mirror collection plate release etch depth is 200 microns. If the etches were done concurrently, the hinges, **612** and **614**, would be subjected to an additional 190-microns of etching which can lead to lateral undercutting, backside etching, and sidewall taper which affects the shock robustness of the hinges, **612** and **614**.

Furthermore, since the mirror collection plate **610** is not protected by the top/bottom cap wafers prior to gold-bonding of the mirror wafer **210** to the top/bottom caps, **205** and **215**, when the mirror collection plate **610** is DRIE dry-etch released, the mirror collection plates **610** are fragile and are free to move in X, Y, Z, and theta. Consequently, the handling of the released mirror collection plate wafers has a critical impact on yield. Also, there is always the possibility of having some "defective" mirrors **210** whose hinges, **612** and **614**, are compromised so that they cannot support the mirror collection plate **610** after the DRIE dry etch release process.

As illustrated in **FIGS. 21a** and **21b**, a merged mask DRIE process is preferably used to micromachine the T-shaped hinges, **612** and **614**, and release the mirror collection plate **610**. The merged mask DRIE process

preferably includes a composite silicon dioxide and photoresist mask that defines various etching regions for a 2-phase DRIE dry etch process. In a preferred embodiment, the exposed silicon dioxide mask is stripped prior to the second phase of the DRIE dry etch process. In a preferred embodiment, the mirror collection plate release etch is defined in photoresist, and the hinge release areas are protected by a silicon dioxide mask. In an exemplary embodiment, the first phase of the DRIE dry etch process, etches the mirror collection plate release lanes to a 190-micron depth. In a preferred embodiment, the silicon dioxide mask is then selectively removed by a wet etch. In an exemplary embodiment, the second phase of the DRIE dry etch process utilizes a 10-micron deep etch to fully release the mirror collection plate **610** and to also release the T-shaped hinges, **612** and **614**. The merged mask DRIE dry etch process de-couples the deep mirror collection plate release etch from the shallow T-shaped hinge release etch. This optimally permits the two etch processes to be individually optimized for near-vertical sidewall profile, minimal undercutting, and no backside hinge etching.

In an alternative embodiment, the mirror collection plate **610** is protected after the release etching process through the attachment of a temporary backing wafer that provides the mirror collection plate **610** with structural support and also catches any defective mirror collection plates.

In an alternative embodiment, the mirror collection plate **610** is protected after the release etching process by using the bottom cap **215** wafer as a backing wafer. In a preferred embodiment, the bottom cap **215** wafer is gold bonded to the mirror **210** wafer prior to the DRIE dry etch process. In an alternative embodiment, during the DRIE dry etch process, the bottom cap **215** provides structural support for the mirror collection plate **610** and the beams, **1035**, **1040**, **1045**, and **1050**, catch any defective mirror collection plates **610**, preventing them from being left inside the etch chamber. In a preferred embodiment, the top cap **205** is then gold bonded to mirror wafer/bottom cap wafer stack after the DRIE dry etch process.

The fabrication process for the mirror assembly **110** preferably utilizes one or more of the following processes: merged mask KOH wet etching, merged mask DRIE dry etching, gold eutectic bonding of cap wafers to mirror wafer, and wafer-level conductive-epoxy bonding of the ceramic wafer to the mirror wafer-stack. The focus of the process modules and the overall fabrication process is improved manufacturability and yield for reduced production prices.

In a preferred embodiment, the merged-mask DRIE dry etching process further incorporates one or more manufacturing options for handling the mirror **210** during fabrication.

In an alternative embodiment, the mirror wafers **210** are attached to a temporary backing wafer for merged-mask DRIE dry etch processing. The backing wafer catches any "defective" mirror collection plate due to automated wafer handling. After merged-mask DRIE dry etching and removal of the backing wafer, both caps, **205** and **215**, are then be bonded to the mirror wafer **210** with one gold-bonding step.

In another alternative embodiment, the mirror collection plate **610** is bonded to the bottom cap wafer **215** prior to the merged-mask DRIE etching process. The bottom cap **215** catches any defective mirror collection plates **610** during the merged-mask DRIE dry etching process and, therefore, acts as an inherent backing wafer. After the completion of the merged-mask DRIE dry etching process, the top cap **205** is gold-bonded to the composite mirror/bottom cap wafer stack.

The ceramic base wafer process **2010** preferably provides the base member **220**. In a preferred embodiment, the base member **220** is fabricated using conventional ceramic machining processes.

The top/bottom cap wafer process **2015** preferably provides the top cap **205** and bottom cap **215**. As illustrated in FIG. 33, the top/bottom cap wafer process **2015** preferably includes the steps of: (1) provide 400 micron thick silicon wafers with pad layers of silicon dioxide and layers of silicon nitride on both sides in step **3305**, (2) photolithography of the front sides of the silicon

wafers for the central cavities in step **3310**, (3) etch the exposed portions of the layers of silicon nitride and pad layers of silicon dioxide on the front sides of the silicon wafers in step **3315**, (4) thin etch of the exposed areas of silicon on the front sides of the silicon wafers in step **3320**, (5) grow field layers of silicon dioxide onto the thin etched portions of the front sides of the silicon wafers in step **3325**, (6) photolithography of the front sides of the silicon wafers for the travel stops in step **3330**, (7) etch the exposed portions of the field layers of silicon dioxide on the front sides of the silicon wafers in step **3335**, (8) photolithography of the back sides of the silicon wafers for the travel stops in step **3340**, (9) etch the exposed portions of the pad layers of silicon dioxide and layers of silicon nitride on the back sides of the silicon wafers in step **3345**, (10) KOH etch the exposed silicon on both sides of the silicon wafers to depth of 150 microns in step **3350**, (11) etch the exposed field layers of silicon dioxide on both sides of the silicon wafers in step **3355**, (12) KOH etch exposed portions of silicon on both sides of the silicon wafers to a depth of 50 microns in step **3360**, (13) strip the layers of silicon nitride on both side of the silicon wafers in step **3365**, (14) etch the exposed layers of silicon dioxide on both sides of the silicon wafers in step **3370**, (15) deposit a layer of gold on the front side of the bottom cap in step **3375**, and (16) deposit a layer of gold on the backside of the bottom cap in step **3380**.

As illustrated in **FIG. 34**, in process step **3305**, silicon wafers **3405** are provided having a frontside **3405a** and a backside **3405b**. In a preferred embodiment, the silicon wafers **3405** comprise 400 micron thick wafers of silicon. In process step **3305**, pad layers, **3410a** and **3410b**, of silicon dioxide are then grown on both sides of the silicon wafers **3405**.

In a preferred embodiment, the starting material specifications for the top/bottom cap and mirror wafers are double-side polish, thickness control of 400 ± 7.5 microns, and a doping concentration of 10^{18} cm^{-3} of boron. For the mirror wafers, the starting wafers preferably are deposited with 7-microns of heavily boron-doped epi on the frontside and the wafers are then polished back to approximately the 400-micron starting thickness. In a preferred embodiment,

the electrical connection from the released mirror collection plate **610** to the ceramic base member **220** is through the thickness of the mirror wafer and the bottom cap wafer. The high doping of these wafers optimally provides a good, ohmic electrical contact between the mirror/bottom cap and bottom cap/base member metallization. In an alternative embodiment, double-side implanting of the bottom cap **220** and backside implanting of the mirror **210** are provided.

The pad layers, **3410a** and **3410b**, of silicon dioxide may be grown using any number of conventional commercially available processes. In a preferred embodiment, the layers, **3410a** and **3410b**, of silicon dioxide are grown by the process of thermal oxidation. The layers, **3410a** and **3410b**, of silicon dioxide may be grown to depths ranging, for example, from about 300 to 10000 Angstroms. In a preferred embodiment, the layers, **3410a** and **3410b**, of silicon dioxide are grown to depths ranging from 300 to 600 Angstroms. In process step **3305**, layers, **3415a** and **3415b**, of silicon nitride are then applied onto the layers, **3410a** and **3410b**, of silicon dioxide. The layers, **3415a** and **3415b**, of silicon nitride may be applied using any number of conventional commercially available processes. In a preferred embodiment, the layers, **3415a** and **3415b**, of silicon nitride are applied by the process of chemical vapor deposition. The layers, **3415a** and **3415b**, of silicon nitride may be applied to depths ranging, for example, from about 0.1 to 2 microns. In a preferred embodiment, the layers, **3415a** and **3415b**, of silicon nitride are applied to depths ranging from about 0.12 to 0.15 microns.

As illustrated in **FIG. 35a**, in process steps **3310** and **3315**, the pad layers **3410a** of silicon dioxide and the layers **3415a** of silicon nitride on the front sides **3405a** of the silicon wafers **3405** are patterned and etched to provide subsequent definition for the central cavities of the top and bottom caps.

As illustrated in **FIG. 35b**, in process steps **3320** and **3325**, the exposed portions of silicon on the front sides **3405a** of the silicon wafers **3405** are then thin etched. In a preferred embodiment, the depth of the thin etch ranges from about 0.5 to 1.5 microns in order to facilitate the growth of the field layers of silicon dioxide. Field layers **3410c** of silicon dioxide are then grown onto the

exposed areas of silicon on the front sides **3405a** of the silicon wafers **3405**. The thickness of the field layers **3410c** of the silicon dioxide is preferably greater than or equal to the combined thickness of the pad layers **3410a** of silicon dioxide and the layers **3410b** of the silicon nitride.

5 As illustrated in **FIG. 36**, in process steps **3330** and **3335**, the exposed portions of the field layer **3410c** of silicon dioxide on the front sides **3405a** of the silicon wafers **3405** are patterned and etched to provide subsequent definition for the travel stops of the top and bottom caps.

10 As illustrated in **FIGS. 37** and **38**, in process steps **3340** and **3345**, the pad layers **3415a** of silicon dioxide and layers **3415b** of silicon nitride on the back sides **3405b** of the silicon wafers **3405** are patterned to provide subsequent definition for the travel stops and central cavities of the top and bottom caps.

15 As illustrated in **FIGS. 39, 39a, 39b** and **39c**, in process step **3350**, the exposed portions of silicon on both sides of the silicon wafers **3405** are KOH etched to a depth of 150 microns. This defines the cavities and travel stops for the top and bottom caps. This KOH etching process preferably results in a central membrane of silicon having a thickness of about 100 microns.

20 As illustrated in **FIGS. 40** and **41**, in process step **3355**, the exposed portions of the pad layers **3410a** and field layers **3410c** of silicon dioxide on both sides of the silicon wafers **3405** are etched. This etching process permits the subsequent recessing of the top surfaces of the travel stops.

25 As illustrated in **FIGS. 42, 42a, 42b**, and **42c**, in process step **3360**, the exposed portions of silicon on both sides of the silicon wafers **3405** are KOH etched to a depth of about 50 microns. This provides final definition for the cavities and travel stops of the top and bottom caps. It further preferably recesses the top surfaces of the travel stops by about 50 microns.

30 As illustrated in **FIGS. 43, 43a, 43b** and **43c**, in process steps **3365, 3370, 3375**, and **3380**, the remaining portions of the layers, **3410a, 3410b, 3415a** and **3415b**, of silicon dioxide and silicon nitride are stripped from both sides of the silicon wafers **3405**. For the top cap **205**, this preferably completes

the manufacturing process. For the bottom cap **215**, layers, **4305a** and **4305b**, of gold are then applied to the top and bottom surfaces of the silicon wafer **3405**. In a preferred embodiment, the layers, **4305a** and **4305b**, of gold are bonded to the silicon substrate **3405** using intermediate layers of titanium.

5 In an alternative embodiment, the processing of the bottom cap **215** includes modified masking steps to provide the beams **1035**, **1040**, **1045**, and **1050**. For example, these may be provided by modifying process steps **3330** and **3340** to include provision for the beams, **1035**, **1040**, **1045**, and **1050**.

10 As illustrated in **FIG. 33**, process steps **3305** to **3370** provide a wet KOH LOCOS merged-mask micro-machining process. More generally, process steps **3305** to **3370** provide a merged-mask micro-machining process including the steps of: (1) providing a silicon substrate; (2) successively applying a plurality of masking layers onto the silicon substrate; (3) successively patterning the layers of masking material; (4) thin etching the exposed regions of silicon; (5) growing a field layer of silicon dioxide; (6) patterning the field layer of silicon dioxide; (6) etching the exposed portions of the silicon substrate; (7) etching the exposed portions of the field layer of silicon dioxide; and (8) etching the exposed portions of the silicon substrate.

15 The gold bonding of cap wafers to mirror process **2020** preferably provides a sub-assembly including the top cap **205**, the mirror **210** and the bottom cap **215**. Referring to **FIG. 43d**, in a preferred embodiment, the gold bonding comprises a gold eutectic wafer bonding process **4350** that includes the steps of: coating one mating wafer surface with a layer of gold, while the mating surface of the other wafer comprises bare silicon in step **4355**, placing the mating surfaces of the wafers in intimate contact in step **4360**, compressing the mating surfaces together in step **4365**, and heating the wafers in step **4370** above the gold/eutectic temperature. In a preferred embodiment, the process **4350** provides a hermetic bond between the wafers.

20 In a preferred embodiment, to minimize the number of gold deposition steps (reduce cost) and to avoid deep cavity lithography to define metallization on the backside of the mirror (yield), both top/bottom cap, **205** and **215**, wafers

30

are bonded to the mirror **210** using gold eutectic bonding. For gold eutectic wafer bonding, one wafer surface is coated with gold while the wafer surface is bare silicon, and the wafers are placed into contact with a large force applied and heated beyond the gold/silicon eutectic point. The gold diffuses into the bare silicon wafer and forms a strong, hermetic wafer bond.

The conductive-epoxy bonding of the ceramic base wafer **220** to the mirror wafer stack process **2025** preferably provides an assembly including the top cap **205**, the mirror **210**, the bottom cap **215**, and the base member **220**. In a preferred embodiment, the conductive-epoxy bonding process includes the use of a conventional conductive epoxy preform. In a preferred embodiment, the metal ring **1340** around the perimeter of the base member **220**, in combination with the conductive-epoxy bonding of the base member **220** to the bottom cap **215**, preferably provides electrical contact to the bottom cap **215**. The wafer bonding process preferably allows the bottom cap **215** to be in direct electrical contact with the mirror collection plate **610**. Consequently, the mirror collection plate **610** preferably can be electrically accessed, controlled, and monitored using the base member **220**. The electrode drive pad and mirror contact metallization, **1310a**, **1315a**, and **1340**, on the base member **220** are preferably further connected to electrical contact pads on the backside of the base member **220**, utilizing conventional thick-film through-hole via technology, which effectively makes the mirror assembly **110** a surface-mount component.

The dicing of the packaged mirror wafer stack **2030** preferably provides the mirror assembly **110**. In a preferred embodiment, the mirror **210** is gold bonded to the top cap **205** and the bottom cap **215**. This gold-bonded sub-assembly is then preferably bonded to the ceramic base member **220**. The gold-bonded sub-assembly, including the top cap **205**, mirror **210** and bottom cap **215**, is preferably bonded to the ceramic base member **220** using a wafer-scale conductive-epoxy preform. In a preferred embodiment, the 4-wafer stacked sub-assembly including the top cap **205**, mirror **210**, bottom cap **215** and base member **220**, defines a packaged mirror wafer stack. In a preferred embodiment, wafer-size sheets of dicing tape are then applied to both the top

cap **205** and to the bottom cap **215** to hermetically protect the 4-wafer stack from the dicing saw water. The 4-wafer stack is then diced using a conventional automated dicing saw into individual packaged mirror dies. The tape is then removed.

5 The testing of the packaged mirror die process **2035** preferably tests the electrical, optical, and mechanical performance of the mirror assembly **110**.

10 A mirror assembly has been described that preferably includes a half-thickness micromirror, silicon T-shaped hinges, and wafer-level micromachined silicon top/bottom caps. The mirror assembly preferably includes the following technical elements: (1) design for reduced cost and improved manufacturability; (2) improved mirror position accuracy (i.e., combination of “droop” and pointing accuracy); (3) robust shock protection for more demanding shock specification; and (4) capping (packaging) of the mirror while addressing laser clipping issues.

15 The manufacturing process for the mirror assembly **110** includes a number of significant manufacturing cost reductions.

20 First, the micromachined silicon cap wafers, **205** and **215**, significantly reduce the material costs of the packaging, as compared with conventional packaging. For example, the top/bottom caps, **205** and **215**, are bonded at the wafer level, which is a batch process. This is more cost-effective than the conventional die level (piece part) assembly process.

25 Second, the half-thickness mirror collection plate **601** is preferably achieved through a balanced combination of wet etching (inexpensive) and dry etching (expensive) techniques. In an exemplary embodiment, the silicon-hinge/half-thickness mirror process typically provides a seventy-two percent (72%) reduction in DRIE etch time compared to a full-thickness mirror process.

30 Third, die size is minimized as much as possible by minimizing the frame area of the mirror. Also, the use of double-side wet etching of the top/bottom cap wafers minimizes the sidewall taper which, in an exemplary embodiment, resulted in a twenty percent (20%) reduction in die size while still optimally addressing the top cap laser clipping issues.

The mirror assembly **110** also provides a number of advantages with regarding to positional accuracy and shock survivability.

For example, in several exemplary bar code scanner applications, the rotational position accuracy of the laser beam may be required to be within 1.3° when the mirror is subject to an across-the-hinge, self-induced gravity torque, Torque = $T = mg \cdot h/2$ (where mg = mirror self-weight, h = mirror thickness). The mirror collection plate **610** position accuracy is composed of the pointing accuracy and “droop” components. Since the torsional spring constant K_r and the mass of the mirror collection plate **610** is predetermined by the mirror resonant frequency F and mirror size, the tilt angle θ of the mirror collection plate **610** is also determined by the relation $\theta = T/K_r$. In an exemplary embodiment, the tilt angle of the mirror collection plate **610** is greater than 1.3° for a full-thickness mirror. The positional accuracy of the mirror collection plate **610** accuracy is improved, in an exemplary embodiment, (i.e., reduction in mirror tilt angle) by increasing the resonant frequency specification to 50 Hz since this increases the torsional spring constant. The half-thickness mirror collection plate design and backside mirror collection plate cavity etch, by reducing the mirror collection plate self weight about the T-shaped hinges, **612** and **614**, allow the exemplary position accuracy specification to be met.

As shown in **FIG 19**, in an exemplary embodiment, an incident laser shines on the mirror collection plate surface at a 45° angle along line A and reflects back to space along line B. In an exemplary embodiment, the laser beam has a finite spot size that is about 500-microns wide and 1000-microns long. The 500-micron wide laser beam is centered along line A and B. In an exemplary embodiment, the mirror collection plate **610** is required to scan $\pm 10^\circ$. In this exemplary embodiment, the reflected laser beam scan range is bounded by B' and B". To avoid laser clipping, it is required that there is no obstruction along the light path. The use of double-side wet etching of the top/bottom caps **205** and **215** provides the double-side tapers in the interior edges of the top/bottom caps, **205** and **210**, that minimize laser clipping and provide “cap capture” shock protection. Furthermore, the “cap capture”

preferably accommodates variations in the x-direction gap ranging from 10 to 100 microns when the mirror collection plate **610** is rotated out of plane. In this manner, the “cap capture” preferably provides shock protection up to about 2000g/1.1 ms half sine wave input. Finally, the left and right rim cut-outs, **330** and **340**, of the top cap **205** preferably minimize the obstruction path along the light path and the clipping effects.

In an exemplary embodiment, to avoid right side clipping, a clear optical pathway is provided in the column space defined by $B'' \pm 250$ microns, which is not a problem for a perfect alignment of the laser beam to the mirror collection plate **610**. The clipping problem typically arises when there is a large misalignment from the manual scan engine assembly operation, shifting the laser source rightwards or leftwards from the mirror centerline. As illustrated in **FIG. 19**, the right most line could be line B''' which is parallel to B'' . Intersecting B''' with the plane of the mirror collection plate **610**, results in a clipping distance of 600 microns. Consequently, the usable portion of the mirror collection plate **610** on the right half is 1250 microns (50% of the 2.5-mm mirror size) - 600 microns (clipping distance) = 650 microns. The allowable misalignment to the right is 650 microns - 250 microns (50% laser spot size) = 400 microns (16 mils). Similarly, in an exemplary embodiment, the clipping on the left side is 240 microns and allowable misalignment to the left can be as large as 760 microns (30 mils). If the laser/mirror alignment is better than 16 mils, then there is no clipping issue. Furthermore, if the position accuracy of the laser is improved, it provides an opportunity to considerably reduce the mirror die size, since the collection area can be reduced and there would be a corresponding reduction in the left/right cap rim cuts. It is understood that this linear position accuracy is coupled with angular position accuracy of the light source at 45° . For example, if the mounting angle happened to be 55° , laser clipping would be much worse.

In an exemplary embodiment, the top cap wafer travel-stop fingers, **310** and **320**, overshadow the mirror collection plate **610** by 300 microns in the y-direction. In an exemplary embodiment, the minimum overlap required for the

travel stop fingers, **310** and **320**, to function as Z-direction travel stops. Therefore, in an exemplary embodiment, the usable mirror collection plate area is 1250 microns (50% of the 2.5-mm mirror size) - 300 microns (clipping distance) = 950 microns and the allowable misalignment is 950 microns - 500 microns (50% of laser spot size) = 450 microns (18 mils).

One method for alleviating the laser clipping effect is to mount the laser source at an angle of less than 45°. In several exemplary embodiments, as illustrated in Table 1, the relationship between the laser mounting angle and the clipping length resulted in the following:

Table 1 Mounting Angle and Clipping Length Relationship

Mounting Angle	Clipping (microns)		Top Cap Rim Width (microns)	
	Left	Right	Left	Right
45	240	600	200	50
40	180	430	200	50
35	80	280	200	50
28	0	100	200	50
35	180	280	300	50
25	0	100	200	100

In an exemplary embodiment, the shock survivability specification for the mirror assembly **110** is a 2,000g, 1.0 milliseconds duration half-sine pulse. This correlates to a 6-foot drop with one hundred percent (100%) rebound. This is a demanding shock specification for a micromachined device. Furthermore, this exemplary specification is for the bare capped mirror assembly **110**, which does not take into account the inherent shock absorbency of a conventional external barcode scanner product package. In an exemplary embodiment, the mirror assembly **110** satisfies these stringent requirements using a variety of shock protection features. For example, as described above, the mirror collection plate **610** is preferably shock protected by the frame, **602**, **604**, **606** and **608**, for translational shock inputs in the plane of the mirror collection plate **610** in either the X-axis and/or Y-axis. As also described above, the travel-stop fingers, **310**, **320**, **1010**, and **1020** of the top/bottom caps, **205** and **215**,

preferably provide shock protection for the mirror collection plate **610** for out-of-plane translational shock inputs in the Z-direction. The most difficult shock protection to provide the mirror collection plate **610** is translational shock while the mirror collection plate **610** is rotated out-of-plane. For the exemplary 3-mm
5 x 3-mm mirror collection plate **610**, when the mirror collection plate **610** rotates more than 7.5° , the half-thickness mirror collection plate **610** is out of the plane of the frame, **602**, **604**, **606** and **608**, so the frame, **602**, **604**, **606**, and **608**, no longer provides shock protection for shock inputs with an X-axis component.

For this situation, the tapered inside perimeter walls of the top/bottom caps,
10 **205** and **215**, preferably capture the mirror collection plate **610** ("cap capture"). For any degree of rotation, the frame, **602**, **604**, **606**, and **608**, still provides shock protection for the Y-axis component of a shock input since some portion of the half-thickness mirror collection plate **610** will always be in the plane of the frame, **602**, **604**, **606** and **608** near the region of the T-shaped hinges. **612** and
15 **614**.

Furthermore, as illustrated in **FIG. 18**, the interior tapered walls of the top/bottom caps, **205** and **215**, provide the mirror collection plate **610** with shock protection for shock inputs with an X-axis component when the mirror collection plate **610** is rotated out of the plane of the frame, **602**, **604**, **606** and **608**. All
20 of these shock protection design features preferably provide the mirror collection plate **610** with three-dimensional shock protection and preferably permit the mirror collection plate to withstand a 2000g/1.0 mS half-sine shock input in any of the (3) directional axes, any combination of directional axes, and any combination of directional axes with the mirror collection plate rotated up
25 to $\pm 14^\circ$.

In a preferred embodiment, the primary purpose of the auxiliary travel-stop fingers, **616**, **618**, **620** and **622**, attached to the mirror collection plate **610** is to provide overswing protection for the mirror collection plate **610** during operation. In an exemplary embodiment, the shock protection capability of
30 these 200-micron thick travel stop fingers, **616**, **618**, **620** and **622**, is 2000g/0.5mS (for any combination of translational and rotational shock inputs).

The addition of the "cap capture" design preferably further enhances this shock protection to a level of 2000g/1.0mS shock specification. The auxiliary travel stops, **616**, **618**, **620** and **622**, also serve a secondary purpose, which is to provide some limited shock protection to the bare mirror wafers for the normal handling that occurs during the fabrication process - in particular, after the DRIE etch to release the mirror collection plate **610** and prior to the top/bottom cap wafer bonding process.

In an alternative embodiment, the mirror assembly **110** is further modified in a well known manner, for example, as disclosed in Marc Madou, Fundamentals Of Microfabrication, CRC Press, New York, NY, Volume A43, pp. 466, to provide a variable capacitance accelerometer.

In an alternative embodiment, the mirror assembly **110** is further modified in a well known manner, for example, as disclosed in Jan Soderkvist, Micromachined Gyroscopes, Sensor and Actuators, Vol. A43, 1994, pp. 65-71 and H. Hashimoto, C. Cabuz, K. Minami and M. Esashi, Silicon Resonant Angular Rate Sensor Using Electromagnetic Excitation And Capacitive Detection, Journal Of Micromechanics and Microengineering, Volume 5, No. 3, 1995, pp. 219-225 to provide a gyroscope.

Referring to **FIG. 44**, several alternative embodiments of a localized oxidation of silicon (LOCOS) merged-mask micro-machining processes **4400** are illustrated. In a preferred embodiment, one of these processes **4400** is used in forming at least a portion of the mirror **210** and/or the top and bottom caps, **205** and **215**. As illustrated in **FIG. 44**, the LOCOS merged-mask micro-machining process **4400** preferably includes the following process steps: (1) provide a silicon wafer in step **4405**, (2) (optionally) grow a buffer layer of silicon dioxide onto the surface of the silicon wafer in step **4410**, (3) apply a layer of silicon nitride onto the silicon wafer in step **4415**, (4) pattern the layer of silicon nitride in step **4420**, (5) (optionally) pattern the exposed portions of the buffer layer of silicon dioxide in step **4425**, (6) (optionally) thin etch the exposed portions of the surface of the silicon wafer in step **4430**, (7) grow field layers of silicon dioxide onto the portions of the silicon wafer not covered by the

patterned layer of silicon nitride in step **4435** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), (8) pattern the layer(s) of silicon dioxide in step **4440**, (9) etch the exposed portions of the silicon wafer in step **4445**, (10) remove the exposed portions of the layer(s) of silicon dioxide in step **4450**, (11) etch the exposed portions of the silicon wafer in step **4455**, and finally (12) remove the remaining portions of the layers of silicon dioxide and silicon nitride in step **4460**. In this manner, five alternative LOCOS merged-mask micro-machining process embodiments are provided for etching a substrate to multiple etch depths.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

In a preferred implementation of the processes **4400**, the same photoresist layer is used as a masking layer for all of the etching steps of steps **4420**, **4425**, **4430** and **4440** in order to minimize the amount of patterning operations. Alternatively, a separate photoresist patterning is used for each patterning in steps **4420**, **4425**, **4430** and **4440**.

In a preferred implementation of the processes **4400**, the etching of the exposed portions of the silicon wafer in steps **4445** and **4455** is provided using KOH.

Referring to **FIGS. 44** and **45a-45i**, the first embodiment of the LOCOS merged-mask micro-machining process, without the use of a buffer layer of silicon dioxide, includes the steps of: (1) providing a silicon wafer **4500** in step **4405** as illustrated in **FIG. 45a**, (2) applying a layer **4505** of silicon nitride onto the silicon wafer **4500** in step **4415** as illustrated in **FIG. 45b**, (3) patterning the layer **4505** of silicon nitride in step **4420** as illustrated in **FIG. 45c**, (4) growing

a field layer of silicon dioxide **4510** onto the portions of the silicon wafer **4500** not covered by the patterned layer **4505** of silicon nitride in step **4435** (the field layer of silicon dioxide is preferably at least as thick as the layer of silicon nitride) as illustrated in **FIG. 45d**, (5) patterning the layer **4510** of silicon dioxide in step **4440** as illustrated in **FIG. 45e**, (6) etching the exposed portions of the silicon wafer **4500** in step **4445** as illustrated in **FIG. 45f**, (7) removing the exposed portions of the layer **4510** of silicon dioxide in step **4450** as illustrated in **FIG. 45g**, (8) etching of the exposed portions of the silicon wafer **4500** in step **4455** as illustrated in **FIG. 45h**, and finally (9) removing the remaining portions of the layers, **4505** and **4510**, of silicon dioxide and silicon nitride in step **4460** as illustrated in **FIG. 45i**.

In a preferred implementation of the first embodiment of the LOCOS merged-mask micro-machining process **4400**, the following process parameters are employed: thickness of layer **4505** of silicon nitride ranging from about 0.1 to 2.0 microns, and the thickness of layer **4510** of silicon dioxide ranging from about 0.2 to 3 microns.

Referring to **FIGS. 44** and **46a-46j**, a second embodiment of the LOCOS merged-mask micro-machining process, without the use of a buffer layer of silicon dioxide but with a thin etch of the exposed portions of the silicon wafer, includes the steps of (1) providing a silicon wafer **4600** in step **4405** as illustrated in **FIG. 46a**, (2) applying a layer **4605** of silicon nitride onto the silicon wafer **4600** in step **4415** as illustrated in **FIG. 46b**, (3) patterning the layer **4605** of silicon nitride in step **4420** as illustrated in **FIG. 46c**, (4) thin etching the exposed portions of the surface of the silicon wafer **4600** in step **4430** as illustrated in **FIG. 46d**, (5) growing a field layer **4610** of silicon dioxide onto the portions of the silicon wafer **4600** not covered by the patterned layer of silicon nitride **4605** in step **4435** (the layer **4610** of silicon dioxide is preferably at least as thick as the layer **4605** of silicon nitride) as illustrated in **FIG. 46e**, (6) patterning the layer **4610** of silicon dioxide in step **4440** as illustrated in **FIG. 46f**, (7) etching the exposed portions of the silicon wafer **4600** in step **4445** as illustrated in **FIG. 46g**, (8) removing the exposed portions of the layer **4610** of

silicon dioxide in step **4450** as illustrated in **FIG. 46h**, (9) etching of the exposed portions of the silicon wafer **4600** in step **4455** as illustrated in **FIG. 46i**, and finally (10) removing the remaining portions of the layers, **4605** and **4610**, of silicon dioxide and silicon nitride in step **4460** as illustrated in **FIG. 46j**.

5 In a preferred implementation of the second embodiment of the LOCOS merged-mask micro-machining process **4400**, the following process parameters are employed: thickness of layer **4605** of silicon nitride ranging from about 0.1 to 2.0 microns, depth of the thin etch of the exposed portions of the silicon wafer **4600** ranging from about 0.5 to 1 microns, thickness of layer **4610** of
10 silicon dioxide ranging from about 0.2 to 3 microns.

Referring to **FIGS. 44** and **47a-47j**, a third embodiment of the LOCOS merged-mask micro-machining process, with a buffer layer of silicon dioxide that is not patterned separately, includes the steps of: (1) providing a silicon wafer **4700** in step **4405** as illustrated in **FIG. 47a**, (2) growing a buffer layer
15 **4705** of silicon dioxide onto the surface of the silicon wafer **4700** in step **4410** as illustrated in **FIG. 47b**, (3) applying a layer **4710** of silicon nitride onto the silicon wafer **4700** in step **4415** as illustrated in **FIG. 47c**, (4) patterning the layer **4710** of silicon nitride in step **4420** as illustrated in **FIG. 47d**, (5) growing a field layer **4715** of silicon dioxide onto the portions of the silicon wafer **4700** not
20 covered by the patterned layer of silicon nitride in step **4435** (the layer of silicon dioxide **4715** is preferably at least as thick as the combined thicknesses of the layer **4710** of silicon nitride and the buffer layer **4705** of silicon dioxide) as illustrated in **FIG. 47e**, (6) patterning the layers, **4705** and **4715**, of silicon dioxide in step **4440** as illustrated in **FIG. 47f**, (7) etching the exposed portions
25 of the silicon wafer **4700** in step **4445** as illustrated in **FIG. 47g**, (8) removing the exposed portions of the layers, **4705** and **4715**, of silicon dioxide in step **4450** as illustrated in **FIG. 47h**, (9) etching of the exposed portions of the silicon wafer **4700** in step **4455** as illustrated in **FIG. 47i**, and finally (10) removing the remaining portions of the layers, **4705**, **4710** and **4715**, of silicon dioxide and
30 silicon nitride in step **4460** as illustrated in **FIG. 47j**.

In a preferred implementation of the third embodiment of the LOCOS merged-mask micro-machining process **4400**, the following process parameters are employed: thickness of the buffer layer **4705** of silicon dioxide ranging from about 0.03 to 1 microns, thickness of layer **4710** of silicon nitride ranging from about 0.1 to 2 microns, thickness of layer **4715** of silicon dioxide ranging from about 0.2 to 3 microns.

Referring to **FIGS. 44** and **48a-48k**, a fourth embodiment of the LOCOS merged-mask micro-machining process, with a buffer layer of silicon dioxide that is separately patterned, includes the steps of: (1) providing a silicon wafer **4800** in step **4405** as illustrated in **FIG. 48a**, (2) growing a buffer layer **4805** of silicon dioxide onto the surface of the silicon wafer **4800** in step **4410** as illustrated in **FIG. 48b**, (3) applying a layer **4810** of silicon nitride onto the silicon wafer **4800** in step **4415** as illustrated in **FIG. 48c**, (4) patterning the layer **4810** of silicon nitride in step **4420** as illustrated in **FIG. 48d**, (5) patterning the exposed portions of the buffer layer **4805** of silicon dioxide in step **4425** as illustrated in **FIG. 48e**, (6) growing a field layer **4815** of silicon dioxide onto the portions of the silicon wafer **4800** not covered by the patterned layer **4810** of silicon nitride in step **4435** (the layer **4815** of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer **4810** of silicon nitride and the buffer layer **4805** of silicon dioxide) as illustrated in **FIG. 48f**, (7) patterning the layers, **4805** and **4815**, of silicon dioxide in step **4440** as illustrated in **FIG. 48g**, (8) etching the exposed portions of the silicon wafer **4800** in step **4445** as illustrated in **FIG. 48h**, (9) removing the exposed portions of the layers, **4805** and **4815**, of silicon dioxide in step **4450** as illustrated in **FIG. 48i**, (10) etching of the exposed portions of the silicon wafer **4800** in step **4455** as illustrated in **FIG. 48j**, and finally (11) removing the remaining portions of the layers, **4805**, **4810** and **4815**, of silicon dioxide and silicon nitride in step **4460** as illustrated in **FIG. 48k**.

In a preferred implementation of the fourth embodiment of the LOCOS merged-mask micro-machining process **4400**, the following process parameters are employed: thickness of the buffer layer **4805** of silicon dioxide ranging from

about 0.03 to 1 microns, thickness of layer **4810** of silicon nitride ranging from about 0.1 to 1.8 microns, thickness of layer **4815** of silicon dioxide ranging from about 0.2 to 3.0 microns.

5 In a preferred implementation of the fourth embodiment of the LOCOS merged-mask micro-machining process **4400**, the patterned layer **4810** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **4805** of silicon dioxide in step **4425**.

10 Referring to **FIGS. 44** and **49a-49l**, a fifth embodiment of the LOCOS merged-mask micro-machining process, with a buffer layer of silicon dioxide that is separately patterned and a thin etch of the silicon wafer, includes the steps of: (1) providing a silicon wafer **4900** in step **4405** as illustrated in **FIG. 49a**, (2) growing a buffer layer **4905** of silicon dioxide onto the surface of the silicon wafer **4900** in step **4410** as illustrated in **FIG. 49b**, (3) applying a layer **4910** of silicon nitride onto the silicon wafer **4900** in step **4415** as illustrated in **FIG. 49c**, (4) patterning the layer **4910** of silicon nitride in step **4420** as illustrated in **FIG. 49d**, (5) patterning the exposed portions of the buffer layer **4905** of silicon dioxide in step **4425** as illustrated in **FIG. 49e**, (6) thin etching the exposed portions of the surface of the silicon wafer **4900** in step **4430** as illustrated in **FIG. 49f**, (7) growing a field layer **4915** of silicon dioxide onto the portions of the silicon wafer **4900** not covered by the patterned layer **4910** of silicon nitride in step **4435** (the layer **4915** of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer **4910** of silicon nitride and the buffer layer **4905** of silicon dioxide) as illustrated in **FIG. 49g**, (8) patterning the layers, **4905** and **4915**, of silicon dioxide in step **4440** as illustrated in **FIG. 49h**, (9) etching the exposed portions of the silicon wafer **4900** in step **4445** as illustrated in **FIG. 49i**, (10) removing the exposed portions of the layers, **4905** and **4915**, of silicon dioxide in step **4450** as illustrated in **FIG. 49j**, (11) etching the exposed portions of the silicon wafer **4900** in step **4455** as illustrated in **FIG. 49k**, and finally (12) removing the remaining portions of the layers, **4905**, **4910** and **4915**, of silicon dioxide and silicon nitride in step **4460** as illustrated in **FIG. 49l**.

In a preferred implementation of the fifth embodiment of the LOCOS merged-mask micro-machining process **4400**, the following process parameters are employed: thickness of the buffer layer **4905** of silicon dioxide ranging from about 0.03 to 1 microns, thickness of layer **4910** of silicon nitride ranging from about 0.1 to 2.0 microns, depth of the thin etch of the exposed portions of the silicon wafer **4900** ranging from about 0.5 to 1 microns, and the thickness of field layer **4915** of silicon dioxide ranging from about 0.2 to 3.0 microns.

In a preferred implementation of the fifth embodiment of the LOCOS merged-mask micro-machining process **4400**, the patterned layer **4910** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **4905** of silicon dioxide in step **4425**.

Referring to **FIG. 50**, several alternative embodiments of a localized oxidation of silicon (LOCOS) merged-mask micro-machining processes **5000** including multiple etch depths are illustrated. In a preferred embodiment, one of these processes **5000** is used in forming at least a portion of the mirror **210** and/or the top and bottom caps, **205** and **215**. As illustrated in **FIG. 50**, the LOCOS merged-mask micro-machining process **5000** preferably includes the following process steps: (1) provide a silicon wafer in step **5005**, (2) (optionally) grow a buffer layer of silicon dioxide onto the surface of the silicon wafer in step **5010**, (3) apply a layer of silicon nitride onto the silicon wafer in step **5015**, (4) pattern the layer of silicon nitride in step **5020**, (5) (optionally) pattern the exposed portions of the buffer layer of silicon dioxide in step **5025**, (6) (optionally) thin etch the exposed portions of the surface of the silicon wafer in step **5030**, (7) grow field layers of silicon dioxide onto the portions of the silicon wafer not covered by the patterned layer of silicon nitride in step **5035** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), (8) pattern a fraction of the thickness of the layer(s) of silicon dioxide in step **5040**, (9) repeat the patterning of the thickness of the layer(s) of silicon dioxide for a predetermined number of times in step **5045**, (10) etch the exposed portions of the silicon wafer in step **5050**, (11) remove a portion of the

exposed portions of the layer(s) of silicon dioxide in step **5055**, (12) etch a portion of the exposed portions of the silicon wafer in step **5060**, and finally (13) repeat the oxide etching and silicon etching sequence a predetermined number of times in step **5065**. In this manner, five alternative LOCOS merged-mask micro-machining process embodiments are provided for etching a substrate to multiple etch depths.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

In a preferred implementation of the processes **5000**, the etching of the exposed portions of the silicon wafer in steps **5050** and **5060** is provided using KOH.

Referring to **FIGS. 50** and **51a-51k**, the first embodiment of the LOCOS merged-mask micro-machining process **5000**, without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **5100** in step **5005**, as illustrated in **FIG. 51a**, (2) apply a layer **5105** of silicon nitride onto the silicon wafer in step **5015**, as illustrated in **FIG. 51b**, (3) pattern the layer **5105** of silicon nitride in step **5020**, as illustrated in **FIG. 51c**, (4) grow a field layer **5110** of silicon dioxide onto the portions of the silicon wafer **5100** not covered by the patterned layer **5105** of silicon nitride in step **5035** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 51d**, (5) repeatedly pattern the layer **5110** of silicon dioxide in steps **5040** and **5045**, as illustrated in **FIG. 51e**, (6) etch the exposed portions of the silicon wafer **5100** in step **5050**, as illustrated in **FIG. 51f**, (7) remove a portion of the exposed portions of the layer **5110** of silicon dioxide in step **5055**, as illustrated in **FIG. 51g**, (8) etch a portion of the exposed portions of the

silicon wafer **5100** in step **5060**, as illustrated in **FIG. 51h**, (9) repeat the oxide etching and silicon etching sequence in step **5065**, as illustrated in **FIGS. 51i** and **51j**, and (10) remove the remaining portions of the layer **5105** of silicon nitride, as illustrated in **FIG. 51k**.

5 In a preferred implementation of the first embodiment of the LOCOS merged-mask micro-machining process **5100**, the following process parameters are employed: the thickness of layer **5105** of silicon nitride ranges from about 0.1 to 2.0 microns, and the thickness of layer **5110** of silicon dioxide ranges from about 0.2 to 3.0 microns.

10 Referring to **FIGS. 50** and **52a-52l**, a second embodiment of the LOCOS merged-mask micro-machining process **5000**, without the use of a buffer layer of silicon dioxide but with a thin etch of the exposed portions of the silicon wafer, includes the steps of: (1) provide a silicon wafer **5200** in step **5005**, as illustrated in **FIG. 52a**, (2) apply a layer **5205** of silicon nitride onto the silicon
15 wafer **5200** in step **5015**, as illustrated in **FIG. 52b**, (3) pattern the layer **5205** of silicon nitride in step **5020**, as illustrated in **FIG. 52c**, (4) thin etch the exposed portions of the silicon wafer **5200** in step **5030**, as illustrated in **FIG. 52d**, (5) grow a field layer **5210** of silicon dioxide onto the portions of the silicon wafer **5200** not covered by the patterned layer **5205** of silicon nitride in step
20 **5035** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 52e**, (6) repeatedly pattern the layer **5210** of silicon dioxide in steps **5040** and **5045**, as illustrated in **FIG. 52f**, (7) etch the exposed portions of the silicon wafer **5200** in step **5050**, as illustrated in **FIG. 52g**, (8) remove a portion of the exposed portions of the layer **5210** of silicon dioxide in step **5055**, as illustrated in **FIG. 52h**, (9) etch a portion of the exposed portions of the silicon wafer **5200** in step **5060**, as illustrated in **FIG. 52i**, (10) repeat the oxide etching and silicon etching sequence in step **5065**, as illustrated in **FIGS. 52j** and **52k**, and (10) remove the remaining portions of the
25 layer **5205** of silicon nitride, as illustrated in **FIG. 52l**.
30

In a preferred implementation of the second embodiment of the LOCOS merged-mask micro-machining process **5000**, the following process parameters are employed: the thickness of the layer **5205** of silicon nitride ranges from about 0.1 to 2.0 microns, the depth of the thin etch of the exposed portions of the silicon wafer **5200** ranges from about 0.5 to 1 microns, and the thickness of layer **5210** of silicon dioxide ranges from about 0.2 to 3.0 microns.

Referring to **FIGS. 50** and **53a-53l**, a third embodiment of the LOCOS merged-mask micro-machining process **5000**, with a buffer layer of silicon dioxide that is not patterned separately, includes the steps of: (1) provide a silicon wafer **5300** in step **5005**, as illustrated in **FIG. 53a**, (2) apply a buffer layer **5305** of silicon dioxide in step **5010**, as illustrated in **FIG. 53b**, (3) apply a layer **5310** of silicon nitride onto the silicon wafer **5300** in step **5015**, as illustrated in **FIG. 53c**, (4) pattern the layer **5310** of silicon nitride in step **5020**, as illustrated in **FIG. 53d**, (5) grow a field layer **5315** of silicon dioxide onto the portions of the silicon wafer **5300** not covered by the patterned layer **5310** of silicon nitride in step **5035** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 53e**, (6) repeatedly pattern the layers, **5305** and **5315**, of silicon dioxide in steps **5040** and **5045**, as illustrated in **FIG. 53f**, (7) etch the exposed portions of the silicon wafer **5300** in step **5050**, as illustrated in **FIG. 53g**, (8) remove a portion of the exposed portions of the layers, **5305** and **5315**, of silicon dioxide in step **5055**, as illustrated in **FIG. 53h**, (9) etch a portion of the exposed portions of the silicon wafer **5300** in step **5060**, as illustrated in **FIG. 53i**, (10) repeat the oxide etching and silicon etching sequence in step **5065**, as illustrated in **FIGS. 53j** and **53k**, and (10) remove the remaining portions of the layers, **5305** and **5310**, of silicon dioxide and silicon nitride, as illustrated in **FIG. 53l**.

In a preferred implementation of the third embodiment of the LOCOS merged-mask micro-machining process **5000**, the following process parameters are employed: the thickness of the buffer layer **5305** of silicon dioxide ranges from about 0.03 to 1.0 microns, the thickness of layer **5310** of silicon nitride

ranges from about 0.1 to 2.0 microns, and the thickness of layer **5315** of silicon dioxide ranges from about 0.2 to 3.0 microns.

In a preferred implementation of the third embodiment of the LOCOS merged-mask micro-machining process **5000**, the patterned layer **5310** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **5305** of silicon dioxide in step **5025**.

Referring to **FIGS. 50** and **54a-54m**, a fourth embodiment of the LOCOS merged-mask micro-machining process **5000**, with a buffer layer of silicon dioxide that is separately patterned, includes the steps of: (1) provide a silicon wafer **5400** in step **5005**, as illustrated in **FIG. 54a**, (2) apply a buffer layer **5405** of silicon dioxide in step **5010**, as illustrated in **FIG. 54b**, (3) apply a layer **5410** of silicon nitride onto the silicon wafer **5400** in step **5015**, as illustrated in **FIG. 54c**, (4) pattern the layer **5410** of silicon nitride in step **5020**, as illustrated in **FIG. 54d**, (5) pattern the buffer layer **5405** of silicon dioxide in step **5025**, as illustrated in **FIG. 54e**, (6) grow a field layer **5415** of silicon dioxide onto the portions of the silicon wafer **5400** not covered by the patterned layer **5410** of silicon nitride in step **5035** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 54f**, (7) repeatedly pattern the layers, **5405** and **5415**, of silicon dioxide in steps **5040** and **5045**, as illustrated in **FIG. 54g**, (8) etch the exposed portions of the silicon wafer **5400** in step **5050**, as illustrated in **FIG. 54h**, (9) remove a portion of the exposed portions of the layers, **5405** and **5415**, of silicon dioxide in step **5055**, as illustrated in **FIG. 54i**, (10) etch a portion of the exposed portions of the silicon wafer **5400** in step **5060**, as illustrated in **FIG. 54j**, (11) repeat the oxide etching and silicon etching sequence in step **5065**, as illustrated in **FIGS. 54k** and **54l**, and (12) remove the remaining portions of the layers, **5405** and **5410**, of silicon dioxide and silicon nitride, as illustrated in **FIG. 54m**.

In a preferred implementation of the fourth embodiment of the LOCOS merged-mask micro-machining process **5000**, the following process parameters are employed: the thickness of the buffer layer **5405** of silicon dioxide ranges

from about 0.03 to 1.0 microns, the thickness of layer **5410** of silicon nitride ranges from about 0.2 to 3.0 microns, and the thickness of layer **5415** of silicon dioxide ranges from about 0.2 to 3.0 microns.

5 In a preferred implementation of the fourth embodiment of the LOCOS merged-mask micro-machining process **5000**, the patterned layer **5410** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **5405** of silicon dioxide in step **5025**.

10 Referring to **FIGS. 50** and **55a-55n**, a fifth embodiment of the LOCOS merged-mask micro-machining process **5000**, with a buffer layer of silicon dioxide that is separately patterned and a thin etch of the silicon wafer, includes the steps of: (1) provide a silicon wafer **5500** in step **5005**, as illustrated in **FIG. 55a**, (2) apply a buffer layer **5505** of silicon dioxide in step **5010**, as illustrated in **FIG. 55b**, (3) apply a layer **5510** of silicon nitride onto the silicon wafer **5500** in step **5015**, as illustrated in **FIG. 55c**, (4) pattern the layer **5510** of silicon
15 nitride in step **5020**, as illustrated in **FIG. 55d**, (5) pattern the layer **5505** of silicon dioxide in step **5025**, as illustrated in **FIG. 55e**, (6) thin etch the exposed portions of the silicon wafer **5500** in step **5030**, as illustrated in **FIG. 55f**, (7) grow a field layer **5515** of silicon dioxide onto the portions of the silicon wafer **5500** not covered by the patterned layer **5510** of silicon nitride in step **5035** (the
20 field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 55g**, (8) repeatedly pattern the layers, **5505** and **5515**, of silicon dioxide in steps **5040** and **5045**, as illustrated in **FIG. 55h**, (9) etch the exposed portions of the silicon wafer **5500** in step **5050**, as illustrated in **FIG. 55i**, (10) remove a portion of the exposed portions of the layers, **5505**
25 and **5515**, of silicon dioxide in step **5055**, as illustrated in **FIG. 55j**, (11) etch a portion of the exposed portions of the silicon wafer **5500** in step **5060**, as illustrated in **FIG. 55k**, (12) repeat the oxide etching and silicon etching sequence in step **5065**, as illustrated in **FIGS. 55l** and **55m**, and (13) remove
30 the remaining portions of the layers, **5505** and **5510**, of silicon dioxide and silicon nitride, as illustrated in **FIG. 55n**.

In a preferred implementation of the fifth embodiment of the LOCOS merged-mask micro-machining process **5000**, the following process parameters are employed: the thickness of the buffer layer **5505** of silicon dioxide ranges from about 0.03 to 1.0 microns, the thickness of the layer **5510** of silicon nitride ranges from about 0.1 to 2.0 microns, the depth of the thin etch of the exposed portions of the silicon wafer **5500** ranges from about 0.5 to 1 microns, and the thickness of field layer **5515** of silicon dioxide ranges from about 0.2 to 3.0 microns.

In a preferred implementation of the fifth embodiment of the LOCOS merged-mask micro-machining process **5000**, the patterned layer **5510** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **5505** of silicon dioxide in step **5025**.

Referring to **FIGS. 56a** and **56b**, several alternative embodiments of localized oxidation of silicon (LOCOS) merged-mask micro-machining processes **5600** including the use of photoresist as an etching mask are illustrated. In a preferred embodiment, one of these processes **5600** is used in forming at least a portion of the mirror **210** and/or the top and bottom caps, **205** and **215**. As illustrated in **FIGS. 56a** and **56b**, the LOCOS merged-mask micro-machining process **5600** preferably includes the following process steps: (1) provide a silicon wafer in step **5602**, (2) (optionally) grow a buffer layer of silicon dioxide onto the surface of the silicon wafer in step **5604**, (3) apply a layer of silicon nitride onto the silicon wafer in step **5606**, (4) pattern the layer of silicon nitride in step **5608**, (5) (optionally) pattern the exposed portions of the buffer layer of silicon dioxide in step **5610**, (6) (optionally) thin etch the exposed portions of the surface of the silicon wafer in step **5612**, (7) grow field layers of silicon dioxide onto the portions of the silicon wafer not covered by the patterned layer of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), (8) pattern the layer(s) of silicon dioxide in step **5616**, (9) (optionally) etch the exposed portions of the silicon wafer using photoresist as an etch mask in step **5618**, (10) (optionally)

apply and pattern a layer of photoresist onto the silicon wafer in step **5620**, (11) (optionally) etch the exposed portions of the silicon wafer using a plasma or gaseous etchant in step **5622**, (12) (optionally) remove the exposed portions of the layer(s) of silicon dioxide in step **5624**, (13) (optionally) etch a portion of the exposed portions of the silicon wafer in step **5626**, (14) remove the layer of photoresist in step **5628**, (15) etch the exposed portions of the silicon wafer in step **5630**, (16) etch the exposed portions of the layers of silicon dioxide in step **5632**, and (17) etch the exposed portions of the silicon wafer in step **5634**. If the LOCOS merged-mask micro-machining processes **5600** are performed without using photoresist as an etching mask in step **5618**, then the process flow is identical to that illustrated in **FIG. 44**. Alternatively, if the LOCOS merged-mask micro-machining processes **5600** are performed using photoresist as an etching mask in step **5618**, then an additional thirty-five (35) alternative LOCOS merged-mask micro-machining process embodiments are provided for etching a substrate to multiple etch depths including the use of photoresist as an etching mask.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

In a preferred implementation of the processes **5600**, the etching of the exposed portions of the silicon wafer in steps **5630** and **5634** is provided using KOH.

In a preferred implementation of the processes **5600**, the etching of the exposed portions of the silicon wafer in steps **5622** and **5626** is provided using DRIE. In a preferred implementation of the processes **5600**, the etchings steps **5622** and **5626** provide sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 57a-57i**, the first embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **5700** in step **5602**, as illustrated in **FIG. 57a**,
5 (2) apply a layer of silicon nitride **5705** onto the silicon wafer **5700** in step **5606**, as illustrated in **FIG. 57b**, (3) pattern the layer **5705** of silicon nitride in step **5608**, as illustrated in **FIG. 57c**, (4) grow a field layer **5710** of silicon dioxide onto the portions of the silicon wafer **5700** not covered by the patterned layer **5705** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably
10 at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 57d**, (5) pattern the layer **5710** of silicon dioxide in step **5616**, as illustrated in **FIG. 57e**, (6) apply and pattern a layer **5715** of photoresist onto the silicon wafer **5700** in step **5620**, as illustrated in **FIG. 57f**, (7) etch the exposed portions of the silicon
15 wafer using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 57g**, (8) remove the layer of photoresist **5715** in step **5628**, as illustrated in **FIG. 57h**, (9) etch the exposed portions of the silicon wafer **5700** in step **5630**, as illustrated in **FIG. 57i**, (10) etch the exposed portions of the layer **5710** of silicon dioxide in step **5632**, as illustrated in **FIG. 57j**, (11) etch the exposed portions
20 of the silicon wafer **5700** in step **5634**, as illustrated in **FIG. 57k**, and (12) remove the remaining portions of the layer **5705** of silicon nitride, as illustrated in **FIG. 57l**.

In a preferred implementation of the first embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters
25 are employed: the thickness of layer **5705** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **5710** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **5715** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the first embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps
30

5622 and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 58a-58m**, the second embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **5800** in step **5602**, as illustrated in **FIG. 58a**, (2) apply a layer **5805** of silicon nitride onto the silicon wafer **5800** in step **5606**, as illustrated in **FIG. 58b**, (3) pattern the layer **5805** of silicon nitride in step **5608**, as illustrated in **FIG. 58c**, (4) grow a field layer **5810** of silicon dioxide onto the portions of the silicon wafer **5800** not covered by the patterned layer **5805** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 58d**, (5) pattern the layer **5810** of silicon dioxide in step **5616**, as illustrated in **FIG. 58e**, (6) apply and pattern a layer **5815** of photoresist onto the silicon wafer **5800** in step **5620**, as illustrated in **FIG. 58f**, (7) etch the exposed portions of the silicon wafer **5800** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 58g**, (8) etch the exposed portions of the layer **5810** of silicon dioxide in step **5624**, as illustrated in **FIG. 58h**, (9) remove the layer **5815** of photoresist in step **5628**, as illustrated in **FIG. 58i**, (10) etch the exposed portions of the silicon wafer **5800** in step **5630**, as illustrated in **FIG. 58j**, (11) etch the exposed portions of the layer **5810** of silicon dioxide in step **5632**, as illustrated in **FIG. 58k**, (12) etch the exposed portions of the silicon wafer **5800** in step **5634**, as illustrated in **FIG. 58l**, and (13) remove the remaining portions of the layer **5805** of silicon nitride, as illustrated in **FIG. 58m**.

In a preferred implementation of the second embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **5805** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **5810** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **5815** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the second embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

5 Referring to **FIGS. 56a, 56b, and 59a-59m**, the third embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **5900** in step **5602**, as illustrated in **FIG. 59a**,
10 (2) apply a layer **5905** of silicon nitride onto the silicon wafer **5900** in step **5606**, as illustrated in **FIG. 59b**, (3) pattern the layer **5905** of silicon nitride in step **5608**, as illustrated in **FIG. 59c**, (4) grow a field layer **5910** of silicon dioxide onto the portions of the silicon wafer **5900** not covered by the patterned layer **5905** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and
15 the optional buffer layer of silicon dioxide), as illustrated in **FIG. 59d**, (5) pattern the layer **5910** of silicon dioxide in step **5616**, as illustrated in **FIG. 59e**, (6) apply and pattern a layer **5915** of photoresist onto the silicon wafer **5900** in step **5620**, as illustrated in **FIG. 59f**, (7) etch the exposed portions of the silicon wafer **5900** using a plasma or gaseous etchant in step **5622**, as illustrated in
20 **FIG. 59g**, (8) etch the exposed portions of the silicon wafer **5900** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 59h**, (9) remove the layer **5915** of photoresist in step **5628**, as illustrated in **FIG. 59i**, (10) etch the exposed portions of the silicon wafer **5900** in step **5630**, as illustrated in **FIG. 59j**, (11) etch the exposed portions of the layer **5910** of silicon dioxide in
25 step **5632**, as illustrated in **FIG. 59k**, (12) etch the exposed portions of the silicon wafer **5900** in step **5634**, as illustrated in **FIG. 59l**, and (13) remove the remaining portions of the layer **5905** of silicon nitride, as illustrated in **FIG. 59m**.

In a preferred implementation of the third embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters
30 are employed: the thickness of layer **5905** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **5910** of silicon dioxide ranges from

about 0.2 to 3.0 microns, and the thickness of layer **5915** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the third embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 60a-60n**, the fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6000** in step **5602**, as illustrated in **FIG. 60a**, (2) apply a layer **6005** of silicon nitride onto the silicon wafer **6000** in step **5606**, as illustrated in **FIG. 60b**, (3) pattern the layer **6005** of silicon nitride in step **5608**, as illustrated in **FIG. 60c**, (4) grow a field layer **6010** of silicon dioxide onto the portions of the silicon wafer **6000** not covered by the patterned layer **6005** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 60d**, (5) pattern the layer **6010** of silicon dioxide in step **5616**, as illustrated in **FIG. 60e**, (6) apply and pattern a layer **6015** of photoresist onto the silicon wafer **6000** in step **5620**, as illustrated in **FIG. 60f**, (7) etch the exposed portions of the silicon wafer **6000** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 60g**, (8) etch the exposed portions of the layer **6010** of silicon dioxide in step **5624**, as illustrated in **FIG. 60h**; (9) etch the exposed portions of the silicon wafer **6000** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 60i**, (10) remove the layer **6015** of photoresist in step **5628**, as illustrated in **FIG. 60j**, (11) etch the exposed portions of the silicon wafer **6000** in step **5630**, as illustrated in **FIG. 60k**, (12) etch the exposed portions of the layer **6010** of silicon dioxide in step **5632**, as illustrated in **FIG. 60l**, (13) etch the exposed portions of the silicon wafer **6000** in step **5634**, as illustrated in **FIG. 60m**, and (14) remove the remaining portions of the layer **6005** of silicon nitride, as illustrated in **FIG. 60n**.

In a preferred implementation of the fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6005** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6010** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **6015** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 61a-61l**, the fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6100** in step **5602**, as illustrated in **FIG. 61a**, (2) apply a layer **6105** of silicon nitride onto the silicon wafer **6100** in step **5606**, as illustrated in **FIG. 61b**, (3) pattern the layer **6105** of silicon nitride in step **5608**, as illustrated in **FIG. 61c**, (4) grow a field layer **6110** of silicon dioxide onto the portions of the silicon wafer **6100** not covered by the patterned layer **6105** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 61d**, (5) pattern the layer **6110** of silicon dioxide in step **5616**, as illustrated in **FIG. 61e**, (6) apply and pattern a layer **6115** of photoresist onto the silicon wafer **6100** in step **5620**, as illustrated in **FIG. 61f**, (7) etch the exposed portions of the layer **6110** of silicon dioxide in step **5624**, as illustrated in **FIG. 61g**; (8) remove the layer **6115** of photoresist in step **5628**, as illustrated in **FIG. 61h**, (9) etch the exposed portions of the silicon wafer **6100** in step **5630**, as illustrated in **FIG. 61i**, (10) etch the exposed portions of the layer **6110** of silicon dioxide in step **5632**, as illustrated in **FIG. 61j**, (11) etch the exposed portions of the silicon wafer **6100** in step **5634**, as illustrated in **FIG. 61k**, and (12) remove the remaining portions of the layer **6105** of silicon nitride, as illustrated in **FIG. 61l**.

In a preferred implementation of the fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6105** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6110** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **6115** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 62a-62m**, the sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6200** in step **5602**, as illustrated in **FIG. 62a**, (2) apply a layer **6205** of silicon nitride onto the silicon wafer **6200** in step **5606**, as illustrated in **FIG. 62b**, (3) pattern the layer **6205** of silicon nitride in step **5608**, as illustrated in **FIG. 62c**, (4) grow a field layer **6210** of silicon dioxide onto the portions of the silicon wafer **6200** not covered by the patterned layer **6205** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 62d**, (5) pattern the layer **6210** of silicon dioxide in step **5616**, as illustrated in **FIG. 62e**, (6) apply and pattern a layer **6215** of photoresist onto the silicon wafer **6200** in step **5620**, as illustrated in **FIG. 62f**, (7) etch the exposed portions of the layer **6210** of silicon dioxide in step **5624**, as illustrated in **FIG. 62g**; (8) etch the exposed portions of the silicon wafer **6200** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 62h**; (9) remove the layer **6215** of photoresist in step **5628**, as illustrated in **FIG. 62i**, (10) etch the exposed portions of the silicon wafer **6200** in step **5630**, as illustrated in **FIG. 62j**, (11) etch the exposed portions of the layer **6210** of silicon dioxide in step **5632**, as illustrated in **FIG. 62k**, (12) etch the exposed portions of the silicon wafer **6200** in step **5634**, as

illustrated in **FIG. 62l**, and (13) remove the remaining portions of the layer **6205** of silicon nitride, as illustrated in **FIG. 62m**.

In a preferred implementation of the sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6205** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6210** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **6215** of photoresist ranges from about 1 to 10 microns.

Referring to **FIGS. 56a, 56b, and 63a-63j**, the seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6300** in step **5602**, as illustrated in **FIG. 63a**, (2) apply a layer **6305** of silicon nitride onto the silicon wafer **6300** in step **5606**, as illustrated in **FIG. 63b**, (3) pattern the layer **6305** of silicon nitride in step **5608**, as illustrated in **FIG. 63c**, (4) grow a field layer **6310** of silicon dioxide onto the portions of the silicon wafer **6300** not covered by the patterned layer **6305** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 63d**, (5) pattern the layer **6310** of silicon dioxide in step **5616**, as illustrated in **FIG. 63e**, (6) apply and pattern a layer **6315** of photoresist onto the silicon wafer **6300** in step **5620**, as illustrated in **FIG. 63f**, (7) etch the exposed portions of the silicon wafer **6300** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 63g**, (9) remove the layer **6315** of photoresist in step **5628**, as illustrated in **FIG. 63h**, (10) etch the exposed portions of the silicon wafer **6300** in step **5630**, as illustrated in **FIG. 63i**, (11) etch the exposed portions of the layer **6310** of silicon dioxide in step **5632**, as illustrated in **FIG. 63j**, (12) etch the exposed

portions of the silicon wafer **6300** in step **5634**, as illustrated in **FIG. 63k**, and (13) remove the remaining portions of the layer **6305** of silicon nitride, as illustrated in **FIG. 63l**.

In a preferred implementation of the seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6305** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6310** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **6315** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 64a-64m**, the eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask, with a thin etch of the exposed portions of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6400** in step **5602**, as illustrated in **FIG. 64a**, (2) apply a layer of silicon nitride **6405** onto the silicon wafer **6400** in step **5606**, as illustrated in **FIG. 64b**, (3) pattern the layer **6405** of silicon nitride in step **5608**, as illustrated in **FIG. 64c**, (4) thin etch the exposed portions of the silicon wafer **6400** in step **5610**, as illustrated in **FIG. 64d**, (5) grow a field layer **6410** of silicon dioxide onto the portions of the silicon wafer **6400** not covered by the patterned layer **6405** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 64e**, (6) pattern the layer **6410** of silicon dioxide in step **5616**, as illustrated in **FIG. 64f**, (7) apply and pattern a layer **6415** of photoresist onto the silicon wafer **6400** in step **5620**, as illustrated in **FIG. 64g**, (8) etch the exposed portions of the silicon wafer **6400** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 64h**, (9) remove the layer **6415** of photoresist in step

5628, as illustrated in **FIG. 64i**, (10) etch the exposed portions of the silicon wafer **6400** in step **5630**, as illustrated in **FIG. 64j**, (11) etch the exposed portions of the layer **6410** of silicon dioxide in step **5632**, as illustrated in **FIG. 64k**, (12) etch the exposed portions of the silicon wafer **6400** in step **5634**, as illustrated in **FIG. 64l**, and (13) remove the remaining portions of the layer **6405** of silicon nitride, as illustrated in **FIG. 64m**.

In a preferred implementation of the eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6405** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6410** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **6415** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **6400** ranges from about 0.5 to 1 microns.

In a preferred implementation of the eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 65a-65n**, the ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask, with a thin etch of the exposed portions of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6500** in step **5602**, as illustrated in **FIG. 65a**, (2) apply a layer **6505** of silicon nitride onto the silicon wafer **6500** in step **5606**, as illustrated in **FIG. 65b**, (3) pattern the layer **6505** of silicon nitride in step **5608**, as illustrated in **FIG. 65c**, (4) thin etch the exposed portions of the silicon wafer **6500** in step **5610**, as illustrated in **FIG. 65d**, (5) grow a field layer **6510** of silicon dioxide onto the portions of the silicon wafer **6500** not covered by the patterned layer **6505** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 65e**, (6) pattern the layer **6510** of silicon dioxide in step **5616**, as illustrated

in **FIG. 65f**, (7) apply and pattern a layer **6515** of photoresist onto the silicon wafer **6500** in step **5620**, as illustrated in **FIG. 65g**, (8) etch the exposed portions of the silicon wafer **6500** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 65h**, (9) etch the exposed portions of the layer **6510** of silicon dioxide in step **5624**, as illustrated in **FIG. 65i**, (10) remove the layer **6515** of photoresist in step **5628**, as illustrated in **FIG. 65j**, (11) etch the exposed portions of the silicon wafer **6500** in step **5630**, as illustrated in **FIG. 65k**, (12) etch the exposed portions of the layer **6510** of silicon dioxide in step **5632**, as illustrated in **FIG. 65l**, (13) etch the exposed portions of the silicon wafer **6500** in step **5634**, as illustrated in **FIG. 65m**, and (14) remove the remaining portions of the layer **6505** of silicon nitride, as illustrated in **FIG. 58n**.

In a preferred implementation of the ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6505** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6510** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **6515** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **6500** ranges from about 0.5 to 1 microns.

In a preferred implementation of the ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b**, and **66a-66n**, the tenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask, with a thin etch of the exposed portions of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6600** in step **5602**, as illustrated in **FIG. 66a**, (2) apply a layer **6605** of silicon nitride onto the silicon wafer **6600** in step **5606**, as illustrated in **FIG. 66b**, (3) pattern the layer **6605** of silicon nitride in step **5608**, as illustrated in **FIG. 66c**, (4) thin etch the exposed portions of the silicon wafer **6600** in step **5610**, as illustrated in **FIG. 66d**, (5) grow a field layer **6610** of silicon

dioxide onto the portions of the silicon wafer **6600** not covered by the patterned layer **6605** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 66e**,
5 (6) pattern the layer **6610** of silicon dioxide in step **5616**, as illustrated in **FIG. 66f**, (7) apply and pattern a layer **5615** of photoresist onto the silicon wafer **6600** in step **5620**, as illustrated in **FIG. 66g**, (8) etch the exposed portions of the silicon wafer **6600** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 66h**, (9) etch the exposed portions of the silicon wafer **6600**
10 using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 66i**, (10) remove the layer **6615** of photoresist in step **5628**, as illustrated in **FIG. 66j**, (11) etch the exposed portions of the silicon wafer **6600** in step **5630**, as illustrated in **FIG. 66k**, (12) etch the exposed portions of the layer **6610** of silicon dioxide in step **5632**, as illustrated in **FIG. 66l**, (13) etch the exposed portions of the
15 silicon wafer **6600** in step **5634**, as illustrated in **FIG. 66m**, and (13) remove the remaining portions of the layer **6605** of silicon nitride, as illustrated in **FIG. 66n**.

In a preferred implementation of the tenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6605** of silicon nitride ranges from about
20 0.1 to 2.0 microns, the thickness of layer **6610** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **6615** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **6600** ranges from about 0.5 to 1 microns.

In a preferred implementation of the tenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps
25 **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 67a-67o**, the eleventh embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as
30 an etching mask, with a thin etch of the exposed portions of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1)

provide a silicon wafer **6700** in step **5602**, as illustrated in **FIG. 67a**, (2) apply a layer **6705** of silicon nitride onto the silicon wafer **6700** in step **5606**, as illustrated in **FIG. 67b**, (3) pattern the layer **6705** of silicon nitride in step **5608**, as illustrated in **FIG. 67c**, (4) thin etch the exposed portions of the silicon wafer **6700** in step **5610**, as illustrated in **FIG. 67d**, (5) grow a field layer **6710** of silicon dioxide onto the portions of the silicon wafer **6700** not covered by the patterned layer **6705** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 67e**, (6) pattern the layer **6710** of silicon dioxide in step **5616**, as illustrated in **FIG. 67f**, (7) apply and pattern a layer **6715** of photoresist onto the silicon wafer **6700** in step **5620**, as illustrated in **FIG. 67g**, (8) etch the exposed portions of the silicon wafer **6700** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 67h**, (9) etch the exposed portions of the layer **6710** of silicon dioxide in step **5624**, as illustrated in **FIG. 67i**; (10) etch the exposed portions of the silicon wafer **6700** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 67j**, (11) remove the layer **6715** of photoresist in step **5628**, as illustrated in **FIG. 67k**, (12) etch the exposed portions of the silicon wafer **6700** in step **5630**, as illustrated in **FIG. 67l**, (13) etch the exposed portions of the layer **6710** of silicon dioxide in step **5632**, as illustrated in **FIG. 67m**, (14) etch the exposed portions of the silicon wafer **6700** in step **5634**, as illustrated in **FIG. 67n**, and (15) remove the remaining portions of the layer **6705** of silicon nitride, as illustrated in **FIG. 67o**.

In a preferred implementation of the eleventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6705** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6710** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **6715** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **6700** ranges from about 0.5 to 1 microns.

In a preferred implementation of the eleventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

5 Referring to **FIGS. 56a, 56b, and 68a-68k**, the twelfth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask, with a thin etch of the exposed portions of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6800** in step **5602**, as illustrated in **FIG. 68a**, (2) apply
10 a layer **6805** of silicon nitride onto the silicon wafer **6800** in step **5606**, as illustrated in **FIG. 68b**, (3) pattern the layer **6805** of silicon nitride in step **5608**, as illustrated in **FIG. 68c**, (4) thin etch the exposed portions of the silicon wafer **6800** in step **5610**, as illustrated in **FIG. 68d**, (5) grow a field layer **6810** of silicon dioxide onto the portions of the silicon wafer **6800** not covered by the
15 patterned layer **6805** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 68e**, (6) pattern the layer **6810** of silicon dioxide in step **5616**, as illustrated in **FIG. 68f**, (7) apply and pattern a layer **6815** of photoresist onto the silicon
20 wafer **6800** in step **5620**, as illustrated in **FIG. 68g**, (8) etch the exposed portions of the layer **6810** of silicon dioxide in step **5624**, as illustrated in **FIG. 68h**; (9) remove the layer **6815** of photoresist in step **5628**, as illustrated in **FIG. 68i**, (10) etch the exposed portions of the silicon wafer **6800** in step **5630**, as illustrated in **FIG. 68j**, (11) etch the exposed portions of the layer **6810** of silicon dioxide in step **5632**, as illustrated in **FIG. 68k**, (12) etch the exposed portions
25 of the silicon wafer **6800** in step **5634**, then (13) remove the remaining portions of the layer **6805** of silicon nitride.

In a preferred implementation of the twelfth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters
30 are employed: the thickness of layer **6805** of silicon nitride ranges from about

0.1 to 2.0 microns, the thickness of layer **6810** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **6815** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **6800** ranges from about 0.5 to 1 microns.

5 In a preferred implementation of the twelfth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

10 Referring to **FIGS. 56a, 56b, and 68a-k and 69l-n**, the thirteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask, with a thin etch of the exposed portions of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **6800** in step **5602**, as illustrated in **FIG. 68a**, (2) apply a layer **6805** of silicon nitride onto the silicon wafer **6800** in step **5606**, as illustrated in **FIG. 68b**, (3) pattern the layer **6805** of silicon nitride in step **5608**, as illustrated in **FIG. 68c**, (4) thin etch the exposed portions of the silicon wafer **6800** in step **5610**, as illustrated in **FIG. 68d**, (5) grow a field layer **6810** of silicon dioxide onto the portions of the silicon wafer **6800** not covered by the patterned layer **6805** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 68e**, (6) pattern the layer **6810** of silicon dioxide in step **5616**, as illustrated in **FIG. 68f**, (7) apply and pattern a layer **6815** of photoresist onto the silicon wafer **6800** in step **5620**, as illustrated in **FIG. 68g**, (8) etch the exposed portions of the layer **6810** of silicon dioxide in step **5624**, as illustrated in **FIG. 68h**; (9) etch the exposed portions of the silicon wafer **6800** using a plasma or gaseous etchant in step **5626**; (10) remove the layer **6815** of photoresist in step **5628**; (11) etch the exposed portions of the silicon wafer **6800** in step **5630**; (12) etch the remaining exposed portions of the layer **6810** of silicon dioxide in step **5632** to achieve a configuration as illustrated in **FIG. 69l**, (13) etch the exposed portions of the silicon wafer **6900** (**6800** in **FIGS.**

68a-68k) in step **5634**, as illustrated in **FIG. 69m**, and (14) remove the remaining portions of the layer **6905** (**6805** in **FIGS. 68a-68k**) of silicon nitride, as illustrated in **FIG. 69n**.

5 In a preferred implementation of the thirteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

10 In a preferred implementation of the thirteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **6905** (**6805** in **FIGS. 68a-68k**) of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **6910** (**6810** in **FIGS. 68a-68k**) of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **6915** (**6815** in **FIGS. 68a-68k**) of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **6900** (**6800** in **FIGS. 68a-68k**) ranges from about 0.5 to 1 microns.

Referring to **FIGS. 56a, 56b, and 70a-70m**, the fourteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask, with a thin etch of the silicon wafer, and without the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7000** in step **5602**, as illustrated in **FIG. 70a**, (2) apply a layer **7005** of silicon nitride onto the silicon wafer **7000** in step **5606**, as illustrated in **FIG. 70b**, (3) pattern the layer **7005** of silicon nitride in step **5608**, as illustrated in **FIG. 70c**, (4) thin etch the exposed portions of the silicon wafer **7000** in step **5610**, as illustrated in **FIG. 70d**, (5) grow a field layer **7010** of silicon dioxide onto the portions of the silicon wafer **7000** not covered by the patterned layer **7005** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 70e**, (6) pattern the layer **7010** of silicon dioxide in step **5616**, as illustrated in **FIG. 70f**, (7) apply and pattern a layer **7015** of photoresist onto the silicon wafer **7000** in step **5620**,

as illustrated in **FIG. 70g**, (8) etch the exposed portions of the silicon wafer **7000** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 70h**, (9) remove the layer **7015** of photoresist in step **5628**, as illustrated in **FIG.**

70i, (10) etch the exposed portions of the silicon wafer **7000** in step **5630**, as illustrated in **FIG. 70j**, (11) etch the exposed portions of the layer **7010** of silicon dioxide in step **5632**, as illustrated in **FIG. 70k**, (12) etch the exposed portions of the silicon wafer **7000** in step **5634**, as illustrated in **FIG. 70l**, and (13) remove the remaining portions of the layer **7005** of silicon nitride, as illustrated in **FIG. 70m**.

In a preferred implementation of the fourteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of layer **7005** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of layer **7010** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **7015** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **7000** ranges from about 0.5 to 1 microns.

In a preferred implementation of the fourteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 71a-71m**, the fifteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7100** in step **5602**, as illustrated in **FIG. 71a**, (2) apply a buffer pad layer **7105** of silicon dioxide onto the silicon wafer **7100** in step **5604**, as illustrated in **FIG. 71b**, (3) apply a layer of silicon nitride **7110** onto the silicon wafer **7100** in step **5606**, as illustrated in **FIG. 71c**, (4) pattern the layer **7110** of silicon nitride in step **5608**, as illustrated in **FIG. 71d**, (5) grow a field layer **7115** of silicon dioxide onto the portions of the silicon wafer **7100** not covered by the patterned layer **7110** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 71e**, (6) pattern the layers **7105** and **7115** of silicon dioxide in step **5616**, as illustrated in **FIG. 71f**, (7) apply and pattern a

layer **7120** of photoresist onto the silicon wafer **7100** in step **5620**, as illustrated in **FIG. 71g**, (8) etch the exposed portions of the silicon wafer **7100** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 71h**, (9) remove the layer **7120** of photoresist in step **5628**, as illustrated in **FIG. 71i**, (10) etch the exposed portions of the silicon wafer **7100** in step **5630**, as illustrated in **FIG. 71j**, (11) etch the exposed portions of the layers **7105** and **7115** of silicon dioxide in step **5632**, as illustrated in **FIG. 71k**, (12) etch the exposed portions of the silicon wafer **7100** in step **5634**, as illustrated in **FIG. 71l**, and (13) remove the remaining portions of the layers **7105**, **7110** and **7115** of silicon dioxide and silicon nitride, as illustrated in **FIG. 71m**.

In a preferred implementation of the fifteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7105** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7110** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7115** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7120** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the fifteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 72a-72n**, the sixteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7200** in step **5602**, as illustrated in **FIG. 72a**, (2) apply a buffer pad layer **7205** of silicon dioxide onto the silicon wafer in step **5604**, as illustrated in **FIG. 72b**, (3) apply a layer **7210** of silicon nitride onto the silicon wafer **7200** in step **5606**, as illustrated in **FIG. 72c**, (4) pattern the layer **7210** of silicon nitride in step **5608**, as illustrated in **FIG. 72d**, (5) grow a field layer **7215** of silicon dioxide onto the portions of the silicon wafer **7200** not covered by the patterned layer **7210** of silicon nitride in step **5614** (the field

layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 72e**, (6) pattern the layers **7205** and **7215** of silicon dioxide in step **5616**, as illustrated in **FIG. 72f**, (7) apply and pattern a layer **7220** of photoresist onto the silicon wafer **7200** in step **5620**, as illustrated in **FIG. 72g**, (8) etch the exposed portions of the silicon wafer **7200** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 72h**, (9) etch the exposed portions of the layers **7205** and **7215** of silicon dioxide in step **5624**, as illustrated in **FIG. 72i**, (10) remove the layer **7220** of photoresist in step **5628**, as illustrated in **FIG. 72j**, (11) etch the exposed portions of the silicon wafer **7200** in step **5630**, as illustrated in **FIG. 72k**, (12) etch the exposed portions of the layers **7205** and **7215** of silicon dioxide in step **5632**, as illustrated in **FIG. 72l**, (13) etch the exposed portions of the silicon wafer **7200** in step **5634**, as illustrated in **FIG. 72m**, and (14) remove the remaining portions of the layers **7205**, **7210** and **7215** of silicon dioxide and silicon nitride, as illustrated in **FIG. 72n**.

In a preferred implementation of the sixteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7205** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7210** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7215** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7220** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the sixteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a**, **56b**, and **73a-73n**, the seventeenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7300** in step **5602**, as illustrated in **FIG. 73a**,

(2) apply a buffer pad layer **7305** of silicon dioxide onto the silicon wafer **7300** in step **5604**, as illustrated in **FIG. 73b**, (3) apply a layer **7310** of silicon nitride onto the silicon wafer **7300** in step **5606**, as illustrated in **FIG. 73c**, (4) pattern the layer **7310** of silicon nitride in step **5608**, as illustrated in **FIG. 73d**, (5) grow a field layer **7315** of silicon dioxide onto the portions of the silicon wafer **7300** not covered by the patterned layer **7310** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 73e**, (6) pattern the layers **7305** and **7315** of silicon dioxide in step **5616**, as illustrated in **FIG. 73f**, (7) apply and pattern a layer **7320** of photoresist onto the silicon wafer **7300** in step **5620**, as illustrated in **FIG. 73g**, (8) etch the exposed portions of the silicon wafer **7300** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 73h**, (9) etch the exposed portions of the silicon wafer **7300** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 73i**, (10) remove the layer **7320** of photoresist in step **5628**, as illustrated in **FIG. 73j**, (11) etch the exposed portions of the silicon wafer **7300** in step **5630**, as illustrated in **FIG. 73k**, (12) etch the exposed portions of the layers **7305** and **7315** of silicon dioxide in step **5632**, as illustrated in **FIG. 73l**, (13) etch the exposed portions of the silicon wafer **7300** in step **5634**, as illustrated in **FIG. 73m**, and (14) remove the remaining portions of the layers **7305**, **7310**, and **7315** of silicon dioxide and silicon nitride, as illustrated in **FIG. 73n**.

In a preferred implementation of the seventeenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7305** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7310** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7315** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7320** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the seventeenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed

in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 74a-74o**, the eighteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7400** in step **5602**, as illustrated in **FIG. 74a**, (2) apply a buffer pad layer **7405** of silicon dioxide onto the silicon wafer **7400** in step **5604**, as illustrated in **FIG. 74b**, (3) apply a layer **7410** of silicon nitride onto the silicon wafer **7400** in step **5606**, as illustrated in **FIG. 74c**, (4) pattern the layer **7410** of silicon nitride in step **5608**, as illustrated in **FIG. 74d**, (5) grow a field layer **7415** of silicon dioxide onto the portions of the silicon wafer **7400** not covered by the patterned layer **7410** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 74e**, (6) pattern the layers **7405** and **7415** of silicon dioxide in step **5616**, as illustrated in **FIG. 74f**, (7) apply and pattern a layer **7420** of photoresist onto the silicon wafer **7400** in step **5620**, as illustrated in **FIG. 74g**, (8) etch the exposed portions of the silicon wafer **7400** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 74h**, (9) etch the exposed portions of the layers **7405** and **7415** of silicon dioxide in step **5624**, as illustrated in **FIG. 74i**; (10) etch the exposed portions of the silicon wafer **7400** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 74j**, (11) remove the layer **7420** of photoresist in step **5628**, as illustrated in **FIG. 74k**, (12) etch the exposed portions of the silicon wafer **7400** in step **5630**, as illustrated in **FIG. 74l**, (13) etch the exposed portions of the layers **7405** and **7415** of silicon dioxide in step **5632**, as illustrated in **FIG. 74m**, (14) etch the exposed portions of the silicon wafer **7400** in step **5634**, as illustrated in **FIG. 74n**, and (15) remove the remaining portions of the layers **7405, 7410** and **7415** of silicon dioxide and silicon nitride, as illustrated in **FIG. 74o**.

In a preferred implementation of the eighteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process

parameters are employed: the thickness of the pad buffer layer **7405** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7410** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7415** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7420** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the eighteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b, and 75a-75m**, the nineteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7500** in step **5602**, as illustrated in **FIG. 75a**, (2) apply a buffer pad layer **7505** of silicon dioxide onto the silicon wafer **7500** in step **5604**, as illustrated in **FIG. 75b**, (3) apply a layer **7510** of silicon nitride onto the silicon wafer **7500** in step **5606**, as illustrated in **FIG. 75c**, (4) pattern the layer **7510** of silicon nitride in step **5608**, as illustrated in **FIG. 75d**, (5) grow a field layer **7515** of silicon dioxide onto the portions of the silicon wafer **7500** not covered by the patterned layer **7510** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 75e**, (6) pattern the layers **7505** and **7515** of silicon dioxide in step **5616**, as illustrated in **FIG. 75f**, (7) apply and pattern a layer **7520** of photoresist onto the silicon wafer **7500** in step **5620**, as illustrated in **FIG. 75g**, (8) etch the exposed portions of the layers **7505** and **7515** of silicon dioxide in step **5624**, as illustrated in **FIG. 75h**; (9) remove the layer **7520** of photoresist in step **5628**, as illustrated in **FIG. 75i**, (10) etch the exposed portions of the silicon wafer **7500** in step **5630**, as illustrated in **FIG. 75j**, (11) etch the exposed portions of the layers **7505** and **7515** of silicon dioxide in step **5632**, as illustrated in **FIG. 75k**, (12) etch the exposed portions of the silicon wafer **7500** in step **5634**, as illustrated in **FIG. 75l**, and (13) remove the

remaining portions of the layers **7505**, **7510** and **7515** of silicon dioxide and silicon nitride, as illustrated in **FIG. 75m**.

In a preferred implementation of the nineteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7505** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7510** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7515** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7520** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the nineteenth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a**, **56b**, and **76a-76n**, the twentieth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7600** in step **5602**, as illustrated in **FIG. 76a**, (2) apply a buffer pad layer **7605** of silicon dioxide onto the silicon wafer **7600** in step **5604**, as illustrated in **FIG. 76b**, (3) apply a layer **7610** of silicon nitride onto the silicon wafer **7600** in step **5606**, as illustrated in **FIG. 76c**, (4) pattern the layer **7610** of silicon nitride in step **5608**, as illustrated in **FIG. 76d**, (5) grow a field layer **7615** of silicon dioxide onto the portions of the silicon wafer **7600** not covered by the patterned layer **7610** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 76e**, (6) pattern the layers **7605** and **7615** of silicon dioxide in step **5616**, as illustrated in **FIG. 76f**, (7) apply and pattern a layer **7620** of photoresist onto the silicon wafer **7600** in step **5620**, as illustrated in **FIG. 76g**, (8) etch the exposed portions of the layers **7605** and **7615** of silicon dioxide in step **5624**, as illustrated in **FIG. 76h**; (9) etch the exposed portions of the silicon wafer **7600** using a plasma or gaseous etchant in step **5626**, as

illustrated in **FIG. 76i**; (10) remove the layer **7620** of photoresist in step **5628**, as illustrated in **FIG. 76j**, (11) etch the exposed portions of the silicon wafer **7600** in step **5630**, as illustrated in **FIG. 76k**, (12) etch the exposed portions of the layers **7605** and **7615** of silicon dioxide in step **5632**, as illustrated in **FIG. 76l**, (13) etch the exposed portions of the silicon wafer **7600** in step **5634**, as illustrated in **FIG. 76m**, and (14) remove the remaining portions of the layers **7605**, **7610** and **7615** of silicon dioxide and silicon nitride, as illustrated in **FIG. 76n**.

In a preferred implementation of the twentieth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7605** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7610** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7615** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7620** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twentieth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a, 56b**, and **77a-77m**, the twenty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of a buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7700** in step **5602**, as illustrated in **FIG. 77a**, (2) apply a buffer pad layer **7705** of silicon dioxide onto the silicon wafer **7700** in step **5604**, as illustrated in **FIG. 77b**, (3) apply a layer **7710** of silicon nitride onto the silicon wafer **7700** in step **5606**, as illustrated in **FIG. 77c**, (4) pattern the layer **7710** of silicon nitride in step **5608**, as illustrated in **FIG. 77d**, (5) grow a field layer **7715** of silicon dioxide onto the portions of the silicon wafer **7700** not covered by the patterned layer **7710** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon

dioxide), as illustrated in **FIG. 77e**, (6) pattern the layers **7705** and **7715** of silicon dioxide in step **5616**, as illustrated in **FIG. 77f**, (7) apply and pattern a layer **7720** of photoresist onto the silicon wafer **7700** in step **5620**, as illustrated in **FIG. 77g**, (8) etch the exposed portions of the silicon wafer **7700** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 77h**, (10) remove the layer **7720** of photoresist in step **5628**, as illustrated in **FIG. 77i**, (11) etch the exposed portions of the silicon wafer **7700** in step **5630**, as illustrated in **FIG. 77j**, (12) etch the exposed portions of the layers **7705** and **7715** of silicon dioxide in step **5632**, as illustrated in **FIG. 77k**, (13) etch the exposed portions of the silicon wafer **7700** in step **5634**, as illustrated in **FIG. 77l**, and (14) remove the remaining portions of the layers **7705**, **7710**, and **7715** of silicon dioxide and silicon nitride, as illustrated in **FIG. 77m**.

In a preferred implementation of the twenty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7705** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7710** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7715** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7720** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring to **FIGS. 56a**, **56b**, and **78a-78n**, the twenty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7800** in step **5602**, as illustrated in **FIG. 78a**, (2) apply a buffer pad layer **7805** of silicon dioxide onto the silicon wafer **7800** in step **5604**, as illustrated in **FIG. 78b**, (3) apply a layer **7810** of silicon nitride onto the silicon wafer **7800** in step **5606**, as illustrated in **FIG. 78c**, (4) pattern the layer **7810** of silicon nitride in step **5608**, as illustrated

in **FIG. 78d**, (5) pattern the buffer pad layer **7805** of silicon dioxide in step **5610**, as illustrated in **FIG. 78e**, (6) grow a field layer **7815** of silicon dioxide onto the portions of the silicon wafer **7800** not covered by the patterned layer **7810** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 78f**, (7) pattern the layers **7805** and **7815** of silicon dioxide in step **5616**, as illustrated in **FIG. 78g**, (8) apply and pattern a layer **7820** of photoresist onto the silicon wafer **7800** in step **5620**, as illustrated in **FIG. 78h**, (9) etch the exposed portions of the silicon wafer **7800** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 78i**, (10) remove the layer **7820** of photoresist in step **5628**, as illustrated in **FIG. 78j**, (11) etch the exposed portions of the silicon wafer **7800** in step **5630**, as illustrated in **FIG. 78k**, (12) etch the exposed portions of the layers **7805** and **7815** of silicon dioxide in step **5632**, as illustrated in **FIG. 78l**, (13) etch the exposed portions of the silicon wafer **7800** in step **5634**, as illustrated in **FIG. 78m**, and (14) remove the remaining portions of the layers **7805**, **7810** and **7815** of silicon dioxide and silicon nitride, as illustrated in **FIG. 78n**.

In a preferred implementation of the twenty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **7805** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7810** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7815** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7820** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **7810**

of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **7805** of silicon dioxide in step **5610**.

Referring to **FIGS. 56a, 56b, and 79a-79o**, the twenty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **7900** in step **5602**, as illustrated in **FIG. 79a**, (2) apply a buffer pad layer **7905** of silicon dioxide onto the silicon wafer in step **5604**, as illustrated in **FIG. 79b**, (3) apply a layer **7910** of silicon nitride onto the silicon wafer **7900** in step **5606**, as illustrated in **FIG. 79c**, (4) pattern the layer **7910** of silicon nitride in step **5608**, as illustrated in **FIG. 79d**, (5) pattern the buffer pad layer **7905** of silicon dioxide in step **5610**, as illustrated in **FIG. 79e**, (6) grow a field layer **7915** of silicon dioxide onto the portions of the silicon wafer **7900** not covered by the patterned layer **7910** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 79f**, (7) pattern the layers **7905** and **7915** of silicon dioxide in step **5616**, as illustrated in **FIG. 79g**, (8) apply and pattern a layer **7920** of photoresist onto the silicon wafer **7900** in step **5620**, as illustrated in **FIG. 79h**, (9) etch the exposed portions of the silicon wafer **7900** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 79i**, (10) etch the exposed portions of the layers **7905** and **7915** of silicon dioxide in step **5624**, as illustrated in **FIG. 79j**, (11) remove the layer **7920** of photoresist in step **5628**, as illustrated in **FIG. 79k**, (12) etch the exposed portions of the silicon wafer **7900** in step **5630**, as illustrated in **FIG. 79l**, (13) etch the exposed portions of the layers **7905** and **7915** of silicon dioxide in step **5632**, as illustrated in **FIG. 79m**, (14) etch the exposed portions of the silicon wafer **7900** in step **5634**, as illustrated in **FIG. 79n**, and (15) remove the remaining portions of the layers **7905**, **7910** and **7915** of silicon dioxide and silicon nitride, as illustrated in **FIG. 79o**.

In a preferred implementation of the twenty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process

parameters are employed: the thickness of the pad buffer layer **7905** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **7910** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **7915** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **7920** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **7910** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **7905** of silicon dioxide in step **5610**.

Referring to **FIGS. 56a, 56b, and 80a-80o**, the twenty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **8000** in step **5602**, as illustrated in **FIG. 80a**, (2) apply a buffer pad layer **8005** of silicon dioxide onto the silicon wafer **8000** in step **5604**, as illustrated in **FIG. 80b**, (3) apply a layer **8010** of silicon nitride onto the silicon wafer **8000** in step **5606**, as illustrated in **FIG. 80c**, (4) pattern the layer **8010** of silicon nitride in step **5608**, as illustrated in **FIG. 80d**, (5) pattern the buffer pad layer **8005** of silicon dioxide in step **5610**, as illustrated in **FIG. 80e**, (6) grow a field layer **8015** of silicon dioxide onto the portions of the silicon wafer **8000** not covered by the patterned layer **8010** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 80f**, (7) pattern the layers **8005** and **8015** of silicon dioxide in step **5616**, as illustrated in **FIG. 80g**, (8) apply and pattern a layer **8020** of photoresist onto the silicon wafer **8000** in step **5620**, as illustrated in **FIG. 80h**, (9) etch the exposed portions of the silicon wafer **8000** using a plasma or gaseous etchant in step **5622**, as illustrated in

FIG. 80i, (10) etch the exposed portions of the silicon wafer **8000** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 80j**, (11) remove the layer **8020** of photoresist in step **5628**, as illustrated in **FIG. 80k**, (12) etch the exposed portions of the silicon wafer **8000** in step **5630**, as illustrated in **FIG. 80l**, (13) etch the exposed portions of the layers **8005** and **8015** of silicon dioxide in step **5632**, as illustrated in **FIG. 80m**, (14) etch the exposed portions of the silicon wafer **8000** in step **5634**, as illustrated in **FIG. 80n**, and (15) remove the remaining portions of the layers **8005**, **8010**, and **8015** of silicon dioxide and silicon nitride, as illustrated in **FIG. 80o**.

In a preferred implementation of the twenty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8005** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8010** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8015** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **8020** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **8010** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **8005** of silicon dioxide in step **5610**.

Referring to **FIGS. 56a, 56b, and 81a-81p**, the twenty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **8100** in step **5602**, as illustrated in **FIG. 81a**, (2) apply a buffer pad layer **8105** of silicon dioxide onto the silicon wafer **8100** in step **5604**, as illustrated in **FIG. 81b**, (3) apply a layer **8110** of silicon nitride onto the silicon wafer **8100** in step **5606**, as illustrated in

FIG. 81c, (4) pattern the layer **8110** of silicon nitride in step **5608**, as illustrated in **FIG. 81d**, (5) pattern the buffer pad layer **8105** of silicon dioxide in step **5610**, as illustrated in **FIG. 81e**, (6) grow a field layer **8115** of silicon dioxide onto the portions of the silicon wafer **8100** not covered by the patterned layer **8110** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 81f**, (7) pattern the layers **8105** and **8115** of silicon dioxide in step **5616**, as illustrated in **FIG. 81g**, (8) apply and pattern a layer **8120** of photoresist onto the silicon wafer **8100** in step **5620**, as illustrated in **FIG. 81h**, (9) etch the exposed portions of the silicon wafer **8100** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 81i**, (10) etch the exposed portions of the layers **8105** and **8115** of silicon dioxide in step **5624**, as illustrated in **FIG. 81j**; (11) etch the exposed portions of the silicon wafer **8100** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 81k**, (12) remove the layer **8120** of photoresist in step **5628**, as illustrated in **FIG. 81l**, (13) etch the exposed portions of the silicon wafer **8100** in step **5630**, as illustrated in **FIG. 81m**, (14) etch the exposed portions of the layers **8105** and **8115** of silicon dioxide in step **5632**, as illustrated in **FIG. 81n**, (15) etch the exposed portions of the silicon wafer **8100** in step **5634**, as illustrated in **FIG. 81o**, and (16) remove the remaining portions of the layers **8105**, **8110** and **8115** of silicon dioxide and silicon nitride, as illustrated in **FIG. 81p**.

In a preferred implementation of the twenty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8105** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8110** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8115** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **8120** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed

in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **8110** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **8105** of silicon dioxide in step **5610**.

Referring to **FIGS. 56a, 56b, and 82a-82m**, the twenty-sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **8200** in step **5602**, as illustrated in **FIG. 82a**, (2) apply a buffer pad layer **8205** of silicon dioxide onto the silicon wafer **8200** in step **5604**, as illustrated in **FIG. 82b**, (3) apply a layer **8210** of silicon nitride onto the silicon wafer **8200** in step **5606**, as illustrated in **FIG. 82c**, (4) pattern the layer **8210** of silicon nitride in step **5608**, as illustrated in **FIG. 82d**, (5) pattern the buffer pad layer **8205** of silicon dioxide in step **5610**, as illustrated in **FIG. 82e**, (6) grow a field layer **8215** of silicon dioxide onto the portions of the silicon wafer **8200** not covered by the patterned layer **8210** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 82f**, (7) pattern the layers **8205** and **8215** of silicon dioxide in step **5616**, as illustrated in **FIG. 82g**, (8) apply and pattern a layer **8220** of photoresist onto the silicon wafer **8200** in step **5620**, as illustrated in **FIG. 82h**, (9) etch the exposed portions of the layers **8205** and **8215** of silicon dioxide in step **5624**, as illustrated in **FIG. 82i**; (10) remove the layer **8220** of photoresist in step **5628**, as illustrated in **FIG. 82j**, (11) etch the exposed portions of the silicon wafer **8200** in step **5630**, as illustrated in **FIG. 82k**, (12) etch the exposed portions of the layers **8205** and **8215** of silicon dioxide in step **5632**, as illustrated in **FIG. 82l**, (13) etch the exposed portions of the silicon wafer **8200** in step **5634**, as illustrated in **FIG. 82m**, and (14) remove the remaining portions of the layers **8205**, **8210** and **8215** of silicon dioxide and silicon nitride, as illustrated in **FIG. 82n**.

In a preferred implementation of the twenty-sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8205** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8210** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8215** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **8220** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-sixth embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **8210** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **8205** of silicon dioxide in step **5610**.

Referring to **FIGS. 56a, 56b, and 83a-83o**, the twenty-seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **8300** in step **5602**, as illustrated in **FIG. 83a**, (2) apply a buffer pad layer **8305** of silicon dioxide onto the silicon wafer **8300** in step **5604**, as illustrated in **FIG. 83b**, (3) apply a layer **8310** of silicon nitride onto the silicon wafer **8300** in step **5606**, as illustrated in **FIG. 83c**, (4) pattern the layer **8310** of silicon nitride in step **5608**, as illustrated in **FIG. 83d**, (5) pattern the buffer pad layer **8305** of silicon dioxide in step **5610**, as illustrated in **FIG. 83e**, (6) grow a field layer **8315** of silicon dioxide onto the portions of the silicon wafer **8300** not covered by the patterned layer **8310** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 83f**, (7) pattern the layers **8305** and **8315** of silicon dioxide in step **5616**, as illustrated in **FIG. 83g**, (8) apply and pattern a layer **8320** of photoresist onto the silicon wafer **8300** in

step **5620**, as illustrated in **FIG. 83h**, (9) etch the exposed portions of the layers **8305** and **8315** of silicon dioxide in step **5624**, as illustrated in **FIG. 83i**; (10) etch the exposed portions of the silicon wafer **8300** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 83j**; (11) remove the layer **8320** of photoresist in step **5628**, as illustrated in **FIG. 83k**, (12) etch the exposed portions of the silicon wafer **8300** in step **5630**, as illustrated in **FIG. 83l**, (13) etch the exposed portions of the layers **8305** and **8315** of silicon dioxide in step **5632**, as illustrated in **FIG. 83m**, (14) etch the exposed portions of the silicon wafer **8300** in step **5634**, as illustrated in **FIG. 83n**, and (15) remove the remaining portions of the layers **8305**, **8310** and **8315** of silicon dioxide and silicon nitride, as illustrated in **FIG. 83o**.

In a preferred implementation of the twenty-seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8305** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8310** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8315** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **8320** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-seventh embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **8310** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **8305** of silicon dioxide in step **5610**.

Referring to **FIGS. 56a**, **56b**, and **84a-84n**, the twenty-eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide, includes the steps of: (1) provide a silicon wafer **8400** in step **5602**, as illustrated in **FIG. 84a**, (2) apply a buffer pad layer **8405** of silicon dioxide onto

the silicon wafer **8400** in step **5604**, as illustrated in **FIG. 84b**, (3) apply a layer **8410** of silicon nitride onto the silicon wafer **8400** in step **5606**, as illustrated in **FIG. 84c**, (4) pattern the layer **8410** of silicon nitride in step **5608**, as illustrated in **FIG. 84d**, (5) pattern the buffer pad layer **8405** of silicon dioxide in step **5610**,
5 as illustrated in **FIG. 84e**, (6) grow a field layer **8415** of silicon dioxide onto the portions of the silicon wafer **8400** not covered by the patterned layer **8410** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 84f**, (7) pattern the
10 layers **8405** and **8415** of silicon dioxide in step **5616**, as illustrated in **FIG. 84g**, (8) apply and pattern a layer **8420** of photoresist onto the silicon wafer **8400** in step **5620**, as illustrated in **FIG. 84h**, (9) etch the exposed portions of the silicon wafer **8400** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 84i**, (10) remove the layer **8420** of photoresist in step **5628**, as illustrated
15 in **FIG. 84j**, (11) etch the exposed portions of the silicon wafer **8400** in step **5630**, as illustrated in **FIG. 84k**, (12) etch the exposed portions of the layers **8405** and **8415** of silicon dioxide in step **5632**, as illustrated in **FIG. 84l**, (13) etch the exposed portions of the silicon wafer **8400** in step **5634**, as illustrated in **FIG. 84m**, and (14) remove the remaining portions of the layers **8405**, **8410**,
20 and **8415** of silicon dioxide and silicon nitride, as illustrated in **FIG. 84n**.

In a preferred implementation of the twenty-eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8405** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8410** of
25 silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8415** of silicon dioxide ranges from about 0.2 to 3.0 microns, and the thickness of layer **8420** of photoresist ranges from about 1 to 10 microns.

In a preferred implementation of the twenty-eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed
30 in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-eighth embodiment of the LOCOS merged-mask micro-machining process **5600**, the patterned layer **8410** of silicon nitride is used as an etch mask for patterning the exposed portions of the buffer layer **8405** of silicon dioxide in step **5610**.

5 Referring to **FIGS. 56a, 56b, and 85a-85o**, the twenty-ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of:

10 (1) provide a silicon wafer **8500** in step **5602**, as illustrated in **FIG. 85a**, (2) apply a buffer pad layer **8505** of silicon dioxide onto the silicon wafer **8500** in step **5604**, as illustrated in **FIG. 85b**, (3) apply a layer **8510** of silicon nitride onto the silicon wafer **8500** in step **5606**, as illustrated in **FIG. 85c**, (4) pattern the layer **8510** of silicon nitride in step **5608**, as illustrated in **FIG. 85d**, (5) pattern the buffer pad layer **8505** of silicon dioxide in step **5610**, as illustrated in **FIG. 85e**,

15 (6) thin etch the exposed portions of the silicon wafer **8500** in step **5612**, as illustrated in **FIG. 85f**, (7) grow a field layer **8515** of silicon dioxide onto the portions of the silicon wafer **8500** not covered by the patterned layer **8510** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 85g**, (8) pattern the layers **8505** and **8515** of silicon dioxide in step **5616**, as illustrated in **FIG. 85h**,

20 (9) apply and pattern a layer **8520** of photoresist onto the silicon wafer **8500** in step **5620**, as illustrated in **FIG. 85i**, (10) etch the exposed portions of the silicon wafer **8500** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 85j**, (11) remove the layer **8520** of photoresist in step **5628**, as illustrated in **FIG. 85k**, (12) etch the exposed portions of the silicon wafer **8500** in step **5630**, as illustrated in **FIG. 85l**, (13) etch the exposed portions of the layers **8505** and **8515** of silicon dioxide in step **5632**, as illustrated in **FIG. 85m**, (14) etch the exposed portions of the silicon wafer **8500** in step **5634**, as illustrated in **FIG. 85n**, and (15) remove the remaining portions of the layers **7805, 7810** and **7815** of silicon dioxide and silicon nitride, as illustrated in **FIG. 85o**.

30

In a preferred implementation of the twenty-ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8505** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8510** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8515** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **8520** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **8500** ranges from about 0.5 to 1 microns.

In a preferred implementation of the twenty-ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the twenty-ninth embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the exposed portions of the silicon wafer **8500** in step **5612** is performed using a layer of photoresist as a masking layer.

Referring to **FIGS. 56a, 56b, and 86a-86p**, the thirtieth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of: (1) provide a silicon wafer **8600** in step **5602**, as illustrated in **FIG. 86a**, (2) apply a buffer pad layer **8605** of silicon dioxide onto the silicon wafer **8600** in step **5604**, as illustrated in **FIG. 86b**, (3) apply a layer **8610** of silicon nitride onto the silicon wafer **8600** in step **5606**, as illustrated in **FIG. 86c**, (4) pattern the layer **8610** of silicon nitride in step **5608**, as illustrated in **FIG. 86d**, (5) pattern the buffer pad layer **8605** of silicon dioxide in step **5610**, as illustrated in **FIG. 86e**, (6) thin etch the exposed portions of the silicon wafer **8600** in step **5612**, as illustrated in **FIG. 86f**, (7) grow a field layer **8615** of silicon dioxide onto the portions of the silicon wafer **8600** not covered by the patterned layer **8610** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least

as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 86g**, (8) pattern the layers **8605** and **8615** of silicon dioxide in step **5616**, as illustrated in **FIG. 86h**, (9) apply and pattern a layer **8620** of photoresist onto the silicon wafer **8600** in step **5620**, as illustrated in **FIG. 86i**, (10) etch the exposed portions of the silicon wafer **8600** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 86j**, (11) etch the exposed portions of the layers **8605** and **8615** of silicon dioxide in step **5624**, as illustrated in **FIG. 86k**, (12) remove the layer **8620** of photoresist in step **5628**, as illustrated in **FIG. 86l**, (13) etch the exposed portions of the silicon wafer **8600** in step **5630**, as illustrated in **FIG. 86m**, (14) etch the exposed portions of the layers **8605** and **8615** of silicon dioxide in step **5632**, as illustrated in **FIG. 86n**, (15) etch the exposed portions of the silicon wafer **8600** in step **5634**, as illustrated in **FIG. 86o**, and (16) remove the remaining portions of the layers **8605**, **8610** and **8615** of silicon dioxide and silicon nitride, as illustrated in **FIG. 86p**.

In a preferred implementation of the thirtieth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8605** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8610** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8615** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **8620** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **8600** ranges from about 0.5 to 1 microns.

In a preferred implementation of the thirtieth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the thirtieth embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the exposed

portions of the silicon wafer **8600** in step **5612** is performed using a layer of photoresist as a masking layer.

Referring to **FIGS. 56a, 56b, and 87a-87p**, the thirty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of: (1) provide a silicon wafer **8700** in step **5602**, as illustrated in **FIG. 87a**, (2) apply a buffer pad layer **8705** of silicon dioxide onto the silicon wafer **8700** in step **5604**, as illustrated in **FIG. 87b**, (3) apply a layer **8710** of silicon nitride onto the silicon wafer **8700** in step **5606**, as illustrated in **FIG. 87c**, (4) pattern the layer **8710** of silicon nitride in step **5608**, as illustrated in **FIG. 87d**, (5) pattern the buffer pad layer **8705** of silicon dioxide in step **5610**, as illustrated in **FIG. 87e**, (6) thin etch the exposed portions of the silicon wafer **8700** in step **5612**, as illustrated in **FIG. 87f**, (7) grow a field layer **8715** of silicon dioxide onto the portions of the silicon wafer **8700** not covered by the patterned layer **8710** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 87g**, (8) pattern the layers **8705** and **8715** of silicon dioxide in step **5616**, as illustrated in **FIG. 87h**, (9) apply and pattern a layer **8720** of photoresist onto the silicon wafer **8700** in step **5620**, as illustrated in **FIG. 87i**, (10) etch the exposed portions of the silicon wafer **8700** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 87j**, (11) etch the exposed portions of the silicon wafer **8700** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 87k**, (12) remove the layer **8720** of photoresist in step **5628**, as illustrated in **FIG. 87l**, (13) etch the exposed portions of the silicon wafer **8700** in step **5630**, as illustrated in **FIG. 87m**, (14) etch the exposed portions of the layers **8705** and **8715** of silicon dioxide in step **5632**, as illustrated in **FIG. 87n**, (15) etch the exposed portions of the silicon wafer **8700** in step **5634**, as illustrated in **FIG. 87o**, and (16) remove the remaining portions of the layers **8705**, **8710**, and **8715** of silicon dioxide and silicon nitride, as illustrated in **FIG. 87p**.

In a preferred implementation of the thirty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8705** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8710** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8715** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **8720** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **8700** ranges from about 0.5 to 1 microns.

In a preferred implementation of the thirty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the thirty-first embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the exposed portions of the silicon wafer **8700** in step **5612** is performed using a layer of photoresist as a masking layer.

Referring to **FIGS. 56a, 56b, and 88a-88q**, the thirty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of: (1) provide a silicon wafer **8800** in step **5602**, as illustrated in **FIG. 88a**, (2) apply a buffer pad layer **8805** of silicon dioxide onto the silicon wafer **8800** in step **5604**, as illustrated in **FIG. 88b**, (3) apply a layer **8810** of silicon nitride onto the silicon wafer **8800** in step **5606**, as illustrated in **FIG. 88c**, (4) pattern the layer **8810** of silicon nitride in step **5608**, as illustrated in **FIG. 88d**, (5) pattern the buffer pad layer **8805** of silicon dioxide in step **5610**, as illustrated in **FIG. 88e**, (6) thin etch the exposed portions of the silicon wafer **8800** in step **5612**, as illustrated in **FIG. 88f**, (7) grow a field layer **8815** of silicon dioxide onto the portions of the silicon wafer **8800** not covered by the patterned layer **8810** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least

as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 88g**, (8) pattern the layers **8805** and **8815** of silicon dioxide in step **5616**, as illustrated in **FIG. 88h**, (9) apply and pattern a layer **8820** of photoresist onto the silicon wafer **8800** in step **5620**, as illustrated in **FIG. 88i**, (10) etch the exposed portions of the silicon wafer **8800** using a plasma or gaseous etchant in step **5622**, as illustrated in **FIG. 88j**, (11) etch the exposed portions of the layers **8805** and **8815** of silicon dioxide in step **5624**, as illustrated in **FIG. 88k**; (12) etch the exposed portions of the silicon wafer **8800** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 88l**, (13) remove the layer **8820** of photoresist in step **5628**, as illustrated in **FIG. 88m**, (14) etch the exposed portions of the silicon wafer **8800** in step **5630**, as illustrated in **FIG. 88n**, (15) etch the exposed portions of the layers **8805** and **8815** of silicon dioxide in step **5632**, as illustrated in **FIG. 88o**, (16) etch the exposed portions of the silicon wafer **8800** in step **5634**, as illustrated in **FIG. 88p**, and (17) remove the remaining portions of the layers **8805**, **8810** and **8815** of silicon dioxide and silicon nitride, as illustrated in **FIG. 88q**.

In a preferred implementation of the thirty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8805** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8810** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8815** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **8820** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **8800** ranges from about 0.5 to 1 microns.

In a preferred implementation of the thirty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the thirty-second embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the exposed portions of the silicon wafer **8800** in step **5612** is performed using a layer of photoresist as a masking layer.

5 Referring to **FIGS. 56a, 56b, and 89a-89o**, the thirty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of:

10 (1) provide a silicon wafer **8900** in step **5602**, as illustrated in **FIG. 89a**, (2) apply a buffer pad layer **8905** of silicon dioxide onto the silicon wafer **8900** in step **5604**, as illustrated in **FIG. 89b**, (3) apply a layer **8910** of silicon nitride onto the silicon wafer **8900** in step **5606**, as illustrated in **FIG. 89c**, (4) pattern the layer **8910** of silicon nitride in step **5608**, as illustrated in **FIG. 89d**, (5) pattern the buffer pad layer **8905** of silicon dioxide in step **5610**, as illustrated in **FIG. 89e**,

15 (6) thin etch the exposed portions of the silicon wafer **8900** in step **5612**, as illustrated in **FIG. 89f**, (7) grow a field layer **8915** of silicon dioxide onto the portions of the silicon wafer **8900** not covered by the patterned layer **8910** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 89g**, (8) pattern the layers **8905** and **8915** of silicon dioxide in step **5616**, as illustrated in **FIG. 89h**,

20 (9) apply and pattern a layer **8920** of photoresist onto the silicon wafer **8900** in step **5620**, as illustrated in **FIG. 89i**, (10) etch the exposed portions of the layers **8905** and **8915** of silicon dioxide in step **5624**, as illustrated in **FIG. 89j**; (11) remove the layer **8920** of photoresist in step **5628**, as illustrated in **FIG. 89k**,

25 (12) etch the exposed portions of the silicon wafer **8900** in step **5630**, as illustrated in **FIG. 89l**, (13) etch the exposed portions of the layers **8905** and **8915** of silicon dioxide in step **5632**, as illustrated in **FIG. 89m**, (14) etch the exposed portions of the silicon wafer **8900** in step **5634**, as illustrated in **FIG. 89n**, and (15) remove the remaining portions of the layers **8905, 8910 and 8915** of silicon dioxide and silicon nitride, as illustrated in **FIG. 89o**.

30

In a preferred implementation of the thirty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **8905** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **8910** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **8915** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **8920** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **8900** ranges from about 0.5 to 1 microns.

In a preferred implementation of the thirty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the thirty-third embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the exposed portions of the silicon wafer **8800** in step **5612** is performed using a layer of photoresist as a masking layer.

Referring to **FIGS. 56a, 56b, and 90a-90p**, the thirty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of: (1) provide a silicon wafer **9000** in step **5602**, as illustrated in **FIG. 90a**, (2) apply a buffer pad layer **9005** of silicon dioxide onto the silicon wafer **9000** in step **5604**, as illustrated in **FIG. 90b**, (3) apply a layer **9010** of silicon nitride onto the silicon wafer **9000** in step **5606**, as illustrated in **FIG. 90c**, (4) pattern the layer **9010** of silicon nitride in step **5608**, as illustrated in **FIG. 90d**, (5) pattern the buffer pad layer **9005** of silicon dioxide in step **5610**, as illustrated in **FIG. 90e**, (6) thin etch the exposed portions of the silicon wafer **9000** in step **5612**, as illustrated in **FIG. 90f**, (7) grow a field layer **9015** of silicon dioxide onto the portions of the silicon wafer **9000** not covered by the patterned layer **9010** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least

as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 90g**, (8) pattern the layers **9005** and **9015** of silicon dioxide in step **5616**, as illustrated in **FIG. 90h**, (9) apply and pattern a layer **9020** of photoresist onto the silicon wafer **9000** in step **5620**, as illustrated in **FIG. 90i**, (10) etch the exposed portions of the layers **9005** and **9015** of silicon dioxide in step **5624**, as illustrated in **FIG. 90j**; (11) etch the exposed portions of the silicon wafer **9000** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 90k**; (12) remove the layer **9020** of photoresist in step **5628**, as illustrated in **FIG. 90l**, (13) etch the exposed portions of the silicon wafer **9000** in step **5630**, as illustrated in **FIG. 90m**, (14) etch the exposed portions of the layers **9005** and **9015** of silicon dioxide in step **5632**, as illustrated in **FIG. 90n**, (15) etch the exposed portions of the silicon wafer **9000** in step **5634**, as illustrated in **FIG. 90o**, and (16) remove the remaining portions of the layers **9005**, **9010** and **9015** of silicon dioxide and silicon nitride, as illustrated in **FIG. 90p**.

In a preferred implementation of the thirty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process parameters are employed: the thickness of the pad buffer layer **9005** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **9010** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **9015** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **9020** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **9000** ranges from about 0.5 to 1 microns.

In a preferred implementation of the thirty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the thirty-fourth embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the

exposed portions of the silicon wafer **9000** in step **5612** is performed using a layer of photoresist as a masking layer.

Referring to **FIGS. 56a, 56b, and 91a-91o**, the thirty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, using photoresist as an etching mask with the use of an etched buffer layer of silicon dioxide and a thin etch of the exposed portions of the silicon wafer, includes the steps of: (1) provide a silicon wafer **9100** in step **5602**, as illustrated in **FIG. 91a**, (2) apply a buffer pad layer **9105** of silicon dioxide onto the silicon wafer **9100** in step **5604**, as illustrated in **FIG. 91b**, (3) apply a layer **9110** of silicon nitride onto the silicon wafer **9100** in step **5606**, as illustrated in **FIG. 91c**, (4) pattern the layer **9110** of silicon nitride in step **5608**, as illustrated in **FIG. 91d**, (5) pattern the buffer pad layer **9105** of silicon dioxide in step **5610**, as illustrated in **FIG. 91e**, (6) thin etch the exposed portions of the silicon wafer **9100** in step **5612**, as illustrated in **FIG. 91f**, (7) grow a field layer **9115** of silicon dioxide onto the portions of the silicon wafer **9100** not covered by the patterned layer **9110** of silicon nitride in step **5614** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), as illustrated in **FIG. 91g**, (8) pattern the layers **9105** and **9115** of silicon dioxide in step **5616**, as illustrated in **FIG. 91h**, (9) apply and pattern a layer **9120** of photoresist onto the silicon wafer **9100** in step **5620**, as illustrated in **FIG. 91i**, (10) etch the exposed portions of the silicon wafer **9100** using a plasma or gaseous etchant in step **5626**, as illustrated in **FIG. 91j**, (11) remove the layer **9120** of photoresist in step **5628**, as illustrated in **FIG. 91k**, (12) etch the exposed portions of the silicon wafer **9100** in step **5630**, as illustrated in **FIG. 91l**, (13) etch the exposed portions of the layers **9105** and **9115** of silicon dioxide in step **5632**, as illustrated in **FIG. 91m**, (14) etch the exposed portions of the silicon wafer **9100** in step **5634**, as illustrated in **FIG. 91n**, and (15) remove the remaining portions of the layers **9105**, **9110**, and **9115** of silicon dioxide and silicon nitride, as illustrated in **FIG. 91o**.

In a preferred implementation of the thirty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the following process

parameters are employed: the thickness of the pad buffer layer **9105** of silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer **9110** of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer **9115** of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of layer **9120** of photoresist ranges from about 1 to 10 microns, and the depth of the thin etch of the exposed portions of the silicon wafer **9100** ranges from about 0.5 to 1 microns.

In a preferred implementation of the thirty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the etching performed in steps **5622** and **5626** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred implementation of the thirty-fifth embodiment of the LOCOS merged-mask micro-machining process **5600**, the thin etch of the exposed portions of the silicon wafer **9100** in step **5612** is performed using a layer of photoresist as a masking layer.

In an alternative embodiment, wet anisotropic etchants such as, for example, (1) aqueous KOH mixed with isopropyl alcohol, (2) tetramethyl ammonium hydroxide, (3) a mixture of ethylenediamine and pyrocatechol, (4) cesium hydroxide, (5) a mixture of ethylene diamine pyrocatechol and water, (6) a mixture of ethanol amine, gallic acid and water, or (7) hydrazine are used in place of KOH.

In an alternative embodiment, where a masking layer of silicon dioxide is used with KOH etching, a thicker layer of silicon dioxide is used and then successively patterned and thinned to create a multiple thickness structure. A layer of a different masking material such as, for example, silicon nitride or silicon carbide is then applied and patterned. This combination of masking layers then provides a merged-mask.

In an alternative embodiment, where DRIE is combined with KOH etching, a number of masking layers are patterned for use with KOH, while other masking layers are patterned for use with DRIE. A combination of DRIE

and KOH etching steps interspersed with mask removal steps are then used to form multiple etching depth structures in a substrate.

5 In an alternative embodiment, gaseous or plasma etching is used in combination with DRIE. In this manner, a merged-mask can be provided having multiple photoresist layers or photoresist layers in combination with metal masking layers.

In an alternative embodiment, DRIE and plasma etching are alternatively used.

10 In an alternative embodiment, masking materials that include diamond, SiC, metals and polymers are used in conjunction with the use of a combination of wet etching and dry etching.

In an alternative embodiment, timed erosion of a multiple thickness etch resistant layer of material is used to provide the different masking layers.

15 In an alternative embodiment, gaseous etchants such as, for example, xenon difluoride, chlorine trifluoride, bromine trifluoride, bromine heptafluoride, or iodine heptafluoride are used in place of, or in addition, to DRIE.

In an alternative embodiment, masking materials such as, for example, silicon carbide, polycrystalline diamond, etch resistant polymers, or aluminum are used in place of silicon dioxide and/or silicon nitride.

20 Referring now to **FIGS. 92a** and **92b**, several alternative embodiments of localized oxidation of silicon (LOCOS) merged-mask micro-machining processes **9200** including multiple etch depths and optionally including the use of photoresist as an etching mask are illustrated. The processes **9200** are substantially a combination of the processes **5000** and **5600**, described above
25 with reference to **FIGS. 50-91o**. In a preferred embodiment, one of these processes **9200** is used in forming at least a portion of the mirror **210** and/or the top and bottom caps, **205** and **215**. As illustrated in **FIGS. 92a** and **92b**, the LOCOS merged-mask micro-machining process **9200** preferably includes the following process steps: (1) provide a silicon wafer in step **9202**, (2) (optionally)
30 grow a buffer layer of silicon dioxide onto the surface of the silicon wafer in step **9204**, (3) apply a layer of silicon nitride onto the silicon wafer in step **9206**, (4)

pattern the layer of silicon nitride in step **9208**, (5) (optionally) pattern the exposed portions of the buffer layer of silicon dioxide in step **9210**, (6) (optionally) thin etch the exposed portions of the surface of the silicon wafer in step **9212**, (7) grow field layers of silicon dioxide onto the portions of the silicon wafer not covered by the patterned layer of silicon nitride in step **9214** (the field layer of silicon dioxide is preferably at least as thick as the combined thicknesses of the layer of silicon nitride and the optional buffer layer of silicon dioxide), (8) pattern layer(s) of silicon dioxide in step **9216** (the etch depth is a fraction of the total thickness of the layers of silicon dioxide), (9) repeat step **9216** a predetermined number of times in step **9218**, (10) (optionally) etch the exposed portions of the silicon wafer using photoresist as an etch mask in step **9220**, (11) (optionally) apply and pattern a layer of photoresist onto the silicon wafer in step **9222**, (12) (optionally) etch the exposed portions of the silicon wafer using a plasma or gaseous etchant in step **9224**, (13) (optionally) remove the exposed portions of the layer(s) of silicon dioxide in step **9226**, (14) (optionally) etch the exposed portions of the silicon wafer in step **9228**, (15) remove the layer of photoresist in step **9230**, (16) etch the exposed portions of the silicon wafer in step **9232**, (17) etch the exposed portions of the layers of silicon dioxide in step **9234** (the etch depth is a fraction of the total thickness of the layers of silicon dioxide), (18) etch the exposed portions of the silicon wafer in step **9236**, and (19) repeat steps **9234** and **9236** a predetermined number of times.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

In a preferred implementation of the processes **9200**, the following process parameters are employed: the thickness of the pad buffer layer of

silicon dioxide ranges from about 0.03 to 1 microns, the thickness of the layer of silicon nitride ranges from about 0.1 to 2.0 microns, the thickness of the field layer of silicon dioxide ranges from about 0.2 to 3.0 microns, the thickness of the layer of photoresist ranges from about 1 to 10 microns, the depth of the thin etch of the exposed portions of the silicon wafer ranges from about 0.5 to 1 microns, the partial etching of the layers of silicon dioxide is repeated from 1 to 10 times for etch depths ranging from about 0.01 to 3 microns, and the partial etching of the silicon substrate is repeated from 1 to 10 times for etch depths ranging from about 1 to 500 microns.

In a preferred implementation of the processes **9200**, the etching performed in steps **9224** and **9228** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal. In a preferred implementation of the processes **9200**, the etching performed in steps **9232** and **9236** preferably comprises KOH etching.

In a preferred implementation of the processes **9200**, the etching of the exposed portions of the silicon wafer in steps **9232** and **9236** is provided using KOH.

Referring now to **FIGS. 93a** and **93b**, several alternative embodiments of merged-mask micro-machining processes **9300** including the use of various alternative masking materials, multiple etch depths, and optionally including the use of photoresist as an etching mask are illustrated. The processes **9300** are substantially identical to the processes **9200** with the subtraction of the various alternative methods of LOCOS, but with the addition of various alternative masking materials. In a preferred embodiment, one of these processes **9300** is used in forming at least a portion of the mirror **210** and/or the top and bottom caps, **205** and **215**. As illustrated in **FIGS. 93a** and **93b**, the merged-mask micro-machining process **9300** preferably includes the following process steps: (1) provide a silicon wafer in step **9302**, (2) apply a masking layer of one of several alternative materials in step **9304**, (3) pattern the masking layer in step **9306** (the etch depth is a fraction of the total thickness of the masking layer), (4) repeat step **9306** a predetermined number of times in step **9308**, (5) (optionally)

etch the exposed portions of the silicon wafer using photoresist as an etch mask in step **9310**, (6) (optionally) apply and pattern a layer of photoresist onto the silicon wafer in step **9312**, (7) (optionally) etch the exposed portions of the silicon wafer using a plasma or gaseous etchant in step **9314**, (8) (optionally) remove the exposed portions of the masking layer in step **9316**, (9) (optionally) etch the exposed portions of the silicon wafer in step **9318**, (10) remove the layer of photoresist in step **9320**, (11) etch the exposed portions of the silicon wafer in step **9322**, (12) etch a fraction of the exposed portions of the masking layer in step **9324** (the etch depth is a fraction of the total thickness of the masking layer), (13) etch the exposed portions of the silicon wafer in step **9326** (the etch depth is a fraction of the total thickness of the silicon wafer), and (14) repeat steps **9324** and **9326** a predetermined number of times in step **9328**.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

In a preferred implementation of processes **9300**, the following process parameters are employed: the partial etching of the masking layer is repeated from 1 to 10 times for etch depths ranging from about 0.01 to 3 microns, and the partial etching of the silicon substrate is repeated from 1 to 10 times for etch depths ranging from about 1 to 500 microns.

In a preferred implementation of the processes **9300**, the etching performed in steps **9314** and **9318** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal. In a preferred implementation of the processes **9300**, the etching performed in steps **9322** and **9326** comprises KOH etching.

In a preferred implementation of the processes **9300**, the etching of the exposed portions of the silicon wafer in steps **9322** and **9326** is provided using KOH.

Referring now to **FIGS. 94-95h**, an embodiment of a merged mask process **9400** for providing multiple etch depths in a substrate will now be described. In a preferred embodiment, the process **9400** includes the steps of:

5 process **9400** for providing multiple etch depths in a substrate will now be described. In a preferred embodiment, the process **9400** includes the steps of:

(1) provide a silicon substrate **9500** in step **9405**, as illustrated in **FIG. 95a**; (2) deposit a layer **9505** of a first masking material onto the silicon substrate **9500** in step **9410**, as illustrated in **FIG. 95b**; (3) pattern the layer **9505** of the first

10 masking material in step **9415**, as illustrated in **FIG. 95c**; (4) deposit a layer **9510** of a second masking material onto the silicon substrate **9500** in step **9420**, as illustrated in **FIG. 95d**; (5) pattern the layer **9510** of the second masking material in step **9425**, as illustrated in **FIG. 95e**; (6) etch the exposed portions **9500a** of the silicon substrate **9500** to a first depth in step **9430**, as illustrated

15 in **FIG. 95f**; (7) etch the exposed portions of the layer **9505** of the first masking material in step **9435**, as illustrated in **FIG. 95g**; and (8) etch the exposed portions, **9500a**, **9500b** and **9500c**, of the silicon substrate **9500** to a second depth in step **9440**, as illustrated in **FIG. 95h**.

As will be recognized by persons having ordinary skill in the art and

20 having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed

25 portions of a layer of material or a substrate.

In a preferred embodiment, as illustrated in **FIG. 95e-95h**, the exposed portions, **9500a**, **9500b** and **9500c** of the silicon substrate **9500** have approximately the same width. In this manner, in a preferred embodiment, the region **9500a** has a deeper final etch depth than that of the regions **9500b** and

30 **9500c**.

In a preferred implementation of the process **9400**, the first masking material comprises silicon dioxide; the second masking material comprises photoresist; the thickness of the first masking material ranges from about 1000 to 6000 angstroms; the thickness of the second masking material ranges from about 3 to 4 microns; the first etch depth ranges from about 10 to 250 microns; and the second etch depth range from about 10 to 300 microns. In an alternative embodiment of the process **9400**, the first masking material comprises metal and the second masking material comprises photoresist or an etch resistant polymer.

In a preferred implementation of the process **9400**, the etching performed in steps **9430** and **9440** comprises DRIE or plasma etching and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

Referring now to **FIGS. 96-97h**, an embodiment of a merged-mask process **9600** for etching a silicon substrate will be described. In a preferred embodiment, the process **9600** includes the steps of: (1) provide a silicon substrate **9700** in step **9605**, as illustrated in **FIG. 97a**; (2) deposit a layer **9705** of a first masking material onto the silicon substrate **9700** in step **9610**, as illustrated in **FIG. 97b**; (3) pattern the layer **9705** of the first masking material in step **9615**, as illustrated in **FIG. 97c**; (4) deposit a layer **9710** of a second masking material onto the silicon substrate **9700** in step **9620**, as illustrated in **FIG. 97d**; (5) pattern the layer **9710** of the second masking material in step **9625**, as illustrated in **FIG. 97e**; (6) etch the exposed portions of the silicon substrate **9700** for a first time period, as illustrated in **FIG. 97f**; (7) etch the exposed portions of the layer **9705** of the first masking material, as illustrated in **FIG. 97g**; and (8) etch the exposed portions of the silicon substrate **9700** for a second time period, as illustrated in **FIG. 97h**. In this manner, the etch depths of all of the etched areas of the silicon substrate **9700** are substantially equal.

As will be recognized by persons having ordinary skill in the art and having the benefit of the present disclosure, patterning refers to the sequential operations of conventional photolithography and etching in order to produce patterns in a layer of material or a substrate. As will also be recognized by

persons having ordinary skill in the art and having the benefit of the present disclosure, etching refers to the removal of at least a portion of the exposed portions of a layer of material or a substrate.

5 In a preferred embodiment, as illustrated in **FIG. 97e-97h**, the exposed portion **9700a** of the silicon substrate **9500** has a smaller width than that for the portions **9700b** and **9700c**. In this manner, in a preferred embodiment, the regions **9700a**, **9700b** and **9700c** have final etch depths that are substantially equal. In a preferred embodiment, the etching time periods are adapted as a function of the widths of the exposed portions **9700a**, **9700b** and **9700c** of the
10 silicon substrate **9500** to provide substantially equal final etch depths wherein the smaller exposed portion **9700a** is etched more often than the larger exposed portions **9700b** and **9700c**.

In a preferred implementation of the process **9600**, the first masking material comprises silicon dioxide; the second masking material comprises
15 photoresist; the thickness of the first masking material ranges from about 1000 to 6000 angstroms; the thickness of the second masking material ranges from about 3 to 4 microns; the first time period ranges from about 5 to 30 minutes; and the second time period range from about 30 minutes to 2 hours. More generally, in a preferred embodiment, the first time period and the second time
20 period are empirically determined by measuring the etch rates for different regions of a substrate having dissimilar widths.

In an alternative embodiment of the process **9600**, the first masking material is silicon dioxide, metal, or an etch resistant polymer. In an alternative embodiment of the process **9600**, the second masking material is photoresist
25 or an etch resistant polymer.

In a preferred implementation of the process **9600**, the etching performed in steps **9630** and **9640** comprises DRIE and provides sidewalls having an angle of $90^\circ \pm 45^\circ$ relative to horizontal.

In a preferred embodiment, the process **9600** is used to eliminate the so-called microloading effect of plasma dry etching in which smaller exposed areas
30 of silicon are etched at slower rates than larger exposed areas. Thus, the

process **9600** provides multiple etching areas, having dissimilar exposed areas, in a silicon substrate having substantially equal final etching depths. In this manner, the microloading effect of plasma dry etching, as well as other types of etching, is optimally overcome.

5 In several alternative embodiments of the merged mask micro machining processes described in the present disclosure, as illustrated, for example, in **FIG. 44-97h**, the etching of the silicon substrate may be carried out using a variety of methods. For example, energetic ions produced in a plasma may be used to etch the silicon. Examples of gases used in a plasma for etching silicon
10 include: sulfur hexafluoride, chlorine, and bromine. A preferred etching technique for high-aspect-ratio trench etching, also called deep-reactive ion etching (DRIE), is to time multiplex an etching gas such as, for example, sulfur hexafluoride with a gas used to form a passivating layer on the sidewalls of the trench. C_4F_8 is an example of a gas used for passivation of silicon sidewalls.
15 Another alternative method of etching silicon is using a gas that is sufficiently reactive that etching of silicon takes place even without the activation by a plasma. Examples of reactive gases for etching silicon include, for example, xenon difluoride, chlorine trifluoride, bromine trifluoride, bromine heptafluoride, and iodine heptafluoride. Still another alternative method of etching silicon
20 using a merged mask process includes the use of liquid etchants. The liquid may etch single crystal silicon in an anisotropic fashion. Examples of wet anisotropic etchants of silicon include, for example, aqueous potassium hydroxide (KOH), aqueous KOH mixed with isopropyl alcohol, tetramethyl ammonium hydroxide, aqueous cesium hydroxide, a mixture of: ethylene
25 diamine, pyrocatechol, and water, and a mixture of: ethanolamine, gallic acid, and water. The liquid may etch single crystal silicon isotropically. An example of an isotropic etchant of silicon is a mixture of nitric acid, ammonium fluoride, and water.

30 In several alternative embodiments, for the merged mask processes described in this application, as illustrated for example in **FIGS. 44-97h**, the etching of the silicon substrate may be carried out, for example, by a

combination of methods. For example, the etching of the silicon substrate may proceed with one wet anisotropic etchant, and then the silicon substrate may be inserted into a different anisotropic etchant or etch chamber. A preferred embodiment of the use of a combination of etchants includes the use of: (1) aqueous KOH to etch silicon to achieve the advantage of a relatively high etch rate of silicon, and then (2) aqueous KOH mixed with isopropyl alcohol to etch the silicon to achieve a large ratio of etching rates between lightly doped single-crystal silicon and single-crystal silicon with substantial boron doping. In general, in a preferred embodiment, the etching process includes: (1) one etchant from any of the classes of wet etchants, plasma etchants, and reactive gaseous etchants, and then (2) switching to another etchant from one of the three classes. In a preferred embodiment, the changing of the silicon etch method may take place a multiplicity of times. The switching between etchants preferably takes advantage of the different etching properties to allow the creation of etch profiles desired for a particular micromechanical structure.

In several alternative embodiments, for the merged mask processes described in this application, as illustrated for example in **FIGS. 44-97h**, the preferred embodiment for etching of the silicon substrate is selected such that the etching method causes insignificant erosion of the masking material.

In several alternative embodiments, referring to **FIG. 44**, silicon etchants from any of the three classes of wet etchants, plasma etchants, and reactive gaseous etchants are preferred for both silicon etching steps **4445** and **4455**. Again referring to **FIG. 44**, silicon etchants from any of the three classes of wet etchants, plasma etchants, and reactive gaseous etchants, for example, may be used for the optional thin silicon etch steps **4430**; however, a preferred embodiment uses a plasma etchant.

In several alternative embodiments, referring to **FIG. 50**, silicon etchants from any of the three classes of wet etchants, plasma etchants, and reactive gaseous etchants are preferred for silicon etching steps **5050**, **5060**, and **5065**.

Among the class of wet etchants, tetramethyl ammonium hydroxide, with its

relatively low etch rate of silicon dioxide in comparison to the etch rate of silicon, is preferred.

5 In several alternative embodiments, referring to **FIGS. 56a-56b**, silicon etchants from any of the three classes of wet etchants, plasma etchants, and reactive gaseous etchants are preferred for silicon etching steps **5630**, and **5634**. A silicon etchant from the class of plasma etchants or reactive gaseous etchants is preferred for the silicon etching steps **5622** and **5626**.

10 In several alternative embodiments, referring to **FIG. 92a-92b**, silicon etchants from any of the three classes of wet etchants, plasma etchants, and reactive gaseous etchants are preferred for silicon etching steps **9232**, **9236**, and **9238**. A silicon etchant from the class of plasma etchants or reactive gaseous etchants are preferred for the silicon etching steps **9224** and **9228**.

15 In several alternative embodiments, referring to **FIGS. 93a-93b**, silicon etchants from any of the three classes of wet etchants, plasma etchants, and reactive gaseous etchants are preferred for silicon etching steps **9322**, **9326**, and **9328**. A silicon etchant from the class of plasma etchants or reactive gaseous etchants are preferred for the silicon etching steps **9314** and **9318**.

20 In several alternative embodiments, referring to **FIGS. 94** through **97h**, the preferred silicon etching method is with a plasma etchant, and the particular preferred etching method is plasma etching with time multiplexing of an etch gas and a gas for passivating the silicon sidewalls.

25 Referring to **FIGS. 44-97h**, the illustrative merged-mask micro-machining processes include features on one wafer surface only; however, in a preferred embodiment, these processes are conducted on both sides of the wafer. In this manner, etching is provided on both sides of the wafer.

30 A method of fabricating a three-dimensional structure has been described that includes (1) providing a substrate; (2) applying a layer of a first masking material onto the substrate; (3) patterning the layer of the first masking material; (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material; (5) patterning the layer of the

second masking material; (6) etching the exposed portions of the substrate; (7) etching the exposed portions of the layer of the second masking material; and (8) etching the exposed portions of the substrate. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, etching the exposed portions of the substrate includes thin etching. In a preferred embodiment, step (2) includes applying a layer of a third masking material onto the substrate and applying the layer of the first masking material onto the layer of the third masking material. In a preferred embodiment, applying the layer of the third masking material includes thermal oxidation of the substrate. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials. In a preferred embodiment, applying the layer of the second material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning the layers of the second and third masking materials. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, etching the exposed portions of the substrate includes thin etching. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials. In a preferred embodiment, applying the layer of second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning the layers of the second and third masking materials. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, etching the exposed portions of the substrate includes thin etching. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials. In a preferred

embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning the layers of the second and third masking materials. In a preferred embodiment, the first masking material comprises silicon nitride; and wherein
5 the second masking material comprises silicon dioxide. In a preferred embodiment, the first masking material comprises silicon nitride, the second masking material comprises silicon dioxide; and the third masking material comprises silicon dioxide. In a preferred embodiment, steps (6) and (8) comprise wet etching the exposed portions of the substrate.

10 A method of fabricating a three-dimensional structure has also been described that includes providing a substrate, applying a layer of a first masking material onto the substrate, patterning the layer of the first masking material, applying a layer of a second masking material onto the patterned layer of the first masking material, patterning the layer of the second masking material, dry
15 etching the exposed portions of the substrate, etching the exposed portions of the patterned layer of the first masking material, and dry etching the exposed portions of the substrate. In a preferred embodiment, applying the layer of the first masking material includes thermal oxidation of the substrate. In a preferred embodiment, the first masking material is selected from the group consisting of
20 silicon dioxide, metal, and etch resistant polymer, and the second masking material is selected from the group consisting of photoresist and etch resistant polymer. In a preferred embodiment, dry etching comprises deep reactive ion etching.

A method of fabricating a three-dimensional structure has also been
25 described that includes (1) providing a substrate, (2) applying a layer of a first masking material onto the substrate, (3) patterning the layer of the first masking material, (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material, (5) patterning a fraction of the
30 thickness of the layer of the second masking material a plurality of times, (6) etching the exposed portions of the substrate, (7) etching a fraction of the thickness of the exposed portions of the layer of the second masking material,

(8) etching the exposed portions of the substrate, and (9) repeating steps (7) and (8) a plurality of times. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched.

5 In a preferred embodiment, step (2) includes applying a layer of a third masking material onto the substrate and applying the layer of the first masking material onto the layer of the third masking material. In a preferred embodiment, applying the layer of the third masking material includes thermal oxidation of the

10 substrate. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials. In a preferred embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes

15 patterning a fraction of the thickness of the layers of the second and third masking materials a plurality of times. In a preferred embodiment, the method further includes prior to step (4), patterning the layer of the third masking material. In a preferred embodiment, step (4) includes applying a layer of a

20 second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials. In a preferred embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes

25 patterning a fraction of the layers of the second and third masking materials a plurality of times. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched. In a

30 preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials. In a preferred embodiment, applying the

layer of the second masking material includes local oxidation of the substrate.

In a preferred embodiment, step (5) includes patterning a fraction of the layers of the second and third masking materials a plurality of times. In a preferred embodiment, the first masking material comprises silicon nitride; and wherein the second masking material comprises silicon dioxide. In a preferred embodiment, the first masking material comprises silicon nitride; wherein the second masking material comprises silicon dioxide; and wherein the third masking material comprises silicon dioxide. In a preferred embodiment, steps (6) and (8) comprise wet etching of the exposed portions of the substrate.

A method of fabricating a three-dimensional structure has also been described that includes (1) providing a substrate, (2) applying a layer of a first masking material onto the substrate, (3) patterning the layer of the first masking material, (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material, (5) patterning the layer of the second masking material, (6) applying a layer of a third masking material onto substrate, (7) patterning the layer of the third masking material, (8) etching the layer of the third masking material, (9) etching the exposed portions of the substrate, (10) etching the exposed portions of the layer of the second masking material, and (11) etching the exposed portions of the substrate. In a preferred embodiment, the first, second and third masking materials comprise silicon nitride, silicon dioxide, and photoresist. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched. In a preferred embodiment, step (2) includes applying a layer of a fourth masking material onto the substrate and applying the layer of the first masking material onto the layer of the fourth masking material. In a preferred embodiment, applying the layer of the fourth masking material includes thermal oxidation of the substrate. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials. In a preferred embodiment, applying the layer of the second masking material

includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning the layers of the second and fourth masking materials. In a preferred embodiment, the method further includes prior to step (4), patterning the layer of the fourth masking material. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials. In a preferred embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning the layers of the second and fourth masking materials. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials. In a preferred embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning the layers of the second and fourth masking materials. In a preferred embodiment, the first masking material comprises silicon nitride; wherein the second masking material comprises silicon dioxide; and wherein the third masking material comprises a photoresist material. In a preferred embodiment, the first masking material comprises silicon nitride; wherein the second masking material comprises silicon dioxide; wherein the third masking material comprises a photoresist material; and wherein the fourth masking material comprises silicon dioxide. In a preferred embodiment, the method further includes between steps (7) and (8), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the substrate and etching the exposed portions of the layer of the second masking material. In a preferred embodiment,

etching the exposed portions of the substrate includes dry etching. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the substrate a plurality of times. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the substrate, etching the exposed portions of the layer of the second masking material and etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes: between steps (7) and (8), performing the following: etching the exposed portions of the layer of the second masking material. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the layer of the second masking material and etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, steps (9) and (11) comprise wet etching of the exposed portions of the substrate.

A method of fabricating a three-dimensional structure has also been described that includes (1) providing a substrate, (2) applying a layer of a first masking material onto the substrate, (3) patterning the layer of the first masking material, (4) applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the layer of the first masking material, (5) patterning a fraction of the thickness of the layer of the second masking material a plurality of times, (6) applying a layer of a third masking material onto substrate, (7) patterning the layer of the third masking material, (8) etching the layer of the third masking material, (9) etching the exposed portions of the substrate, (10) etching a fraction of the thickness of the exposed portions of the layer of the second masking material, (11) etching the exposed portions of the substrate, and (12) repeat steps (10) and (11) a plurality of times. In a preferred embodiment, the

first, second and third masking materials comprise silicon nitride, silicon dioxide, and photoresist. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched. In a preferred embodiment, step (2) includes applying a layer of a fourth masking material onto the substrate and applying the layer of the first masking material onto the layer of the fourth masking material. In a preferred embodiment, applying the layer of the fourth masking material includes thermal oxidation of the substrate. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials. In a preferred embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning a fraction of the thickness of the layers of the second and fourth masking materials a plurality of times. In a preferred embodiment, the method further includes prior to step (4), patterning the layer of the fourth masking material. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials. In a preferred embodiment, applying the layer of the second masking material includes local oxidation of the substrate. In a preferred embodiment, step (5) includes patterning a fraction of the thickness of the layers of the second and fourth masking materials a plurality of times. In a preferred embodiment, the method further includes prior to step (4), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are thin etched. In a preferred embodiment, step (4) includes applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials. In a preferred embodiment, applying the layer of the second masking material includes local

oxidation of the substrate. In a preferred embodiment, step (5) includes patterning a fraction of the thickness of the layers of the second and fourth masking materials a plurality of times. In a preferred embodiment, the first masking material comprises silicon nitride, the second masking material comprises silicon dioxide, and the third masking material comprises a photoresist material. In a preferred embodiment, the first masking material comprises silicon nitride, the second masking material comprises silicon dioxide, the third masking material comprises a photoresist material, and the fourth masking material comprises silicon dioxide. In a preferred embodiment, the method further includes between steps (7) and (8), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the substrate and etching the exposed portions of the layer of the second masking material. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the substrate a plurality of times. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the substrate, etching the exposed portions of the layer of the second masking material, and etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the layer of the second masking material. In a preferred embodiment, the method further includes between steps (7) and (8), performing the following: etching the exposed portions of the layer of the second masking material and etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, steps (9) and (11) comprise wet etching.

A method of fabricating a three-dimensional structure has also been described that includes (1) providing a substrate, (2) applying a layer of a first masking material onto the substrate, (3) patterning a fraction of the thickness of the layer of the first masking material a plurality of times, (4) applying a layer of a second masking material onto substrate, (5) patterning the layer of the second masking material, (6) etching the layer of the second masking material, (7) etching the exposed portions of the substrate, (8) etching a fraction of the thickness of the exposed portions of the layer of the first masking material, (9) etching the exposed portions of the substrate, and (10) repeat steps (8) and (9) a plurality of times. In a preferred embodiment, the first masking material is selected from the group consisting of: silicon carbide, silicon nitride, polycrystalline diamond, and an etch resistant polymer. In a preferred embodiment, the second masking material comprises a photoresist material. In a preferred embodiment, the method further includes between steps (5) and (6), etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (5) and (6), performing the following: etching the exposed portions of the substrate and etching the exposed portions of the layer of the second masking material. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (5) and (6), performing the following: etching the exposed portions of the substrate a plurality of times. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (5) and (6), performing the following: etching the exposed portions of the substrate, etching the exposed portions of the layer of the second masking material, and etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, the method further includes between steps (5) and (6), performing the following: etching the exposed portions of the layer of the second masking material. In a preferred embodiment, the method further includes between steps (5) and (6), performing

the following: etching the exposed portions of the layer of the second masking material and etching the exposed portions of the substrate. In a preferred embodiment, the exposed portions of the substrate are dry etched. In a preferred embodiment, steps (7) and (9) include wet etching.

5 A method of fabricating a three-dimensional structure has also been described that includes providing a substrate, applying a layer of a first masking material onto the substrate, patterning the layer of the first masking material, applying a layer of a second masking material onto the patterned first layer of masking material, patterning the layer of the second masking material, dry
10 etching the exposed portions of the substrate, etching the exposed portions of the layer of the first masking material, and dry etching the exposed portions of the substrate. In a preferred embodiment, dry etching includes deep reactive ion etching. In a preferred embodiment, the first masking material is selected from the group consisting of silicon dioxide, metal and etch resistant polymer,
15 and the second masking material is selected from the group consisting of photoresist and etch resistant polymer.

 A method of fabricating a three-dimensional structure has also been described that includes providing a substrate, applying a layer of a first masking material onto the substrate, patterning the layer of the first masking material,
20 applying a layer of a second masking material onto the patterned first layer of masking material, patterning the layer of the second masking material, dry etching a first group of exposed portions of the substrate for a first time period, etching the exposed portions of the layer of the first masking material, and dry etching a second group of exposed portions of the substrate for a second time
25 period, wherein the first time period and the second time period are a function of the relative sizes of the exposed portions of the substrate. In a preferred embodiment, the first group of exposed portions of the substrate include exposed portions having first cross-sectional areas and the second group of exposed portions of the substrate includes exposed portions having first and
30 second cross-sectional areas. The second cross-sectional areas are greater than the first cross-sectional areas. In a preferred embodiment, dry etching includes deep reactive ion etching. In a preferred embodiment, the first

masking material is selected from the group consisting of silicon dioxide, metal and etch resistant polymer, and the second masking material is selected from the group consisting of photoresist and etch resistant polymer.

5 A method of micro-machining a substrate has also been described that includes wet etching the substrate and dry etching the substrate. In a preferred embodiment, the wet etching includes a wet merged-mask micro-machining process. In a preferred embodiment, the method includes the use of masking layers comprised of silicon dioxide and silicon nitride. In a preferred embodiment, the dry etching includes a dry merged-mask micro-machining process. In a preferred embodiment, the method includes the use of masking layers comprised of silicon dioxide and photoresist.

10 A method of creating multiple masking layers for use in micro-machining a substrate has also been described that includes applying a layer of an etch resistant material onto the substrate and eroding different areas of the layer at different rates to form a multiple thickness layer.

15 A method of micromachining a substrate has also been described that includes using a combination of different etchants having different anisotropic properties.

20 A method of micromachining a substrate has also been described that includes decoupling a first etching process from a second etching process.

25 Although illustrative embodiments of the invention have been shown and described, a wide range of modification, changes and substitution is contemplated in the foregoing disclosure. In some instances, some features of the present invention may be employed without a corresponding use of the other features. Accordingly, it is appropriate that the appended claims be construed broadly and in a manner consistent with the scope of the invention.

WHAT IS CLAIMED IS:

1. A method of fabricating a three-dimensional structure, comprising:
 providing a substrate;
 5 applying a layer of a first masking material onto the substrate;
 patterning the layer of the first masking material;
 thin etching exposed portions of the substrate;
 applying a layer of a second masking material onto the etched portions of
 the substrate, the layer of the second masking material is at least as thick as the
 10 layer of the first masking material;
 patterning the layer of the second masking material;
 etching exposed portions of the substrate;
 etching the layer of the second masking material; and
 etching exposed portions of the substrate.
 15
2. The method of claim 1, wherein the first masking material comprises
 silicon nitride; and wherein the second masking material comprises silicon
 dioxide.
- 20 3. The method of claim 1, wherein applying the layer of the second masking
 material includes local oxidation of the substrate.
4. The method of claim 1, wherein etching the exposed portions of the
 substrate comprises wet etching of the exposed portions of the substrate.
 25
5. The method of claim 1 further including between said patterning the layer
 of the second masking material and said etching the exposed portions of the
 substrate, performing the following:
 applying a layer of a third masking material onto the patterned layer of the
 30 second masking material;
 patterning the layer of the third masking material;
 etching exposed areas of the second masking material;
 applying a layer of a fourth masking material onto the substrate;

etching the exposed portions of the substrate; and
removing the fourth masking material.

- 5 6. A method of fabricating a three-dimensional structure, comprising:
providing a substrate;
applying a layer of a first masking material onto the substrate, said first
masking material being one of silicon dioxide and a metal;
patterning the layer of the first masking material;
applying a layer of a second masking material onto the patterned layer of
10 the first masking material, said second masking material being one of a
photoresist and an etch resistant polymer;
patterning the layer of the second masking material;
dry etching the exposed portions of the substrate;
etching the exposed portions of the patterned layer of the first masking
15 material;
and
dry etching the exposed portions of the substrate.

- 20 7. A method of fabricating a three-dimensional structure, comprising:
(1) providing a substrate;
(2) applying a layer of a first masking material onto the substrate;
(3) patterning the layer of the first masking material;
(4) applying a layer of a second masking material onto the portions of the
substrate not covered by the patterned layer of the first masking material, the
25 layer of the second masking material is at least as thick as the layer of the first
masking material;
(5) patterning a fraction of the thickness of the layer of the second
masking material a plurality of times;
(6) etching the exposed portions of the substrate;
30 (7) etching a fraction of the thickness of the exposed portions of the layer
of the second masking material;
(8) etching the exposed portions of the substrate; and
(9) repeating steps (7) and (8) a plurality of times.

8. The method of claim 7, further including prior to step (4), etching the exposed portions of the substrate.
9. The method of claim 7, wherein step (2) comprises:
5 applying a layer of a third masking material onto the substrate; and
 applying the layer of the first masking material onto the layer of the third masking material.
10. The method of claim 9, further including prior to step (4), etching the
10 exposed portions of the third masking material and then etching the exposed portions of the substrate.
11. The method of claim 7, wherein step (4) comprises:
 applying a layer of a second masking material onto the exposed portions
15 of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials.
12. The method of claim 7, wherein step (5) comprises patterning a fraction
 of the thickness of the layers of the second and third masking materials a
20 plurality of times.
13. The method of claim 9 further including prior to step (4), patterning the layer of the third masking material.
14. The method of claim 13, wherein step (4) comprises applying a layer of a
25 second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials.
15. The method of claim 13, wherein step (5) comprises patterning a fraction
30 of the layers of the second and third masking materials a plurality of times.
16. The method of claim 7, further including prior to step (4), etching the exposed portions of the substrate.

17. The method of claim 16, wherein step (4) comprises applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and third masking materials.

5

18. The method of claim 16, wherein step (5) comprises patterning a fraction of the layers of the second and third masking materials a plurality of times.

19. A method of fabricating a three-dimensional structure, comprising:

10

(1) providing a substrate;

(2) applying a layer of a first masking material onto the substrate;

(3) patterning the layer of the first masking material;

(4) applying a layer of a second masking material onto the portions of the substrate not covered by the patterned layer of the first masking material, the layer of the second masking material is at least as thick as the layer of the first masking material;

15

(5) patterning a fraction of the thickness of the layer of the second masking material a plurality of times;

(6) applying a layer of a third masking material onto the substrate;

20

(7) patterning the layer of the third masking material;

(8) etching the layer of the third masking material;

(9) etching the exposed portions of the substrate;

(10) etching a fraction of the thickness of the exposed portions of the layer of the second masking material;

25

(11) etching the exposed portions of the substrate; and

(12) repeat steps (10) and (11) a plurality of times.

20. The method of claim 19, further including prior to step (4), etching the exposed portions of the substrate.

30

21. The method of claim 20, wherein the step (2) comprises applying a layer of a fourth masking material onto the substrate, and applying the layer of the first masking material onto the layer of the fourth masking material.

22. The method of claim 20, wherein the exposed portions of the substrate are thin etched.

5 23. The method of claim 19, wherein step (2) comprises:
applying a layer of a fourth masking material onto the substrate; and
applying the layer of the first masking material onto the layer of the fourth
masking material.

10 24. The method of claim 23, wherein step (4) comprises applying a layer of a
second masking material onto the exposed portions of the substrate, the layer of
the second masking material is at least as thick as the combined thickness of the
layers of the first and fourth masking materials.

15 25. The method of claim 23, wherein step (5) comprises patterning the a
fraction of the thickness of the layers of the second and fourth masking materials
a plurality of times.

20 26. The method of claim 23, further including prior to step (4), patterning the
layer of the fourth masking material.

25 27. The method of claim 26, wherein step (4) comprises applying a layer of a
second masking material onto the exposed portions of the substrate, the layer of
the second masking material is at least as thick as the combined thickness of the
layers of the first and fourth masking materials.

28. The method of claim 27, wherein applying the layer of the second
masking material includes local oxidation of the substrate.

30 29. The method of claim 26, wherein step (5) comprises patterning a fraction
of the thickness of the layers of the second and fourth masking materials a
plurality of times.

30. The method of claim 26, wherein the first masking material comprises
silicon nitride;

wherein the second masking material comprises silicon dioxide; wherein the third masking material comprises a photoresist material; and wherein the fourth masking material comprises silicon dioxide.

5 31. The method of claim 23, further including prior to step (4), etching the exposed portions of the substrate.

10 32. The method of claim 31, wherein step (4) comprises applying a layer of a second masking material onto the exposed portions of the substrate, the layer of the second masking material is at least as thick as the combined thickness of the layers of the first and fourth masking materials.

15 33. The method of claim 31, wherein step (5) comprises patterning a fraction of the thickness of the layers of the second and fourth masking materials a plurality of times.

34. The method of claim 23, wherein the first masking material comprises silicon nitride;

20 wherein the second masking material comprises silicon dioxide; wherein the third masking material comprises a photoresist material; and wherein the fourth masking material comprises silicon dioxide.

25 35. The method of claim 23, further including between steps (7) and (8), etching the exposed portions of the substrate.

36. The method of claim 23, further including between steps (7) and (8), performing the following:

30 etching the exposed portions of the substrate; and
 etching the exposed portions of the layer of the second masking material.

37. The method of claim 23, further including between steps (7) and (8), performing the following:

 etching the exposed portions of the substrate a plurality of times.

38. The method of claim 23, further including between steps (7) and (8), performing the following:
- etching the exposed portions of the substrate;
 - etching the exposed portions of the layer of the second masking material;
 - 5 and
 - etching the exposed portions of the substrate.
39. The method of claim 23, further including between steps (7) and (8), performing the following:
- 10 etching the exposed portions of the layer of the second masking material.
40. The method of claim 23, further including between steps (7) and (8), performing the following:
- 15 etching the exposed portions of the layer of the second masking material;
 - and
 - etching the exposed portions of the substrate.
41. The method of claim 19, wherein the first masking material comprises silicon nitride; wherein the second masking material comprises silicon dioxide;
- 20 and wherein the third masking material comprises a photoresist material.






FIG. 1
(PRIOR ART)

**FIG. 2**

**FIG. 3**




FIG. 4




FIG. 5







FIG. 6

6/96**FIG. 6A****FIG. 6B****FIG. 6C**




FIG. 6D




FIG. 7











FIG. 8


9/96**FIG. 9**

10/96**FIG. 10**

11/96**FIG. 11****FIG. 12**

12/96**FIG. 13**

13/96**FIG. 14****FIG. 15**

15/96**FIG. 17**




FIG. 18

17/96




FIG. 19

18/96










FIG. 20


19/96**FIG. 21A**



20/96**FIG. 21B**



21/96**FIG. 22****FIG. 23**

22/96**FIG. 23a**



23/96**FIG. 23b**



24/96**FIG. 24**



25/96**26****26****FIG. 25****FIG. 26**



26/96**FIG. 27****FIG. 28**

SUBSTITUTE SHEET (RULE 26)


27/96**FIG. 29a****FIG. 29b**




28/96**FIG. 30a****FIG. 30b**




29/96**FIG. 30c****FIG. 30d**




30/96**FIG. 31****FIG. 32**




SUBSTITUTE SHEET (RULE 26)




31/96**FIG. 33**




32/96**FIG. 34****FIG. 35a****FIG. 35b**




33/96**FIG. 36****FIG. 37****FIG. 38**


34/96**FIG. 39****FIG. 39a****FIG. 39b**





35/96**FIG. 39c****FIG. 40****FIG. 41**








36/96**FIG. 42****FIG. 42a****FIG. 42b**





37/96**FIG. 42c****FIG. 43****FIG. 43a**





38/96**FIG. 43b****FIG. 43c****FIG. 43d**













39/96**FIG. 44**


40/96**FIG. 45a****FIG. 45e****FIG. 45h****FIG. 45b****FIG. 45f****FIG. 45i****FIG. 45c****FIG. 45g****FIG. 45d**





41/96**FIG. 46a****FIG. 46e****FIG. 46h****FIG. 46b****FIG. 46f****FIG. 46i****FIG. 46c****FIG. 46g****FIG. 46j****FIG. 46d**





42/96**FIG. 47a****FIG. 47e****FIG. 47h****FIG. 47b****FIG. 47f****FIG. 47i****FIG. 47c****FIG. 47g****FIG. 47j****FIG. 47d**





43/96**FIG. 48a****FIG. 48e****FIG. 48i****FIG. 48b****FIG. 48f****FIG. 48j****FIG. 48c****FIG. 48g****FIG. 48k****FIG. 48d****FIG. 48h**





44/96**FIG. 49a****FIG. 49e****FIG. 49i****FIG. 49b****FIG. 49f****FIG. 49j****FIG. 49c****FIG. 49g****FIG. 49k****FIG. 49d****FIG. 49h****FIG. 49l**















45/96**FIG. 50**


46/96**FIG. 51a****FIG. 51e****FIG. 51i****FIG. 51b****FIG. 51f****FIG. 51j****FIG. 51c****FIG. 51g****FIG. 51k****FIG. 51d****FIG. 51h**


47/96**FIG. 52a****FIG. 52e****FIG. 52i****FIG. 52b****FIG. 52f****FIG. 52j****FIG. 52c****FIG. 52g****FIG. 52k****FIG. 52d****FIG. 52h****FIG. 52l**





48/96**FIG. 53a****FIG. 53e****FIG. 53i****FIG. 53b****FIG. 53f****FIG. 53j****FIG. 53c****FIG. 53g****FIG. 53k****FIG. 53d****FIG. 53h****FIG. 53l**










49/96**FIG. 54a****FIG. 54e****FIG. 54i****FIG. 54b****FIG. 54f****FIG. 54j****FIG. 54c****FIG. 54g****FIG. 54k****FIG. 54d****FIG. 54h****FIG. 54l****FIG. 54m**


50/96**FIG. 55a****FIG. 55f****FIG. 55k****FIG. 55b****FIG. 55g****FIG. 55l****FIG. 55c****FIG. 55h****FIG. 55m****FIG. 55d****FIG. 55i****FIG. 55n****FIG. 55e****FIG. 55j**










51/96**FIG. 56a**








52/96**FIG. 56b**









53/96


54/96


55/96






56/96










57/96






58/96






59/96









60/96


61/96


62/96






63/96






64/96






65/96**FIG. 70a****FIG. 70f****FIG. 70k****FIG. 70b****FIG. 70g****FIG. 70l****FIG. 70c****FIG. 70h****FIG. 70m****FIG. 70d****FIG. 70i****FIG. 70e****FIG. 70j**






66/96


67/96















68/96











69/96






70/96


71/96


72/96











73/96**FIG. 78a****FIG. 78f****FIG. 78k****FIG. 78b****FIG. 78g****FIG. 78l****FIG. 78c****FIG. 78h****FIG. 78m****FIG. 78d****FIG. 78i****FIG. 78n****FIG. 78e****FIG. 78j**


74/96**FIG. 79a****FIG. 79f****FIG. 79k****FIG. 79b****FIG. 79g****FIG. 79l****FIG. 79c****FIG. 79h****FIG. 79m****FIG. 79d****FIG. 79i****FIG. 79n****FIG. 79e****FIG. 79j****FIG. 79o**











75/96


76/96


77/96

















78/96
















79/96


80/96
















81/96

82/96

83/96**FIG. 88a****FIG. 88g****FIG. 88i****FIG. 88b****FIG. 88h****FIG. 88m****FIG. 88c****FIG. 88j****FIG. 88n****FIG. 88d****FIG. 88k****FIG. 88o****FIG. 88e****FIG. 88l****FIG. 88p****FIG. 88f****FIG. 88q**

84/96**FIG. 89a****FIG. 89g****FIG. 89i****FIG. 89b****FIG. 89h****FIG. 89m****FIG. 89c****FIG. 89j****FIG. 89n****FIG. 89d****FIG. 89k****FIG. 89o****FIG. 89e****FIG. 89f****FIG. 89l**

85/96

86/96**FIG. 91a****FIG. 91b****FIG. 91c****FIG. 91d****FIG. 91e****FIG. 91f****FIG. 91g****FIG. 91h****FIG. 91i****FIG. 91j****FIG. 91k****FIG. 91l****FIG. 91m****FIG. 91n****FIG. 91o**

87/96








FIG. 92a





88/96**FIG. 92b**








**FIG. 93b**





91/96**FIG. 94**





SUBSTITUTE SHEET (RULE 26)

92/96**FIG. 95a****FIG. 95b****FIG. 95c****FIG. 95d**

93/96**FIG. 95e****FIG. 95f****FIG. 95g****FIG. 95h**

94/96**FIG. 96**

95/96**FIG. 97a****FIG. 97b****FIG. 97c****FIG. 97d**

96/96**FIG. 97E****FIG. 97F****FIG. 97G****FIG. 97H**